

Description

This invention relates to modified polymers having useful properties as additives for lubricating oils.

The newer engines place increased demands on the lubricants to be employed. In the past a number of different additives has been added to lubricating oils to improve properties such as viscosity index and dispersancy. One such additive added to lubricating oils to improve viscosity index (VI) is a two-block copolymer having the general configuration A-B where A is styrene and B is hydrogenated isoprene, e.g. as described in U.S. Patents Nos. 3,763,044 and 3,772,196. A VI improver having greatly improved mechanical shear stability is the selectively hydrogenated star-shaped polymer disclosed in U.K. Patent Specification 1,575,507. Employing a single additive that improves a number of lubricant properties can achieve significant reductions in cost, and also circumvent the compatibility problems that can arise between the various additives and/or base oil. However, in attempting to improve more than a single lubricant property, care must be taken in not causing the deterioration of other properties. For example, the use of an oxidation step to attach polar groups to the polymer backbone in U.S. Patent No. 3,864,268 leads to reduced lubricant stability by introducing sites for oxidative attack.

FR-A-2 390 496 discloses an ashless, oil-soluble additive having both dispersant and viscosity-index (VI) improving properties prepared by the process comprising:

(a) reacting a selectively hydrogenated star-shaped polymer with an alpha-beta unsaturated carboxylic acid, anhydride or ester wherein said star-shaped polymer comprises a poly (polyalkenyl coupling agent) nucleus and at least 4 polymeric arms linked to said nucleus wherein said polymeric arms are selected from the group consisting of:

- (i) hydrogenated homopolymers and hydrogenated copolymers of conjugated dienes;
- (ii) hydrogenated copolymers of conjugated dienes and monoalkenyl arenes; and
- (iii) mixtures thereof;

and wherein at least about 80% of the aliphatic unsaturation of the star-shaped polymer has been reduced by hydrogenation while less than 20% of the aromatic unsaturation has been reduced; and

(b) reacting the product of step (a) with a C₁ to C₁₈ amine containing 1 to 8 nitrogen atoms and/or with an alkane polyol having at least two hydroxy groups.

GB-A-2 144 431 discloses a process for the preparation of an oil-soluble, star-shaped product having viscosity index-improving and dispersant properties, comprising modifying a hydrogenated star-shaped polymer comprising a nucleus and polymeric arms linked to said nucleus, wherein said arms are selected from the group consisting of:

- (i) hydrogenated homopolymers and hydrogenated copolymers of conjugated dienes;
- (ii) hydrogenated copolymers of conjugated dienes and monoalkenyl arenes; and
- (iii) mixtures thereof;

and wherein at least about 80% of the aliphatic unsaturation of the star-shaped polymer has been reduced by hydrogenation while less than 20% of the aromatic unsaturation has been reduced, characterised in that the hydrogenated polymer is metallated with an organolithium compound in the presence of a metallation promoter, and subsequently reacted with

- (a) a vinyl pyridine, or
- (b) a carbonyl group containing organic compound, or
- (a) followed by (b).

According to the present invention, ashless, oil-soluble additives having both dispersant and viscosity-index (VI) improving properties are produced by

1) reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester thereof (active derivative thereof), preferably at a temperature of between about 100°C and about 300°C for between about 1 hour and about 24 hours, with a selectively hydrogenated star-shaped polymer comprising a polyvinyl aromatic nucleus and at least 4 polymeric arms e.g. 4-25 arms, which arms each can have a number average molecular weight of e.g. 5,000 to 150,000 and which are linked to said nucleus wherein said polymeric arms are selected from the group consisting of:

- (i) hydrogenated homopolymers and hydrogenated copolymers of conjugated dienes;
- (ii) hydrogenated copolymers of conjugated dienes and monoalkenyl arenes; and
- (iii) mixtures thereof;

and wherein at least 80%, preferably 90 to 98%, of the aliphatic unsaturation of the star-shaped polymer has been reduced by hydrogenation while less than 20% of the aromatic unsaturation has been reduced; and

2) reacting the activated hydrogenated star polymer thus formed with:

- a) a long chain alkane-substituted carboxylic acid, anhydride or ester thereof (active derivative thereof), obtainable by reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester with a polyolefin derived from olefin monomers having from 2 to 16 carbon atoms, and
- b) with a C₁ to C₁₈ amine containing 1 to 8 nitrogen atoms and/or with an alkane polyol having at least two hydroxy groups; or with
- c) the preformed product of reactants a) and b).

The star polymers employed in making the present dispersant VI improvers are generally produced by the process comprising the following reaction steps:

- (i) polymerizing one or more conjugated dienes in solution in the presence of an ionic initiator to form a living polymer;
- (ii) reacting the living polymer with a polyvinyl aromatic compound, preferably divinyl benzene, to form a star-shaped polymer; and
- (iii) hydrogenating the star-shaped polymer to form a hydrogenated star-shaped polymer.

This preparation is described in detail in UK Patent Specification 1575507.

The living polymers produced in reaction step (i) of the present process are the precursors of the hydrogenated polymer chains which extend outwardly from the polyvinyl aromatic nucleus. Preferably each polymeric arm is a hydrogenated polyisoprene homopolymer.

The molecular weights of the star-shaped polymer to be hydrogenated in reaction step (iii) may vary between relatively wide limits. It is possible to produce star polymers having peak molecular weights between about 25,000 and about 1,250,000. Preferred molecular weights are 100,000 to 500,000. These peak molecular weights are determined by gel permeation chromatography (GPC) on a polystyrene scale.

In step (iii), the star-shaped polymers are hydrogenated by any suitable technique. Suitably at least 80%, preferably about 90 to about 98%, of the original olefinic unsaturation is hydrogenated. The amount of aromatic unsaturation which is hydrogenated, if any, will depend on the hydrogenation conditions used. However, preferably less than 20%, more preferably less than 5%, of such aromatic unsaturation is hydrogenated.

The molecular weights of the hydrogenated star-shaped polymers correspond to those of the unhydrogenated star-shaped polymers.

The hydrogenation can be carried out as described in UK Patent Specification 1,575,507, the preferred process being the selective hydrogenation process described in U.S. Patent 3,595,942. In that process hydrogenation is conducted, preferably in the same solvent in which the polymer was prepared, utilizing a catalyst comprising the reaction product of an aluminium alkyl and a nickel or cobalt carboxylate or alkoxide. A favoured catalyst is the reaction product formed from triethyl aluminium and nickel octoate.

The hydrogenated star-shaped polymer is then recovered in solid form from the solvent in which it is hydrogenated by any convenient technique such as by evaporation of the solvent. Alternatively, an oil, e.g. a lubricating oil, may be added to the solution and the solvent stripped off from the mixture so formed to produce concentrates. Easily handleable concentrates are produced even when the amount of hydrogenated star-shaped polymer therein exceeds 10%w. Suitable concentrates contain from 10 to 25%w of the hydrogenated star-shaped polymer.

The selectively hydrogenated star polymers as prepared above do not in themselves have adequate dispersancy characteristics and are modified as explained below.

- 1) The star polymer is first activated by reaction with an alpha-beta unsaturated carboxylic acid or active derivative thereof. Suitable unsaturated acids and derivatives include maleic acid, maleic anhydride, itaconic acid, dimethyl itaconate, acrylic acid, ethyl acrylate, methacrylic acid, methyl methacrylate, oleic acid, linoleic acid, etc., with maleic anhydride being especially preferred.

The unsaturated carboxylic compound and the hydrogenated star polymer are suitably reacted together at a temperature of between 100°C and 300°C, preferably between 130°C and 250°C. The contacting time may be between 1 hour and 24 hours, preferably between 4 hours and 8 hours. The carboxylic compound reacts with the residual olefinic bonds available on the diene portion of the star polymer, and/or with the radicals initiated on the polymer chain; temperatures between 100° and 150°C being suitable in the latter case.

Various solvents may be employed in the carboxylic acid derivative addition step 1) including generally olefin-free petroleum hydrocarbons, aromatics and halogenated hydrocarbons. A preferred solvent is a lubricating oil basestock. Preferably a concentration in the range of about 1% to about 20% by weight of the copolymer in solvent may conveniently be used for this conversion.

Generally the amount of unsaturated carboxylic compound is an excess over that stoichiometrically necessary to react with all the residual double bonds remaining in the diene portion of the selectively hydrogenated star polymer. Preferably, at least one mole of carboxylic compound is used for each

olefinic unsaturation present in the selectively hydrogenated star polymer, with equivalent ratios of carboxylic compound to olefinic double bonds of between 1:1 and 2:1 being particularly suitable. However, less than stoichiometric amounts of carboxylic compound may also be used.

The above reaction may be carried out with or without the use of catalyst or radical initiators such as tert. butyl hydroperoxide or tert. butyl perbenzoate. Any excess carboxylic compound is typically removed either by vacuum distillation or through the use of a stripping gas stream.

2) The activated hydrogenated star polymer resulting from the above reaction with unsaturated carboxylic acid is then modified by reaction with: a) a long-chain alkane-substituted carboxylic acid, anhydride or ester thereof, preferably succinic acid, anhydride or ester, and b) with a C₁ to C₁₈ amine containing 1 to 8 nitrogen atoms and/or with an alkane polyol having at least two hydroxy groups; or with c) the preformed product of reactants a) and b). Reaction of the activated star polymer with the alkane carboxylic acid (reactant a)), alkylamine or alkane polyol (reactant b)), or the pre-formed reaction product of a) and b), is suitably effected by heating these reactants together, suitably at a temperature between 100°C and 200°C, preferably between 140°C and 170°C. The reaction may be carried out in the presence of a solvent, conveniently the same solvent as that used in the star polymer activating step 1), a luboil basestock being particularly convenient for both process steps. It is desirable to operate under an inert atmosphere, suitably nitrogen.

The long-chain alkane-substituted carboxylic acid/derivative is obtainable by reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester thereof with a polyolefin, derived from a homopolymer or copolymer of one or more olefin monomers having 2 to 16 preferably from 2 to 6, carbon atoms. The copolymers include random, block and tapered copolymers. Suitable monomers include ethene, propene, butenes, isobutene, pentenes, octenes, and also diolefines such as butadiene and isoprene. If a diene is used as monomer the resulting polymer is preferably hydrogenated to saturate at least 90%, more preferably substantially all unsaturated bonds. It is especially preferred to use a polyolefin substituent derived from polyisobutylene.

The number average molecular weight of the polyolefin substituent is suitably not greater than 5000, since molecular weights above 5000 can impair the dispersancy properties of the final products, especially in crankcase lubricants. To reduce the risk of problems the number average molecular weight is preferably from 700 to 3000. The number average molecular weight (M_n) can easily be determined by vapour pressure osmometry or by gel permeation chromatography with calibration of the polymer, as will be appreciated by those skilled in the art. The weight average molecular weight (M_w) can also be determined by gel permeation chromatography. The quotient M_w/M_n, which is a measure indicating the width of molecular weight distribution, suitably has a value from 1.5 to 4.0.

The unsaturated acid reacting with the polyolefin may be any of those listed earlier as suitable for activating the hydrogenated star polymer, maleic acid or anhydride being particularly preferred. In the case of maleic acid/anhydride, the addition of the polyolefin to the unsaturated bonding yields a polyolefin-substituted succinic acid derivative.

The average number of carboxylic acid groups per polyolefin moiety is normally between 0.5 and 1.5. This means that some of the polyolefin moieties are connected to more than one succinic group. Preferably, the average number of succinic groups per polyolefin moiety is between 0.9 and 1.1.

A preferred embodiment of the process of the invention is given in claim 6.

The polyolefin-substituted carboxylic acids may be prepared according to established procedures from an alkene of required molecular weight and an appropriate amount of the unsaturated carboxylic acid or active derivative. Thus, the polyolefin, e.g. polyisobutylene, may be mixed with maleic anhydride and chlorine passed through the mixture, yielding hydrochloric acid and polyolefin-substituted succinic anhydride, as described in e.g. GB-A-949,981. Another method for the preparation of polyolefin substituted succinic anhydride is described in US-A-3,172,892, according to which a halogenated, in particular chlorinated, polyolefin is reacted with maleic anhydride.

From e.g. NL-A-74 12 057 it is known to prepare hydrocarbon-substituted succinic anhydride by thermally reacting a polyolefin with maleic anhydride, a procedure which may be combined with that of GB-A-949,981, as is illustrated in GB-A-1,440,219 and GB-A-1,543,627. The products prepared in this way include compounds in which the polyolefin chain is connected to one or both of the alpha carbon atoms of the succinic group.

The amine or polyol modifier (reactant b)) confers dispersant properties in the final modified star polymer combined VI improver/dispersant.

The C₁ to C₁₈ amines employed in the instant invention can be branched or unbranched, saturated, aliphatic, primary or secondary amines, containing 1 to 8 nitrogens, preferably mono- or diamines, such as ethylamine, butylamine, sec. butylamine, diethylamine, 3-dimethylamino propylamine etc., but including

higher polyamines such as alkylene polyamines, wherein pairs of nitrogen atoms are joined by alkylene groups of 2 to 4 carbon atoms. Thus, polyamines of the formula:



are included where n is 2 to 4 and m is 0 to 6. Examples of such polyamines include tetraethylene pentamine, tripropylene tetramine, triethylene tetramine, diethylene triamine, N-aminoalkyl piperazines, e.g., N-(2-aminoethyl) piperazine, N,N'-di(2-aminoethyl) piperazine, etc. Preferred are diethylene triamine, triethylene tetramine or tetraethylene pentamine, as well as corresponding commercial mixtures such as "Polyamine H", and "Polyamine 500".

The alkane polyols useful in making the esters are alkane polyols having at least two and preferably at least four hydroxy groups such as the trihydroxyalkanes, e.g. ethylene glycol, propylene glycol, polymethylene glycols, trihydroxybutanes, pentanes, hexanes, heptanes, octanes, nonanes, dodecanes, etc., as well as tetrahydroxy alkanes, pentahydroxy alkanes, hexahydroxy alkanes, as well as the sugar alcohols such as erythritol, pentaerythritol, tetritols, pentitols, hexitols, mannitol, sorbitol, glucose and the like. Particularly preferred alcohols are pentaerythritol and mannitol. Especially preferred is pentaerythritol.

The molar ratio of amine or polyol to the sum of the carboxylic compounds is typically between about 0.1:1 and about 2:1, preferably between about 0.25:1 and about 2:1, most preferably about 0.5:1. The conditions during imide formation or esterification are typically about 150 °C to 250 °C for between about 1 hour and 20 hours.

In both reaction steps a) and b) it is much preferred that the reactions take place in the absence of oxygen. A nitrogen blanket is often used to accomplish this result. The reason for performing the reaction in the absence of oxygen is that the resulting additive may be more oxidatively unstable if any oxygen is present during the formation of the additive.

If excess amine or polyol is employed, then it may be desirable to remove the excess. One means of doing this is to first exchange the tri-chlorobenzene solvent for a lube base stock by vacuum distillation, and then add a volume of heptane equal to the volume of oil solution. Then an equal volume of methanol is added and mixed. Two separate layers are therein formed upon settling; one layer comprising predominantly wash solvent and the unreacted amine or polyol, and a second layer comprising predominantly oil, heptane, and the additive product. After separating the wash layer, the volatiles present in the product layer can then be removed by a distillation technique. Alternatively, the excess amine or polyol may be removed under a vacuum or with a stripping gas stream.

The dispersant VI improvers of the present invention possess a useful combination of viscosity improving properties with oxidative stability, mechanical shear stability, and dispersancy. In particular, lubricating oils containing these VI improver/ dispersants possess a good combination of thickening efficiency and shear stability at high temperature and also good low temperature viscosity characteristics. A lower amount of the present VI improver/dispersants is normally required in order to obtain the required thickening performance, as compared with the prior art VI improvers. Further, the VI improver/dispersants also possess a superior combination of oxidative shear stability, permanent shear stability, and "temporary shear loss". Temporary shear loss refers to the temporary viscosity loss at high shear stress conditions resulting from the non-Newtonian character of the polymeric VI improvers. Still further, the dispersing power of the instant polymeric additive is excellent.

The reaction product of this invention can be incorporated in lubricating oil compositions, e.g. automotive crankcase oils, in concentrations e.g. within the range of about 0.1 to about 15, preferably about 0.1 to 3, weight percent based on the weight of the total compositions. The lubricating oils to which the additives of the invention can be added include not only mineral lubricating oils, but synthetic oils also. Synthetic hydrocarbon lubricating oils may also be employed, as well as non-hydrocarbon synthetic oils including dibasic acid esters such as di-2-ethyl hexyl sebacate, carbonate esters, phosphate esters, halogenated hydrocarbons, polysilicones, polyglycols, glycol esters such as C₁₃ oxo acid diesters of tetraethylene glycol, etc. When used in gasoline or fuel oil, e.g. diesel fuel, No. 2 fuel oil, etc., then usually about 0.001 to 0.5 weight percent, based on the weight of the total composition of the reaction product will be used. Concentrations comprising a minor proportion, e.g. 15 to 45 weight percent, of said reaction product in a major amount of hydrocarbon diluent, e.g. 85 to 55 weight percent mineral lubricating oil, with or without other additives present, can also be prepared for ease of handling.

In the above compositions or concentrates, other conventional additives may also be present, including dyes, pour point depressants, antiwear agents, e.g. tricresyl phosphate, zinc dialkyl dithiophosphates of 3 to 8 carbon atoms, antioxidants such as phenyl-alpha-naphthylamine, tert-octylphenol sulphide, bis-phenols such as 4,4'-methylene bis(3,6-di-tert-butylphenol), viscosity index improvers such as the ethylene-higher

olefin copolymer, polymethylacrylates, polyisobutylene, alkyl fumaratevinyl acetate copolymers, and the like as well as other ashless dispersants or detergents such as overbased sulphonates.

The invention is further illustrated by means of the following Examples, which are given for the purpose of illustration alone, and is not meant to limit the invention to the particular reactants and amounts disclosed.

Example 1

I. A concentrate of "SHELLVIS 200" (trade mark) star polymer in "XHVI-6" oil (13.8% m/m) was reacted under stirring with maleic anhydride (MALA) (2% m/m on star polymer) at 133 °C during 18 hours in the presence of tert. butylperbenzoate in a N₂-atmosphere (50 ppm O₂). The radical initiator is dosed (by pumping) in a 41 minute period (as a 50% m/m solution in oil).

	GRAMS	% m/m
Intake: "SHELLVIS 200"	340.94	13.66
MALA	6.82	0.27 (= 2% m/m on starpolymer)
"Trigonox C" (trade mark) (=75% tert. butylperbenzoate)	9.21	0.37 (= 2% m/m tert. tert. butylperbenzoate on starpolymer)
"XHVI-oil"	2138.87	85.70
Total	2495.84	100.0

Then the reaction mixture was stripped at 110 °C under high vacuum (0.06 mm Hg) to remove residual non-reacted maleic anhydride.

The maleic anhydride content of the thus obtained VI-improver concentrate was determined by titration with 0.1 mol/l sodium methoxide solution in methanol, using phenolphthalein as the indicator. The MALA contents of the reaction product before high vacuum stripping was: 0.022 mmol/g product, whilst after stripping 0.019 mmol/g. The theoretical MALA-contents (assuming 100% grafting) is 0.028 mmol/g. Therefore the efficiency of MALA grafting is maximally some 70%.

II. 1112.7 gramms of the above-described stripped reaction product I and 21.7 gramms of PIBMALA (polyisobutylene/maleic anhydride adduct) (1.95 meg/g Acid Number) were heated to 150 °C under stirring in a N₂ atmosphere. 2.18 gramms (2.29 ml) of diethylenetriamine (DETA) was dosed by continuous pumping in 57 minutes. The temperature was raised to 175 °C and the reaction mixture was kept at that temperature for 4 hours. During the last hour N₂ was led through the reaction mixture to remove the last traces of H₂O and other residual volatiles.

IIA. (Comparison Example). 1280.1 gramms of the above-described stripped reaction product I, 224 gramms of xylene (to reduce the viscosity) and 12.40g dimethylaminopropylamine (DAP) (a 5-fold excess based on grafted MALA) were reacted for 1 hour at 80 °C under stirring in a N₂ atmosphere. Then the xylene was stripped off at 130 °C at 0.03mm Hg after which the reaction product was kept for 3 hours at 170 °C in a N₂ atmosphere under stirring. The last hour N₂ was led through the reaction mixture to remove the last traces of H₂O and other residual volatiles.

III. At 100°C 101.48g of PIBMALA in xylene (as a 52.2% solution) was added over 3 hours to 20.38g of diethylenetriamine (DETA) in a N₂ atmosphere. After cooling to room temperature the xylene was distilled off in vacuum and then the unconverted DETA was removed by vacuum distillation at 170°. The product is a mixture of PIBMALA-DETA and (PIBMALA)₂DETA which can be reacted with Product I above to form a PIBMALADETA grafted star polymer.

IV. Various other similarly grafted star polymers were prepared generally according to the procedure outlined in Examples I and II, including several outside the present invention (viz. test products N, S and V) for comparative purposes. The salient details of the experiments are given in Table I.

TABLE I

Test Product	Intake first step				Dosing		MALA	Intake second step				Dosing		Star		Product N theoretical %w on %w on star conc.	
	XSA 006A3 g	MALA		Trigonox C g	g	star	TrigC mmol	time min.	SV200/MALA g	mmol	PIB/MALA	type	amine g	mmol	time min.		%w
		g	star														
-Q	3360.2	9.27	2	12.52	2.7	56	0.016	3241.5	51.96	53.2	DETA	5.34	51.84	56	13.44	0.49 0.066	
-M	2470.6	6.82	2	9.21	2.7	41	0.019	1112.7	21.14	21.7	DETA	2.18	21.17	57	13.4	0.57 0.078	
-N	2470.6	6.82	2	9.21	2.7	41	0.019	1280.1	24.32	-	DAP	12.40	121.6	-	13.6	0.39 0.053	
-T	3701.0	10.21	2	13.79	2.7	41	0.016	1843.5	29.7	30.5	TEPA	5.62	29.7	59	13.2	0.83 0.11	
-U	3701.0	10.21	2	13.79	2.7	41	0.016	1796.2	28.7	29.5	TETA	4.20	28.8	59	13.4	0.66 0.088	
-R	3585.1	4.95	1	13.36	2.7	40	0.01	1856.7	18.6	19.0	DETA	1.91	18.54	54	13.5	0.31 0.041	
-S	3585.1	4.95	1	13.36	2.7	40	0.01	1708.6	17.09	-	DAP	8.7	85.3	-	13.7	0.20 0.08	
-V	3585.2	19.79	4	13.36	2.7	40	0.04	1775.1	71.0	-	DAP	36.2	355	-	13.6	0.82 0.112	

1st step Reactiontime and temperature 18 hrs 133-135°C

2nd step Amine addition at 150°C 4 hrs 195°C

Reaction with DAP Star/MALA concentrate diluted with xylene.

Addition of 5 equivalents of DAP 1 hr at 80°C - Removal of xylene at 130°C

3 hrs at 170°C

V. Certain of these VI improvers, and also existing commercially available VI improvers ("SHELLVIS" 250, ECA 8358 and TLA 856), were blended (as a concentrate in mineral oil) with a SAE 10w/40 lubeoil containing some 8% w/w of an additive package comprising an overbased salicylate detergent, a succinimide ashless dispersant, a zinc-based anti-wear additive and a polymethacrylate pour point depressant. The resulting oil was then evaluated according to the sequence VE (as described in

"Sequence VE test procedure", 7th draft dated 19th May, 1988; ASTM Monitoring Center, 4400 5th Avenue Pittsburgh USA). The results of these evaluations are set out in Table II, from which it clearly emerges that Product M (present invention) provides the best performance for each of the parameters evaluated.

TABLE II

	VI Improver (% w/w concentrate)	Rocker Arm Sludge (RAC)	VE Test Parameter Av. Engine Sludge (AES)	Av. Cam Lobe Wear (μm)
SG Pass Limit	-	≥ 7.5	≥ 9	≤ 125
"Shellvis" 250	8.4	2.2	3.5	198
ECA 8358	11.0	7.9	8.9	63
TIA 656	10.4	6.7	6.6	159
Product N. (2% MALA/DAP)	8.8	7.2	7.4	126
Product M. (2% MALA/DETA/ PIBMAIA)	6.0	8.0	9.2	18

VI. The VI improver Q from Table I was subjected to a carbon black dispersancy test, together with the commercially available VI improvers ECA 8358 and TLA 656.

In the carbon black dispersancy test 3%w of carbon black is added to a lubricating oil formulation and the increase in kinematic viscosity at 60 °C is determined, using an Ubbelohde viscometer. A large increase denotes a poor performance. It appears that the outcome of the relatively simple test correlates excellently with the ranking in dispersancy behaviour in diesel engine crank case lubricating oils. The test is described in British Rail publication BR 669:1984.

The formulation used was a SAE 10W40 Middle East lubricating oil which contained a commercial package of a zinc dialkyldithiophosphate, overbased calcium alkyl salicylate and a polymethacrylate pour point depressant. To samples of this formulation were added quantities of the VI improvers in amounts to achieve formulated oils which were equiviscous at 100 °C. The resulting oils were subjected to the carbon black dispersancy test (using 3%w "Cabot Carbon Elftex 460" as the carbon black). Results are given in Table III, from which it can be seen that VI improver Q gave the best performance by giving very much the lowest increase in kinematic viscosity at 60 °C.

TABLE III

VI improver	Quantity of VI Improver (%w/w concentrate)	Increase in Kinematic viscosity at 60 °C (%)
Product Q	7.0	2.4
ECA 8358	14.6	15.4
TLA 656	11.5	15.7

Claims

Claims for the following Contracting States: BE, DE, FR, GB, IT, NL

1. Process for preparing a dispersant/VI improver which comprises

1) reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester thereof with a selectively hydrogenated star-shaped polymer comprising a polyvinylaromatic nucleus and at least 4 polymeric arms linked to said nucleus wherein said polymeric arms are selected from the group consisting of:

(i) hydrogenated homopolymers and hydrogenated copolymers of conjugated dienes;

(ii) hydrogenated copolymers of conjugated dienes and monoalkenyl arenes; and

(iii) mixtures thereof; and wherein at least 80% of the aliphatic unsaturation of the star-shaped polymer has been reduced by hydrogenation while less than 20% of the aromatic unsaturation has been reduced;

and

2) reacting the activated star polymer thus formed with:

a) a long chain alkane-substituted carboxylic acid, anhydride or ester thereof, obtainable by reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester with a polyolefin derived from olefin monomers having from 2 to 16 carbon atoms,

and b) a C₁ to C₁₈ amine containing 1 to 8 nitrogen atoms and/or an alkane polyol having at least two hydroxy groups;

or with c) the pre-formed product of reactants a) and b).

2. Process as claimed in claim 1 wherein the number of polymeric arms is between 4 and 25, and the polyvinyl aromatic compound is divinyl benzene.

3. Process according to claim 1 or 2, wherein, in the star polymer, the number average molecular weight of each polymeric arm is between 5,000 and 150,000, and the peak molecular weight of the hydrogenated star-shaped polymer is between 25,000 and 1,250,000.

4. Process as claimed in claim 1, 2 or 3, wherein said star-shaped polymer and said carboxylic acid, anhydride or ester are reacted in a ratio of moles of carboxylic acid, anhydride or ester to olefinic double bonds remaining in the selectively hydrogenated star-shaped polymer of between 1:1 and 2:1.



VI. The VI improver Q from Table I was subjected to a carbon black dispersancy test, together with the commercially available VI improvers ECA 8358 and TLA 656.

In the carbon black dispersancy test 3%w of carbon black is added to a lubricating oil formulation and the increase in kinematic viscosity at 60 °C is determined, using an Ubbelohde viscometer. A large increase denotes a poor performance. It appears that the outcome of the relatively simple test correlates excellently with the ranking in dispersancy behaviour in diesel engine crank case lubricating oils. The test is described in British Rail publication BR 669:1984.

The formulation used was a SAE 10W40 Middle East lubricating oil which contained a commercial package of a zinc dialkyldithiophosphate, overbased calcium alkyl salicylate and a polymethacrylate pour point depressant. To samples of this formulation were added quantities of the VI improvers in amounts to achieve formulated oils which were equiviscous at 100 °C. The resulting oils were subjected to the carbon black dispersancy test (using 3%w "Cabot Carbon Elftex 460" as the carbon black). Results are given in Table III, from which it can be seen that VI improver Q gave the best performance by giving very much the lowest increase in kinematic viscosity at 60 °C.

TABLE III

VI improver	Quantity of VI Improver (%w/w concentrate)	Increase in Kinematic viscosity at 60 °C (%)
Product Q	7.0	2.4
ECA 8358	14.6	15.4
TLA 656	11.5	15.7

Claims

Claims for the following Contracting States: BE, DE, FR, GB, IT, NL

1. Process for preparing a dispersant/VI improver which comprises

1) reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester thereof with a selectively hydrogenated star-shaped polymer comprising a polyvinylaromatic nucleus and at least 4 polymeric arms linked to said nucleus wherein said polymeric arms are selected from the group consisting of:

- (i) hydrogenated homopolymers and hydrogenated copolymers of conjugated dienes;
- (ii) hydrogenated copolymers of conjugated dienes and monoalkenyl arenes; and
- (iii) mixtures thereof; and wherein at least 80% of the aliphatic unsaturation of the star-shaped polymer has been reduced by hydrogenation while less than 20% of the aromatic unsaturation has been reduced;

and

2) reacting the activated star polymer thus formed with:

- a) a long chain alkane-substituted carboxylic acid, anhydride or ester thereof, obtainable by reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester with a polyolefin derived from olefin monomers having from 2 to 16 carbon atoms,
- and b) a C₁ to C₁₈ amine containing 1 to 8 nitrogen atoms and/or an alkane polyol having at least two hydroxy groups;
- or with c) the pre-formed product of reactants a) and b).

2. Process as claimed in claim 1 wherein the number of polymeric arms is between 4 and 25, and the polyvinyl aromatic compound is divinyl benzene.

3. Process according to claim 1 or 2, wherein, in the star polymer, the number average molecular weight of each polymeric arm is between 5,000 and 150,000, and the peak molecular weight of the hydrogenated star-shaped polymer is between 25,000 and 1,250,000.

4. Process as claimed in claim 1, 2 or 3, wherein said star-shaped polymer and said carboxylic acid, anhydride or ester are reacted in a ratio of moles of carboxylic acid, anhydride or ester to olefinic double bonds remaining in the selectively hydrogenated star-shaped polymer of between 1:1 and 2:1.



5. Process as claimed in any one of claims 1-4 wherein the star polymer and carboxylic acid are reacted at a temperature between 130 °C and 250 °C.
6. Process as claimed in any one of the preceding claims wherein the long chain alkane-substituted carboxylic acid (reactant a)) is derived by reacting an alpha, beta unsaturated carboxylic acid or active derivative thereof with polyisobutylene having molecular weight not greater than 5000, quotient Mw/Mn between 1.5 and 4.0 and average number of carboxylic acid groups per polyolefin moiety between 0.5 and 1.5.
7. Process as claimed in claim 6 wherein maleic acid or its anhydride is used as the alpha, beta unsaturated carboxylic acid both in preparing the activated star poly ery (stage 1), and in preparing the polyolefin-substituted carboxylic acid (reactant a)).
8. Process as claimed in any one of the preceding claims, wherein the C₁₋₁₈ amine has the formula:

$$\text{NH}_2(\text{CH}_2)_n\text{--}[\text{NH}(\text{CH}_2)_m]_m\text{--NH}_2$$

where n is 2 to 4 and m is 0 to 6.
9. Process as claimed in claim 8, wherein the amine is diethylene triamine, triethylene tetramine or tetraethylenepentamine.
10. Process as claimed in any one of claims 1-7, wherein the alkane polyol is pentaerythritol.
11. Process as claimed in any one of the preceding claims, wherein the molar ratio of amine or polyol to the sum of the carboxylic compounds is between 0.25:1 and 2:1.
12. An ashless, oil-soluble dispersant/VI improver when prepared by a process as claimed in any one of the preceding claims.
13. A lubricating composition comprising a major amount of a lubricating oil and a minor amount of a dispersant/VI improver as claimed in claim 12.

Claims for the following Contracting State : ES

1. Process for preparing a dispersant/VI improver which comprises
 - 1) reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester thereof with a selectively hydrogenated star-shaped polymer comprising a polyvinylaromatic nucleus and at least 4 polymeric arms linked to said nucleus wherein said polymeric arms are selected from the group consisting of:
 - (i) hydrogenated homopolymers and hydrogenated copolymers of conjugated dienes;
 - (ii) hydrogenated copolymers of conjugated dienes and monoalkenyl arenes; and
 - (iii) mixtures thereof; and wherein at least 80% of the aliphatic unsaturation of the star-shaped polymer has been reduced by hydrogenation while less than 20% of the aromatic unsaturation has been reduced;

and
 - 2) reacting the activated star polymer thus formed with:
 - a) a long chain alkane-substituted carboxylic acid, anhydride or ester thereof, obtainable by reacting an alpha-beta unsaturated carboxylic acid, anhydride or ester with a polyolefin derived from olefin monomers having from 2 to 16 carbon atoms,
 - and b) a C₁ to C₁₈ amine containing 1 to 8 nitrogen atoms and/or an alkane polyol having at least two hydroxy groups;
 - or with c) the pre-formed product of reactants a) and b).
2. Process as claimed in claim 1 wherein the number of polymeric arms is between 4 and 25, and the polyvinyl aromatic compound is divinyl benzene.
3. Process according to claim 1 or 2, wherein, in the star polymer, the number average molecular weight of each polymeric arm is between 5,000 and 150,000, and the peak molecular weight of the



hydrogenated star-shaped polymer is between 25,000 and 1,250,000.

4. Process as claimed in claim 1, 2 or 3, wherein said star-shaped polymer and said carboxylic acid, anhydride or ester are reacted in a ratio of moles of carboxylic acid, anhydride or ester to olefinic double bonds remaining in the selectively hydrogenated star-shaped polymer of between 1:1 and 2:1.
5. Process as claimed in any one of claims 1-4 wherein the star polymer and carboxylic acid are reacted at a temperature between 130 °C and 250 °C.
6. Process as claimed in any one of the preceding claims wherein the long chain alkane-substituted carboxylic acid (reactant a)) is derived by reacting an alpha, beta unsaturated carboxylic acid or active derivative thereof with polyisobutylene having molecular weight not greater than 5000, quotient Mw/Mn between 1.5 and 4.0 and average number of carboxylic acid groups per polyolefin moiety between 0.5 and 1.5.
7. Process as claimed in claim 6 wherein maleic acid or its anhydride is used as the alpha, beta unsaturated carboxylic acid both in preparing the activated star polymer (stage 1), and in preparing the polyolefin-substituted carboxylic acid (reactant a)).
8. Process as claimed in any one of the preceding claims, wherein the C₁₋₁₈ amine has the formula:

$$\text{NH}_2(\text{CH}_2)_n\text{[NH}(\text{CH}_2)_m\text{]}_m\text{-NH}_2$$
 where n is 2 to 4 and m is 0 to 6.
9. Process as claimed in claim 8, wherein the amine is diethylene triamine, triethylene tetramine or tetraethylenepentamine.
10. Process as claimed in any one of claims 1-7, wherein the alkane polyol is pentaerythritol.
11. Process as claimed in any one of the preceding claims, wherein the molar ratio of amine or polyol to the sum of the carboxylic compounds is between 0.25:1 and 2:1.
12. A process for the preparation of a lubricating composition which comprises mixing a major amount of a lubricating oil and a minor amount of a dispersant/VI improver prepared by a process as claimed in any one of the preceding claims.

Patentansprüche

Patentansprüche für folgende Vertragsstaaten : BE, DE, FR, GB, IT, NL

1. Verfahren zur Herstellung eines Dispergiermittel/Viskositätsindexverbesserungsmittels, das umfaßt
 - (1) Umsetzen einer alpha,beta-ungesättigten Carbonsäure, deren Anhydrid oder Ester mit einem selektiv hydrierten sternförmigen Polymer, das einen polyvinylaromatischen Kern und mindestens 4 polymere, an besagten Kern gebundene Zweige umfaßt, wobei besagte polymere Zweige aus der Gruppe, bestehend aus
 - (i) hydrierten Homopolymeren und hydrierten Copolymeren von konjugierten Dienen;
 - (ii) hydrierten Copolymeren von konjugierten Dienen und Monoalkenylarenen; und
 - (iii) deren Gemischen
 ausgewählt sind, und wobei mindestens 80 % der aliphatischen Ungesättigtheit des sternförmigen Polymers durch Hydrierung reduziert worden sind, während weniger als 20 % der aromatischen Ungesättigtheit reduziert worden sind; und
 - (2) Umsetzen des derart gebildeten aktivierten hydrierten Sternpolymers mit
 - a) einer langkettigen alkansubstituierten Carbonsäure, deren Anhydrid oder Ester, erhältlich durch Umsetzen einer alpha,beta-ungesättigten Carbonsäure, deren Anhydrid oder Ester mit einem Polyolefin, das sich von Olefinmonomeren mit 2 bis 16 Kohlenstoffatomen ableitet, und
 - b) einem C₁- bis C₁₈-Amin, das 1 bis 8 Stickstoffatome enthält, und/oder einem Alkanpolyol mit mindestens zwei Hydroxylgruppen, oder
 - c) einem vorgebildeten Produkt der Umsetzungsprodukte a) und b).



2. Verfahren, wie in Anspruch 1 beansprucht, wobei die Anzahl der polymeren Zweige zwischen 4 und 25 liegt und die polyvinylaromatische Verbindung Divinylbenzol ist.
3. Verfahren nach Anspruch 1 oder 2, wobei bei dem Sternpolymer das durchschnittliche Molekulargewichtszahlenmittel jedes polymeren Zweiges zwischen 5000 und 150000 liegt und der Höchstwert des Molekulargewichts des hydrierten sternförmigen Polymers zwischen 25000 und 1250000 liegt.
4. Verfahren wie in Anspruch 1, 2 oder 3 beansprucht, wobei das besagte sternförmige Polymer und die besagte Carbonsäure, deren Anhydrid oder Ester in einem Molverhältnis Carbonsäure, deren Anhydrid oder Ester zu olefinischen Doppelbindungen, die in dem selektiv hydrierten sternförmigen Polymer verbleiben, zwischen 1:1 und 2:1 umgesetzt werden.
5. Verfahren wie in irgendeinem der Ansprüche 1-4 beansprucht, wobei das Sternpolymer und die Carbonsäure bei einer Temperatur zwischen 130 °C und 250 °C umgesetzt werden.
6. Verfahren wie in irgendeinem der vorstehenden Ansprüche beansprucht, wobei die langkettige alkan-substituierte Carbonsäure (Reaktionsteilnehmer (a)) durch Umsetzen einer alpha,beta-ungesättigten Carbonsäure oder deren aktivem Derivat mit Polyisobutylen mit einem Molekulargewicht kleiner als 5000, einem Quotienten Mw/Mn zwischen 1,5 und 4,0 und einer durchschnittlichen Anzahl von Carboxylgruppen je Polyolefinmolekülteil zwischen 0,5 und 1,5 abgeleitet wird.
7. Verfahren wie in Anspruch 6 beansprucht, wobei Maleinsäure oder deren Anhydrid als alpha,beta-ungesättigte Carbonsäure sowohl bei der Herstellung des aktivierten Sternpolymers (Stufe 1) als auch bei der Herstellung der polyolefinsubstituierten Carbonsäure (Reaktionsteilnehmer (a)) verwendet wird.
8. Verfahren wie in irgendeinem der vorstehenden Ansprüche beansprucht, wobei C₁₋₁₈-Amin die Formel

$$\text{NH}_2(\text{CH}_2)_n[\text{NH}(\text{CH}_2)_m]_m\text{-NH}_2$$
 hat, in der n 2 bis 4 ist und m 0 bis 6 ist.
9. Verfahren wie in Anspruch 8 beansprucht, wobei das Amin Diethylentriamin, Triethylentetramin oder Tetraethylenpentamin ist.
10. Verfahren wie in irgendeinem der Ansprüche 1-7 beansprucht, wobei das Alkanpolyol Pentaerythrit ist.
11. Verfahren wie in irgendeinem der vorstehenden Ansprüche beansprucht, wobei das molare Verhältnis von Amin oder Polyol zur Summe der Carboxylverbindungen zwischen 0,25:1 und 2:1 liegt.
12. Ein verbrennungsrückstandsfreies, öllösliches Dispergiermittel/Viskositätsindexverbesserungsmittel, wenn es durch ein Verfahren, wie in irgendeinem der vorstehenden Ansprüche beansprucht, hergestellt worden ist.
13. Eine Schmierölzusammensetzung, umfassend eine größere Menge eines Schmieröls und einer geringeren Menge eines Dispergiermittels/Viskositätsindexverbesserungsmittels wie in Anspruch 12 beansprucht.

Patentansprüche für folgenden Vertragsstaat : ES

1. Verfahren zur Herstellung eines Dispergiermittel/Viskositätsindexverbesserungsmittels, das umfaßt
 - (1) Umsetzen einer alpha,beta-ungesättigten Carbonsäure, deren Anhydrid oder Ester mit einem selektiv hydrierten sternförmigen Polymer, das einen polyvinylaromatischen Kern und mindestens 4 polymere, an besagten Kern gebundene Zweige umfaßt, wobei besagte polymere Zweige aus der Gruppe, bestehend aus
 - (i) hydrierten Homopolymeren und hydrierten Copolymeren von konjugierten Dienen;
 - (ii) hydrierten Copolymeren von konjugierten Dienen und Monoalkenylarenen; und
 - (iii) deren Gemischen
 ausgewählt sind, und wobei mindestens 80 % der aliphatischen Ungesättigtheit des sternförmigen



Polymers durch Hydrierung reduziert worden sind, während weniger als 20 % der aromatischen Ungesättigkeit reduziert worden sind; und

(2) Umsetzen des derart gebildeten aktivierten hydrierten Sternpolymers mit

- a) einer langkettigen alkansubstituierten Carbonsäure, deren Anhydrid oder Ester, erhältlich durch Umsetzen einer alpha,beta-ungesättigten Carbonsäure, deren Anhydrid oder Ester mit einem Polyolefin, das sich von Olefinmonomeren mit 2 bis 16 Kohlenstoffatomen ableitet, und
- b) einem C₁- bis C₁₈-Amin, das 1 bis 8 Stickstoffatome enthält, und/oder einem Alkanpolyol mit mindestens zwei Hydroxylgruppen, oder
- c) einem vorgebildeten Produkt der Umsetzungsprodukte a) und b).

2. Verfahren, wie in Anspruch 1 beansprucht, wobei die Anzahl der polymeren Zweige zwischen 4 und 25 liegt und die polyvinylaromatische Verbindung Divinylbenzol ist.

3. Verfahren nach Anspruch 1 oder 2, wobei bei dem Sternpolymer das durchschnittliche Molekulargewichtszahlenmittel jedes polymeren Zweiges zwischen 5000 und 150000 liegt und der Höchstwert des Molekulargewichts des hydrierten sternförmigen Polymers zwischen 25000 und 1250000 liegt.

4. Verfahren wie in Anspruch 1, 2 oder 3 beansprucht, wobei das besagte sternförmige Polymer und die besagte Carbonsäure, deren Anhydrid oder Ester in einem Molverhältnis Carbonsäure, deren Anhydrid oder Ester zu olefinischen Doppelbindungen, die in dem selektiv hydrierten sternförmigen Polymer verbleiben, zwischen 1:1 und 2:1 umgesetzt werden.

5. Verfahren wie in irgendeinem der Ansprüche 1-4 beansprucht, wobei das Sternpolymer und die Carbonsäure bei einer Temperatur zwischen 130 °C und 250 °C umgesetzt werden.

6. Verfahren wie in irgendeinem der vorstehenden Ansprüche beansprucht, wobei die langkettige alkansubstituierte Carbonsäure (Reaktionsteilnehmer (a)) durch Umsetzen einer alpha,beta-ungesättigten Carbonsäure oder deren aktivem Derivat mit Polyisobutylen mit einem Molekulargewicht kleiner als 5000, einem Quotienten Mw/Mn zwischen 1,5 und 4,0 und einer durchschnittlichen Anzahl von Carboxylgruppen je Polyolefinmolekülteil zwischen 0,5 und 1,5 abgeleitet wird.

7. Verfahren wie in Anspruch 6 beansprucht, wobei Maleinsäure oder deren Anhydrid als alpha,beta-ungesättigte Carbonsäure sowohl bei der Herstellung des aktivierten Sternpolymers (Stufe 1) als auch bei der Herstellung der polyolefinsubstituierten Carbonsäure (Reaktionsteilnehmer (a)) verwendet wird.

8. Verfahren wie in irgendeinem der vorstehenden Ansprüche beansprucht, wobei C₁₋₁₈-Amin die Formel



hat, in der n 2 bis 4 ist und m 0 bis 6 ist.

9. Verfahren wie in Anspruch 8 beansprucht, wobei das Amin Diethylentriamin, Triethylentetramin oder Tetraethylenpentamin ist.

10. Verfahren wie in irgendeinem der Ansprüche 1-7 beansprucht, wobei das Alkanpolyol Pentaerythrit ist.

11. Verfahren wie in irgendeinem der vorstehenden Ansprüche beansprucht, wobei das molare Verhältnis von Amin oder Polyol zur Summe der Carboxylverbindungen zwischen 0,25:1 und 2:1 liegt.

12. Ein Verfahren zur Herstellung einer Schmierölzusammensetzung, die ein Mischen einer größeren Menge eines Schmieröls und einer geringeren Menge eines Dispergiermittels/Viskositätsindexverbesserungsmittels umfaßt, das mittels eines Verfahrens, wie in irgendeinem der vorstehenden Ansprüche beansprucht, hergestellt worden ist.



Revendications

Revendications pour les Etats contractants suivants : BE, DE, FR, GB, IT, NL

1. Procédé de préparation d'un dispersant/agent améliorant l'indice de viscosité, qui comprend
 - 1) la réaction d'un acide carboxylique insaturé en alpha-bêta ou d'un anhydride ou ester d'un tel acide avec un polymère en étoile sélectivement hydrogéné comprenant un noyau polyvinyl aromatique et au moins 4 branches polymères reliées au noyau, où les branches polymères sont choisies dans le groupe constitué par :
 - (i) des homopolymères hydrogénés et des copolymères hydrogénés de diènes conjugués ;
 - (ii) des copolymères hydrogénés de diènes conjugués et de monoalcényl arènes ; et
 - (iii) leurs mélanges ;
 et où au moins 80 % de l'insaturation aliphatique du polymère en étoile a été réduite par hydrogénation tandis que moins de 20 % de l'insaturation aromatique a été réduite ; et
 - 2) la réaction du polymère en étoile ainsi formé avec :
 - a) un acide alcane-carboxylique à chaîne longue ou un anhydride ou ester d'un tel acide, pouvant être obtenu en faisant réagir un acide carboxylique insaturé en alpha-bêta ou un anhydride ou ester d'un tel acide avec une polyoléfine dérivée de monomères oléfiniques ayant de 2 à 16 atomes de carbone ; et
 - b) une amine de C₁ à C₁₈ contenant 1 à 8 atomes d'azote et/ou un alcane polyol ayant au moins deux groupes hydroxy ; ou avec
 - c) le produit préformé des corps en réaction a) et b).
2. Procédé selon la revendication 1, dans lequel le nombre de branches polymères est compris entre 4 et 25 et le composé polyvinyl aromatique est du divinyl benzène.
3. Procédé selon la revendication 1 ou 2, dans lequel, dans le polymère en étoile, le poids moléculaire moyen en nombre de chaque branche polymère est compris entre 5 000 et 150 000 et le poids moléculaire au pic du polymère en étoile hydrogéné est compris entre 25 000 et 1 250 000.
4. Procédé selon la revendication 1, 2 ou 3, dans lequel le polymère en étoile et l'acide carboxylique ou son anhydride ou ester sont mis à réagir dans un rapport des moles d'acide carboxylique, anhydride ou ester aux doubles liaisons oléfiniques restantes dans le polymère en étoile sélectivement hydrogéné compris entre 1:1 et 2:1.
5. Procédé selon l'une quelconque des revendications 1-4, dans lequel le polymère en étoile et l'acide carboxylique sont mis à réagir à une température comprise entre 130 °C et 250 °C.
6. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'acide alcane carboxylique à chaîne longue (corps en réaction a)) est obtenu par réaction d'un acide carboxylique insaturé en alpha,bêta ou d'un dérivé actif d'un tel acide avec un polyisobutylène ayant un poids moléculaire pas supérieur à 5000, un quotient Mw/Mn compris entre 1,5 et 4,0 et un nombre moyen de groupes acide carboxylique par portion polyoléfine compris entre 0,5 et 1,5.
7. Procédé selon la revendication 6, dans lequel l'acide maléique ou son anhydride est utilisé comme acide carboxylique insaturé en alpha,bêta tant dans la préparation du polymère en étoile activé (étape 1) que dans la préparation de l'acide carboxylique substitué par une polyoléfine (corps en réaction a)).
8. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'amine en C₁₋₁₈ a la formule :

$$\text{NH}_2(\text{CH}_2)_n\text{-(NH}(\text{CH}_2)_m\text{)}_m\text{-NH}_2$$
 dans laquelle n va de 2 à 4 et m va de 0 à 6.
9. Procédé selon la revendication 8, dans lequel l'amine est la diéthylène triamine, la triéthylène tétramine ou la tétraéthylène pentamine.



10. Procédé selon l'une quelconque des revendications 1-7, dans lequel l'alcane polyol est le pentaérythritol.
11. Procédé selon l'une quelconque des revendications précédentes, dans lequel le rapport molaire de l'amine ou du polyol à la somme des composés carboxyliques est compris entre 0,25:1 et 2:1.
12. Un dispersant/agent améliorant l'indice de viscosité soluble dans l'huile, sans cendre, quand il est préparé par un procédé selon l'une quelconque des revendications précédentes.
13. Une composition lubrifiante comprenant une quantité majeure d'une huile lubrifiante et une quantité mineure d'un dispersant/agent améliorant l'indice de viscosité selon la revendication 12.

Revendications pour l'Etat contractant suivant : ES

1. Procédé de préparation d'un dispersant/agent améliorant l'indice de viscosité, qui comprend
 - 1) la réaction d'un acide carboxylique insaturé en alpha-bêta ou d'un anhydride ou ester d'un tel acide avec un polymère en étoile sélectivement hydrogéné comprenant un noyau polyvinyl aromatique et au moins 4 branches polymères reliées au noyau, où les branches polymères sont choisies dans le groupe constitué par :
 - (i) des homopolymères hydrogénés et des copolymères hydrogénés de diènes conjugués ;
 - (ii) des copolymères hydrogénés de diènes conjugués et de monoalcényl arènes ; et
 - (iii) leurs mélanges ;
 et où au moins 80 % de l'insaturation aliphatique du polymère en étoile a été réduite par hydrogénation tandis que moins de 20 % de l'insaturation aromatique a été réduite ; et
 - 2) la réaction du polymère en étoile ainsi formé avec :
 - a) un acide alcane-carboxylique à chaîne longue ou un anhydride ou ester d'un tel acide, pouvant être obtenu en faisant réagir un acide carboxylique insaturé en alpha-bêta ou un anhydride ou ester d'un tel acide avec une polyoléfine dérivée de monomères oléfiniques ayant de 2 à 16 atomes de carbone ; et
 - b) une amine de C₁ à C₁₈ contenant 1 à 8 atomes d'azote et/ou un alcane polyol ayant au moins deux groupes hydroxy ; ou avec
 - c) le produit préformé des corps en réaction a) et b).
2. Procédé selon la revendication 1, dans lequel le nombre de branches polymères est compris entre 4 et 25 et le composé polyvinyl aromatique est du divinyl benzène.
3. Procédé selon la revendication 1 ou 2, dans lequel, dans le polymère en étoile, le poids moléculaire moyen en nombre de chaque branche polymère est compris entre 5 000 et 150 000 et le poids moléculaire au pic du polymère en étoile hydrogéné est compris entre 25 000 et 1 250 000.
4. Procédé selon la revendication 1, 2 ou 3, dans lequel le polymère en étoile et l'acide carboxylique ou son anhydride ou ester sont mis à réagir dans un rapport des moles d'acide carboxylique, anhydride ou ester aux doubles liaisons oléfiniques restantes dans le polymère en étoile sélectivement hydrogéné compris entre 1:1 et 2:1.
5. Procédé selon l'une quelconque des revendications 1-4, dans lequel le polymère en étoile et l'acide carboxylique sont mis à réagir à une température comprise entre 130 °C et 250 °C.
6. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'acide alcane carboxylique à chaîne longue (corps en réaction a)) est obtenu par réaction d'un acide carboxylique insaturé en alpha,bêta ou d'un dérivé actif d'un tel acide avec un polyisobutylène ayant un poids moléculaire pas supérieur à 5000, un quotient Mw/Mn compris entre 1,5 et 4,0 et un nombre moyen de groupes acide carboxylique par portion polyoléfine compris entre 0,5 et 1,5.
7. Procédé selon la revendication 6, dans lequel l'acide maléique ou son anhydride est utilisé comme acide carboxylique insaturé en alpha,bêta tant dans la préparation du polymère en étoile activé (étape 1) que dans la préparation de l'acide carboxylique substitué par une polyoléfine (corps en réaction a)).



8. Procédé selon l'une quelconque des revendications précédentes, dans lequel l'amine en C_{1-18} a la formule :



dans laquelle n va de 2 à 4 et m va de 0 à 6.

9. Procédé selon la revendication 8, dans lequel l'amine est la diéthylène triamine, la triéthylène tétramine ou la tétraéthylène pentamine.

10. Procédé selon l'une quelconque des revendications 1-7, dans lequel l'alcane polyol est le pentaérythritol.

11. Procédé selon l'une quelconque des revendications précédentes, dans lequel le rapport molaire de l'amine ou du polyol à la somme des composés carboxyliques est compris entre 0,25:1 et 2:1.

12. Un procédé de préparation d'une composition lubrifiante, selon lequel on mélange une quantité majeure d'une huile lubrifiante et une quantité mineure d'un dispersant/agent améliorant l'indice de viscosité préparé par un procédé selon l'une quelconque des revendications précédentes.