

ABSTRACT**METHODS OF ACTIVATING CHROMIUM CATALYSTS**

New methods for activating chromium catalysts for polymerization processes decrease the amount of time required for activation and increase catalyst activity. Rapid heating to a first temperature is followed by a first hold period before heating to a higher second temperature and maintaining the second temperature for a second hold period. In one aspect, the overall activation process takes less than 10 hours.

Fig. 1