

**MAGNETIC THIN FILM LAMINATED STRUCTURE DEPOSITION METHOD,  
MAGNETIC THIN FILM LAMINATED STRUCTURE AND MICRO-INDUCTANCE  
DEVICE**

**TECHNICAL FIELD**

**[0001]** The present disclosure relates to the field of microelectronics and, in particular, to a deposition method of a magnetic thin film laminated structure, a magnetic thin film laminated structure, and a micro-inductive device.

**BACKGROUND**

**[0002]** With the development of science and technology, the integrated circuit manufacturing process can significantly reduce the size of a processor, but some core components such as integrated inductors, noise suppressors, etc., still face many difficulties in terms of high frequency, miniaturization, and integration. In order to solve this problem, soft magnetic thin film materials having high magnetization, high magnetic permeability, high resonance frequency, and high electrical resistivity have attracted more and more attention.

**[0003]** FIG. 1 is a structural view showing a conventional magnetic thin film laminated structure. As shown in FIG. 1, the magnetic thin film laminated structure is formed by alternately providing an isolation layer and a magnetic film layer, where the isolation layer is directly deposited on a workpiece to be processed.

**[0004]** However, in the above magnetic thin film laminated structure, because the magnetic film layer has a large tensile stress and is brittle, it is not easy to fabricate a thick magnetic thin film laminated structure obtained from the magnetic film layer. If the total thickness of the above-

fabricated magnetic thin film laminated structure is more than 500 nm, due to the large tensile stress and brittleness of the magnetic film layer, the tensile stress of the magnetic thin film laminated structure is correspondingly large. Thus, the above-mentioned magnetic thin film laminated structure may encounter a phenomenon of detaching (or cracked detaching) from the attached workpiece, and hence is not suitable for the fabrication of a micro-inductive device. In addition, because it is not easy to fabricate a thick above-mentioned magnetic thin film laminated structure, an applied frequency range of an inductor device obtained thereby is usually only 1 to 5 GHz, and cannot cover a frequency range of MHz.

## **SUMMARY**

**[0005]** Aiming to at least solve one of the technical problems existing in the existing technology, the present disclosure provides a deposition method of a magnetic thin film laminated structure, a magnetic thin film laminated structure, and a micro-inductive device. The deposition method of the magnetic thin film laminated structure can increase a total thickness of the magnetic thin film laminated structure, broaden the application frequency range of the inductor device fabricated by the same, and can be applied to a large-sized workpiece to fabricate the micro-inductance device.

**[0006]** To achieve the object of the present disclosure, there is provided a deposition method of a magnetic thin film laminated structure including the following steps: S1, depositing an adhesion layer on a workpiece to be processed, S2, depositing a magnetic/isolation unit on the adhesion layer, where the magnetic/isolation unit includes at least one pair of magnetic film layer and an isolation layer that are alternately disposed.

**[0007]** In the step S2, the magnetic film layer is deposited on the adhesion layer, and the isolation layer is deposited on the magnetic film layer.

**[0008]** The step S1 and the step S2 are alternately performed at least twice.

**[0009]** The deposition method of the magnetic thin film laminated structure further includes: S3, depositing a layer of the magnetic film on the magnetic/isolation unit.

**[0010]** The step S1, the step S2, and the step S3 are alternately performed at least twice.

**[0011]** The adhesive layer is made of a material having compressive stress.

**[0012]** The material having compressive stress includes a Ta film, a TaN film or a TiN film.

**[0013]** In the step S1, the adhesion layer is deposited by a sputtering process, in which a target is electrically connected to a pulsed direct current (DC) power source, and a sputtering power output by the pulsed DC power source is less than or equal to 15 kW; or the target is electrically connected to a radio frequency (RF) power source, a sputtering power output by the RF power source is less than or equal to 3 kW; or the target is electrically connected to a DC power source, and a sputtering power output by the DC power source is less than or equal to 20 kW.

**[0014]** In a scenario that the target is electrically connected to the pulsed DC power source, the sputtering power output by the pulsed DC power source ranges from 3 to 10 kW; or in a scenario that the target is electrically connected to the RF power source, the sputtering power output by the RF power source ranges from 0.3 to 1.5 kW; or in a scenario that the target is electrically connected to the DC power source, the sputtering power output by the DC power source ranges from 15~19kw.

**[0015]** In the step S1, the adhesion layer is deposited by the sputtering process, and a process pressure of the sputtering process is less than or equal to 5 mTorr.

**[0016]** The process pressure of the sputtering process ranges from 0.5 to 2 mTorr.

**[0017]** The magnetic film layer is made of a material having soft magnetic properties.

**[0018]** The material having the soft magnetic properties includes a NiFe permalloy material, a CoZrTa amorphous material, a Co-based material, a Fe-based material, or a Ni-based material.

**[0019]** In the step S2, the magnetic film layer is deposited by a sputtering process, in which the target is electrically connected to an excitation power source, a sputtering power output by the excitation power source is less than or equal to 2 kw, and a process pressure of the sputtering process is less than or equal to 5 mTorr.

**[0020]** The sputtering power ranges from 0.5 to 1.5 kw; and a process pressure of the sputtering process ranges from 0.3 to 3 mTorr.

**[0021]** While the magnetic film layer is deposited, a bias magnetic field device is used to form a horizontal magnetic field in a vicinity of a wafer for depositing the magnetic thin film laminated structure; and the horizontal magnetic field is configured to cause the deposited magnetic film layer to have in-plane anisotropy.

**[0022]** The isolation layer is made of a non-magnetic material.

**[0023]** The non-magnetic material includes Cu, Ta, SiO<sub>2</sub> or TiO<sub>2</sub>.

**[0024]** In the step S2, the isolation layer is deposited by a sputtering process, in which the target is electrically connected to the excitation power source, the sputtering power output by the

excitation power source is less than or equal to 5 kW, and the process pressure of the sputtering process is less than or equal to 20 mTorr.

**[0025]** The sputtering power output by the excitation power source ranges from 1 to 2 kw; and the process pressure of the sputtering process ranges from 9 to 12 mTorr.

**[0026]** A thickness of the adhesion layer ranges from 50 to 300 nm, a thickness of the magnetic film layer ranges from 30 to 200 nm, and a thickness of the isolation layer ranges from 3 to 10 nm.

**[0027]** The thickness of the adhesion layer ranges from 80 to 200 nm, the thickness of the magnetic film layer ranges from 50 to 150 nm, and the thickness of the isolation layer ranges from 5 to 8 nm.

**[0028]** In another aspect, the present disclosure also provides a magnetic thin film laminated structure, which includes an adhesion layer and a magnetic/isolation unit. The magnetic/isolation unit includes at least one pair of magnetic film layer and an isolation layer disposed alternately.

**[0029]** The magnetic film layer is located on the adhesive layer, and the isolation layer is located on the magnetic film layer.

**[0030]** The magnetic thin film laminated structure includes at least two magnetic laminated film units, where each of the magnetic laminated film units includes the adhesive layer and the magnetic/isolation unit.

**[0031]** One magnetic film layer is further provided on a top layer of the magnetic thin film laminated structure.

**[0032]** The magnetic thin film laminated structure includes at least two magnetic laminated film units, where each of the magnetic laminated film units includes the adhesion layer, the magnetic/isolation unit and the magnetic film layer.

**[0033]** A total thickness of the magnetic thin film laminated structure ranges from 400 to 3000 nm.

**[0034]** There are two to fifty pairs of the magnetic film layer and the isolation layer that are alternately arranged.

**[0035]** The thickness of the adhesion layer ranges from 3 to 50 nm.

**[0036]** As another aspect, the present disclosure provides a micro-inductive device including a magnetic core, which is fabricated by using the magnetic thin film laminated structure according to any one of the foregoing aspects of the present disclosure, and an application frequency of the micro-inductive device ranges from 100MHz to 5GHz.

**[0037]** The disclosure has the following beneficial effects.

**[0038]** In the deposition method of the magnetic thin film laminated structure provided by the present disclosure, the magnetic/isolation unit is deposited on the adhesion layer, and the adhesion layer can adjust the tensile stress of the magnetic thin film laminated structure caused by the tensile stress of the magnetic film layer to avoid a phenomenon that tensile stress of the magnetic thin film laminated structure is too big, thereby making it possible to obtain a magnetic

thin film laminated structure having a large total thickness, broadening the application frequency range of the inductive device fabricated therefrom; and, in addition, due to the stress adjustment effect of the adhesive layer on the magnetic thin film laminated structure, a large-thickness magnetic laminated film structure can be fabricated on the workpiece to be processed, thereby avoiding cracking and shedding.

**[0039]** The magnetic thin film laminated structure provided by the embodiment of the present disclosure has a magnetic/isolation unit deposited on the adhesive layer, and the adhesive layer can adjust the tensile stress of the magnetic film layer to further adjust the tensile stress of the magnetic thin film laminated structure. As such, the total thickness of the magnetic thin film laminated structure can be increased, thereby broadening the application frequency range of the inductor device fabricated therefrom.

**[0040]** The present disclosure also provides a micro-inductive device including a magnetic core fabricated by the above-mentioned magnetic thin film laminated structure provided by the present disclosure. The total thickness of the magnetic thin film laminated structure is increased, which broadens the application frequency range of the inductive device. For example, the application frequency of the micro-inductive device can range from 100 MHz to 5 GHz.

## **DESCRIPTION OF THE DRAWINGS**

**[0041]** FIG. 1 is a structural view of a conventional magnetic thin film laminated structure;

**[0042]** FIG. 2 is a flow chart of a deposition method of a magnetic thin film laminated structure according to a first embodiment of the present disclosure;

**[0043]** FIG. 3 is a structural view showing a magnetic thin film laminated structure obtained by a deposition method of a magnetic thin film laminated structure according to a first embodiment of the present disclosure; and

**[0044]** FIG. 4 is a structural view showing a magnetic thin film laminated structure obtained by a deposition method of a magnetic thin film laminated structure according to a second embodiment of the present disclosure.

### **DETAILED DESCRIPTION**

**[0045]** In order to enable those skilled in the art to better understand the technical solutions of the present disclosure, a deposition method of a magnetic thin film laminated structure, a magnetic thin film laminated structure and a micro-inductive device provided by the present disclosure are described in detail below with reference to the accompanying drawings.

**[0046]** FIG. 2 is a flow chart of a deposition method of a magnetic thin film laminated structure according to a first embodiment of the present disclosure. FIG. 3 is a structural view showing a magnetic thin film laminated structure obtained by a deposition method of a magnetic thin film laminated structure according to a first embodiment of the present disclosure. Referring to FIG. 2 and FIG. 3 together, the deposition method of the magnetic thin film laminated structure includes the following steps.

**[0047]** S1, an adhesive layer 1 is deposited on a workpiece to be processed.

**[0048]** It should be noted that, in S1 of the embodiment of the present disclosure, the workpiece to be processed includes a workpiece to be processed of which a surface is not deposited with a

film, and a workpiece to be processed of which a surface is deposited with a magnetic film layer 2 or an isolating layer 3.

**[0049]** S2, a magnetic/isolation unit is deposited on the adhesion layer 1, where the magnetic/isolation unit includes at least one pair of magnetic film layer 2 and the isolation layer 3 that are alternately arranged. The so-called alternating arrangement means alternately laminating layers along an axial direction of the workpiece to be processed.

**[0050]** A layer in contact with the adhesion layer 1 in the magnetic/isolation unit is the magnetic film layer 2, and accordingly, the isolation layer 3 is deposited on the magnetic film layer 2.

**[0051]** The isolation layer 3 is made of a non-magnetic material, and the non-magnetic material includes Cu, Ta, SiO<sub>2</sub> or TiO<sub>2</sub>. The isolation layer 3 can not only isolate the adjacent two magnetic film layers 2 and reduce the magnetic flux skin effect, and can also play a role to adjust the resistivity of the magnetic thin film laminated structure, reduce the eddy current loss, and improve a high-frequency performance of the magnetic thin film laminated structure. It is easy to understand that in order to enable the isolation layer 3 to fully play the above role, the magnetic film layer 2 may be deposited on the adhesion layer 1, and then the isolation layer 3 is deposited on the magnetic film layer 2, so that the magnetic film layer 2 and the isolation layer 3 are alternately disposed. Further, the topmost layer is the isolation layer 3, which can further increase the electrical resistivity of the magnetic thin film laminated structure.

**[0052]** Moreover, optionally, the deposition method of the magnetic thin film laminated structure provided by the present disclosure may further increase the following step:

S3, a magnetic film layer 2 is deposited on the magnetic/isolation unit.

**[0053]** In the present embodiment, there are four pairs of the magnetic film layer 2 and the isolation layer 3, and a magnetic film layer 2 is further deposited on the uppermost isolation layer 3. That is, there are a total number of five layers of the magnetic film layer 2; a total number of four layers of the isolation layer 3. Of course, in practical applications, step S3 may be omitted, that is, the total number of layers of the magnetic film layer 2 is equal to that of the isolation layer 3.

**[0054]** With the help of the above-mentioned adhesive layer 1, the excessive tensile stress of the magnetic thin film laminated structure caused by the tensile stress of the magnetic film layer 2 can be avoided. As such, a magnetic thin film laminated structure having a large total thickness can be obtained, thereby broadening the applicable frequency range of the fabricated inductive device.

**[0055]** The adhesion layer 1 can be made of a material having compressive stress, such as a Ta film, a TaN film, or a TiN film, so as to play a role to adjust the tensile stress of the magnetic thin film laminated structure.

**[0056]** For the magnetic thin film laminated structure, the performance of the magnetic thin film laminated structure is determined by the magnetic film layer 2 and the insulating layer 3 together. The magnetic film layer 2 forms a micro-inductive magnetic core to increase the magnetic flux. The isolation layer 3 plays a role to isolate the adjacent two magnetic film layers 2, and adjusts the resistivity of the magnetic film layer 2, reduces eddy current loss, and improves high frequency performance. Preferably, by depositing a magnetic film layer 2 on the magnetic/isolation unit by step S3, the overall thickness of the magnetic film layer 2 in the magnetic thin film laminated structure can be further increased, thereby increasing magnetic

properties. Therefore, in practical applications, the magnetic properties of the desired magnetic thin film laminated structure can be matched.

**[0057]** The deposition method of the adhesion layer 1 is described in detail below.

**[0058]** Specifically, in step S1, the adhesion layer 1 is deposited using a sputtering process. The apparatus for performing the sputtering process mainly includes a reaction chamber, a target, a base for carrying the substrate, and a pulsed DC power source, where the target is disposed at the top of the reaction chamber, and the base is disposed in the reaction chamber and located below the target. Optionally, the vertical spacing between the target and the base (i.e., the target spacing) is 30 to 90 mm. Moreover, the target is electrically connected to the pulsed DC power source for applying sputtering power to the target, so as to excite the process gas in the reaction chamber to form a plasma, bombard the target to sputter a target material and deposit it on the surface of the wafer and form a film. Due to the limited temperature range of a photoresist used in the process, in the process integration, it is easier to control the temperature of the wafer and the photoresist thereon by using lower sputtering power. The target is electrically connected to the pulsed DC power source, so that the adhesion layer 1 having a superior stress adjustment effect can be obtained at the lower sputtering power.

**[0059]** The parameters of the above sputtering process are as follows: the sputtering power output by the pulsed DC power source is less than or equal to 15 kw; and the process pressure of the sputtering process is less than or equal to 5 mTorr. Preferably, in order to meet the process integration requirements and improve the process effect, the sputtering power output by the pulsed DC power source ranges from 3 to 10 kw. The process pressure of the sputtering process ranges from 0.5 to 2 mTorr. The thickness of the sputtering ranges from 80 to 200 nm.

**[0060]** Optionally, in step S1, the target may also be electrically connected to a radio frequency power source, and the sputtering power output by the radio frequency power source is less than or equal to 3 kw; or the target may be electrically connected to the DC power source, and the sputtering power output by the DC power source is less than or equal to 20 kW. Preferably, in order to meet the process integration requirements and improve the process effect, the sputtering power output by the RF power source ranges from 0.3 to 1.5 kW. Alternatively, the sputtering power output by the DC power source ranges from 15 to 19 kW.

**[0061]** In step S2, the magnetic film layer 2 may be deposited using a sputtering process. The apparatus for performing the sputtering process mainly includes a reaction chamber, a target, a base for carrying the substrate, a sputtering power source, and a bias magnetic field device, where the target is disposed at the top of the reaction chamber, and the base is disposed in the reaction chamber and is located below the target. The target is electrically connected to the sputtering power source, and the sputtering power source is used to apply sputtering power to the target to excite the process gas in the reaction chamber to form a plasma and bombard the target to sputter a target material out of the target and deposited on the surface of the adhesive layer 1, thereby forming the magnetic film layer 2.

**[0062]** In addition, the bias magnetic field device is disposed in the reaction chamber and includes two sets of magnets of opposite polarities. The two sets of magnet sets are respectively disposed on opposite sides of the base. The bias magnetic field device can form a horizontal magnetic field (parallel to the surface of the wafer) in a region close to the base in the reaction chamber, and the magnetic field strength of the horizontal magnetic field can reach 50 to 300 Gs. As such, when the sputtering process is performed, magnetic domains of the magnetic materials deposited on the wafer are arranged in the horizontal direction so that an easy magnetization

field can be formed in the magnetic domain arrangement direction, and a hard-magnetic field is formed in a direction perpendicular to the magnetic domain alignment direction. That is, an in-plane anisotropy field is formed, so as to obtain an in-plane anisotropic magnetic thin film laminated structure for fabricating a micro-inductive device.

**[0063]** The parameters of the above sputtering process are as follows: the sputtering power output by the excitation power source is less than or equal to 2 kw; and the process pressure of the sputtering process is less than or equal to 5 mTorr. Preferably, in order to meet the process integration requirements, optimize the performance of the magnetic film layer, and improve the process effect, the sputtering power output by the excitation power ranges from 0.5 to 1.5 kW; the process pressure of the sputtering process ranges from 0.3 to 3mTorr.

**[0064]** The magnetic film layer 2 is made of a material having soft magnetic properties. The soft magnetic material satisfies conditions such as high saturation magnetization ( $M_s$ ), low residual magnetization ( $M_r$ ), high initial magnetic permeability ( $\mu_i$ ), and high maximum magnetic permeability ( $\mu_{max}$ ), and small coercivity ( $H_c$ ). As such, the change in the external magnetic field can be quickly responded, and the high magnetic flux density can be obtained with low loss.

**[0065]** Optionally, the soft magnetic material includes a NiFe permalloy material, a CoZrTa amorphous material, a Co-based material, a Fe-based material, or a Ni-based material. Among them, the NiFe permalloy material may be, for example,  $Ni_{80}Fe_{20}$ ,  $Ni_{45}Fe_{55}$ ,  $Ni_{81}Fe_{19}$ , etc. The CoZrTa amorphous material may be, for example,  $Co_{91.5}Zr_{4.0}Ta_{4.5}$ , etc. The Co-based material, the Fe-based material, or the Ni-based material may be, for example,  $Co_{60}Fe_{40}$ , NiFeCr, etc.

**[0066]** In step S2, the isolation layer 3 may be deposited using a sputtering process. The apparatus for performing the sputtering process mainly includes a reaction chamber, a target, a

base for carrying the substrate, and a sputtering power source, where the target is disposed at a top of the reaction chamber, and the base is disposed in the reaction chamber and located below the target. Moreover, the target is electrically connected to the sputtering power source.

**[0067]** Parameters of the above sputtering process are as follows: a sputtering power output by the sputtering power output is less than or equal to 5 kw; and a process pressure of the sputtering process is less than or equal to 20 mTorr. Preferably, in order to meet the process integration requirements and improve the process effect, the sputtering power output by the sputtering power source ranges from 1 to 2 kw; and the process pressure of the sputtering process ranges from 9 to 12 mTorr.

**[0068]** Optionally, the thickness of the adhesion layer 1 ranges from 50 to 300 nm. The thickness of the magnetic film layer 2 ranges from 30 to 200 nm. The thickness of the isolation layer 3 ranges from 3 to 10 nm. Preferably, the thickness of the adhesion layer 1 ranges from 80 to 200 nm. The thickness of the magnetic film layer 2 ranges from 50 to 150 nm. The thickness of the isolation layer 3 ranges from 5 to 8 nm.

**[0069]** FIG. 4 is a structural view showing a magnetic thin film laminated structure obtained by a deposition method of a magnetic thin film laminated structure according to a second embodiment of the present disclosure. Referring to FIG. 4, compared to the foregoing first embodiment, the deposition method provided by the embodiment of the present disclosure is different in that the step S1 and the step S2 are alternately performed at least twice to obtain a magnetic thin film laminated structure.

**[0070]** Specifically, the magnetic thin film laminated structure obtained by the deposition method provided by the embodiment includes M magnetic laminated film units, that is, a first

magnetic laminated film unit 100, a second magnetic laminated film unit 200, ..., a Mth the magnetic laminated film unit, where M is an integer greater than 1. For each of the magnetic laminated film units, an adhesion layer 1 and a magnetic/isolation unit are included. The magnetic/isolation unit includes at least one pair of magnetic film layer 2 and the isolation layer 3 that are alternately arranged. Preferably, for each magnetic/isolation unit, the layer that is in contact with the adhesion layer 1 is the magnetic film layer 2, and the isolation layer 3 is disposed on the magnetic film layer 2.

**[0071]** In a scenario that the thickness of the magnetic thin film laminated structure is constant, if the number of pairs of the magnetic film layer 2 and the isolation layer 3 is too large, it indicates that the number of times of fabricating the magnetic film layer 2 and the isolation layer 3 is too large. Therefore, for the entire process equipment system, a total number of process is large, which causes a large process pressure of the system, so that a productivity of the system per unit time is reduced, resulting in an increase in the production cost of the system. On the other hand, the number of pairs of the magnetic film layer 2 and the isolation layer 3 is too small, the thickness of the single layer of each of the adhesion layer 1, the magnetic film layer 2, and the isolation layer 3 involved in the magnetic thin film laminated structure is large, which causes the performance of the magnetic thin film laminated structure to be impaired. Therefore, for the magnetic thin film laminated structure, it is necessary to comprehensively consider the performance of the system and the performance of the magnetic thin film laminated structure to optimize the total thickness of the magnetic thin film laminated structure and the thickness of each layer, especially to optimize the number of pairs of the insulating layer 3 and the magnetic film layer 2. Preferably, the number of pairs of the isolation layer 3 and the magnetic film layer

2 is two to fifty, and the range the number of pairs can satisfy the performance requirements of the magnetic thin film laminated structure and ensure good system productivity.

**[0072]** By adopting multilayer-structured magnetic thin film laminated structure, the total thickness of the magnetic thin film laminated structure can be further increased, thereby broadening the application frequency range of the inductive device fabricated therefrom. Preferably, the total thickness of the magnetic thin film laminated structure ranges from 400 to 3000 nm. Preferably, the application frequency of the magnetic thin film laminated structure ranges from 100 MHz to 5 GHz.

**[0073]** In the present embodiment, the sputtering thickness of the adhesion layer 1 ranges from 3 to 50 nm. The thicknesses of the magnetic film layer 2 and the isolation layer 3 are the same as that of the first embodiment described above. Further, other process parameters for fabricating the adhesion layer 1, the magnetic film layer 2, and the isolation layer 3 are the same as those of the first embodiment described above.

**[0074]** Further, in the present embodiment, each time step S2 is performed, a magnetic/isolation unit is deposited, that is, there is a single-layer magnetic/isolation unit between adjacent two adhesive layers 1. However, the present disclosure is not limited thereto. In practical applications, each time the step S2 is performed, two or more layers of magnetic/isolation units may be deposited for, that is, there are two or more magnetic/isolated units continuously between adjacent two layers of adhesion layers 1.

**[0075]** It should be noted that, in the present embodiment, each of the magnetic laminated film units includes the adhesion layer 1 and the magnetic/isolation unit. However, the present

disclosure is not limited thereto, and in practical applications, each of the magnetic laminated film units includes an adhesion layer 1, a magnetic/isolation unit, and a magnetic film layer 2.

**[0076]** As another technical solution, the present disclosure also provides a magnetic thin film laminated structure including an adhesion layer 1 and a magnetic/isolation unit. The magnetic/isolation unit includes at least one pair of a magnetic film layer 2 and an isolation layer 3 that are alternately arranged.

**[0077]** Optionally, the magnetic film layer 2 is located on the adhesion layer, and the isolation layer 3 is located on the magnetic film layer 2.

**[0078]** Alternatively, as shown in FIG. 3, a magnetic film layer 2 is further disposed on the top layer of the magnetic thin film laminated structure (including at least one pair of magnetic film layer 2 and the isolation layer 3 that are alternately disposed).

**[0079]** Preferably, as shown in FIG. 4, the magnetic thin film laminated structure includes M magnetic laminated film units, that is, a first magnetic laminated film unit 100, a second magnetic laminated film unit 200, ..., a Mth the magnetic laminated film unit, where M is an integer greater than 1. For each of the magnetic laminated film units, an adhesion layer 1 and a magnetic/isolation unit are included. The magnetic/isolation unit includes at least one pair of magnetic film layer 2 and the isolation layer 3 that are alternately arranged. Alternatively, the magnetic film layer 2 is located on the adhesion layer, and the isolation layer 3 is located on the magnetic film layer 2. Preferably, a number of pairs of the isolation layer 3 and the magnetic film layer 2 is two to fifty. A sputtering thickness of the adhesion layer 1 ranges from 3 to 50 nm.

**[0080]** By adopting the structure of the multilayer magnetic thin film laminated structure, the total thickness of the magnetic thin film laminated structure can be further increased, thereby broadening the range of application frequency of the inductive device fabricated therefrom. Preferably, the total thickness of the magnetic thin film laminated structure ranges from 400 to 3000 nm. Preferably, the application frequency of the inductive device fabricated by the above magnetic thin film laminated structure ranges from 100 MHz to 5 GHz.

**[0081]** Further, in the present embodiment, a single layer of magnetic/isolation unit is provided between the adjacent two adhesive layers 1. However, the present disclosure is not limited thereto, and in practical applications, two or more magnetic/isolated units that are continuously disposed may be provided between adjacent two adhesive layers 1.

**[0082]** It should be noted that, in the present embodiment, each of the magnetic laminated film units includes the adhesion layer 1 and the magnetic/isolation unit. However, the present disclosure is not limited thereto, and in practical applications, each of the magnetic laminated film units may further include an adhesion layer 1, a magnetic/isolation unit, and a magnetic film layer 2.

**[0083]** In the deposition method of the magnetic thin film laminated structure provided by the present disclosure, the magnetic/isolation unit is deposited on the adhesion layer, and the adhesion layer can adjust the tensile stress of the magnetic thin film laminated structure caused by the tensile stress of the magnetic film layer to avoid a phenomenon that tensile stress of the magnetic thin film laminated structure is too big, thereby making it possible to obtain a magnetic thin film laminated structure having a large total thickness, broadening the application frequency range of the inductive device fabricated therefrom; and, in addition, due to the stress adjustment

effect of the adhesive layer on the magnetic thin film laminated structure, a large-thickness magnetic laminated film structure can be fabricated on the workpiece to be processed, thereby avoiding cracking and shedding.

**[0084]** The magnetic thin film laminated structure provided by the embodiment of the present disclosure has a magnetic/isolation unit deposited on the adhesive layer 1, and the adhesive layer 1 can adjust the tensile stress of the magnetic thin film laminated structure caused by the tensile stress of the magnetic film layer 2. The total thickness of the magnetic thin film laminated structure is increased, thereby broadening the application frequency range of the inductor device fabricated therefrom.

**[0085]** As another technical solution, the present disclosure also provides a micro-inductive device including a magnetic core fabricated by the above-mentioned magnetic thin film laminated structure provided by the present disclosure. The total thickness of the magnetic thin film laminated structure is increased, which broadens the application frequency range of the inductive device. For example, the application frequency of the micro-inductive device can range from 100 MHz to 5 GHz.

**[0086]** It should be understood that the above embodiments are merely exemplary embodiments to explain the principles of the disclosure, but the present disclosure is not limited thereto. Various modifications and improvements can be made by those skilled in the art without departing from the spirit and scope of the disclosure, and such modifications and improvements are also considered to be within the scope of the disclosure.

## CLAIMS

### WHAT IS CLAIMED IS:

1. A deposition method of a magnetic thin film laminated structure, comprising steps of:  
  
S1, depositing an adhesive layer on a workpiece to be processed; and  
  
S2, depositing a magnetic/isolation unit on the adhesion layer, the magnetic/isolation unit including at least one pair of magnetic film layer and an isolation layer disposed alternately.
2. The deposition method of the magnetic thin film laminated structure according to claim 1, wherein in the step S2, the magnetic film layer is deposited on the adhesive layer, and the isolation layer is deposited on the magnetic film layer.
3. The deposition method of the magnetic thin film laminated structure according to claim 1, wherein the step S1 and the step S2 are alternately performed at least twice.
4. The deposition method of the magnetic thin film laminated structure according to claim 1, further comprising a step S3: depositing a layer of the magnetic film on the magnetic/isolation unit.
5. The deposition method of the magnetic thin film laminated structure according to claim 4, wherein the step S1, the step S2, and the step S3 are alternately performed at least twice.

6. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein the adhesive layer is made of a material having compressive stress.

7. The deposition method of the magnetic thin film laminated structure according to any one of claims 6 to 4, wherein the material having compressive stress comprises a Ta film, a TaN film or a TiN film.

8. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein in the step S1, the adhesive layer is deposited by a sputtering process, and in the sputtering process, a target is electrically connected to a pulsed direct current (DC) power source, and a sputtering power output by the pulsed DC power is less than or equal to 15 kW; or

the target is electrically connected to a radio frequency (RF) power source, and a sputtering power of the RF power output is less than or equal to 3 kW; or

the target is electrically connected to a DC power source, and a sputtering power of the DC power output is less than or equal to 20 kW.

9. The deposition method of the magnetic thin film laminated structure according to claim 8, wherein:

in a scenario that the target is electrically connected to the pulsed DC power source, the sputtering power output by the pulsed DC power source ranges from 3 to 10 kW; or

in a scenario that the target is electrically connected to the RF power source, the sputtering power output by the RF power source ranges from 0.3 to 1.5 kW; or

in a scenario that the target is electrically connected to a DC power source, the sputtering power output by the DC power source ranges from 15 to 19 kW.

10. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein in the step S1, the adhesive layer is deposited by a sputtering process, and

a process pressure of the sputtering process is less than or equal to 5 mTorr.

11. The deposition method of the magnetic thin film laminated structure according to claim 10, wherein the process pressure of the sputtering process ranges from 0.5 to 2 mTorr.

12. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein the magnetic film layer is made of a material having soft magnetic properties.

13. The deposition method of the magnetic thin film laminated structure according to claim 12, wherein the material having soft magnetic properties comprises a NiFe permalloy material, a CoZrTa amorphous material, a Co-based material, a Fe-based material, or a Ni-based material.

14. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 4, wherein in the step S2, the magnetic film layer is deposited by a sputtering process, and in the sputtering process, the target is electrically connected to an excitation power source;

a sputtering power output by the excitation power source is less than or equal to 2kw; and  
a process pressure of the sputtering process is less than or equal to 5 mTorr.

15. The deposition method of the magnetic thin film laminated structure according to claim 14, wherein the sputtering power ranges from 0.5 to 1.5 kW; and  
the process pressure of the sputtering process ranges from 0.3 to 3 mTorr.

16. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein, while the magnetic film layer is deposited, a bias magnetic field device is used to form a horizontal magnetic field in a vicinity of a wafer for depositing the magnetic thin film laminated structure, and the horizontal magnetic field is configured to cause the deposited magnetic film layer to have in-plane anisotropy.

17. The deposition method of the magnetic thin film laminated structure according to claim 1 to 5, wherein the isolation layer is made of a non-magnetic material.

18. The deposition method of the magnetic thin film laminated structure according to claim 17, wherein the non-magnetic material comprises Cu, Ta, SiO<sub>2</sub> or TiO<sub>2</sub>.

19. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein in the step S2, the isolation layer is deposited by a sputtering process, and in the sputtering process, a target is electrically connected to an excitation power source;

an excitation power output by the sputtering power is less than or equal to 5kw; and  
a process pressure of the sputtering process is less than or equal to 20 mTorr.

20. The deposition method of the magnetic thin film laminated structure according to claim 19, wherein

the sputtering power output by the excitation power source ranges from 1 to 2 kw; and  
the process pressure of the sputtering process ranges from 9 to 12 mTorr.

21. The deposition method of the magnetic thin film laminated structure according to any one of claims 1 to 5, wherein:

a thickness of the adhesion layer ranges from 50 to 300 nm;  
a thickness of the magnetic film layer ranges from 30 to 200 nm; and  
a thickness of the isolation layer ranges from 3 to 10 nm.

22. The deposition method of the magnetic thin film laminated structure according to claim 21, wherein:

the thickness of the adhesion layer ranges from 80 to 200 nm;  
the thickness of the magnetic film layer ranges from 50 to 150 nm; and  
the thickness of the isolation layer ranges from 5 to 8 nm.

23. A magnetic thin film laminated structure, comprising:  
an adhesive layer; and  
a magnetic/isolation unit, the magnetic/isolation unit including at least one pair of the magnetic film layer and the isolation layer disposed alternately.

24. The magnetic thin film laminated structure according to claim 23, wherein the magnetic film layer is located on the adhesive layer, and the isolation layer is located on the magnetic film layer.

25. The magnetic thin film laminated structure according to claim 23, comprising at least two magnetic laminated film units, wherein each of the magnetic laminated film units includes the adhesive layer and the magnetic/isolation unit.

26. The magnetic thin film laminated structure according to claim 23, wherein one magnetic film layer is further provided on a top layer of the magnetic thin film laminated structure.

27. The magnetic thin film laminated structure according to claim 23, comprising at least two magnetic laminated film units, wherein each of the magnetic laminated film units includes the adhesive layer, the magnetic/isolation unit, and the magnetic film layer.

28. The magnetic thin film laminated structure according to any one of claims 23 to 27, wherein a total thickness of the magnetic thin film laminated structure ranges from 400 to 3000 nm.

29. The magnetic thin film laminated structure according to any one of claims 23 to 27, wherein a number of pairs of the magnetic film layer and the isolation layer that are alternately disposed is two to fifty.

30. The magnetic thin film laminated structure according to any one of claims 23 to 27, wherein a thickness of the adhesive layer ranges from 3 to 50 nm.

31. A micro-inductive device comprising a magnetic core, wherein the magnetic core is fabricated by using a magnetic thin film laminated structure according to any one of claims 23-27, wherein an application frequency of the micro-inductive device ranges from 100MHz to 5GHz.