

ABSTRACT

Cosmetic Compositions with Improved Transfer Resistance

A cosmetic composition comprising:

- a) 1-70% volatile solvent;
- b) 0.1-15% silicone resin;
- c) 10-45% wax;
- d) 5-50% powder; and
- e) 1-30% oil

has improved transfer resistance over previously-known cosmetics. They may be prepared by grinding some of the dry components with the solvent and resin, adding the wax and oil followed by the remainder of the dry components. When filled into suitable receptacles, the composition may be used as a concealer, blusher, eye shadow, foundation, lipstick or the like.

This Sheet Has Been Replaced



57 4-811802

201 111 57