

SURFACE -TREATED CALCIUM CARBONATE AND ITS USE IN WATER PURIFICATION AND FOR THE DEWATERING OF SLUDGES AND SEDIMENTS

The invention relates to a process for the purification of water and/or dewatering of sludges and/or sediments, to the use of a surface-treated calcium carbonate for water
5 purification and/or dewatering of sludges and/or sediments, as well as to the use of a surface-treated calcium carbonate for reducing the amount of polymeric flocculation aids in water and/or sludges and/or sediments and to a composite material comprising a surface-treated calcium carbonate and impurities originated from different sources obtainable by said process.

10

Water pollution has posed a serious problem all over the world. In this regard, water pollution is suggested as being the leading cause of death and diseases in developing countries but also industrialized countries continue struggling with such pollution problems. In general, water, sludges and sediments are referred to as being polluted
15 when impaired by anthropogenic contaminants and either does not support a human use, such as serving as drinking water, and/or has negative impacts on aquatic and/or land based flora and fauna.

The specific contaminants or impurities leading to pollution in water, sludges and
20 sediments, include a wide variety of chemical substances, pathogens and physical or sensory changes such as elevated temperature and discoloration. In this regard, the chemical contaminants may include organic substances as well as inorganic substances. In particular, many of the inorganic components may also be naturally occurring (calcium salts, sodium salts, manganese salts etc.) so that their
25 concentration is often the key in determining what is a natural water, sludge, or sediment component and what is a contaminant. Sources of such water, sludge or sediment pollutions typically originate from urban waste waters, i.e. domestic waste water or a mixture of domestic waste water with industrial waste water and/or run-off rain water, as well industrial waste waters, i.e. any waste water which is discharged
30 from premises used for carrying on any trade or industry.

In the art, several approaches for the purification of polluted water, sludges or sediments have been proposed. For instance, one approach involves the addition of flocculants to remove or at least to reduce the amount of contaminants such as fine solids, micro-organisms and dissolved inorganic and organic materials. Flocculation
5 refers to a process where dissolved compounds and/or colloidal particles are removed from the solution in the form of flocs or "flakes." The term is also used to refer to the process by which fine particulates are caused to clump together into flocs. The flocs may then float to the top of the liquid, settle to the bottom of the liquid, or can be readily filtered from the liquid.

10

Flocculants, or flocculating agents, are chemicals that are used to promote flocculation. Flocculants are used in water treatment processes to improve the sedimentation or filterability of small particles. Many flocculants are multivalent cations such as aluminium, iron, calcium or magnesium. These positively charged
15 ions interact with negatively charged particles and molecules to reduce the barriers to aggregation. In addition, many of these chemicals, under appropriate pH and other conditions, react with water to form insoluble hydroxides which, upon precipitating, link together to form long chains or meshes, physically trapping small particles into the larger floc.

20

Common flocculants or coagulants used are aluminium sulphate or polyaluminium chloride (PAC). Aluminium sulphate reacts with water to form flocs of aluminium hydroxide. Coagulation with aluminum compounds may leave a residue of aluminium in the finished water, which can be toxic to humans at high
25 concentrations. In solutions of polyaluminium chloride (PAC), aluminium ions have formed into polymers consisting of clusters of ions bridged by oxygen atoms. PAC is used e.g. for the treatment of brown drinking water comprising organic materials such as leaves and/or inorganic materials such as iron and manganese compounds which cause the brown discolouration. However, PAC is generally not sufficient to
30 remove all brown discolouration from the water.

Iron(III) chloride is another common coagulant. Iron(III) coagulants work over a larger pH range than aluminium sulphate but are not effective with many source waters. Coagulation with iron compounds typically leaves a residue of iron in the finished water. This may impart a slight taste to the water, and may cause brownish stains on porcelain fixtures. Furthermore, iron(III) chloride impart corrosion risks in the water treatment system.

Further well-known flocculants for the water treatment based on a high specific surface area such as activated carbon or bentonite have the general drawback that they are very difficult to separate after the adsorption of the substance to be removed from the medium due to their finely divided state.

The skilled man also knows US 2006/0273039 A1, which refers to a product and an apparatus for cleaning water or industrial and sewage waste water includes a mixture of diatomite that is heated and stirred to impart an enhanced negative electrical charge to the diatomite. EP 2 0111 766 A1 relates to a process for reducing the amount of organic components in water, wherein a surface-reacted natural calcium carbonate and a hydrophobic adsorbent, selected from the group consisting of talc, hydrophobised calcium carbonate, hydrophobised bentonite, hydrophobised kaolinite, hydrophobised glass, or any mixture thereof, are brought into contact with the water to be purified, the surface-reacted natural calcium carbonate being the reaction product of a natural calcium carbonate with an acid and carbon dioxide, which is formed in situ by the acid treatment and/or supplied externally, and the surface-reacted natural calcium carbonate being prepared as an aqueous suspension having a pH of greater than 6.0, measured at 20 °C. EP 1 982 759 A1 relates to a process for the purification of water, wherein a surface-reacted natural calcium carbonate is brought into contact with the water to be purified, the surface-reacted natural calcium carbonate being the reaction product of a natural calcium carbonate with an acid and carbon dioxide, which is formed in situ by the acid treatment and/or

- supplied externally. EP 1 974 807 A1 relates to the removal of endocrine disrupting compounds from an aqueous medium by adding surface-reacted natural calcium carbonate or an aqueous suspension comprising surface-reacted calcium carbonate and having a pH greater than 6.0 measured at 20 °C, to the medium, wherein the
- 5 surface-reacted calcium carbonate is a reaction product of natural calcium carbonate with carbon dioxide and one or more acids. EP 1 974 806 A1 relates to a process for the purification of water by adding surface-reacted natural calcium carbonate or an aqueous suspension comprising surface-reacted calcium carbonate and having a pH greater than 6.0 measured at 20 °C, to the medium, wherein the surface-reacted
- 10 calcium carbonate is a reaction product of natural calcium carbonate with carbon dioxide and one or more acids. EP 1 493 716 A1 refers to a wastewater treatment process, wherein wastewater containing fluoride ion and/or phosphate ion is added with a calcium-containing compound, and then added with a film-forming agent and complexing agent.
- 15
- One problem with the addition of such flocculants, however, is that it tends to merely bind and agglomerate organic contaminants while inorganic impurities are still finely dispersed in the water sample. Furthermore, the flocculated material needs to be removed from the water phase by a dewatering process such as filtration or
- 20 centrifugation so that the obtained filter cake can be further disposed by e.g. burning. However, due to the overall incomplete flocculation process the water content in such obtained filter cake is comparatively high resulting in a dramatically increased energy consumption on combustion.
- 25
- Another strategy involves the use of polymeric flocculation aids in conjunction with other inorganic flocculants. However, when used in combination with one of the above-mentioned inorganic flocculants such as iron(III) chloride, the polymeric flocculation aid needs to be cationic, i.e. needs to have a positive overall charge, for effectively acting as a flocculation aid. The long chains of positively charged
- 30 polymers can help to strengthen the floc making it larger, faster settling and easier to

filter out. Due to the restriction to cationic polymers, the process flexibility is reduced.

5 A known polymeric flocculation aid is polyacrylamide. By using of specific comonomers, anionic as well as cationic, polyacrylamide can be provided. However, as already indicated above, when used in combination with inorganic flocculants such as iron(III) chloride, only cationic polyacrylamide is effective.

10 However, one problem with this approach is that these polymeric flocculation aids are usually overdosed to a large extent in order to ensure the agglomeration of all fine solid particles in the water to be treated. Thus, after the separation of the flocculated material from the water phase, the content of polyacrylamide in the filtrate is usually increased due to the high amounts of polymeric flocculating aids used. However, as there are severe environmental concerns regarding water
15 containing polymeric flocculation aids, and especially polyacrylamide, the filtrate cannot be readily disposed in nature and, thus, further time and cost consuming purification steps are required to remove the polymeric flocculation aid from the filtrate.

20 Therefore, there is a continuous need for alternative water treatment processes, which provide a better performance than existing processes and effectively decrease the concentration of impurities and especially inorganic impurities and the concentration of polymeric flocculation aids in waste water to be treated but still enables easy performance at low cost.

25

This and other objects are solved by the subject-matter of the present invention. According to a first aspect of the present invention, a process for the purification of water and/or dewatering of sludges and/or sediments, comprising the following steps of:

- a) providing water to be purified and/or sludge and/or sediment to be dewatered comprising impurities;
- b) providing at least one surface-treated calcium carbonate, wherein at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer, and
- c) contacting the water and/or sludge and/or sediment of step a) with the at least one surface-treated calcium carbonate of step b) for obtaining a composite material of surface-treated calcium carbonate and impurities.

10 The inventors surprisingly found that the foregoing process according to the present invention leads to an improved quality of the obtained filter cake and purified water providing a lower amount of polymeric flocculation aids than water, sludges and/or sediments treated the same way but without contacting it with the at least one surface-treated calcium carbonate (step c)). More precisely, the inventors found that

15 the quality of water and of a filter cake being obtained by a purification process can be improved by a defined calcium carbonate that is surface-treated with cationic polymers.

It should be understood that for the purposes of the present invention, the following

20 terms have the following meaning:

The term "purification" in the meaning of the present invention refers to the removal of harmful compounds and/or other compounds not tolerated in the water.

Furthermore, the term refers to the reduction in concentration of naturally occurring

25 compounds in the water.

The term "dewatering" in the meaning of the present invention refers to the removal of residual liquid from sludges and/or sediments.

The term "impurities" in the meaning of the present invention refers to naturally occurring compounds, wherein their concentration in the water and/or sludge and/or sediment is above the natural concentration and/or compounds that are not naturally occurring.

5

The term "calcium carbonate" in the meaning of the present invention refers to ground or natural calcium carbonate (GCC), and/or synthetic or precipitated calcium carbonate (PCC) and/or surface modified calcium carbonate (MCC). "Ground calcium carbonate" (GCC) in the meaning of the present invention is a calcium carbonate obtained from natural sources, such as limestone, marble or chalk or dolomite, and processed through a treatment such as grinding, screening and/or fractionizing by a wet and/or dry process, for example, by means of a cyclone or classifier. "Precipitated calcium carbonate" (PCC) in the meaning of the present invention is a synthesized material, generally obtained by precipitation following reaction of carbon dioxide and lime in an aqueous environment or by precipitation of a calcium and carbonate ion source in water. "Surface-modified calcium carbonate" (MCC) in the meaning of the present invention refers to a natural calcium carbonate and/or precipitated calcium carbonate obtained by reacting it with an acid or ion and with carbon dioxide prior to the preparation of the surface-treated calcium carbonate, wherein the carbon dioxide is formed in situ by the acid treatment and/or is supplied from an external source.

The term "surface-treated" calcium carbonate in the meaning of the present invention refers to a ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate that has been processed with cationic polymers through an additional treatment step in order to render the surface of the calcium carbonate particles more cationic.

The term "cationic polymer" in the meaning of the present invention refers to any polymer providing for a positive overall charge when bound to calcium carbonate

30

particles. Thus, the presence of anionic monomer units is not excluded as long as there are still sufficient cationic monomer units providing a positive overall charge. The same applies for amphoteric polymers which provide for an overall positive charge when bound to the calcium carbonate particles.

5

The term "accessible surface area" in the meaning of the present invention refers to the surface of the calcium carbonate particle that is accessible or exposed to the cationic polymer applied by mixing and/or coating techniques known to the skilled person and thereby forming a monolayer of cationic polymer on the surface of the calcium carbonate particle. In this regard, it should be noted that the amount of cationic polymer required for full saturation of the accessible surface area is defined as a monolayer concentration. Higher concentrations thus can be chosen thereby forming bilayered or multi-layered structures on the surface of the calcium carbonate particle. Such monolayer concentrations can be readily calculated by the skilled person, based on the publication of Papirer, Schultz and Turchi (Eur. Polym. J., Vol. 20, No. 12, pp. 1155-1158, 1984).

Another aspect of the present invention is directed to the use of a surface-treated calcium carbonate for water purification and/or dewatering of sludges and/or sediments, wherein at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer. A further aspect of the present invention is directed to the use of a surface-treated calcium carbonate for reducing the amount of polymeric flocculation aids in water and/or sludges and/or sediments, wherein at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer.

It is preferred that the surface-treated calcium carbonate comprises ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate, preferably surface-modified calcium carbonate. It is also preferred that the source of ground calcium carbonate (GCC) is selected from marble, chalk, calcite,

dolomite, limestone and mixtures thereof and/or the precipitated calcium carbonate (PCC) is selected from one or more of the aragonitic, vateritic and calcitic mineralogical crystal forms. It is further preferred that the calcium carbonate particles of the surface-treated calcium carbonate have a weight median particle diameter d_{50} value of between 0.04 μm and 250 μm , preferably between 0.06 μm and 225 μm , more preferably between 1 μm and 200 μm , even more preferably between 1 μm and 150 μm , and most preferably between 1 μm and 100 μm and/or the calcium carbonate particles of the surface-treated calcium carbonate have a specific surface area of from 1 to 250 m^2/g , more preferably from 20 to 200 m^2/g , even more preferably from 30 to 150 m^2/g and most preferably from 30 to 100 m^2/g . It is still further preferred that the coating of the surface-treated calcium carbonate comprises at least one cationic polymer having a positive charge density in the range of 1 mEq/g and 15 mEq/g, more preferably in the range of 2.5 mEq/g and 12.5 mEq/g and most preferably in the range of 5 mEq/g and 10 mEq/g and/or the coating of the surface-treated calcium carbonate comprises at least one cationic polymer in which at least 60 % of the monomer units have a cationic charge, preferably at least 70 %, more preferably at least 80 %, even more preferably at least 90 % and most preferably equal to 100 %. It is even further preferred that the coating of the surface-treated calcium carbonate comprises at least one cationic polymer having a weight average molecular weight M_w of below 1,000,000 g/mole, more preferably from 50,000 to 750,000 g/mole, even more preferably from 50,000 to 650,000 g/mole and most preferably from 100,000 to 300,000 g/mole. It is also preferred that the coating of the surface-treated calcium carbonate comprises at least one cationic polymer being a homopolymer based on monomer units selected from the group consisting of diallyldialkyl ammonium salts; tertiary and quaternized amines; quaternized imines; acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; styrene; methyl methacrylate and vinyl acetate, preferably diallyldialkyl ammonium salts and acrylic acid and most preferably diallyldimethyl ammonium chloride and acrylic acid. It is also preferred that the coating of the surface-treated calcium carbonate comprises at

least one cationic polymer being a copolymer based on monomer units selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from the group consisting of acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl
5 acrylate; styrene; methyl methacrylate; vinyl acetate and mixtures thereof, preferably the monomer units are selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from acrylamide and acrylic acid. It is further preferred that at least 10 % of the accessible surface area of the calcium carbonate is covered by a coating comprising a cationic polymer, preferably at least 20 % of the
10 accessible surface area, more preferably at least 30 %, even more preferably at least 40 % and most preferably at least 50 % of the accessible surface area. It is still further preferred that the surface-treated calcium carbonate is in powder form and/or in the form of granules or in the form of slurry. In a further embodiment the surface-treated calcium carbonate is used in combination with at least one polymeric
15 flocculation aid. The polymeric flocculation aid has a weight average molecular weight M_w in the range from 100,000 to 10,000,000 g/mole, preferably in the range from 300,000 to 5,000,000 g/mole, more preferably in the range from 300,000 to 1,000,000 g/mole and most preferably in the range from 300,000 to 800,000 g/mole and/or the polymeric flocculation aid is non-ionic or ionic, preferably a cationic or
20 anionic polymer selected from polyacrylamides, polyacrylates, poly(diallyldimethylammonium chloride), polyethyleneimines, polyamines, starches and mixtures thereof.

A still further aspect of the present invention is directed to a composite material
25 comprising a surface-treated calcium carbonate and impurities obtainable by the process.

When in the following reference is made to preferred embodiments or technical
details of the inventive process for the purification of water and/or dewatering of
30 sludges and/or sediments, it is to be understood that these preferred embodiments or

technical details also refer to the inventive use of the surface-treated calcium carbonate for water purification and/or dewatering of sludges and/or sediments, to the inventive use of the surface-treated calcium carbonate for reducing the amount of polymeric flocculation aids in water and/or sludges and/or sediments as well as to the composite material comprising the surface-treated calcium carbonate and impurities defined herein and vice versa (as far as applicable). If, for example, it is set out that the surface-treated calcium carbonate provided in the inventive process preferably comprises ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate, also the inventive uses as well as the inventive composite material preferably comprise ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate.

According to one preferred embodiment of the inventive process, the water and/or sludge and/or sediment of step a) is selected from industrial waste water, drinking water, urban waste water, sludge such as harbour sludge, river sludge, coastal sludge or digested sludge, waste water or process water from breweries or other beverage industries, waste water or process water in the paper industry, colour-, paints-, or coatings industry, agricultural waste water, slaughterhouse waste water, leather industry waste water and leather tanning industry.

According to another preferred embodiment of the inventive process, the at least one surface-treated calcium carbonate of step b) comprises ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate, preferably surface-modified calcium carbonate.

According to yet another preferred embodiment of the inventive process, the source of ground calcium carbonate (GCC) is selected from marble, chalk, calcite, dolomite, limestone and mixtures thereof and/or the precipitated calcium carbonate (PCC) is selected from one or more of the aragonitic, vateritic and calcitic mineralogical crystal forms.

According to one preferred embodiment of the inventive process, the calcium carbonate particles of the at least one surface-treated calcium carbonate have a weight median particle diameter d_{50} value of between 0.01 μm and 250 μm ,
5 preferably between 0.06 μm and 225 μm , more preferably between 1 μm and 200 μm , even more preferably between 1 μm and 150 μm and most preferably between 1 μm and 100 μm and/or the calcium carbonate particles of the at least one surface-treated calcium carbonate have a specific surface area of from 1 to 250 m^2/g , more preferably from 10 to 200 m^2/g , even more preferably from 20 to 150 m^2/g and
10 most preferably from 30 to 100 m^2/g .

According to another preferred embodiment of the inventive process, the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer having a positive charge density in the range of 1 mEq/g and 15 mEq/g,
15 more preferably in the range of 2.5 mEq/g and 12.5 mEq/g and most preferably in the range of 5 mEq/g and 10 mEq/g and/or the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer in which at least 60 % of the monomer units have a cationic charge, preferably at least 70 %, more preferably at least 80 %, even more preferably at least 90 % and most preferably equal to
20 100 %.

According to yet another preferred embodiment of the inventive process, the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer having a weight average molecular weight M_w of below 1,000,000 g/mole,
25 more preferably from 50,000 to 750,000 g/mole, even more preferably from 50,000 to 650,000 g/mole and most preferably from 100,000 to 300,000 g/mole.

According to one preferred embodiment of the inventive process, the coating of the at least one surface-treated calcium carbonate comprises at least one cationic

polymer being a homopolymer based on monomer units selected from the group consisting of diallyldialkyl ammonium salts; tertiary and quaternized amines; quaternized imines; acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; 5 styrene; methyl methacrylate and vinyl acetate, preferably diallyldialkyl ammonium salts and acrylic acid and most preferably diallyldimethyl ammonium chloride and acrylic acid.

According to another preferred embodiment of the inventive process, the coating of 10 the at least one surface-treated calcium carbonate comprises at least one cationic polymer being a copolymer based on monomer units selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from the group consisting of acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; 15 styrene; methyl methacrylate; vinyl acetate and mixtures thereof, preferably the monomer units are selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from acrylamide and acrylic acid.

According to yet another preferred embodiment of the inventive process, at least 20 10 % of the accessible surface area of the calcium carbonate is covered by a coating comprising a cationic polymer, preferably at least 20 % of the accessible surface area, more preferably at least 30 %, even more preferably at least 40 % and most preferably at least 50 % of the accessible surface area.

25 According to one preferred embodiment of the inventive process, the at least one surface-treated calcium carbonate is in powder form and/or in the form of granules or in the form of slurry.

According to another preferred embodiment of the inventive process, the process 30 further comprises step d) of contacting the water and/or sludge and/or sediment to be

purified of step a) with at least one polymeric flocculation aid. It is preferred that the polymeric flocculation aid has a weight average molecular weight M_w in the range from 100,000 to 10,000,000 g/mole, preferably in the range from 300,000 to 5,000,000 g/mole, more preferably in the range from 300,000 to 1,000,000 g/mole and most preferably in the range from 300,000 to 800,000 g/mole and/or the polymeric flocculation aid is non-ionic or ionic, preferably a cationic or anionic polymer selected from polyacrylamides, polyacrylates, poly(diallyldimethylammonium chloride), polyethyleneimines, polyamines, starches and mixtures thereof.

10

According to yet another preferred embodiment of the inventive process, step c) and step d) are carried out simultaneously or separately, preferably separately.

15

According to one preferred embodiment of the inventive process, step c) and/or step d) are carried out by at least partially covering the surface of the water and/or sludge and/or sediment to be treated of step a) with the at least one surface-treated calcium carbonate of step b) and/or mixing the water and/or sludge and/or sediment to be treated of step a) with the at least one surface-treated calcium carbonate of step b).

20

According to another preferred embodiment of the inventive process, step c) and/or step d) are repeated one or more times.

25

According to yet another preferred embodiment of the inventive process, the composite material of the at least one surface-treated calcium carbonate and impurities is removed from the water and/or sludge and/or sediment phase by filtration, sedimentation and/or centrifugation.

30

According to one preferred embodiment of the inventive process, the water and/or sludge and/or sediment obtained by the process contains an amount of polymeric flocculation aid of at least 10 wt.-%, preferably at least 20 wt.-%, more preferably at

least 30 wt.-%, even more preferably at least 40 wt.-%, still more preferably at least 50 wt.-% and most preferably at least 60 wt.-% below the amount of polymeric flocculation aid contained in a corresponding water and/or sludge and/or sediment being treated the same way but in the absence of the at least one surface-treated
5 calcium carbonate.

As set out above, the inventive process for the purification of water and/or dewatering of sludges and/or sediments comprises the steps a), b) and c). In the following, it is referred to further details of the present invention and especially the
10 foregoing steps of the inventive process for the purification of water providing improved filter cake and water quality in that the amount of polymeric flocculation aids is reduced.

15 Step a): provision of water and/or sludge and/or sediment to be purified

According to step a) of the process of the present invention, water to be purified and/or sludge and/or sediment to be dewatered is provided, wherein the water and/or sludge and/or sediment comprises impurities.

20

The water and/or sludge and/or sediment treated by the process of the present invention is preferably selected from industrial waste water, drinking water, urban waste water, sludge such as harbour sludge, river sludge or digested sludge, waste water or process water from breweries or other beverage industries, waste water or
25 process water in the paper industry, colour-, paints-, or coatings industry, agricultural waste water, slaughterhouse waste water, leather industry waste water and leather tanning industry.

Within the context of the present invention, the term "process water" refers to any water which is necessary to run or maintain an industrial process. The term "waste water" refers to any water drained from its place of use, e.g. an industrial plant.

- 5 The term "sludge" in the meaning of the present invention refers to any kind of sludge, e.g. primary sludge, biological sludge, mixed sludge, digested sludge, physico-chemical sludge and mineral sludge. In this regard, primary sludge comes from the settling process and usually comprises large and/or dense particles. Biological sludge comes from the biological treatment of wastewater and is usually
10 made of a mixture of microorganisms. These microorganisms, mainly bacteria, amalgamate in bacterial flocs through the synthesis of exo-polymers. Mixed sludge is a blend of primary and biological sludges and usually comprises 35 wt.-% to 45 wt.-% of primary sludge and 65 wt.-% to 55 wt.-% of biological sludge. Digested sludge comes from a biological stabilizing step in the process called digestion and is usually
15 performed on biological or mixed sludge. It can be done under different temperatures (mesophilic or thermophilic) and with or without the presence of oxygen (aerobic or anaerobic). Physico-chemical sludge is the result of a physico-chemical treatment of the wastewater and is composed of flocs produced by the chemical treatment. Mineral sludge is given to sludge produced during mineral processes such as quarries
20 or mining beneficiation processes and essentially comprises mineral particles of various sizes).

Within the context of the present invention, the term "sediment" refers to any water containing particles of naturally occurring material.

25

Preferably, the water and/or sludge and/or sediment to be treated comprises organic impurities and/or inorganic impurities.

- In accordance with the process of the present invention, the water and/or sludge
30 and/or sediment to be treated comprise inorganic impurities. The term "inorganic

impurities" in the meaning of the present invention refers to naturally occurring compounds, wherein their concentration in the water and/or sludge and/or sediment is above the natural concentration typically observed in water and/or compounds that are not naturally occurring.

5

In particular, many inorganic impurities are typically present as dissolved inorganics, i.e. inorganic substances in solution, such as bicarbonates of calcium and/or magnesium, which give rise to temporary hardness, while the sulfates and chlorides cause permanent hardness. Other inorganic impurities present in water and/or sludge and/or sediment include carbon dioxide, which dissolves in water to give weakly acidic carbonic acid, sodium salts, silicates leached from sandy river beds, chlorides from saline intrusion, aluminium from dosing chemicals and minerals, phosphates from fertilizers, fluoride compounds derived from additives promoting strong teeth and as discharge from fertilizer and aluminum factories, nitrate and nitrite compounds derived as runoff from fertilizer use as well as leaking from septic tanks, sewage or chlorine derived from the chlorination of the municipal system to combat water-borne diseases and cyanide compounds derived as discharge from steel and metal factories as well as plastic and fertilizer factories.

10

15

20

25

30

If the water and/or sludge and/or sediments to be treated comprises heavy metal impurities, they are typically ferrous and ferric iron compounds derived from minerals and rusty iron pipes; antimony compounds derived as discharge from petroleum refineries, fire retardants or electronics; arsenic compounds derived from erosion of natural deposits, runoff from orchards, runoff from glass and electronics production wastes; barium compounds as discharge of drilling wastes and from metal refineries; beryllium compounds derived as discharge from metal refineries and coal-burning factories as well as electrical, aerospace, and defense industries; cadmium compounds derived from corrosion processes of galvanized pipes, discharge from metal refineries and runoff from waste batteries and paints; chromium compounds derived from discharge from steel and pulp mills; cobalt and nickel compounds

derived as discharge from metal refineries and runoff from waste batteries; copper and lead compounds derived from corrosion processes of household plumbing systems;; selenium compounds derived as discharge from petroleum refineries and mines such as mines for metal or metal ore extraction or any other mines producing
5 polluted sludge; thallium compounds derived as leaching from ore-processing sites as well as discharge from electronics, glass, and drug factories or zinc, or mercury compounds derived from mining, smelting metals (like zinc, lead and cadmium) and steel production, as well as burning coal and certain wastes can release zinc into the environment.

10

Furthermore, the water and/or sludge and/or sediment to be treated may also comprise organic impurities. In the context of the present invention, the term "organic impurities" has to be interpreted broadly and encompasses specific organic compounds such as surfactants, polycyclic compounds, cholesterol, or endocrine
15 disrupting compounds as well as more complex organic materials (e.g. organic material from microorganisms).

Impurities within the meaning of the present invention shall encompass organic, inorganic, biological, mineral impurities or combinations thereof, wherein said
20 impurities can be present in dissolved, dispersed, or emulsified forms as well as in colloidal form or adsorbed to solids, as well as in combination thereof, or still other forms.

Preferably, the water and/or sludge and/or sediment to be purified includes at least
25 one of the following organic impurities which are selected from the group consisting of surfactants; cholesterol; endocrine disrupting compounds; amino acids; proteins; carbohydrates; defoamers; sizing agents selected from the group consisting of alkyl ketene dimer (AKD), alkenyl succinic anhydride (ASA), or mixtures thereof; polyvinylacetates; polyacrylates, in particular polyacrylate latex; styrene butadiene

copolymers, in particular styrene butadiene latex; microorganisms; mineral oils; vegetable oils and fats; or any mixture thereof.

In another preferred embodiment of the process of the present invention, the organic
5 impurities also comprise pitch. The term "pitch" as used in the present invention refers to a specific type of organic material generated in the papermaking or pulping process. The primary fibre source in papermaking is wood, which is reduced to its constituent fibres during pulping by combinations of grinding, thermal and chemical treatment. During this process the natural resin contained within the wood is released
10 into the process water in the form of microscopic droplets. These droplets are referred to as pitch. The chemical composition of pitch is generally divided into four classes of lipophilic components: fats and fatty acids; steryl esters and sterols; terpenoids; and waxes. The chemical composition depends on the fibre source, such as variety of tree, and on the seasonal growth from which the sample is produced.

15

If the organic component is a surfactant, the surfactant can be ionic or non-ionic. If the surfactant is anionic, it can have a functional group selected from carboxylate, sulfate, or sulfonate. If the surfactant is cationic, its functional group can be a quaternary ammonium group.

20

If the water and/or sludge and/or sediment to be treated comprises endocrine disrupting compounds, they are preferably selected from the group comprising, e.g. endogenous hormones such as 17 β -estradiol (E2), estrone (E1), estriol (E3), testosterone or dihydro testosterone; phyto and myco hormones such as β -sitosterol,
25 genistein, daidzein or zeraleon; drugs such as 17 β -ethinylestradiol (EE2), mestranol (ME), diethylstilbestrol (DES), and industrial chemicals such as 4-nonyl phenol (NP), 4-tert-octyl phenol (OP), bisphenol A (BPA), tributyltin (TBT), methylmercury, phthalates, PAK or PCB.

- If the water and/or sludge and/or sediment to be treated comprises defoamer, it can be ethylene oxide glycol ether, a silicone oil based defoamer, a fatty acid ester defoamer, or any mixture thereof. The defoamer may be preferably selected from stickies. Stickies are potentially deposit-forming components originating from recycled paper. In general, examples are glues, hot-melt plastics, printing inks, and latex. The papermaking industry utilizes various amounts of recycled fiber or papers as a source of paper fiber furnish in the production of finished paper products. The recycled papers are often contaminated with the synthetic polymeric materials outlined above and these polymeric materials are referred to as stickies in the papermaking art. Stickies are different from pitch which is a naturally occurring resinous material from the extractive fraction of wood. Reference is made to E.L. Back and L.H. Allen, "Pitch Control, Wood Resin and Deresination", Tappi Press, Atlanta, 2000, wherein stickies are described in further detail.
- 15 If the water and/or sludge and/or sediment to be treated comprises microorganisms, they are preferably selected from bacteria, fungi, archaea or protists.

Preferred vegetable oils are edible oils such as coconut oil, corn oil, cottonseed oil, canola oil, palm oil, soybean oil, sunflower oil, or linseed oil.

- 20 The exact composition of the water and/or sludge and/or sediment to be purified and especially the amount of inorganic and/or organic impurities varies depending on the origin of the polluted water and/or sludge and/or sediment.

Step b): provision of at least one surface-treated calcium carbonate

According to step b) of the process of the present invention, at least one surface-
5 treated calcium carbonate is provided.

In accordance with the inventive process, at least 1 % of the accessible surface area
of the calcium carbonate is covered by a coating comprising at least one cationic
polymer.

10

In one preferred embodiment, the surface-treated calcium carbonate comprises
ground (or natural) calcium carbonate (GCC) or precipitated (or synthetic) calcium
carbonate (PCC) or surface-modified calcium carbonate (MCC). In another preferred
embodiment, the surface-treated calcium carbonate comprises a mixture of at least
15 two calcium carbonates selected from GCC, PCC and MCC. For example, the
surface-treated calcium carbonate comprises a mixture of GCC and PCC.

Alternatively, the surface-treated calcium carbonate comprises a mixture of GCC and
MCC. Alternatively, the surface-treated calcium carbonate comprises a mixture of
PCC and MCC.

20

In one especially preferred embodiment, the surface-treated calcium carbonate
comprises surface-modified calcium carbonate (MCC).

Ground (or natural) calcium carbonate (GCC) is understood to be a naturally
25 occurring form of calcium carbonate, mined from sedimentary rocks such as
limestone or chalk, or from metamorphic marble rocks. Calcium carbonate is known
to exist as three types of crystal polymorphs: calcite, aragonite and vaterite. Calcite,
the most common crystal polymorph, is considered to be the most stable crystal form
of calcium carbonate. Less common is aragonite, which has a discrete or clustered
30 needle orthorhombic crystal structure. Vaterite is the rarest calcium carbonate

polymorph and is generally unstable. Ground calcium carbonate is almost exclusively of the calcitic polymorph, which is said to be trigonal-rhombohedral and represents the most stable of the calcium carbonate polymorphs.

- 5 Preferably, the source of the ground calcium carbonate is selected from the group comprising marble, chalk, calcite, dolomite, limestone and mixtures thereof. In a preferred embodiment, the source of the ground calcium carbonate is calcite.

10 The term "source" of the calcium carbonate in the meaning of the present invention refers to the naturally occurring mineral material from which the calcium carbonate is obtained. The source of the calcium carbonate may comprise further naturally occurring components such as magnesium carbonate, alumino silicate etc.

15 Additionally or alternatively, the surface-treated calcium carbonate comprises a precipitated calcium carbonate (PCC). Calcium carbonate polymorphs of the PCC type often include, in addition to calcites, less stable polymorphs of the aragonitic-type, which has an orthorhombic, acicular crystal shape, and hexagonal vateritic-type, which has an even lower stability than aragonite. The different PCC forms may be identified according to their characteristic x-ray powder diffraction (XRD) peaks.

20 PCC synthesis most commonly occurs by a synthetic precipitation reaction that includes a step of contacting carbon dioxide with a solution of calcium hydroxide, the latter being most often provided on forming an aqueous suspension of calcium oxide, also known as burnt lime, and the suspension of which is commonly known as milk of lime. Depending on the reaction conditions, this PCC can appear in various

25 forms, including both stable and unstable polymorphs. Indeed, PCC often represents a thermodynamically unstable calcium carbonate material. When referred to in the context of the present invention, PCC shall be understood to mean synthetic calcium carbonate products obtained notably by carbonation of a slurry of calcium hydroxide, commonly referred to in the art as a slurry of lime or milk of lime when derived from

30 finely divided calcium oxide particles in water.

Preferred precipitated calcium carbonate is selected from aragonitic, vateritic or calcitic mineralogical crystal forms or mixtures thereof.

- 5 Additionally or alternatively, said GCC or PCC may be surface reacted to form a surface-modified calcium carbonate, which is a material comprising GCC and/or PCC and an insoluble, at least partially crystalline, non-carbonate calcium salt extending from the surface of at least part of the calcium carbonate. Such surface-modified products may, for example, be prepared according to WO 00/39222,
10 WO 2004/083316, WO 2005/121257, WO 2009/074492, EP 2 264 108 A1, EP 2 264 109 A1.

For example, the surface-modified calcium carbonate is obtained by reacting a natural calcium carbonate and/or precipitated calcium carbonate with an acid and
15 with carbon dioxide prior to the preparation of the surface-treated calcium carbonate, wherein the carbon dioxide is formed in situ by the acid treatment and/or is supplied from an external source. The acid treatment can be carried out with an acid having a pK_a at 25 °C of 6 or less. If the pK_a at 25 °C is 0 or less, the acid is preferably selected from sulphuric acid, hydrochloric acid, or mixtures thereof. If the pK_a at 25
20 °C is from 0 to 2.5, the acid is preferably selected from H_2SO_3 , $M^+HSO_4^-$ (M^+ is an alkali metal ion selected from the group comprising sodium and potassium), H_3PO_4 , oxalic acid or mixtures thereof. If the pK_a at 25 °C is from 2.5 to 6, the acid is preferably selected from acetic acid, formic acid, propanoic acid and mixtures thereof. Furthermore, the subject-matters of EP 2 264 108 A1 and EP2 264 109 A1
25 relating to the acid treatment and the acid used for the acid treatment are hereby incorporated by reference in its entirety.

In an especially preferred embodiment, the calcium carbonate particles of the present surface-treated calcium carbonate have a weight median particle diameter d_{50} value
30 of from 0.01 μm to 250 μm before surface treatment, preferably from 0.06 μm to

225 μm , more preferably from 1 μm to 200 μm , even more preferably from 1 μm to 150 μm and most preferably from 1 μm to 100 μm , measured according to the sedimentation process. Calcium carbonate particles having a d_{98} of less than 100 microns, preferably of less than 85 microns may also be advantageous. Alternatively,
5 calcium carbonate particles having a d_{98} of less than 50 microns, preferably of less than 25 microns may be advantageous.

If the present surface-treated calcium carbonate comprises ground calcium carbonate, the calcium carbonate particles of the surface-treated calcium carbonate preferably
10 have a weight median particle diameter d_{50} value of from 0.04 μm to 250 μm before surface treatment, more preferably from 0.06 μm to 225 μm , even more preferably from 1 μm to 200 μm , still more preferably from 1 μm to 150 μm and most preferably from 1 μm to 100 μm , measured according to the sedimentation process.

15 If the present surface-treated calcium carbonate comprises precipitated calcium carbonate, the calcium carbonate particles of the surface-treated calcium carbonate preferably have a weight median particle diameter d_{50} value of from 0.01 μm to 10 μm before surface treatment, more preferably from 0.02 μm to 5 μm , even more preferably from 0.02 μm to 2.5 μm and most preferably from 0.02 μm to 1 μm ,
20 measured according to the sedimentation process.

If the present surface-treated calcium carbonate comprises surface-modified calcium carbonate, the calcium carbonate particles of the surface-treated calcium carbonate preferably have a weight median particle diameter d_{50} value of from 0.5 μm to
25 150 μm before surface treatment, preferably from 0.5 μm to 100 μm , more preferably from 0.5 μm to 100 μm and most preferably from 1 μm to 50 μm , measured according to the sedimentation process.

As used herein and as generally defined in the art, the weight median particle
30 diameter " d_{98} " value is defined as the size at which 98 % (the mean point) of the

particle volume or mass is accounted for by particles having a diameter equal to the specified value. The weight median particle diameter was measured according to the sedimentation process. The sedimentation process is an analysis of sedimentation behaviour in a gravimetric field. The measurement is made with a SedigraphTM 5100
5 of Micromeritics Instrument Corporation.

The calcium carbonate particles of the present surface-treated calcium carbonate preferably have a specific surface area of from 1 m²/g to 250 m²/g before surface treatment, more preferably 10 m²/g to 200 m²/g, even more preferably 20 m²/g to
10 150 m²/g and most preferably 30 m²/g to 100 m²/g, measured using nitrogen and the BET process. For example, the calcium carbonate particles of the surface-treated calcium carbonate have a specific surface area of from 40 m²/g to 50 m²/g before surface treatment, e.g. a specific surface area of 45 m²/g. Alternatively, the calcium carbonate particles of the present surface-treated calcium carbonate have a specific
15 surface area of from 50 m²/g to 60 m²/g, e.g. a specific surface area of 56 m²/g.

If the present surface-treated calcium carbonate comprises ground calcium carbonate, the calcium carbonate particles of the surface-treated calcium carbonate preferably have a specific surface area of from 1 m²/g to 100 m²/g before surface treatment,
20 more preferably 1 m²/g to 75 m²/g, even more preferably 1 m²/g to 50 m²/g and most preferably 1 m²/g to 20 m²/g, measured using nitrogen and the BET process.

If the present surface-treated calcium carbonate comprises precipitated calcium carbonate, the calcium carbonate particles of the surface-treated calcium carbonate
25 preferably have a specific surface area of from 1 m²/g to 150 m²/g before surface treatment, more preferably 1 m²/g to 100 m²/g, even more preferably 1 m²/g to 70 m²/g and most preferably 1 m²/g to 50 m²/g, measured using nitrogen and the BET process.

If the present surface-treated calcium carbonate comprises surface-modified calcium carbonate, the calcium carbonate particles of the surface-treated calcium carbonate preferably have a specific surface area of from 1 m²/g to 250 m²/g before surface treatment, more preferably 1 m²/g to 200 m²/g, even more preferably 10 m²/g to 200 m²/g and most preferably 15 m²/g to 170 m²/g, measured using nitrogen and the BET process.

In one preferred embodiment, the calcium carbonate particles of the present surface-treated calcium carbonate have a specific surface area within the range of 1 m²/g to 250 m²/g and a weight median particle diameter d_{50} value within the range of 0.01 µm to 250 µm before surface treatment. Preferably, the specific surface area is within the range of 10 m²/g to 200 m²/g and the weight median particle diameter d_{50} value is within the range of 0.06 µm to 225 µm before surface treatment. More preferably, the specific surface area is within the range of 20 m²/g to 150 m²/g and the weight median particle diameter is within the range of 1 µm to 200 µm before surface treatment. Even more preferably, the specific surface area is within the range of 30 m²/g to 100 m²/g and the weight median particle diameter d_{50} value is within the range of 1 µm to 150 µm before surface treatment. Most preferably, the specific surface area is within the range of 30 m²/g to 100 m²/g and the weight median particle diameter d_{50} value is within the range of 1 µm to 100 µm before surface treatment. For example, the calcium carbonate particles of the present surface-treated calcium carbonate have a specific surface area within the range of 40 m²/g to 50 m²/g and a weight median particle diameter d_{50} value within the range of 1 µm to 50 µm. Alternatively, the calcium carbonate particles of the present surface-treated calcium carbonate have a specific surface area within the range of 50 m²/g to 60 m²/g and a weight median particle diameter d_{50} value within the range of 1 µm to 50 µm.

In accordance with the inventive process, at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer.

In this regard, the at least one cationic polymer being comprised in the coating of the surface-treated calcium carbonate may be selected from any cationic polymer having a positive charge density in the range of 1 mEq/g and 15 mEq/g. Preferably, the at least one cationic polymer is selected such that it has a positive charge density in the range of 2.5 mEq/g and 12.5 mEq/g and most preferably in the range of 5 mEq/g and 10 mEq/g.

For example, the at least one cationic polymer has a positive charge density in the range of 6 mEq/g and 8 mEq/g and most preferably in the range from 6 mEq/g and 7 mEq/g. Alternatively, the at least one cationic polymer has a positive charge density in the range of 7 mEq/g and 8 mEq/g.

Additionally or alternatively, the at least one cationic polymer being comprised in the coating of the surface-treated calcium carbonate is selected such that at least 60 % of the monomer units carry a cationic charge. Preferably, the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer in which at least 70 % of the monomer units have a cationic charge, more preferably at least 80 % and even more preferably at least 90 %. In one preferred embodiment of the present invention, the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer in which equal to 100 %, preferably 100 %, of the monomer units have a cationic charge.

In one preferred embodiment, the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer having a weight average molecular weight M_w of below 1,000,000 g/mole, more preferably from 50,000 to 750,000 g/mole, even more preferably from 50,000 to 650,000 g/mole and most preferably from 100,000 to 300,000 g/mole.

In the process of the present invention, the surface-treated calcium carbonate is covered by a coating comprising a homopolymer and/or a copolymer of the at least one cationic polymer.

5 In one preferred embodiment, the coating of the at least one surface-treated calcium carbonate comprises a homopolymer of the at least one cationic polymer. That is to say, the cationic polymer consists substantially, i.e. of equal or below than 99.5 wt.-%, of the respective monomer units.

10 In one preferred embodiment, only monomer units selected from the group consisting of diallyldialkyl ammonium salts, tertiary amines, quaternized amines, quaternized imines, acrylamide, methacrylamide, N,N-dimethyl acrylamide, acrylic acid, methacrylic acid, vinylsulfonic acid, vinyl pyrrolidone, hydroxyl ethyl acrylate, styrene, methyl methacrylate and vinyl acetate are detectable in the homopolymer.

15

In one preferred embodiment of the present invention, the coating of the at least one surface-treated calcium carbonate comprises a homopolymer based on diallyldialkyl ammonium salt monomers. In one preferred embodiment, the diallyldialkyl ammonium salt monomers are diallyldimethyl ammonium chloride.

20

In another preferred embodiment of the present invention, the coating of the at least one surface-treated calcium carbonate comprises a homopolymer based on acrylic acid monomers.

25 In case the cationic polymer is a copolymer, it is appreciated that the copolymer comprises monomers copolymerizable with suitable comonomers. Preferably, the cationic polymer being a copolymer according to this invention comprises, preferably consists of, monomer units selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from the group consisting of
30 acrylamide, methacrylamide, N,N-dimethyl acrylamide, acrylic acid, methacrylic

acid, vinylsulfonic acid, vinyl pyrrolidone, hydroxyl ethyl acrylate, styrene, methyl methacrylate, vinyl acetate and mixtures thereof.

For example, the coating of the surface-treated calcium carbonate may comprise a
5 cationic polymer as described as comb polymer in US 2009/0270543 A1. The
subject-matter of US 2009/0270543 A1 relating to the polymer is hereby
incorporated by reference in its entirety.

In one preferred embodiment, the cationic polymer is a copolymer prepared from
10 92 wt.-% methoxy polyethylene glycol methacrylate of molecular weight 2,000
g/mole and 8 wt.-% acrylic acid and at least partially neutralised by soda. In a further
preferred embodiment, the cationic polymer is a copolymer prepared from 92 wt.-%
methoxy polyethylene glycol methacrylate of molecular weight 2,000 g/mole and
8 wt.-% acrylic acid and totally neutralised by soda.

15 If the monomer and/or comonomer units of the homopolymer or copolymer are
diallyldialkyl ammonium salts, they are preferably selected from the group consisting
of diallyldimethyl ammonium bromide, diallyldimethyl ammonium chloride,
diallyldimethyl ammonium phosphate, diallyldiethyl ammonium sulfate,
20 diallyldiethyl ammonium bromide, diallyldiethyl ammonium chloride, diallyldiethyl
ammonium phosphate, diallyldiethyl ammonium sulphate, diallyldipropyl
ammonium bromide, diallyldipropyl ammonium chloride, diallyldipropyl ammonium
phosphate and diallyldipropyl ammonium sulphate. In one preferred embodiment, the
diallyldialkyl ammonium salt monomers are diallyldimethyl ammonium chloride
25 monomers.

In an especially preferred embodiment, the cationic polymer is a homopolymer based
on diallyldimethyl ammonium chloride (PolyDADMAC).

If the monomer and/or comonomer units of the homopolymer or copolymer are quaternized amines, they are preferably epichlorhydrin reaction products such as polyamine epichlorhydrin.

- 5 If the monomer and/or comonomer units of the homopolymer or copolymer are quaternized imines, they are preferably polyethyleneimine.

In one preferred embodiment, the cationic polymer of this invention being a copolymer comprising monomer units selected from diallyldialkyl ammonium salts
10 and methacrylic acid, and acrylamide or acrylic acid as comonomer units.

For example, the coating of the at least one surface-treated calcium carbonate comprises a copolymer of the at least one cationic polymer, wherein the monomer and comonomer units are derivable from diallyldialkyl ammonium salts and
15 acrylamide only. In one preferred embodiment, the cationic polymer being a copolymer of this invention comprises monomer and comonomer units derivable from diallyldimethyl ammonium chloride and acrylamide only. Alternatively, the coating of the at least one surface-treated calcium carbonate comprises a copolymer of the at least one cationic polymer, wherein the monomer and comonomer units are
20 derivable from methacrylic acid and acrylic acid only.

Additionally or alternatively, the coating of the at least one surface-treated calcium carbonate comprises a copolymer of the at least one cationic polymer, wherein the monomer and comonomer units are derivable from acrylic acid and acrylamide only.

25

Additionally, it is appreciated that the copolymer has preferably a comonomer content of more than 2.0 wt.-%, more preferably more than 5 wt.-%, yet more preferably more than 7.5 wt.-%. For example, the copolymer has preferably a comonomer content in the range between 2 wt.-% and 80 wt.-%, more preferably in
30 the range between 5 wt.-% and 60 wt.-% and most preferably in the range between

7.5 wt.-% and 40 wt.-%. The weight percentage is based on the total weight of the copolymer.

5 In one preferred embodiment, the coating of the at least one surface-treated calcium carbonate comprises a copolymer, wherein the molar ratio of monomer units and comonomer units is from 5:1 to 1:5, more preferably from 4:1 to 1:4, even more preferably from 3:1 to 1:3 and most preferably from 3:1 to 1:1.

10 In one preferred embodiment, the cationic polymer comprises a mixture of at least two cationic polymers. Preferably, if the cationic polymer comprises a mixture of at least two cationic polymers, one cationic polymer is a homopolymer based on diallyldimethyl ammonium chloride. Alternatively, if the cationic polymer comprises a mixture of at least two cationic polymers, one cationic polymer is a homopolymer based on acrylic acid.

15

In a further preferred embodiment, the cationic polymer comprises a mixture of two cationic polymers, wherein one cationic polymer is a homopolymer based on diallyldimethyl ammonium chloride and the other one is selected from the group consisting of a homopolymer based on acrylic acid, a copolymer based on
20 diallyldimethyl ammonium chloride and acrylamide and a copolymer based on methacrylic acid and acrylic acid. Alternatively, if the cationic polymer comprises a mixture of two cationic polymers, wherein one cationic polymer is a homopolymer based on acrylic acid, the other one is selected from the group consisting of a homopolymer based on diallyldimethyl ammonium chloride, a copolymer based on
25 diallyldimethyl ammonium chloride and acrylamide and a copolymer based on methacrylic acid and acrylic acid.

If the cationic polymer comprises a mixture of two cationic polymers, the molar ratio of the homopolymer based on diallyldimethyl ammonium chloride and the second
30 cationic polymer is from 99:1 to 1:99, more preferably from 50:1 to 1:50, even more

preferably from 25:1 to 1:25 and most preferably from 10:1 to 1:10. In one especially preferred embodiment of the present invention, the molar ratio of the homopolymer based on diallyldimethyl ammonium chloride and the second cationic polymer is from 90:1 to 1:1, more preferably from 90:1 to 10:1 and most preferably from 90:1 to 50:1.

In another preferred embodiment, the molar ratio of the homopolymer based on acrylic acid and the second cationic polymer is from 99:1 to 1:99, more preferably from 50:1 to 1:50, even more preferably from 25:1 to 1:25 and most preferably from 10:1 to 1:10. In one especially preferred embodiment of the present invention, the mole ratio of the homopolymer based on acrylic acid and the second cationic polymer is from 90:1 to 1:1, more preferably from 90:1 to 10:1 and most preferably from 90:1 to 50:1.

The at least one cationic polymer is preferably present in the coating covering the calcium carbonate in a quantity such that the total weight of said at least one cationic polymer on the surface of the surface-treated calcium carbonate product is between 0.01% w/w and 80 % w/w of the calcium carbonate.

In one preferred embodiment, the at least one cationic polymer is present in the coating covering the calcium carbonate in a quantity such that the total weight of said at least one cationic polymer on the surface of the surface-treated calcium carbonate product is less than 80 % w/w, more preferably less than 60 % w/w and most preferably less than 50 % w/w of the calcium carbonate.

In another preferred embodiment, the at least one cationic polymer is present in the coating covering at least 1 % of the accessible surface area of the calcium carbonate in an amount of about 0.1 wt.-% to 30 wt.-%, more preferably of about 0.1 wt.-% to 20 wt.-%, even more preferably of about 0.2 wt.-% to 15 wt.-% and most preferably of about 0.2 wt.-% to 10 wt.-%, based on the dry weight of the calcium carbonate.

Alternatively, at least 10 % of the accessible surface area of the calcium carbonate particles is covered by a coating comprising the at least one cationic polymer. In a preferred embodiment, at least 20 % of the accessible surface area of the calcium carbonate particles is covered by a coating comprising the at least one cationic polymer, preferably at least 30 % of the accessible surface area, more preferably at least 40 % of the accessible surface area and most preferably at least 50 % of the accessible surface area. In another preferred embodiment, at least 75 % of the accessible surface area of the calcium carbonate particles is covered by a coating comprising the at least one cationic polymer. For example, at least 90 % of the accessible surface area of the calcium carbonate particles is covered by a coating comprising the at least one cationic polymer.

In one preferred embodiment, at least 75 % of the aliphatic carboxylic acid accessible surface area of the calcium carbonate particles is covered by a coating comprising a homopolymer based on diallyldimethyl ammonium chloride. In another preferred embodiment, at least 75 % of the aliphatic carboxylic acid accessible surface area of the calcium carbonate particles is covered by a coating comprising a homopolymer based on acrylic acid.

In one preferred embodiment, the at least one cationic polymer has a solubility in water of above 50 g/100 ml of water, preferably of above 75 g/100 ml of water, even more preferably of above 100 g/100 ml of water and most preferably of above 150 g/100 ml of water. In one especially preferred embodiment, the at least one cationic polymer is readily soluble in water.

Preferably, the surface-treated calcium carbonate used in the present process is prepared by mixing the ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate, preferably in form of slurry,

and the cationic polymer, preferably in form of a suspension, before being brought into contact with the water to be treated. Mixing can be accomplished by any conventional means known to the skilled person.

- 5 The surface-treated calcium carbonate is preferably in the form of a particulate material, and may have a particle size distribution as conventionally employed for the material(s) involved in the treatment of polluted water. In general, the weight median particle diameter d_{50} value of the surface-treated calcium carbonate is in the range between 0.01 μm and 250 μm , preferably between 0.06 μm and 225 μm , more
10 preferably between 1 μm and 200 μm , even more preferably between 1 μm and 150 μm , and most preferably between 1 μm and 100 μm , measured according to the sedimentation process. A surface-treated calcium carbonate having a d_{98} of less than 100 microns, preferably of less than 85 microns may also be advantageous. Alternatively, surface-treated calcium carbonate having a d_{98} of less than 50 microns,
15 preferably of less than 25 microns may be advantageous.

- If the surface-treated calcium carbonate comprises ground calcium carbonate, the surface-treated calcium carbonate preferably has a weight median particle diameter d_{50} value of from 0.04 μm to 250 μm , more preferably from 0.06 μm to 225 μm ,
20 even more preferably from 1 μm to 200 μm , still more preferably from 1 μm to 150 μm and most preferably from 1 μm to 100 μm , measured according to the sedimentation process.

- If the surface-treated calcium carbonate comprises precipitated calcium carbonate,
25 the surface-treated calcium carbonate preferably has a weight median particle diameter d_{50} value of from 0.01 μm to 10 μm , more preferably from 0.02 μm to 5 μm , even more preferably from 0.02 μm to 2.5 μm and most preferably from 0.02 μm to 1 μm , measured according to the sedimentation process.

- If the surface-treated calcium carbonate comprises surface-modified calcium carbonate, the surface-treated calcium carbonate preferably has a weight median particle diameter d_{50} value of from 0.5 μm to 150 μm , preferably from 0.5 μm to 100 μm , more preferably from 0.5 μm to 100 μm and most preferably from 1 μm to 50 μm , measured according to the sedimentation process. In a preferred embodiment, the surface-treated calcium carbonate may be in the form of agglomerated particles, having a weight median particle diameter d_{50} value of from 0.5 μm to 250 μm and preferably from 0.5 μm to 150 μm measured according to the sedimentation process.
- 10 The surface-treated calcium carbonate preferably has a specific surface area of from 1 m^2/g to 250 m^2/g , preferably 20 m^2/g to 200 m^2/g , more preferably 30 m^2/g to 150 m^2/g and most preferably 30 m^2/g to 100 m^2/g , measured using nitrogen and the BET process. For example, the surface-treated calcium carbonate has a specific surface area of from 40 m^2/g to 50 m^2/g , e.g. a specific surface area of 45 m^2/g .
- 15 Alternatively, the surface-treated calcium carbonate has a specific surface area of from 50 m^2/g to 60 m^2/g , e.g. a specific surface area of 56 m^2/g .

- If the surface-treated calcium carbonate comprises ground calcium carbonate, the surface-treated calcium carbonate preferably has a specific surface area of from 1 m^2/g to 100 m^2/g , more preferably 1 m^2/g to 75 m^2/g , even more preferably 1 m^2/g to 50 m^2/g and most preferably 1 m^2/g to 20 m^2/g , measured using nitrogen and the BET process.
- 20

- If the surface-treated calcium carbonate comprises precipitated calcium carbonate, the surface-treated calcium carbonate preferably has a specific surface area of from 1 m^2/g to 150 m^2/g , more preferably 1 m^2/g to 100 m^2/g , even more preferably 1 m^2/g to 70 m^2/g and most preferably 1 m^2/g to 50 m^2/g , measured using nitrogen and the BET process.
- 25

If the surface-treated calcium carbonate comprises surface-modified calcium carbonate, the surface-treated calcium carbonate preferably has a specific surface area of from 1 m²/g to 250 m²/g before surface treatment, more preferably 1 m²/g to 200 m²/g, even more preferably 10 m²/g to 200 m²/g and most preferably 15 m²/g to 170 m²/g, measured using nitrogen and the BET process.

In one preferred embodiment, the at least one surface-treated calcium carbonate has a specific surface area within the range of 1 m²/g to 250 m²/g and a weight median particle diameter d_{50} value within the range of 0.01 μm to 250 μm. Preferably, the specific surface area is within the range of 20 m²/g to 200 m²/g and the weight median particle diameter d_{50} value is within the range of 0.06 μm to 225 μm. More preferably, the specific surface area is within the range of 30 m²/g to 150 m²/g and the weight median particle diameter is within the range of 1 μm to 200 μm. Even more preferably, the specific surface area is within the range of 30 m²/g to 100 m²/g and the weight median particle diameter d_{50} value is within the range of 1 μm to 150 μm. Most preferably, the specific surface area is within the range of 30 m²/g to 100 m²/g and the weight median particle diameter d_{50} value is within the range of 1 μm to 100 μm. For example, the at least one surface-treated calcium carbonate has a specific surface area within the range of 40 m²/g to 50 m²/g and a weight median particle diameter d_{50} value within the range of 1 μm to 50 μm. Alternatively, the at least one surface-treated calcium carbonate has a specific surface area within the range of 50 m²/g to 60 m²/g and a weight median particle diameter d_{50} value within the range of 1 μm to 50 μm.

The surface-treated calcium carbonate to be used in the inventive process can be present in any appropriate form, e.g. in the form of granules and/or a powder or in the form of a cake. Preferably, the surface-treated calcium carbonate to be used in the inventive process is in powder form and/or in the form of granules. In a preferred embodiment, the surface-treated calcium carbonate to be used in the inventive process is in powder form. Alternatively, the surface-treated calcium carbonate to be

used in the inventive process can be present as an aqueous suspension, e.g. in the form of a slurry or a paste which can be metered with a conveying screw.

Said slurry may comprise at least one further cationic polymer, wherein said cationic
5 polymer can be the same cationic polymer used for coating or a different cationic polymer, e.g. a further cationic polymer as described herein. After coating the slurry may be used directly without further purification, or at least one further cationic polymer may be added to the slurry.

10 A "slurry" or "suspension" in the meaning of the present invention comprises undissolved solids, i.e. surface-treated calcium carbonate and water and optionally further additives. Suspensions usually contain large amounts of solids and are more viscous and generally of higher density than the liquid from which they are formed. It is accepted in the art that the general term "dispersion" *inter alia* covers
15 "suspensions" or "slurries" as a specific type of dispersion.

In one preferred embodiment, the surface-treated calcium carbonate to be used in the inventive process is suspended in water such that the slurry has a content of surface-treated calcium carbonate within the range of 1 wt.-% to 80 wt.-%, more preferably
20 3 wt.-% to 60 wt.-%, and even more preferably 5 wt.-% to 50 wt.-%, based on the weight of the slurry.

Step c) contacting the water and/or sludge and/or sediment with the at least one surface-treated calcium carbonate

5 According to step c) of the process of the present invention, the water to be purified and/or sludge and/or sediment to be dewatered provided in step a) is contacted with the at least one surface-treated calcium carbonate of step b) for obtaining a composite material of surface-treated calcium carbonate and impurities from different sources.

10 In general, the water to be purified and/or sludge and/or sediment to be dewatered and the surface-treated calcium carbonate can be brought into contact by any conventional means known to the skilled person.

For example, the step of contacting the water to be purified and/or sludge and/or sediment to be dewatered with the at least one surface-treated calcium carbonate, 15 wherein at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer, preferably takes place in that the surface of the polluted water and/or sludge and/or sediment is at least partially covered with the at least one surface-treated calcium carbonate.

20 Additionally or alternatively, the step of contacting the water to be purified and/or sludge and/or sediment to be dewatered with the at least one surface-treated calcium carbonate preferably takes place in that the polluted water and/or sludge and/or sediment of step a) is mixed with the surface-treated calcium carbonate of step b). The skilled man will adapt the mixing conditions (such as the configuration of mixing speed) according to his needs and available equipment.

25 Preferably, the surface-treated calcium carbonate is suspended in the water and/or sludge and/or sediment to be treated, e.g. by agitation means.

The treatment time for carrying out the contacting of the water to be purified and/or 30 sludge and/or sediment to be dewatered with the at least one surface-treated calcium

carbonate is carried out for a period in the range of several seconds to several minutes, e.g. 20 s or more, preferably 30 s or more, more preferably 60 s or more and most preferably for a period of 120 s or more. In general, the length of contacting the water and/or sludge and/or sediment to be treated with the at least one surface-treated calcium carbonate is determined by the degree of water and/or sludge and/or sediment pollution and the specific water and/or sludge and/or sediment to be treated.

It is to be understood that the amount of surface-treated calcium carbonate according to the present process is selected such that it is sufficient in the water and/or sludge and/or sediment to be treated, i.e. high enough for providing efficient binding activity for at least one type of inorganic impurities present in the polluted water and/or sludge and/or sediment but at the same time is so low that no significant amount of unbound surface-treated calcium carbonate would be observed in the water and/or sludge and/or sediment to be treated.

The amount of surface-treated calcium carbonate depends on the type of water and/or sludge and/or sediment to be treated as well as on the type and amount of impurities. Preferably, an amount of 10 ppm to 1 wt.-%, more preferably 100 ppm to 0.2 wt.-% surface-treated calcium carbonate, based on the total weight of the water and/or sludge and/or sediment to be treated, is added.

The surface-treated calcium carbonate can be added as an aqueous suspension, e.g. the suspension described above. Alternatively, it can be added to the water to be purified and/or sludge and/or sediment to be dewatered in any appropriate solid form, e.g. in the form of granules or a powder or in form of a cake.

Within the context of the present invention, it is also possible to provide an immobile phase, e.g. in the form of a cake or layer, comprising the surface-treated calcium carbonate, the water and/or sludge and/or sediment to be treated running through said immobile phase.

In a preferred embodiment, the water and/or sludge and/or sediment to be purified is passed through a permeable filter comprising the surface-treated calcium carbonate and being capable of retaining, via size exclusion, the inorganic impurities on the filter surface as the liquid is passed through by gravity and/or under vacuum and/or under pressure. This process is called "surface filtration".

In another preferred technique known as depth filtration, a filtering aid comprising a number of tortuous passages of varying diameter and configuration retains impurities by molecular and/or electrical forces adsorbing the impurities onto the surface-treated calcium carbonate which is present within said passages, and/or by size exclusion, retaining the impurity particles if they are too large to pass through the entire filter layer thickness.

The techniques of depth filtration and surface filtration may additionally be combined by locating the depth filtration layer on the surface filter; this configuration presents the advantage that those particles that might otherwise block the surface filter pores are retained in the depth filtration layer.

In one preferred embodiment of the present invention, the process further comprises step d) of contacting the water to be purified and/or sludge and/or sediment to be dewatered with at least one polymeric flocculation aid.

In a preferred embodiment of the present invention, the polymeric flocculation aid and the surface-treated calcium carbonate are added simultaneously to the water and/or sludge and/or sediment to be treated. In another preferred embodiment of the present invention, the polymeric flocculation aid and the surface-treated calcium carbonate are added separately to the water and/or sludge and/or sediment to be treated. In this case, the water and/or sludge and/or sediment to be treated is first

contacted with the surface-treated calcium carbonate and then with the polymeric flocculation aid.

For example, the polymeric flocculation aid is added to the water and/or sludge
5 and/or sediment to be treated when adsorption of impurities on the surface-treated calcium carbonate has reached its maximum, i.e. there is no further decrease of inorganic impurities within the water. However, it is also possible to add the polymeric flocculation aid at an earlier stage, e.g. when at least 50%, at least 70% or at least 90% of maximum adsorption of impurities on the surface-treated calcium
10 carbonate has been reached.

The step of contacting the water to be purified and/or sludge and/or sediment to be dewatered with the at least one surface-treated calcium carbonate and the polymeric flocculation aid preferably takes place in that the surface of the water and/or sludge
15 and/or sediment is at least partially covered, either simultaneously or separately, with the at least one surface-treated calcium carbonate and the polymeric flocculation aid. Additionally or alternatively, the step of contacting the water to be purified and/or sludge and/or sediment to be dewatered with the at least one surface-treated calcium carbonate and the polymeric flocculation aid preferably takes place in that the water
20 and/or sludge and/or sediment is, either simultaneously or separately, mixed with the surface-treated calcium carbonate and the polymeric flocculation aid. The skilled man will adapt the mixing conditions (such as the configuration of mixing speed) according to his needs and available equipment.

25 The treatment time for carrying out the contacting of the water to be purified and/or sludge and/or sediment to be dewatered with the at least one surface-treated calcium carbonate and the polymeric flocculation aid is carried out for a period in the range of several seconds to several minutes, e.g. 30 s or more, preferably 60 s or more, more preferably 90 s or more and most preferably for a period of 180 s or more. In
30 general, the length of contacting the water and/or sludge and/or sediment to be

treated with the at least one surface-treated calcium carbonate and the polymeric flocculation aid is determined by the degree of water pollution and the specific water and/or sludge and/or sediment to be treated.

- 5 In a preferred embodiment of the present invention, process step c) and step d) are repeated one or more times. In a preferred embodiment of the present invention, process step c) or step d) is repeated one or more times. If step c) and step d) are repeated one or more times, step c) and step d) may be repeated independently, i.e. step c) may be repeated several times, while step d) is repeated more or less times
10 than step c) and vice versa. For example, step c) may be repeated twice, while step d) is repeated once or more than twice.

- Any polymeric flocculation aid known in the art can be used in the process of the present invention. Examples of preferred polymeric flocculation aids include
15 polyacrylamides or polyelectrolytes based on polyacrylates, poly(diallyldimethylammonium chloride), polyethyleneimines, polyamines or mixtures of these, and natural polymers such as starch, or natural modified polymers like modified carbohydrates.

- 20 In a preferred embodiment, the polymeric flocculation aid is no polyacrylamide.

- Preferably, the polymeric flocculation aid has a weight average molecular weight of at least 100,000 g/mole. In a preferred embodiment, the polymeric flocculation aid has a weight average molecular weight M_w in the range from 100,000 to 10,000,000
25 g/mole, preferably in the range from 300,000 to 5,000,000 g/mole, more preferably in the range from 300,000 to 1,000,000 g/mole and most preferably in the range from 300,000 to 800,000 g/mole.

The polymeric flocculation aid can be ionic or non-ionic. Preferably, the polymeric flocculation aid is ionic, i.e. an anionic polymeric flocculation aid or a cationic polymeric flocculation aid.

- 5 In the context of the present invention, the term "cationic" refers to any polymer having a positive overall charge. Thus, the presence of some anionic monomer units is not excluded as long as there are still sufficient cationic monomer units providing a positive overall charge and enabling its use as a flocculation aid. Furthermore, the term "cationic polymeric flocculation aid" also comprises those polymers having
10 monomer units with functional groups which become cationic upon addition to the water to be treated, e.g. amine groups becoming ammonium groups in acidic water.

- The term "anionic" refers to any polymer having a negative overall charge. Thus, the presence of some cationic monomer units is not excluded as long as there are still
15 sufficient anionic monomer units providing a negative overall charge and enabling its use as a flocculation aid. Furthermore, the term "anionic polymeric flocculation aid" also comprises those polymers having monomer units with functional groups which become anionic upon addition to the water to be treated, e.g. acid groups such as sulfonic acid groups.

20

A preferred polymeric flocculation aid of the present invention is polyacrylamide. By appropriate modifications which are known to the skilled person, the polyacrylamide can be used as a cationic polymeric flocculation aid as well as an anionic polymeric flocculation aid.

25

Preferably, the polyacrylamide contains at least 50 mol-%, more preferably at least 60 mol-%, even more preferably at least 75 mol-% monomer units derived from acrylamide.

An anionic polyacrylamide, i.e. a polyacrylamide having a negative overall charge, can be obtained by introducing appropriate comonomer units, e.g. derived from (meth)acrylic acid.

- 5 A cationic polyacrylamide, i.e. a polyacrylamide having a positive overall charge, can be obtained by introducing appropriate comonomer units, e.g. derived from aminoalkyl(meth)acrylates such as dimethylaminomethyl(meth)acrylate, dimethylaminoethyl(meth)acrylate, dimethylaminopro-pyl(meth)acrylate, diethylaminomethyl(meth)acrylate, diethylaminoethyl(meth)acrylate or
10 diethylaminopropyl(meth)acrylate which can be quaternized by alkyl halides.

- In another preferred embodiment, polyacrylate is used as a preferred polymeric flocculation aid in the process of the present invention. Preferably, the polyacrylate is used as a cationic polymeric flocculation aid. More specifically, the polyacrylate
15 used as a cationic polymeric flocculation aid is free of acrylamide.

- Preferably, the polyacrylate contains at least 50 mol-%, more preferably at least 60 mol-%, even more preferably at least 75 mol-% monomer units derived from aminoalkyl(meth)acrylates such as dimethylaminomethyl(meth)acrylate,
20 dimethylaminoethyl(meth)acrylate, dimethylaminopro-pyl(meth)acrylate, diethylaminomethyl(meth)acrylate, diethylaminoethyl(meth)acrylate or diethylaminopropyl(meth)acrylate which can be quaternized by alkyl halides.

- Alternatively, the polymeric flocculation aid may be a polymer as described as comb
25 polymer in US 2009/0270543 A1. The subject-matter of US 2009/0270543 A1 relating to the polymer is hereby incorporated by reference in its entirety.

- In one preferred embodiment, the polymeric flocculation aid is a copolymer prepared from 92 wt.-% methoxy polyethylene glycol methacrylate of molecular weight 2,000
30 g/mole and 8 wt.-% acrylic acid and at least partially neutralised by soda. In a further

preferred embodiment, the polymeric flocculation aid is a copolymer prepared from 92 wt.-% methoxy polyethylene glycol methacrylate of molecular weight 2,000 g/mole and 8 wt.-% acrylic acid and totally neutralised by soda.

- 5 Optionally, further additives can be added to the water and/or sludge and/or sediment to be treated. These might include agents for pH adjustment and conventional flocculants such as polyaluminium chloride, iron chloride or aluminium sulphate. However, in a preferred embodiment, the water purification process and/or dewatering process of sludge and/or sediment of the present invention does not use
10 any additional conventional inorganic flocculation aids such as polyaluminium chloride, iron chloride or aluminium sulphate.

- After the contacting/flocculation has been completed, the flocculated composite material can be removed from the treated water by conventional separation means
15 known to the skilled person such as filtration, sedimentation and/or centrifugation.

- In an alternative approach, the water to be purified and/or sludge and/or sediment to be dewatered is preferably passed through a permeable filter comprising the surface-treated calcium carbonate and being capable of retaining, via size exclusion, the
20 impurities on the filter surface as the filtrate is passed through by gravity and/or under vacuum and/or under pressure. This process is called "surface filtration".

- In accordance with the present invention, the process for the purification of water and/or dewatering of sludge and/or sediment is suitable for effectively reducing the
25 amount of polymeric flocculation aid contained in a purified water sample and/or dewatered sludge and/or sediment sample.

- In a preferred embodiment, the water and/or sludge and/or sediment obtained by the process of the present invention contains an amount of polymeric flocculation aid of
30 at least 10 wt.-%, preferably at least 20 wt.-%, more preferably at least 30 wt.-%,

even more preferably at least 40 wt.-%, still more preferably at least 50 wt.-% and most preferably at least 60 wt.-% below the amount of free flocculation aid contained in corresponding water and/or sludge and/or sediment being treated the same way but in the absence of the at least one surface-treated calcium carbonate. For example, the

5 water and/or sludge and/or sediment obtained by the process of the present invention contains an amount of polymeric flocculation aid of at least 70 wt.-%, preferably at least 80 wt.-% and most preferably at least 90 wt.-% below the amount of free flocculation aid contained in corresponding water and/or sludge and/or sediment being treated the same way but in the absence of the at least one surface-treated

10 calcium carbonate.

The use of the inventive process for the purification of water and/or dewatering of sludges and/or sediments provides a number of improved properties. First of all, the inventive process provides excellent binding activity for impurities when the at least

15 one surface-treated calcium carbonate is at least partially applied onto the surface of the water and/or sludge and/or sediment to be treated or mixed with the water and/or sludge and/or sediment to be treated. Furthermore, the use of the inventive process results in a composite material of surface-treated calcium carbonate and impurities which can be easily removed from the medium to be treated. Furthermore, the

20 binding of impurities by the inventive process results in a good cleansing quality of the water and/or sludge and/or sediment to be treated as well as of the obtained filter cake. A further advantage of the inventive process resides in the fact that the used surface-treated calcium carbonate lowers the amount of polymeric flocculation aid in the treated water and/or sludge and/or sediment and thus decreases the disturbance of

25 the ecological balance. Another advantage of the inventive process is that the quality of the obtained filter cake is increased so that the subsequent disposal is less energy-consuming.

Depending on the specific requirements and/or the respective physical and/or

30 chemical properties of the water and/or sludge and/or sediment to be treated, the

surface-treated calcium carbonate and the optional polymeric flocculation aid to be used according to the inventive process can be applied both separately or a finished mixture may be used. In the form of a separately metered addition of the individual components of the surface-treated calcium carbonate and the optional polymeric
5 flocculation aid, the concentration ratio may be individually adjusted depending on the present water and/or sludge and/or sediment to be treated. The pwater and/or sludge and/or sediment may be treated with the surface-treated calcium carbonate being formulated, for example, as a customary formulation, such as, for example, a slurry, a powder or granules.

10

Applications are possible for the purification of water and dewatering of sludges and/or sediments originated in different industries such as industrial waste water, drinking water, urban waste water, sludge such as harbour sludge, river sludge, coastal sludge or digested sludge, waste water or process water from breweries or
15 other beverage industries, waste water or process water in the paper industry, colour-, paints-, or coatings industry, agricultural waste water, slaughterhouse waste water, leather industry waste water and leather tanning industry.

In a preferred embodiment, the surface-treated calcium carbonate can also be
20 advantageously used for neutralizing or buffering the water and/or sludge and/or sediment to be treated, such as industrial waste water, drinking water, urban waste water, sludge such as harbour sludge, river sludge, coastal sludge or digested sludge, waste water or process water from breweries or other beverage industries, waste water or process water in the paper industry, colour-, paints-, or coatings industry,
25 agricultural waste water, slaughterhouse waste water, leather industry waste water and leather tanning industry.

In view of the very good results of the inventive process in the purification of water and/or dewatering of sludges and/or sediments as defined above, a further aspect of
30 the present invention is the use of the surface-treated calcium carbonate in the

purification of water and/or dewatering of sludges and/or sediments. According to another aspect of the present invention, the use of the surface-treated calcium carbonate for reducing the amount of polymeric flocculation aids in water and/or sludges and/or sediments is provided.

5

According to a further aspect of the present invention, a composite material comprising the surface-treated calcium carbonate and impurities is provided.

Preferably, the composite material further comprises a polymeric flocculation aid as defined above. When the surface-treated calcium carbonate is used in combination with a polymeric flocculation aid as defined above, it has surprisingly been found that a flocculated composite material of improved compactness is obtained while the concentration of polymeric flocculation aid in the filtrate is considerably reduced.

10 If the flocculated composite material is separated from the water and/or sludge and/or sediment by filtration, sedimentation and/or centrifugation, the composite material can be present in the form of a filter cake.

With regard to the definition of the surface-treated calcium carbonate and preferred
20 embodiments thereof, reference is made to the statements provided above when discussing the technical details of the process of the present invention.

The following examples may additionally illustrate the invention, but are not meant to restrict the invention to the exemplified embodiments.

25

EXAMPLES

Measurement processes

- 5 The following measurement processes were used to evaluate the parameters given in the examples and claims.

BET specific surface area of a material

- 10 The BET specific surface area was measured via the BET process according to ISO 9277 using nitrogen, following conditioning of the sample by heating at 250°C for a period of 30 minutes. Prior to such measurements, the sample was filtered, rinsed and dried at 110°C in an oven for at least 12 hours.

- 15 **Particle size distribution (mass % particles with a diameter $< X$) and weight median diameter (d_{50}) of a particulate material**

Weight median grain diameter and grain diameter mass distribution of a particulate material were determined via the sedimentation process, i.e. an analysis of sedimentation behaviour in a gravitational field. The measurement was made with a SedigraphTM 5100.

20

The weight median grain diameter of the surface reacted calcium carbonate was determined by using a Malvern Mastersizer 2000 Laser Diffraction System.

- 25 The processes and instruments are known to the skilled person and are commonly used to determine grain size of fillers and pigments. The measurements were carried out in an aqueous solution of 0.1 wt.-% Na₄P₂O₇. The samples were dispersed using a high speed stirrer and ultrasound.

Accessible surface area

The accessible surface area of the calcium carbonate may be determined by the process described in the publication of Papirer, Schultz and Turchi (Eur. Polym. J., Vol. 20, No. 12, pp. 1155-1158, 1984).

5

Haze

The haze of the water samples is measured by using a standard photometer in accordance with standard procedures.

10 **pH measurement**

The pH of the water samples is measured by using a standard pH-meter at approximately 25°C.

Alkalinity

15 The alkalinity of the water samples is measured by using standard titration procedures.

Oxydizability

20 The oxydizability of the water samples is measured by using the well known CSB method using potassium dichromate.

Example 1

25 The following illustrative Example involves the use of a surface-treated calcium carbonate in combination with a polymeric flocculation aid for the purification of two different sludge samples. Said surface-treated calcium carbonate comprises a modified calcium carbonate and has a weight medium particle diameter d_{50} value of 1.6 μm (measured according to the sedimentation process) and a specific surface area of 45 m^2/g (measured using nitrogen and the BET process), before surface treatment.

The surface-treated natural calcium carbonate is covered by a coating comprising polyacrylate having a cationic charge density of 7 mEq/g. The polyacrylate is present in the coating in an amount of 0.95 wt.-%, based on the dry weight of the calcium carbonate. As the polymeric flocculation aid, the commercially available flocculation aid FLOPAMTM FB 608 (commercially available from SNF Floerger, France) was used.

The purification process was performed on a mixed sludge (a blend of a primary and biological sludge) sampled from STEP Collombey-Muraz and a digested sludge sampled from STEP AIEE Penthaz. 200 ml of the respective sludge sample was added to a slurry of surface-treated calcium carbonate having a content of surface-treated calcium carbonate of 44.2 wt.-%, based on the total weight of the slurry. After manual agitation, the flocculation was completed by adding the polymeric flocculation aid. The polymeric flocculation aid was used in the form of a suspension having a content of flocculation aid of 0.5 wt.-%, based on the total weight of the suspension. The content of flocculation aid in the sample was monitored for the respective sludge samples. Tables 1 and 2 summary the details of the utilized amounts of surface-treated calcium carbonate and the measured reduction of polymeric flocculation aid.

20

Table 1: results for the mixed sludge

MCC [g]	MCC [kg/TDM]	Cationic polymer [kg/TDM]	polymeric flocculation aid [ml]	polymeric flocculation aid [kg/TDM]
0.0	0.0	0	33	41.7
5.0	126.3	1.2	25	30.3
10.0	252.6	2.4	18	22.2
15.0	378.9	3.6	18	22.2
20.0	505.2	4.8	18	22.2

kg/TDM means kg per ton dry mass.

Table 2: results for the digested sludge

MCC [g]	MCC [kg/TDM]	Cationic polymer [kg/TDM]	polymeric flocculation aid [ml]	polymeric flocculation aid [kg/TDM]
0.0	0.0	0	38	51.8
5.0	136.2	1.3	26	35.4
10.0	272.5	2.6	22	29.9
15.0	408.7	3.9	22	29.9
20.0	545.0	5.2	22	29.9

During the purification process of the mixed sludge as well as for the digested sludge samples treated with a combination of the surface-treated calcium carbonate and a polymeric flocculation aid, a concentration reduction in the range of about 42 to 47 % was obtained for the polymeric flocculation aid. It can thus be concluded that during the purification process a reduced amount of polymeric flocculation aid is needed.

10

Example 2

The following illustrative Example involves the use of a surface-treated calcium carbonate in combination with a polymeric flocculation aid for the purification of two different sludge samples. Said surface-treated calcium carbonate comprises a modified calcium carbonate and has a weight medium particle diameter d_{50} value of 2.0 μm (measured according to the sedimentation process) and a specific surface area of 56 m^2/g (measured using nitrogen and the BET process), before surface treatment. The surface-treated natural calcium carbonate is covered by a coating comprising poly(diallyldimethylammonium chloride) having a cationic charge density of 6.2 mEq/g. The poly(diallyldimethylammonium chloride) is present in the coating in an

20

amount of 1.5 wt.-%, based on the dry weight of the calcium carbonate. As the polymeric flocculation aid, the commercially available flocculation aid FLOPAMTM FB 608 (commercially available from SNF Floerger, France) was used.

- 5 The purification process was performed on a mixed sludge (a blend of a primary and biological sludge) sampled from STEP Collombey-Muraz and a digested sludge sampled from STEP AIEE Penthaz. 200 ml of the respective sludge sample was added to a slurry of surface-treated calcium carbonate having a content of surface-treated calcium carbonate of 31.0 wt.-%, based on the total weight of the slurry.
- 10 After manual agitation, the flocculation was completed by adding the polymeric flocculation aid. The polymeric flocculation aid was used in the form of a suspension having a content of flocculation aid of 0.5 wt.-%, based on the total weight of the suspension. The content of polymeric flocculation aid in the sample was monitored for the respective sludge samples. Tables 3 and 4 summary the details of the utilized
- 15 amounts of surface-treated calcium carbonate and the measured reduction of polymeric flocculation aid.

Table 3: results for the mixed sludge

MCC [g]	MCC [kg/ToTDM]	Cationic polymer [kg/TDM]	polymeric flocculation aid [ml]	polymeric flocculation aid [kg/TDM]
0.0	0.0	0	33	41.7
5.0	126.3	1.9	15	19.8
10.0	252.6	3.8	13	16.4
15.0	378.9	5.7	11	13.9
20.0	505.2	7.6	11	13.9

Table 4: results for the digested sludge

MCC [g]	MCC [kg/TDM]	Cationic polymer [kg/TDM]	polymeric flocculation aid [ml]	polymeric flocculation aid [kg/TDM]
0.0	0.0	0	38	51.8
5.0	136.2	2.0	24	32.7
10.0	272.5	4.1	18	24.5
15.0	408.7	6.1	15	20.4
20.0	545.0	8.2	15	20.4

During the purification process of the mixed sludge as well as for the digested sludge samples treated with a combination of the surface-treated calcium carbonate and a polymeric flocculation aid, a concentration reduction in the range of about 61 to 67 % for the polymeric flocculation aid was observed. It can thus be concluded that during the purification process a reduced amount of polymeric flocculation aid is needed.

10

Example 3

The following illustrative Example involves the use of a modified calcium carbonate, i.e. the calcium carbonate is not covered by a coating comprising at least one cationic polymer, in combination with a polymeric flocculation aid for the purification of two different sludge samples. Said modified calcium carbonate has a weight medium particle diameter d_{50} value of 1.6 μm (measured according to the sedimentation process) and a specific surface area of 45 m^2/g (measured using nitrogen and the BET process), before surface treatment. As the polymeric flocculation aid, the commercially available flocculation aid FLOPAMTM FB 608 (commercially available from SNF Floerger, France) was used.

20

The purification process was performed on a mixed sludge (a blend of a primary and biological sludge) sampled from STEP Collombey-Muraz and a digested sludge sampled from STEP AIEE Penthaz. 200 ml of the respective sludge sample was added to a slurry of modified calcium carbonate having a content of surface-treated calcium carbonate of 31.8 wt.-%, based on the total weight of the slurry. After manual agitation, the flocculation was completed by adding the polymeric flocculation aid. The polymeric flocculation aid was used in the form of a suspension having a content of flocculation aid of 0.5 wt.-%, based on the total weight of the suspension. The content of polymeric flocculation aid in the sample was monitored for the respective sludge samples. Tables 5 and 6 summary the details of the utilized amounts of surface-treated calcium carbonate and the measured reduction of polymeric flocculation aid.

Table 5: results for the mixed sludge

MCC [g]	MCC [kg/TDM]	Cationic polymer [kg/TDM]	polymeric flocculation aid [ml]	polymeric flocculation aid [kg/TDM]
0.0	0.0	0	33	41.7
5.0	126.3	0	30	37.7
10.0	252.6	0	28	35.4
15.0	378.9	0	26	32.8
20.0	505.2	0	26	32.8

Table 6: results for the digested sludge

MCC [g]	MCC [kg/TDM]	Cationic polymer [kg/TDM]	polymeric flocculation aid [ml]	polymeric flocculation aid [kg/TDM]
0.0	0.0	0	38	51.8
5.0	136.2	0	36	49.0
10.0	272.5	0	33	44.9
15.0	408.7	0	33	44.9
20.0	545.0	0	33	44.9

During the purification process of the mixed sludge as well as for the digested sludge samples treated with a combination of the modified calcium carbonate and a
 5 polymeric flocculation aid, a concentration reduction in the range of 13 to 21 % for the polymeric flocculation aid was obtained.

Overall, it can be concluded that the use of the modified calcium carbonate in combination with a polymeric flocculation aid has only slight effects on the amounts
 10 of polymeric flocculation aid required for complete flocculation, i.e. of below 21 %. In contrast thereto, the inventive surface-treated calcium carbonate achieves a reduction of polymeric flocculation aid of up to 79 % compared to the initial concentration.

15

Example 4

The following illustrative Example involves the use of different amounts of a surface-treated calcium carbonate in combination with a polymeric flocculation aid for the purification of river water. Said surface-treated calcium carbonate comprises
 20 a modified calcium carbonate and has a weight medium particle diameter d_{50} value of 2.0 μm (measured according to the sedimentation process) and a specific surface area

- of 56 m²/g (measured using nitrogen and the BET process), before surface treatment. The surface-treated natural calcium carbonate is covered by a coating comprising poly(diallyldimethylammonium chloride) having a cationic charge density of 6.2 mEq/g. The poly(diallyldimethylammonium chloride) is present in the coating in an amount of 1.5 wt.-%, based on the dry weight of the calcium carbonate. As the polymeric flocculation aid, the commercially available flocculation aid Nerolan AG 580 (commercially available from Nerolan Wassertechnik GmbH, Germany) was used. Nerolan AG 580 represents a polyacrylate which is free of acrylamide.
- 10 As a comparative Example, aluminum sulfate in combination with a polyacrylmide as the polymeric flocculation aid was used. As the polymeric flocculation aid, the commercially available flocculation aid Praestol 650 TR (commercially available from Ashland Deutschland GmbH, Germany) was used.
- 15 The purification process was performed on river water of the Neva in Russia sampled from a water barrage. Differing amounts of surface-treated calcium carbonate and 10 ppm of aluminum sulfate, respectively, was added to about 450 ml of the water sample. After agitation at 400 U/min for about 30 s, the flocculation was completed by adding the respective polymeric flocculation aid. Table 7 summaries the details of
- 20 the utilized amounts of surface-treated calcium carbonate, the utilized amounts of polymeric flocculation aid and the physical and chemical results of purification.

Table 7

		Start	CE	IE1	IE2	IE3	IE.4
River water	ml		500	500	500	500	500
Aluminium Sulfate (Al_2SO_3)	ppm		10				
Polyacrylamide (as flocculation aid, Praestol 650 TR)	ppm		7				
MCC	ppm			400	450	600	200
PolyDadmac on MCC	wt.-%			1.5	1.5	1.5	1.5
PolyDadmac (from MCC, 10%)	ppm			6	6,75	9	3
Polyacrylate (Nerolan AG 580)	ppm			2	2	2	1
Mix Speed	UPM		400	400	400	400	400
Mix Time	s		30	30	30	30	30
haze [mg/l]		0.90	0.25	0.40	0.30	0.25	0.25
pH		7.70	6.60	8.50	8.30	8.45	8.40
alkalinity [mmol/l]		0.45	0.25	0.73	0.74	0.75	0.75
oxydizability [mg/l]		7.10	3.00	5.00	4.10	3.80	3.20

Overall, it can be concluded that the use of the surface-treated calcium carbonate in combination with a polymeric flocculation aid has a positive effect on the quality of the water obtained by the purification process.

Example 5

The following illustrative example involves the use of a surface-treated calcium carbonate in combination with a polymeric flocculation aid for the purification of a river wherein said flocculation aid is being added in two portions. Said surface-treated calcium carbonate comprises a modified calcium carbonate and has a weight medium particle diameter d_{50} value of 2.0 μm (measured according to the sedimentation process) and a specific surface area of 56 m^2/g (measured using nitrogen and the BET process), before surface treatment. The surface-treated natural calcium carbonate is covered by a coating comprising poly(diallyldimethylammonium chloride) having a cationic charge density of 6.2 mEq/g. The poly(diallyldimethylammonium chloride) is present in the coating in an amount of 1.5 wt.-%, based on the dry weight of the calcium carbonate. As the polymeric flocculation aid, the commercially available flocculation aid Nerolan AG 580 (commercially available from Nerolan Wassertechnik GmbH, Germany) was used. Nerolan AG 580 represents a polyacrylate which is free of acrylamide.

The purification process was performed on a river sludge sampled from the Elbe near Hamburg, Germany. The solid content of the river sludge was adapted to 17g/L. 45 ppm of the surface-treated calcium carbonate was added to the sludge under stirring conditions of 350 rpm during 5 seconds. The polymeric flocculation aid was added in amounts of 2000 ppm. Addition can be made in one or more portions. The final mixture was allowed to settle for 60 seconds, and was checked by visual inspection.

The supernatant was clear with no apparent particles visible. Sedimentation showed a proper separation between solid and liquid. Stability of the flocculated sludge was very good and determined as described hereto below. The settled mixture was poured 10x from one beaker glass to another and finally the mixture was filtered over a 200 μm sieve. The filtrate was checked by visual inspection. If the filtrate remained clear, the stability of the flocculated sludge is considered as very good. If the filtrate shows

to be cloudy then the stability of the flocculated sludge is less stable, depending on the degree of the haze of the filtrate.

Claims

- 5 1. A process for the purification of water and/or dewatering of sludges and/or
sediments, comprising the following steps of:
- a) providing water to be purified and/or sludge and/or sediment to be
dewatered comprising impurities;
 - b) providing at least one surface-treated calcium carbonate, wherein at least 1
10 % of the accessible surface area of the calcium carbonate is covered by a
coating comprising at least one cationic polymer, and
 - c) contacting the water and/or sludge and/or sediment of step a) with the at
least one surface-treated calcium carbonate of step b) for obtaining a
composite material of surface-treated calcium carbonate and impurities.
- 15
2. The process according to claim 1, wherein the water and/or sludge and/or
sediment of step a) is selected from industrial waste water, drinking water, urban
waste water, sludge such as harbour sludge, river sludge, coastal sludge or digested
sludge, waste water or process water from breweries or other beverage industries,
20 waste water or process water in the paper industry, colour-, paints-, or coatings
industry, agricultural waste water, slaughterhouse waste water, leather industry waste
water and leather tanning industry.
3. The process according to claims 1 or 2, wherein the at least one surface-
25 treated calcium carbonate of step b) comprises ground calcium carbonate and/or
precipitated calcium carbonate and/or surface-modified calcium carbonate,
preferably surface-modified calcium carbonate.
4. The process according to any one of claims 1 to 3, wherein the source of
30 ground calcium carbonate (GCC) is selected from marble, chalk, calcite, dolomite,
limestone and mixtures thereof and/or the precipitated calcium carbonate (PCC) is

selected from one or more of the aragonitic, vateritic and calcitic mineralogical crystal forms.

5. The process according to any one of claims 1 to 4, wherein the calcium carbonate particles of the at least one surface-treated calcium carbonate has a weight median particle diameter d_{50} value of between 0.01 μm and 250 μm , preferably between 0.06 μm and 225 μm , more preferably between 1 μm and 200 μm , even more preferably between 1 μm and 150 μm and most preferably between 1 μm and 100 μm and/or the calcium carbonate particles of the at least one surface-treated calcium carbonate has a specific surface area of from 1 to 250 m^2/g , more preferably from 20 to 200 m^2/g , even more preferably from 30 to 150 m^2/g and most preferably from 30 to 100 m^2/g .
6. The process according to any one of claims 1 to 5, wherein the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer having a positive charge density in the range of 1 mEq/g and 15 mEq/g, more preferably in the range of 2.5 mEq/g and 12.5 mEq/g and most preferably in the range of 5 $\mu\text{Eq/g}$ and 10 mEq/g and/or the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer in which at least 60 % of the monomer units have a cationic charge, preferably at least 70 %, more preferably at least 80 %, even more preferably at least 90 % and most preferably equal to 100 %.
7. The process according to any one of claims 1 to 6, wherein the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer having a weight average molecular weight M_w of below 1,000,000 g/mole, more preferably from 50,000 to 750,000 g/mole, even more preferably from 50,000 to 650,000 g/mole and most preferably from 100,000 to 300,000 g/mole.

8. The process according to any one of claims 1 to 7, wherein the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer being a homopolymer based on monomer units selected from the group consisting of diallyldialkyl ammonium salts; tertiary and quaternized amines; quaternized imines; acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; styrene; methyl methacrylate and vinyl acetate, preferably diallyldialkyl ammonium salts and acrylic acid.
9. The process according to any one of claims 1 to 7, wherein the coating of the at least one surface-treated calcium carbonate comprises at least one cationic polymer being a copolymer based on monomer units selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from the group consisting of acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; styrene; methyl methacrylate; vinyl acetate and mixtures thereof, preferably the monomer units are selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from acrylamide and acrylic acid.
10. The process according to any one of claims 1 to 9, wherein at least 10 % of the accessible surface area of the calcium carbonate is covered by a coating comprising a cationic polymer, preferably at least 20 % of the accessible surface area, more preferably at least 30 %, even more preferably at least 40 % and most preferably at least 50 % of the accessible surface area.
11. The process according to any one of claims 1 to 10, wherein the at least one surface-treated calcium carbonate is in powder form and/or in the form of granules or in the form of a slurry.

12. The process according to any one of claims 1 to 11, wherein the process further comprises step d) of contacting the water to be purified and/or sludge and/or sediment to be dewatered of step a) with at least one polymeric flocculation aid.
- 5 13. The process according to claim 12, wherein the polymeric flocculation aid has a weight average molecular weight M_w in the range from 100,000 to 10,000,00 g/mole, preferably in the range from 300,000 to 5,000,000 g/mole, more preferably in the range from 300,000 to 1,000,000 g/mole and most preferably in the range from 300,000 to 800,000 g/mole and/or the polymeric flocculation aid is non-
10 ionic or ionic, preferably a cationic or anionic polymer selected from polyacrylamides, polyacrylates, poly(diallyldimethylammonium chloride), polyethyleneimines, polyamines, starches and mixtures thereof.
14. The process according to any one of claims 12 or 13, wherein step c) and step
15 d) are carried out simultaneously or separately, preferably simultaneously.
15. The process according to any one of claims 1 to 14, wherein step c) and/or step d) are carried out by at least partially covering the surface of the water and/or sludge and/or sediment to be treated of step a) with the at least one surface-treated
20 calcium carbonate of step b) and/or mixing the water and/or sludge and/or sediment to be treated of step a) with the at least one surface-treated calcium carbonate of step b).
16. The process according to any one of claims 1 to 15, wherein step c) and/or
25 step d) are repeated one or more times.
17. The process according to any one of claims 1 to 16, wherein the composite material of the at least one surface-treated calcium carbonate and impurities is removed from the water and/or sludge and/or sediment phase by filtration,
30 sedimentation and/or centrifugation.

18. The process according to any one of claims 1 to 17, wherein the water and/or sludge and/or sediment obtained by the process contains an amount of flocculation aid of at least 10 wt.-%, preferably at least 20 wt.-%, more preferably at least 30 wt.-%, even more preferably at least 40 wt.-%, still more preferably at least 50 wt.-% and most preferably at least 60 wt.-% below the amount of flocculation aid contained in a corresponding water and/or sludge and/or sediment being treated the same way but in the absence of the at least one surface-treated calcium carbonate.
19. Use of a surface-treated calcium carbonate for water purification and/or dewatering of sludges and/or sediments, wherein at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer.
20. Use of a surface-treated calcium carbonate for reducing the amount of polymeric flocculation aids in water and/or sludges and/or sediments, wherein at least 1 % of the accessible surface area of the calcium carbonate is covered by a coating comprising at least one cationic polymer.
21. The use according to any one of claims 19 or 20, wherein the surface-treated calcium carbonate comprises ground calcium carbonate and/or precipitated calcium carbonate and/or surface-modified calcium carbonate, preferably surface-modified calcium carbonate.
22. The use according to any one of claims 19 to 21, wherein the source of ground calcium carbonate (GCC) is selected from marble, chalk, calcite, dolomite, limestone and mixtures thereof and/or the precipitated calcium carbonate (PCC) is selected from one or more of the aragonitic, vateritic and calcitic mineralogical crystal forms.

23. The use according to any one of claims 19 to 22, wherein the calcium carbonate particles of the at least one surface-treated calcium carbonate has a weight median particle diameter d_{50} value of between 0.01 μm and 250 μm , preferably between 0.06 μm and 225 μm , more preferably between 1 μm and 200 μm , even
5 more preferably between 1 μm and 150 μm and most preferably between 1 μm and 100 μm and/or the calcium carbonate particles of the surface-treated calcium carbonate has a specific surface area of from 1 to 250 m^2/g , more preferably from 2 to 200 m^2/g , even more preferably from 30 to 150 m^2/g and most preferably from 30 to 100 m^2/g .

10

24. The use according to any one of claims 19 to 23, wherein the coating of the surface-treated calcium carbonate comprises at least one cationic polymer having a positive charge density in the range of 1 mEq/g and 15 mEq/g, more preferably in the range of 2.5 mEq/g and 12.5 mEq/g and most preferably in the range of 5 mEq/g and
15 10 mEq/g and/or the coating of the surface-treated calcium carbonate comprises at least one cationic polymer in which at least 60 % of the monomer units have a cationic charge, preferably at least 70 %, more preferably at least 80 %, even more preferably at least 90 % and most preferably equal to 100 %.

20

25. The use according to any one of claims 19 to 24, wherein the coating of the surface-treated calcium carbonate comprises at least one cationic polymer having a weight average molecular weight M_w of below 1,000,000 g/mole, more preferably from 50,000 to 750,000 g/mole, even more preferably from 50,000 to 650,000 g/mole and most preferably from 100,000 to 300,000 g/mole.

25

26. The use according to any one of claims 19 to 25, wherein the coating of the surface-treated calcium carbonate comprises at least one cationic polymer being a homopolymer based on monomer units selected from the group consisting of diallyldialkyl ammonium salts; tertiary and quaternized amines; quaternized imines; acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; styrene; methyl methacrylate and vinyl acetate, preferably diallyldialkyl ammonium salts and acrylic acid.
27. The use according to any one of claims 19 to 25, wherein the coating of the surface-treated calcium carbonate comprises at least one cationic polymer being a copolymer based on monomer units selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from the group consisting of acrylamide; methacrylamide; N,N-dimethyl acrylamide; acrylic acid; methacrylic acid; vinylsulfonic acid; vinyl pyrrolidone; hydroxyl ethyl acrylate; styrene; methyl methacrylate; vinyl acetate and mixtures thereof, preferably the monomer units are selected from diallyldialkyl ammonium salts and methacrylic acid and comonomer units selected from acrylamide and acrylic acid.
28. The use according to any one of claims 19 to 27, wherein at least 10 % of the accessible surface area of the calcium carbonate is covered by a coating comprising a cationic polymer, preferably at least 20 % of the accessible surface area, more preferably at least 30 %, even more preferably at least 40 % and most preferably at least 50 % of the accessible surface area.
29. The use according to any one of claims 19 to 28, wherein the surface-treated calcium carbonate is in powder form and/or in the form of granules or in the form of slurry.

30. The use according to any one of claims 19 to 29, wherein the surface-treated calcium carbonate is used in combination with at least one polymeric flocculation aid.

5 31. The use according to claim 30, wherein the polymeric flocculation aid has a weight average molecular weight M_w in the range from 100,000 to 10,000,000 g/mole, preferably in the range from 300,000 to 5,000,000 g/mole, more preferably in the range from 300,000 to 1,000,000 g/mole and most preferably in the range from 300,000 to 800,000 g/mole and/or the polymeric flocculation aid is non-
10 ionic or ionic, preferably a cationic or anionic polymer selected from polyacrylamides, polyacrylates, poly(diallyldimethylammonium chloride), polyethyleneimines, polyamines, starches and mixtures thereof.

32. A composite material comprising a surface-treated calcium carbonate and
15 impurities obtainable by the process according to any one of claims 1 to 18.