

Description

5

Synthetic Fiber Rope

10 The invention relates to a synthetic fiber rope consisting of strands that are arranged in at least one layer of strands, a strand consisting of twisted yarns, and a yarn consisting of synthetic fibers, at least one strand having at least one layer of strands of indicator fibers or at least one indicator yarn to monitor the service life of the rope according to the definition of the independent patent claims.

From Patent Application EP 1 371 597 A1 a sheathed rope used as suspension means for elevators has become known. 20 The rope has inner strand layers and outer strand layers, a strand layer consisting of several twisted strands and the direction of twist of the inner strand layer being opposite to the direction of twist of the outer strand layer. The tensile strength of the inner strand layer is higher than the tensile strength of the outer strand layer. Each strand 25 is constructed of twisted and impregnated aramid synthetic fibers. The service life of the outer strand layer is less than the service life of the inner strand layer. For the purpose of monitoring the rope, individual strands of the outer strand layer are provided with electrically 30 conducting wires, every two adjacent strands being provided with electrically conducting wires that mutually abrade and thereby promptly detect the expiration of the service life of the rope or the end of the rope service life of the rope. 35

From Patent Application EP 0 731 209 A1 a sheathed rope used as suspension means for elevators has become known.

The rope has inner strand layers and outer strand layers, a strand layer consisting of several twisted strands and the direction of twist of the inner strand layer being in the same direction as the direction of twist of the outer strand layer. Each strand is constructed of twisted and impregnated aramid synthetic fibers. For the purpose of monitoring the rope service life or state of wear of the synthetic fiber rope, in each case one strand of a layer of strands is provided with electrically conductive carbon fibers. In regular operation, it is always the case that the carbon fibers, either as a result of excessive stretching or an excessive number of reverse bendings, snap or break sooner than the load-bearing aramid fibers of the strand. With the aid of a voltage source, the number of snapped carbon fibers can be determined. So that the residual load-bearing capacity of the synthetic fiber rope can be assured, only a certain percentage of the carbon fibers may fail. The elevator is then automatically driven to a predetermined stop and switched off.

It is here that the invention sets out to provide a remedy. The invention as characterized in Claim 1 solves the problem of creating a synthetic fiber rope with increased sensitivity for monitoring the rope service life.

Advantageous further developments of the invention are stated in the dependent patent claims.

Monitoring of the rope service life is a basic problem of all synthetic fiber ropes, especially such ropes that are surrounded by a sheath.

According to the present state of the art, the carbon fibers can be selected and arranged according to the load situation in the rope. A disadvantage of this method can be that the parameters that should be conditioned cannot be optimally adapted to each other and the suspension means must be replaced too early so as to be sufficiently far

away from the critical condition. In elevator construction, synthetic fiber ropes that serve as suspension means can be used up to 60% to 80% of the residual breaking strength relative to the normal breaking strength. The more
5 accurately this point can be reached, the more economically the suspension means can be used.

Depending on the type, field of application, and safety requirements of the synthetic fiber rope application, the
10 requirements for the monitoring sensitivity of the indicator strands of the synthetic fiber rope are increased. Correct responsive behavior and reproducibility depending on the requirement are advantageous characteristics of the synthetic fiber rope according to
15 the invention. It is known that synthetic fiber ropes serving as suspension means for elevators are permanently electrically monitored by means of yarns of carbon fiber that are integrated in the rope strands. This has the advantage that the synthetic fiber ropes are monitored over
20 their entire length including areas that are not visible as, for example, the areas in the rope sockets. The synthetic fiber ropes detect the abrasive wear within the rope and reliably detect damage acting from outside and give the elevator user a maximum of safety through the
25 continuous connection to the elevator control which in case of need can respond quickly and uncompromisingly.

The requirements for a modern monitoring of suspension means have increased relative to the past. So that the
30 synthetic fiber rope can be taken to its limit of failure, and thus the economic potential of the new type of suspension means more fully exploited, or the user can set a sensitivity for detection of the state of wear of the rope that is needed for his requirements, the strands with
35 indicator fibers must be even better adjustable in their response behavior, the indicator fibers of the strands having a high probability of losing their electrical

conductivity depending on a number of reverse flexures and residual breaking force and thereby detecting a rope wear.

5 An indicator fiber or an indicator yarn can be of any material that in any form is conductive, as for example fibers with light-conducting properties or metal coated technical fibers, carbon fibers, etc. that are electrically conductive, the fibers with direct contact wearing sooner than the load-bearing fibers.

10

For permanent monitoring, the conductive indicator fibers are contacted at the rope end and connected to instruments. At one rope end, the indicator fibers are connected to a signal transmitter and at the other rope end the indicator
15 fibers are connected to a signal receiver. The transmitter signal is measured by means of the signal receiver and the condition of the indicator fibers is evaluated on the basis of the measured or absent signal. EP 0 731 209 A1 shows an example of an indicator fiber monitoring by means of
20 electric signals.

A synthetic fiber rope consists of a plurality of twisted strands that are arranged in different layers, each strand consisting of twisted yarns, a yarn consisting of, for
25 example, 1000 synthetic fibers. A raw yarn consists either of unidirectional synthetic fibers or, for better processability, already has from the factory a protective twist of, for example, 15 turns per meter. In general, "fiber" is used as a length-independent generic term for
30 all textile fiber materials. "Filament" is the term used in chemical fiber manufacturing for textile fibers of great, or virtually endless, length. The direction of twist of the yarn in the strands is so foreseen that the individual fiber is advantageously aligned in the direction of tension
35 of the rope or in the longitudinal axis of the rope. The synthetic fiber rope can be constructed of chemical fibers as, for example, aramid fibers or fibers of related type, polyethylene fibers, polyester fibers, glass fibers, etc.

The synthetic fiber rope can consist of one or two or three or more than three layers of strands. At least one strand of at least one layer of strands has indicator fibers or at least one indicator yarn for monitoring the rope service life.

According to the invention, the plastic, also called matrix, that surrounds the strand that is provided with at least one indicator fiber or indicator yarn has a lower resistance to abrasion than the matrix of the other strands.

In the synthetic fiber rope according to the invention, the matrix material or resin that surrounds the strands of the strands with indicator fibers or indicator yarns consists of a softer plastic (for example Shore hardness scale A) than the matrix materials (for example Shore hardness scale D) of the neighboring or other strands, as a result of which these strands relative to a strand without indicator fibers or indicator yarn has a lower resistance to abrasion. As an alternative to the softer plastic, the matrix material can be impregnated with a softener. For this purpose, known softeners can be used. As a result of the poorer abrasion behavior of the strands with indicator fibers, through the movement relative to the adjacent strands that arises during bending, an early onset of wear and thus an earlier failure of the indicator fibers in the strands is provoked. The strand with indicator fibers or indicator yarn acts as intended breaking point. The strand with indicator fibers or indicator yarn is referred to hereafter as "indicator strand". Depending on the type and amount of the selected softener, the increase in wear can be controlled.

Phthalate and adipate are typical softeners that make the strands softer, their lateral rigidity lower, and their resistance to abrasion lower. Through a selected weight ratio of 1% to 30% on the matrix of the indicator strand,

the matrix can be executed "softer" relative to the neighboring strands, the abrasion behavior worsening with increasing amount of softener depending on the degree of softness.

5

Furthermore, the matrix material of the neighboring strand or other strands (strand without indicator fibers or indicator yarn) that is identical to the matrix material of the indicator strands can be impregnated with an additive that reduces the friction relative to the indicator strand. Examples of additive that can be added are waxes or small amounts of Teflon (1 to 3% wax or 5 to 15% Teflon powder relative to the solid content of the matrix excluding the fiber content).

15

Further, the matrix material of the indicator strand that is identical to the matrix material of the neighboring strand can be treated during manufacture in such manner that the plastic matrix degrades until the hardness and the wear resistance diminish. This is achieved by a temperature treatment of the indicator strand at a temperature greater than 230° and a treatment time of more than 20 s. As a result of the temperature, the long molecule chains that are required for the material properties separate to such an extent that on cooling the molecules no longer completely recombine. To support this process, water molecules can be added to the strands matrix, which prevents a complete recombination of the molecule chains. As substitute, other molecules are conceivable that impair or prevent the recombination. An initial degradation of the matrix occurs that causes a sharply lower abrasion resistance and thereby provokes a failure of the indicator fibers or of the indicator yarn. The abrasion protection is caused to deteriorate in targeted manner.

35

The indicator fibers or indicator yarn are/is located near to the surface of the strand and participate(s) in the spiral structure of the synthetic fibers or of the

synthetic fiber yarn. On account of the softer strands matrix, the indicator fibers or the indicator yarn are worn through. The permanent monitoring of the load-bearing strand is thereby interrupted and detected as wear before
5 the other load-bearing strands are affected. This assures that the indicator strands not only have a different performance capacity on account of the different extension to breaking elongation, but also that a reliable failure probability is generated as a result of the different
10 hardness of the matrix. (The breakage extension is the extension of a fiber, a yarn, or a strand until it breaks.)

There is also the further possibility of positioning the indicator strands in a multilayer synthetic fiber rope in
15 such manner that the load that is absorbed is higher than that in the neighboring strands. For example, in a synthetic fiber rope with three strand layers, the two inner concentric strand layers absorb a higher proportion of the load since, although the length of lay relative to
20 the outermost layer is constant, the angle of lay relative to the midpoint of the synthetic fiber rope constantly decreases. In a laid rope, the strands lie significantly steeper, as a result of which the strands are shorter or longer depending on the layer. In view of the geometrical
25 limitation, the innermost strands are the shortest and therefore bear the greater load. It is therefore advisable to arrange further indicator fibers or indicator yarns in individual strands of the two inner strand layers. In the case of a three-layer rope, the middle strand layer is to
30 be preferred since on account of the different wrapping radii and therefore different bending speeds this layer is subject to higher stress loads.

Furthermore, for the strand construction of the strand
35 without indicator fibers a synthetic fiber with very good dynamic reverse bending capacity can be used. For the indicator yarn of the indicator strand the indicator fibers (for example carbon fibers) can be combined with synthetic

fibers (for example carbon fibers) whose dynamic reverse bending capacity is inferior to that of the other synthetic fibers of the indicator strands or that of the strand without indicator fibers. The superior synthetic fibers exist for the application of running suspension means on the basis of co-polymers, for example copolyterephthalamide, the under these conditions inferiorly functioning fibers can be of poly-p-phenylenterephthalamide. (The dynamic reverse bending capacity is the reverse bending capacity under changing loads.)

Furthermore, for the construction of the indicator yarn, the indicator fibers (for example carbon fibers) can be combined with synthetic fibers which, relative to the other synthetic fibers of the indicator strand or relative to the synthetic fibers of the strand without indicator yarn, have a higher modulus of elasticity. For the synthetic fibers that are combined with the indicator yarns in the indicator strands Twaron fibers, for example, with a modulus of elasticity of 100,000 to 120,000 N/mm² can be used. The other fibers of the non-indicator strands can consist of, for example, Technora fibers with 76,000 N/mm².

The aforementioned measures to monitor the rope service life can also be combined. For example, the resistance to abrasion can be provided by changing the strands matrix and, at the same time, the indicator yarn can consist of indicator fibers and synthetic fibers that in relation to stress are inferior to the other synthetic fibers.

Patent Claims

1.

5 Synthetic fiber rope consisting of strands that are arranged in at least one strand layer, a strand consisting of twisted yarns and a yarn consisting of synthetic fibers, at least one strand having at least one strand layer of indicator fibers or at least one indicator yarn to monitor
10 the rope service life, characterized in that the strands with indicator fibers or with at least one indicator yarn have a lower resistance to abrasion than the other strands.

15

2.

Synthetic fiber rope according to Claim 1, characterized in that the matrix of the strand with indicator fibers or with at least one indicator yarn has a
20 lower resistance to abrasion than the matrix of the other fibers.

3.

Synthetic fiber rope according to Claim 2, characterized in that the matrix of the strand with indicator fibers or with at least one indicator yarn is
25 impregnated with softener.

4.

30 Synthetic fiber rope according to Claim 2, characterized in that the matrix of the strand with indicator fibers or with at least one indicator yarn is executed with a lower Shore hardness than the matrix of the adjacent or other strand.

35

5.

Synthetic fiber rope according to Claim 2,
characterized in that the matrix of the strand with
5 indicator fibers or with at least one indicator yarn is
degraded by means of heat treatment and/or by means of the
addition of molecules.

6.

10 Synthetic fiber rope according to one of the foregoing
claims,
characterized in that the matrix of the other strands is
impregnated with an additive that reduces the friction
relative to the strands with indicator fibers or with at
15 least one indicator yarn.

7.

Synthetic fiber rope according to one of the foregoing
claims,
20 characterized in that the strand with indicator fibers or
with at least one indicator yarn is positioned so that its
load absorption relative to the adjacent fibers is higher.

8.

25 Method for monitoring the rope service life of a synthetic
fiber rope according to claims 1 to 7,
characterized in that the strands are permanently monitored
by means of indicator fibers.

9.

Method according to Claim 8,
characterized in that for the purpose of monitoring
5 indicator fibers at one end of the rope the indicator
fibers are connected to a signal transmitter and at the
other end of the rope the indicator fibers are connected to
a signal receiver, and that a transmission signal of the
signal transmitter is measured by means of the signal
10 receiver and on the basis of the measured or absent signal
the condition of the indicator fibers is evaluated.

10.

Method according to Claim 9,
15 characterized in that monitoring of the indicator fibers
takes place by means of optical or electric signals.

11.

Elevator with synthetic fiber rope according to one of the
20 foregoing claims.

25

30

35