

PROCESS FOR MAKING A STRIP FROM A HOT ROLLED ROD**Background Of The Invention****1. Field of the Invention**

5 The present invention relates to a process for producing a rectangular strip from a hot rolled, round rod by passing the rod consecutively through a series of rolling mills. More specifically, the invention relates to a process which employs inter-cooling between consecutive rolling mills as well as strip tension control to produce a strip which exceeds currently achievable maximum width to thickness ratios.

2. Description of the Related Art

10 Finned tubes are employed in many commercial applications as a means to allow heat exchange to occur between mediums of different temperatures without necessitating commingling of the mediums. One common design for finned tubes employs a fin constructed of a continuous strip of metal fin material. In cross section, this strip is rectangular in dimension, having a width exceeding its thickness. To form the finned tube, the strip is helically wound around the exterior surface of a hollow tube and secured thereto so that one of the shorter sides of the cross-sectional rectangular shaped strip is secured adjacent to the tube's exterior surface and the width of the strip extends outward away from and perpendicular to the tube's exterior surface.

15 For optimum performance of the finned tube, it is desirable to employ strips having a width to thickness ratio (calculated by dividing the width by the thickness) of approximately 17 to 1. For example, one common strip size has a width of 0.80 inches and a thickness of 0.047 inches resulting in a width to thickness ratio of approximately 17.2 to 1.

20 The current method for producing strips of the desired dimensions is to begin with a sheet of continuous cold rolled metal, often carbon steel, of the desired thickness. The sheet is then slit into strips of the desired width. During manufacture

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED

of the cold rolled sheets, the sheets are uniformly rolled to close tolerances. The price of these sheets reflects the time and effort required to roll them to close tolerances. When the cost of slitting the sheets is added to the cost of the sheets, the total cost to produce strips according to current methods is quite expensive.

5 The cost for producing strips could be reduced considerably if the strips could be made from less expensive hot rolled rod instead of from the cold rolled sheets. Current methods for converting a hot rolled rod into a strip generally consists of passing a rod consecutively through a series of rolling mills. Each rolling mill further flattens and widens the rod until the desired strip dimension is achieved. However,
10 certain dimensional limitations are encountered when employing currently known methods for converting rods into strips.

 Specifically, current methods for converting a rod into a strip are limited to creation of strips with width to thickness ratios of less than approximately 12 to 1. When current methods are employed to create strips having width to thickness ratios
15 exceeding approximately 12 to 1, for example having ratios of 15 to 1 or 17 to 1, during the rolling process the metal strip develops severe edge fractures. These fractures cause the strip to break. The cause these fractures appear to be two-fold. First, as the metal rod is passed through each consecutive rolling mill, heat is added to the metal until the metal finally reaches a temperature at which it fails, causing it
20 to fracture or break. Second, in addition to the heat stress exerted on the metal, mechanical stress is inflicted on the metal by the tug on the rod from the subsequent rolling mill as it pulls the rod toward the mill. This mechanical stress seems to contribute to the metal failure which is observed. Regardless of the cause of the failures, until now the practical upper limit for rolling rod into strips has been the 12
25 to 1 width to thickness ratio. Because strips having higher width to thickness ratios than 12 to 1 are necessary for construction of finned tubes, production of strips for this use from hot rolled rod has not until now been a viable option.

 The present invention addresses this problem of limited width to thickness ratio by providing a method for producing strips from rods which utilizes cooling and feed



THIS SHEET HAS BEEN
REPLACED

3

backward tension controls between adjacent rolling mills in order to produce strips having width to thickness ratios of up to approximately 17 to 1.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

SUMMARY OF THE INVENTION

The present invention is a process for creating strips from hot rolled metal rods such that the strip which is produced achieves a width to thickness ratio of approximately 17 to 1. The process consists of cooling the rod after it passes through each consecutive rolling mill to reduce the thermal stress on the rod and employs feed backward tension controllers following each consecutive rolling mill in order to control the previous rolling mill and thereby reduce the mechanical stress on the rod. Cooling is preferably accomplished by immersing the rod in a liquid cooling bath and/or by spraying cooling fluid directly on the rod.

10

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



BRIEF DESCRIPTION OF THE DRAWINGS

5 Figure 1 is a diagrammatic representation showing the process of the present invention, starting on the left-hand side with a spool of hot rolled rod and ending on the right-hand side with a strip which is rewound into a spool and ready for use or for further processing.

Figure 2 is a cross-sectional view of the rod taken along line 2-2 of Figure 1.

Figure 3 is a cross-sectional view of the partially flattened rod, taken along line 3-3 of Figure 1.

10 Figure 4 is a cross-sectional view of the further flattened rod, taken along line 4-4 of Figure 1.

Figure 5 is a cross-sectional view of the still further flattened rod, taken along line 5-5 of Figure 1.

Figure 6 is a cross-sectional view of the strip which was created by flattening the rod, taken along line 6-6 of Figure 1.

15 Figure 7 is an enlarged view of one of the liquid cooling baths and feed forward tension controllers depicted in Figure 1.

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Referring now to the drawings and initially to Figure 1, there is diagrammatically illustrated a process according to a preferred embodiment of the present invention for converting a rod 10, such as a hot rolled rod of carbon steel,
5 into a strip 12 suitable for use as a fin for a finned tube (not illustrated) or for other commercial applications. Beginning on the left-hand side of Figure 1 and moving toward the right-hand side, there is illustrated a spool 14 of rolled up rod 10 which is next unwound through an eye 16. The purpose of the eye 16 is to prevent the rod 10 from becoming tangled or kinked as it unwinds from the spool 14. Next, the rod
10 10 enters a descaler 18 which removes any scale or oxidation product present on the surface of the rod 10. After being descaled, the rod 10 enters a straightener 20 which straightens the rod 10 in preparation for entering a rolling train portion 22 of the process. The rolling train portion 22 consists of a plurality of rolling mills 24, 26, 28, 30, etc. arranged in series, with each individual rolling mill 24, 26, 28, or 30, being
15 followed by its respective liquid cooling bath 34, 36, 38 or 40. This arrangement is best illustrated in Figure 1 where the first rolling mill 24 is followed consecutively by the first liquid cooling bath 34, the second rolling mill 26, the second liquid cooling bath 36, the third rolling mill 28, the third liquid cooling bath 38, etc. until the rolling train portion 22 ends with the final rolling mill 30 followed by the final liquid cooling
20 bath 40.

As illustrated in Figures 2 through 6, as the rod 10 progresses through the rolling train portion 22, it is progressively flattened and widened, resulting in conversion of the rod 10 to the strip 12 as it exits the rolling train portion 22. The strip 12 has a width 42 and a thickness 44 measured perpendicular to its width 42.
25 Referring now to Figure 7, there is shown in enlarged detail a preferred arrangement of the first liquid cooling bath 34. Although the first liquid cooling bath 34 is illustrated and discussed, the remaining liquid cooling baths 36, 38, 40, etc. are similarly

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



arranged. The first liquid cooling bath 34 is filled with a cooling fluid 46, such as water, which enters the first liquid cooling bath 34 via an inlet 48 and exits the first liquid cooling bath 34 via an outlet 50 as will be further explained hereafter.

5 As illustrated in Figure 7, the rod 10 exits from the first rolling mill 24 upstream of the first liquid cooling bath 34. The rod 10 then enters the first liquid cooling bath 34 where the rod 10 is cooled by direct contact with the cooling fluid 46. The rod 10 is immersed in the cooling fluid as the rod 10 passes under a roller 52 provided on a feed forward tension controller 54 before reemerging from the first liquid cooling bath 34 in order to travel through the second rolling mill 26.

10 Although the process is described with cooling of the rod 10 being provided between each adjacent rolling mill 24, 26, 28, and 30, it is anticipated that adequate cooling of the rod 10 may be accomplished with fewer cooling baths 34, 36, 38, and 40, fewer cooling nozzles 58, or fewer other alternate cooling means (not illustrated).

15 The roller 52 is in rolling contact with the rod 10 which passes under the roller 52 as the rod 10 travels through the first liquid cooling bath 34. The roller 52 responds to increases in tension in the rod 10 by moving upwardly and responds to decreases in tension in the rod 10 by moving downwardly. This upward and downward movement is illustrated by the arrows shown in Figure 7. This upward and downward movement is translated into an electronic signal which controls the drive speed of the preceding first rolling mill 24, as is illustrated in Figure 7 schematically by a broken line 56 which connects the feed backward tension controller 54 and the first rolling mill 24. By controlling the speed of the preceding first rolling mill 24, mechanical stress is decreased on the rod 10 as the rod 10 exits the first rolling mill 24.

20 25 In order to maintain the cooling fluid 46 contained within the first liquid cooling bath 34 at an acceptable temperature, i.e., at a temperature below the boiling point of the cooling fluid 46, warm cooling fluid 46-W is continuously removed via the outlet 50, cooled by passing it through a conventional heat exchange process 57, and then

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



recirculating cool cooling fluid 46-C back to the first liquid cooling bath 34 via the inlet 48.

As illustrated in Figures 1 and 7, cooling nozzles 58 are optionally provided at each of the rolling mills 24, 26, 28, and 30. The purpose for these cooling nozzles 58 is to provide additional cooling in the form of cooling fluid 46 which is supplied from a cooling fluid source 60. The cooling fluid 46 enters the cooling nozzles 58 from the cooling fluid source 60 and is emitted from the cooling nozzles 58, impinging directly on the heated rod 10 as the rod 10 passes through each of the rolling mills 24, 26, 28, and 30.

Alternately, the cooling nozzles 58 may be used solely to provide the necessary cooling of the rod 10, thereby eliminating the need for cooling baths 34-40. Although the cooling nozzles 58 and the cooling baths 34-40 have been described for use with cooling fluid 46, other coolants, not illustrated, such as liquids or gases may be substituted for the cooling fluid, and other alternate cooling means, not illustrated, may be employed instead of either cooling nozzles 58 or cooling baths 34-40.

Once the strip 12 is produced, the strip 12 is rewound into a spool 62, as illustrated in Figure 1. The spool 62 of strip 12 is then ready for use or for further processing.

Examples of results achieved:

The following data illustrates the results which have been successfully attained employing this process.

Example 1:

<u>Rod Diameter:</u>	7/16"
<u>Number and Size of Rolling Mills:</u>	4 10" Diameter Rolls
<u>Width of Strip:</u>	0.80"
<u>Thickness of Strip:</u>	0.048"
<u>Width/Thickness Ratio:</u>	17:1

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



Example 2:

Rod Diameter: 1/2"

Number of Rolling Mills: 5 6 1/2" Diameter Rolls

Width of Strip: 0.80"

Thickness of Strip: 0.048"

Width/Thickness Ratio: 17:1

Although this process has been described in terms of producing carbon steel strips to be used in producing finned tubes, the process is not so limited and may be employed to produce strips of different metal compositions or strips for use in different functional applications.

While the invention has been described with a certain degree of particularity, it is manifest that many changes may be made in the details of construction and the arrangement of components without departing from the spirit and scope of this disclosure. It is understood that the invention is not limited to the embodiments set forth herein for the purposes of exemplification, but is to be limited only by the scope of the attached claim or claims, including the full range of equivalency to which each element thereof is entitled.

THIS SHEET HAS BEEN
REPLACED

This Sheet Has Been Replaced



CLAIMS**What is claimed is:**

- 1 1. A process for creating a strip from a rod comprising passing a rod through a
2 series of rolling mills and cooling the rod as the rod passes between consecutive
3 rolling mills.
- 1 2. A process according to claim 1 wherein the cooling of the strip is accomplished
2 by immersing the rod in a cooling fluid.
- 3 3. A process according to claim 2 wherein the cooling fluid employed is water.
- 1 4. A process according to claim 2 wherein the cooling of the strip is further
2 accomplished by spraying cooling fluid onto the rod.
- 1 5. A process according to claim 4 wherein the cooling fluid employed is water.
- 1 6. A process according to claim 1 wherein the cooling of the strip is accomplished
2 by spraying cooling fluid onto the rod.
- 1 7. A process according to claim 6 wherein the cooling fluid employed is water.
- 1 8. A process according to claim 1 further comprising monitoring tension in the
2 rod immediately downstream of each rolling mill with a feed backward tension
3 controller and employing the feed backward tension controllers to control speed of the
4 adjacent upstream rolling mill.

This Sheet Has Been Replaced

**THIS SHEET HAS BEEN
REPLACED**



9. A process for creating a strip from a rod comprising the following steps:

1. cleaning and straightening a rod,
2. passing the rod through a rolling mill,
3. cooling the rod,
4. repeating steps 2 and 3 until a strip of the desired dimensions is produced.

10. A process according to claim 9 wherein the cooling of step 3 is accomplished by immersing the rod in a cooling bath filled with cooling fluid.

11. A process according to claim 10 wherein the cooling bath is filled with water.

12. A process according to claim 9 wherein speed of each of the rolling mills is controlled by a feed backward tension controller which continuously monitors tension of the rod.

13. A process according to claim 12 wherein the cooling of step 3 is further accomplished by spraying cooling fluid onto the rod from spray heads located at each rolling mill.

14. A process according to claim 13 wherein the cooling fluid is water.


This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED



12

**AMENDED CLAIMS**

[received by the International Bureau on 23 July 1996 (23.07.96);
original claims 1 and 9 amended; remaining claims unchanged (2 pages)]

- 1 1. A process for creating a strip from a rod comprising passing a rod through a
2 series of rolling mills, cooling the rod as the rod passes between consecutive rolling
3 mills and minimizing tension on the rod as the rod passes between consecutive rolling
4 mills.

- 1 2. A process according to claim 1 wherein the cooling of the strip is accomplished
2 by immersing the rod in a cooling fluid.

- 1 3. A process according to claim 2 wherein the cooling fluid employed is water.

- 1 4. A process according to claim 2 wherein the cooling of the strip is further
2 accomplished by spraying cooling fluid onto the rod.

- 1 5. A process according to claim 4 wherein the cooling fluid employed is water.

- 1 6. A process according to claim 1 wherein the cooling of the strip is accomplished
2 by spraying cooling fluid onto the rod.

- 1 7. A process according to claim 6 wherein the cooling fluid employed is water.

- 1 8. A process according to claim 1 further comprising monitoring tension in the
2 rod immediately downstream of each rolling mill with a feed backward tension
3 controller and employing the feed backward tension controllers to control speed of the
4 adjacent upstream rolling mill.

**THIS SHEET HAS BEEN
REPLACED**

This Sheet Has Been Replaced






- 1 9. A process for creating a strip from a rod comprising the following steps:
- 2 1. cleaning and straightening a rod,
- 3 2. passing the rod through a rolling mill,
- 4 3. cooling the rod and minimizing tension on the rod,
- 5 4. repeating steps 2 and 3 until a strip of the desired dimensions is
- 6 produced.
- 1 10. A process according to claim 9 wherein the cooling of step 3 is accomplished
- 2 by immersing the rod in a cooling bath filled with cooling fluid.
- 1 11. A process according to claim 10 wherein the cooling bath is filled with water.
- 1 12. A process according to claim 9 wherein speed of each of the rolling mills is
- 2 controlled by a feed backward tension controller which continuously monitors tension
- 3 of the rod.
- 1 13. A process according to claim 12 wherein the cooling of step 3 is further
- 2 accomplished by spraying cooling fluid onto the rod from spray heads located at each
- 3 rolling mill.
- 1 14. A process according to claim 13 wherein the cooling fluid is water.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED






Fig. 1




Fig. 6




Fig. 5




Fig. 4




Fig. 3




Fig. 2

2/2





Fig. 7



Amex

1

PROCESS FOR MAKING A STRIP FROM A HOT ROLLED ROD

Background Of The Invention

1. Field of the Invention

5 The present invention relates to a process for producing a rectangular strip from a hot rolled, round rod by passing the rod consecutively through a series of rolling mills. More specifically, the invention relates to a process which employs inter-cooling between consecutive rolling mills as well as strip tension control to produce a strip which exceeds currently achievable maximum width to thickness ratios.

2. Description of the Related Art

10 Finned tubes are employed in many commercial applications as a means to allow heat exchange to occur between mediums of different temperatures without necessitating commingling of the mediums. One common design for finned tubes employs a fin constructed of a continuous strip of metal fin material. In cross section, this strip is rectangular in dimension, having a width exceeding its thickness. To form the finned tube, the strip is helically wound around the exterior surface of a hollow tube and secured thereto so that one of the shorter sides of the cross-sectional rectangular shaped strip is secured adjacent to the tube's exterior surface and the width of the strip extends outward away from and perpendicular to the tube's exterior surface.

20 For optimum performance of the finned tube, it is desirable to employ strips having a width to thickness ratio (calculated by dividing the width by the thickness) of approximately 17 to 1. For example, one common strip size has a width of 2.032 centimeters (0.80 inches) and a thickness of 0.1938 centimeters (0.047 inches) resulting in a width to thickness ratio of approximately 17.2 to 1.

25 The current method for producing strips of the desired dimensions is to begin with a sheet of continuous cold rolled metal, often carbon steel, of the desired thickness. The sheet is then slit into strips of the desired width. This is briefly described in an article entitled "The Rolling of Round Wire into Flats/Rectangles"

AMENDED SHEET

published in the October, 1959 issue of FENN Engineering News, a publication by Fenn Manufacturing Co., Newington, Connecticut, U.S.A. During manufacture of the cold rolled sheets, the sheets are uniformly rolled to close tolerances. The price of these sheets reflects the time and effort required to roll them to close tolerances. When the cost of slitting the sheets is added to the cost of the sheets, the total cost to produce strips according to current methods is quite expensive.


The cost for producing strips could be reduced considerably if the strips could be made from less expensive hot rolled rod instead of from the cold rolled sheets. Current methods for converting a hot rolled rod into a strip generally consists of passing a rod consecutively through a series of rolling mills. This is described in an article entitled "Wire-Flattening-Theory and Practice" produced by Stanat Precision Machine Company of Schiller Park, Illinois, U.S.A. Each rolling mill further flattens and widens the rod until the desired strip dimension is achieved. However, certain dimensional limitations are encountered when employing currently known methods for converting rods into strips.

Specifically, current methods for converting a rod into a strip are limited to creation of strips with width to thickness ratios of less than approximately 12 to 1. When current methods are employed to create strips having width to thickness ratios exceeding approximately 12 to 1, for example having ratios of 15 to 1 or 17 to 1, during the rolling process the metal strip develops severe edge fractures. These fractures cause the strip to break. The cause these fractures appear to be two-fold. First, as the metal rod is passed through each consecutive rolling mill, heat is added to the metal until the metal finally reaches a temperature at which it fails, causing it to fracture or break. Second, in addition to the heat stress exerted on the metal, mechanical stress is inflicted on the metal by the tug on the rod from the subsequent rolling mill as it pulls the rod toward the mill. Exerting a significant pulling or tugging force on a rod is the basis upon which rolling of rod has been accomplished in the past, for example, as described in United States Patent No. 2,226,948. This mechanical stress seems to contribute to the metal failure which is observed. Regardless of the cause of the failures, until now the practical upper limit for rolling rod into strips has been the 12 to 1 width to thickness ratio. Because strips having

higher width to thickness ratios than 12 to 1 are necessary for construction of finned tubes, production of strips for this use from hot rolled rod has not until now been a viable option.

5 The present invention addresses this problem of limited width to thickness ratio by providing a method for producing strips from rods which utilizes cooling and tension controls between adjacent rolling mills in order to minimize tension on the material being rolled so that it is possible to produce strips having width to thickness ratios of up to approximately 17 to 1.

10 The present invention is a cold rolling processes, and as such, should be distinguished from hot rolling processes such as those described in EP-A O 314 667.



THIS SHEET HAS BEEN
REPLACED


This Sheet Has Been Replaced

A standard 1D barcode with vertical black bars of varying widths on a white background.

AMENDED SHEET

SUMMARY OF THE INVENTION

5 The present invention is a process for creating strips from hot rolled metal rods such that the strip which is produced achieves a width to thickness ratio of approximately 17 to 1. The process consists of cooling the rod after it passes through each consecutive rolling mill to reduce the thermal stress on the rod and employs tension controllers following each consecutive rolling mill in order to control the previous rolling mill and thereby reduce the mechanical stress on the rod. Cooling is preferably accomplished by immersing the rod in a liquid cooling bath and/or by spraying cooling fluid directly on the rod.



BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a diagrammatic representation showing the process of the present invention, starting on the left-hand side with a spool of hot rolled rod and ending on the right-hand side with a strip which is rewound into a spool and ready for use or for further processing.

Figure 2 is a cross-sectional view of the rod taken along line 2-2 of Figure 1.


Figure 3 is a cross-sectional view of the partially flattened rod, taken along line 3-3 of Figure 1.


Figure 4 is a cross-sectional view of the further flattened rod, taken along line 4-4 of Figure 1.

Figure 5 is a cross-sectional view of the still further flattened rod, taken along line 5-5 of Figure 1.

Figure 6 is a cross-sectional view of the strip which was created by flattening the rod, taken along line 6-6 of Figure 1.

Figure 7 is an enlarged view of one of the liquid cooling baths and tension controllers depicted in Figure 1.




**DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT**

Referring now to the drawings and initially to Figure 1, there is diagrammatically illustrated a process according to a preferred embodiment of the present invention for converting a rod 10, such as a hot rolled rod of carbon steel, into a strip 12 suitable for use as a fin for a finned tube (not illustrated) or for other commercial applications. Beginning on the left-hand side of Figure 1 and moving toward the right-hand side, there is illustrated a spool 14 of rolled up rod 10 which is next unwound through an eye 16. The purpose of the eye 16 is to prevent the rod 10 from becoming tangled or kinked as it unwinds from the spool 14. Next, the rod 10 enters a descaler 18 which removes any scale or oxidation product present on the surface of the rod 10. After being descaled, the rod 10 enters a straightener 20 which straightens the rod 10 in preparation for entering a rolling train portion 22 of the process. The rolling train portion 22 consists of a plurality of rolling mills 24, 26, 28, 30, etc. arranged in series, with each individual rolling mill 24, 26, 28, or 30, being followed by its respective liquid cooling bath 34, 36, 38 or 40. This arrangement is best illustrated in Figure 1 where the first rolling mill 24 is followed consecutively by the first liquid cooling bath 34, the second rolling mill 26, the second liquid cooling bath 36, the third rolling mill 28, the third liquid cooling bath 38, etc. until the rolling train portion 22 ends with the final rolling mill 30 followed by the final liquid cooling bath 40. As indicated by employment of spool 14, descaler 18 and cooling baths 34, 36 and 38, the present invention is limited to use as a cold rolling process.

As illustrated in Figures 2 through 6, as the rod 10 progresses through the rolling train portion 22, it is progressively flattened and widened, resulting in conversion of the rod 10 to the strip 12 as it exits the rolling train portion 22. The strip 12 has a width 42 and a thickness 44 measured perpendicular to its width 42. Referring now to Figure 7, there is shown in enlarged detail a preferred arrangement of the first liquid cooling bath 34. Although the first liquid cooling bath 34 is illustrated and discussed, the remaining liquid cooling baths 36, 38, 40, etc. are similarly

AMENDED SHEET




arranged. The first liquid cooling bath **34** is filled with a cooling fluid **46**, such as water, which enters the first liquid cooling bath **34** via an inlet **48** and exits the first liquid cooling bath **34** via an outlet **50** as will be further explained hereafter.

As illustrated in Figure 7, the rod **10** exits from the first rolling mill **24** upstream of the first liquid cooling bath **34**. The rod **10** then enters the first liquid cooling bath **34** where the rod **10** is cooled by direct contact with the cooling fluid **46**. The rod **10** is immersed in the cooling fluid as the rod **10** passes under a roller **52** provided on a tension controller **54** before reemerging from the first liquid cooling bath **34** in order to travel through the second rolling mill **26**.

Although the process is described with cooling of the rod **10** being provided between each adjacent rolling mill **24**, **26**, **28**, and **30**, it is anticipated that adequate cooling of the rod **10** may be accomplished with fewer cooling baths **34**, **36**, **38**, and **40**, fewer cooling nozzles **58**, or fewer other alternate cooling means (not illustrated).

The roller **52** is in rolling contact with the rod **10** which passes under the roller **52** as the rod **10** travels through the first liquid cooling bath **34**. The roller **52** responds to increases in tension in the rod **10** by moving upwardly and responds to decreases in tension in the rod **10** by moving downwardly. This upward and downward movement is illustrated by the arrows shown in Figure 7. This upward and downward movement is translated into an electronic signal which controls the drive speed of the preceding first rolling mill **24**, as is illustrated in Figure 7 schematically by a broken line **56** which connects the tension controller **54** and the first rolling mill **24**. By controlling the speed of the preceding first rolling mill **24**, mechanical stress is decreased on the rod **10** as the rod **10** exits the first rolling mill **24**.

In order to maintain the cooling fluid **46** contained within the first liquid cooling bath **34** at an acceptable temperature, i.e., at a temperature below the boiling point of the cooling fluid **46**, warm cooling fluid **46-W** is continuously removed via the outlet **50**, cooled by passing it through a conventional heat exchange process **57**, and then recirculating cool cooling fluid **46-C** back to the first liquid cooling bath **34** via the inlet **48**.



As illustrated in Figures 1 and 7, cooling nozzles 58 are optionally provided at each of the rolling mills 24, 26, 28, and 30. The purpose for these cooling nozzles 58 is to provide additional cooling in the form of cooling fluid 46 which is supplied from a cooling fluid source 60. The cooling fluid 46 enters the cooling nozzles 58 from the cooling fluid source 60 and is emitted from the cooling nozzles 58, impinging directly on the heated rod 10 as the rod 10 passes through each of the rolling mills 24, 26, 28, and 30.

Alternately, the cooling nozzles 58 may be used solely to provide the necessary cooling of the rod 10, thereby eliminating the need for cooling baths 34-40. Although the cooling nozzles 58 and the cooling baths 34-40 have been described for use with cooling fluid 46, other coolants, not illustrated, such as liquids or gases may be substituted for the cooling fluid, and other alternate cooling means, not illustrated, may be employed instead of either cooling nozzles 58 or cooling baths 34-40.

Once the strip 12 is produced, the strip 12 is rewound into a spool 62, as illustrated in Figure 1. The spool 62 of strip 12 is then ready for use or for further processing.

Examples of results achieved:

The following data illustrates the results which have been successfully attained employing this process.

Example 1:

<u>Rod Diameter:</u>	1.111 centimeters (7/16")
<u>Number and Size of Rolling Mills:</u>	4 25.4 centimeters (10")
	Diameter Rolls
<u>Width of Strip:</u>	2.032 centimeters (0.80")
<u>Thickness of Strip:</u>	0.1219 centimeters (0.048")
<u>Width/Thickness Ratio:</u>	17:1

Example 2:

Rod Diameter: 1.27 centimeters (1/2")

Number of Rolling Mills: 5 16.51 centimeters (6 1/2") Diameter Rolls


Width of Strip: 2.032 centimeters (0.80")

Thickness of Strip: 0.1219 centimeters (0.048")

Width/Thickness Ratio: 17:1

Although this process has been described in terms of producing carbon steel strips to be used in producing finned tubes, the process is not so limited and may be employed to produce strips of different metal compositions or strips for use in different functional applications.

While the invention has been described with a certain degree of particularity, it is manifest that many changes may be made in the details of construction and the arrangement of components without departing from the spirit and scope of this disclosure. It is understood that the invention is not limited to the embodiments set forth herein for the purposes of exemplification, but is to be limited only by the scope of the attached claim or claims, including the full range of equivalency to which each element thereof is entitled.




AMENDED SHEET



10

CLAIMS



What is claimed is:

1 1. A cold rolling process for creating a strip (12) from a rod (10) comprising
2 passing a rod (10) through a series of cold processing rolling mills (24-30), cooling
3 the rod (10) as the rod (10) passes between consecutive rolling mills (24-30) and
4 minimizing tension on the rod (10) as the rod (10) passes between consecutive
5 rolling mills (24-30).

1 2. A process according to Claim 1 wherein the cooling of the rod (10) is
2 accomplished by immersing the rod (10) in a cooling fluid (46).

1 3. A process according to Claim 2 wherein the cooling fluid (46) employed is
2 water.


1 4. A process according to Claim 2 wherein the cooling of the rod (10) is further
2 accomplished by spraying cooling fluid onto the rod (10).

1 5. A process according to Claim 4 wherein the cooling fluid (46) employed is
2 water.

1 6. A process according to Claim 1 wherein the cooling of the rod (10) is
2 accomplished by spraying cooling fluid (46) onto the rod (10).

1 7. A process according to Claim 6 wherein the cooling fluid (46) employed is
2 water.

1 8. A process according to Claim 1 further comprising monitoring tension in the
2 rod (10) immediately downstream of each rolling mill (24-30) with a tension controller



3 (54) and employing the tension controllers (54) to control speed of an adjacent
4 upstream rolling mill (24-28).

1 9. A process according to Claim 1 wherein said rod (10) is steel.

1 10. A process according to Claim 1 further comprising cleaning and straightening
2 said rod (10) prior to passing said rod (10) through said series of cold processing
3 rolling mills (24-30).

1 11. A process according to Claim 10 wherein said rod (10) is steel.

1 12. A process according to Claim 11 wherein the cooling is accomplished by
2 immersing the rod (10) in a cooling bath (34-40) filled with cooling fluid (46).

1 13. A process according to Claim 12 wherein the cooling bath (34-40) is filled with
2 water.

1 14. A process according to Claim 13 wherein the cooling is further accomplished
2 by spraying cooling fluid (46) onto the rod (10) from cooling nozzles (58) located at
3 each rolling mill (24-30).

1 15. A process according to Claim 14 wherein the cooling fluid (46) is water.

1 16. A process according to Claim 11 wherein speed of each of the rolling mills
2 (24-30) is controlled by a tension controller (54) which continuously monitors tension
3 of the rod (10).

This Sheet Has Been Replaced




THIS SHEET HAS BEEN
REPLACED

AMENDED SHEET

PROCESS FOR MAKING A STRIP FROM A HOT ROLLED**Abstract Of The Disclosure**


The invention is a process which converts rods of hot rolled metal into strips with width to thickness ratios as high as approximately 17 to 1. The process cools the rod between successive rolling mills and employs tension controls to direct the speed of each individual upline rolling mill in order to reduce the thermal and mechanical shock experienced by the rod as it is flattened into a strip.



higher width to thickness ratios than 12 to 1 are necessary for construction of finned tubes, production of strips for this use from hot rolled rod has not until now been a viable option.

The present invention addresses this problem of limited width to thickness ratio by providing a method for producing strips from rods which utilizes cooling and tension controls between adjacent rolling mills in order to minimize tension on the material being rolled so that it is possible to produce strips having width to thickness ratios of up to approximately 17 to 1.

The present invention is a cold rolling ~~processes~~ process and as such should be distinguished from hot rolling ~~processes~~ processing such as those described in EP-A-O 314 667.



This Sheet Has Been Replaced





3 (54) and employing the tension controllers (54) to control speed of an adjacent
4 upstream rolling mill (24-28).

1 9. A process according to Claim 1 wherein said rod (10) is steel.

1 10. A process according to Claim 1 further comprising cleaning and straightening
2 said rod (10) prior to passing said rod (10) through said series of cold processing
3 rolling mills (24-30).

1 11. A process according to Claim 10 wherein said rod (10) is steel.

1 12. A process according to Claim 11 wherein the cooling is accomplished by
2 immersing the rod (10) in a cooling bath (34-40) filled with cooling fluid (46).

1 13. A process according to Claim 12 wherein the cooling bath (34-40) is filled
2 with water.

1 14. A process according to Claim 13 wherein the cooling is further accomplished
2 by spraying cooling fluid (46) onto the rod (10) from cooling nozzles (58) located at
3 each rolling mill (24-30).

1 15. A process according to Claim 14 wherein the cooling fluid (46) is water.

1 16. A process according to Claim 11 wherein speed of each of the rolling mills
2 (24-30) is controlled by a tension controller (54) which continuously monitors tension
3 of the rod (10).


1 17. A cold rolling process for creating a strip from a steel rod comprising the
2 following steps:

3 1. cleaning and straightening a steel rod.

4 2. passing the rod through a rolling mill.

5 3. cooling the rod and minimizing tension on the rod.


6 4. repeating steps 2 and 3 until a strip of the desired dimensions is produced.



higher width to thickness ratios than 12 to 1 are necessary for construction of finned tubes, production of strips for this use from hot rolled rod has not until now been a viable option.

The present invention addresses this problem of limited width to thickness ratio by providing a method for producing strips from rods which utilizes cooling and tension controls between adjacent rolling mills in order to minimize tension on the material being rolled so that it is possible to produce strips having width to thickness ratios of up to approximately 17 to 1.

The present invention is a cold rolling ~~processes~~ process and as such should be distinguished from hot rolling ~~processes~~ processing processes such as those described in EP-A-O 314 667.



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B21B 1/16, 45/02, 37/50	A1	(11) International Publication Number: WO 96/30135 (43) International Publication Date: 3 October 1996 (03.10.96)
--	----	--

(21) International Application Number: PCT/US95/03752

(22) International Filing Date: 31 March 1995 (31.03.95)


(71) Applicant: FINTUBE LIMITED PARTNERSHIP [US/US];
4150 South Elwood, Tulsa, OK 74107-5822 (US).(72) Inventors: RYAN, Jerry, E.; 3201 East 56th Street, Tulsa, OK
74136 (US). McREYNOLDS, James, C.; 941 Henshaw,
Sapulpa, OK 74066 (US). BUTCHKO, Thomas, J.; 245
East 28th Street, Tulsa, OK 74114 (US).(74) Agent: McKAY, Molly, D.; Molly D. McKay, P.C., Suite 212,
810 S. Cincinnati, Tulsa, OK 74119-1612 (US).(81) Designated States: CN, JP, KP, KR, MX, SG, European patent
(AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE).

Published

With international search report.

With amended claims and statement.

(54) Title: PROCESS FOR MAKING A STRIP FROM A HOT ROLLED ROD



(57) Abstract

The invention is a process which converts rods of hot rolled metal into strips with width to thickness ratios as high as approximately 17 to 1. The process cools the rod between successive rolling mills and employs feed backward tension controls to direct the speed of each individual upline rolling mill in order to reduce the thermal and mechanical shock experienced by the rod as it is flattened into a strip.

This Sheet Has Been Replaced

