

Method for producing spray powders containing chromium nitride

The present invention relates to a process for producing chromium nitride-
5 containing sintered spraying powders. Such sintered spraying powders can be
used for coating wear parts, construction components or tools by thermal
spraying. In particular, the spraying powder produced by means of the process of
the invention can be used for the surface coating of wear parts, construction
10 components and tools in the case of highly stressed friction pairings when these
friction pairings tend to undergo frictional welding or microwelding, for example
in the case of internal combustion engines, piston compressors or piston
machines or piston rods.

Wear frequently determines the life of a component. Optimizations within a
15 tribological system therefore directly increase the life and thus reduce costs for
the user. Components of this type are provided with coatings in order to improve
the tribological and wear properties. Coatings display, in a manner analogous to
massive materials, various properties which can be determined empirically.
These include, for example, hardness, wear resistance and corrosion behavior in
20 various media. In many applications, however, the frictional behavior of coatings
opposite a second friction partner plays a particular role. These are, for example,
coated piston rods which run in a guide sheath made of steel or cast iron. The
behavior of the friction pairing "coating/friction partner" is of predominant
importance in, for example, (internal) combustion engines where coated piston
25 rings run in a bushing made of, for example, grey cast iron or AlSi alloys. In such
applications in particular, CrN has been found to be particularly useful. Coatings
composed of or containing CrN are therefore widely applied by PVD (physical
vapor deposition) to piston rings for (internal) combustion engines, piston
compressors and similar piston machines, and also to extruder screws and
30 similar components. Such layers allow good running performance with minimal
wear and are now widely established in the motor vehicle sector. However, a
disadvantage is a high capital outlay for plant engineering, which is economical
only in the case of large numbers and of small components. In the case of larger
components or thicker layers, CrN has hitherto not been applied economically by

means of PVD. In addition, stresses caused by different coefficients of thermal expansion of substrate and layer material build up in PVD layers with increasing layer thickness. Such stresses lead to crack formation through to detachment of the layer. This results in insufficient wear reserves being present because the layer thickness is too low for many applications in highly stressed friction pairings. Coatings produced by means of PVD have low roughnesses of less than 10 μm , which is very advantageous for friction pairings. Thermal spraying is an alternative to PVD. Thermal spraying powders are used for producing coatings on substrates. Here, pulverulent particles are introduced into a combustion flame or plasma flame which is directed at the (usually metallic) substrate which is to be coated. The particles melt completely or partly in the flame, impinge on the substrate, solidify there and form the coating in the form of solidified "splats". Coatings produced by thermal spraying can have a layer thickness up to several 100 μm and often consist of one or more usually ceramic and/or metallic component(s). Here, the metallic component is able to dissipate thermally induced stresses (residual stress) in the layer by plastic flow, while the ceramic hard phase produces the necessary wear resistance of the layer. In addition, thermally sprayed layers often have porosities which is advantageous for dissipating stresses.

Wear surfaces having tribologically adjusted friction pairings, in particular piston rings and piston rods, are thermally coated in industry with thermal spraying powders based on molybdenum carbide or chromium carbide in combination with metals and alloys such as nickel, molybdenum, nickel-chromium ("thermal spraying"). This makes possible to produce layers having a thickness of up to a few 100 μm . Such layers and the spraying powders used consist in each case of at least one metallic component (e.g. NiCrBSi alloy, molybdenum) and a hardness carrier which modulates the wear of the piston ring (e.g. chromium carbides and/or molybdenum carbides).

However, the intrinsic hardness of these hardness carriers must not be too high since otherwise the cylinder surface is cut. For this reason, hard materials having a high intrinsic hardness, e.g. titanium carbide or tungsten carbide, are not used. It is usual to use carbides which have an intrinsic hardness of less than 2000 HV,

e.g. Cr carbides and Mo carbides, as hardness carriers. The latter has an intrinsic hardness of 1900 HV (Mo_2C). The particle size of these hardness carriers is preferably as small as possible so as to polish and not cut the cylinder surface. This also applies to any additional oxides present, e.g. chromium oxide or aluminum oxide.

Thermal spraying powders comprising hardness carriers can be produced in various ways.

Agglomerated and subsequently intrinsically sintered (sintered together in itself) spraying powders are produced by dispersing (disparging) pulverulent hardness carriers together with metallic binder alloys in powder form (for example Ni or Ni-based alloy powders) in a liquid and then carrying out a granulation step by separating off the liquid, for example by means of spray drying. This gives particles which consist of an agglomerated mixture of the powders used. These agglomerates have a mechanical strength which is typically unsuitable for modern spraying processes such as HVOF ("High Velocity Oxygen Fuel") since these require mechanically stable agglomerates because of the high flame velocities. The spray-dried granulate (granules) is subsequently optionally screened (classified/sized) and intrinsically sintered in a subsequent thermal process step to such an extent that the granulate has a mechanical strength which is sufficient for it not to disintegrate (collapse/degrade) during the thermal spraying process, e.g. by means of HVOF. The thermal process step ("sintering") is usually carried out either under reduced pressure or under a protective gas which avoids oxidation in the vicinity of atmospheric pressure, usually hydrogen, optionally with proportions of argon and/or other noble gases. This gives a powder or a loosely sintered cake which can easily be converted back into powder, in this case the spraying powder. The powders obtained are similar in size and appearance to the spray-dried granulate. This intrinsically sintered agglomerate will hereinafter be referred to as "sintered agglomerate". It is therefore customary in industry to speak of "agglomerated/sintered spraying powders" and of "agglomerated/sintered powders". The typical internal structure of such agglomerated/sintered spraying powders can be seen from Figure A.1 in DIN EN 1274 (February 2005). The two powder components (hard material and

metallic matrix) can be seen clearly. Agglomerated/sintered spraying powders are particularly advantageous since they offer great freedom in the choice of the components (for example their contents and particle sizes) and can be readily metered in the spraying process because of their good flowability. In particular, it is possible to use very fine hardness carriers which in use leads to very smooth wear surfaces, which in turn leads to low coefficients of friction and high operating lives during use of the friction surface. The particle size of the pulverulent hardness carriers is typically below 10 µm. Particularly finely divided carbides are obtained by reacting metallic components with carbon during sintering, as is practiced in the case of Mo- and NiCr-containing spraying powders.

Sintered and subsequently crushed spraying powders ("sintered/crushed spraying powders") are produced in a manner analogous to agglomerated/sintered spraying powders, with the difference that the powder components are not necessarily mixed wet in dispersion but can be dry mixed and optionally tableted or compacted to form shaped bodies. The subsequent sintering is carried out analogously, but the temperature and/or any precompaction is effected in such a way that compact, solid sintered bodies are obtained and have to be converted back into powder form by action of mechanical force. The powders obtained are therefore irregular in shape and characterized by fracture phenomena on the surface. They also typically have no or barely any internal porosity as is typical in the case of agglomerated/sintered spraying powders. Figure A.6 of DIN EN 1274 (February 2005) shows the typical structure of sintered/crushed spraying powders. The starting powders can barely be discerned. These spraying powders display significantly poorer flowability, which is disadvantageous for a constant application rate during thermal spraying, but is often still practicable.

"Cladded" spraying powders are obtained when the pulverulent hardness carrier is coated with the metallic component by means of electrolytic or electroless deposition. For example, the hardness carrier can be dispersed in pulverulent form in a nickel salt solution, whereupon a shell having a thickness of a few µm is deposited on it by means of electrolytic or chemical reduction. However, this

process can be carried out only above a particle size of the hardness carrier of about 10 μm since otherwise due to the small radii of curvature on the surface of the hardness carrier the nucleation energies required for fresh formation of the metallic phase increase too greatly and a shell is no longer obtained. The layers obtained after thermal spraying therefore contain relatively coarse hard material particles and thus hardness carriers projecting from the layer surface, which is disadvantageous for a very smooth wear surface. Figure A.2 of EN 1274 (February 2005) shows the typical shape of a metal-cladded hard material.

- 10 A further embodiment of spraying powders composed of a plurality of different powders are "blends". These are a simple mixture of powders which is then used for coating. However, in the case of modern coating processes such as the HVOF process, demixing (segregation) of the powder components usually occurs as a result of the high flow velocity and the turbulences, and the composition of the layer therefore no longer corresponds to the composition of the blend.

Hardness carriers which are of particular interest for friction coatings are nitrides. They generally have lower intrinsic hardnesses than the corresponding carbides or even borides, thus TiN has a hardness of 2450 kg/mm^2 (for comparison: TiC 3200 kg/mm^2). For example, chromium carbides have intrinsic hardnesses in the range from 1880 kg/mm^2 (Cr_7C_3) and 1663 kg/mm^2 (Cr_{23}C_6), whereas Cr_2N has a hardness of 1591 kg/mm^2 and CrN a hardness of only 1093 kg/mm^2 . It is clear from this why pure CrN has become established as coating material for piston rings. While Cr_2N has an intrinsic hardness of the same order of magnitude as chromium carbides, and is thus tribologically suitable for friction pairings, CrN has a lower intrinsic hardness. The far higher hardnesses measured for PVD coatings are due to residual stresses and the particular substructure of the coating and must not be compared with the hardnesses determined on crystallites ("intrinsic hardnesses").

30

In addition, chromium nitrides have excellent resistance to frictional wear and due to their pronounced chemical inertness are insensitive to microwelding phenomena as have to be avoided in many uses because of the resulting adhesion wear.

It would therefore be desirable to have agglomerated/sintered spraying powders having a metallic component such as nickel and containing chromium nitrides as hardness carriers. These would make it possible to produce thicker layers which would have sufficient wear reserves.

Agglomerated/sintered spraying powders or sintered/crushed spraying powders (in the present disclosure described collectively as "sintered spraying powders"), in particular ones containing CrN, have hitherto not become known. The reason is that decomposition of the CrN into Cr₂N, from Cr₂N to metallic chromium and, depending on the presence of carbon during sintering, also a further reaction to form Cr carbides, whose intrinsic hardnesses are all higher, occurs during sintering of chromium nitride-containing granulates or powder mixtures. Owing to the rapidity of the spraying process and the splitting-off the nitrogen being slower, compared to heat transport, due to diffusive transport, it can be assumed that sintered spraying powders could also produce chromium nitride-containing coatings if sintered spraying powders of this type could be produced.

Owing to the high melting points in the production of atomized spraying powders, the nitrogen content necessary for formation of significant contents of chromium nitrides cannot be obtained in the melt since the solubility of nitrogen in it is too low.

A further possible way of producing chromium nitride-containing coatings is the use of powder mixtures ("blends"), for example mixtures of Ni or NiCr powder with chromium nitrides and optionally other hardness carriers. However, a disadvantage is that comparatively coarse hardness carriers have to be used in order that the oxidation thereof is sufficiently slow during thermal spraying and sufficient kinetic energy is present on impingement. Typical particle sizes for hardness carriers and matrix metal are in this case from 10 to 100 µm. Layers produced in this way accordingly have high roughnesses and poor distribution of hardness carriers in the metallic matrix. Blends are therefore not alternatives.

DE 10 2008 056 720 B3 describes the production of a sprayed layer, which serves as sliding element in an (internal) combustion engine, from chromium nitride-containing spraying powders whose production process is not disclosed. The sliding layer has a nominal composition of from 10 to 30% of Ni, from 0.1 to 5% of carbon, from 10 to 20% of nitrogen and from 40 to 79.9% of chromium. The spraying powder which is described in the working example and whose production method is unknown had a nominal composition of 60% of CrN, 10% of Cr_3C_2 , 25% of Ni and 5% of Cr. The homogeneous distribution of the carbides (i.e., the 10% of Cr_3C_2 contained in the spraying powder) in the sprayed layer is described. The size and distribution of the CrN is likewise not disclosed. The CrN used led, in the elemental analysis, to only 11% of nitrogen instead of the theoretically to be expected 12.72%. It can therefore be deduced that the chromium nitride component described as "CrN" cannot be pure CrN since otherwise a nitrogen content of 12.7% would be expected in the elemental analysis. It can be calculated from the indicated 11% of nitrogen that the chromium nitride component present to an extent of 60% in the spraying powder consisted of only 41% of CrN containing 21.2% of N and of 19% of Cr_2N containing 12.1% of N, i.e. it consisted of 68.3% of CrN and 31.7% of Cr_2N . According to the disclosure, the wear properties of the CrN PVD coating were therefore presumably not achieved (Table 1 of DE 10 2008 056 720 B3). In addition, the powder disclosed contains chromium carbides, which can be seen from the material system disclosed, the structural micrographs of the sprayed layer ("homogeneously distributed carbides") and the elemental analysis. Owing to the high intrinsic hardness of the chromium carbides, the chromium nitride-based sliding coating cannot display its full potential and is not comparable in terms of performance with the CrN coating produced by means of PVD.

It is an object of the invention to solve the abovementioned problems of the prior art. In particular, it was an object of the present invention to provide a process for producing chromium nitride-containing, in particular CrN-containing, sintered spraying powders which have a sufficient agglomerate strength for the spraying process.

It has been found that a solution to this problem comprises production of an agglomerate of chromium or CrN or Cr₂N with a metallic binder alloy and subsequent sintering in a nitrogen atmosphere under superatmospheric pressure (overpressure/excess pressure) in which Cr can react to form chromium nitrides or Cr₂N can react to form CrN or the chromium nitrides can be at least retained.

The present invention provides a process for producing chromium nitride-containing sintered spraying powder, which comprises the following steps:

a) production of a powder mixture (A) comprising

10 i) a powder (B) comprising one or more constituents selected from the group consisting of Cr, CrN and Cr₂N, and

ii) a powder (C) comprising one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys, cobalt alloys and iron alloys,

15 b) sintering of the powder mixture (A) in a gas atmosphere which contains nitrogen, with the nitrogen chemically bound in the form of chromium nitrides increasing or being at least maintained during the sintering and the nitrogen partial pressure during sintering being above 1 bar.

20

The present invention further provides a process for producing CrN-containing sintered spraying powder, which comprises the following steps:

a) production of a powder mixture (A) comprising

25 i) a powder (B) comprising one or more constituents selected from the group consisting of Cr, CrN and Cr₂N, and

ii) a powder (C) comprising one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys, cobalt alloys and iron alloys,

- b) sintering of the powder mixture (A) at a nitrogen partial pressure of greater than 1 bar, with maintenance of or an increase in the chemically bound nitrogen compared to the powder mixture (A).
- 5 The present invention further provides a process for producing CrN-containing sintered spraying powder, which comprises the following steps:
- a) production of a powder mixture (A) comprising
- i) a powder (B) comprising one or more constituents selected from the group consisting of Cr, CrN and Cr₂N, and
- 10 ii) a powder (C) comprising one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys, cobalt alloys and iron alloys,
- b) sintering of the powder mixture (A) in a gas atmosphere which contains nitrogen, with the content of nitrogen chemically bound in
- 15 the form of chromium nitrides increasing or being at least maintained, based on the powder mixture before sintering.

Unless indicated otherwise, the percentages indicated are in percent by weight.

- 20 The process of the invention for producing chromium nitride-containing sintered spray powder comprises, in a first step a), production of a powder mixture (A) comprising a powder (B) and a powder (C).

The powder (B) comprises one or more constituents selected from the group consisting of chromium, CrN and Cr₂N. The powder (B) particularly preferably comprises mixtures of CrN and Cr₂N. The weight ratio of CrN to Cr₂N can vary within a wide range, but preference is given to a weight ratio of from 1:100 to 100:1, more preferably from 1:10 to 10:1, in particular from 1:8 to 1:1 and especially from 1:6 to 1:2.

30

In a further preferred embodiment, the powder (B) comprises chromium nitrides (CrN and Cr₂N) in an amount of at least 70% by weight, preferably at least 80%

by weight, more preferably at least 90% by weight, in particular at least 95% by weight, and the powder (B) especially preferably consists of chromium nitrides.

However, the powder (B) can also consist exclusively of chromium or else of CrN or Cr₂N. Powder B can be produced not only by mixing phase-pure CrN and Cr₂N powders but also be a multiphase powder which, according to X-ray diffraction analysis, contains both CrN and Cr₂N in a powder particle. In addition, such a multiphase powder can also consist of metallic chromium and Cr₂N, possibly even metallic chromium, Cr₂N and CrN, possibly also further chromium nitrides which have not yet been found.

Particularly for uses in which the spraying powder obtained by means of the process of the invention is to be used for coating friction surfaces having a low roughness, it has been found to be advantageous to make the particle size of the powder (B) as small as possible. In a preferred embodiment, the powder (B) therefore has a particle size D50 below 20 µm, more preferably below 15 µm. In a particular embodiment, the D50 of the powder (B) is in the range from 0.5 to 10 µm. The D50 here is the volumetric diameter and is measured by means of laser light scattering. D50 means that 50% of the particles have diameters smaller than the value indicated.

In a further preferred embodiment, the powder (B) has a particle size D90 below 20 µm, preferably below 15 µm.

The powder mixture (A) usually comprises the powder (B) in an amount of from 50 to 90% by weight, preferably from 60 to 80% by weight, in each case based on the total weight of the powder mixture (A).

The powder (C) comprises one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys (alloys which contain nickel, i.e., in particular, including nickel-based alloys), cobalt alloys (alloys which contain cobalt, i.e., in particular, including cobalt-based alloys) and iron alloys (alloys which contain iron, i.e., in particular, including iron-based alloys).

The powder (C) serves as metal matrix (binder metal) for the chromium nitrides which act as hard materials.

In a preferred embodiment, the powder mixture (A) comprises a cobalt base alloy or nickel base alloy or iron base alloy. The base alloy can contain one or more constituents selected from the group consisting of Cr, Si, Mo, Ti, Ta, B, Y, W and Mn. The alloy can optionally comprise up to 25% by weight of these constituents.

Depending on the sintering conditions selected, one or more of the abovementioned constituent(s) may be nitrided.

In a particularly preferred embodiment of the process of the invention, the powder mixture (A) comprises a nickel powder and/or a nickel-chromium alloy powder.

In a preferred embodiment, the powder (C) comprises one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys, cobalt alloys and iron alloys in an amount of 50% by weight, preferably 60% by weight, more preferably 75% by weight, in particular 85% by weight and especially at least 95% by weight, based on the total weight of the powder (C). In a further preferred embodiment, the powder (C) consists of one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys, cobalt alloys and iron alloys.

Nickel powders and nickel-based alloy powders, for example nickel-chromium alloy powder, have been found to be particularly suitable metal matrix materials for chromium nitride-containing sintered spraying powders, but Co powders and Fe-based alloys are also particularly useful when they are alloyed with Cr, Si, Mo and Mn. In a preferred embodiment of the present invention, the powder (C) therefore contains at least 50% by weight of a nickel powder and/or nickel-chromium alloy powder, preferably up to 75% by weight, more preferably up to at least 95% by weight, based on the total weight of the powder (C), and the

powder mixture (C) particularly consists of a nickel powder and/or a nickel-chromium alloy powder.

5 The powder mixture (A) usually comprises the powder (C) in an amount of from 10 to 50% by weight, preferably from 15 to 45% by weight and in particular from 20 to 40% by weight, in each case based on the total weight of the powder mixture (A).

10 The powder mixture (A) advantageously comprises CrN and/or chromium and/or Cr₂N and preferably a nickel powder and/or nickel-chromium alloy powder.

15 In a further preferred embodiment, the powder mixture (A) comprises a cobalt base alloy or nickel base alloy or iron base alloy, where the alloy optionally contains one or more constituents, in particular constituents selected from the group consisting of Cr, Si, Mo, Ti, Ta, B, Y, W and Mn.

20 Owing to their hardness, the presence of carbides in the sintered spraying powder should be kept as low as possible. The carbon content of the powder mixture (A) should thus be as low as possible. In a preferred embodiment, the powder mixture (A) is essentially free of carbon. For the purposes of the present invention, essentially free of carbon means that the amount of carbon in the powder mixture (A) is below 1% by weight, preferably below 0.1% by weight, particularly preferably below 0.08% and in particular below 0.05% by weight, but especially preferably the powder mixture is free of carbon, where the
25 percentages by weight are based on the total weight of the powder mixture (A).

30 In a further preferred embodiment, the powder mixture (A) is essentially free of chromium carbides. For the purposes of the present invention, essentially free of chromium carbides means that the amount of chromium carbides is below 15% by weight, preferably below 1.5% by weight, more preferably below 0.8% by weight, in particular below 0.2% by weight, and the powder mixture is particularly preferably free of chromium carbide.

The powder mixture (A) can be produced by simple dry mixing of the powder (B) and the powder (C). Mixing of the powders is for this purpose usually carried out in mixing apparatuses with which a person skilled in the art will be familiar, in particular high-speed mixers (high-speed blenders) having high shear forces.

5

In a preferred embodiment of the process of the invention, the powder mixture (A) is produced by dispersing the powders (B) and (C) together in a liquid, with the liquid being removed after mixing has been carried out.

10 Suitable liquids for this purpose have been found to be, in particular, low-boiling liquids, in particular those selected from the group consisting of water, aliphatic alcohols, ketones and any mixtures thereof. The liquids are especially preferably selected from among water, methanol, ethanol and propanol and mixtures thereof.

15

The subsequent removal of the liquid can be effected by evaporation, preferably with application of a reduced pressure. In a particularly preferred embodiment, the liquid is removed by spray drying since agglomerated/sintered spraying powders are obtained at the end of the process.

20

In an especially preferred embodiment, the dispersion admixed with liquid can additionally comprise a temporary organic binder as adhesive which promotes agglomerate formation of the powder and ensures a mechanical stability which is sufficient for further processing. Suitable temporary organic binders here are, for
25 example, polyvinyl alcohol (PVA), polyvinylpyrrolidone (PVP), cellulose derivatives, polysaccharides, acrylic acid polymers.

In step b) of the process of the invention, sintering, preferably solid-state sintering, of the powder mixture (A) is carried out in a gas atmosphere
30 containing nitrogen with a partial pressure of greater than 1 bar. The conditions of the solid-state sintering (in particular nitrogen partial pressure and temperature) are, according to the invention, selected so that formation of or an increase in the amount of or stabilization of chromium nitrides occurs as a result of nitrogen uptake during sintering. Thus, a loss of chemically bound nitrogen

during sintering of the powder mixture does not occur in the process of the invention, but instead an increase in the chemically bound nitrogen but at least maintaining the chemically bound nitrogen present in the powder mixture occurs.

- 5 The presence of nitrogen gas having a partial pressure of > 1 bar in the gas atmosphere during sintering is essential to the inventive process of the present invention. In an advantageous embodiment, the gas atmosphere comprises at least 90% by volume, preferably 95% by volume, more preferably at least 98% by volume and in particular at least 99.5% by volume, of nitrogen, in each case
10 based on the total volume of the gas atmosphere.

The presence of oxygen is disadvantageous for the process step of sintering, in particular solid-state sintering. The presence of oxygen leads to formation of oxides which adversely affect the property profile of the spraying powders.

15

- In addition, it has been found that the absolute pressure of the gas atmosphere during sintering, preferably solid-state sintering, can exert a considerable influence on the formation of chromium nitrides and here especially the formation of CrN. The absolute pressure of the gas atmosphere is therefore
20 preferably above 1 bar, for example above 1.5 bar.

- Particularly good results can be obtained when sintering, in particular solid-state sintering, is carried out at a nitrogen partial pressure above 6 bar, preferably in the range from 7 to 100 bar, more preferably from 8 to 50 bar and in particular
25 from 9 to 20 bar. The higher the sintering temperature, the higher the required minimum value for the nitrogen partial pressure.

- Sintering, in particular solid-state sintering, is usually carried out at temperatures which promote the formation of sintering necks in the powder
30 mixture. These sintering necks give the sintered agglomerate sufficient mechanical strength, as is necessary for thermal spraying, in particular in HVOF and HVOF spraying processes. Suitable is sintering at temperatures above 1000°C, preferably in the range from 1050°C to 1500°C, more preferably from 1100°C to 1350°C and in particular from 1100°C to 1250°C.

Solid-state sintering is particularly preferably carried out for a time and under conditions such that the sintered spraying powder comprises chromium nitrides, with the amount of CrN being at least 5% by weight, preferably at least 20% by weight, more preferably at least 50% by weight and in particular at least 80% by weight, in each case based on the total weight of the two chromium nitrides Cr₂N and CrN in the sintered spraying powder. The proportion of the two chromium nitrides is determined by the chromium content of the spraying powder and the nitrogen content of the spraying powder, with a conceivable metallic chromium content in the metallic matrix being disregarded.

Solid-state sintering is usually carried out over a period of at least 1 hour, preferably at least 2 hours, more preferably at least 2.5 hours and in particular in the range from 3 to 48 hours. Longer times lead, under otherwise identical sintering conditions, to a higher nitrogen uptake.

In a particularly preferred embodiment of the present invention, the process for producing chromium nitride-containing sintered spraying powders comprises the following steps:

- a) production of a powder mixture (A) comprising
 - i) a powder (B) comprising Cr₂N powder and optionally CrN and
 - ii) a powder (C),
- b) sintering of the powder mixture (A) in a gas atmosphere containing at least 99.5% by volume of nitrogen at a pressure of the gas atmosphere of above 6 bar and temperatures in the range from 1050°C to 1400°C.

In a further, particularly preferred embodiment of the present invention, the process for producing CrN-containing sintered spraying powders comprises the following steps:

- a) production of a powder mixture (A) comprising
 - i) a powder (B) comprising chromium powder and
 - ii) a powder (C),

b) sintering of the powder mixture (A) in a gas atmosphere containing at least 99.5% by volume of nitrogen at a pressure of the gas atmosphere of above 6 bar and temperatures in the range from 1050°C to 1400°C.

- 5 The chromium nitride-containing, sintered spraying powders obtainable by the process of the invention have excellent properties. In particular, the thermal spraying process makes it possible to form substantially thicker layers.

10 The present invention further provides a chromium nitride-containing sintered spraying powder which is obtainable by the process of the invention. The chromium nitride-containing sintered spraying powder preferably contains chromium nitride particles having an average diameter of from 1 to 20 μm (e.g. determined electrooptically as number average from image analysis of (electron) micrographs, for instance as Jeffries diameter).

15

In a further preferred embodiment, the sintered spraying powder comprises chromium nitride, with CrN being present in an amount of at least 5% by weight, preferably at least 20% by weight, more preferably at least 50% by weight and in particular at least 80% by weight, in each case based on the total weight of
20 chromium nitride in the sintered spraying powder.

The chromium nitride-containing spraying powders of the invention are particularly suited for the surface coating of components, for example friction surfaces.

25

The present invention therefore further provides a process for producing a surface-coated component by coating of a component by means of thermal spraying of the spraying powder of the invention. Thermal spraying can, for example, be carried out by high-speed flame spraying or plasma spraying. The
30 components obtainable by the coating process have extremely good frictional properties and especially low roughnesses. In addition, the component can be provided with a thicker wear layer as compared to layers which can be conventionally produced by the PVD process.

The present invention therefore further provides a coated component obtainable by the coating process of the invention. The coated component preferably has a wear layer obtained by thermal spraying which has a thickness of at least 15 μm , preferably at least 50 μm , in particular at least 100 μm , in particular at least 200 μm and especially at least 250 μm .

The present invention therefore further provides for the use of the spray powder of the invention for the surface coating of components.

Examples

Example 1 (comparative example)

(CrN+ Ni, sintering conventional, Cr₂N formation)

35 kg of chromium nitride containing 15.65% by weight of nitrogen (consisting of CrN having a theoretical nitrogen content of 21.2% by weight and Cr₂N having a theoretical nitrogen content of 12.1% by weight) were screened to a particle size of -10 μm , dispersed in water together with 15 kg of an NiCr 80/20 alloy produced by atomization and spray dried. The granules obtained were screened and sintered at 1000°C in a carbon crucible in a push-through furnace (pusher – type kiln) customary for sintering spraying powders at a residence time in the heating zone of 3 hours 12 minutes. The furnace atmosphere had a pressure of a few millibar above atmospheric pressure and consisted essentially of hydrogen. This gave an agglomerated/sintered spraying powder having the following properties:

Table 1

Element (measurement parameter) (% values are percentages by weight)	Measured value	Measurement method
Nickel (%)	23.7	
Nitrogen (%)	7.2	
Oxygen (%)	0.64	
Carbon (%)	0.58	
Average particle size (μm)	31	Microtrac S3500

The expected value for the nitrogen content in the spraying powder would be 70 percent by weight of the nitrogen content of the chromium nitride used (= 10.95 percent by weight in the spraying powder) if no decomposition of the chromium nitride used took place. However, the value is actually below the expected value when all of the chromium nitride is present as Cr_2N (= 70% of 12.1% = 8.47%), which indicates that mainly Cr_2N is present and chromium carbides have additionally been formed (0.58% by weight of carbon were taken up during sintering). Accordingly, only Cr_2N and no CrN was identified in addition to the NiCr phase by means of X-ray diffraction. In the case of conventional sintering of agglomerated/sintered spraying powders, decomposition of the chromium nitrides, in particular of the particularly desirable CrN , into Cr_2N and chromium carbides thus has to be expected.

Example 2 (comparative example, partly according to the invention = *)

A spray-dried granulate composed of 70% by weight of chromium nitride powder having a nitrogen content of 11.87% by weight (consisting essentially of Cr_2N) and 30% by weight of atomized NiCr 80/20 alloy powder was produced in a manner analogous to example 1. The spray-dried granulate was sintered in a carbon crucible at various combinations of sintering temperature and nitrogen partial pressure for 3 hours in a pressure sintering furnace (pressure-type sintering furnace), cooled to room temperature under the same pressure, and the nitrogen content of the resulting spraying powders was determined. The nitrogen content of the starting material calculated from the formulation is 8.31%.

Table 2

Temperature (°C)	Nitrogen pressure (bar)	Nitrogen (% by weight)	Chromium nitride phases according to X-ray diffraction
1300	5	7.64	Cr_2N , little CrN
1300	7*	12.50	Cr_2N , CrN
1300	10*	13.60	little Cr_2N , CrN
1200	10*	13.70	CrN

It can clearly be seen that loss or regaining of the nitrogen content takes place at the given temperature as a function of the nitrogen pressure and the proportion of Cr_2N phase can be decreased by means of a suitable choice of the parameters pressure and temperature, while the proportion of particularly desirable CrN phase increases. The proportion of CrN in the chromium nitride component cannot be calculated precisely since it has to be expected that the Cr present in the NiCr has likewise formed chromium nitrides to an unknown extent. However, if this effect is disregarded, a proportion of 82% of CrN in the chromium nitride component can be calculated at 1200°C/10 bar nitrogen pressure.

In all cases, a sintered cake was obtained which could be reconverted into a sintered/crushed spraying powder only under the action of mechanical force.

Example 3 (according to the invention)

A dispersion in water was produced from 60% chromium nitride powder having a nitrogen content of 14.7% (corresponding to a CrN content of about 29%) and a carbon content of 0.05% and also 40% of finely divided nickel powder (Vale-INCO, Type T255) and a spray-dried granulate was produced from this dispersion. This was sintered at 1150°C at a nitrogen pressure of 11 bar for 3 hours in a pressure sintering furnace, and the content of nitrogen in the agglomerated/sintered spraying powder was determined. The nitrogen content of the spray-dried granulate calculated from the formulation is 8.82%.

Table 3

Temperature (°C)	Nitrogen pressure (bar)	Nitrogen (% by weight)	Chromium nitride phases according to X-ray diffraction
1150	11	11.6	CrN, traces of Cr_2N

Table 4

Element (measurement parameter) (% values are percentages by weight)	Measured value	Measurement method
Nickel (%)	40.4	
Nitrogen (%)	11.5	
Oxygen (%)	0.53	
Carbon (%)	0.19	
Hall flow (s/50g)	30	ASTM B-212
Average particle size (μm)	38	Microtrac S3500
Apparent density (g/cm^3)	2.75	ASTM B-213

By sieving, the agglomerated/sintered spraying powder obtained could easily be comminuted to the particle size class from 45 to 15 μm required for HVOF spraying processes since the sintered material was only very loosely sintered. The individual granulates obtained in spray drying had for their part a strength (stability) sufficient for thermal spraying.

It can be seen from the nitrogen content that additional nitrogen was chemically bound during sintering. Taking into account the theoretical nitrogen contents, the proportion of CrN in the chromium nitride component was 79% by weight and that of Cr_2N was 21% by weight. The lower carbon content and chromium carbide content compared to example 1 is particularly advantageous.

Example 4 (according to the invention)

A dispersion in water was produced from 75% by weight chromium nitride powder having a nitrogen content of 14.7% by weight (corresponding to a CrN content of about 29% by weight) and a carbon content of < 0.08% by weight and also 25% of finely divided cobalt powder and a spray-dried granulate were produced from this dispersion. This was sintered at 1150°C at a nitrogen pressure of 11 bar for 3 hours in a pressure sintering furnace, and the content of nitrogen in the spraying powder was determined. The nitrogen content of the spray-dried granulate calculated from the formulation is 11.0% by weight.

Table 5

Element (measurement parameter) (% values are percentages by weight)	Measured value	Measurement method
Cobalt (%)	22.9	
Nitrogen (%)	14.9	
Oxygen (%)	0.7	
Carbon (%)	0.32	
Hall flow (s/50g)	35	ASTM B-212
Average particle size (μm)	34	Microtrac S3500
Apparent density (g/cm^3)	2.3	ASTM B-213

- By sieving, the agglomerated/sintered spraying powder obtained could easily be comminuted to the required particle size class from 45 to 15 μm since the
- 5 sintered material was only very loosely sintered together. The individual granulates formed during spray drying themselves had sufficient strength for thermal spraying.

Claims

1. Process for producing chromium nitride-containing sintered spraying powder, which comprises the following steps:
 - a) production of a powder mixture (A) comprising
 - 5 i) a powder (B) comprising one or more constituents selected from the group consisting of Cr, CrN and Cr₂N, and
 - ii) a powder (C) comprising one or more constituents selected from the group consisting of nickel, cobalt, nickel alloys, cobalt alloys and iron alloys,
 - 10 b) sintering of the powder mixture (A) at a nitrogen partial pressure of greater than 1 bar, with maintenance of or an increase in the chemically bound nitrogen compared to the powder mixture (A).
2. Process according to claim 1, characterized in that the powder mixture (A) comprises CrN and/or Cr₂N.
- 15 3. Process according to claim 1 or 2, characterized in that the powder mixture (A) contains a nickel powder and/or NiCr alloy powder, preferably a cobalt base alloy or nickel base alloy or iron base alloy, with the alloy optionally containing one or more constituents selected from the group consisting of Cr, Si, Mo, Ti, Ta, B, Y, W and Mn.
- 20 4. Process according to one or more of claims 1 to 3, characterized in that the production of the powder mixture (A) is effected by dispersing the powder (B) together with the powder (C) in a liquid, with the liquid being removed after mixing is complete.
5. Process according to claim 4, characterized in that the liquid is selected
 - 25 from the group consisting of water, aliphatic alcohols, ketones and any mixtures thereof, preferably selected from among water, methanol, ethanol and propanol and mixtures thereof.
6. Process according to claim 4 or 5, characterized in that the removal of the liquid is carried out by spray drying.

7. Process according to one or more of claims 1 to 6, characterized in that the powder (B) has a particle size D90 below 20 μm , preferably below 15 μm .
- 5 8. Process according to one or more of claims 1 to 7, characterized in that the solid-state sintering is carried out in a gas atmosphere comprising at least 90% by volume, preferably at least 95% by volume, more preferably at least 98% by volume and in particular at least 99.5% by volume, of nitrogen, in each case based on the total volume of the atmosphere.
- 10 9. Process according to one or more of claims 1 to 8, characterized in that sintering is carried out at a nitrogen partial pressure above 6 bar, preferably in the range from 7 to 100 bar, more preferably from 8 to 50 bar and in particular from 9 to 20 bar.
- 15 10. Process according to one or more of claims 1 to 9, characterized in that sintering, in particular solid-state sintering, is carried out at a temperature above 1000°C, preferably in the range from 1050°C to 1500°C, more preferably from 1100°C to 1350°C and in particular from 1100°C to 1250°C.
- 20 11. Process according to one or more of claims 1 to 10, characterized in that sintering, in particular solid-state sintering, is carried out for a period of at least 1 hour, preferably at least 2 hours, more preferably at least 2.5 hours and in particular in the range from 3 to 48 hours.
- 25 12. Process according to one or more of claims 1 to 11, characterized in that the powder mixture (A) is essentially free of chromium carbides.
13. Process according to one or more of claims 1 to 12, characterized in that the powder mixture (A) contains the powder (B) in an amount of from 50 to 90% by weight, preferably from 60 to 80% by weight, in each case based on the total weight of the powder mixture (A).
- 30 14. Process according to one or more of claims 1 to 13, characterized in that the powder mixture (A) contains the powder (C) in an amount of from 10 to 50% by weight, preferably from 15 to 45% by weight and in particular

from 20 to 40% by weight, in each case based on the total weight of the powder mixture (A).

15. Process according to one or more of claims 1 to 14, characterized in that the sintered spraying powder comprises chromium nitrides, with the amount of CrN being at least 50% by weight, preferably at least 75% by weight, more preferably at least 78% by weight and in particular at least 80% by weight, in each case based on the total weight of chromium nitride in the sintered spraying powder.
16. Chromium nitride-containing sintered spray powder, obtainable by a process according to one or more of claims 1 to 15.
17. Process for producing a surface coated component by coating a component by means of thermal spraying of a spraying powder according to claim 16.
18. Use of the spraying powder according to claim 16 for the surface coating of components.
19. Coated component obtainable by the process according to claim 17.