

A METHOD TO GENERATE IONIZED METAL PLASMA USING ELECTRON BEAMS AND MAGNETIC FIELD

Inventors: Zheng Xu; Sesh Ramaswami

5

FIELD OF THE INVENTION

The present invention relates to plasma generators, and more particularly, to a method and apparatus for generating a plasma to sputter deposit a layer of material in the fabrication of semiconductor devices.

10

BACKGROUND OF THE INVENTION

Low density plasmas have become convenient sources of energetic ions and activated atoms which can be employed in a variety of semiconductor device fabrication processes including surface treatments, depositions, and etching processes. For example, to deposit materials onto a semiconductor wafer using a sputter deposition process, a plasma is produced in the vicinity of a sputter target material which is negatively biased. Ions created adjacent to the target impact the surface of the target to dislodge, i.e., "sputter" material from the target. The sputtered materials are then transported and deposited on the surface of the semiconductor wafer.

20

Sputtered material has a tendency to travel in straight line paths from the target to the substrate being deposited, at angles which are oblique to the surface of the substrate. As a consequence, materials deposited in etched trenches and holes of semiconductor devices having trenches or holes with a high depth to width aspect ratio, can bridge over causing undesirable cavities in the deposition layer. To prevent such cavities, the sputtered material can be redirected into substantially vertical paths between the target and the substrate by negatively charging the substrate to position

25

This Sheet Has Been Replaced



vertically oriented electric fields adjacent the substrate if the sputtered material is sufficiently ionized by the plasma. However, material sputtered in a low density plasma often has an ionization degree of less than 1% which is usually insufficient to avoid the formation of an excessive number of cavities. Accordingly, it is desirable to increase the density of the plasma to increase the ionization rate of the sputtered material in order to decrease the formation of unwanted cavities in the deposition layer. As used herein, the term "dense plasma" is intended to refer to one that has a high electron and ion density.

There are several known techniques for exciting a plasma with RF fields including capacitive coupling, inductive coupling and wave heating. In a standard inductively coupled plasma (ICP) generator, RF current passing through a coil surrounding the plasma induces electromagnetic currents in the plasma. These currents heat the conducting plasma by ohmic heating, so that it is sustained in steady state. As shown in U.S. Pat. No. 4,362,632, for example, current through a coil is supplied by an RF generator coupled to the coil through an impedance-matching network, such that the coil acts as the first windings of a transformer. The plasma acts as a single turn second winding of a transformer.

In a number of deposition chambers such as a physical vapor deposition chamber, the chamber walls are often formed of a conductive metal such as stainless steel. Because of the conductivity of the chamber walls, it is often necessary to place the antenna coils or electrodes within the chamber itself because the conducting chamber walls would block or substantially attenuate the electromagnetic energy radiating from the antenna. As a result, the coil and its supporting structures are directly exposed to the deposition flux and energetic plasma particles. This is a potential source of contamination of the film deposited on the wafer, and is undesirable.

To protect the coils, shields made from nonconducting materials, such as ceramics, can be placed in front of the coil. However, many deposition processes



involve deposition of conductive materials such as aluminum on the electronic device being fabricated. Because the conductive material will coat the ceramic shield, it will soon become conducting, thus again substantially attenuating penetration of electromagnetic radiation into the plasma. Consequently, it is preferred to place a shield wall behind the coil to protect the interior of the deposition chamber from the deposition material. However, the problem of particulate matter remains for sputtering chambers of this design.

This Sheet Has Been Replaced




SUMMARY OF THE PREFERRED EMBODIMENTS

It is an object of the present invention to provide an improved method and apparatus for generating a plasma within a chamber and for sputter-depositing a layer which obviate, for practical purposes, the above-mentioned limitations.

5 These and other objects and advantages are achieved by, in accordance with one aspect of the invention, a plasma-generating apparatus which comprises at least one electron source which injects energetic electrons into a semiconductor fabrication chamber to initiate and sustain a relatively high density plasma at extremely low pressures. In addition to ionizing atoms of the extremely low pressure precursor gas, 10 such as an argon gas at 100 microTorr, for example, the energetic electrons are also believed to collide with target material atoms sputtered from a target positioned above a substrate, thereby ionizing the target material atoms and losing energy as a result of the collisions. As a consequence, coils or other structures for inductively coupling RF power to sustain a plasma can be eliminated.

15 Preferably, the electrons are injected by electron guns positioned to inject the electrons substantially tangentially to the walls of a chamber shield surrounding the high density plasma into a confining magnetic field. The magnetic field is preferably oriented generally parallel to a central axis of the semiconductor fabrication chamber and substantially perpendicular to the surface of the substrate. As the injected 20 electrons lose energy, colliding with and ionizing the target material atoms, and atoms of the extremely low pressure precursor gas, the electrons spiral inward toward a central region of the semiconductor fabrication chamber surrounding the central axis, forming an electron cloud in the central region. An arrangement of electromagnets may be positioned adjacent the walls of the chamber shield surrounding the high density 25 plasma to generate the confining magnetic field. It is believed that the configuration of confining magnetic fields also keeps electrons from colliding with the walls of the chamber shield surrounding the high density plasma.



BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a perspective, partial cross-sectional view of a plasma-generating chamber in accordance with an embodiment of the present invention.

5 Fig. 2 is a partial cross-sectional view of the plasma-generating chamber of Fig. 1 shown installed in a vacuum chamber.

Fig. 3 is a schematic diagram of the electrical interconnections to the plasma-generating chambers of Figs. 1-2.

Fig. 4 is a schematic diagram of alternative electrical interconnections to the plasma-generating chambers of Figs. 1-2.

10 Fig. 5 is a schematic cross-sectional view of a plasma-generating chamber in accordance with the embodiments of Figs. 1-4.

Fig. 6 is a graph schematically depicting the magnitude of the axial magnetic field strength of the magnetic field configuration of Fig. 5.

15 Fig. 7 is a schematic, plan view from above of electron trajectories of the plasma-generating chambers in accordance with the embodiments of Figs. 1-4.

This Sheet Has Been Replaced




DETAILED DESCRIPTION OF THE DRAWINGS

Referring first to Figs. 1-3, a plasma generator in accordance with an embodiment of the present invention comprises a substantially cylindrical deposition system 100 which is received in a vacuum chamber 102 (shown schematically in Fig. 3). The deposition system 100 of this embodiment has a chamber shield 106 that protects the interior walls 108 (Fig. 2) of the vacuum chamber 102 from the material being deposited within the interior of the deposition system 100.

An ion flux strikes a negatively biased target 110 positioned at the top of the vacuum chamber 102. The target 110 is negatively biased by a DC power source 3000. The ions eject material from the target 110 onto a substrate 112 which may be a wafer or other workpiece which is supported by a pedestal 114 at the bottom of the deposition system 100. A rotating magnetron magnet assembly 116 provided above the target 110 produces magnetic fields which sweep over the face of the target 110 to promote uniform erosion of the target.

In accordance with one aspect of the present invention, energetic electrons are injected into the interior of the deposition system 100 by one or more electron guns 104 arranged tangentially around the periphery of the deposition system 100, energizing a plasma 900 (Fig. 5) within the deposition system 100. The atoms of material ejected from the target 110 are in turn ionized by the electron cloud 900 such that the ionized deposition material is attracted to the substrate 112 to form a deposition layer thereon. The pedestal 114 may be negatively biased by an AC (or DC or RF) source so as to externally bias the substrate 112.

The electron guns 104 may be synchronized to inject the energetic electrons substantially continuously or in a pulsed manner. For example, using eight electron guns 104, each operating at an electron injection energy of about 20 keV and an electron current density of about 100 mAcm^{-2} , an electron density of about $5 \times 10^{12} \text{ cm}^{-3}$ may be generated in the high density electron cloud 900. As explained in greater detail



below, a magnetic field is used to confine the high density electron cloud 900. The magnetic field strength needed to generate such a high density electron cloud 900 may be about 50 Gauss or less. Because the ionizing electrons are provided externally by the electron guns 104, the operation pressure of the argon (Ar) gas may be reduced to less than or equal to about 5×10^{-4} Torr (0.5 milliTorr or 500 microTorr). It is believed that a high density electron cloud 900, with an electron density of about $5 \times 10^{12} \text{ cm}^{-3}$, in an argon (Ar) gas, at an extremely low operation pressure of less than or equal to about 5×10^{-4} Torr, may advantageously be used. More target material atoms may be ionized by the high density electron cloud 900 while fewer target material ions may be deflected by the extremely low pressure argon (Ar) gas.

As shown in Figs. 1 and 7, the electron guns 104 may have recessed windows 105 (shown in phantom) positioned a distance D from the end of the electron gun 104 exposed to the interior of deposition system 100. As shown, for example, in Fig. 2, the portion of the electron gun 104 exposed to the interior of deposition system 100 may pass through the wall 140 of the chamber shield 106 through a slot 107. The recessed windows 105 of the electron guns 104 allow the interior of the deposition system 100 to be maintained at a high vacuum. The distance D is chosen to be large enough (although necessarily less than the length L of the electron gun 104) so that window 105 is not plated over by the target material to be deposited on substrate 112 passing through the opening of the electron gun 104 having height H and width W (Figs. 1 and 2), with aspect ratios chosen so that D/H is preferably greater than or equal to about 5 and H/W is preferably greater than or equal to about 2. While electron gun 104 is shown in Fig. 2 disposed on the interior of vacuum chamber wall 108, alternative embodiments may have one or more of the electron guns 104 extending outside of the vacuum chamber wall 108. Alternative sources for energetic electrons include "hot" filaments thermally emitting energetic electrons, and "cold" filaments using electron



field emission, with "hot" emission being preferred using a tungsten or tantalum filament.

As will be explained in greater detail below, in accordance with one aspect of the present invention, the chamber shield 106 is magnetically shielded by magnetic fields
5 generated by various types of magnets such as electromagnet coils 1000 and 1010 so as to minimize sputtering of material from the chamber shield 106. In addition, the deposition of target material onto the chamber shield 106 may also be reduced. As a consequence, contamination of the substrate 112 by material sputtered from the chamber shield 106 or by particulate matter shed by the chamber shield 106 may be
10 reduced.


Fig. 3 is a schematic representation of the electrical connections of the plasma generating apparatus of this illustrated embodiment. To attract the ions generated by the plasma, the target 110 is preferably negatively biased by a variable DC power source 3000. In the same manner, the pedestal 114 may be negatively biased by a
15 variable DC power source 3010 to bias the substrate 112 negatively to attract the ionized deposition material to the substrate 112. In an alternative embodiment, as shown in Fig. 4, the pedestal 114 may be biased by a high frequency RF power source to bias the substrate 112 so as to attract the ionized deposition material more uniformly to the substrate 112. The pedestal 114 is coupled to an RF source such as the output
20 of an amplifier and matching network 3025, the input of which is coupled to an RF generator 3045.

One end of the electromagnet coil 1000 may be coupled to a DC power source such as the output of a transformer and rectifying circuit 4020, the input of which is coupled to an AC power generator 4040. The other end of the electromagnet coil 1000
25 is coupled to ground, preferably through a resistor 4060, which may also be a variable resistor. Likewise, one end of the electromagnet coil 1010 may be coupled to a DC power source such as the output of a transformer and rectifying circuit 5020, the input



of which is coupled to an AC power generator 5040. The other end of the electromagnet coil 1010 is coupled to ground, preferably through a resistor 5060, which may also be a variable resistor. Alternatively, both electromagnet coils 1000 and 1010 may be identical, or both may be coupled to a common DC power generator, of course, or one or more DC power sources may be used. One or more of the electromagnet coils such as 1000 and 1010 may be superconducting, using windings of high-temperature or low-temperature superconducting materials, cryogenically cooled as needed, and able to be disconnected from any power supply once energized.


Fig. 5 schematically represents the operation of the electromagnet coils 1000 and 1010 to reduce the sputtering of material from the chamber shield 106, and to reduce the generation of particulate matter by the chamber shield 106, and hence reduce contamination of the substrate 112. As shown in Fig. 5, magnetic field lines 1100 are generated by the electromagnet coils 1000 and 1010, causing the energized electrons from the high density electron cloud 900 to spiral in helical paths 1200 around the magnetic field lines 1100, deflecting the energized electrons from impacting the chamber shield 106. The deflection of the energized electrons by the magnetic field lines 1100 also creates an electric field along the general direction of motion of the deflected electrons, deflecting energized ions of the high density electron cloud 900 and target material ions from impacting the chamber shield 106. Furthermore, the magnetic field lines 1100 are believed to squeeze the high density electron cloud 900 inward toward the central axis of the plasma chamber 100, creating a buffer region from a few mm up to a cm or more, depending on the strength of the magnetic field lines 1100, radially inward from the chamber shield 106, advantageously avoiding direct plasma heating of the chamber shield 106. This inhibits the energized electrons from lingering in the immediate vicinity of the chamber shield 106 and ionizing gas atoms and molecules that could sputter material from the chamber shield 106, which could in turn contaminate the substrate 112. Still further, the magnetic field lines 1100 can



magnetically shield the chamber shield 106 to a limited extent from ionized deposition material which was originally ejected from the target 110. As a consequence, the accumulation of target material on the chamber shield 106 can be reduced, thereby reducing the formation of particulates that could subsequently dislodge from the chamber shield 106 and fall upon and contaminate the substrate 112. Typical magnetic field strengths generated by the electromagnet coils 1000 and 1010 in the region adjacent the chamber shield 106 may be in the range of 50-110 Gauss. Typical electron densities in the high density electron cloud 900 may be on the order of about 10^{12} cm^{-3} to about $5 \times 10^{12} \text{ cm}^{-3}$. The operation pressure of the argon (Ar) gas may be less than or equal to about 5×10^{-4} Torr (0.5 milliTorr or 500 microTorr).

Fig. 6 schematically illustrates a preferred uniform arrangement for the magnitude of the magnetic field strength B_z in the axial direction, plotted against the distance x from the central symmetry axis of the plasma chamber 100. For example, as shown in Fig. 6, the magnitude of the magnetic field strength a (Fig. 5) in the axial direction at the position x_a closer to the central symmetry axis of the plasma chamber 100 is substantially the same as the magnitude of the magnetic field strength b (Fig. 5) in the axial direction at the position x_b more distant from the central symmetry axis of the plasma chamber 100. Consequently, the influence of the magnetic field lines 1100 on the central region of the high density electron cloud 900 may be undiminished in such a preferred uniform arrangement for the magnitude of the magnetic field strength B_z in the axial direction, and a uniform plasma may be generated. Typical values for the magnitude of the magnetic field strength B_z in the axial direction, at all distances x from the central symmetry axis of the plasma chamber 100, are on the order of 50 Gauss, as shown in Fig. 6, or less.

Electromagnet coils 1000 and 1010 are positioned externally of the chamber shield 106, supported by electromagnet coil supports 1005 and 1015, respectively, as shown in Fig. 2. Electromagnet coil support 1005 may be attached to adapter ring



assembly 152, and electromagnet coil support 1015 may be attached to vacuum chamber wall 108. The electromagnet coil 1000 connects, through an adapter ring assembly feedthrough (not shown), to a DC power source, as shown in Fig. 3. The electromagnet coil 1010 also connects, through a vacuum chamber wall feedthrough (not shown), to a DC power source, as shown in Fig. 3. Alternatively, one or both of the electromagnet coils 1000 and 1010 may be connected to an AC power source, which may cause the high density electron cloud 900 to rotate, which can lead to enhanced uniformity of deposition of material from the target 110 onto the substrate 112.

The embodiment of Figs. 1-5 shows only two electromagnet coils 1000 and 1010 being used, but, of course as few as one electromagnet coil could be used, and as many as ten or more electromagnet coils could also be used, or a combination of electromagnet coils and permanent magnets could be used as well. An advantage of using more electromagnet coils is that more electromagnet coils enable more precise shaping or "bottling" of the high density electron cloud 900, which can increase the effective electron density of the high density electron cloud 900 and lead to enhanced uniformity of deposition of material from the target 110 onto the substrate 112, especially onto the fine features and structures of the substrate 112, particularly those with very high aspect ratios, such as deep, narrow trenches, vias and contact holes.


Fig. 7 shows a schematic, plan view from above of electron trajectories of the deposition systems 100 in accordance with the embodiments of Figs. 1-5. As shown in Fig. 7, magnetic field lines 1100, generated by electromagnet coils 1000 and 1010, as in the embodiments of Figs. 1-5, cause the energized electrons in the high density electron cloud 900 to cycle in spiral paths 1200 around the magnetic field lines 1100. As shown in Fig. 7, the electron guns 104 are arranged to inject the energetic electrons substantially tangentially into the interior of chamber shield 106. Also as shown in Fig. 7, an electron at radial (vector) distance r from the center of high density electron cloud 900 has a (vector) velocity v directed tangentially along the spiral path 1200. The



spiral paths 1200 shown in Fig. 7 are appropriate for electrons since the magnetic field lines 1100 are coming out of the plane of the figure in Fig. 7. The magnetic component of the Lorentz force in the i th direction F_{im} on an electron moving with velocity v_j in the j th direction in a magnetic field B_k in the k th direction (the directions 1, 2 and 3 forming a right-handed coordinate system) is given by

$$F_{im} = -\frac{e}{c} \sum_{j=1}^3 \sum_{k=1}^3 \epsilon_{ijk} v_j B_k = -\frac{m_e v^2}{r^2} x_i$$

where the absolute value of the electric charge e of an electron is $1.6021892 \pm 0.0000046 \times 10^{-19}$ Coulombs, the speed of light c is $2.99792458 \pm 0.00000012 \times 10^{10}$ cm/sec, ϵ_{ijk} is the completely antisymmetric tensor ($\epsilon_{123}=1=\epsilon_{231}=\epsilon_{312}=-\epsilon_{213}=-\epsilon_{132}=-\epsilon_{321}$, all other components vanishing identically), the rest mass of an electron m_e is 0.511 MeV/ c^2 , the magnitude of the electron's velocity is v , the radius of the electron's orbit is r , and the unit vector in the i th direction is x_i/r , the last equality following by equating the magnetic component of the Lorentz force on the electron to the centripetal force on the electron. For example, in Fig. 7, with the 1 direction horizontal, the 2 direction vertical and the 3 direction normal to, and coming out of, the plane of the figure, since the magnetic field lines 1100 are coming out of the plane of the figure in the positive 3 direction ($B_1=0$, $B_2=0$, $B_3=B$), when the electron's velocity in the plane of the figure is upward in the positive 2 direction ($v_1=0$, $v_2=v$, $v_3=0$), the magnetic component of the Lorentz force is to the left in the negative 1 direction ($F_{1m}=-e_{123}ev_2B_3/c=-evB/c$, $F_{2m}=0$, $F_{3m}=0$); when the electron's velocity in the plane of the figure is to the left in the negative 1 direction ($v_1=-v$, $v_2=0$, $v_3=0$), the magnetic component of the Lorentz force is downward in the negative 2 direction ($F_{1m}=0$, $F_{2m}=-e_{213}ev_1B_3/c=-evB/c$, $F_{3m}=0$); when the electron's velocity in the plane of the figure is downward in the negative 2 direction ($v_1=0$, $v_2=-v$, $v_3=0$), the magnetic component of the Lorentz force is to the right in the positive 1 direction ($F_{1m}=-e_{123}ev_2B_3/c=evB/c$,



$F_{2m}=0$, $F_{3m}=0$); and when the electron's velocity in the plane of the figure is to the right in the positive 1 direction ($v_1=v$, $v_2=0$, $v_3=0$), the magnetic component of the Lorentz force is upward in the positive 2 direction ($F_{1m}=0$, $F_{2m}=-e_{213}ev_1B_3/c=evB/c$, $F_{3m}=0$), resulting in a counterclockwise rotation of the electron in the plane of the figure, as shown in Fig. 7.


For the counterclockwise rotation of the electron in the plane of the figure, as shown in Fig. 7, equating the magnitudes in the above-given equation for the magnetic component of the Lorentz force gives the radius r of the electron's orbit

$$r = \frac{c}{eB} m_e v = \frac{c}{eB} (2m_e E)^{\frac{1}{2}}$$

where the kinetic energy E of the electron is $\frac{1}{2}m_e v^2$ so that $2m_e E$ is $(m_e v)^2$, the square of the electron's (non-relativistic) momentum. As the kinetic energy E of the electron decreases, for example, as the result of collisions with argon and titanium atoms in the high density electron cloud 900, the radius r of the electron's orbit decreases as $E^{\frac{1}{2}}$, spiraling inward toward a central region of the high density electron cloud 900 within the deposition system 100, as shown by the spiral path 1200 in Fig. 7. Electrons are believed to create ions by colliding with gas and/or metal atoms with sufficient energy. By magnetically trapping electrons, more ionizations are believed to occur.

The chamber shield 106 protects the vacuum chamber walls 108 from the material being deposited. In the illustrated embodiment, the chamber shield 106 is made of a conductive material such as heavy-duty, bead-blasted solid high-purity (preferably 99.995% pure) titanium formed into a generally cylindrical shape having a diameter of 25-36 cm (10-14 inches). However, other highly conductive materials may be utilized depending upon the material being sputtered and other factors.

The material of the structure which will be coated should have a coefficient of thermal expansion which closely matches that of the material being sputtered to reduce



flaking of sputtered material from the shield or other chamber internal structure onto the wafer. In addition, the material to be coated should have good adhesion to the sputtered material. Thus for example if the deposited material is titanium, the preferred metal of the shields, brackets and other structures likely to be coated is bead-blasted titanium. Any surfaces which are likely to sputter would preferably be made of the same type of material as the target such as high purity titanium, for example. Of course, if the material to be deposited is a material other than titanium, the preferred metal is the deposited material, stainless steel or copper. Adherence can also be improved by coating the structures with molybdenum prior to sputtering the target. However, it is preferred that the coil (or any other surface likely to sputter) not be coated with molybdenum or other materials since the molybdenum can contaminate the workpiece if sputtered from the coil.

The chamber shield 106 is generally bowl-shaped (Fig. 2) and includes a generally cylindrically shaped, vertically oriented wall 140. The chamber shield 106 further has a generally annular-shaped floor wall 142 which surrounds the pedestal 114 which supports the substrate 112 which has a 20 cm (8") diameter in the illustrated embodiment. A clamp ring 154 may be used to clamp the substrate 112 to the pedestal 114 and cover the gap between the floor wall of the chamber shield 106 and the pedestal 114.

The deposition system 100 is supported by an adapter ring assembly 152 which engages an upper annular flange 150 of the vacuum chamber wall 108. The outer shield 106 is grounded to the system ground through the adapter ring assembly 152. The darkspace shield 130, like the chamber shield 106, is grounded through the adapter ring assembly 152. The darkspace shield 130 also has an upper flange 170 which is fastened to the horizontal flange 162 of the adapter ring assembly 152. The darkspace shield 130, like the chamber shield 106, is grounded through the adapter ring assembly 152.




The target 110 is generally disk-shaped and is also supported by the adapter ring assembly 152. However, the target 110 is negatively biased and therefore should be insulated from the adapter ring assembly 152 which is grounded. Accordingly, seated in a circular channel 176 formed in the underside of the target 110 is a ceramic insulation ring assembly 172 which is also seated in a corresponding channel 174 in the upper side of the adapter ring assembly 152. The insulator ring assembly 172 which may be made of a variety of insulative materials including ceramics spaces the target 110 from the adapter ring assembly 152 so that the target 110 may be adequately negatively biased. The target, adapter and ceramic ring assembly are provided with O-ring sealing surfaces 178 to provide a vacuum tight assembly from the vacuum chamber 102 to the target 110.

To promote uniform erosion of the target 110, a magnetron 116 (Fig. 2) may be provided above the target 110. However, in some applications the magnetron might be omitted by increasing the energetic electron injection ionization of the high density electron cloud 900.

A DC power setting for biasing the target 110 of 3 kW is preferred but a range of 2-5 kW and a pedestal bias voltage of -30 volts DC is believed to be satisfactory for many applications.

The substrate 112 to target 110 spacing is preferably about 140 mm but can range from about 8 cm to 20 cm (3" to 8"). For this substrate 112 to target 110 spacing, a chamber shield diameter of about 36 cm (14 inches) is preferred.

A variety of gases may be utilized in the plasma chamber 100, including Ar, H₂ or reactive gases such as NF₃, CF₄ and many others. Various gas pressures are suitable including pressures of about 0.1 milliTor or less. For ionized PVD, a pressure less than or equal to about 5×10^{-4} Torr (0.5 milliTor or 500 microTor) is suitable for ionization of sputtered material.




It will, of course, be understood that modifications of the present invention, in its various aspects, will be apparent to those skilled in the art, some being apparent only after study others being matters of routine mechanical and electronic design. Other embodiments are also possible, their specific designs depending upon the particular application. As such, the scope of the invention should not be limited by the particular embodiments herein described but should be defined only by the appended claims and equivalents thereof.

This Sheet Has Been Replaced



**WHAT IS CLAIMED IS:**

1. An apparatus for energizing a plasma within a semiconductor fabrication system to sputter material onto a substrate, the apparatus comprising:
 - a semiconductor fabrication chamber having a target and a plasma generation region adjacent to said target;
 - 5 an arrangement of magnets positioned adjacent said semiconductor fabrication chamber to generate a configuration of magnetic fields within said semiconductor fabrication chamber; and
 - at least one electron source positioned to inject energetic electrons into said semiconductor fabrication chamber, to ionize said sputtered material, wherein said
 - 10 configuration of magnetic fields within said semiconductor fabrication chamber confines said electrons within said semiconductor fabrication chamber.
2. The apparatus of claim 1, wherein said magnet includes an electromagnet.
3. The apparatus of claim 1, wherein said electron source includes an electron gun.
4. An apparatus for energizing a plasma within a semiconductor fabrication system to sputter material onto a substrate, the apparatus comprising:
 - a semiconductor fabrication chamber having a target and a plasma generation region adjacent to said target;
 - an arrangement of electromagnets positioned adjacent said semiconductor fabrication chamber to generate a configuration of magnetic fields within said semiconductor fabrication chamber; and





at least one electron gun positioned to inject energetic electrons into said semiconductor fabrication chamber, wherein said energetic electrons lose energy ionizing said sputtered material and said configuration of magnetic fields within said semiconductor fabrication chamber keeps said electrons away from said chamber shield so that said electrons losing energy spiral inward toward a central region of said semiconductor fabrication chamber.

5. The apparatus of claim 4 wherein said at least one electron gun injects said energetic electrons into said semiconductor fabrication chamber substantially tangentially to said chamber shield.

6. The apparatus of claim 4, wherein said target includes titanium and said chamber shield includes titanium.

7. The apparatus of claim 4, wherein said target includes aluminum and said chamber shield includes aluminum.

8. The apparatus of claim 4 including:
a source for applying a bias to said substrate to attract said ionized sputtered material.

9. An apparatus for energizing a plasma within a semiconductor fabrication system to sputter material onto a substrate, the apparatus comprising:
a semiconductor fabrication chamber having a surrounding chamber shield and having a plasma generation region;





an arrangement of electromagnets positioned adjacent said semiconductor fabrication chamber to generate a configuration of magnetic fields within said semiconductor fabrication chamber; and


5 a plurality of electron guns arranged substantially tangentially around said chamber shield with portions of said electron guns passing through said chamber shield to inject energetic electrons into said semiconductor fabrication chamber, wherein said energetic electrons lose energy ionizing said sputtered material and said configuration of magnetic fields within said semiconductor fabrication chamber keeps said electrons away from said chamber shield so that said electrons losing energy
10 spiral inward toward a central region of said semiconductor fabrication chamber, and said configuration of magnetic fields within said semiconductor fabrication chamber confines said electrons in a central region of said semiconductor fabrication chamber.

10. A method of depositing material on a substrate, the method comprising sputtering material from a target positioned above said substrate; injecting energetic electrons into a plasma to ionize said sputtered material; and
5 confining said electrons in a central region of a semiconductor fabrication chamber.

11. The method of claim 10 including varying a biasing of said substrate.

10 12. The method of claim 10, wherein said confining includes generating a configuration of magnetic fields so as to confine said electrons in said central region.

13. The method of claim 12, wherein said confining further includes keeping said electrons away from a chamber shield surrounding said plasma using said





generated configuration of magnetic fields so that said electrons lose energy ionizing material sputtered from said target, said electrons spiraling inward toward said central region forming an electron cloud.

14. A method of depositing material on a substrate, the method comprising sputtering material from a target positioned above said substrate; injecting energetic electrons using a plurality of electron guns into a plasma to ionize said sputtered material; and
- 5 confining said electrons within a semiconductor fabrication chamber.
15. The method of claim 14 including varying a biasing of said substrate.
16. The method of claim 14, wherein said confining includes generating a configuration of magnetic fields.
17. The method of claim 16, wherein said confining further includes keeping said electrons away from a chamber shield surrounding said plasma using said generated configuration of magnetic fields so that said electrons lose energy ionizing material sputtered from said target, said electrons spiraling inward toward a central region of said semiconductor fabrication chamber forming an electron cloud.

This Sheet Has Been Replaced

