

METHODS AND SYSTEMS FOR MICROFLUIDIC DEVICE MANUFACTURING**CROSS-REFERENCE**

[0001] This application claims the benefit of U.S. Provisional Patent Application No. 62/965,690, filed January 24, 2020, which is entirely incorporated herein by reference.

GOVERNMENT INTEREST STATEMENT

[0002] This invention was made with government support under Small Business Innovation Research grant number 1R43OD023028-01 awarded by the National Institute of Health. The U.S. government has certain rights in the invention.

BACKGROUND

[0003] Microfluidic devices are devices that contain structures that handle fluids on a small scale. Typically, a microfluidic device operates on a sub-millimeter scale and handles micro-liters, nano-liters, or smaller quantities of fluids. In microfluidic devices, a major fouling mechanism is trapped air, or bubbles, inside the micro-structure. This can be particularly problematic when using a thermoplastic material to create the microfluidic structure, as the gas permeability of thermoplastics is very low.

[0004] In order to avoid fouling by trapped air, microfluidic structures use either simple straight channel or branched channel designs with thermoplastic materials, or else manufacture the device using high gas permeability materials such as elastomers. However, simple designs limit possible functionality of the microfluidic device, and elastomeric materials are both difficult and expensive to manufacture, particularly at scale.

[0005] One application of microfluidic structures is in digital polymerase chain reaction (dPCR). dPCR dilutes a nucleic acid sample down to one or less nucleic acid template in each partition of a microfluidic structure providing an array of many partitions, and performs a PCR reaction across the array. By counting the partitions in which the template was successfully PCR amplified and applying Poisson statistics to the result, the target nucleic acid is quantified. Unlike the popular quantitative real-time PCR (qPCR) where templates are quantified by comparing the rate of PCR amplification of an unknown sample to the rate for a set of known qPCR standards, dPCR has proven to exhibit higher sensitivity, better precision and greater reproducibility.

[0006] For genomic researchers and clinicians, dPCR is particularly powerful in rare mutation detection, quantifying copy number variants, and Next Gen Sequencing library quantification. The potential use in clinical settings for liquid biopsy with cell free DNA and viral load

quantification further increases the value of dPCR technology. Existing dPCR solutions have used elastomeric valve arrays, silicon through-hole approaches, and microfluidic encapsulation of droplets in oil. Despite the growing number of available dPCR platforms, dPCR has been at a disadvantage when compared to the older qPCR technology which relies on counting the number of PCR amplification cycles. The combination of throughput, ease of use, performance and cost are the major barriers for gaining adoption in the market for dPCR.

SUMMARY

[0007] Provided herein are methods and devices that may be useful for amplifying and quantifying nucleic acids. The present disclosure provides methods, systems, and devices that may enable sample preparation, sample amplification, and sample analysis through the use of dPCR. This may enable a nucleic acid to be amplified and quantified at a reduced cost and complexity as compared to other systems and methods.

[0008] In an aspect, the present disclosure provides a method for forming a microfluidic device, comprising: providing a microfluidic structure and a film; (b) treating a surface of the microfluidic structure, a surface of the film, or both with a solvent; (c) subsequent to (b), pressing the microfluidic structure together with the film under a first heating condition to form the microfluidic device comprising the solvent; and (d) applying a negative pressure to the microfluidic device under a second heating condition, which negative pressure is applied for a time period greater than 30 minutes or at a pressure less than 20 kilopascals (kPa) to remove at least a portion of the solvent from (b).

[0009] In some embodiments, the microfluidic structure comprises a microchannel, a plurality of microchambers, a plurality of siphon apertures, or any combination thereof. In some embodiments, the treating comprises application of one or more solvents. In some embodiments, the one or more solvents include a solvent selected from the group consisting of isopropyl alcohol, acetone, ethyl alcohol, hexanes, cyclohexane, toluene, and benzene. In some embodiments, the pressing comprises applying a force of at least about 0.5 kilo-Newtons (kN). In some embodiments, the first heating condition comprises heating to a temperature of at least about 60 °C. In some embodiments, the applying the negative pressure comprises applying a pressure less than about 7 kPa. In some embodiments, the second heating condition comprises heating the microfluidic device to a temperature of at least about 70 °C. In some embodiments, the heating the microfluidic device to a temperature of at least about 70°C removes at least about 75% of the solvent from the microfluidic device. In some embodiments, the applying the negative pressure comprises applying the negative pressure for at least about 2 hours. In some

embodiments, the applying the negative pressure removes at least about 50 % of the solvent from the microfluidic device. In some embodiments, the applying the negative pressure under the second heating condition reduces separation between the microfluidic structure and the film. In some embodiments, the microfluidic structure comprises a channel or chamber with a feature size of at most about 500 micrometers. In some embodiments, the removing the solvent increases a yield of the microfluidic device by at least about 25%. In some embodiments, the microfluidic device has a usable feature fraction of at least about 0.5. In some embodiments, the method further comprises applying an increased pressure to the microfluidic device, wherein the increased pressure is sufficient to expel at least a portion of the solvent.

[0010] Additional aspects and advantages of the present disclosure will become readily apparent to those skilled in this art from the following detailed description, wherein only illustrative embodiments of the present disclosure are shown and described. As will be realized, the present disclosure is capable of other and different embodiments, and its several details are capable of modifications in various obvious respects, all without departing from the disclosure. Accordingly, the drawings and description are to be regarded as illustrative in nature, and not as restrictive.

INCORPORATION BY REFERENCE

[0011] All publications, patents, and patent applications mentioned in this specification are herein incorporated by reference to the same extent as if each individual publication, patent, or patent application was specifically and individually indicated to be incorporated by reference.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] The novel features of the invention are set forth with particularity in the appended claims. A better understanding of the features and advantages of the present invention will be obtained by reference to the following detailed description that sets forth illustrative embodiments, in which the principles of the invention are utilized, and the accompanying drawings (also “Figure” and “FIG.” herein), of which:

[0013] **FIGs. 1A and 1B** illustrate an example of a microfluidic structure; **FIG. 1A** shows the structure from an overhead view, while **FIG. 1B** illustrates a cross-section of the structure;

[0014] **FIGs. 2A and 2B** schematically illustrates example arrangements of microchambers, siphon apertures, and microchannels within a microfluidic device; **FIG. 2A** shows an embodiment in which parallel sub-channels and one or more cross-channels are used to form a grid of microchambers; **FIG. 2B** shows an embodiment in which a single microchannel in a serpentine pattern forms a hexagonal grid of microchambers;

[0015] **FIGs. 3A-3D** show methods for use of an example microfluidic device; **FIG. 3A** shows providing reagent at low pressure; **FIG. 3B** shows applying a pressure differential across the microfluidic device to permit partitioning and outgassing; **FIG. 3C** shows providing a fluid at low pressure to clear the microchannel; **FIG. 3D** shows the state of the system after the completion of the method;

[0016] **FIG. 4** schematically illustrates a method of manufacture of a microfluidic device;

[0017] **FIG. 5** schematically illustrates an example digital PCR process to be employed with a microfluidic device;

[0018] **FIG. 6** schematically illustrates a machine for performing a nucleic acid amplification and quantification method in a single machine;

[0019] **FIG. 7** schematically illustrates an example computer control system that is programmed or otherwise configured to implement methods provided herein;

[0020] **FIGs. 8A and 8B** show the microfluidic device and sample partitioning; **FIG. 8A** shows a microfluidic device formed by micromolding a thermoplastic; **FIG. 8B** show fluorescent images of the sample partitioning process;

[0021] **FIG. 9** shows an example system for processing a nucleic acid sample;

[0022] **FIGs. 10A – 10D** show two color (one color representing sample signal and the other representing a normalization signal) fluorescent detection of nucleic acid amplification of partitions containing approximately one nucleic acid template copy on average and partitions containing zero nucleic acid template copies (no template control or NTC); **FIG. 10A** shows zero copies per partition (NTC) after amplification; **FIG. 10B** shows nucleic acid amplification of partitions containing approximately one copy per partition; **FIG. 10C** shows a plot of NTC fluorescence intensity of both fluorescent colors; and **FIG. 10D** shows a plot of fluorescence intensity of both fluorescent colors of the amplified sample.

[0023] **FIG. 11** is a flowchart of an example process for forming a microfluidic device.

[0024] **FIG. 12** is an example schematic for forming a microfluidic device.

[0025] **FIG. 13** is an example of a microfluidic device fabricated by the methods described herein.

[0026] **FIG. 14** is an example of a microfluidic device fabricated without removing solvent subsequent to liquid pressurization and heating.

[0027] **FIG. 15** is an example of a microfluidic device fabricated without solvent removal subsequent to air pressurization and heating.

[0028] **FIG. 16** is an example of a microfluidic device fabricated with solvent removal subsequent to liquid pressurization and heating.

[0029] FIG. 17 is an example of a microfluidic device fabricated with solvent removal subsequent to air pressurization and heating.

[0030] FIGs. 18A – 18B are example magnified images of a microfluidic device fabricated without solvent removal before (FIG. 18A) and after (FIG. 18B) liquid pressurization and heating.

[0031] FIGs. 19A – 19B are example magnified images of a vacuum treated microfluidic device before (FIG. 19A) and after (FIG. 19B) liquid pressurization and heating.

[0032] FIGs. 20A – 20B are example magnified images of a heat treated microfluidic device before (FIG. 20A) and after (FIG. 20B) liquid pressurization and heating.

[0033] FIGs. 21A – 21B are example close ups of a vacuum and heat treated microfluidic device before (FIG. 21A) and after (FIG. 21B) liquid pressurization and heating.

DETAILED DESCRIPTION

[0034] While various embodiments of the invention have been shown and described herein, it will be obvious to those skilled in the art that such embodiments are provided by way of example only. Numerous variations, changes, and substitutions may occur to those skilled in the art without departing from the invention. It should be understood that various alternatives to the embodiments of the invention described herein may be employed.

[0035] As used herein, the terms “amplification” and “amplify” are used interchangeably and generally refer to generating one or more copies or “amplified product” of a nucleic acid. Such amplification may be using polymerase chain reaction (PCR) or isothermal amplification, for example.

[0036] As used herein, the term “nucleic acid” generally refers to a polymeric form of nucleotides of any length (e.g., at least 2, 3, 4, 5, 6, 7, 8, 9, 10, 100, 500, or 1000 nucleotides), either deoxyribonucleotides or ribonucleotides, or analogs thereof. A nucleic acid may include one or more subunits selected from adenosine (A), cytosine (C), guanine (G), thymine (T), and uracil (U), or variants thereof. A nucleotide can include A, C, G, T, or U, or variants thereof. A nucleotide can include any subunit that can be incorporated into a growing nucleic acid strand. Such subunit can be A, C, G, T, or U, or any other subunit that is specific to one of more complementary A, C, G, T, or U, or complementary to a purine (e.g., A or G, or variant thereof) or pyrimidine (e.g., C, T, or U, or variant thereof). In some examples, a nucleic acid may be single-stranded or double stranded, in some cases, a nucleic acid molecule is circular. Non-limiting examples of nucleic acids include DNA and RNA. Nucleic acids can include coding or non-coding regions of a gene or gene fragment, loci (locus) defined from linkage analysis, exons,

introns, messenger RNA (mRNA), transfer RNA, ribosomal RNA, short interfering RNA (siRNA), short-hairpin RNA (shRNA), micro-RNA (miRNA), ribozymes, cDNA, recombinant nucleic acids, branched nucleic acids, plasmids, vectors, isolated DNA of any sequence, isolated RNA of any sequence, nucleic acid probes, and primers. A nucleic acid may comprise one or more modified nucleotides, such as methylated nucleotides and nucleotide analogs.

[0037] As used herein, the terms “polymerase chain reaction reagent” or “PCR reagent” are used interchangeably and generally refer to a composition comprising reagents necessary to complete a nucleic acid amplification reaction (e.g., DNA amplification), with non-limiting examples of such reagents including primer sets or priming sites (e.g., nick) having specificity for a target nucleic acid, polymerases, suitable buffers, co-factors (e.g., divalent and monovalent cations), dNTPs, and other enzymes. A PCR reagent may also include probes, indicators, and molecules that comprise probes and indicators.

[0038] As used herein, the term “probe” generally refers to a molecule that comprises a detectable moiety, the presence or absence of which may be used to detect the presence or absence of an amplified product. Non-limiting examples of detectable moieties may include radiolabels, stable isotope labels, fluorescent labels, chemiluminescent labels, enzymatic labels, colorimetric labels, or any combination thereof.

[0039] As used herein, the term “extension” generally refers to incorporation of nucleotides into a nucleic acid in a template directed fashion. Extension may occur via the aid of an enzyme. For example, extension may occur via the aid of a polymerase. Conditions at which extension may occur include an “extension temperature” that generally refers to a temperature at which extension is achieved and an “extension duration” that generally refers to an amount of time allotted for extension to occur.

[0040] As used herein, the term “indicator molecule” generally refers to a molecule that comprises a detectable moiety, the presence or absence of which may be used to indicate sample partitioning. Non-limiting examples of detectable moieties may include radiolabels, stable isotope labels, fluorescent labels, chemiluminescent labels, enzymatic labels, colorimetric labels, or any combination thereof.

[0041] The term “sample,” as used herein, generally refers to any sample containing or suspected of containing a nucleic acid molecule. For example, a sample can be a biological sample containing one or more nucleic acid molecules. The biological sample can be obtained (e.g., extracted or isolated) from or include blood (e.g., whole blood), plasma, serum, urine, saliva, mucosal excretions, sputum, stool and tears. The biological sample can be a fluid or tissue sample (e.g., skin sample). In some examples, the sample is obtained from a cell-free

bodily fluid, such as whole blood. In such instance, the sample can include cell-free DNA and/or cell-free RNA. In some examples, the sample can include circulating tumor cells. In some examples, the sample is an environmental sample (e.g., soil, waste, ambient air and etc.), industrial sample (e.g., samples from any industrial processes), and food samples (e.g., dairy products, vegetable products, and meat products).

[0042] As used herein, the term “fluid” generally refers to a liquid or a gas. A fluid cannot maintain a defined shape and will flow during an observable time frame to fill the container into which it is put. Thus, the fluid may have any suitable viscosity that permits flow. If two or more fluids are present, each fluid may be independently selected among essentially any fluids (liquids, gases, and the like) by those of ordinary skill in the art.

[0043] As used herein, the term “partition” generally refers to a division into or distribution into portions or shares. For example, a partitioned sample is a sample that is isolated from other samples. Examples of structures that enable sample partitioning include wells and microchambers.

[0044] As used herein, the term “microfluidic” generally refers to a chip, area, device, article, or system including at least one microchannel, a plurality of siphon apertures, and an array of microchambers. The microchannel may have a cross-sectional dimension less than or equal to about 10 millimeters (mm), less than or equal to about 5 mm, less than or equal to about 4 mm, less than or equal to about 3 mm, less than or equal to about 2 mm, less than or equal to about 1.5 mm, less than or equal to about 1 mm, less than or equal to about 750 micrometers (μm), less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , or less.

[0045] As used herein, the term “depth” generally refers to the distance measured from the bottom of the microchannel, siphon aperture, or microchamber to the thin film that caps the microchannel, plurality of siphon apertures, and array of microchambers.

[0046] As used herein, the terms “cross-section” or “cross-sectional” may be used interchangeably and generally refer to a dimension or area of a microchannel or siphon aperture that is substantially perpendicularly to the long dimension of the feature.

[0047] The present disclosure describes a microfluidic device formed out of a thermoplastic and incorporating a thin film to allow for pressurized outgassing while serving as a gas barrier when pressure is released. The use of thermoplastic to form the microfluidic structure may allow for the use of an inexpensive and highly scalable injection molding process, while the thin film may provide the ability to outgas via pressurization, avoiding the fouling problems that may be present some microfluidic structures that do not incorporate such thin films.

[0048] One use for this structure is a microfluidic design incorporating an array of dead-ended microchambers connected by microchannels, formed out of thermoplastics. This design can be used in a dPCR application to partition reagents into the array of microchambers and thereby used to quantify nucleic acids in dPCR.

Microfluidic device for analyzing nucleic acid samples

[0049] In an aspect, the present disclosure provides a microfluidic device for analyzing nucleic acid samples. The device may comprise a microchannel connected to an inlet and an outlet. The microfluidic device may also include a plurality of microchambers and a plurality of siphon apertures. The plurality of microchambers may be connected to the microchannel by the plurality of siphon apertures. The microfluidic device may include a thermoplastic thin film which caps and seals (e.g., hermetically seals) the microchannel, microchambers, and siphon apertures. The thermoplastic thin film may be at least partially gas permeable when a pressure differential is applied across the thermoplastic thin film.

[0050] **FIGs. 1A and 1B** show examples of a microfluidic structure according to certain embodiments of the present disclosure. **FIG. 1A** shows an example microfluidic device from a top view. The microfluidic device comprises a microchannel **110**, with an inlet **120**, and an outlet **130**. The microchannel is connected to a plurality of siphon apertures **101B - 109B**. The plurality of siphon apertures connects the microchannel to a plurality of microchambers **101A - 109A**. **FIG. 1B** shows a cross-sectional view of a single microchamber along the dashed line marked **A-A'**. The single microchamber **101A** is connected to the microchannel **110** by a siphon aperture **101B**. The microfluidic device body **140** may be formed from a rigid plastic material. The microstructures of the microfluidic device may be capped and sealed by a thin film **150**. The thin film may be gas impermeable when a small pressure differential is applied across the film and gas permeable when a large pressure differential is applied across the film. This may allow for outgassing through the thin film when a pressure is applied to the interior structure of the microfluidic device. In an alternative embodiment, outgassing may occur when a vacuum is applied external to the microfluidic device.

[0051] The gas permeability of the thin film may be induced by elevated pressures. In some embodiments the pressure induced gas permeable thin film may cover the array of microchambers and the microchannel and siphon apertures may be covered by a non-gas permeable film. In some embodiments, the pressure induced gas permeable thin film may cover the array of microchambers and the siphon apertures and the microchannel may be covered by a non-gas permeable film. Alternatively, the pressure induced gas permeable thin film may cover the array of microchambers, the siphon apertures, and the microchannel. In some embodiments,

the thickness of the thin film may be less than or equal to about 500 micrometers (μm), less than or equal to about 250 μm , less than or equal to about 200 μm , less than or equal to about 150 μm , less than or equal to about 100 μm , less than or equal to about 75 μm , less than or equal to about 50 μm , less than or equal to about 25 μm , or less. In some embodiments, the thickness of the thin film may be from about 0.1 μm to about 200 μm or about 0.5 μm to about 150 μm . In some examples, the thickness of the thin film may be from about 50 μm to about 200 μm . In some examples, the thickness of the thin film may be from about 100 μm to about 200 μm . In some examples, the thickness of the thin film is about 100 μm to about 150 μm . In an example, the thin film is approximately 100 μm in thickness. The thickness of the film may be selected by manufacturability of the thin film, the air permeability of the thin film, the volume of each partition to be out-gassed, the available pressure, and/or the time to complete the siphoning process.

[0052] In some embodiments, the microfluidic device may comprise a single array of microchambers. In some embodiments, the microfluidic device may comprise multiple arrays of microchambers, each array of microchambers isolated from the others. The arrays of microchambers may be arranged in a row, in a grid configuration, in an alternating pattern, or in any other configuration. In some embodiments, the microfluidic device may have at least about 1, at least about 2, at least about 3, at least about 4, at least about 5, at least about 10, at least about 15, at least about 20, at least about 30, at least about 40, at least about 50, or more arrays of microchambers. In some embodiments, the arrays of microchambers are identical. In some embodiments, the microfluidic device may comprise multiple arrays of microchambers that are not identical. The arrays of microchambers may all have the same external dimension (e.g., the length and width of the array of microchambers that encompasses all features of the array of microchambers) or the arrays of microchambers may have different external dimensions.

[0053] In some embodiments, an array of microchambers may have a width of at most about 100 mm, about 75 mm, about 50 mm, about 40 mm, about 30 mm, about 20 mm, about 10 mm, about 8 mm, about 6 mm, about 4 mm, about 2 mm, about 1 mm, or less. The array of microchambers may have a length of at most about 50 mm, about 40 mm, about 30 mm, about 20 mm, about 10 mm, about 8 mm, about 6 mm, about 4 mm, about 2 mm, 1 mm, or less. The width may be from about 1 mm to 100 mm, or 10 mm to 50 mm. The length may be from about 1 mm to 50 mm, or 5 mm to 20 mm.

[0054] In some examples, the array of microchambers may have a width of about 100 mm and a length of about 40 mm. In some examples, the array of microchambers may have a width of about 80 mm and a length of about 30 mm. In some examples, the array of microchambers may

have a width of about 60 mm and a length of about 25 mm. In some examples, the array of microchambers may have a width of about 40 mm and a length of about 15 mm. In some examples, the array of microchambers may have a width of about 30 mm and a length of about 10 mm. In some examples, the array of microchambers may have a width of about 20 mm and a length of about 8 mm. In some examples, the array of microchambers may have a width of about 10 mm and a length of about 4 mm. The external dimension may be determined by the total number of microchambers used, the dimension of each microchamber, and the minimum distance between each microchamber for manufacturability.

[0055] In some embodiments, the microchannel is substantially parallel to the long dimension of the microfluidic device. In some embodiments, the microchannel may be substantially perpendicular to the long dimension of the microfluidic device. In some embodiments, the microchannel may be neither substantially parallel nor substantially perpendicular to the long dimension of the microfluidic device. The angle between the microchannel and the long dimension of the microfluidic device may be at least about 5 °, at least about 10 °, at least about 15 °, at least about 20 °, at least about 30 °, at least about 40 °, at least about 50 °, at least about 60 °, at least about 70 °, at least about 90 °, at least about 100 °, at least about 110 °, at least about 120 °, at least about 130 °, at least about 140 °, at least about 150 °, at least about 160 °, or at least about 170 °. In some embodiments, the microchannel may be a single long channel. In some embodiments, the microchannel may have bends, curves, or angles. The microchannel may have a long dimension that is less than or equal to 100 mm, less than or equal to about 75 mm, less than or equal to about 50 mm, less than or equal to about 40 mm, less than or equal to about 30 mm, less than or equal to about 20 mm, less than or equal to about 10 mm, less than or equal to about 8 mm, less than or equal to about 6 mm, less than or equal to about 4 mm, less than or equal to about 2 mm, or less. The length of the microchannel may be bounded by the external length or width of the microfluidic device. The microchannel may have a depth of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 80 μm , less than or equal to about 60 μm , less than or equal to about 30 μm , less than or equal to about 20 μm , less than or equal to about 10 μm , or less. The microchannel may have a cross-sectional dimension (e.g., width) of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 75 μm , less than or equal to about 50 μm , less than or equal to about 40 μm , less than or equal to about 30 μm , less than or equal to about 20 μm , less than or equal to about 10 μm , or less.

[0056] In some examples, the cross-sectional dimensions of the microchannel may be about 100 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 100 μm wide by about 80 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 100 μm wide by about 60 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 100 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 100 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 100 μm wide by about 10 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 80 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 60 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 40 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 20 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 10 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 80 μm wide by about 80 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 60 μm wide by about 60 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 40 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 20 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the microchannel may be about 10 μm wide by about 10 μm deep. The cross-sectional shape of the microchannel may be any suitable cross-sectional shape including, but not limited to, circular, oval, triangular, square, or rectangular. The cross-sectional area of the microchannel may be constant along the length of the microchannel. Alternatively, or in addition to, the cross-sectional area of the microchannel may vary along the length of the microchannel. The cross-sectional area of the microchannel may vary between about 50% and 150%, between about 60% and 125%, between about 70% and 120%, between about 80% and 115%, between about 90% and 110%, between about 95% and 100%, or between about 98% and 102%. The cross-sectional area of the microchannel may be less than or equal to about 10,000 micrometers squared (μm^2), less than or equal to about 7,500 μm^2 , less than or equal to about 5,000 μm^2 , less than or equal to about 2,500 μm^2 , less than or equal to about 1,000 μm^2 , less than or equal to about 750 μm^2 , less than or equal to about 500 μm^2 , less than or equal to about 400 μm^2 , less than or equal to about 300 μm^2 , less than or equal to about 200 μm^2 , less than or equal to about 100 μm^2 , or less.

[0057] In some embodiments, the microchannel may have a single inlet and a single outlet. Alternatively, the microchannel may have multiple inlets, multiple outlets, or multiple inlets and multiple outlets. The inlets and outlets may have the same diameter or they may have different diameters. The inlets and outlets may have diameters less than or equal to about 2.5 millimeters (mm), less than or equal to about 2 mm, less than or equal to about 1.5 mm, less than or equal to about 1 mm, less than about 0.5 mm, or less.

[0058] In some embodiments, the array of microchambers may have at least about 1,000 microchambers, at least about 5,000 microchambers, at least about 10,000 microchambers, at least about 20,000 microchambers, at least about 30,000 microchambers, at least about 40,000 microchambers, at least about 50,000 microchambers, at least about 100,000 microchambers, or more. In some examples, the microfluidic device may have from about 10,000 to about 30,000 microchambers. In some examples, the microfluidic device may have from about 15,000 to about 25,000 microchambers. The microchambers may be cylindrical in shape, hemispherical in shape, or a combination of cylindrical and hemispherical in shape. The microchambers may have diameters of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 80 μm , less than or equal to about 60 μm , less than or equal to about 30 μm , less than or equal to about 15 μm , or less. The depth of the microchambers may be less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 80 μm , less than or equal to about 60 μm , less than or equal to about 30 μm , less than or equal to about 15 μm , or less. In some examples, the microchambers may have a diameter of about 30 μm and a depth of about 100 μm . In some examples, the microchambers may have a diameter of about 35 μm and a depth of about 80 μm . In some examples, the microchambers may have a diameter of about 40 μm and a depth of about 70 μm . In some examples, the microchambers may have a diameter of about 50 μm and a depth of about 60 μm . In some examples, the microchambers may have a diameter of about 60 μm and a depth of about 40 μm . In some examples, the microchambers may have a diameter of about 80 μm and a depth of about 35 μm . In some examples, the microchambers may have a diameter of about 100 μm and a depth of about 30 μm . In some embodiments, the microchambers and the microchannel have the same depth. In an alternative embodiment, the microchambers and the microchannel have different depths.

[0059] In some embodiments, the lengths of the siphon apertures are constant. In some embodiments, the lengths of the siphon apertures vary. The siphon apertures may have a long dimension that is less than or equal to about 150 μm , less than or equal to about 100 μm , less than or equal to about 50 μm , less than or equal to about 25 μm , less than or equal to about 10

μm , less than or equal to about 5 μm , or less. In some embodiments, the depth of the siphon aperture may be less than or equal to about 50 μm , less than or equal to about 25 μm , less than or equal to about 10 μm , less than or equal to about 5 μm or less. The siphon apertures may have a cross-sectional width less than or equal to about 50 μm , less than or equal to about 40 μm , less than or equal to about 30 μm , less than or equal to about 20 μm , less than or equal to about 10 μm , less than or equal to about 5 μm , or less.

[0060] In some examples, the cross-sectional dimensions of the siphon aperture may be about 50 μm wide by about 50 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 50 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 50 μm wide by about 30 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 50 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 50 μm wide by about 10 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 50 μm wide by about 5 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 40 μm wide by about 50 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 30 μm wide by about 50 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 20 μm wide by about 50 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 10 μm wide by about 50 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 5 μm wide by about 50 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 40 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 30 μm wide by about 30 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 20 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 10 μm wide by about 10 μm deep. In some examples, the cross-sectional dimensions of the siphon aperture may be about 5 μm wide by about 5 μm deep. The cross-sectional shape of the siphon aperture may be any suitable cross-sectional shape including, but not limited to, circular, oval, triangular, square, or rectangular. In some embodiments, the cross-sectional area of the siphon aperture may be constant along the length of the siphon aperture. Alternatively, or in addition to, the cross-sectional area of the siphon aperture may vary along the length of the siphon aperture. The cross-sectional area of the siphon aperture may be greater at the connection to the microchannel than the cross-sectional area of the siphon aperture at the connection to the microchamber. Alternatively, the cross-sectional area of the siphon aperture at the connection to

the microchamber may be greater than the cross-sectional area of the siphon aperture at the connection to the microchannel. The cross-sectional area of the siphon aperture may vary between about 50% and 150%, between about 60% and 125%, between about 70% and 120%, between about 80% and 115%, between about 90% and 110%, between about 95% and 100%, or between about 98% and 102%. The cross-sectional area of the siphon aperture may be less than or equal to about $2,500\ \mu\text{m}^2$, less than or equal to about $1,000\ \mu\text{m}^2$, less than or equal to about $750\ \mu\text{m}^2$, less than or equal to about $500\ \mu\text{m}^2$, less than or equal to about $250\ \mu\text{m}^2$, less than or equal to about $100\ \mu\text{m}^2$, less than or equal to about $75\ \mu\text{m}^2$, less than or equal to about $50\ \mu\text{m}^2$, less than or equal to about $25\ \mu\text{m}^2$, or less. The cross-sectional area of the siphon aperture at the connection to the microchannel may be less than or equal to the cross-sectional area of the microchannel. The cross-sectional area of the siphon aperture at the connection to the microchannel may be less than or equal to about 98 %, less than or equal to about 95 %, less than or equal to about 90%, less than or equal to about 85 %, less than or equal to about 80%, less than or equal to about 75 %, less than or equal to about 70%, less than or equal to about 60%, less than or equal to about 50%, less than or equal to about 40%, less than or equal to about 30 %, less than or equal to about 20 %, less than or equal to about 10%, less than or equal to about 5%, less than or equal to about 1%, or less than or equal to about 0.5% of the cross-sectional area of the microchannel.

[0061] In some embodiments, the siphon apertures are substantially perpendicular to the microchannel. In some embodiments, the siphon apertures are not substantially perpendicular to the microchannel. In some embodiments, an angle between the siphon apertures and the microchannel may be at least about 5° , at least about 10° , at least about 15° , at least about 20° , at least about 30° , at least about 40° , at least about 50° , at least about 60° , at least about 70° , at least about 90° , at least about 100° , at least about 110° , at least about 120° , at least about 130° , at least about 140° , at least about 150° , at least about 160° , or at least about 170° .

[0062] The microchambers may be arranged in a variety of patterns. **FIGs. 2A** and **2B** illustrate example patterns of microchamber, siphon aperture, and microchannel arrangements. In some embodiments, multiple microchannels are employed, while in some embodiments, a single microchannel may be used. In some embodiments, a microchannel may comprise a group of sub-channels. The group of sub-channels may be connected by one or more cross-channels. In some of these embodiments, the sub-channels are substantially parallel to one another so that the array of microchambers forms a grid of microchambers. **FIG. 2A** illustrates an embodiment in which parallel sub-channels **230** and one or more cross-channels **220** are used to form a grid of microchambers.

[0063] In some embodiments, microchambers are constructed so as to form a hexagonal grid of microchambers, with curved or angled sub-channels connecting the microchambers. A hexagonal grid of microchambers may also be formed and connected by a single microchannel, such as by a microchannel that forms a serpentine pattern **240** across the microfluidic device.

FIG. 2B illustrates an embodiment in which a single microchannel in a serpentine pattern forms a hexagonal grid of microchambers.

[0064] In some embodiments, the lengths of the sub-channels are constant. In some embodiments, the lengths of the sub-channel may vary. The sub-channel may have a long dimension that is less than or equal to 100 mm, less than or equal to about 75 mm, less than or equal to about 50 mm, less than or equal to about 40 mm, less than or equal to about 30 mm, less than or equal to about 20 mm, less than or equal to about 10 mm, less than or equal to about 8 mm, less than or equal to about 6 mm, less than or equal to about 4 mm, less than or equal to about 2 mm, or less. The length of the sub-channel may be bounded by the external length or width of the microfluidic device. In some embodiments, the sub-channel may have the same cross-sectional dimension as the microchannel. In some embodiments, the sub-channel may have different cross-sectional dimension than the microchannel. In some embodiments, the sub-channel may have the same depth as the microchannel and a different cross-sectional dimension. In some embodiments, the sub-channel may have the same cross-sectional dimension as the microchannel and a different depth. For example, the sub-channel may have a depth of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 80 μm , less than or equal to about 60 μm , less than or equal to about 30 μm , less than or equal to about 15 μm , or less. The sub-channel may have a cross-section width of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 75 μm , less than or equal to about 50 μm , less than or equal to about 40 μm , less than or equal to about 30 μm , less than or equal to about 20 μm , less than or equal to about 10 μm , or less.

[0065] In some examples, the cross-sectional dimensions of the sub-channel may be about 100 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 100 μm wide by about 80 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 100 μm wide by about 60 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 100 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 100 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 100 μm wide by about 10 μm deep. In some examples, the cross-

sectional dimensions of the sub-channel may be about 80 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 60 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 40 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 20 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 10 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 80 μm wide by about 80 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 60 μm wide by about 60 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 40 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 20 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the sub-channel may be about 10 μm wide by about 10 μm deep. The cross-sectional shape of the sub-channel may be any suitable cross-sectional shape including, but not limited to, circular, oval, triangular, square, or rectangular. In some embodiments, the cross sectional shape of the sub-channel is different than the cross-sectional shape of the microchannel. In some embodiments, the cross-sectional shape of the sub-channel is the same as the cross-sectional shape of the microchannel. The cross-sectional area of the sub-channel may be constant along the length of the sub-channel. Alternatively, or in addition to, the cross-sectional area of the sub-channel may vary along the length of the microchannel. The cross-sectional area of the sub-channel may vary between about 50% and 150%, between about 60% and 125%, between about 70% and 120%, between about 80% and 115%, between about 90% and 110%, between about 95% and 100%, or between about 98% and 102%. The cross-sectional area of the sub-channel may be less than or equal to about 10,000 μm^2 , less than or equal to about 7,500 μm^2 , less than or equal to about 5,000 μm^2 , less than or equal to about 2,500 μm^2 , less than or equal to about 1,000 μm^2 , less than or equal to about 750 μm^2 , less than or equal to about 500 μm^2 , less than or equal to about 400 μm^2 , less than or equal to about 300 μm^2 , less than or equal to about 200 μm^2 , less than or equal to about 100 μm^2 , or less. In some embodiments, the cross-sectional area of the sub-channel is the same as the cross-sectional area of the microchannel. In some embodiments, the cross-sectional area of the sub-channel may be less than or equal to the area of the cross-sectional area of the microchannel. The cross-sectional area of the sub-channel may be less than or equal to about 98 %, less than or equal to about 95 %, less than or equal to about 90%, less than or equal to about 85 %, less than or equal to about 80%, less than or equal to about 75 %, less than or equal to about 70%, less than or equal to about 60%, less than or equal to about 50%, less than or equal to about 40%, less

than or equal to about 30 %, less than or equal to about 20 %, less than or equal to about 20%, or less of the cross-sectional area of the microchannel.

[0066] In some embodiments, the lengths of the cross-channels are constant. In some embodiments, the lengths of the cross-channel may vary. The cross-channel may have a long dimension that is less than or equal to about 100 mm, less than or equal to about 75 mm, less than or equal to about 50 mm, less than or equal to about 40 mm, less than or equal to about 30 mm, less than or equal to about 20 mm, less than or equal to about 10 mm, less than or equal to about 8 mm, less than or equal to about 6 mm, less than or equal to about 4 mm, less than or equal to about 2 mm, or less. The length of the cross-channel may be bounded by the external length or width of the microfluidic device. In some embodiments, the cross-channel may have the same cross-sectional dimension as the microchannel. In some embodiments, the cross-channel may have a different cross-sectional dimension than the microchannel. In some embodiments, the cross-channel may have the same depth as the microchannel and a different cross-sectional dimension. In some embodiments, the cross-channel may have the same cross-sectional dimension as the microchannel and a different depth. For example, the cross-channel may have a depth of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 80 μm , less than or equal to about 60 μm , less than or equal to about 30 μm , less than or equal to about 15 μm , or less. The cross-channel may have a cross-section width of less than or equal to about 500 μm , less than or equal to about 250 μm , less than or equal to about 100 μm , less than or equal to about 75 μm , less than or equal to about 50 μm , less than or equal to about 40 μm , less than or equal to about 30 μm , less than or equal to about 20 μm , less than or equal to about 10 μm , or less.

[0067] In some examples, the cross-sectional dimensions of the cross-channel may be about 100 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 100 μm wide by about 80 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 100 μm wide by about 60 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 100 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 100 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 100 μm wide by about 10 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 80 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 60 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 40 μm wide by about 100 μm deep. In some examples, the cross-sectional

dimensions of the cross-channel may be about 20 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 10 μm wide by about 100 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 80 μm wide by about 80 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 60 μm wide by about 60 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 40 μm wide by about 40 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 20 μm wide by about 20 μm deep. In some examples, the cross-sectional dimensions of the cross-channel may be about 10 μm wide by about 10 μm deep.

[0068] The cross-sectional shape of the cross-channel may be any suitable cross-sectional shape including, but not limited to, circular, oval, triangular, square, or rectangular. In some embodiments, the cross sectional shape of the cross-channel is different than the cross-sectional shape of the microchannel. In some embodiments, the cross-sectional shape of the cross-channel is the same as the cross-sectional shape of the microchannel. The cross-sectional area of the cross-channel may be constant down the length of the cross-channel. Alternatively, or in addition to, the cross-sectional area of the cross-channel may vary down the length of the microchannel. The cross-sectional area of the cross-channel may vary between about 50% and 150%, between about 60% and 125%, between about 70% and 120%, between about 80% and 115%, between about 90% and 110%, between about 95% and 100%, or between about 98% and 102%. The cross-sectional area of the cross-channel may be less than or equal to about 10,000 μm^2 , less than or equal to about 7,500 μm^2 , less than or equal to about 5,000 μm^2 , less than or equal to about 2,500 μm^2 , less than or equal to about 1,000 μm^2 , less than or equal to about 750 μm^2 , less than or equal to about 500 μm^2 , less than or equal to about 400 μm^2 , less than or equal to about 300 μm^2 , less than or equal to about 200 μm^2 , less than or equal to about 100 μm^2 , or less. In some embodiments, the cross-sectional area of the cross-channel is the same as the cross-sectional area of the microchannel. In some embodiments, the cross-sectional area of the cross-channel is less than the area of the cross-sectional area of the microchannel. The cross-sectional area of cross-channel may be less than or equal to about 98 %, less than or equal to about 95 %, less than or equal to about 90%, less than or equal to about 85 %, less than or equal to about 80%, less than or equal to about 75 %, less than or equal to about 70%, less than or equal to about 60%, less than or equal to about 50%, less than or equal to about 40%, less than or equal to about 30 %, less than or equal to about 20 %, less than or equal to about 20%, or less of the cross-sectional area of the microchannel.

Method for fabricating a microfluidic device

[0069] In an aspect, the present disclosure provides methods for fabricating a microfluidic device. The method may comprise injection molding a thermoplastic to create a microfluidic structure. The microfluidic structure may comprise a microchannel, a plurality of microchambers, and a plurality of siphon apertures. The plurality of microchambers may be connected to the microchannel by the plurality of siphon apertures. The microchannel may comprise an inlet and an outlet. A thermoplastic thin film may be applied to cap the microfluidic structure. The thermoplastic thin film may be at least partially gas permeable when a pressure differential is applied across the thermoplastic thin film.

[0070] In some embodiments, the thermoplastic thin film is formed by injection molding. The thermoplastic thin film may be applied to the microfluidic structure by thermal bonding. Alternatively, or in addition to, the thin film may be applied by chemical bonding. In some embodiments, the thermoplastic thin film is formed as part of and during the injection molding process to form the microfluidic device.

[0071] The body of the microfluidic device and the thin film may comprise the same materials. Alternatively, the body of the microfluidic device and the thin film may comprise different materials. The body of the microfluidic device and the thin film may comprise a thermoplastic. Example thermoplastics include, but are not limited to, cyclo-olefin polymers, acrylic, acrylonitrile butadiene styrene, nylon, polylactic acid, polybenzimidazole, polycarbonate, polyether sulfone, poly ether ether ketone, polyetherimide, polyethylene, polyphenylene oxide, polyphenylene sulfide, polypropylene, polystyrene, polyvinyl chloride, polytetrafluoroethylene, polyester, polyurethane or any derivative thereof. The microfluidic device may comprise homopolymers, copolymers, or a combination thereof. The microfluidic device may be formed of inelastic materials. Alternatively, or in addition to, the microfluidic device may be formed of elastic materials.

[0072] In an example embodiment of the present disclosure, both the thermoplastic and the thin film are composed of a cyclo-olefin polymer. One suitable thermoplastic is Zeonor 1430R (Zeon Chemical, Japan) while one suitable thin film is Zeonox 1060R (Zeon Chemical, Japan). In some embodiments, the thin film is a material that is gas-impermeable at low pressure and at least partially gas permeable under pressure.

[0073] In some embodiments, the inlet and the outlet are formed by mechanical drilling. In some embodiments, the inlet and outlet are formed by melting, dissolving, or etching the thermoplastic.

[0074] **FIG. 4** illustrates a method of manufacture of embodiments of the present disclosure. In **FIG. 4**, an injection molding process **401** is used to form a microfluidic structure. The

microfluidic structure includes an array of microchambers, which are connected to at least one microchannel via siphon apertures, as shown in **FIGs. 1A** and **1B**. The microfluidic structure is capped by a thin film. In the capping process, openings in at least one side of the microstructure are covered over in order to close and seal the microstructures. In some embodiments of the present disclosure, the capping is performed by a process **402** of applying a thin film to the injection molded microfluidic structure. In some embodiments of the present disclosure, the capping is performed by forming the thin film as part of the injection molding process **401**.

[0075] As another example, while described in the context of a microstructure which is formed via injection molding, microfluidic devices formed by other microfabrication techniques may also benefit from the use of such a thin thermoplastic film to allow outgassing as described above. Such techniques include micromachining, microlithography, and hot embossing, as well as other microfabrication techniques.

[0076] In an aspect, the present disclosure provides method for forming a microfluidic device. A method for forming a microfluidic device may comprise providing a microfluidic structure and a film. A surface of the microfluidic structure, a surface of the film, or both may be treated with a solvent. The microfluidic structure may be pressed together with the film under a first heating condition to form the microfluidic device comprising the solvent. A negative pressure may be applied to the microfluidic device under a second heating condition, which negative pressure may be applied for a time period greater than 30 minutes or at a pressure less than 20 kilopascals (kPa) to remove at least a portion of the solvent.

[0077] **FIG. 11** is a flowchart of an example process 1100 for forming a microfluidic device. The process may be implemented using at least one appropriately configured system as described elsewhere herein. The system may be an operator (e.g., a human technician), an automated system (e.g., able to function without human intervention), or a semi-automated system (e.g., a human implements some operations while a machine implements others). The system may perform all operations in one system (e.g., have one chamber for pressing, heating, and applying vacuum) or perform the operations in multiple systems (e.g., a heated jig to thermally bond as well as a heated vacuum oven to remove solvents).

[0078] The system may provide a microfluidic structure and a film (1110). The microfluidic structure may be a microfluidic structure as described elsewhere herein. The microfluidic structure may comprise at least about 2, 3, 4, 5, 6, 7, 8, 9, 10, 50, 100, 250, 500, 1,000, 5,000, 10,000, 50,000, 100,000, 500,000, 1,000,000, or more features. The microfluidic structure may comprise at most about 1,000,000, 500,000, 100,000, 50,000, 10,000, 5,000, 1,000, 500, 250, 100, 50, 10, 9, 8, 7, 6, 5, 4, 3, 2, or less features. The feature may be at least one microchannel,

at least one microchamber, at least one siphon aperture, or any combination thereof. For example, a microfluidic structure can have 100,000 microchannels, 100,000 microchambers, and 5 siphon arrays. The microfluidic structure may be generated by an injection method (e.g., injection molding), an extrusion method (e.g., filament deposition 3D printing), a light-based method (e.g., stereolithography, digital light projection 3D printing, laser sintering), or the like. The microfluidic structure may be configured to house and contain a reaction (e.g., a PCR reaction, a chemical synthesis reaction). The microfluidic structure may be made of one or more materials. The one or more materials may be composites, plastics, metals, or the like. The plastics may be a methacrylate (e.g., polymethyl methacrylate (PMMA), polyethyl methacrylate (PEMA)), polylactic acid (PLA), a poly unsaturated polymer (e.g., polyethylene, polypropylene), a cyclic olefin copolymer (COC), a polycarbonate, a polysulphone, a polyetherimide, or the like. The composite may be a combination of a plastic a reinforcing agent (e.g., carbon fiber, nanoparticles, etc.). The metal may be a pure metal (e.g., aluminum, iron) or an alloy (e.g., stainless steel, tin).

[0079] The film may be a plain film (e.g., not having defined features), a patterned film (e.g., comprising defined features), a microfluidic system, or the like. The film may be a same microfluidic system as the microfluidic system (e.g., having the same features) or a different microfluidic system (e.g., having different microfluidic features). The film may be generated by an injection method (e.g., injection molding), an extrusion method (e.g., filament deposition 3D printing, film extrusion), a light-based method (e.g., stereolithography, digital light projection 3D printing, laser sintering), or the like. The film may be made of a material as described above. The film may be of a same material as the microfluidic structure. Alternatively, the film may be of a different material as the microfluidic structure. For example, a microfluidic structure made of PMMA can be bound to a film made of PLMA. In another example, both the microfluidic structure and the film can be a COC polymer.

[0080] The system may treat a surface of the microfluidic structure, a surface of the film, or both with a solvent (1120). The treatment may be a treatment with a solvent, a physical process (e.g., plasma treatment, heat treatment), a surface roughening, or any combination thereof. The solvent may be an organic solvent or an inorganic solvent (e.g., water, a solution in water, a eutectic metal mixture, a molten salt). The organic solvent may be a non-polar solvent (e.g., hexanes, cyclohexane, cyclohexene, toluene, xylenes, toluene, benzene, carbon tetrachloride, etc.) or a polar solvent (e.g., methanol, ethanol, isopropanol, ethyl acetate, chloroform, acetone, dimethyl sulphoxide (DMSO), N-methyl formamide (NMF), etc.). The solvent may be selected based on a solubility of the material of the microfluidic structure, the film, or both. For example, a solvent

can be selected because it does not fully dissolve the polymer of the film, but it does provide enough solvation to generate a strong seal between the film and the microfluidic structure. The treatment may comprise introduction of the solvent by drop casting, spin coating, doctor blading, centrifugal casting, as a vapor (e.g., passing a carrier gas through a bubbler chamber, providing an open dish of solvent in a container with the microfluidic device and/or the film), or the like. For example, a film can be placed into a bell jar with an inlet of nitrogen gas that has bubbled through cyclohexane, thus applying cyclohexane that evaporated into the gas to the film. The microfluidic device and the film may be treated with the same solvent or different solvents. For example, the microfluidic device can be treated with cyclohexane and the film can be treated with a mixture of xylenes. The treatment may comprise a waiting period after the solvent is applied. The waiting period may be a time to let the solvent interact with the microfluidic device and/or film before further processing. The waiting period may be at least about 0.5, 1, 5, 10, 30, 60, 120, 180, 240, 300, 500, 1,000, or more seconds. The waiting period may be at most about 1,000, 500, 300, 240, 180, 120, 60, 30, 10, 5, 1, 0.5, or less seconds. The waiting period may be a range defined by any two numbers above. For example, after applying acetone, the film can be left for 30-60 seconds to allow the acetone to soften the polymer of the film.

[0081] The system may press the microfluidic structure together with the film under a first heating condition to form the microfluidic device comprising the solvent (1130). The pressing may be performed with the aid of a jig, a vice, a hydraulic press, a pressurized gas chamber (e.g., an autoclave, a pressurized oven), or the like to bond the microfluidic structure to the film. The pressing may include applying a force of at least about 0.5 kilo-Newtons (kN), 1 kN, 2 kN, 4 kN, 6 kN, 8 kN, 10 kN, 15 kN, 20 kN, 25 kN, 30 kN, 40 kN, 50 kN, or larger force. The pressing may include applying a force of at most about 50 kN, 40 kN, 30 kN, 25 kN, 20 kN, 15 kN, 10 kN, 8 kN, 6 kN, 4 kN, 2 kN, 1 kN, 0.5 kN, or smaller force. The pressing may include applying a force of about 0.5 kN to 1 kN, 0.5 kN to 2 kN, 0.5 kN to 4 kN, 0.5 kN to 6 kN, 0.5 kN to 8 kN, 0.5 kN to 10 kN, 0.5 kN to 15 kN, 0.5 kN to 20 kN, 0.5 kN to 25 kN, 0.5 kN to 30 kN, 0.5 kN to 40 kN, 0.5 kN to 50 kN, 1 kN to 2 kN, 1 kN to 4 kN, 1 kN to 6 kN, 1 kN to 8 kN, 1 kN to 10 kN, 1 kN to 15 kN, 1 kN to 20 kN, 1 kN to 25 kN, 1 kN to 30 kN, 1 kN to 40 kN, 1 kN to 50 kN, 2 kN to 4 kN, 2 kN to 6 kN, 2 kN to 8 kN, 2 kN to 10 kN, 2 kN to 15 kN, 2 kN to 20 kN, 2 kN to 25 kN, 2 kN to 30 kN, 2 kN to 40 kN, 2 kN to 50 kN, 4 kN to 6 kN, 4 kN to 8 kN, 4 kN to 10 kN, 4 kN to 15 kN, 4 kN to 20 kN, 4 kN to 25 kN, 4 kN to 30 kN, 4 kN to 40 kN, 4 kN to 50 kN, 6 kN to 8 kN, 6 kN to 10 kN, 6 kN to 15 kN, 6 kN to 20 kN, 6 kN to 25 kN, 6 kN to 30 kN, 6 kN to 40 kN, 6 kN to 50 kN, 8 kN to 10 kN, 8 kN to 15 kN, 8 kN to 20 kN, 8 kN to 25 kN, 8 kN to 30 kN, 8 kN to 40 kN, 8 kN to 50 kN, 10 kN to 15 kN, 10 kN to 20 kN, 10 kN to 25 kN, 10 kN

to 30 kN, 10 kN to 40 kN, 10 kN to 50 kN, 15 kN to 20 kN, 15 kN to 25 kN, 15 kN to 30 kN, 15 kN to 40 kN, 15 kN to 50 kN, 20 kN to 25 kN, 20 kN to 30 kN, 20 kN to 40 kN, 20 kN to 50 kN, 25 kN to 30 kN, 25 kN to 40 kN, 25 kN to 50 kN, 30 kN to 40 kN, 30 kN to 50 kN, or 40 kN to 50 kN. In an example, the pressing includes applying a force of at least 1 kN. In another example, includes applying a force of 1 kN to 40 kN. The first heating condition may be heating the microfluidic structure together with the film to a temperature of at least about 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 105, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, or more °C. The first heating condition may be heating the microfluidic structure together with the film to a temperature of at most about 200, 190, 180, 170, 160, 150, 140, 130, 120, 110, 105, 100, 95, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, or less °C. The first heating condition may be heating to a temperature range defined by any two numbers above. For example, the first heating condition can be heating to a temperature within a range of 75 °C – 85 °C. The first heating condition may be heating to at least about 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, or more °C under the boiling point of the solvent. The first heating condition may be heating to at most about 10, 9, 8, 7, 6, 5, 4, 3, 2, 1, or less °C under the boiling point of the solvent. For example, if cyclohexane was used as a solvent, the first heating condition can be heating to 78 °C, as the boiling point of cyclohexane is approximately 80 °C. The pressing may occur concurrently to the first heating condition. The pressing may occur before and/or after the first heating condition. For example, the microfluidic device can be heated and then placed under pressure. The pressing and the first heating condition may be maintained for at least about 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 30, 45, 60, or more minutes. The pressing and the first heating condition may be maintained for at most about 60, 45, 30, 20, 19, 18, 17, 16, 15, 14, 13, 12, 11, 10, 9, 8, 7, 6, 5, 4, 3, 2, 1, or less minutes. For example, n-hexane can be applied to both a microfluidic structure and a film, the two can be pressed together at 350 kPa and held at a temperature of 80 °C for 2 minutes to form the microfluidic device. The heating of the first heating condition may remove at least a fraction of the solvent from the microfluidic device. The heating of the first heating condition may remove at least about 1, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 97, 98, 99, or more percent of the solvent. The heating of the first heating condition may remove at most about 99, 98, 97, 95, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, 20, 15, 10, 5, 1, or less percent of the solvent.

[0082] Subsequently to form the microfluidic device, the system may apply a negative pressure to the microfluidic device under a second heating condition for a time period greater than 30 minutes to remove at least a portion of the solvent (1140) in order to remove at least a portion of residual solvent. The residual solvent may be solvent left over from operation 1120. The negative

pressure may be applied using a vacuum pump. The vacuum pump may be attached to a chamber (e.g., a bell jar, a vacuum oven) containing the microfluidic device. The negative pressure may be a reduction of pressure of at least about 1, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 100, or more kPa. The negative pressure may be a reduction of pressure of at most about 100, 99, 98, 97, 96, 95, 94, 93, 92, 91, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, 20, 15, 10, 5, 1, or less kPa. The negative pressure may be applied in tandem with the second heating condition. The negative pressure may be applied before and/or after the second heating condition. The second heating condition may be heating the microfluidic device to a temperature of at least about 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 105, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, or more °C. The second heating condition may be heating the microfluidic device to a temperature of at most about 200, 190, 180, 170, 160, 150, 140, 130, 120, 110, 105, 100, 95, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, or less °C. The second heating condition may be heating to a temperature range defined by any two numbers above. For example, the second heating condition can be heating to a temperature within a range of 80 °C – 90 °C. The second heating condition may be heating to at least about 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, or more °C under the boiling point of the solvent. The second heating condition may be heating to at most about 10, 9, 8, 7, 6, 5, 4, 3, 2, 1, or less °C under the boiling point of the solvent. The boiling point of the solvent may depend on the magnitude of the negative pressure applied. For example, if cyclohexane was used as a solvent, the second heating condition can be heating to 44 °C, as the boiling point of cyclohexane is approximately 45 °C at a pressure of 20 kPa. The negative pressure and/or the second heating condition may be applied for at least about 0.25, 0.5, 0.75, 1, 1.5, 2, 2.5, 3, 3.5, 4, 4.5, 5, 5.5, 6, 6.5, 7, 7.5, 8, 8.5, 9, 9.5, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 30, 36, 42, 48, 54, 60, 66, 72, or more hours. The negative pressure and/or the second heating condition may be applied for at most about 72, 66, 60, 54, 48, 42, 36, 30, 24, 23, 22, 21, 20, 19, 18, 17, 16, 15, 14, 13, 12, 11, 10, 9.5, 9, 8.5, 8, 7.5, 7, 6.5, 6, 5.5, 5, 4.5, 4, 3.5, 3, 2.5, 2, 1.5, 1, 0.75, 0.5, 0.25, or less hours. The heating and/or the negative pressure of operation 1140 may remove at least a fraction of the residual solvent from the microfluidic device. The heating and/or the negative pressure of operation 1140 may remove at least about 1, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 99.9, or more percent of the residual solvent. The heating and/or the negative pressure of operation 1140 may remove at most about 99.9, 99, 98, 97, 96, 95, 94, 93, 92, 91, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, 20, 15, 10, 5, 1, or less percent of the residual solvent. The applying the negative

pressure under the second heating condition may reduce separation between the microfluidic structure and the film.

[0083] Additional strategies may be utilized to further decrease the amount of residual solvent in the microfluidic device. An increased pressure may be applied to the microfluidic device. The increased pressure may be sufficient to expel at least a portion of the residual solvent. For example, a pressurized gas line can be attached to the microfluidic device and dry gas can be flowed through the device, further removing residual solvent. The microfluidic device may be washed with a different solvent with a higher vapor pressure. For example, if octane was used as the solvent to bond the microfluidic structure and the film, pentane can be quickly flowed through the remove the majority of the high boiling point octane before the microfluidic device is subjected to negative pressure and the second heating condition to remove the pentane.

[0084] **FIG. 12** is an example schematic for forming a microfluidic device. Microfluidic structure 1210 and film 1220 can be formed as described elsewhere herein. Microfluidic structure 1210 may have features with a feature size of at least about 0.1, 1, 5, 10, 20, 30, 40, 50, 60, 70, 80, 90, 100, 125, 150, 175, 200, 225, 250, 275, 300, 325, 350, 375, 400, 450, 500, 550, 600, 650, 700, 750, 800, 850, 900, 950, 1,000, or more micrometers. Microfluidic structure 1210 may have features with a feature size of at most about 1,000, 950, 900, 850, 800, 750, 700, 650, 600, 550, 500, 450, 400, 375, 350, 325, 300, 275, 250, 225, 200, 175, 150, 125, 100, 90, 80, 70, 60, 50, 40, 30, 20, 10, 5, 1, 0.1, or less micrometers. The microfluidic structure may have a plurality of different feature sizes. For example, a microfluidic structure can have a 500 micrometer well connected to a 250 micrometer channel by a 100 micrometer trough. The feature may be a channel, a chamber, a well, a pump, a neck, or the like. In this example schematic, film 1220 has solvent 1230 applied to it, as described in operation 1120 of **FIG. 11**.

[0085] Following operation 1130 of **FIG. 11**, the microfluidic structure and the film are bound to generate microfluidic device 1240. Microfluidic device 1240 may comprise void 1250. The void may be a feature as described above. Void 1250 may retain some of solvent 1230 after the bonding process is complete. The retained solvent can weaken the microfluidic device, causing microfluidic structure 1210 and film 1220 to delaminate or separate when pressure and/or heat is applied. To remove the residual solvent from void 1250, microfluidic device 1240 may be placed into vacuum chamber 1260. Vacuum chamber 1260 can be involved in the implementation of operation 1140 of **FIG. 11** to remove the residual solvent from the microfluidic device. The removing the residual solvent may decrease the delamination of the microfluidic structure and the film. The amount of delamination may be reduced by at least about 1, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 99.9, or more

percent. The amount of delamination may be reduced by at most about 99.9, 99, 98, 97, 96, 95, 94, 93, 92, 91, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, 20, 15, 10, 5, 1, or less percent. For example, a microfluidic device treated with heat and vacuum can have 50% less delamination under operation conditions than a microfluidic device that has not been treated.

[0086] FIGs. 18A – 18B are example magnified images of of a microfluidic device fabricated without solvent removal before (**FIG. 18A**) and after (**FIG. 18B**) liquid pressurization and heating. The liquid pressurization and heating may simulate operation conditions of the microfluidic device. The large, dark bubbles seen throughout **FIG. 18B** may be indications of delamination of the microfluidic structure from the film.

[0087] FIGs. 19A – 19B are example magnified images of a vacuum treated microfluidic device before (**FIG. 19A**) and after (**FIG. 19B**) liquid pressurization and heating. **FIGs. 20A – 20B** are example magnified images of a heat treated microfluidic device before (**FIG. 20A**) and after (**FIG. 20B**) liquid pressurization and heating. Both of the microfluidic devices of **FIGs. 19B** and **20B** show a decrease in the number and severity of bubbles and delamination as compared to **FIG. 18B**.

[0088] FIGs. 21A – 21B are example magnified images of a vacuum and heat treated, as described elsewhere herein, microfluidic device before (**FIG. 21A**) and after (**FIG. 21B**) liquid pressurization and heating. The use of both heat treatment and negative pressure may eliminate residual solvent and delamination. The removing the residual solvent may increase a yield of a microfluidic device generation process by at least about 1, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 125, 150, 175, 200, 250, 300, 400, 500, 600, 700, 800, 900, 1,000, or more percent. The removing the residual solvent may increase a yield of a microfluidic device generation process by at most about 1,000, 900, 800, 700, 600, 500, 400, 300, 250, 200, 175, 150, 125, 100, 95, 90, 85, 80, 75, 70, 65, 60, 55, 50, 45, 40, 35, 30, 25, 20, 15, 10, 5, 1, or less percent. The usable feature fraction of a microfluidic device may be the number of a usable feature (e.g., microchambers) divided by the total number of that feature within the microfluidic device. For example, a microfluidic device with 500 usable microchambers out of a total of 1,500 microchambers has a usable microchamber fraction of 0.33. A microfluidic device produced my methods and systems described herein may have a usable feature fraction of at least about 0.01, 0.05, 0.1, 0.15, 0.2, 0.25, 0.3, 0.35, 0.4, 0.45, 0.5, 0.55, 0.6, 0.65, 0.7, 0.75, 0.8, 0.85, 0.9, 0.95, 0.96, 0.97, 0.98, 0.99, 0.999, or more. A microfluidic device produced my methods and systems described herein may have a usable feature fraction of at most about 0.999, 0.99, 0.95, 0.9, 0.85, 0.8, 0.75, 0.7, 0.65, 0.6, 0.55, 0.5, 0.45, 0.4, 0.35, 0.3, 0.25, 0.2, 0.15, 0.1, 0.05, 0.01, or less.

Method of analyzing a nucleic acid sample

[0089] In an aspect, the present disclosure provides methods for using a microfluidic device to analyze a nucleic acid sample. The method may comprise providing a microfluidic device comprising a microchannel. The microchannel may comprise an inlet and an outlet. The microfluidic device may further comprise a plurality of microchambers connected to the microchannel by a plurality of siphon apertures. The microfluidic device may be sealed by a thermoplastic thin film disposed adjacent to a surface of the microfluidic device such that the thermoplastic thin film caps the microchannel, the plurality of microchambers, and the plurality of siphon apertures. A reagent may be applied to the inlet or the outlet. The microfluidic device may be filled by providing a first pressure differential between the reagent and the microfluidic device, causing the reagent to flow into the microfluidic device. The reagent may be partitioned into the microchambers by applying a second pressure differential between the microchannel and the plurality of microchambers to move the reagent into the plurality of microchambers and to force gas within the plurality of microchambers to pass through the thermoplastic thin film. The second pressure differential may be greater than the first pressure differential. A third pressure differential between the inlet and the outlet may be applied to introduce a fluid into the microchannel without introducing the fluid into the microchambers. The third pressure differential may be less than the second pressure differential.

[0090] In some embodiments, the inlet and the outlet are in fluid communication with a pneumatic pump. In some embodiments, the microfluidic device is in contact with a vacuum system. Filling and partitioning of a sample may be performed by applying pressure differentials across various features of the microfluidic device. In some embodiments, filling and partitioning of the sample may be performed without the use of valves between the microchambers and the microchannel to isolate the sample. For example, filling of the microchannel may be performed by applying a pressure differential between the sample to be loaded and the microchannel. This pressure differential may be achieved by pressurizing the sample or by applying vacuum to the microchannel. Filling the microchambers may be performed by applying a pressure differential between the microchannel and the microchambers. This may be achieved by pressurizing the microchannel or by applying a vacuum to the microchambers. Partitioning the sample may be performed by applying a pressure differential between a fluid and the microchannel. This pressure differential may be achieved by pressurizing the fluid or by applying a vacuum to the microchannel.

[0091] The thin film may employ different permeability characteristics under different applied pressure differentials. For example, the thin film may be gas impermeable at the first and third pressure differentials (e.g., low pressure), which may be smaller magnitude pressure differentials. The thin film may be at least partially gas permeable at the second pressure differential (e.g., high pressure), which may be a higher magnitude pressure differential. The first and third pressure differentials may be the same or they may be different. The first pressure differential may be the difference in pressure between the reagent in the inlet or outlet and the microfluidic device. During filling of the microfluidic device, the pressure of the reagent may be higher than the pressure of the microfluidic device. During filling of the microfluidic device, the pressure difference between the reagent and the microfluidic device (e.g., low pressure) may be less than or equal to about 8 pounds per square inch (psi), less than or equal to about 6 psi, less than or equal to about 4 psi, less than or equal to about 2 psi, less than or equal to about 1 psi, or less. In some examples, during filling of the microfluidic device, the pressure differential between the reagent and the microfluidic device may be from about 1 psi to about 8 psi. In some examples, during filling of the microfluidic device, the pressure differential between the reagent and the microfluidic device may be from about 1 psi to about 6 psi. In some examples, during filling of the microfluidic device, the pressure differential between the reagent and the microfluidic device may be from about 1 psi to about 4 psi. The microfluidic device may be filled by applying a pressure differential between the reagent and the microfluidic device for less than or equal to about 20 minutes, less than or equal to about 15 minutes, less than or equal to about 10 minutes, less than or equal to about 5 minutes, less than or equal to about 3 minutes, less than or equal to about 2 minutes, less than or equal about 1 minute, or less.

[0092] A filled microfluidic device may have reagent in the microchannel, siphon apertures, microchambers, or any combination thereof. Backfilling of the reagent into the microchambers may occur upon filling of the microfluidic device or may occur during application of a second pressure differential. The second pressure differential (e.g., high pressure) may correspond to the difference in pressure between the microchannel and the plurality of microchambers. During application of the second pressure differential a first fluid in the higher pressure domain may push a second fluid in the lower pressure domain through the thin film and out of the microfluidic device. The first and second fluids may comprise a liquid or a gas. The liquid may comprise an aqueous mixture or an oil mixture. The second pressure differential may be achieved by pressurizing the microchannel. Alternatively, or in addition to, the second pressure differentially may be achieved by applying a vacuum to the microchambers. During application

of the second pressure differential, reagent in the microchannel may flow into the microchambers. Additionally, during the application of the second pressure differential gas trapped within the siphon apertures, microchambers, and microchannel may outgas through the thin film. During backfilling and outgassing of the microchambers, the pressure differential between the microchambers and the microchannel may be greater than or equal to about 6 psi, greater than or equal to about 8 psi, greater than or equal to about 10 psi, greater than or equal to about 12 psi, greater than or equal to about 14 psi, greater than or equal to about 16 psi, greater than or equal to about 18 psi, greater than or equal to about 20 psi, or greater. In some examples, during backfilling of the microchambers, the pressure differential between the microchambers and the microchannel is from about 8 psi to about 20 psi. In some examples, during backfilling of the microchambers, the pressure differential between the microchambers and the microchannel is from about 8 psi to about 18 psi. In some examples, during backfilling of the microchambers, the pressure differential between the microchambers and the microchannel is from about 8 psi to about 16 psi. In some examples, during backfilling of the microchambers, the pressure differential between the microchambers and the microchannel is from about 8 psi to about 14 psi. In some examples, during backfilling of the microchambers, the pressure differential between the microchambers and the microchannel is from about 8 psi to about 12 psi. In some examples, during backfilling of the microchambers, the pressure differential between the microchambers and the microchannel is from about 8 psi to about 10 psi. The microchambers may be backfilled and outgassed by applying a pressure differential for more than about 5 minutes, more than about 10 minutes, more than about 15 minutes, more than about 20 minutes, more than about 25 minutes, more than about 30 minutes, or more.

[0093] The sample may be partitioned by removing the excess sample from the microchannel. Removing excess sample from the microchannel may prevent reagents in one microchamber from diffusing through the siphon aperture into the microchannel and into other microchambers. Excess sample within the microchannel may be removed by introducing a fluid to the inlet or the outlet of the microchannel. The pressure of the fluid may be greater than the pressure of the microchannel, thereby creating a pressure differential between the fluid and the microchannel. The fluid may be oxygen, nitrogen, carbon dioxide, air, a noble gas, or any combination thereof. During partitioning of the sample, the pressure differential between the fluid and the microchannel may be less than or equal to about 8 psi, less than or equal to about 6 psi, less than or equal to about 4 psi, less than or equal to about 2 psi, less than or equal to about 1 psi, or less. In some examples, during partitioning of the sample, the pressure differential between the fluid and the microchannel may be from about 1 psi to about 8 psi. In some

examples, during partitioning of the sample, the pressure differential between the fluid and the microchannel may be from about 1 psi to about 6 psi. In some examples, during partitioning of the sample, the pressure differential between the fluid and the microchannel may be from about 1 psi to about 4 psi. The sample may be partitioned by applying a pressure differential between the fluid and the microchannel for less than or equal to about 20 minutes, less than or equal to about 15 minutes, less than or equal to about 10 minutes, less than or equal to about 5 minutes, less than or equal to about 3 minutes, less than or equal to about 2 minutes, less than or equal to about 1 minute, or less.

[0094] FIGs. 3A-3D illustrate a method for use of the microfluidic device shown in FIG. 1A. In FIG. 3A, a low pressure is applied to reagent at the inlet 120 via a pneumatic pump 300 to force reagent into the microchannel 110 and thereby fill the microchambers via the siphon apertures. The pressure forces reagent to flow through the microchannel, and thereby to flow into the microchambers via the siphon apertures. At this time, gas bubbles such as bubble 301 may remain within the microchambers, siphon apertures, or microchannel. Filling via the application of low pressure may continue until the microchambers, siphon apertures, and microchannel are substantially filled with reagent. The reagent may be a reagent to be used in a polymerase chain reaction. In some embodiments, the reagent is diluted such that no more than one PCR template is present in the reagent per microchamber of the microfluidic device.

[0095] In FIG. 3B, the pneumatic pump 300 is connected to both inlets 120 and outlets 130 and a high pressure is applied. The high pressure is transmitted via the reagent and applied to gas bubbles such as bubble 301. Under the influence of this high pressure, thin film 150 becomes gas permeable, and the bubble 301 can outgas through the thin film 150. By applying this high pressure, the microchambers, siphon apertures, and microchannel can be rendered substantially free of gas bubbles, thereby avoiding fouling.

[0096] In FIG. 3C, fluid is reintroduced by applying low pressure to a gas at the inlet 120 via pneumatic pump 300. The air pressure may not be sufficient to allow the gas to outgas through the thin film or high enough to force gas bubbles into the siphon apertures and microchambers. Instead, the gas may clear the microchannel of reagent, leaving the reagent isolated in each microchamber and siphon aperture. In some embodiments, the gas is air. In some embodiments, the gas may be an inert gas such as nitrogen, carbon dioxide, or a noble gas. Such a gas may be used to avoid reaction between the reagent and the component gases of air.

[0097] FIG. 3D illustrates the state of the system after the low pressure has been applied in FIG. 3C. After application of the low pressure gas the microchambers and siphon apertures may remain filled with reagent, while the microchannel may be cleared of reagent. The reagent may

remain stationary within the microchambers due to the capillary force and high surface tension created by the siphon aperture. The capillary force and high surface tension may prevent the reagent from flowing into the microchannel and minimize reagent evaporation.

[0098] Partitioning of the sample may be verified by the presence of an indicator within the reagent. An indicator may include a molecule comprising a detectable moiety. The detectable moiety may include radioactive species, fluorescent labels, chemiluminescent labels, enzymatic labels, colorimetric labels, or any combination thereof. Non-limiting examples of radioactive species include ^3H , ^{14}C , ^{22}Na , ^{32}P , ^{33}P , ^{35}S , ^{42}K , ^{45}Ca , ^{59}Fe , ^{123}I , ^{124}I , ^{125}I , ^{131}I , or ^{203}Hg . Non-limiting examples of fluorescent labels include fluorescent proteins, optically active dyes (e.g., a fluorescent dye), organometallic fluorophores, or any combination thereof. Non-limiting examples of chemiluminescent labels include enzymes of the luciferase class such as Cypridina, Gaussia, Renilla, and Firefly luciferases. Non-limiting examples of enzymatic labels include horseradish peroxidase (HRP), alkaline phosphatase (AP), beta galactosidase, glucose oxidase, or other labels.

[0099] In some embodiments, an indicator molecule is a fluorescent molecule. Fluorescent molecules may include fluorescent proteins, fluorescent dyes, and organometallic fluorophores. In some embodiments, the indicator molecule is a protein fluorophore. Protein fluorophores may include green fluorescent proteins (GFPs, fluorescent proteins that fluoresce in the green region of the spectrum, generally emitting light having a wavelength from 500-550 nanometers), cyan-fluorescent proteins (CFPs, fluorescent proteins that fluoresce in the cyan region of the spectrum, generally emitting light having a wavelength from 450-500 nanometers), red fluorescent proteins (RFPs, fluorescent proteins that fluoresce in the red region of the spectrum, generally emitting light having a wavelength from 600-650 nanometers). Non-limiting examples of protein fluorophores include mutants and spectral variants of AcGFP, AcGFP1, AmCyan, AmCyan1, AQ143, AsRed2, Azami Green, Azurite, BFP, Cerulean, CFP, CGFP, Citrine, copGFP, CyPet, dKeima-Tandem, DsRed, dsRed-Express, DsRed-Monomer, DsRed2, dTomato, dTomato-Tandem, EBFP, EBFP2, ECFP, EGFP, Emerald, EosFP, EYFP, GFP, HcRed-Tandem, HcRed1, JRed, Katuska, Kusabira Orange, Kusabira Orange2, mApple, mBanana, mCerulean, mCFP, mCherry, mCitrine, mECFP, mEmerald, mGrape1, mGrape2, mHoneydew, Midori-Ishi Cyan, mKeima, mKO, mOrange, mOrange2, mPlum, mRaspberry, mRFP1, mRuby, mStrawberry, mTagBFP, mTangerine, mTeal, mTomato, mTurquoise, mWasabi, PhiYFP, ReAsH, Sapphire, Superfolder GFP, T-Sapphire, TagCFP, TagGFP, TagRFP, TagRFP-T, TagYFP, tdTomato, Topaz, TurboGFP, Venus, YFP, YPet, ZsGreen, and ZsYellow1.

[00100] In some embodiments, the indicator molecule is a fluorescent dye. Non-limiting examples of fluorescent dyes include SYBR green, SYBR blue, DAPI, propidium iodine, Hoechst, SYBR gold, ethidium bromide, acridines, proflavine, acridine orange, acriflavine, fluorocoumarin, ellipticine, daunomycin, chloroquine, distamycin D, chromomycin, homidium, mithramycin, ruthenium polypyridyls, anthramycin, phenanthridines and acridines, ethidium bromide, propidium iodide, hexidium iodide, dihydroethidium, ethidium homodimer-1 and -2, ethidium monoazide, and ACMA, Hoechst 33258, Hoechst 33342, Hoechst 34580, DAPI, acridine orange, 7-AAD, actinomycin D, LDS751, hydroxystilbamidine, SYTOX Blue, SYTOX Green, SYTOX Orange, POPO-1, POPO-3, YOYO-1, YOYO-3, TOTO-1, TOTO-3, JOJO-1, LOLO-1, BOBO-1, BOBO-3, PO-PRO-1, PO-PRO-3, BO-PRO-1, BO-PRO-3, TO-PRO-1, TO-PRO-3, TO-PRO-5, JO-PRO-1, LO-PRO-1, YO-PRO-1, YO-PRO-3, PicoGreen, OliGreen, RiboGreen, SYBR Gold, SYBR Green I, SYBR Green II, SYBR DX, SYTO-40, -41, -42, -43, -44, -45 (blue), SYTO-13, -16, -24, -21, -23, -12, -11, -20, -22, -15, -14, -25 (green), SYTO-81, -80, -82, -83, -84, -85 (orange), SYTO-64, -17, -59, -61, -62, -60, -63 (red), fluorescein, fluorescein isothiocyanate (FITC), tetramethyl rhodamine isothiocyanate (TRITC), rhodamine, tetramethyl rhodamine, R-phycoerythrin, Cy-2, Cy-3, Cy-3.5, Cy-5, Cy5.5, , Cy-7, Texas Red, Phar-Red, allophycocyanin (APC), Sybr Green I, Sybr Green II, Sybr Gold, CellTracker Green, 7-AAD, ethidium homodimer I, ethidium homodimer II, ethidium homodimer III, ethidium bromide, umbelliferone, eosin, green fluorescent protein, erythrosin, coumarin, methyl coumarin, pyrene, malachite green, stilbene, lucifer yellow, cascade blue, dichlorotriazinylamine fluorescein, dansyl chloride, fluorescent lanthanide complexes such as those including europium and terbium, carboxy tetrachloro fluorescein, 5 and/or 6-carboxy fluorescein (FAM), 5- (or 6-) iodoacetamidofluorescein, 5-{[2(and 3)-5-(Acetylmercapto)-succinyl]amino} fluorescein (SAMSA-fluorescein), lissamine rhodamine B sulfonyl chloride, 5 and/or 6 carboxy rhodamine (ROX), 7-amino-methyl-coumarin, 7-Amino-4-methylcoumarin-3-acetic acid (AMCA), BODIPY fluorophores, 8-methoxypyrene-1,3,6-trisulfonic acid trisodium salt, 3,6-Disulfonate-4-amino-naphthalimide, phycobiliproteins, AlexaFluor 350, 405, 430, 488, 532, 546, 555, 568, 594, 610, 633, 635, 647, 660, 680, 700, 750, and 790 dyes, DyLight 350, 405, 488, 550, 594, 633, 650, 680, 755, and 800 dyes, or other fluorophores.

[00101] In some embodiments, the indicator molecule is an organometallic fluorophore. Non limiting examples of organometallic fluorophores include lanthanide ion chelates, nonlimiting examples of which include tris(dibenzoylmethane) mono(1,10-phenanthroline)europium(III), tris(dibenzoylmethane) mono(5-amino-1,10-phenanthroline)europium (III), and Lumi4-Tb cryptate.

[00102] In some embodiments, the images are taken of the microfluidic device. Images may be taken of single microchambers, an array of microchambers, or of multiple arrays of microchambers concurrently. In some embodiments, the images are taken through the body of the microfluidic device. In some embodiments, images are taken through the thin film of the microfluidic device. In some embodiments, images are taken through both the body of the microfluidic device and through the thin film. In some embodiments, the body of the microfluidic device is substantially optically transparent. In some embodiments, the body of the microfluidic device is substantially optically opaque. In some embodiments, the thin film is substantially optically transparent. In some embodiments, images may be taken prior to filling the microfluidic device with reagent. In some embodiments, images may be taken after filling of the microfluidic device with reagent. In some embodiments, images may be taken during filling the microfluidic device with reagent. In some embodiments, images are taken to verify partitioning of the reagent. In some embodiments, images are taken during a reaction to monitor products of the reaction. In some embodiments, products of the reaction comprise amplification products. In some embodiments, images are taken at specified intervals. Alternatively, or in addition to, a video may be taken of the microfluidic device. The specified intervals may include taking an image at least every 300 seconds, at least every 240 seconds, at least every 180 seconds, at least every 120 seconds, at least every 90 seconds, at least every 60 seconds, at least every 30 seconds, at least every 15 seconds, at least every 10 seconds, at least every 5 seconds, at least every 4 seconds, at least every 3 seconds, at least every 2 seconds, at least every 1 second, or more frequently during a reaction.

[00103] In some embodiments, the method for using a microfluidic device may further comprise amplification of a nucleic acid sample. The microfluidic device may be filled with an amplification reagent comprising nucleic acid molecules, components necessary for an amplification reaction, an indicator molecule, and an amplification probe. The amplification may be performed by thermal cycling the plurality of microchambers. Detection of nucleic acid amplification may be performed by imaging the microchambers of the microfluidic device. The nucleic acid molecules may be quantified by counting the microchambers in which the nucleic acid molecules are successfully amplified and applying Poisson statistics. In some embodiments, nucleic acid amplification and quantification may be performed in a single integrated unit.

[00104] A variety of nucleic acid amplification reactions may be used to amplify the nucleic acid molecule in a sample to generate an amplified product. Amplification of a nucleic acid target may be linear, exponential, or a combination thereof. Non-limiting examples of nucleic acid amplification methods include primer extension, polymerase chain reaction, reverse

transcription, isothermal amplification, ligase chain reaction, helicase-dependent amplification, asymmetric amplification, rolling circle amplification, and multiple displacement amplification. In some embodiments, the amplification product is DNA or RNA. For embodiments directed towards DNA amplification, any DNA amplification method may be employed. DNA amplification methods include, but are not limited to, PCR, real-time PCR, assembly PCR, asymmetric PCR, digital PCR, dial-out PCR, helicase-dependent PCR, nested PCR, hot start PCR, inverse PCR, methylation-specific PCR, miniprimer PCR, multiplex PCR, overlap-extension PCR, thermal asymmetric interlaced PCR, touchdown PCR, and ligase chain reaction. In some embodiments, DNA amplification is linear, exponential, or any combination thereof. In some embodiments, DNA amplification is achieved with digital PCR (dPCR).

[00105] Reagents necessary for nucleic acid amplification may include polymerizing enzymes, reverse primers, forward primers, and amplification probes. Examples of polymerizing enzymes include, without limitation, nucleic acid polymerase, transcriptase, or ligase (e.g., enzymes which catalyze the formation of a bond). The polymerizing enzyme can be naturally occurring or synthesized. Examples of polymerases include a DNA polymerase, and RNA polymerase, a thermostable polymerase, a wild-type polymerase, a modified polymerase, E. coli DNA polymerase I, T7 DNA polymerase, bacteriophage T4 DNA polymerase $\Phi 29$ (phi29) DNA polymerase, Taq polymerase, Tth polymerase, Tli polymerase, Pfu polymerase Pwo polymerase, VENT polymerase, DEEPVENT polymerase, Ex-Taq polymerase, LA-Taw polymerase, Sso polymerase Poc polymerase, Pab polymerase, Mth polymerase ES4 polymerase, Tru polymerase, Tac polymerase, Tne polymerase, Tma polymerase, Tca polymerase, Tih polymerase, Tfi polymerase, Platinum Taq polymerases, Tbr polymerase, Tfl polymerase, Pfutubo polymerase, Pyrobest polymerase, KOD polymerase, Bst polymerase, Sac polymerase, Klenow fragment polymerase with 3' to 5' exonuclease activity, and variants, modified products and derivatives thereof. For a Hot Start polymerase, denaturation at a temperature from about 92 °C to 95 °C for a time period from about 2 minutes to 10 minutes may be used.

[00106] In some embodiments, the amplification probe is a sequence-specific oligonucleotide probe. The amplification probe may be optically active when hybridized with an amplification product. In some embodiments, the amplification probe is detectable as nucleic acid amplification progresses. The intensity of the optical signal may be proportional to the amount of amplified product. A probe may be linked to any of the optically-active detectable moieties (e.g., dyes) described herein and may also include a quencher capable of blocking the optical activity of an associated dye. Non-limiting examples of probes that may be useful as detectable moieties include TaqMan probes, TaqMan Tamara probes, TaqMan MGB probes, Lion probes, locked

nucleic acid probes, or molecular beacons. Non-limiting examples of quenchers that may be useful in blocking the optical activity of the probe include Black Hole Quenchers (BHQ), Iowa Black FQ and RQ quenchers, or Internal ZEN Quenchers. Alternatively, or in addition to, the probe or quencher may be any probe that is useful in the context of the methods of the present disclosure.

[00107] In some embodiments, the amplification probe is a dual labeled fluorescent probe. The dual labeled probe may include a fluorescent reporter and a fluorescent quencher linked with a nucleic acid. The fluorescent reporter and fluorescent quencher may be positioned in close proximity to each other. The close proximity of the fluorescent reporter and fluorescent quencher may block the optical activity of the fluorescent reporter. The dual labeled probe may bind to the nucleic acid molecule to be amplified. During amplification, the fluorescent reporter and fluorescent quencher may be cleaved by the exonuclease activity of the polymerase. Cleaving the fluorescent reporter and quencher from the amplification probe may cause the fluorescent reporter to regain its optical activity and enable detection. The dual labeled fluorescent probe may include a 5' fluorescent reporter with an excitation wavelength maximum of about 450 nanometers (nm), 500 nm, 525 nm, 550 nm, 575 nm, 600 nm, 625 nm, 650 nm, 675 nm, 700 nm, or higher and an emission wavelength maximum of about 500 nm, 525 nm, 550 nm, 575 nm, 600 nm, 625 nm, 650 nm, 675 nm, 700 nm, or higher. The dual labeled fluorescent probe may also include a 3' fluorescent quencher. The fluorescent quencher may quench fluorescent emission wavelengths between about 380 nm and 550 nm, 390 nm and 625 nm, 470 nm and 560 nm, 480 nm and 580 nm, 550 nm and 650 nm, 550 nm and 750 nm, or 620 nm and 730 nm.

[00108] In some embodiments, the nucleic acid amplification is performed by thermal cycling the microchambers of the microfluidic device. Thermal cycling may include controlling the temperature of the microfluidic device by applying heating or cooling to the microfluidic device. Heating or cooling methods may include resistive heating or cooling, radiative heating or cooling, conductive heating or cooling, convective heating or cooling, or any combination thereof. Thermal cycling may include cycles of incubating the microchambers at a temperature sufficiently high to denature nucleic acid molecules for a duration followed by incubation of the microchambers at an extension temperature for an extension duration. Denaturation temperatures may vary depending upon, for example, the particular nucleic acid sample, the reagents used, and reaction conditions. In some embodiments, a denaturation temperature may be from about 80 °C to about 110 °C. In some embodiments, a denaturation temperature may be from about 85 °C to about 105 °C. In some embodiments, a denaturation temperature may be from about 90 °C to about 100 °C. In some embodiments, a denaturation temperature may be from about 90 °C to

about 98 °C. In some embodiments, a denaturation temperature may be from about 92 °C to about 95 °C. In some embodiments, a denaturation temperature may be at least about 80 °C, at least about 81 °C, at least about 82 °C, at least about 83 °C, at least about 84 °C, at least about 85 °C, at least about 86 °C, at least about 87 °C, at least about 88 °C, at least about 89 °C, at least about 90 °C, at least about 91 °C, at least about 92 °C, at least about 93 °C, at least about 94 °C, at least about 95 °C, at least about 96 °C, at least about 97 °C, at least about 98 °C, at least about 99 °C, at least about 100 °C, or higher.

[00109] The duration for denaturation may vary depending upon, for example, the particular nucleic acid sample, the reagents used, and reaction conditions. In some embodiments, the duration for denaturation may be less than or equal to about 300 seconds, 240 seconds, 180 seconds, 120 seconds, 90 seconds, 60 seconds, 55 seconds, 50 seconds, 45 seconds, 40 seconds, 35 seconds, 30 seconds, 25 seconds, 20 seconds, 15 seconds, 10 seconds, 5 seconds, 2 seconds, or 1 second. In an alternative embodiment, the duration for denaturation may be no more than about 120 seconds, 90 seconds, 60 seconds, 55 seconds, 50 seconds, 45 seconds, 40 seconds, 35 seconds, 30 seconds, 25 seconds, 20 seconds, 15 seconds, 10 seconds, 5 seconds, 2 seconds, or 1 second.

[00110] Extension temperatures may vary depending upon, for example, the particular nucleic acid sample, the reagents used, and reaction conditions. In some embodiments, an extension temperature may be from about 30 °C to about 80 °C. In some embodiments, an extension temperature may be from about 35 °C to about 75 °C. In some embodiments, an extension temperature may be from about 45 °C to about 65 °C. In some embodiments, an extension temperature may be from about 55 °C to about 65 °C. In some embodiments, an extension temperature may be from about 40 °C to about 60 °C. In some embodiments, an extension temperature may be at least about 35 °C, at least about 36 °C, at least about 37 °C, at least about 38 °C, at least about 39 °C, at least about 40 °C, at least about 41 °C, at least about 42 °C, at least about 43 °C, at least about 44 °C, at least about 45 °C, at least about 46 °C, at least about 47 °C, at least about 48 °C, at least about 49 °C, at least about 50 °C, at least about 51 °C, at least about 52 °C, at least about 53 °C, at least about 54 °C, at least about 55 °C, at least about 56 °C, at least about 57 °C, at least about 58 °C, at least about 59 °C, at least about 60 °C, at least about 61 °C, at least about 62 °C, at least about 63 °C, at least about 64 °C, at least about 65 °C, at least about 66 °C, at least about 67 °C, at least about 68 °C, at least about 69 °C, at least about 70 °C, at least about 71 °C, at least about 72 °C, at least about 73 °C, at least about 74 °C, at least about 75 °C, at least about 76 °C, at least about 77 °C, at least about 78 °C, at least about 79 °C, or at least about 80 °C.

[00111] Extension time may vary depending upon, for example, the particular nucleic acid sample, the reagents used, and reaction conditions. In some embodiments, the duration for extension may be less than or equal to about 300 seconds, 240 seconds, 180 seconds, 120 seconds, 90 seconds, 60 seconds, 55 seconds, 50 seconds, 45 seconds, 40 seconds, 35 seconds, 30 seconds, 25 seconds, 20 seconds, 15 seconds, 10 seconds, 5 seconds, 2 seconds, or 1 second. In an alternative embodiment, the duration for extension may be no more than about 120 seconds, 90 seconds, 60 seconds, 55 seconds, 50 seconds, 45 seconds, 40 seconds, 35 seconds, 30 seconds, 25 seconds, 20 seconds, 15 seconds, 10 seconds, 5 seconds, 2 seconds, or 1 second.

[00112] Nucleic acid amplification may include multiple cycles of thermal cycling. Any suitable number of cycles may be performed. In some embodiments, the number of cycles performed may be more than about 5, more than about 10, more than about 15, more than about 20, more than about 30, more than about 40, more than about 50, more than about 60, more than about 70, more than about 80, more than about 90, more than about 100 cycles, or more. The number of cycles performed may depend upon the number of cycles necessary to obtain detectable amplification products. For example, the number of cycles necessary to detect nucleic acid amplification during dPCR may be less than or equal to about 100, less than or equal to about 90, less than or equal to about 80, less than or equal to about 70, less than or equal to about 60, less than or equal to about 50, less than or equal to about 40, less than or equal to about 30, less than or equal to about 20, less than or equal to about 15, less than or equal to about 10, less than or equal to about 5 cycles, or less.

[00113] The time to reach a detectable amount of amplification product may vary depending upon the particular nucleic acid sample, the reagents used, the amplification reaction used, the number of amplification cycles used, and reaction conditions. In some embodiments, the time to reach a detectable amount of amplification product may be about 120 minutes or less, 90 minutes or less, 60 minutes or less, 50 minutes or less, 40 minutes or less, 30 minutes or less, 20 minutes or less, 10 minutes or less, or 5 minutes or less.

[00114] In some embodiments, the ramping rate (e.g., the rate at which the microchamber transitions from one temperature to another) is important for amplification. For example, the temperature and time for which an amplification reaction yields a detectable amount of amplified product may vary depending upon the ramping rate. The ramping rate may impact the time(s), temperature(s), or both the time(s) and temperature(s) used during amplification. In some embodiments, the ramping rate is constant between cycles. In some embodiments, the ramping rate varies between cycles. The ramping rate may be adjusted based on the sample being

processed. For example, optimum ramping rate(s) may be selected to provide a robust and efficient amplification method.

[00115] FIG. 5 illustrates a digital PCR process to be employed with the above-described microfluidic device. In operation **501**, reagent is partitioned as shown in **FIGs. 3A-3D**. In operation **502**, the reagent is subjected to thermal cycling to run the PCR reaction on the reagent in the microchambers. This operation may be performed, for example, using a flat block thermal cycler. In operation **503**, image acquisition is performed to determine which microchambers have successfully run the PCR reaction. Image acquisition may, for example, be performed using a three color probe detection unit. In operation **504**, Poisson statistics are applied to the count of microchambers determined in operation **503** to convert the raw number of positive chambers into a nucleic acid concentration.

System for analyzing a nucleic acid sample

[00116] In an aspect, the present disclosure provides an apparatus for using a microfluidic device to analyze nucleic acid samples. The apparatus may comprise a transfer stage configured to hold one or more microfluidic devices. The microfluidic devices may comprise a microchannel with an inlet and an outlet, a plurality of microchambers connected to the microchannel by a plurality of siphon apertures, and a thin film capping or covering the microfluidic device. The apparatus may comprise a pneumatic module in fluid communication with the microfluidic device. The pneumatic module may load reagent into the microfluidic device and partition the reagent into the microchambers. The apparatus may comprise a thermal module in thermal communication with the plurality of microchambers. The thermal module may control the temperature of the microchambers and thermal cycle the microchambers. The apparatus may comprise an optical module capable of imaging the plurality of microchambers. The apparatus may also comprise a computer processor coupled to the transfer stage, pneumatic module, thermal module, and optical module. The computer processor may be programmed to (i) direct the pneumatic module to load reagent into the microfluidic device and partition the reagent into the plurality of microchambers, (ii) direct the thermal module to thermal cycle the plurality of microchambers, and (iii) direct the optical module to image the plurality of microchambers.

[00117] The transfer stage may be configured input the microfluidic device, hold the microfluidic device, and output the microfluidic device. The transfer stage may be stationary in one or more coordinates. Alternatively, or in addition to, the transfer stage may be capable of moving in the X-direction, Y-direction, Z-direction, or any combination thereof. The transfer stage may be capable of holding a single microfluidic device. Alternatively, or in

addition to, the transfer stage may be capable of holding at least 2, at least 3, at least 4, at least 5, at least 6, at least 7, at least 8, at least 9, at least 10, or more microfluidic devices.

[00118] The pneumatic module may be configured to be in fluid communication with the inlets and the outlets of the microfluidic device. The pneumatic module may have multiple connection points capable of connecting to multiple inlets and multiple outlets. The pneumatic module may be able to fill, backfill, and partition a single array of microchambers at a time or multiple arrays of microchambers in tandem. The pneumatic module may further comprise a vacuum module. The pneumatic module may provide increased pressure to the microfluidic device or provide vacuum to the microfluidic device.

[00119] The thermal module may be configured to be in thermal communication with the microchambers of the microfluidic devices. The thermal module may be configured to control the temperature of a single array of microchambers or to control the temperature of multiple arrays of microchambers. The thermal control module may perform the same thermal program across all arrays of microchambers or may perform different thermal programs with different arrays of microchambers.

[00120] The optical module may be configured to emit and detect multiple wavelengths of light. Emission wavelengths may correspond to the excitation wavelengths of the indicator and amplification probes used. The emitted light may include wavelengths with a maximum intensity around about 450 nm, 500 nm, 525 nm, 550 nm, 575 nm, 600 nm, 625 nm, 650 nm, 675 nm, 700 nm, or any combination thereof. Detected light may include wavelengths with a maximum intensity around about 500 nm, 525 nm, 550 nm, 575 nm, 600 nm, 625 nm, 650 nm, 675 nm, 700 nm, or any combination thereof. The optical module may be configured to emit one, two, three, four, or more wavelengths of light. The optical module may be configured to detect one, two, three, four, or more wavelengths of light. One emitted wavelength of light may correspond to the excitation wavelength of indicator molecule. Another emitted wavelength of light may correspond to the excitation wavelength of the amplification probe. One detected wavelength of light may correspond to the emission wavelength of an indicator molecule. Another detected wavelength of light may correspond to an amplification probe used to detect a reaction within the microchambers. The optical module may be configured to image sections of an array of microchambers. Alternatively, or in addition to, the optical module may image an entire array of microchambers in a single image.

[00121] **FIG. 6** illustrates a machine **600** for performing the process of **FIG. 5** in a single machine. The machine **600** includes a pneumatic module **601**, which contains pumps and manifolds and may be moved in a Z-direction, operable to perform the application of pressure as

described in **FIGs. 3A-3D**. Machine **600** also includes a thermal module **602**, such as a flat block thermal cycler, to thermally cycle the microfluidic device and thereby cause the polymerase chain reaction to run. Machine **600** further includes an optical module **603**, such as an epi-fluorescent optical module, which can optically determine which microchambers in the microfluidic device have successfully run the PCR reaction. The optical module **603** may feed this information to a processor **604**, which uses Poisson statistics to convert the raw count of successful microchambers into a nucleic acid concentration. A transfer stage **605** may be used to move a given microfluidic device between the various modules and to handle multiple microfluidic devices simultaneously. The microfluidic device described above, combined with the incorporation of this functionality into a single machine, reduces the cost, workflow complexity, and space requirements for dPCR over other implementations of dPCR.

[00122] The present disclosure is not to be limited in scope by the specific embodiments described herein. Indeed, other various embodiments of and modifications to the present disclosure, in addition to those described herein, will be apparent to those of ordinary skill in the art from the foregoing description and accompanying drawings.

[00123] For example, while described in the context of a dPCR application, other microfluidic devices which may require a number of isolated microchambers filled with a liquid, that are isolated via a gas or other fluid, may benefit from the use of a thin thermoplastic film to allow outgassing to avoid gas fouling while also providing an advantage with respect to manufacturability and cost. Other than PCR, other nucleic acid amplification methods such as loop mediated isothermal amplification can be adapted to perform digital detection of specific nucleic acid sequences according to embodiments of the present disclosure. The microchambers can also be used to isolate single cells with the siphoning apertures designed to be close to the diameter of the cells to be isolated. In some embodiments, when the siphoning apertures are much smaller than the size of blood cells, embodiments of the present disclosure can be used to separate blood plasma from whole blood.

Computer systems for analyzing a nucleic acid sample and for forming a microfluidic device

[00124] The present disclosure provides computer control systems that are programmed to implement methods of the disclosure. **FIG. 7** shows a computer system **701** that can be programmed or otherwise configured for nucleic acid sample processing and analysis, including sample partitioning, amplification, and detection. The computer system **701** can regulate various aspects of methods and systems of the present disclosure. The computer system **701** can be an electronic device of a user or a computer system that can be remotely located with respect to the

electronic device. The electronic device can be a mobile electronic device. The computer system **701** can be programmed or otherwise configured to implement one or more of the operations of **FIG. 11**. For example, the application of heating conditions and negative pressures can be computer controlled. In another example, the computer system can control the application of the solvent to the microfluidic structure.

[00125] The computer system **701** includes a central processing unit (CPU, also “processor” and “computer processor” herein) **705**, which can be a single core or multi core processor, or a plurality of processors for parallel processing. The computer system **701** also includes memory or memory location **710** (e.g., random-access memory, read-only memory, flash memory), electronic storage unit **715** (e.g., hard disk), communication interface **720** (e.g., network adapter) for communicating with one or more other systems, and peripheral devices **725**, such as cache, other memory, data storage and/or electronic display adapters. The memory **710**, storage unit **715**, interface **720** and peripheral devices **725** are in communication with the CPU **705** through a communication bus (solid lines), such as a motherboard. The storage unit **715** can be a data storage unit (or data repository) for storing data. The computer system **701** can be operatively coupled to a computer network (“network”) **730** with the aid of the communication interface **720**. The network **730** can be the Internet, an internet and/or extranet, or an intranet and/or extranet that can be in communication with the Internet. The network **730** in some cases can be a telecommunication and/or data network. The network **730** can include one or more computer servers, which can enable distributed computing, such as cloud computing. The network **730**, in some cases with the aid of the computer system **701**, can implement a peer-to-peer network, which may enable devices coupled to the computer system **701** to behave as a client or a server.

[00126] The CPU **705** can execute a sequence of machine-readable instructions, which can be embodied in a program or software. The instructions may be stored in a memory location, such as the memory **710**. The instructions can be directed to the CPU **705**, which can subsequently program or otherwise configure the CPU **705** to implement methods of the present disclosure. Examples of operations performed by the CPU **705** can include fetch, decode, execute, and writeback.

[00127] The CPU **705** can be part of a circuit, such as an integrated circuit. One or more other components of the system **701** can be included in the circuit. In some cases, the circuit is an application specific integrated circuit (ASIC).

[00128] The storage unit **715** can store files, such as drivers, libraries and saved programs. The storage unit **715** can store user data, e.g., user preferences and user programs. The computer system **701** in some cases can include one or more additional data storage units that are external

to the computer system **701**, such as located on a remote server that is in communication with the computer system **701** through an intranet or the Internet.

[00129] The computer system **701** can communicate with one or more remote computer systems through the network **730**. For instance, the computer system **701** can communicate with a remote computer system of a user (e.g., service provider). Examples of remote computer systems include personal computers (e.g., portable PC), slate or tablet PC's (e.g., Apple® iPad, Samsung® Galaxy Tab), telephones, Smart phones (e.g., Apple® iPhone, Android-enabled device, Blackberry®), or personal digital assistants. The user can access the computer system **701** via the network **730**.

[00130] Methods as described herein can be implemented by way of machine (e.g., computer processor) executable code stored on an electronic storage location of the computer system **701**, such as, for example, on the memory **710** or electronic storage unit **715**. The machine executable or machine readable code can be provided in the form of software. During use, the code can be executed by the processor **705**. In some cases, the code can be retrieved from the storage unit **715** and stored on the memory **710** for ready access by the processor **705**. In some situations, the electronic storage unit **715** can be precluded, and machine-executable instructions are stored on memory **710**.

[00131] The code can be pre-compiled and configured for use with a machine having a processor adapted to execute the code, or can be compiled during runtime. The code can be supplied in a programming language that can be selected to enable the code to execute in a pre-compiled or as-compiled fashion.

[00132] In one aspect, the present disclosure provides a non-transitory computer-readable medium comprising machine executable code that, upon execution by one or more computer processors, implements a method for forming a microfluidic device to amplify and quantify a nucleic acid sample. The method may comprise: injection molding thermoplastic to create a microfluidic structure comprising at least one microchannel, a plurality of microchambers, and a plurality of siphon apertures, wherein the plurality of microchambers are connected to the at least one microchannel by the plurality of siphon apertures; forming at least one inlet and at least one outlet, wherein the at least one inlet and the at least one outlet are in fluid communication with the at least one microchannel; and applying a thermoplastic thin film to cap the microfluidic structure, wherein the thermoplastic thin film is at least partially gas permeable to a pressure differential is applied across the thermoplastic thin film.

[00133] In one aspect, the present disclosure provides a non-transitory computer-readable medium comprising machine executable code that, upon execution by one or more computer

processors, implements a method for analyzing and quantifying a nucleic acid sample. The method may comprise: providing the microfluidic device comprising at least one microchannel, wherein the at least one microchannel comprises at least one inlet and at least one outlet, and wherein the microfluidic device further comprises a plurality of microchambers connected to the microchannel by a plurality of siphon apertures, and a thermoplastic thin film disposed adjacent to a surface of the microfluidic device such that the thermoplastic thin film caps the microchannel, the plurality of microchambers, and the plurality of siphon apertures; providing a reagent to the at least one inlet or to the at least one outlet; filling the microfluidic device by providing a first pressure differential between the reagent and the microfluidic device, wherein the first pressure differential causes the reagent to flow into the microfluidic device; applying a second pressure differential between the microchannel and the plurality of microchambers to move the reagent into the plurality of microchambers and to force gas within the plurality of microchambers to pass through the thermoplastic thin film capping or covering the plurality of microchambers, the plurality of siphon apertures, and the microchannel, wherein the second pressure differential is greater than the first pressure differential; and applying a third pressure differential between the at least one inlet and the at least one outlet to introduce a fluid into the microchannel without introducing the fluid into the microchambers, wherein the third pressure differential is less than the second pressure differential.

[00134] In one aspect, the present disclosure provides a non-transitory computer-readable medium comprising machine executable code that, upon execution by one or more computer processors, implements a method for forming a microfluidic device. The method may comprise: providing a microfluidic structure and a film; treating a surface of the microfluidic structure, a surface of the film, or both with a solvent; subsequently, pressing the microfluidic structure together with the film under a first heating condition to form the microfluidic device comprising the solvent; and applying a negative pressure to the microfluidic device under a second heating condition. The negative pressure may be applied for a time period greater than 30 minutes or at a pressure less than 20 kilopascals to remove at least a portion of the solvent. The implementation of the method may comprise selecting a solvent based at least in part on the material the microfluidic structure and/or the film is constructed from. The computer may monitor a progress of the pressing of the microfluidic structure and the film. For example, a sum harmonic generation signal formed at the interface of the solvent and the film can be used to determine the extent of solvent intercalation into the polymer of the film. The computer-readable medium may be configured to improve the

consistency of microfluidic devices produced. For example, the computer-readable medium can maintain substantially similar conditions for a series of microfluidic devices, thus reducing the variation present between the devices.

[00135] Aspects of the systems and methods provided herein, such as the computer system **701**, can be embodied in programming. Various aspects of the technology may be thought of as “products” or “articles of manufacture” typically in the form of machine (or processor) executable code and/or associated data that is carried on or embodied in a type of machine readable medium. Machine-executable code can be stored on an electronic storage unit, such as memory (e.g., read-only memory, random-access memory, flash memory) or a hard disk. “Storage” type media can include any or all of the tangible memory of the computers, processors or the like, or associated modules thereof, such as various semiconductor memories, tape drives, disk drives and the like, which may provide non-transitory storage at any time for the software programming. All or portions of the software may at times be communicated through the Internet or various other telecommunication networks. Such communications, for example, may enable loading of the software from one computer or processor into another, for example, from a management server or host computer into the computer platform of an application server. Thus, another type of media that may bear the software elements includes optical, electrical and electromagnetic waves, such as used across physical interfaces between local devices, through wired and optical landline networks and over various air-links. The physical elements that carry such waves, such as wired or wireless links, optical links or the like, also may be considered as media bearing the software. As used herein, unless restricted to non-transitory, tangible “storage” media, terms such as computer or machine “readable medium” refer to any medium that participates in providing instructions to a processor for execution.

[00136] Hence, a machine readable medium, such as computer-executable code, may take many forms, including but not limited to, a tangible storage medium, a carrier wave medium or physical transmission medium. Non-volatile storage media include, for example, optical or magnetic disks, such as any of the storage devices in any computer(s) or the like, such as may be used to implement the databases, etc. shown in the drawings. Volatile storage media include dynamic memory, such as main memory of such a computer platform. Tangible transmission media include coaxial cables; copper wire and fiber optics, including the wires that comprise a bus within a computer system. Carrier-wave transmission media may take the form of electric or electromagnetic signals, or acoustic or light waves such as those generated during radio frequency (RF) and infrared (IR) data communications. Common forms of computer-readable media therefore include for example: a floppy disk, a flexible disk, hard disk, magnetic tape, any

other magnetic medium, a CD-ROM, DVD or DVD-ROM, any other optical medium, punch cards paper tape, any other physical storage medium with patterns of holes, a RAM, a ROM, a PROM and EPROM, a FLASH-EPROM, any other memory chip or cartridge, a carrier wave transporting data or instructions, cables or links transporting such a carrier wave, or any other medium from which a computer may read programming code and/or data. Many of these forms of computer readable media may be involved in carrying one or more sequences of one or more instructions to a processor for execution.

[00137] The computer system **701** can include or be in communication with an electronic display **735** that comprises a user interface (UI) **740** for providing, for example, depth profile of an epithelial tissue. Examples of UI's include, without limitation, a graphical user interface (GUI) and web-based user interface.

[00138] Methods and systems of the present disclosure can be implemented by way of one or more algorithms. An algorithm can be implemented by way of software upon execution by the central processing unit **705**. The algorithm can, for example, regulate systems or implement methods provided herein. For example, the algorithm can monitor the pressure of solvent off gassing from a microfluidic device, and adjust the heat, vacuum pressure, and/or time to reach a predetermined level of solvent in the microfluidic device.

[00139] While preferred embodiments of the present invention have been shown and described herein, it will be obvious to those skilled in the art that such embodiments are provided by way of example only. Numerous variations, changes, and substitutions will now occur to those skilled in the art without departing from the invention. It should be understood that various alternatives to the embodiments of the invention described herein may be employed in practicing the invention. It is intended that the following claims define the scope of the invention and that methods and structures within the scope of these claims and their equivalents be covered thereby.

Example 1: Demonstration of reagent partitioning

[00140] Reagent partitioning is demonstrated using a microfluidic device fabricated using standard microscope slide dimensions. The total dimensions of the microfluidic device are 1 inch wide, 3 inches long, and 0.6 inches thick. The device contains four different microchamber array designs and a total of eight different arrays of microchambers. **FIG. 8A** shows the eight-unit device and an enlarged perspective of one of the four array designs. The microfluidic device is molded from a cyclo-olefin polymer (COP), Zeonor 790R (Zeon Chemicals, Japan) and sealed by thermal bonding with a 100 μm COP thin film, Zeonox ZF14 (Zeon Chemicals, Japan). The shown enlarged microfluidic segment has a serpentine microchannel connected to microchambers by siphon apertures. The microchambers are in a gridded configuration. The

microchambers and microchannel have a depth of 40 μm the siphon apertures have a depth of 10 μm . Each isolated microfluidic segment has an inlet and an outlet channel. The inlet and outlet channels are mechanically drilled before the film is thermally bonded to the base of the microfluidic device. The inlet and outlet channels are 1.6 mm in diameter.

[00141] FIG. 8B shows fluorescent images of reagent loading, microchamber backfilling, and partitioning. Prior to loading the microfluidic device 2 microliters (μL) of a 4 kiloDalton (kDa) fluorescein conjugated dextran (Sigma-Aldrich, St. Louis, MO) is pipetted into the inlet. The microfluidic device is then contacted with a pneumatic controller. The pneumatic controller loads the microchannel of the microfluidic device by applying 4 psi of pressure to the inlet for 3 minutes. The microchambers are filled by pressurizing both the inlet and the outlet to 10 psi for 20 minutes. The reagent is then partitioned by flowing air at 4 psi from the inlet of the microfluidic device to clear reagent from the microchannel.

Example 2: Single instrument workflow for dPCR

[00142] The methods for amplification and quantification of nucleic acids in the microfluidic device may be performed in a single instrument. The instrument may be capable of reagent partitioning, thermal cycling, image acquisition, and data analysis. FIG. 9 shows a prototype instrument capable of a single instrument work flow. The instrument is designed to accommodate up to four devices at a time and enable concurrent image acquisition and thermal cycling. The instrument contains a pneumatic module for reagent partitioning, a thermal module for temperature control and thermal cycling, an optical module for imaging, and a scanning module. The optical module has two fluorescent imaging capabilities and is able to detect fluorescent emissions of approximately 520 nm and 600 nm, which correspond to the emission wavelengths of FAM and ROX fluorophores, respectively. The optical module has a 25 mm by 25 mm field of view and a Numerical Aperture (NA) of 0.14.

[00143] The single instrument workflow may be tested using a well-established qPCR assay utilizing a TaqMan probe as a reporter. Briefly, a nucleic acid sample is mixed with PCR reagents. The PCR reagents include forward primers, reverse primers, TaqMan probes, and a ROX indicator. The sequence of the forward primer is 5' – GCC TCA ATA AAG CTT GCC TTG A – 3'. The sequence of the reverse primer is 5' – GGG GCG CAC TGC TAG AGA – 3'. The sequence of the TaqMan probe is 5' – [FAM] – CCA GAG TCA CAC AAC AGA CGG GCA CA – [BHQ1] – 3'. The nucleic acid sample and PCR reagents are loaded and partitioned within the microfluidic device following the above mentioned protocol. PCR amplification is performed by increasing the temperature of the microchambers to 95 °C and holding the temperature for 10 minutes followed by forty cycles ramping the temperature of the

microchambers from 95 °C to 59 °C at a rate of 2.4 °C per second with a 1 minute hold at 59 °C prior to returning the temperature to 95 °C. **FIGs. 10A-10D** show fluorescent images of samples containing approximately one nucleic acid template copy per partition and partitions containing zero nucleic acid template copies per partition (no template control or NTC) after PCR amplification and fluorescence intensity plots of samples containing approximately one nucleic acid copy per partition and NTC partitions after PCR amplification. **FIG. 10A** shows a fluorescent image of the partitioned sample containing no nucleic acid template and each grey dot represents a single microchamber containing the PCR reagents. The image is taken by exciting the ROX indicator within each microchamber with approximately 575 nm light and imaging the emission spectrum, which has a max emission at approximately 600 nm. **FIG. 10B** shows the partitioned sample containing approximately one nucleic acid template copy per partition after PCR amplification. After PCR amplification, imaging shows microchambers that contain the ROX indicator and microchambers that contain both the ROX indicator and emission from the FAM probe. The FAM probe has an excitation wavelength of approximately 495 nm and an emission wavelength maximum of approximately 520 nm. Individual microchambers contain the ROX indicator, the FAM probe, and the BHQ-1 quencher. As with **FIG. 10A** each grey dot represents a microchamber containing the partitioned sample with no nucleic acid template. The white dots represent microchambers that contain nucleic acid samples that have been successfully amplified. Upon successful PCR amplification, the FAM fluorophore and BHQ-1 quencher may be cleaved from the TaqMan probe, resulting in a detectable fluorescent signal. **FIGs. 10C and 10D** show a 2-dimensional scatter plot of the FAM fluorescent intensity as a function of the ROX fluorescent intensity for each microchamber for the partitioned and amplified microfluidic device, respectively. **FIG. 10C** shows a sample containing zero nucleic acid templates per partition, resulting in a FAM fluorescent intensity that is predominantly constant over a range of ROX fluorescent intensities. **FIG. 10D** shows a sample containing approximately one nucleic acid template copy per partition, resulting in a FAM fluorescent intensity that varies as a function of ROX fluorescent intensity due to the presence of amplification signals within the partition.

Example 3: Effects of treatment on fabricated microfluidic devices

[00144] **FIGs. 13 - 17** are examples of microfluidic devices at various points of the operations of **FIG. 11**. In each of **FIGs. 13 – 17**, the five images are optical microscope images showing a wide area of the microfluidic device. **FIG. 13** is an example of a microfluidic device after treatment of a surface of the microfluidic structure or surface of the film, or both, with solvent. The microfluidic device can be formed by applying cyclohexane or ethanol to an extruded cyclo-

olefin-polymer (COP) film via spin coating and subsequently pressing a injection molded COP microfluidic structure to the solvent coated film at 350 kPa and 80 °C for 2 minutes. **FIG. 14** is an example of a microfluidic device after liquid pressurization and heating. A microfluidic device can be subjected to heat and liquid pressure as a part of the use of the microfluidic device. The heat and liquid pressure can result in delamination events 1410. The delamination events may be observable by the darkening of the image. More delamination events are observable in **FIG. 14** than are marked. More intensive delamination can be observed in **FIG. 15**, which is an example of a microfluidic device after air pressurization and heating. The increased darkness throughout the images of the microfluidic device may show a near complete delamination of the microfluidic structure from the film.

[00145] **FIG. 16** is an example of a treated microfluidic device after liquid pressurization and heating. The treatment of the microfluidic device can include reducing the pressure around the device to about 4 kPa (a reduction of about 97 kPa) while heating the device to 80 °C, and maintaining the vacuum and temperature for 24 hours. In contrast to **FIG. 14**, **FIG. 16** does not show any delamination events. Similarly, **FIG. 17**, which is an example of a treated microfluidic device after air pressurization and heating, does not show the full delamination observed in **FIG. 15**. This may be due to a more complete removal of the solvent in **FIGs. 16 – 17** as compared to **FIGs. 14 – 15**. The removal of the residual solvent can increase the fraction of microfluidic devices that are usable, reducing waste and cost.

[00146] While preferred embodiments of the present invention have been shown and described herein, it will be obvious to those skilled in the art that such embodiments are provided by way of example only. It is not intended that the invention be limited by the specific examples provided within the specification. While the invention has been described with reference to the aforementioned specification, the descriptions and illustrations of the embodiments herein are not meant to be construed in a limiting sense. Numerous variations, changes, and substitutions will now occur to those skilled in the art without departing from the invention. Furthermore, it shall be understood that all aspects of the invention are not limited to the specific depictions, configurations or relative proportions set forth herein which depend upon a variety of conditions and variables. It should be understood that various alternatives to the embodiments of the invention described herein may be employed in practicing the invention. It is therefore contemplated that the invention shall also cover any such alternatives, modifications, variations or equivalents. It is intended that the following claims define the scope of the invention and that methods and structures within the scope of these claims and their equivalents be covered thereby.

CLAIMS

WHAT IS CLAIMED IS:

1. A method for forming a microfluidic device, comprising:
 - a) providing a microfluidic structure and a film;
 - b) treating a surface of said microfluidic structure, a surface of said film, or both with a solvent;
 - c) subsequent to (b), pressing said microfluidic structure together with said film under a first heating condition to form said microfluidic device comprising said solvent; and
 - d) applying a negative pressure to said microfluidic device under a second heating condition, which negative pressure is applied for a time period greater than 30 minutes or at a pressure less than 20 kilopascals (kPa) to remove at least a portion of said solvent from (b).
2. The method of claim 1, wherein said microfluidic structure comprises a microchannel, a plurality of microchambers, a plurality of siphon apertures, or any combination thereof.
3. The method of claim 1, wherein said treating comprises application of one or more solvents.
4. The method of claim 3, wherein said one or more solvents include a solvent selected from the group consisting of isopropyl alcohol, acetone, ethyl alcohol, hexanes, cyclohexane, toluene, and benzene.
5. The method of claim 1, wherein said pressing comprises applying a force of at least about 0.5 kilo-Newtons (kN).
6. The method of claim 1, wherein said first heating condition comprises heating to a temperature of at least about 60 °C.
7. The method of claim 1, wherein said applying said negative pressure comprises applying a pressure less than about 7 kPa.
8. The method of claim 1, wherein said second heating condition comprises heating said microfluidic device to a temperature of at least about 70 °C.
9. The method of claim 8, wherein said heating said microfluidic device to a temperature of at least about 70°C removes at least about 75% of said solvent from said microfluidic device.
10. The method of claim 1, wherein said applying said negative pressure comprises applying said negative pressure for at least about 2 hours.
11. The method of claim 1, wherein said applying said negative pressure removes at least about 50 % of said solvent from said microfluidic device.

12. The method of claim 1, wherein said applying said negative pressure under said second heating condition reduces separation between said microfluidic structure and said film.
13. The method of claim 1, wherein said microfluidic structure comprises a channel or chamber with a feature size of at most about 500 micrometers.
14. The method of claim 1, wherein said removing said solvent increases a yield of a microfluidic device generation process by at least about 25%.
15. The method of claim 1, wherein said microfluidic device has a usable feature fraction of at least about 0.5.
16. The method of claim 1, further comprising applying an increased pressure to said microfluidic device, wherein said increased pressure is sufficient to expel at least a portion of said solvent.