

**Method for Cooling a Workpiece made of Semiconductor
Material during Wire Sawing**

5 The present invention relates to a method for cooling a cylindrical workpiece made of semiconductor material, for example silicon, germanium or gallium arsenide, during wire sawing, a liquid coolant being applied onto the semiconductor material workpiece by means of nozzles during the cutting.

10

For electronics, microelectronics and micro-electromechanics, semiconductor wafers with extreme requirements for global and local planarity, one-side referenced local planarity (nanotopology), roughness
15 and cleanness are needed as starting materials (substrates). Semiconductor wafers are wafers of semiconductor materials, in particular compound semiconductors such as gallium arsenide and predominantly elementary semiconductors such as silicon
20 and sometimes germanium. According to the prior art, semiconductor wafers are produced in a multiplicity of successive process steps: in a first step, for example, a single crystal (rod) of semiconductor material is pulled by the Czochralski method or a polycrystalline
25 block of semiconductor material is cast, and in a further step the resulting circular-cylindrical or block-shaped workpiece of semiconductor material (ingot) is cut into individual semiconductor wafers by wire sawing.

30

Wire saws are used in order to cut a multiplicity of wafers from a workpiece made of semiconductor material. US-5,771,876 describes the functional principle of a wire saw, which is suitable for the production of
35 semiconductor wafers. The essential components of these wire saws include a machine frame, a forward feed

device and a sawing tool, which consists of a web (wire web) of parallel wire sections.

5 In general, the wire web is formed by a multiplicity of parallel wire sections which are tensioned between at least two wire guide rolls, the wire guide rolls being rotatably mounted and at least one of them being a driven roll.

10 The wire sections may belong to a single finite wire, which is guided spirally around the roll system and is unwound from a stock roll onto a receiver roll. Patent specification US 4,655,191, on the other hand, discloses a wire saw in which a multiplicity of finite
15 wires are provided and each wire section of the wire web is assigned to one of these wires. EP 522 542 A1 also discloses a wire saw in which a multiplicity of endless wire loops run around the roll system.

20 The sawing wire may be covered with a cutting layer. When using wire saws having a sawing wire without firmly bound abrasive, abrasive in the form of a suspension (cutting suspension, sawing slurry, slurry) is supplied during the cutting process. During the
25 cutting process, the workpiece passes through the wire web, in which the sawing wire is arranged in the form of wire sections lying parallel to one another. The passage through the wire web is brought about by means of a forward feed device, which moves the workpiece
30 against the wire web, the wire web against the workpiece or the workpiece and the wire web against one another.

35 When cutting semiconductor wafers from a workpiece made of semiconductor material, it is conventional for the workpiece to be connected to a sawing strip into which the sawing wire cuts at the end of the process. The

sawing strip is for example a graphite strip, which is adhesively bonded or cemented on the lateral face of the workpiece. The workpiece with the sawing strip is then cemented on a support body. After the cutting, the
5 resulting semiconductor wafers remain fixed on the sawing strip like the teeth of a comb, and can thus be removed from the wire saw. Subsequently, the remaining sawing strip is separated from the semiconductor wafers.

10

The production of semiconductor wafers from workpieces made of semiconductor material, for example from circular-cylindrical single crystal rods or cuboid polycrystalline blocks, places great demands on the
15 wire sawing. The aim of the sawing process is generally for each sawed semiconductor wafer to have side faces which are as plane as possible and lie parallel to one another. The so-called warp of the wafers is a known measure of the deviation of the actual wafer shape from
20 the desired ideal shape. The warp should generally amount to at most a few micrometers (μm). It results from a relative movement of the sawing wire sections relative to the workpiece, which takes place in the axial direction with respect to the workpiece in the
25 course of the sawing process. This relative movement may for example be caused by cutting forces which occurred during the sawing, axial displacements of the wire guide rolls due to thermal expansion, bearing plays or thermal expansion of the workpiece.

30

A significant amount of heat is released when the workpiece is cut by the abrasive, which in the course of the sawing process leads to heating of the workpiece and therefore to thermal expansion. This in turn leads
35 not only to an increase of the warp, but also to significant waviness of the sawed wafers. A particularly strong temperature increase takes place

over the first millimeters of the cut after cutting into the workpiece. With an increasing engagement length, the temperature of the workpiece increases further. In the region of the maximum engagement length, the workpiece temperature also reaches its maximum and subsequently decreases slightly, which besides the decreasing cutting heat is also attributable to the cooling fin effect of the resulting wafers. Workpiece temperature changes of $\pm 5^{\circ}\text{C}$ during the wire sawing have a negligible effect on the warp and the waviness, but cannot generally be achieved without additional outlay.

Since the workpiece is heated during the wire sawing process in order to produce semiconductor wafers, it needs to be cooled continuously during the sawing process in order to prevent thermally induced expansion of the workpiece and therefore to prevent a perturbing curvature of the cutting profile. Various methods for cooling the workpiece during wire sawing are known. In EP 2 070 653 A1, the cooling rate of the workpiece is monitored and an additional coolant (cooling slurry, slurry) is added when the cutting depth of the sawing wire is $\frac{2}{3}$ or more of the diameter of the workpiece. EP 1097782 B1 and DE 10122628 A1 describe methods in which a thermally regulated coolant is applied onto the workpiece.

The disadvantage of the aforementioned methods is that the coolant flows into the region of the cut, where it is mixed with the cutting suspension. The choice of a suitable coolant is therefore greatly restricted, and it must have a similar composition to the cutting suspension. Even when using exactly the same media for the coolant and the cutting suspension, the problem remains that the coolant detrimentally affects the cutting behavior.

The detrimental effect is due to the fact that the temperature of the coolant for optimal cooling of the crystal must be at a different level from the temperature of the cutting suspension. However, the temperature of the cutting suspension is crucial for its viscosity, which determines the transport properties for the abrasive and therefore in turn affects the quality of the cut. The temperature of the cutting suspension is therefore usually regulated accurately, and optionally varied in a controlled way during the cutting. Particularly when using glycols as a carrier medium in the cutting suspension, there is a large temperature dependency of the viscosity.

Furthermore, the coolant flowing onto the cutting web also affects the temperature of the cutting suspension. This leads to an undesirable change of the wire web temperature, which results in a degradation of the quality of the cut.

US 2010/163010 A1 describes a method in which an attempt is made to avoid this problem. In this case, the coolant is alternately switched off and on so that the coolant is only applied onto the side of the workpiece on which the sawing wire leaves the workpiece. This is intended to prevent the coolant from being mixed directly with the sawing suspension which enters the sawing kerf. However, coolant still reaches the wire web and - albeit to a reduced extent - alters the thermal and mechanical conditions of the cut. In this method, it is necessary to use exactly the same medium for the coolant and the cutting suspension, since otherwise the cutting suspension would be uncontrollably modified.

JP 2005 329506 A2 discloses a method in which a cooling gas is blown as a coolant onto the sawing wire. In this way, the viscosity of the cutting suspension can likewise be impaired and the quality of the cut
5 degraded. Furthermore, gases are only very limitedly suitable for cooling since their relatively low heat capacity does not ensure sufficient dissipation of the amounts of heat usually produced during the cutting.

10 It was an object of the invention to develop a method which ensures optimal cooling during the wire sawing of a workpiece made of semiconductor material and at the same time does not affect the properties of the cutting suspension (sawing slurry, slurry).

15

This object is achieved by a method for cooling a cylindrical workpiece made of semiconductor material during wire sawing, the wire web consisting of wire sections arranged parallel penetrating into the
20 workpiece during the sawing by an oppositely directed relative movement of the wire sections and the workpiece, and the temperature of the workpiece being controlled during the wire sawing by a liquid coolant, wherein wipers bear on the workpiece, the liquid
25 coolant is applied onto the workpiece above the wipers bearing on the workpiece surface and the liquid coolant is removed from the workpiece surface by the wipers bearing on the workpiece. The method according to the invention also makes it possible to cool a crystal in
30 such a way that the warp and nanotopography product properties of the resulting semiconductor wafers are improved. Furthermore, the method according to the invention makes it possible to use a coolant which can be selected independently of the cutting suspension.

35

A cylindrical workpiece is a geometrical body having a surface consisting of two parallel plane faces (end

faces) and a lateral face, which is formed by parallel straight lines. In the case of a circular-cylindrical body, the end faces are round and the lateral face is convex. In the case of a cuboid cylindrical workpiece, the lateral face is plane.

Fig. 1 shows the structure for sawing a circular-cylindrical workpiece made of semiconductor material according to the prior art. The designation of the objects represented in Fig. 1 is identical to the designation in Fig. 2, and will be discussed in the explanatory text for Fig. 2.

Fig. 2 shows the preferred basic structure of the method according to the invention with reference to the example of a circular-cylindrical workpiece made of semiconductor material.

An embodiment of the method according to the invention will be described below with the aid of Fig. 2:

A conventional wire saw is used in the method according to the invention. The essential components of these wire saws include a machine frame, a forward feed device and a sawing tool, which consists of a web of parallel wire sections. The workpiece is generally fixed on a mounting plate and clamped with it in the wire saw.

In general, the wire web of the wire saw is formed by a multiplicity of parallel wire sections 6, which are tensioned between at least two (and optionally three, four or more) wire guide rolls 7, the wire guide rolls being rotatably mounted and at least one of the wire guide rolls being driven. The wire sections generally belong to a single finite wire, which is guided

spirally around the roll system and is unwound from a stock roll onto a receiver roll.

5 A cutting suspension is applied by means of the nozzles
5 to the wire sections. The workpiece 3 to be sawed,
having a lateral face 10 and two end faces 3a, is
fastened by means of a sawing strip 1 on a holding
device (not shown) so that the end faces 3a are aligned
parallel with the wire sections 6. During the sawing
10 process, the forward feed device induces an oppositely
directed relative movement of the wire sections and the
workpiece. As a consequence of this forward feed
movement the wire, to which a sawing suspension is
applied, works through the workpiece to form parallel
15 sawing kerfs.

Both wire saws in which the sawing wire in the wire web
contains firmly bound abrasives, for example diamond
abrasive or silicon carbide, and wire saws in which the
20 sawing wire does not have an abrasive layer and the
cutting power is provided by a cutting suspension
containing abrasives, which is applied onto the sawing
wire during or before the sawing process, are suitable
for the method according to the invention.

25 All suspensions according to the prior art are suitable
as a cutting suspension. Cutting suspensions comprising
glycol, oil or water as carrier material and silicon
carbide as abrasive are preferably used.

30 All liquid media which have a heat capacity sufficient
to dissipate the heat produced during the sawing
process are suitable as a coolant. Suitable coolants
are for example water, glycols, or cutting suspensions
35 according to the prior art.

The cutting suspension which is used during the sawing process is preferably used as the coolant.

5 A medium having a high heat capacity, for example water, is also preferably used as the coolant.

The carrier medium for the cutting suspension (for example glycol, oil or water) is particularly preferably used as the coolant.

10

The wire sections 6 of the wire web preferably penetrate into the workpiece 3 below the application points of the wipers 8 during the sawing. The coolant 4 is applied through the nozzles 2 during the sawing process above the wiper system used in the method according to the invention, onto the lateral face 10 of the workpiece 3 on which the wipers 8 preferably also bear on both sides. The wiper system, preferably consisting of two wipers 8 and preferably a respective collection trough 9 bearing on each of the wipers 8, is guided by means of a fastening device consisting of holders 11 so that the two wipers 8 bear on the left and right (in relation to the workpiece axis) on the lateral face 10 during the sawing process until a defined horizontal cutting position of the wire web is reached in the workpiece 3 to be cut. The coolant 4 flowing over the lateral face 10 is removed into the respective collection troughs 9 by the wipers 8 bearing on the lateral face 10. This ensures that the coolant 4 is discharged during the sawing process and does not come in contact with the cutting suspension 12 and the wire sections 6 of the wire web which lie below the wipers.

35 In a preferred embodiment, the cooling of the workpiece begins before or at the start of cutting, that is to

say at the time when the sawing wires 6 of the wire web come in contact with the surface of the workpiece 3.

5 The coolant 4 is preferably applied onto the lateral face 10 of the cylindrical workpiece 3 above the wiper system bearing on the lateral face 10 of the workpiece 3 during the sawing process.

10 In a likewise preferred configuration of the invention, the coolant 4 is applied onto the end faces 3a of the workpiece above the wiper system bearing on the end faces during the sawing process.

15 In another possible configuration of the invention, the sawing strip 1 is applied below the workpiece 3 and the wire web penetrates into the workpiece from above during the sawing. The wiper system, which in this embodiment lies below the wire web, removes the cutting suspension from the surface (either lateral face or end
20 faces) of the workpiece in this embodiment, and thus prevents mixing with the coolant 4 which is guided onto the surface from below.

25 The fastening device for the wiper system may consist of preferably mobile holders 11 which, for example, can be tilted and/or moved horizontally with respect to the wire web.

30 The fastening device used in a preferred embodiment of the invention for the wiper system consists of two mobile (preferably tiltable) holders 11, which are preferably connected by means of a spring 13. On each of the ends of the two holders directed toward the workpiece, there is a wiper 8 and a collection trough 9
35 bearing on the wiper 8. The fastening device is firmly connected to the wire sawing device so that the vertical distance between the application points of the

wipers 8 on the lateral face 10 or the end faces 3a and the wire web is constant until a defined, freely selectable horizontal cutting position or penetration depth of the wire web is reached in the workpiece to be sawed. The defined point may, for example, be reached when the wire sections 6 of the wire web cut into the sawing strip 1.

When the wire web cuts in the sawing strip 1, the development of heat by the cutting is already relatively small since the cutting length is short, and cooling is no longer necessary. In addition, the faces of the wafers which are generated up to this time by the sawing process act as cooling fins.

Until the defined point is reached, the wipers 8 bear on the lateral face 10 or the end faces 3a during the sawing process. When this defined point is reached, the application of the coolant 4 onto the lateral face 10 or the end faces 3a is ended and the wiper system is removed with the holders 11 from the lateral face 10 or the end faces 3a.

The removal of the wipers 8 on both sides from the lateral face 10 or the end faces 3a of the workpiece 3 is preferably carried out mechanically using a suitable end-stop device coupled to the forward feed movement of the wire web. The end-stop device preferably triggers folding of the wipers away from the lateral face 10 or the end faces 3a of the workpiece 3. Likewise preferably, the removal of the wipers on both sides from the lateral face 10 or the end faces 3a of the workpiece 3 is carried out on a rail extending horizontally with respect to the plane of the wire web.

Particularly preferably, the removal of the wipers 8 from the lateral face 10 or the end faces 3a of the

workpiece 3 is carried out using sensor control with the aid of a servo motor.

5 The holders 11 of the wiper system are preferably designed (not represented in Fig. 2 for the sake of clarity) so as to ensure that even in the case of a circular-cylindrical workpiece 3 having a convex lateral face 10, the wipers 8 bear continuously on both sides of the lateral face 10 during the sawing process according to the prior art, until the defined point is reached, so as to ensure flow of the coolant 4 into the collection troughs 9 until removal of the wipers.

15 At the start of the sawing process, in the case of a circular-cylindrical workpiece 3 having a convex lateral face 10, the spacing of the two application points of the wipers 8 is smaller in comparison with the diameter of the workpiece 3, and it increases in the course of the sawing process up to the diameter of the workpiece 3 then decreases again (in relation to the diameter of the workpiece 3). When the defined point is reached, the wipers 8 together with the collection troughs 9 are removed from the lateral face 10. The continuous bearing of the wipers 8 on the convex lateral face 10, from the start of the sawing process until the defined point is reached, is preferably ensured by the tension force of the spring 13 and the design of the holders 11.

30 In the case of a block-shaped workpiece, in which the lateral face is formed by parallel straight lines that are perpendicular to the end faces, the holders 11 together with the spring 13 likewise ensure that during the sawing process, until the defined point is reached, the wipers 8 together with the collection troughs 9 bear on the lateral face 10 to which the coolant 4 is applied.

In a likewise preferred embodiment of the invention, the mobile (preferably tiltable) holders 11 are connected to the wire sawing device so that the holders
5 can be moved parallel in the cutting direction of the wire sections 6 of the wire web, for example on a rail, in order for example to be able to compensate for different spacings of the application points of the wipers on the lateral face 10 during the sawing
10 process.

Preferably, the bearing of the wipers 8 on the lateral face 10 or the end faces 3a of the workpiece 3 is ensured by the force of a spring 13.

15 In another preferred embodiment, the bearing of the wiper system is controlled by sensors. The movement of the holders 11 of the fastening device during the sawing process, which is dictated by the external shape
20 of the workpiece to be sawed, is carried out mechanically by motors so that the wipers 8 bear with a constant pressure on the lateral face 10 or the end faces 3a during the sawing process until a defined point is reached.

25 A respective collection trough 9 preferably bears on each of the wipers 8, as represented in Fig. 2. Likewise preferred is a collection trough 9 which is located below the wiper but does not bear on the wiper
30 8. The medium flowing away by means of the wiper is preferably guided via a channel or a slope into the collection trough 9 in this embodiment.

The collection trough 9 is preferably designed so that
35 no liquid medium contained in the collection trough 9 can emerge uncontrolledly. This may preferably be

achieved by an outlet device (not represented in Fig. 2) integrated into the collection trough 9.

5 The coolant 4 preferably flowing away by means of the wipers 8 is collected in the collection troughs 9. The coolant 4 may if necessary be separated and fed through a regulated cooling circuit (not shown). In this case, the desired temperature of the coolant 4 is restored and the coolant 4 is applied again onto the lateral
10 face 10 of the workpiece 3 through the nozzles 2. As an alternative, the coolant 4 may also be discharged from the collection troughs 9 into a storage container.

For the sawing process (cutting), a cutting suspension
15 12 is applied through the nozzles 5 onto the wire sections 6 of the wire web. The wire web is guided according to the prior art by means of the rolls 7 perpendicularly (vertically) with respect to the axis of the workpiece 3.

20

A cutting suspension which contains glycol as a carrier material and silicon carbide as an abrasive is particularly preferably used.

25 The length of the wiper 8 is preferably equal to or greater than the length of the lateral face 10 of the workpiece to be sawed. The wiper system is preferably placed so that the wiper 8 bears on the entire axial length of the workpiece to be sawed.

30

The length of the wiper 8 when it bears on the end faces 3a of the workpiece is preferably equal to or greater than the horizontal width of the end face of the workpiece to be sawed. The wiper system is
35 preferably placed so that the wiper 8 bears on the entire horizontal width of the end face of the workpiece to be sawed.

The wiper 8 is preferably made of a soft material, for example a soft plastic or rubber, which does not cause any damage to the lateral face 10 or the end faces 3a

5 and ensures good sealing.

A plastic or a rubber having a Shore A hardness of between 60 and 80 is preferably used.

10 In the likewise preferred embodiment in which the wipers 8 bear on the workpiece 3 with a constant pressure, a plastic or a rubber having a Shore A hardness of less than 60 is preferably used.

15 After the sawing, the semiconductor wafers sawed by the method according to the invention have a significantly more planar surface in relation to nanotopology than semiconductor wafers which have been sawed according to the prior art.

20

Fig. 3 shows as an example the nanotopology parameters "waviness" (W) and "local warp" (L) for a semiconductor wafer having a diameter of 300 mm, which was produced according to the prior art by wire sawing from a crystal made of semiconductor material.

25

Fig. 4 shows as an example the nanotopology parameters "waviness" (W) and "local warp" (L) for a semiconductor wafer having a diameter of 300 mm, which was produced with the method according to the invention by wire sawing from a crystal made of semiconductor material.

30

The changes of the "waviness" (W) and the "local warp" (L) in Fig. 3 and Fig. 4 are represented in a normalized fashion (without units) for better representation, the same normalization having been used for both figures.

35

Figs 3 and 4 represent the "local warp" (L) as a measure of the curvature of the wafer in the saw forward feed direction, and the "waviness" (W), which is derived from the "local warp" (L) by placing a moving window with a window length of 10 mm over the local warp curve and plotting the respective maximum deviations within this window.

10 The "local warp" (L) represented in **Fig. 3** is characteristic of a wafer when the temperature of the crystal 3 is controlled during the cutting by supplying a coolant 4 onto the crystal lateral face 10, the coolant 4 having had a temperature profile applied to it so that the crystal 3 is at a substantially constant temperature during the cutting. The coolant 4 in this case flows unimpeded over the crystal 3 onto the wire sections 6 of the wire web, where it is mixed with the cutting suspension 12 and affects the mechanical and thermal properties of the wire sections 6 of the wire web.

The geometry measurement in **Fig. 3** shows a clearly detrimental effect caused by this on the sawed wafer made of semiconductor material. This perturbing effect is in particular greatest from the middle of the wafer (large decrease of the "local warp" (L) from about position +35 mm), since the angle between the crystal side face 10 and the wire web is less than 90 degrees here and a perturbing effect of stagnation of the cutting suspension 12 occurs, which is further exacerbated by the coolant 4.

Fig. 4 shows for comparison a wafer made of semiconductor material which was sawed under the same conditions but by using the method according to the invention. Owing to the lateral removal of the coolant

4, no detrimental effect on the cutting behavior of the wire web occurs and a substantially straight cutting profile is ensured. With the method according to the invention, a reduction of the "local warp" (L) by more
5 than 65% can be achieved.

The method according to the invention is suitable for all workpieces to be wire-sawed, regardless of the diameter.

10

The method according to the invention is preferably used for crystals having a diameter of more than 200 mm.

15 The method according to the invention is particularly preferably used for crystals having a diameter greater than or equal to 300 mm.

Patent Claims:

1. A method for cooling a cylindrical workpiece made of semiconductor material having a surface consisting of two end faces and a lateral face, during wire
5 sawing, the wire web consisting of wire sections arranged parallel penetrating into the workpiece during the sawing by an oppositely directed relative movement of the wire sections and the workpiece, and
10 the temperature of the workpiece being controlled during the wire sawing by a liquid coolant, wherein wipers bear on the workpiece surface, the liquid coolant is applied onto the workpiece above the wipers bearing on the workpiece surface and the
15 liquid coolant is removed from the workpiece surface by the wipers bearing on the workpiece.
2. The method as claimed in claim 1, wherein the liquid coolant is applied onto the lateral face above the
20 wipers bearing on the lateral face of the workpiece.
3. The method as claimed in claim 1, wherein the liquid coolant is applied onto the end faces above the wipers bearing on the end faces of the workpiece.
25
4. The method as claimed in one of claims 1 to 3, wherein the wire sections of the wire web penetrate into the workpiece below the wipers bearing on the workpiece.
30
5. The method as claimed in one of claims 1 to 4, wherein during penetration of the wire sections of the wire web into the workpiece, the wipers bear on the lateral face or the end faces until a freely
35 selectable penetration depth of the wire web into the workpiece is reached, and when this penetration depth is reached the application of the coolant is

ended and the wipers are removed from the workpiece surface.

5 6. The method as claimed in one of claims 1 to 5,
wherein a cutting suspension, which contains loose
abrasives, is applied onto the wire sections of the
saw web.

10 7. The method as claimed in claim 6, wherein the
cutting suspension contains a glycol as a carrier
material.

15 8. The method as claimed in one of claims 6 and 7,
wherein the liquid coolant consists of the carrier
medium for the cutting suspension.

9. The method as claimed in one of claims 1 to 5,
wherein the wire sections contain firmly bound
abrasives.