

ASPHALT COMPOSITION

FIELD OF THE INVENTION

[0001]

The present invention relates to an asphalt composition to be used for road pavement, an asphalt mixture, and a method for producing an asphalt mixture.

BACKGROUND OF THE INVENTION

[0002]

An asphalt pavement using an asphalt composition has been frequently performed for paving driveways, parking spaces, cargo yards, sidewalks, etc., because of relatively easy construction and a short period of time from beginning of paving works to traffic start.

The asphalt pavement includes a road surface which is formed of an asphalt mixture containing aggregates bonded with each other through asphalt, and hence, paved roads exhibit good hardness and durability.

However, a rut of a wheel or a crack is generated on the asphalt pavement surface due to long-term use. Therefore, in such a case, repair of the pavement is inevitably needed, which results in increased maintenance costs and significant influence on car traffic.

[0003]

PTL 1 describes a waste toner-containing paving material containing 100 parts by weight of asphalt and 1 to 10 parts by weight of a waste toner. PTL 1 describes that according to the foregoing paving material, not only a paving material having excellent flowability resistance, abrasion resistance, and crack resistance is provided upon being blended with a toner that is the waste, but also the waste toner which has hitherto been treated as an industrial waste is reused.

CITATION LIST

PATENT LITERATURE

[0004]

PTL 1: JP 2000-169208 A

SUMMARY OF THE INVENTION

[0005]

Embodiments of the present invention are concerned with the following [1] to [3].

[1] An asphalt composition containing asphalt, a thermoplastic elastomer, and a polyester,

wherein

the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and

a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

[2] An asphalt mixture including the asphalt composition as set forth above in [1] and an aggregate.

[3] A method for producing an asphalt mixture, including a step of mixing a heated aggregate, asphalt, a thermoplastic elastomer, and a polyester, wherein

the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and

a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

DETAILED DESCRIPTION OF THE INVENTION

[0006]

Hitherto, in the case of using a composition containing asphalt and a polyester, an asphalt composition having strong dry strength is obtained; however, there is demanded an asphalt composition capable of forming a paved surface which is much more hardly rutted and exhibits excellent durability.

Then, embodiments of the present invention are concerned with an asphalt composition which is excellent in durability of a paved surface after laying, an asphalt mixture, and a method for producing an asphalt mixture.

The embodiments of the present invention are concerned with the aforementioned [1] to [3].

In accordance with the embodiments of the present invention, it is possible to provide an asphalt composition which is excellent in durability of a paved surface after laying, an asphalt mixture, and a method for producing an asphalt mixture.

[0007]

[Asphalt Composition]

The asphalt composition according to the embodiment of the present invention (hereinafter also referred to simply as "asphalt composition") contains asphalt, a thermoplastic elastomer, and a polyester.

The polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower.

Furthermore, a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

According to the foregoing, an asphalt composition which is excellent in durability of the paved surface after laying (hereinafter also referred to simply as "durability") is obtained. Furthermore, by applying this technology, an asphalt mixture and a method for producing an asphalt mixture can be provided.

Although reasons why the effects of the embodiments of the present invention are obtained are not always elucidated yet, the following may be considered.

It may be considered that in view of the fact that the polyester has a softening point equal to or higher than a predetermined value and a glass transition point equal to or higher than a predetermined value, not only it exhibits a high intermolecular force (van der Waals force) to undergo an intermolecular interaction with the thermoplastic elastomer that is an asphalt-modifying component, but also it adsorbs on the aggregate.

In the case where the polyester has a softening point of a range equal to or lower than the predetermined value and a glass transition point of a range equal to or lower than the predetermined value, by imparting an effect for anchoring an aggregate on asphalt, which when using only a thermoplastic elastomer, has been unable to be realized so far, the flowability resistance is improved, and the durability of the paved surface after laying is improved, while remaining flexibility of the thermoplastic elastomer.

[0008]

Definitions and so on regarding various terminologies in this specification are hereunder described.

A "binder mixture" means a mixture of asphalt and a thermoplastic elastomer, and for example, it has a concept including modified asphalt with a thermoplastic elastomer as mentioned later.

In the polyester, an "alcohol component-derived structural unit" means a structure resulting from eliminating a hydrogen atom from a hydroxy group of the alcohol component, and a "carboxylic acid component-derived structural unit" means a structure resulting from eliminating a hydroxy group from a carboxy group of the carboxylic acid component.

A "carboxylic acid compound" has a concept including not only a carboxylic acid thereof but also an anhydride which is decomposed during the reaction to form an acid and an alkyl ester of carboxylic acid (for example, the carbon number of the alkyl group is 1 or more and 3 or less).

In the case where the carboxylic acid compound is an alkyl ester of carboxylic acid, the carbon number of the alkyl group that is an alcohol residue of the ester is not calculated for

the carbon number of the carboxylic acid compound.

[0009]

[Asphalt]

As the asphalt, for example, various kinds of asphalts can be used. Examples thereof include in addition to straight asphalt that is petroleum asphalt for pavement, blown asphalt.

The straight asphalt refers to a residual bituminous material obtained by treating a crude oil with an atmospheric distillation apparatus, a vacuum distillation apparatus, or the like.

The blown asphalt means asphalt obtained by heating a mixture of straight asphalt and a heavy oil and then blowing air to undergo oxidation.

[0010]

Of these, from the viewpoint of versatility, straight asphalt is preferred.

A penetration of the asphalt is preferably more than 40, and it is preferably 120 or less, more preferably 80 or less, and still more preferably 60 or less. A measurement method of the penetration conforms to the method prescribed in JIS K2207:2006. When a prescribed needle penetrates vertically into a sample under a test condition described in JIS K2207:2006, 0.1 mm of a length of the needle penetrated into the sample is expressed as 1.

The content of the asphalt in the asphalt composition is preferably 60% by mass or more, more preferably 70% by mass or more, still more preferably 75% by mass or more, and yet still more preferably 80% by mass or more, and it is preferably 98% by mass or less, more preferably 96% by mass or less, and still more preferably 95% by mass or less.

[0011]

[Thermoplastic Elastomer]

Examples of the thermoplastic elastomer include a styrene/butadiene block copolymer (hereinafter also referred to simply as "SB"), a styrene/butadiene/styrene block copolymer (hereinafter also referred to simply as "SBS"), a styrene/butadiene random copolymer (hereinafter also referred to simply as "SBR"), a styrene/isoprene block copolymer (hereinafter also referred to simply as "SI"), a styrene/isoprene/styrene block copolymer (hereinafter also referred to simply as "SIS"), a styrene/isoprene random copolymer (hereinafter also referred to simply as "SIR"), an ethylene/vinyl acetate copolymer, and an ethylene/acrylic acid ester copolymer.

Examples of a commercially available product of the ethylene/acrylic acid ester copolymer include "Elvaroy" (manufactured by DuPont de Nemours, Inc.).

Of these thermoplastic elastomers, from the viewpoint of more improving the durability, a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a

styrene/isoprene/styrene block copolymer, and a styrene/isoprene random copolymer are preferred; and a styrene/butadiene random copolymer and a styrene/butadiene/styrene block copolymer are more preferred.

[0012]

From the viewpoint of more improving the durability, the content of the thermoplastic elastomer in the asphalt composition is preferably 0.1% by mass or more, more preferably 0.5% by mass or more, still more preferably 1% by mass or more, and yet still more preferably 2% by mass or more, and it is preferably 30% by mass or less, more preferably 20% by mass or less, still more preferably 10% by mass or less, and yet still more preferably 5% by mass or less.

[0013]

In the asphalt composition, from the viewpoint of more improving the durability, a ratio of the thermoplastic elastomer is preferably 0.1 parts by mass or more, more preferably 0.5 parts by mass or more, still more preferably 1 part by mass or more, and yet still more preferably 2 parts by mass or more, and it is preferably 30 parts by mass or less, more preferably 20 parts by mass or less, still more preferably 10 parts by mass or less, and yet still more preferably 5 parts by mass or less based on 100 parts by mass of the asphalt.

[0014]

It is preferred that the asphalt and the thermoplastic elastomer are used as a binder mixture that is a mixture of these materials. Examples of the binder mixture include straight asphalt that is asphalt modified with a thermoplastic elastomer (the straight asphalt will be hereinafter also referred to as "modified asphalt").

[0015]

[Polyester]

From the viewpoint of more improving the durability of the paved surface after laying, the polyester preferably contains an alcohol component-derived structural unit containing 60 mol% or more of an alkylene oxide adduct of bisphenol A and a carboxylic acid component-derived structural unit.

From the viewpoint of more improving the durability, the polyester according to a first embodiment contains 50 mol% or more of an aromatic dicarboxylic acid compound based on the carboxylic acid component.

From the viewpoint of more improving the durability, the polyester according to a second embodiment contains 50 mol% or more of an aliphatic dicarboxylic acid compound based on the carboxylic acid component.


[0016]

<Alcohol Component>

Examples of the alcohol component include diols and trihydric or higher-hydric and octahydric or lower-hydric alcohols.

Examples of the alcohol component include aliphatic diols, aromatic diols, and trihydric or higher-hydric alcohols. These alcohol components can be used alone or in combination of two or more thereof.

From the view of obtaining excellent durability, the alcohol component preferably contains an alkylene oxide adduct of bisphenol A, and more preferably contains an alkylene oxide adduct of bisphenol A represented by the following formula (I):



wherein OR^1 and R^1O each represent an alkylene oxide; R^1 represents an alkylene group having 2 or 3 carbon atoms; x and y each represent a positive number expressing an average addition molar number of the alkylene oxide; and a sum total of x and y is 1 or more, and preferably 1.5 or more, and it is 16 or less, preferably 8 or less, and more preferably 4 or less.

It may be considered that in view of the fact that the polyester contains an alcohol component-derived structural unit containing 60 mol% or more of an alkylene oxide adduct of bisphenol A, the polyester not only undergoes an intermolecular interaction with the thermoplastic elastomer that is an asphalt-modifying component but also adsorbs on the aggregate. According to this, it may be considered that by imparting an effect for anchoring an aggregate on asphalt, which when using only a thermoplastic elastomer, has been unable to be realized so far, the flowability resistance is improved, and the durability of the paved surface after laying is improved, while remaining flexibility of the thermoplastic elastomer. In particular, among thermoplastic elastomers, SBS and SBR as mentioned later readily reveal this effect.

[0017]

Examples of the alkylene oxide adduct of bisphenol A represented by the formula (I) include a propylene oxide adduct of bisphenol A [2,2-bis(4-hydroxyphenyl)propane] and an ethylene oxide adduct of bisphenol A. Of these, a combination of a propylene oxide adduct of bisphenol A and an ethylene oxide adduct of bisphenol A is preferred.

[0018]

From the viewpoint of not only enhancing melt-dispersibility in the asphalt but also enhancing affinity with the thermoplastic elastomer and obtaining excellent durability, the

amount of the alkylene oxide adduct of bisphenol A in the alcohol component is preferably 65 mol% or more, and more preferably 80 mol% or more, and it is 100 mol% or less.

[0019]

A molar ratio of the propylene oxide adduct of bisphenol A to the ethylene oxide adduct of bisphenol A in the alcohol component is preferably 5/95 or more, and more preferably 10/90 or more, and from the viewpoint of not only enhancing melt-dispersibility in the asphalt but also enhancing affinity with the thermoplastic elastomer and obtaining excellent durability, the foregoing molar ratio is preferably 50/50 or less, more preferably 40/60 or less, and still more preferably 30/70 or less.

[0020]

The aliphatic diol is, for example, an aliphatic diol having 2 or more and 20 or less carbon atoms. Examples of the aliphatic diol include ethylene glycol, 1,2-propanediol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,4-butenediol, 1,3-butanediol, neopentyl glycol, 1,10-decanediol, and 1,12-dodecanediol.

The trihydric or higher-hydric alcohol is, for example, a trihydric alcohol. Examples of the trihydric or higher-hydric alcohol include glycerin.

[0021]

<Carboxylic Acid Component>

Examples of the carboxylic acid component include aliphatic dicarboxylic acid compounds, aromatic dicarboxylic acid compounds, trivalent or higher-valent and hexavalent or lower-valent carboxylic acid compounds. These carboxylic acid components can be used alone or in combination of two or more thereof.

[0022]

The carboxylic acid component in the polyester of the first embodiment is hereunder described.

From the viewpoint of more improving the durability, the carbon number of the main chain of the aliphatic dicarboxylic acid is preferably 3 or more, and more preferably 4 or more, and it is preferably 10 or less, and more preferably 8 or less.

Examples of the aliphatic dicarboxylic acid compound include fumaric acid, maleic acid, oxalic acid, malonic acid, citraconic acid, itaconic acid, glutaconic acid, succinic acid, adipic acid, suberic acid, azelaic acid, sebacic acid, dodecane diacid, and a succinic acid substituted with an alkyl group having 1 or more and 20 or less carbon atoms or an alkenyl group having 2 or more and 20 or less carbon atoms, and anhydrides or alkyl esters (for example, the carbon number of the alkyl group is 1 or more and 3 or less) thereof. Examples of the substituted succinic acid include dodecyl succinic acid, dodecenylsuccinic acid, and octenyl

succinic acid.

Of the foregoing aliphatic dicarboxylic acid compounds, fumaric acid, maleic acid, and adipic acid are preferred, and adipic acid is more preferred.

From the viewpoint of enhancing the flexibility of the polyester to more improve the durability, the content of the aliphatic dicarboxylic acid compound based on the carboxylic acid component is preferably 1 mol% or more, more preferably 5 mol% or more, and still more preferably 10 mol% or more, and it is preferably 30 mol% or less, and more preferably 25 mol% or less.

[0023]

Examples of the aromatic dicarboxylic acid compound include terephthalic acid, phthalic acid, isophthalic acid, and naphthalenedicarboxylic acid, and anhydrides or alkyl esters (for example, the carbon number of the alkyl group is 1 or more and 3 or less) thereof.

Of the foregoing aromatic dicarboxylic acids, terephthalic acid and isophthalic acid are preferred. Of these, from the viewpoint of more improving the durability, terephthalic acid is preferred.

From the viewpoint of enhancing affinity between the thermoplastic elastomer and the polyester and obtaining excellent durability, the content of the aromatic dicarboxylic acid compound based on the carboxylic acid component is preferably 65 mol% or more, and more preferably 70 mol% or more, and it is preferably 99 mol% or less, more preferably 95 mol% or less, and still more preferably 90 mol% or less.

[0024]

The trivalent or higher-valent and hexavalent or lower-valent carboxylic acid compound is preferably a trivalent carboxylic acid.

Examples of the trivalent or higher-valent and hexavalent or lower-valent carboxylic acid compound include trimellitic acid, 2,5,7-naphthalenetetracarboxylic acid, and pyromellitic acid.

From the viewpoint of controlling physical properties, a monohydric alcohol may be appropriately contained in the alcohol component, and a monovalent carboxylic acid compound may be appropriately contained in the carboxylic acid component.

[0025]

The carboxylic acid component in the polyester of the second embodiment is hereunder described. Portions common to those in the carboxylic acid component of the polyester of the first embodiment are omitted, and only preferred modes in the polyester of the second embodiment are described.

From the viewpoint of more improving the durability, the carbon number of the main

chain of the aliphatic dicarboxylic acid is preferably 3 or more, and it is preferably 10 or less, more preferably 6 or less, and still more preferably 4 or less.

[0026]

Of the aliphatic dicarboxylic acid compounds, fumaric acid, maleic acid, and adipic acid are preferred, and fumaric acid is more preferred.

From the viewpoint of more improving the durability, the content of the aliphatic dicarboxylic acid compound based on the carboxylic acid component is preferably 65 mol% or more, more preferably 70 mol% or more, and still more preferably 75 mol% or more, and it is preferably 99 mol% or less, more preferably 95 mol% or less, and still more preferably 90 mol% or less.

[0027]

From the viewpoint of obtaining excellent durability, the content of the aromatic dicarboxylic acid compound based on the carboxylic acid component is preferably 1 mol% or more, more preferably 5 mol% or more, and still more preferably 10 mol% or more, and it is preferably 30 mol% or less, and more preferably 25 mol% or less.

[0028]

(Molar Ratio of Carboxylic Acid Component-Derived Structural Unit to Alcohol Component-Derived Structural Unit)

From the viewpoint of controlling an acid value, a molar ratio of the carboxylic acid component-derived structural unit to the alcohol component-derived structural unit $[(\text{carboxylic acid component})/(\text{alcohol component})]$ is preferably 0.7 or more, and more preferably 0.8 or more, and it is preferably 1.5 or less, more preferably 1.3 or less, and still more preferably 1.1 or less.

[0029]

(Physical Properties of Polyester)

From the viewpoint of obtaining the durability, the softening point of the polyester is 90°C or higher, preferably 95°C or higher, and more preferably 100°C or higher, and it is preferably 140°C or lower, more preferably 130°C or lower, still more preferably 125°C or lower, yet still more preferably 120°C or lower, and even yet still more preferably 115°C or lower.

[0030]

From the viewpoint of promoting the absorption onto the aggregate and more improving the durability, an acid value of the polyester is preferably 2 mgKOH/g or more, more preferably 3 mgKOH/g or more, and still more preferably 5 mgKOH/g or more, and from the viewpoint of enhancing the water resistance of the paved surface, the acid value of the polyester

is preferably 30 mgKOH/g or less, more preferably 20 mgKOH/g or less, and still more preferably 18 mgKOH/g or less.

[0031]

From the viewpoint of more improving the durability, a hydroxyl value of the polyester is preferably 1 mgKOH/g or more, more preferably 2 mgKOH/g or more, still more preferably 5 mgKOH/g or more, and yet still more preferably 10 mgKOH/g or more, and it is preferably 70 mgKOH/g or less, more preferably 50 mgKOH/g or less, still more preferably 30 mgKOH/g or less, yet still more preferably 20 mgKOH/g or less, even yet still more preferably less than 20 mgKOH/g, and even still more preferably 18 mgKOH/g or less.

[0032]

From the viewpoint of obtaining the durability and the viewpoint of improving the flowability resistance at a high temperature, the glass transition point of the polyester is 40°C or higher, and more preferably 45°C or higher, and it is 80°C or lower, more preferably 70°C or lower, and still more preferably 60°C or lower.

[0033]

The softening point, the acid value, the hydroxyl value, and the glass transition point can be measured by the methods described in the section of Examples. The softening point, the acid value, the hydroxyl value, and the glass transition point can be controlled according to a raw material monomer composition, a molecular weight, a catalyst amount, or a reaction condition.

[0034]

(Production Method of Polyester)

Although a method for producing the polyester is not particularly limited, for example, the polyester can be produced by subjecting the alcohol component and the carboxylic acid component as mentioned above to polycondensation.

Although a temperature of the polycondensation reaction is not particularly limited, it is preferably 160°C or higher and 260°C or lower from the viewpoint of reactivity.

[0035]

For the polycondensation reaction, a tin(II) compound not having an Sn-C bond, such as tin(II) di(2-ethylhexanoate), may be used as a catalyst in an amount of preferably 0.01 parts by mass or more, and more preferably 0.2 parts by mass or more, and it is preferably 1.5 parts by mass or less, and more preferably 0.6 parts by mass or less, based on 100 parts by mass of a total amount of the alcohol component and the carboxylic acid component.

For the polycondensation reaction, in addition to the catalyst, a pyrogallol compound, such as gallic acid, may be used as an esterification catalyst in an amount of preferably 0.001

parts by mass or more, more preferably 0.005 parts by mass or more, and still more preferably 0.01 parts by mass or more, and it is preferably 0.15 parts by mass or less, more preferably 0.10 parts by mass or less, and still more preferably 0.05 parts by mass or less, based on 100 parts by mass of a total amount of the alcohol component and the carboxylic acid component.

[0036]

(Ratio of Polyester)

In the asphalt composition, from the viewpoint of improving the durability, a ratio of the polyester is 1 part by mass or more, preferably 2 parts by mass or more, and more preferably 3 parts by mass or more, and it is 17 parts by mass or less, preferably 15 parts by mass or less, more preferably 12 parts by mass or less, still more preferably 10 parts by mass or less, yet still more preferably 7 parts by mass or less, even yet still more preferably 5 parts by mass or less, and even still more preferably 4 parts by mass or less, based on 100 parts by mass of the asphalt.

[0037]

[Dispersant]

The asphalt composition may contain a dispersant.

The dispersant is preferably one capable of being dissolved in the asphalt and having affinity with the polyester.

Examples of the dispersant include polymer dispersants and surfactants, such as polyoxyethylene alkylamines and alkanolamines.

Examples of the polymer dispersant include a polyamide amine and a salt thereof, a polycarboxylic acid and a salt thereof, a high-molecular weight unsaturated acid ester, a modified polyurethane, a modified polyester, a modified poly(meth)acrylate, a (meth)acrylic copolymer, and a naphthalenesulfonic acid formalin condensate. These dispersants may be used alone or in combination of two or more thereof.

From the viewpoint of improving the high-temperature storage stability, the dispersant is preferably a polymer dispersant. It is to be noted that the "polymer dispersant" as referred to in the present invention means a dispersant having a weight average molecular weight of 1,000 or more. Although the weight average molecular weight varies with the polymer species, it is preferably 2,000 or more, and more preferably 4,000 or more, and it is preferably 80,000 or less, and more preferably 40,000 or less.

[0038]

The dispersant preferably has a basic functional group. The basic functional group means a group such that a pKa of a conjugate acid is -3 or more.

Examples of the basic functional group include an amino group, an imino group, and a quaternary ammonium group

A base number of the dispersant is preferably 10 mgKOH/g or more, more preferably 20 mgKOH/g or more, and still more preferably 30 mgKOH/g or more, and it is preferably 150 mgKOH/g or less, more preferably 120 mgKOH/g or less, and still more preferably 100 mgKOH/g or less.

As for the measurement method of the base number, the measurement is performed by the method prescribed in JIS K7237:1995.

[0039]

Examples of the commercially available dispersant include "DISPER" Series "byk-101", "byk-130", "byk-161", "byk-162", "byk-170", "byk-2020", "byk-2164", and "byk-LPN21324" (all of which are manufactured by BYK Additives & Instruments; "SOLSPERSE" Series "9000", "11200", "13240", "13650", "13940", "17000", "18000", "24000", "28000", "32000", "38500", and "71000" (all of which are manufactured by Lubrizol Corp.); "AJISPER" Series "PB821", "PB822", "PB880", and "PB881" (all of which are manufactured by Ajinomoto Fine-Techno Co., Inc.); "EFKA" Series "46", "47", "48", "49", "4010", "4047", "4050", "4165", and "5010" (all of which are manufactured by BASF SE); "FLOWLEN TG-710" (manufactured by Kyoeisha Chemical Co., Ltd.); and "TAMN-15" (manufactured by Nikko Chemicals Co., Ltd.).

[0040]

The content of the dispersant is preferably 1 part by mass or more, more preferably 3 parts by mass or more, and still more preferably 4 parts by mass or more, and it is preferably 80 parts by mass or less, more preferably 60 parts by mass or less, still more preferably 40 parts by mass or less, yet still more preferably 30 parts by mass or less, and even yet still more preferably 20 parts by mass or less, based on 100 parts by mass of the polyester.

[0041]

[Asphalt Mixture]

The asphalt mixture according to the embodiment of the present invention contains the aforementioned asphalt composition and the aggregate. Namely, the asphalt mixture contains the asphalt, the thermoplastic elastomer, the polyester, and the aggregate.

From the viewpoint of more improving the durability, the content of the asphalt composition in the asphalt mixture is preferably 2% by mass or more, more preferably 3% by mass or more, and still more preferably 4% by mass or more, and it is preferably 15% by mass or less, more preferably 10% by mass or less, and still more preferably 8% by mass or less.

[0042]

(Aggregate)

The aggregate can be, for example, optionally selected from crushed stone, cobble

stone, gravel, sand, reclaimed aggregate, and ceramics, and used.

As the aggregate, all of a coarse aggregate having a particle diameter of 2.36 mm or more and a fine aggregate having a particle diameter of less than 2.36 mm can be used.

Examples of the coarse aggregate include crushed stone having a particle diameter range of 2.36 mm or more and 4.75 mm or less, crushed stone having a particle diameter range of 4.75 mm or more and 12.5 mm or less, crushed stone having a particle diameter range of 12.5 mm or more and 19 mm or less, and crushed stone having a particle diameter range of 19 mm or more and 31.5 mm or less.

The fine aggregate is preferably a fine aggregate having a particle diameter of 0.075 mm or more and less than 2.36 mm. Examples of the fine aggregate include river sand, hill sand, mountain sand, sea sand, crushed sand, fine sand, screenings, crushed stone dust, silica sand, artificial sand, glass cullet, molding sand, and reclaimed aggregate-crushed sand.

The aforementioned particle diameter is a value prescribed in JIS 5001:1995.

Of these, a combination of the coarse aggregate and the fine aggregate is preferred.

The fine aggregate may contain a filler having a particle diameter of less than 0.075 mm (for example, sand). A lower limit value of the average particle diameter of the filler is, for example, 0.001 mm or more.

[0043]

From the viewpoint of improving the dry strength, the average particle diameter of the filler is preferably 0.001 mm or more, and it is preferably 0.05 mm or less, more preferably 0.03 mm or less, and still more preferably 0.02 mm or less. The average particle diameter of the filler can be measured by a laser diffraction particle size distribution analyzer. Here, the average particle diameter means an average particle diameter of 50% cumulative volume.

[Measurement Method of Average Particle Diameter of Filler]

The average particle diameter of the filler is a value measured by a laser diffraction particle size distribution analyzer (LA-950, manufactured by HORIBA, Ltd.) under the following condition.

- Measurement method: Flow method
- Dispersion medium: Ethanol
- Sample preparation: 2 mg/100mL
- Dispersing method: Stirring and 1 minute of built-in ultrasonic waves

[0044]

Examples of the filler include sand, fly ash, calcium carbonate, and hydrated lime. Of these, calcium carbonate is preferred from the viewpoint of improving the dry strength.

[0045]

A mass ratio of the coarse aggregate to the fine aggregate is preferably 10/90 or more, more preferably 20/80 or more, and still more preferably 30/70 or more, and it is preferably 90/10 or less, more preferably 80/20 or less, and still more preferably 70/30 or less.

The content of the aggregate is preferably 1,000 parts by mass or more, more preferably 1,200 parts by mass or more, and still more preferably 1,400 parts by mass or more, and it is preferably 3,000 parts by mass or less, more preferably 2,500 parts by mass or less, and still more preferably 2,000 parts by mass or less, based on 100 parts by mass of a sum total of the asphalt, the thermoplastic elastomer, and the polyester.

[0046]

Suitable blending examples of the asphalt mixture are as follows.

(1) An example of the asphalt mixture includes, for example, 30% by volume or more and less than 45% by volume of the coarse aggregate, 30% by volume or more and 50% by volume or less of the fine aggregate, and 5% by volume or more and 10% by volume or less of the asphalt composition (fine-graded asphalt).

(2) An example of the asphalt mixture includes, for example, 45% by volume or more and less than 70% by volume of the coarse aggregate, 20% by volume or more and 45% by volume or less of the fine aggregate, and 3% by volume or more and 10% by volume or less of the asphalt composition (dense-graded asphalt).

(3) An example of the asphalt mixture includes, for example, 70% by volume or more and 80% by volume or less of the coarse aggregate, 10% by volume or more and 20% by volume or less of the fine aggregate, and 3% by volume or more and 10% by volume or less of the asphalt composition (porous asphalt).

[0047]

In the asphalt mixture, other components may be further blended, as the need arises.

The blending ratio of the asphalt in the conventional asphalt mixtures containing the aggregate and the asphalt is in general adopted by referring to an optimum asphalt amount obtained from "Formulation and Design of Asphalt Mixture" as described in "Guideline for Pavement Design and Construction" published by Japan Road Association.

In this specification, the aforementioned optimum asphalt amount corresponds to the total amount of the asphalt, the thermoplastic elastomer, and the polyester. In consequence, in general, the total blending amount of the asphalt, the thermoplastic elastomer, and the polyester is preferably determined from the aforementioned optimum asphalt amount.

However, it is not needed to limit the optimum asphalt amount to the method as described in "Guideline for Pavement Design and Construction", and it may also be determined by any other methods.

[0048]

[Production Method of Asphalt Mixture]

From the viewpoint of more improving the durability, a method for producing the asphalt mixture according to the embodiment of the present invention includes a step of mixing the heated aggregate, the asphalt, the thermoplastic elastomer, and the polyester as mentioned above.

[0049]

As the specific production method, there is exemplified the conventional production method of an asphalt mixture which is called a plant mix method, a premix method, or the like. All of these methods are concerned with a method for adding the asphalt, the thermoplastic elastomer, and the polyester to the heated aggregate. Examples of the addition method include a premix method in which the asphalt, the thermoplastic elastomer, and the polyester are previously dissolved; and a plant mix method in which modified asphalt having the thermoplastic elastomer dissolved in the asphalt is added, and then, the polyester is charged. Of these, the premix method is preferred.

More specifically, in the production method of the asphalt mixture, the mixing step is preferably

- (i) a method in which the asphalt and the thermoplastic elastomer are added to and mixed with the heated aggregate, and then, the polyester is added and mixed; or
- (ii) a method in which the asphalt, the thermoplastic elastomer, and the polyester are simultaneously added to and mixed with the heated aggregate.

Of these, the method (i) is preferred.

[0050]

In the mixing step, from the viewpoint of durability, a temperature of the heated aggregate is preferably a temperature higher than the softening point of the polyester. The temperature of the heated aggregate is preferably 130°C or higher, more preferably 150°C or higher, still more preferably 170°C or higher, and yet still more preferably 180°C or higher, and from the viewpoint of preventing thermal degradation of the asphalt from occurring, the temperature of the heated aggregate is preferably 230°C or lower, more preferably 210°C or lower, and still more preferably 200°C or lower.

[0051]

In the mixing step, a mixing temperature is preferably a temperature higher than the softening point of the polyester. The mixing temperature is preferably 130°C or higher, more preferably 150°C or higher, still more preferably 170°C or higher, and yet still more preferably 180°C or higher, and from the viewpoint of preventing thermal degradation of the asphalt from

occurring, the mixing temperature is preferably 230°C or lower, more preferably 210°C or lower, and still more preferably 200°C or lower.

In the mixing step, a mixing time is, for example, 30 seconds or more, preferably 1 minute or more, more preferably 2 minutes or more, and still more preferably 5 minutes or more. Although an upper limit of the time is not particularly limited, it is, for example, about 30 minutes.

[0052]

From the viewpoint of more improving the durability, the production method of the asphalt mixture preferably includes a step of, after the mixing step, holding the resulting mixture at a temperature equal to or higher than the softening point of the polyester.

In the holding step, though the mixture may be further mixed, the mixture may be held at a temperature equal to or higher than the aforementioned temperature.

In the holding step, the mixing temperature is preferably a temperature higher than the softening point of the polyester, more preferably 130°C or higher, still more preferably 150°C or higher, yet still more preferably 170°C or higher, and even yet still more preferably 180°C or higher, and from the viewpoint of preventing thermal degradation of the asphalt composition from occurring, the mixing temperature is preferably 230°C or lower, more preferably 210°C or lower, and still more preferably 200°C or lower.

A holding time in the holding step is preferably 0.5 hours or more, more preferably 1 hour or more, and still more preferably 1.5 hours or more. Although an upper limit of the time is not particularly limited, it is, for example, about 5 hours.

[0053]

[Road Paving Method]

The asphalt mixture is used for road pavement.

The road paving method preferably includes a step of laying the aforementioned asphalt mixture, thereby forming an asphalt paving material layer.

The asphalt paving material layer is preferably a base layer or a surface layer.

[0054]

The asphalt mixture may be subjected to compacting laying using a known laying machine and the same laying method. In the case of using the asphalt mixture as the heated asphalt mixture, a compacting temperature thereof is preferably a temperature higher than the softening point of the polyester. The compacting temperature is preferably 100°C or higher, more preferably 120°C or higher, and still more preferably 130°C or higher, and it is preferably 200°C or lower, and more preferably 180°C or lower.

[0055]

With respect to the aforementioned embodiments, the specification further discloses the following asphalt composition, asphalt mixture, and so on. It should be construed that it is possible to replace the terms "containing" and "including" by "comprising".

<1> An asphalt composition containing asphalt, a thermoplastic elastomer, and a polyester, wherein

the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and

a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

<2> The asphalt composition as set forth in <1>, wherein the polyester contains an alcohol component-derived structural unit containing 60 mol% or more of an alkylene oxide adduct of bisphenol A and a carboxylic acid component-derived structural unit.

<3> The asphalt composition as set forth in <2>, wherein the polyester contains 50 mol% or more of an aromatic dicarboxylic acid compound based on the carboxylic acid component.

<4> The asphalt composition as set forth in <2>, wherein the polyester contains 50 mol% or more of an aliphatic dicarboxylic acid compound based on the carboxylic acid component.

<5> The asphalt composition as set forth in any of <1> to <4>, wherein the polyester has a hydroxyl value of 1 mgKOH/g or more and 70 mgKOH/g or less.

<6> The asphalt composition as set forth in any of <1> to <5>, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, a styrene/isoprene random copolymer, an ethylene/vinyl acetate copolymer, and an ethylene/acrylic acid ester copolymer.

<7> The asphalt composition as set forth in any of <1> to <6>, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, and a styrene/isoprene random copolymer.

<8> An asphalt mixture including the asphalt composition as set forth above in any of <1> to <7> and an aggregate.

<9> A method for producing an asphalt mixture, including a step of mixing a heated aggregate, asphalt, a thermoplastic elastomer, and a polyester, wherein

the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and

a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

<10> The method for producing an asphalt mixture as set forth in <9>, wherein in the mixing step,

- (i) the asphalt and the thermoplastic elastomer are added to and mixed with the heated aggregate, and then, the polyester is added and mixed; or
- (ii) the asphalt, the thermoplastic elastomer, and the polyester are simultaneously added to and mixed with the heated aggregate.

<11> The method for producing an asphalt mixture as set forth in <9> or <10>, wherein the polyester contains an alcohol component-derived structural unit containing 60 mol% or more of an alkylene oxide adduct of bisphenol A and a carboxylic acid component-derived structural unit.

<12> The method for producing an asphalt mixture as set forth in <11>, wherein the polyester contains 50 mol% or more of an aromatic dicarboxylic acid compound based on the carboxylic acid component.

<13> The method for producing an asphalt mixture as set forth in <11>, wherein the polyester contains 50 mol% or more of an aliphatic dicarboxylic acid compound based on the carboxylic acid component.

<14> The method for producing an asphalt mixture as set forth in any of <9> to <13>, wherein the polyester has a hydroxyl value of 1 mgKOH/g or more and 70 mgKOH/g or less.

<15> The method for producing an asphalt mixture as set forth in any of <9> to <14>, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, a styrene/isoprene random copolymer, an ethylene/vinyl acetate copolymer, and an ethylene/acrylic acid ester copolymer.

<16> The method for producing an asphalt mixture as set forth in any of <9> to <15>, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, and a styrene/isoprene random copolymer.

<17> Use of the asphalt composition as set forth in any of <1> to <7> for road pavement.

<18> Use of the asphalt mixture as set forth in <8> for road pavement.

EXAMPLES

[0056]

Respective physical values of resins and the like were measured and evaluated by the following methods.

[0057]

[Measurement Method]

[Acid Value and Hydroxyl value of Polyester]

An acid value and a hydroxyl value of a polyester were each measured on the basis of the method of JIS K0070:1992. However, only the measuring solvent was changed from a mixed solvent of ethanol and ether as prescribed in JIS K0070:1992 to a mixed solvent of acetone and toluene (acetone/toluene = 1/1 (volume ratio)).

[0058]

[Softening Point and Glass Transition Point of Polyester]

(1) Softening Point

Using a flow tester "CFT-500D" (manufactured by Shimadzu Corporation), while heating 1 g of a sample at a temperature rise rate of 6°C/min, a load of 1.96 MPa was applied by a plunger, and the sample was extruded through a nozzle having a diameter of 1 mm and a length of 1 mm. The amount of descent of the plunger of the flow tester versus the temperature was plotted, and a temperature at which a half amount of the sample flowed out was defined as the softening point of the sample.

(2) Glass Transition Point

Using a differential scanning calorimeter "Q-100" (manufactured by TA Instruments Japan Inc.), 0.01 to 0.02 g of a sample was weighed in an aluminum pan, subjected to temperature rise to 200°C, and then cooled from that temperature to 0°C at a temperature drop rate of 10°C/min. Subsequently, the measurement was performed while raising the temperature to 150°C at a temperature rise rate of 10°C/min. A temperature at which an extension of a baseline of not higher than the maximum endothermic peak temperature was intersected with a tangential line having a maximum inclination of the curve in a region of from a rise-up portion of the peak to an apex of the peak was read as the glass transition point of the sample.

[0059]

[Evaluation]

[Durability]

Using a Hamburg wheel tracking tester (load: 705 N, iron wheel width: 47 mm, linear pressure: 150 N/cm) as used for the durability test, a test specimen was immersed in warm water set at 60°C and measured for a displacement at the number of tire passes of 10,000 and 20,000, respectively. The measurement condition followed AASHTO T-324-04 (2008) except

for the immersion temperature.

Although it cannot be unequivocally said depending upon the traffic state, the displacement of 0.5 mm at the number of tire passes of 20,000 is corresponding to 1 to 2 years in terms of service life and is a significant difference which can be distinguished in terms of practical durability.

[0060]

Production Examples A1 to A3 (Resins A-1 to A-3)

In a 5 liter-volume four-necked flask equipped with a thermometer, a stainless steel-made stirring rod, a flow-down type condenser, and a nitrogen inlet tube, an alcohol component and terephthalic acid for a polyester, which are shown in Table 1, were charged, and 20 g of tin(II) di(2-ethylhexanoate) and 2 g of gallic acid were added in a nitrogen atmosphere. The temperature was raised to 235°C over 3 hours in a mantle heater, and after the temperature reached 235°C, the contents were held for 7 hours. Then, the reaction was performed under reduced pressure at 8.0 kPa for 1 hour. Thereafter, the resultant was cooled to 180°C, the residual acid was charged, and the temperature was then raised to 210°C over 2 hours. The temperature was held at 210°C for 1 hour, and the reaction was further performed under reduced pressure at 8.0 kPa, followed by performing the reaction until reaching a softening point shown in the table. There were thus obtained the target Resins A-1 to A-3.

[0061]

Production Examples A4, A6, and A7 (Resins A-4, A-6, and A-7)

In a 5 liter-volume four-necked flask equipped with a thermometer, a stainless steel-made stirring rod, a flow-down type condenser, and a nitrogen inlet tube, an alcohol component and a carboxylic acid component for a polyester, which are shown in Table 1, were charged, and 20 g of tin(II) di(2-ethylhexanoate), 2 g of gallic acid, and 2 g of t-butylcatechol were added in a nitrogen atmosphere. The temperature was raised to 210°C over 5 hours in a mantle heater, and after the temperature reached 210°C, the contents were held for 2 hours. Then, the reaction was performed under reduced pressure at 8.0 kPa, followed by performing the reaction until reaching a softening point shown in the table. There were thus obtained the target Resins A-4, A-6, and A-7.

[0062]

Production Example A5 (Resin A-5)

In a 5 liter-volume four-necked flask equipped with a thermometer, a stainless steel-made stirring rod, a flow-down type condenser, and a nitrogen inlet tube, an alcohol component and terephthalic acid for a polyester, which are shown in Table 1, were charged, and 20 g of tin(II) di(2-ethylhexanoate) and 2 g of gallic acid were added in a nitrogen atmosphere.

The temperature was raised to 235°C over 10 hours in a mantle heater, and after the temperature reached 235°C, the contents were held for 5 hours. Then, the reaction was performed under reduced pressure at 8.0 kPa for 1 hour. Thereafter, the resultant was cooled to 180°C, and then, fumaric acid, adipic acid, and 2 g of t-butylcatechol were charged. The temperature was raised to 210°C over 2 hours, and the temperature was held at 210°C for 1 hour. Then, the reaction was performed under reduced pressure at 8.0 kPa, followed by performing the reaction until reaching a softening point shown in the table. There was thus obtained the target Resin A-5.

[0063]

Table 1(1/2)

Production Example		A1		A2		A3		A4		
Resin		A-1		A-2		A-3		A-4		
Raw material monomer	Alcohol component	Charged amount (g)	Molar ratio *3	Charged amount (g)	Molar ratio *3	Charged amount (g)	Molar ratio *3	Charged amount (g)	Molar ratio *3	
		710	25	2872	100	710	25	785	25	
		1977	75	-	-	1977	75	2186	75	
	Carboxylic acid component	-	-	-	-	-	-	-	-	
		1077	80	749	55	1077	80	-	-	
		-	-	-	-	-	-	832	80	
		-	-	79	5	-	-	-	-	
Physical properties	Adipic acid		237	20	300	25	237	20	196	15
	Softening point (°C)		103.6		99.6		107.5		95.0	
	Acid value (mgKOH/g)		12.7		2.9		10.9		15.0	
	Hydroxyl value (mgKOH/g)		13.3		32.2		12.6		21.5	
Glass transition point (°C)		57.8		52		58		49		

*1: BPA-PO: Polyoxypropylene (2.2) adduct of bisphenol A

*2: BPA-EO: Polyoxyethylene (2.2) adduct of bisphenol A

*3: Molar amount based on 100 mol of alcohol component (molar ratio)

[0064]

Table 1(2/2)

Production Example		A5		A6		A7	
Resin		A-5		A-6		A-7	
Raw material monomer	Alcohol component	BPA-PO *1	Charged amount (g)	Molar ratio *3	Charged amount (g)	Molar ratio *3	Molar ratio *3
			989	25	611	20	20
			918	25	2271	80	80
	Carboxylic acid component	Ethylene glycol	350	50	-	-	-
			1595	85	-	-	-
			66	5	608	60	40
Physical properties	Softening point (°C)	Acid value (mgKOH/g)	-	-	-	-	-
			83	5	510	40	60
			102.0		87.0		85.2
			18.2		20.3		9.4
Physical properties	Hydroxyl value (mgKOH/g)	Glass transition point (°C)	49.2		25.4		11.5
			54		45		38

*1: BPA-PO: Polyoxypropylene (2.2) adduct of bisphenol A

*2: BPA-EO: Polyoxyethylene (2.2) adduct of bisphenol A

*3: Molar amount based on 100 mol of alcohol component (molar ratio)

[0065]

Example A1

In a 3-liter stainless steel vessel, 2,200 g of modified asphalt containing 3% by mass of SBS (manufactured by FESPA, Mexico) heated to 180°C was charged as a binder mixture and stirred at 100 rpm, to which was then added 3.4 g of a dispersant "SOLSPERS 11200" (manufactured by Lubrizol Corp., a polymer dispersant having a basic functional group, base number: 37 mgKOH/g). Thereafter, 68 g of the polyester was gradually added, and the contents were stirred at 500 rpm for 2 hours, thereby preparing Asphalt Composition AS-1. A component ratio of the prepared Asphalt Composition AS-1 is shown in Table 2.

[0066]

Subsequently, an aggregate produced in La Vega (Mexico) heated to 190°C (see a composition of the aggregate as shown below) was charged in a mixer for asphalt and mixed at 190°C for 30 seconds.

Subsequently, 552 g of the aforementioned Asphalt Composition AS-1 was added and mixed in the mixer for asphalt for 2 minutes. The resulting asphalt mixture was stored at 180°C for 2 hours and then charged in a gyratory compactor (a circular molding machine, manufactured by Cooper Research Technology, load: 600 kPa, 100 rotation pressure), thereby obtaining a specimen. The various evaluation tests were performed, and the results are shown in Table 3.

[0067]

<Composition of Aggregate Produced in La Vega (Mexico)>

Passing mass%:

Sieve opening 19 mm:	100% by mass
Sieve opening 12.5 mm:	81.3% by mass
Sieve opening 9.5 mm:	68.1% by mass
Sieve opening 4.75 mm:	45.1% by mass
Sieve opening 2.36 mm:	31.3% by mass
Sieve opening 1.18 mm:	18.5% by mass
Sieve opening 0.6 mm:	11.5% by mass
Sieve opening 0.3 mm:	8.1% by mass
Sieve opening 0.15 mm:	6.1% by mass
Sieve opening 0.075 mm:	4.5% by mass

[0068]

Examples A2 to A6 and A8 and Comparative Examples A1 to A4

Specimens were obtained in the same manner as in Example A1, except for using

components having the kind and amount shown in Tables 2 and 3. The various evaluation tests were performed, and results thereof are shown in Table 3.

[0069]

Example A7

In a 3-liter stainless steel vessel, 2,200 g of modified asphalt containing 2.2% by mass of SBS (manufactured by ARO, Mexico) heated to 180°C was charged as a binder mixture and stirred at 100 rpm, to which was then added 3.4 g of a dispersant "SOLSPERS 11200" (manufactured by Lubrizol Corp.). Thereafter, 68 g of the polyester (Resin A-1) was gradually added, and the contents were stirred at 500 rpm for 2 hours, thereby preparing Asphalt Composition AS-7. A component ratio of the prepared Asphalt Composition AS-7 is shown in Table 2.

[0070]

In a mixing machine for asphalt, 9,200 g of an aggregate produced in Carretera (aggregate Grava: 2,300 g, aggregate Sello: 2,300 g, aggregate Arena: 4,600 g (see a composition of the aggregate as shown below)) which had been previously heated to 190°C was charged and mixed at 190°C for 30 seconds. Subsequently, 640 g of the aforementioned asphalt composition was added and mixed in the mixer for asphalt for 2 minutes. The resulting asphalt mixture was stored at 180°C for 2 hours and then charged in a gyratory compactor (a circular molding machine, manufactured by Cooper Research Technology, load: 600 kPa, 100 rotation pressure), thereby obtaining a specimen. The various evaluation tests were performed, and the results are shown in Table 3.

[0071]

<Composition of Aggregate Produced in Carretera (Mexico)>

Passing mass%:

Sieve opening 19 mm:	98.7% by mass
Sieve opening 12.5 mm:	84.4% by mass
Sieve opening 9.5 mm:	76.7% by mass
Sieve opening 4.75 mm:	57.5% by mass
Sieve opening 2.36 mm:	34.3% by mass
Sieve opening 1.18 mm:	22.6% by mass
Sieve opening 0.6 mm:	13.8% by mass
Sieve opening 0.3 mm:	10.3% by mass
Sieve opening 0.15 mm:	7.8% by mass
Sieve opening 0.075 mm:	4.6% by mass

[0072]

Table 2

Asphalt composition													
	Kind	Binder mixture				Polyester				Surfactant			
		Kind #1	Blending amount (g)	Asphalt	Thermoplastic elastomer	Kind	Ratio #3 (mass%)	Kind	Blending amount (g)	Ratio #3 (mass%)	Ratio #2 (parts by mass)	Blending amount (g)	Ratio #3 (mass%)
Example A1	AS-1	MAS-1	2200	94	SBS	3	A-1	68	3	3		3.4	0.1
Example A2	AS-2	MAS-1	2200	92	SBS	3	A-1	110	5	5		3.4	0.1
Example A3	AS-3	MAS-1	2200	87	SBS	3	A-1	242	10	11		3.4	0.1
Example A4	AS-4	MAS-1	2200	94	SBS	3	A-2	68	3	3		3.4	0.1
Example A5	AS-5	MAS-1	2200	94	SBS	3	A-3	68	3	3		3.4	0.1
Example A6	AS-6	MAS-1	2200	94	SBS	3	A-4	68	3	3		3.4	0.1
Example A7	AS-7	MAS-2	2200	95	SBS	2	A-1	68	3	3		3.4	0.1
Example A8	AS-8	MAS-1	2200	94	SBS	3	A-5	68	3	3		3.4	0.1
Comparative Example A1	AS-51	MAS-1	2200	97	SBS	3	-	-	-	-		3.4	0.1
Comparative Example A2	AS-52	SAS-1	2200	95	-	0	A-1	110	5	5		3.4	0.1
Comparative Example A3	AS-53	MAS-1	2200	94	SBS	3	A-6	68	3	3		3.4	0.1
Comparative Example A4	AS-54	MAS-1	2200	94	SBS	3	A-7	68	3	3		3.4	0.1

*1: MAS-1: Modified asphalt containing 3% by mass of SBS

MAS-2: Modified asphalt containing 2.2% by mass of SBS

SAS-1: Straight asphalt

*2: Ratio based on 100 parts by mass of asphalt (parts by mass)

*3: Proportion relative to the whole of asphalt composition

[0073]

Table 3

	Asphalt mixture							Evaluation			
	Asphalt composition				Blending amount (g)	Kind #4	Aggregate		Displacement in Hamburg (at 60°C) (mm)		
	Binder mixture	Polyester		Blending amount (g)			Coarse aggregate Proportion *3 (mass%)	Fine aggregate Proportion *3 (mass%)			
Kind	Kind #1	Kind	Ratio #2 (parts by mass)								10,000 times
Example A1	AS-1	MAS-1	A-1	3	552	AGG-1	9200	68.7	31.3	4.2	5.0
Example A2	AS-2	MAS-1	A-1	5	564	AGG-1	9200	68.7	31.3	4.3	5.4
Example A3	AS-3	MAS-1	A-1	11	595	AGG-1	9200	68.7	31.3	5.0	5.5
Example A4	AS-4	MAS-1	A-2	3	552	AGG-1	9200	68.7	31.3	5.5	7.5
Example A5	AS-5	MAS-1	A-3	3	552	AGG-1	9200	68.7	31.3	3.8	4.5
Example A6	AS-6	MAS-1	A-4	3	552	AGG-1	9200	68.7	31.3	5.2	6.0
Example A7	AS-7	MAS-2	A-1	3	640	AGG-2	9200	65.7	34.3	-	4.0
Example A8	AS-8	MAS-1	A-5	3	552	AGG-1	9200	68.7	31.3	7.0	9.0
Comparative Example A1	AS-51	MAS-1	-	0	535	AGG-1	9200	68.7	31.3	9.9	15.5
Comparative Example A2	AS-52	SAS-1	A-1	5	564	AGG-1	9200	68.7	31.3	8.0	10.0
Comparative Example A3	AS-53	MAS-1	A-6	3	552	AGG-1	9200	68.7	31.3	7.6	9.5
Comparative Example A4	AS-54	MAS-1	A-7	3	552	AGG-1	9200	68.7	31.3	8.3	10.8

*1: MAS-1: Modified asphalt containing 3% by mass of SBS

MAS-2: Modified asphalt containing 2.2% by mass of SBS

SAS-1: Straight asphalt

*2: Ratio based on 100 parts by mass of asphalt (parts by mass)

*3: Proportion relative to the whole of aggregate

*4: AGG-1: Aggregate produced in La Vega (Mexico)

AGG-2: Aggregate produced in Carretera (Mexico)

[0074]

Example B1

In a mixing machine for asphalt, an aggregate produced in Carretera (coarse aggregate Grava: 2,300 g, coarse aggregate Sello: 2,300 g, fine aggregate Arena: 4,600 g (the composition of the aggregate is the same as mentioned above)) which had been previously heated to 190°C was charged and mixed at 190°C for 30 seconds. Subsequently, 640 g of modified asphalt containing 2.2% by mass of SBS (manufactured by ARO, Mexico) was added and mixed in the mixer for asphalt for 1 minute. Subsequently, 20 g of the Resin A-1 was added and mixed for 1 minute. The resulting asphalt mixture was stored at 180°C for 2 hours and then charged in a gyratory compactor (a circular molding machine, manufactured by Cooper Research Technology, load: 600 kPa, 100 rotation pressure), thereby obtaining a specimen. The durability test was performed. As a result, a displacement at the number of tire passes of 20,000 was 6 mm.

[0075]

Comparative Example B1

In a mixing machine for asphalt, an aggregate produced in Carretera (coarse aggregate Grava: 2,300 g, coarse aggregate Sello: 2,300 g, fine aggregate Arena: 4,600 g (the composition of the aggregate is the same as mentioned above)) heated to 190°C was charged and mixed at 190°C for 30 seconds. Subsequently, 660 g of modified asphalt containing 2.2% by mass of SBS was added and mixed in the mixer for asphalt for 1 minute. The resulting asphalt mixture was stored at 180°C for 2 hours and then charged in a gyratory compactor (a circular molding machine, manufactured by Cooper Research Technology, load: 600 kPa, 100 rotation pressure), thereby obtaining a specimen. The durability test was performed. As a result, a displacement at the number of tire passes of 20,000 was 10 mm.

[0076]

It can be understood that the Examples are excellent in the durability as compared with the Comparative Examples.

CLAIMS

1. An asphalt composition comprising asphalt, a thermoplastic elastomer, and a polyester, wherein
the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and
a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.
2. The asphalt composition according to claim 1, wherein the polyester comprises an alcohol component-derived structural unit containing 60 mol% or more of an alkylene oxide adduct of bisphenol A and a carboxylic acid component-derived structural unit.
3. The asphalt composition according to claim 2, wherein the polyester comprises 50 mol% or more of an aromatic dicarboxylic acid compound based on the carboxylic acid component.
4. The asphalt composition according to claim 2, wherein the polyester comprises 50 mol% or more of an aliphatic dicarboxylic acid compound based on the carboxylic acid component.
5. The asphalt composition according to any of claims 1 to 4, wherein the polyester has a hydroxyl value of 1 mgKOH/g or more and 70 mgKOH/g or less.
6. The asphalt composition according to any of claims 1 to 5, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer, a styrene/isoprene random copolymer, an ethylene/vinyl acetate copolymer, and an ethylene/acrylic acid ester copolymer.
7. The asphalt composition according to any of claims 1 to 6, wherein the thermoplastic elastomer is at least one selected from the group consisting of a styrene/butadiene block copolymer, a styrene/butadiene/styrene block copolymer, a styrene/butadiene random copolymer, a styrene/isoprene block copolymer, a styrene/isoprene/styrene block copolymer,

and a styrene/isoprene random copolymer.

8. An asphalt mixture comprising the asphalt composition according to any of claims 1 to 7 and an aggregate.

9. A method for producing an asphalt mixture, comprising a step of mixing a heated aggregate, asphalt, a thermoplastic elastomer, and a polyester, wherein
the polyester has a softening point of 90°C or higher and 140°C or lower and a glass transition point of 40°C or higher and 80°C or lower, and
a ratio of the polyester is 1 part by mass or more and 17 parts by mass or less based on 100 parts by mass of the asphalt.

10. The method for producing an asphalt mixture according to claim 9, wherein in the mixing step,

- (i) the asphalt and the thermoplastic elastomer are added to and mixed with the heated aggregate, and then, the polyester is added and mixed; or
- (ii) the asphalt, the thermoplastic elastomer, and the polyester are simultaneously added to and mixed with the heated aggregate.