

LOW OXYGEN CONTENT ALLOY COMPOSITIONS

Field of the Invention

[0001] The invention concerns low oxygen content alloy compositions, and more particularly concerns low oxygen content alloy compositions having magnetic properties useful in magnetic memory applications.

Background of the Invention

[0002] Magnetoresistive (MR) heads and Magnetic Random Access Memory (MRAM) are expected to be key technologies for future generations of vertical magnetic recording and cell phone memory applications. New materials are being studied in order to improve designs that will increase memory area density and reduce the size of memory chips. Not only must these new materials possess particular magnetic properties for use in these technologies, they must also have high purity levels.

[0003] Material purity plays a significant role in the performance of thin film materials used in magnetic data storage and MRAM applications. For example, the presence of impurities such as oxygen, nitrogen, sulfur and alkalides alters the lattice structure of a thin film material and thereby displaces atoms in the lattice. This effect on the structural order of the material degrades the material's magnetic properties and therefore its performance in magnetic memory applications. In addition, the presence of impurities such as oxygen can produce short diffusion paths through the thin film material into the magnetic layers. Accordingly, there is a need to identify and develop thin film materials having particular magnetic properties as well as high levels of purity.

Summary of the Invention

[0004] The present invention comprises a series of alloy compositions having preferred magnetic properties for use in magnetic memory applications. The alloy compositions form ordered compounds having $L1_0$ or $L1_2$ type crystalline structures within the claimed compositional ranges. In addition, the alloy compositions of the invention have low levels of impurities, such as oxygen and sulfur, which provide better performance in magnetic memory applications. The alloy compositions preferably are formed into sputtering targets used for thin film applications.

[0005] The alloy compositions of the invention include Mn alloys that combine Mn with one element selected from Ga, In, Ni and Zn. Also included in the alloy compositions are Fe alloys and Co alloys, in which Fe or Co are combined with either Pt or Pd.

[0006] The oxygen content of the alloy compositions of the invention is 500 ppm or less and preferably 100 ppm or less. Additionally, the sulfur content of the alloy compositions is 100 ppm or less and preferably 50 ppm or less.

[0007] The foregoing summary of the invention has been provided so that the nature of the invention may be understood quickly. A more complete understanding of the invention can be obtained by reference to the following detailed description of the invention.

Brief Description of the Drawings

[0008] Figure 1 is an optical micrograph of an as-cast Ni₄₀Mn at. % alloy.

[0009] Figure 2 is an optical micrograph of an as-cast Ni₃₀Mn at. % alloy.

[0010] Figure 3 is an SEM micrograph of an as-cast In₅₀Mn at. % alloy.

[0011] Figure 4 is an optical micrograph of an as-cast Fe₄₅Pt at. % ordered alloy.

Detailed Description of the Invention

[0012] The inventors identified and developed a series of alloy compositions that exhibited preferred magnetic characteristics and had low impurity levels. The alloy compositions of the invention form ordered compounds having $L1_0$ or $L1_2$ type crystalline structures. In addition, the oxygen and sulfur content of the alloy compositions was significantly reduced.

[0013] Table 1 summarizes the relevant compositional and structural data for the alloy compositions of the present invention. Specifically, Table 1 identifies the ordered phase symbol, the structure designation, the composition range in which the phase of interest exists, and the compositional range in which the phase of interest could coexist with other phase types. The phase symbols used in Table 1 were obtained from phase diagrams found in Binary Phase Diagrams, 2nd Edition (Thaddeus B. Massalski, ed.).

TABLE 1

Alloy System X-Y	Ordered Phase Symbol	Structure Designation	Composition at.% Y	Compositional Range at.% Y
Mn-Ga	γ_3	L1 ₀	55-63	50-70
Mn-In	InMn ₃	L1 ₀ or L1 ₂	75	50-85
Mn-Ni	η'	L1 ₀	47-55.5	44-60
Ni-Mn	γ	L1 ₂	15-29	10-30
Zn-Mn	α'	L1 ₂	25-31	20-40
Zn-Mn	α'_1	L1 ₀	25-30	20-40
Fe-Pt	Fe ₃ Pt	L1 ₂	16-33	16-35
Fe-Pt	FePt	L1 ₀	35-55	35-59
Fe-Pt	FePt ₃	L1 ₂	57-79	57-83
Fe-Pd	FePd(a)	L1 ₀	48.5-60	30-63
Fe-Pd	FePd ₃ (b)	L1 ₂	63-86	60-88
Co-Pt	CoPt(a)	L1 ₀	42-74	40-76
Co-Pt	CoPt ₃ (b)	L1 ₂	75-88	75-90
Co-Pd	α'	L1 ₀	48-52	30-58
Co-Pd	α	L1 ₂	60-90	58-94

[0014] The first group of alloys listed in Table 1 comprises Mn alloys which exhibit L1₀ or L1₂ crystalline structures. These Mn alloys possess antiferromagnetic properties desirable for thin film materials used in magnetic data storage and MRAM applications. Specifically, these Mn alloys are of interest for use in anisotropic magnetoresistive (AMR) and giant magnetoresistive (GMR) spin-valve sensors used in high-density recording. These Mn alloys are also of interest since the alloy constituents used with Mn are lower cost materials than those typically used, such as Pt, Pd, Ir or Rh. Examples 1 and 2 below describe Mn-Ni alloys and an Mn-In alloy, respectively, according to the present invention.

[0015] Example 1: A series of three Ni-Mn melt tests were conducted. The melt charge compositions for each of the tests are shown below in Table 2. The melt charge compositions were made using 99.95% pure Ni shots and 99.9% pure Mn flakes.

TABLE 2

Melt Charge Constitution	First Ni-Mn Melt Test	Second Ni-Mn Melt Test	Third Ni-Mn Melt Test
Ni Input (g)	630.0	6477.5	4886.0
Mn Input (g)	870.0	3583.1	2094.0
CaSi ₂ Input (g)	13.1	60.0	20.0
Ce Input (g)	7.9	77.4	None

[0016] In the first melt test, an alloy ingot was directly solidified in an MgO crucible. In the second and third melt tests, the alloys were melted and cast into graphite molds. The graphite molds were BN sprayed and pre-heated to 500 F in a separate furnace prior to being installed in a VIM unit chamber. For all three melt tests, the VIM unit chamber was evacuated to about 0.05 mbar in preparation for the melting operation.

[0017] The melting operation for all three tests was performed by powering the VIM unit to 5kW for 20 minutes and increasing the power by 5kW every 5 minutes for an additional 20 minutes. Once the Mn flakes began melting, the VIM unit chamber was back filled with argon to a pressure of about 40 mbar for the first test. For the second and third tests, the VIM unit chamber was subsequently back filled with argon to 500 mbar at 25 minutes and then to 700 mbar at 37 minutes.

[0018] Samples of the alloys were prepared from the bulk of the ingots for analyzing chemical composition. Inspection of the MgO crucible and the graphite molds after the ingots were turned out revealed no noticeable signs of erosion. Figures 1 and 2 are optical micrographs depicting the microstructures of the as-cast Ni40Mn at. % alloy and the as-cast Ni30Mn at. % alloy, respectively. The results of the chemical analysis of the alloy samples from the three melt tests are shown below in Table 3.

TABLE 3

	Si ppm	Ca ppm	Ce ppm	Mg ppm	Na ppm	K ppm	O ppm	C ppm	N ppm	S ppm	Mn wt. %
First Melt Test	4979	166	52	35	/	/	10	170	37	36	57.94
Second Melt Test	655	3	49	78	18	0	20	139	28	10	32.28
Third Melt Test	240	/	43	0	/	1	64	98	62	15	28.61

[0019] As shown in Table 3, each of the three melted alloys were sufficiently deoxidized, with none of the oxygen levels exceeding 100 ppm. Comparing the oxygen levels of the first and second melt tests with that of the third melt tests reveals that Ce also contributes to the deoxidization of the alloy compositions. Furthermore, with a measured sulfur content of the Mn flakes being around 300 ppm, the data shown in Table 3 indicate that CaSi_2 also plays a role in the desulfurization of the alloy melts. In table 3, “/” indicates that no measurement was taken for the particular element and “0” indicates that the particular element was not detected.

[0020] Example 2: A melt test was conducted using 2427 grams of 99.9% pure Mn flakes and 5073 grams of 99.9% pure In rods. In addition to the Mn and In constituents, 25 grams of CaSi_2 and 10 grams of Ce were added as deoxidizers. The melt charge was preheated to 500 F under a 0.07 mbar partial vacuum in an MgO crucible within a VIM unit chamber. The VIM unit chamber was then back filled with argon to 500 mbar and the melt charge melted by applying 5kW to the VIM unit for 20 minutes and increasing the power by 5kW every 5 minutes for an additional 20 minutes. The melt charge was then cast into a graphite mold.

[0021] Figure 3 is an SEM micrograph depicting the microstructure of the as-cast In50Mn at. % alloy. The microstructure depicted in this micrograph consists of three phases: a light Indium matrix, an (In,Mn) solid solution shown as a light gray phase, and an InMn_3 compound shown as dark gray grains. The black spots in the micrograph are pores. The

chemical composition of the as-cast material was analyzed, the results of which are shown below in Table 4.

TABLE 4

Si Ppm	Cu ppm	Al ppm	Ni ppm	Fe ppm	O ppm	C Ppm	N ppm	S Ppm	Mn at. %
15	2	10	6	23	40	62	19	33	50.7

[0022] Also included in the alloys described in Table 1 are Fe and Co alloys. In these alloys, Fe or Co is combined with either Pt or Pd to form the alloy composition. These alloy compositions are of interest for future generations of recording media using vertical recording technology, which are expected to reach a capacity of 200 GB or more. These alloy compositions are of particular interest for forming magnetic hard layers for which a high anisotropic constant ($K_u > 10^7 \text{ J.m}^{-1}$) can be achieved. Example 3 below describes one example of an Fe-Pt alloy composition.

[0023] Example 3: A melt test was conducted using 13.500 kg of 99.9% pure Pt shots and 4.724 kg of 99.97% pure electrolytic Fe flake. 91 g (~0.50 wt.%) of CaSi_2 was added to the melt charge for deoxidation. The charge was arranged in a magnesia crucible with alternate layers of Pt and Fe with the CaSi_2 equally distributed between the layers. The VIM unit chamber was sealed and a vacuum drawn to an initial level of 0.07 mbar. The chamber was then back filled with argon and maintained at 500 mbar pressure during melting and casting. The melt was performed by powering the VIM unit to 5kW for 20 minutes and then increasing the power by 5kW every 5 minutes for an additional 20 minutes. The mold system was a graphite shell 8.00" wide, 15.00" long and 0.60" thick.

[0024] Figure 4 is an optical micrograph depicting the microstructure of the as-cast Fe₄₅Pt at. % alloy. The microstructure consists of heavily twinned grains of the single-phase FePt described in Table 1 above. The twinned grains attribute to lattice distortion during the transformation of ($\gamma_{\text{Fe,Pt}}$) fcc solid solution into tetragonal FePt at 1300 C. The chemical composition of the as-cast material was analyzed, the results of which are shown below in Table 5.

TABLE 5

Al ppm	Cu ppm	Ni ppm	Si ppm	Ta ppm	Au ppm	Re ppm	O ppm	C ppm	N ppm	S ppm	Fe wt. %
<5	<5	<5	90	23	200	515	34	27	4	10	25.77

[0025] The foregoing examples are intended to illustrate examples of alloy compositions according to the present invention. These examples are not intended to limit the scope and the invention, which should be interpreted from the claims set forth below.

[0026] While the foregoing has described what are considered to be the best mode and/or other examples, it is understood that various modifications may be made therein and that the subject matter disclosed herein may be implemented in various forms and examples, and that they may be applied in numerous applications, only some of which have been described herein.

What is Claimed Is:

1. An alloy composition comprising 56-40 at. % Mn and 44-60 at. % Ni, wherein the alloy composition contains 500 ppm or less O and 100 ppm or less S.

2. The alloy composition according to Claim 1, wherein the alloy composition comprises 53-44.5 at. % Mn and 47-55.5 at. % Ni.

3. The alloy composition according to Claim 1, wherein the alloy composition contains 100 ppm or less O and 50 ppm or less S.

4. An alloy composition comprising 90-70 at. % Ni and 10-30 at. % Mn, wherein the alloy composition contains 500 ppm or less O and 100 ppm or less S.

5. The alloy composition according to Claim 4, wherein the alloy composition comprises 85-71 at. % Ni and 15-29 at. % Mn.

6. The alloy composition according to Claim 4, wherein the alloy composition contains 100 ppm or less O and 50 ppm or less S.