

Method for the surface treatment of a titanium dioxide pigment

The invention relates to a method for the surface treatment of a titanium dioxide pigment, a titanium dioxide pigment with high greying resistance and high hiding power, and its use in the production of decorative laminating paper.

Decorative laminating paper is an element of a decorative thermoset surface, which is used with preference for finishing furniture surfaces and for laminate floorings. Laminate is the term used for materials in which wood and paper, for example, are pressed with resin. The use of special synthetic resins results in extraordinarily high resistance of the laminates to scratching, impact, chemicals and heat.

The use of special-purpose papers (decorative laminating papers) permits the production of decorative surfaces, where the decorative laminating paper serves not only as facing paper for unattractive wood material surfaces, but also as a carrier for the synthetic resin.

The requirements imposed on decorative laminating paper include, for example, hiding power (opacity), light-fastness (greying resistance), colour-fastness, wet strength, impregnability and printability.

In principle, a pigment based on titanium dioxide is eminently suitable for achieving the necessary opacity of the decorative laminating paper. As a rule, a titanium dioxide pigment or a titanium dioxide pigment suspension is mixed with a fibre suspension during paper production. The interactions between the individual components (fibres, pigment, water) contribute to formation of the paper sheet and determine the retention of the pigment. The term retention refers to the retention of all inorganic substances in the paper during production.

In addition to the pigment and fibres used as feedstock, auxiliaries and additives are generally also used. These may affect the mechanisms of interaction between the fibres, the pigment and the water.

A number of titanium dioxide pigments exists for applications in decorative laminating paper. Alongside the most important properties, such as retention and opacity (hiding power), the greying resistance also plays a decisive role.

It is generally known that titanium dioxide is photochemically active. When exposed to UV radiation in the presence of moisture, decorative laminating paper pigmented with titanium

dioxide displays increasing greying. To avoid this problem, the surface of the pigments is treated with various substances, for instance with Al_2O_3 aquate and a colourless metal phosphate (US 3 926 660), with zinc phosphate (US 5 114 486), with cerium phosphate and aluminium phosphate (GB 2 042 573), or only with aluminium phosphate (EP 0 753 546 A2).

5 DE 15 92 873 describes a method for improving the light-fastness of pigments, where calcination at 600 °C is performed following coating with magnesium silicate.

A TiO_2 pigment with improved retention properties, having a core coated with consecutive layers of aluminium oxide phosphate, aluminium oxide and magnesium oxide, is presented in EP 0 713 904 B1.

10 However, when using pigments produced by these methods in laminates, the improvement in opacity is accompanied by a deterioration in greying resistance.

Therefore, the object of the present invention is to offer a method capable of producing pigments with high hiding power and simultaneously high greying resistance for use in decorative laminating papers.

The object is solved by subjecting a titanium dioxide pigment to a surface treatment process characterised by the following steps:

- a) Preparation of an aqueous suspension of titanium dioxide base material,
 - 20 b) Addition of a phosphorus compound,
 - c) Addition of a titanium compound,
 - d) Addition of an aluminium compound,
 - e) Adjustment of the pH value of the suspension to a pH value of 8 to 10, preferably 8.5 to 9.5,
 - 25 f) Addition of a magnesium compound,
 - g) Stabilisation of the pH value of the suspension in the range from 8 to 10, preferably 8.5 to 9.5,
 - h) Separation of the TiO_2 pigment by filtration, followed by washing, drying and milling of the pigment.
- 30 Other advantageous versions of the method are described in the sub-claims.

The object of the invention is, therefore, a method for the surface treatment of titanium dioxide pigments that results in pigments with high hiding power and high retention with simultaneously high greying resistance, as well as a pigment with these properties and the use of this pigment in the production of decorative laminating paper.

Surprisingly, it was found that the addition of a titanium compound during the inorganic surface treatment of the pigment with phosphorus and aluminium compounds is capable of achieving both high opacity and very good greying resistance.

5 The surface treatment process is based on TiO_2 base material, preferably produced by the chloride process. The term TiO_2 base material refers to the raw TiO_2 pigment prior to post-treatment. The base material can first be milled, for example in a wet-milling process. A dispersant is preferably added during wet-milling. The milled base material is used to prepare an aqueous suspension. This suspension can be basic or acidic and is preferably basic with
10 a pH value of 9 to 11. The method is performed at a temperature of less than 70°C , preferably at 55 to 65°C .

A phosphorus compound is added to the suspension in a quantity of 0.4 to 6.0% by weight, preferably 1.0 to 4.0% by weight, calculated as P_2O_5 , referred to TiO_2 base material.

Particularly good results are obtained with P_2O_5 contents of 1.6 to 2.8% by weight, referred to
15 the base material. Suitable phosphorus compounds are preferably inorganic phosphorus compounds, such as alkali phosphates, ammonium phosphate, polyphosphates, phosphoric acid or, where appropriate, mixtures of these compounds. Other inorganic phosphorus compounds can, however, also be used.

Moreover, a titanium compound is added, e.g. titanyl sulphate, titanyl chloride or another
20 hydrolysable titanium compound, or mixtures of these compounds. The quantity of titanium compound added is 0.1 to 3.0% by weight, preferably 0.1 to 1.5% by weight, and particularly 0.1 to 1.0% by weight, calculated as TiO_2 , referred to TiO_2 base material in the suspension.

An aluminium compound of acidic or basic character is subsequently added to the suspension. Particularly suitable as an acidic aluminium compound is aluminium sulphate,
25 although this is not to be taken as a restriction. Suitable alkaline aluminium compounds include sodium aluminate, alkaline aluminium chloride, alkaline aluminium nitrate or other alkaline aluminium salts, or mixtures of these compounds.

The suspension will customarily be stirred for about 30 minutes following each addition, in order to achieve homogenisation. It is, however, also possible to add the titanium compound
30 and the aluminium compound simultaneously.

In a special embodiment of the method, an acid or a base, or a second aluminium compound, is added in parallel with the aluminium compound, in order to maintain a constant pH value in the range from 2 to 10, preferably in the range from 4 to 9 and particularly in the range from 6 to 8. In a particularly advantageous version of the method, the pH value is
35 controlled by the balanced, parallel addition of sodium aluminate and HCl. A further procedure consists in keeping the pH value constant by means of the controlled addition of

aluminium sulphate and sodium aluminate.

The suspension is subsequently adjusted to a pH value of 8 to 10, preferably 8.5 to 9.5. A person skilled in the art adjusts the pH value in the customary manner with the help of appropriate acidic or alkaline compounds. The alkalis used for this purpose include, for example, alkaline aluminium salts, such as sodium aluminate, alkaline aluminium chloride or alkaline aluminium nitrate, or bases, such as sodium hydroxide solution or ammonia, or a combination of these alkalis.

The total quantity of aluminium added to the suspension by way of the various aluminium compounds is 2.0 to 7.5% by weight, preferably 3.5 to 7.5% by weight, calculated as Al_2O_3 , referred to TiO_2 base material.

0.1 to 1% by weight, preferably 0.2 to 0.5% by weight, of a magnesium compound is then added, calculated as MgO and referred to TiO_2 base material. Suitable for use as the magnesium compound are water-soluble magnesium salts, such as magnesium sulphate, magnesium chloride and other magnesium salts, as well as mixtures of these compounds.

The pH value should be maintained at 8 to 10, preferably at 8.5 to 9.5, with the help of appropriate alkaline media, if necessary.

The post-treated TiO_2 pigment is subsequently separated from the suspension by filtration, and the resultant filter cake is washed.

To further improve the greying resistance, the pigment can additionally be treated with nitrate at a concentration of up to 1.0% by weight NO_3 in the finished pigment.

Moreover, the final pH value may be set by adding a suitable substance or a combination of suitable substances. The pH value is controlled by means of the degree of acidity and the added quantity of the substance. In principle, all compounds may be used which do not impair the optical pigment properties, which are temperature resistant during the final pigment drying or pigment milling and which can be added to the filter paste, into the dryer or during steam jet milling. For instance, acids like sulphuric acid, nitric acid, hydrochloric acid or citric acid or acidic salts like chlorides, sulfates or the like are suitable if they comply to the conditions specified.

Nitrate compounds are particularly suitable. By utilizing sodium nitrate the final pH value comes to more than 9. Yet, the decrease of the pH value can be achieved by the use of acidic nitrate compounds or a combination of acidic and non-acidic nitrate compounds as for instance aluminium nitrate, a combination of aluminium nitrate and sodium nitrate, a combination of aluminium nitrate and nitric acid and so forth. For example, the addition of aluminium nitrate in a quantity of 0.4% by weight calculated as NO_3 in the filter paste results in a lowered final pH value of about 8.

Finally, the pigment is dried and milled.

5 In comparison with the reference pigments, the pigment produced according to this method displays improved hiding power and improved greying resistance in the laminate, as well as good retention, and is outstandingly suitable for use in decorative laminating paper.

Examples:

10 An example of the invention is described below. Unless otherwise stated, the quantity data refer to TiO_2 base material in the suspension.

Example 1

After sand-milling, a suspension of titanium dioxide from the chloride process with a TiO_2 concentration of 400 g/l is adjusted to a pH value of 10 with NaOH at 60 °C. 2.4% by weight P_2O_5 are added to the suspension in the form of disodium hydrogenphosphate solution while stirring. The solution is added over a period of 60 minutes. After stirring for 30 minutes, 0.2% by weight TiO_2 are then added in the form of titanyl sulphate solution. This is followed by further stirring for 30 minutes. In the next step, 2.7% by weight Al_2O_3 are mixed into the suspension in the form of acidic aluminium sulphate solution within 30 minutes. After stirring for 30 minutes, the acidic suspension is set to a pH value of 9.0 with the help of an alkaline sodium aluminate solution in a quantity of 3.7% by weight, calculated as Al_2O_3 . The solution is added over a period of 40 minutes. After stirring for 30 minutes, 0.5% by weight MgO are added in the form of magnesium sulphate solution. After further stirring for 30 minutes the suspension is set to a pH value of 9 with NaOH.

25 After being stirred for a further 2 hours, the post-treated TiO_2 suspension is filtered and washed. Following the addition of 0.25% by weight NO_3 in the form of NaNO_3 , referred to TiO_2 pigment, the washed filter paste is dried in a spray drier and subsequently steam-milled.

Comparative example 1

30 The pigment is produced in a manner comparable to that described in Example 1, except that titanyl sulphate and magnesium sulphate are not components of the post-treatment. While stirring, 2.4% by weight P_2O_5 in the form of disodium hydrogenphosphate solution are added to the sand-milled TiO_2 suspension (400 g/l TiO_2), which has a temperature of 60 °C and a pH value of 10. In the next step, 3.0% by weight Al_2O_3 are mixed into the suspension in the form of acidic aluminium sulphate solution. The acidic suspension is set to a pH value of 7.2 with the help of an alkaline sodium aluminate solution in a quantity of 3.4% by weight,

calculated as Al_2O_3 . The further processing steps (filtration, washing, nitrate treatment, drying, milling) are the same as in Example 1.

Comparative example 2

- 5 The pigment is produced in a manner comparable to that described in Example 1, except that titanyl sulphate is not a component of the post-treatment.

While stirring, 2.4% by weight P_2O_5 in the form of disodium hydrogenphosphate solution are added to the sand-milled TiO_2 suspension (400 g/l TiO_2), which has a temperature of 60 °C and a pH value of 10. In the next step, 2.6% by weight Al_2O_3 are mixed into the suspension
10 in the form of acidic aluminium sulphate solution. The acidic suspension is set to a pH value of 9.2 with the help of an alkaline sodium aluminate solution in a quantity of 3.0% by weight, calculated as Al_2O_3 . This is followed by the addition of 0.5% by weight MgO in the form of magnesium sulphate solution. NaOH is used to set a pH value of 9. The further processing steps are the same as in Example 1 and Comparative example 1.

15

Test methods

The titanium dioxide pigments produced in this way were incorporated into decorative laminating paper based on melamine resin and subsequently tested with regard to their optical properties and greying resistance in pressed laminates. To this end, the titanium
20 dioxide pigment to be tested was incorporated into cellulose, and sheets with a sheet weight of roughly 100 g/m² and a TiO_2 content of about 40% by mass were produced.

a) Laminate production (laboratory scale)

A 36.5% aqueous pigment suspension made of 146 g titanium dioxide pigment and 254 g tap
25 water is prepared. Testing is based on 30 g pulp (oven-dry). The corresponding quantity of pigment suspension is adapted to the retention and the required ash content, $40 \pm 1\%$ in this case, and the grammage, 100 ± 1 g/m² in this case. A person skilled in the art is familiar with the procedure and the auxiliaries used.

The ash content (titanium dioxide content) of a sheet and the retention of the pigment are
30 subsequently determined. The ash content is determined by incinerating a defined weight of the produced paper in a rapid incinerator at 900 °C. The TiO_2 content by mass (equivalent to the ash content) can be calculated by weighing the residue.

The retention is defined as the capacity to retain all inorganic substances in the sheet of paper on the wire screen of the paper-making machine. The "one-pass retention" indicates
35 the percentage retained during a single feeding step to the paper-making machine. The ash content in percent referred to the percentage by mass of the pigment used relative to the

total solids in the suspension yields the retention.

The further processing of the paper encompasses its impregnation and pressing into laminates. The sheet to be impregnated with resin is immersed in a resin solution and pre-condensed for 25 seconds at 130 °C in a recirculating-air drying oven. Impregnation is performed a second time in similar manner, where the dwell time in the drying oven is 110 seconds. The sheet has a residual moisture content of 4 to 6% by weight. The condensed sheets are combined into stacks with phenolic resin-impregnated core papers, and white and black underlay paper.

The laminate structure used for the test comprised 9 layers: décor sheet, décor sheet, core paper, core paper, black underlay, core paper, core paper, black/white underlay, décor sheet.

The stacks are pressed for 300 seconds with the help of a Wickert Type 2742 laminating press at a temperature of 140 °C and a pressure of 90 bar.

b) Testing

The optical properties and the greying resistance of the laminates were measured using commercially available equipment (spectrophotometer, Xenotest weathering machine).

In order to assess the optical properties of laminates, the optical values (CIELAB L^* , a^* , b^*) to DIN 6174 are measured with the help of the ELREPHO® 3000 colorimeter over white and black underlay. The opacity is a measure of the light transmission of the paper. The following parameters were selected as a measure of the opacity of the laminates: CIELAB L^*_{black} , the brightness of the laminates measured over black underlay paper, and the opacity value L [%] = $Y_{black}/Y_{white} \times 100$, determined from the Y-value measured over black underlay paper (Y_{black}) and the Y-value measured over white underlay paper (Y_{white}).

The values are measured using a spectrophotometer (ELREPHO® 3000).

To assess the greying resistance (light-fastness) of the titanium dioxide pigments or titanium dioxide pigment blends, the corresponding laminate samples are exposed in a XENOTEST® 150S. The side of the laminate on which two papers are laminated together is measured for the assessment. The CIELAB L^* , a^* and b^* optical values to DIN 6174 are measured before and after 96 hours of exposure in the XENOTEST® 150S. The light source is a xenon-arc lamp. The temperature inside the device is 23 ± 3 °C, the relative humidity being $65 \pm 5\%$. The samples are rotated during the exposure cycle. Both $\Delta L^* = L^*_{before} - L^*_{after}$ and $\Delta E^* = ((\Delta L^*)^2 + (\Delta a^*)^2 + (\Delta b^*)^2)^{1/2}$ are stated as a measure of the greying resistance.

Test results:

The test results for the laminates produced using the pigment according to the invention from the Example 1 and the pigments from Comparative examples 1 and 2 are summarised in the Table. All three examples and comparative examples are set to the same ash content.

It can be seen that the laminate produced using the pigment according to the invention

5 (Example 1) is characterised by both high opacity (L^*_{black} and L) and high greying resistance (ΔL^* and ΔE^*). In contrast, the laminates produced using the two reference pigments 1 and 2 display significantly lower values for either opacity (Comparative example 1) or greying resistance (Comparative example 2). In addition, the retention of the paper produced using the pigment according to the invention was improved relative to Comparative example 2.

Table

5	CIELAB optical values							Opacity	Ash content [% by wt.]	Retention (one-pass) [% by wt.]	Greying	
	over white			over black			resistance				ΔL^*	ΔE^*
	L*	a*	b*	L*	a*	b*	L [%]					
10	Example 1	93.1	-1.2	2.6	90.9	-1.3	0.5	94.1	40.4	74	1.0	1.5
	Comparative											
	example 1	92.9	-1.2	2.8	90.2	-1.3	0.5	92.8	40.6	75	1.1	1.6
	Comparative											
15	example 2	93.2	-1.2	2.5	90.9	-1.2	0.4	93.7	40.5	72	1.3	1.8

The grammage was 100 g/m² in all tests.

CLAIMS

1. Method for the surface treatment of a titanium dioxide pigment, characterised by the following steps:
 - a) Preparation of an aqueous suspension of titanium dioxide base material,
 - b) Addition of a phosphorus compound,
 - c) Addition of a titanium compound,
 - d) Addition of an aluminium compound,
 - e) Adjustment of the pH value of the suspension to a value of 8 to 10, preferably 8.5 to 9.5,
 - f) Addition of a magnesium compound,
 - g) Stabilisation of the pH value of the suspension in the range from 8 to 10, preferably 8.5 to 9.5,
 - h) Separation of the TiO_2 pigment by filtration, followed by washing, drying and milling of the pigment.
2. Method according to Claim 1, characterised in that the added phosphorus compound is an inorganic phosphorus compound.
3. Method according to Claim 2, characterised in that the inorganic phosphorus compound is selected from the group comprising alkali phosphates, ammonium phosphates, polyphosphates, phosphoric acid and, where appropriate, mixtures of these compounds.
4. Method according to one or more of Claims 1 to 3, characterised in that the quantity of phosphorus compound added is 0.4 to 6.0% by weight, preferably 1.0 to 4.0% by weight and particularly 1.6 to 2.8% by weight, calculated as P_2O_5 , referred to TiO_2 base material in the suspension.
5. Method according to Claim 1, characterised in that the titanium compound added is selected from the group comprising titanyl sulphate, titanyl chloride and other hydrolysable titanium compounds, as well as mixtures of these compounds.
6. Method according to Claim 1 or 5, characterised in that the quantity of titanium compound added is 0.1 to 3.0% by weight, preferably 0.1 to

1.5% by weight and particularly 0.1 to 1.0% by weight, calculated as TiO_2 , referred to TiO_2 base material in the suspension.

- 5 7. Method according to Claim 1, characterised in that
the aluminium compound added is of either alkaline or acidic character.
8. Method according to one or more of Claims 1 to 7, characterised in that,
during the addition of the aluminium compound, the pH value is maintained constant
by the simultaneous addition of an acid or a base, the pH value being in the range
10 from 2 to 10, preferably in the range from 4 to 9 and particularly in the range from 6 to
8.
- 15 9. Method according to one or more of Claims 1 to 7, characterised in that
an acidic aluminium compound is added in process step d), and the adjustment of the
pH value according to process step e) is accomplished with the help of an alkaline
aluminium compound or a combination of an alkaline aluminium compound and a
base.
- 20 10. Method according to Claim 7 and/or Claim 9, characterised in that
the alkaline aluminium compound is selected from the group comprising sodium
aluminate, alkaline aluminium chloride, alkaline aluminium nitrate and other alkaline
aluminium salts, as well as mixtures of these compounds.
- 25 11. Method according to one or more of Claims 1, 7, 8, 9 and 10, characterised in that
the total quantity of the aluminium compounds added is 2.0 to 7.5% by weight,
preferably 3.5 to 7.5% by weight, calculated as Al_2O_3 , referred to TiO_2 base material.
- 30 12. Method according to Claim 1, characterised in that
the magnesium compound added is selected from the group comprising water-
soluble magnesium salts, such as magnesium sulphate, magnesium chloride and
other water-soluble magnesium salts, as well as mixtures of these compounds.
- 35 13. Method according to Claim 1 or 12, characterised in that
the quantity of magnesium compound added is 0.1 to 1.0% by weight, preferably 0.2
to 0.5% by weight, calculated as MgO , referred to TiO_2 base material in the

suspension.

14. Method according to one or more of Claims 1 to 13, characterised in that
the pigment is treated with a substance or a combination of substances in order to
influence the final pH value whereas the final pH value is controlled by the acidity and
the quantity of the added substance.

15. Method according to Claim 14, characterised in that
the added substances are nitrate compounds, especially aluminium nitrate.

16. Method according to one or more of Claims 1 to 15, characterised in that
the finished pigment which had been treated with nitrate contains up to 1.0% by
weight NO_3

17. Method according to one or more of Claims 1 to 16, characterised in that
the titanium dioxide base material is first milled.

18. Method according to Claim 17, characterised in that
the titanium dioxide base material is wet-milled and, where appropriate, a dispersant
is added during milling.

19. Surface-treated titanium dioxide pigment, obtainable by the method according to one
or more of Claims 1 to 18.

20. Use of the surface-treated titanium dioxide pigment according to Claim 19 in the
production of decorative laminating paper.