



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 218/08, 14/06, C07C 409/00	A1	(11) International Publication Number: WO 98/18835 (43) International Publication Date: 7 May 1998 (07.05.98)
(21) International Application Number: PCT/EP97/05919 (22) International Filing Date: 21 October 1997 (21.10.97) (30) Priority Data: 96203017.7 30 October 1996 (30.10.96) EP (34) Countries for which the regional or international application was filed: NL et al. (71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): O. Boen Ho [NL/NL]; Koekoekstraat 14, NL-3514 CW Utrecht (NL). MALTHA, Annemarieke [NL/NL]; Zesakkers 2102, NL-6605 TG Wijchen (NL). WESTMIJZE, Hans [NL/NL]; Burgemeester Boreellaan 1, NL-7437 BB Bathmen (NL). ALFERINK, Petrus, Johannes, Theodorus [NL/NL]; Sint Anfriedlaan 4, NL-6931 GD Westervoort (NL). (74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Patent Dept. (Dept. APTA), P.O. Box 9300, NL-6800 SB Arnhem (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PROCESS TO MAKE INITIATOR COMPOSITIONS COMPRISING POLYVINYL ALCOHOL AND SURFACTANT (57) Abstract A process to make suspensions of thermally labile organic compounds in water is provided. The suspensions comprise at least one polyvinyl alcohol with an average degree of hydrolysis from 60 to 80 % and at least one non-ionic surfactant with an average HLB value from 14.5 to 20.0, and are suitable for use in polymerization processes. The organic compounds in the suspensions preferably have a particle size distribution where the d_{90} is less than 20 μm. The particle size distribution of the thermally labile organic compound and the specific ingredients enable the production of chemically as well as physically storage stable suspensions that combine a high compound concentration and a low viscosity. When used in vinyl chloride polymerization processes, the suspensions ensure a low fish eye level and good electrical properties, without adversely affecting the PVC's porosity and bulk density.		