

Description

This invention relates to improvements in laser marking of plastic articles, and is more particularly although not exclusively concerned with laser marking of articles, such as thin plastic slides, with a bar code.

It is customary to provide bar codes on dried, slide-like test elements used in analyzers to test for analytes of liquids. The bar code information provides machine-readable information such as the type of assay for that element, and optionally, calibration data needed to calibrate that particular test element.

The test element body is typically made from a plastic material, such as polystyrene. This underlying material is not an easy material to print on. Thus, conventional printing techniques have been difficult to use as they do not always provide a sufficiently contrasting color. A preferred format is to use a white test element, hereinafter "slide", with a dark or black ink. Although flexographic printing of a black ink has been used, this process suffers the disadvantages of high cost, the need to print in continuous web format and possible voids in the printing.

Therefore, there has been a need prior to this invention to develop a method of marking the plastic slides by a technique other than printing.

Laser marking has been developed for articles in general, and is described, for example, in US-A-4323755 and US-A-4515867. However, there is a problem in applying this technique to plastic articles in general, and particularly to polystyrene articles. In particular, the coating which is to be ablated away to reveal the contrasting color of the native plastic underneath, is not readily ablatable without damaging the plastic material itself with the laser. This is because the contrasting color coating adheres so well to the plastic that the last molecules of the color do not readily ablate without unduly damaging the plastic. This is particularly a problem with certain plastic articles, such as polystyrene slides, which contain the dried reagents used to assay for liquid analytes. Furthermore, these plastic articles, if ablated so as to remove some of the plastic, will tend to flow and as a consequence become warped or distorted.

It is not entirely clear what the mechanism is for the tenacious binding of the contrast color coating to the plastic. It may be solvent attack of the plastic, inherent porosity of the plastic surface, or even a binding which is enhanced by the heat of the ablation process. It appears to occur whether or not the contrast color coating is solvent-based or aqueous-based.

Thus, prior to this invention it has been a problem to mark plastic articles by laser ablation techniques.

An additional problem arising from marking by laser ablation is the tendency of the laser process to cause redepositing of the contrast coating in other areas. For this reason, laser marking of lot numbers on bottles has in the past used large dark areas and an ablation in the middle of that area, so that the ablation debris falls onto the bordering dark area, rather than a white area. The disadvantage of this approach is that considerable area is wasted in the large dark area which is required.

Thus, a further problem has been to mark any substance with laser ablation, without leaving debris behind in white areas and without requiring large areas of dark borders.

In accordance with one aspect of the present invention, there is provided a method of preventing damage to a pigmented plastic article when ink on the article is ablated away to form an image, the method comprising the steps of:

- a) coating the plastic article with a colored coating comprising a binder and a contrasting color to that of the pigment of the plastic article, with a wet-laydown sufficient to give a dried thickness sufficient to produce a minimum print contrast of at least 0.75 compared to the color of the plastic article,
- b) drying the colored coating, and
- c) ablating away all of the colored coating in predetermined portions using a laser to form the image, characterized in that the plastic article is coated with an intermediate layer prior to being coated with the colored coating, the intermediate layer comprising binder and solvent which has a sufficient wet-laydown to provide a dried coating coverage of at least 1.5gm^{-2} .

Accordingly, is it an advantageous feature of the invention that markings such as bar code labelling can easily be placed on plastic articles using a laser.

It is a related advantageous feature of the invention that laser ablation can be used in such a process without distorting the plastic article.

It is a further advantageous feature that such ablation can be done without requiring a large dark border around the information area.

The present invention will now be described, by way of example only, with reference to the accompanying drawing in which:-

Figure 1 is an enlarged sectioned elevational view of a plastic article marked with a laser in accordance with the present invention;

Figure 2 is a fragmentary plan view of a marking made by a laser in accordance with the present invention;

and

Figure 3 is a plan view of a prior art laser marking included for comparison.

The invention is hereinafter described with respect to the preferred embodiments, wherein specific preferred coatings are applied to polystyrene slides used for liquid assay, using preferred lasers to ablate away dark coatings to form bar codes on a white support. In addition, it is applicable to any coating formulations, white or dark, applied to any plastic articles for selective removal by any type of laser to provide any kind of marking or image, provided the intermediate layer of the invention is used to keep from distorting the underlying plastic.

Thus, the preferred plastic articles to be bar-coded are polystyrene liquid assay slides. Highly preferred are the slides available from Eastman Kodak Company under the trademark "Ektachem". Such slides are preferably manufactured to be white in color, so that the bar code is formed in black as the contrasting color. However, the slide color can be formulated with a black pigment, so that the bar codes are formed from an applied layer which has a contrasting white color. It will be further apparent that the contrasting colors need not be pure white and pure black. Rather, what is important is that the colors be selected so that a minimum print contrast of at least 0.75 is provided between the bar code and what is exposed under the bar code coating. This "minimum print contrast" is determined by measuring the white reflectance and the dark reflectance on a reflectometer available from MacBeth under the tradename "PC Meter II", and using the formula:-

$$\text{print contrast} = \frac{(\text{white reflectance} - \text{dark reflectance})}{\text{white reflectance}}$$

Any dark coating can be applied onto the white slide to provide the material to be ablated by the laser, so long as the minimum print contrast noted above is achieved. Highly preferred are conventional black inks or coatings containing carbon black or a black dye. Both solvent-based and aqueous-based coatings are useful. In fact, one of the two layers can be either solvent or aqueous based and the other layer aqueous or solvent based, respectively. The dark coating can be applied to either completely cover the slide, or to only partially cover it. The coverage is not critical, provided that it provide a reflectance of the dark coating, when read at 700nm, which is less than about 5%. Excessive thicknesses (those greater than about 10gm⁻²) should be avoided, as these require so much more laser ablation to remove.

Because the black coatings are conventional, further details are unnecessary.

In accordance with the invention, an intermediate layer is applied between the plastic slide and the dark coating, which is of sufficient thickness that the ablation of the last-remaining dark coating at any one place, will ablate away at least some of the intermediate layer, without unduly distorting the underlying plastic. It is unimportant whether this intermediate layer is applied all at once or in layers, provided this thickness is achieved.

The actual minimum thickness required will vary, depending upon certain factors. In particular, the power and effectiveness of the laser which is used will vary with the thickness of the ablation which occurs - the more powerful the laser, the thicker the intermediate layer which might be required, since more of the intermediate layer may be ablated. Another factor is the ability of the intermediate layer to be ablated - if a binder is used which is more difficult to ablate, less thickness is required.

Using the preferred coating and laser described hereinafter, the preferred minimum thickness of the intermediate layer is that which provides a dry coverage of 1.5gm⁻². Highly preferred is a dry coverage of from 3 to 10gm⁻². This ensures that the dark coating is spaced sufficiently far from the plastic, and damage, if any, to the plastic from the laser is negligible.

In coating this layer, care must be taken to avoid causing the underlying plastic, particularly polystyrene, from curling. This is caused by the action of certain solvents, namely any solvent which will attack the plastic in question. For polystyrene, this means solvents which are non-alcoholic and non-aqueous need to be used with care. Highly preferred solvents for a solvent-based intermediate layer are ethyl acetate and n-propyl acetate, and these should be used in amounts which are less than about 20gm⁻².

Thus, the intermediate layer will comprise a binder, a solvent for the binder, and optionally a pigment comparable in color to that of the underlying plastic, for example, titanium dioxide. If a pigment is present, preferably it is present in amounts which range from one-half to twice the amount of binder. If no pigment is present, preferably the binder is transparent.

Highly preferred binders for the intermediate layer include cellulose nitrate, polyalkyl methacrylates such as poly(ethyl methacrylate), and copolyesters such as of diethylene glycol and phthalates such as dimethyl isophthalate and dimethyl sodiosulfisophthalate used alone or together. Preferred such copolyesters include those obtainable from Tennessee Eastman Company under the tradenames AQ55 and AQ29. The former of these also includes 1,4-cyclohexanedimethanol as an alcohol component. The binder can be a mixture of these, the ratio of which is not critical.

The above-mentioned preferred binders are also useful in an aqueous-based intermediate layer.

In applying the dark coating over the intermediate layer, if the solvent of the former is effective against the latter, care must be taken to not completely disturb the underlying layer. One method of doing this is to increase the coating thickness of the intermediate layer.

Thus, the intermediate layer can be considerably thicker than 5gm^{-2} , so long as the solvent coverage is less than that which is effective to cause curl, as noted above. As noted above, highly preferred maximum thicknesses of the intermediate layer are those which produce a maximum dry coverage of about 10gm^{-2} . More than this thickness suffers the disadvantages of too much flaking of the layer due to finishing operations, and too much drying time.

Optionally, a final clear protective coating of, for example, a layer of the binder used in the intermediate layer can be applied to the dark layer, preferably in amounts no greater than about 2.0gm^{-2} dried coverage.

Most preferably, the intermediate layer is dried before applying the dark coating. Any drying protocol can be used.

Any coating technique can be used to apply either or both the intermediate layer and the final colored layer which has the contrasting color. For example, conventional extrusion hopper coating, multi-slot dies, or multi-station hoppers can be used, preferably using a single pass to make each of the two layers.

Turning next to the laser which is used, any laser capable of ablating away the dark coating without ablating away all of the intermediate layer is useful. Highly preferred for such purposes are conventional pulsed lasers which deliver high energy in one or more pulses on a short period of time. Most preferred are those which deliver at least 4MW ($4\text{J}/\mu\text{s}$) over an area of about 1.2cm^2 , such as CO_2 lasers. Conventional TEA CO_2 lasers are well-known to be useful for this purpose, for example, as described in the article "Image Micro-machining with TEA CO_2 Lasers", Nelson et al, printed in 1975 in the SME Technical Paper identified as MR75-584. Still other useful lasers which deliver useful energy include pulsed YAG and scanning beam lasers such as continuous CO_2 or Q-switched YAG lasers.

The following examples further illustrate the invention. They are not in any way an exhaustive listing of the possibilities:

Example 1: Solvent-Based Pigmented Coating

A polystyrene slide having a thickness of about 1mm was manufactured so as to be white in color. Over this slide, an intermediate protective layer was coated as follows:

A wet-laydown of 12gm^{-2} was applied by an extrusion hopper of the following composition:

Function	Material	Wet Coverage (gm^{-2})
Solvent	Water	6
Pigment	TiO_2	2
Binder	Copolyester	
	AQ55	4

This was dried by heating in an oven at about 65°C for about 7.5min to give a dried coverage of about 6gm^{-2} . The resulting intermediate layer had a final dried coverage of about 6gm^{-2} .

Thereafter, a black layer was applied using a similar hopper, at a wet-laydown of about 3gm^{-2} of the following composition:

	Function	Material	Coverage (gm^{-2})
5	Solvent	isopropyl acetate	2
	Pigment	carbon black	0.4
	Binder	cellulose nitrate	0.6
10		and poly(ethyl methacrylate)	
	Other Addenda	a plasticizer	less than 0.1

15 This was dried by heating in an oven at about 65°C for about 3min to give a dried coverage of about 1gm^{-2} .
A protective overcoat of the same binder was applied to the black layer by applying a wet-laydown of 4gm^{-2} using a weight % concentration of 40% in isopropyl acetate. This was dried by heating in an oven at 65°C for 3min.

The finished article was then processed in a TEA CO₂ laser as follows:

20 It was mounted at a distance of about 305mm from the emitting point of the laser, with a bar code mask positioned in between. The mask exposed an area of about 1.2cm^2 . The laser was fired with a pulse of about 5MW (5J for about $1\mu\text{s}$). This was effective to remove all of the black layer on the slide where exposed, and some of the intermediate layer.

25 Example 2: Aqueous Based Coatings

The intermediate layer was applied in an identical fashion to that described in Example 1.

The colored (black) layer applied over the intermediate layer was applied as a wet-laydown coverage of 2.4gm^{-2} of the following composition:

	<u>Function</u>	<u>Material</u>	<u>Coverage</u> (gm^{-2})
30	Solvent	Water	1.8
35	Binder	copolyester AQ55	0.3
	Pigment	carbon black	0.3

40 Drying was done in an oven for about 3min at about 65°C to produce a final layer having a dried coverage of about 0.6gm^{-2} .

The above-described method is further illustrated in Figure 1. A plastic support, such as a white polystyrene slide 10, has an intermediate layer 12 coated thereon, and a black coating 14 is applied thereover. A laser, not shown, is used to send beams, indicated by arrows 16 and 18, through a mask, not shown, to remove portions 20, 22 from coating 14. In addition, all of the layer 12 underlying portion 20 was removed, but only a portion of layer 12 is removed by the laser under portion 22. Thus, some of the plastic 10 is exposed to the action of laser beam 16. However, the thickness t of layer 12 is selected to prevent any significant distortion of plastic 10. As noted, t is at least sufficient to give a dried coverage of about 1.5gm^{-2} .

45 In addition to the process noted above, it is a preferred option to ablate coating 14 in such a way as to minimize the amount of dust and dirt from coating 14 which falls back on to white or clear layer 12. In particular, there tends to be a scattering of the parts of coating 14 during laser ablation, which ends up as smudges, dirt or discoloration on the white or transparent layer 12. A process for correcting this is illustrated in Figure 2. Parts similar to those previously described bear the same reference numeral to which the distinguishing suffix A is appended.

55 In Figure 2, a black stripe 14A is applied as a coating to any suitable support 10A (with or without an intermediate layer as described above). The support is white, so that any debris which falls outside the black stripe will be noticeable. The bar code 30 or other marking is formed widthwise across the stripe, so that laser ablation using known techniques stops just outside the edges of the stripe. The laser operates in the prior art only for a distance x . However, in accordance with the invention, the mask used with the laser provides for additional ablation in the areas 32 and 34 outlined by a dotted line. This includes a dimension y which preferably

exceeds the height y' of the bar code 30. It is important that areas 32 and 34 at least touch stripe 14A, and preferably, overlap the stripe. As a result, any debris which might fall into area 32 or 34 is ablated away. Preferably, the width of each of areas 32 and 34 is about 4mm and the height y is about 6mm. For comparison, y' is typically only 4mm.

Figure 3 illustrates the prior art approach. The number "11" is ablated by laser in black strip 40, leaving large black border areas 42 all around the marking. As a result, the number cannot be formed close to the edge of the stripe, and much area is wasted in the borders.

Claims

1. A method of preventing damage to a pigmented plastic article (10; 10A) when ink on the article is ablated away to form an image, the method comprising the steps of:
 - a) coating the plastic article (10; 10A) with a colored coating (14; 14A) comprising a binder and a contrasting color to that of the pigment of the plastic article (10; 10A), with a wet-laydown sufficient to give a dried thickness sufficient to produce a minimum print contrast of at least 0.75 compared to the color of the plastic article (10; 10A),
 - b) drying the colored coating (14; 14A), and
 - c) ablating away all of the colored coating (14; 14A) in predetermined portions (20, 22; 30) using a laser (16, 18) to form the image, characterized in that the plastic article (10; 10A) is coated with an intermediate layer (12) prior to being coated with the colored coating (14; 14A), the intermediate layer (12) comprising binder and solvent which has a sufficient wet-laydown to provide a dried coating coverage of at least 1.5gm^{-2} .
2. A method according to claim 1, wherein the image is a bar-code.
3. A method according to claim 1 or 2, wherein the plastic article (10; 10A) is made of polystyrene.
4. A method according to any one of the preceding claims, wherein the plastic article (10; 10A) is a test element.
5. A method according to any one of the preceding claims, wherein the colored coating (14; 14A) of step a) contains a black pigment.
6. A method according to any one of the preceding claims, wherein the dried coating thickness of the intermediate layer (12) provides a coverage of between about 3gm^{-2} and about 10gm^{-2} .
7. A method according to any one of the preceding claims, wherein the binder of each of the coatings is a binder capable of being ablated by the laser.
8. A method according to claim 1, wherein the binder of the intermediate layer (12) comprises cellulose nitrate, polyalkyl methacrylate, or a copolyester of diethylene glycol and an isophthalate.
9. A method according to any one of the preceding claims, wherein the laser is operated at a power of at least 3.0MWcm^{-2} .

Patentansprüche

1. Verfahren zur Verhinderung der Beschädigung eines Kunststoffartikels (10; 10A), wenn Farbe auf dem Artikel unter Erzeugung eines Bildes abgetragen wird, wobei das Verfahren die folgenden Stufen umfaßt:
 - a) Beschichtung des Kunststoffartikels (10; 10A) mit einer farbigen Beschichtung (14; 14A) mit einem Bindemittel und einer Farbe, die zu der des Pigmentes des Kunststoffartikels (10; 10A) einen Kontrast aufweist, mit einer nassen Auftragsmenge, die ausreicht, um eine Trockendichte zu erzielen, die ausreicht, um einen Mindest-Druck-Kontrast von mindestens 0,75, im Vergleich zur Farbe des Kunststoffartikels (10; 10A) zu erzeugen,
 - b) Trocknen der farbigen Beschichtung (14; 14A) und
 - c) Abtragen der gesamten farbigen Beschichtung (14; 14A) in vorbestimmten Anteilen (20, 22; 30) unter Verwendung eines Lasers (16, 18) unter Erzeugung des Bildes,



exceeds the height y' of the bar code 30. It is important that areas 32 and 34 at least touch stripe 14A, and preferably, overlap the stripe. As a result, any debris which might fall into area 32 or 34 is ablated away. Preferably, the width of each of areas 32 and 34 is about 4mm and the height y is about 6mm. For comparison, y' is typically only 4mm.

Figure 3 illustrates the prior art approach. The number "11" is ablated by laser in black strip 40, leaving large black border areas 42 all around the marking. As a result, the number cannot be formed close to the edge of the stripe, and much area is wasted in the borders.

Claims

1. A method of preventing damage to a pigmented plastic article (10; 10A) when ink on the article is ablated away to form an image, the method comprising the steps of:
 - a) coating the plastic article (10; 10A) with a colored coating (14; 14A) comprising a binder and a contrasting color to that of the pigment of the plastic article (10; 10A), with a wet-laydown sufficient to give a dried thickness sufficient to produce a minimum print contrast of at least 0.75 compared to the color of the plastic article (10; 10A),
 - b) drying the colored coating (14; 14A), and
 - c) ablating away all of the colored coating (14; 14A) in predetermined portions (20, 22; 30) using a laser (16, 18) to form the image, characterized in that the plastic article (10; 10A) is coated with an intermediate layer (12) prior to being coated with the colored coating (14; 14A), the intermediate layer (12) comprising binder and solvent which has a sufficient wet-laydown to provide a dried coating coverage of at least 1.5gm^{-2} .
2. A method according to claim 1, wherein the image is a bar-code.
3. A method according to claim 1 or 2, wherein the plastic article (10; 10A) is made of polystyrene.
4. A method according to any one of the preceding claims, wherein the plastic article (10; 10A) is a test element.
5. A method according to any one of the preceding claims, wherein the colored coating (14; 14A) of step a) contains a black pigment.
6. A method according to any one of the preceding claims, wherein the dried coating thickness of the intermediate layer (12) provides a coverage of between about 3gm^{-2} and about 10gm^{-2} .
7. A method according to any one of the preceding claims, wherein the binder of each of the coatings is a binder capable of being ablated by the laser.
8. A method according to claim 1, wherein the binder of the intermediate layer (12) comprises cellulose nitrate, polyalkyl methacrylate, or a copolyester of diethylene glycol and an isophthalate.
9. A method according to any one of the preceding claims, wherein the laser is operated at a power of at least 3.0MWcm^{-2} .

Patentansprüche

1. Verfahren zur Verhinderung der Beschädigung eines Kunststoffartikels (10; 10A), wenn Farbe auf dem Artikel unter Erzeugung eines Bildes abgetragen wird, wobei das Verfahren die folgenden Stufen umfaßt:
 - a) Beschichtung des Kunststoffartikels (10; 10A) mit einer farbigen Beschichtung (14; 14A) mit einem Bindemittel und einer Farbe, die zu der des Pigmentes des Kunststoffartikels (10; 10A) einen Kontrast aufweist, mit einer nassen Auftragsmenge, die ausreicht, um eine Trockendichte zu erzielen, die ausreicht, um einen Mindest-Druck-Kontrast von mindestens 0,75, im Vergleich zur Farbe des Kunststoffartikels (10; 10A) zu erzeugen,
 - b) Trocknen der farbigen Beschichtung (14; 14A) und
 - c) Abtragen der gesamten farbigen Beschichtung (14; 14A) in vorbestimmten Anteilen (20, 22; 30) unter Verwendung eines Lasers (16, 18) unter Erzeugung des Bildes,



- dadurch gekennzeichnet, daß der Kunststoffartikel (10; 10A) mit einer Zwischenschicht (12) vor der Beschichtung mit der farbigen Beschichtung (14; 14A) beschichtet wird, wobei die Zwischenschicht (12) ein Bindemittel umfaßt sowie ein Lösungsmittel mit einer ausreichenden nassen Auftragsmenge, zur Erzeugung einer Trocken-Beschichtungsstärke von mindestens $1,5 \text{ gm}^{-2}$.
2. Verfahren nach Anspruch 1, bei dem das Bild ein Strichcode ist.
 3. Verfahren nach Anspruch 1 oder 2, bei dem der Kunststoffartikel (10; 10A) aus Polystyrol hergestellt ist.
 4. Verfahren nach einem der vorstehenden Ansprüche, bei dem der Kunststoffartikel (10; 10A) ein Testelement ist.
 5. Verfahren nach einem der vorstehenden Ansprüche, bei dem die farbige Beschichtung (14; 14A) der Stufe a) ein schwarzes Pigment enthält.
 6. Verfahren nach einem der vorstehenden Ansprüche, bei dem die trockene Beschichtungsstärke der Zwischenschicht (12) einer Beschichtungsstärke zwischen etwa 3 gm^{-2} und etwa 10 gm^{-2} entspricht.
 7. Verfahren nach einem der vorstehenden Ansprüche, bei dem das Bindemittel jeder der Beschichtungen ein Bindemittel ist, das durch den Laser abgetragen werden kann.
 8. Verfahren nach Anspruch 1, bei dem das Bindemittel der Zwischenschicht (12) Cellulosenitrat, Polyalkylmethacrylat oder einen Copolyester aus Diethylenglykol und einem Isophthalat umfaßt.
 9. Verfahren nach einem der vorstehenden Ansprüche, bei dem der Laser mit einer Leistung von mindestens $3,0 \text{ MWcm}^{-2}$ betrieben wird.

Revendications

1. Méthode pour empêcher la détérioration d'un article en plastique pigmenté (10 ; 10A) lorsque l'encre sur l'article est éliminée pour former une image, la méthode consistant à :
 - (a) recouvrir l'article en plastique (10 ; 10A) avec une couche colorée (14 ; 14A) comprenant un liant et une couleur qui contraste avec le pigment de l'article en plastique (10 ; 10A), par un dépôt humide suffisant pour obtenir une épaisseur de la couche sèche suffisante pour produire un contraste d'impression minimum d'au moins 0,75 par rapport à la couleur de l'article en plastique (10 ; 10A),
 - (b) sécher la couche colorée (14 ; 14A), et
 - (c) éliminer la couche colorée (14 ; 14A) sur des parties prédéterminées (20, 22, 30) avec un laser (16,18), pour former l'image,
 la méthode étant caractérisée en ce que l'article en plastique (10, 10A) est recouvert avec une couche intermédiaire (12) avant d'être recouvert avec la couche colorée (14 ; 14A), la couche intermédiaire (12) comprenant un liant et un solvant qui forment un dépôt humide suffisant pour obtenir une épaisseur de la couche sèche ayant un titre d'au moins $1,5 \text{ g/m}^2$.
2. Méthode selon la revendication 1 dans laquelle l'image est un code barres.
3. Méthode selon la revendication 1 ou 2 dans laquelle l'article en plastique (10 ; 10A) est en polystyrène.
4. Méthode selon l'une quelconque des revendications précédentes dans laquelle l'article en plastique (10, 10A) est un élément de test.
5. Méthode selon l'une quelconque des revendications précédentes dans laquelle la couche colorée (14, 14A) de l'étape a) contient un pigment noir.
6. Méthode selon l'une quelconque des revendications précédentes dans laquelle l'épaisseur de la couche intermédiaire sèche (12) a un titre compris entre 3 g/m^2 et 10 g/m^2 .
7. Méthode selon l'une quelconque des revendications précédentes dans laquelle le liant de chacune des couches est un liant qui peut être éliminé par laser.



8. Méthode selon la revendication 1 dans laquelle le liant de la couche intermédiaire (12) comprend du nitrate de cellulose, du polyméthacrylate d'alkyle, ou un copolyester de diéthylène glycol et un isophthalate.
- 5 9. Méthode selon l'une quelconque des revendications précédentes dans laquelle le laser est utilisé à une puissance d'au moins 3,0 MW/cm².

10

15

20

25

30

35

40

45

50

55