


A-18591/A/CGM 390Asymmetric aryl phosphites

The invention relates to novel phosphites, to the use thereof as stabilisers, to a novel phosphorochloridite as intermediate, and to compositions containing said phosphites.

A number of patent applications, eg. JP-A-54/039 455, JP-A-54/036 363, JP-A-54/055 043 and JP-A-62/086 036, disclose principally symmetrically substituted triaryl phosphites as stabilisers, and JP-A-54/041 948 uses these phosphites together with other stabilisers in synthetic resin compositions. One of the concrete examples given here is tris(2,4-di-tert-butyl-6-methylphenyl) phosphite. Phosphites containing at least one aryl radical are disclosed in JP-A-55/005 927, JP-A-54/163 938, US-A-4 348 308 and US-A-3 558 554. The aryl radical in US-A-3 558 554 is preferably tert-butyl-substituted p-cresyl. US-A-4 348 308 discloses, for example, compounds such as bis(2,4-di-tert-butylphenyl) cyclohexyl phosphite and bis(2-tert-butylphenyl) isodecyl phosphite. US-A-4 444 929 uses compounds such as bis(2-tert-butyl-4-methylphenyl) 2,6-di-tert-butyl-4-methylphenyl phosphite in stabiliser mixtures. Analogues of the intermediate for the preparation of the compounds according to the invention have already been disclosed in the literature. Thus, US-A-4 584 146 and US-A-4 444 929 disclose bis(2,6-di-tert-butyl-4-methylphenyl) phosphorochloridite as an intermediate in the preparation of phosphites. US-A-4 233 208 uses bis(2,6-di-tert-butyl-4-methylphenyl) phosphorochloridite and similar chlorides and hydroxides as stabilisers.

There continues to be a demand for effective stabilisers for organic materials which are sensitive to photoinduced and/or thermooxidative degradation.

The invention relates to compounds of the formula I





This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED


in which x is 1, 2 or 3, and,


if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl, halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, naphthyl, a radical of the



R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6, with the proviso that R¹ is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,

if x = 2, R¹ is C₂-C₁₈alkylene, C₂-C₁₈alkylene which is interrupted by -NR⁵-, -O- or -S-,



if x = 3, R¹ is C₄-C₁₂alkanetriyl or a  group in which m is 1-4.

C₁-C₃₀alkyl R¹ may be linear or branched and is, for example, methyl, ethyl, isomers of propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl, tetradecyl, heptadecyl, octadecyl, icosyl, tetracosyl or triacontyl. Alkyl R¹ is in particular C₁-C₂₄alkyl, very particularly C₁-C₁₈alkyl, preferably C₁-C₁₂alkyl, eg. C₁-C₄alkyl.

C₁-C₁₈alkyl R², R³, R⁴ and R⁵ may be linear or branched and are defined, for example, as for C₁-C₃₀alkyl R¹ apart from the corresponding number of carbon atoms. Preference is





given to C_1 - C_{12} alkyl, in particular C_1 - C_4 alkyl.

Halogen-substituted C_1 - C_{18} alkyl R^1 may be linear or branched and monosubstituted or polysubstituted, eg. monosubstituted to trisubstituted, in particular monosubstituted or disubstituted, and is, for example, chloromethyl, dichloromethyl, trichloromethyl, chloroethyl, dichloroethyl, chloropropyl, fluoromethyl, trifluoromethyl, trifluoroethyl, trifluoropropyl, etc.

-COOR²-substituted C_1 - C_{18} alkyl R^1 is, for example, methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl or octadecyl, each of which is substituted by methoxycarbonyl, ethoxycarbonyl, isomers of propoxycarbonyl, butoxycarbonyl, pentoxycarbonyl, hexyloxycarbonyl, heptyloxycarbonyl, ethylhexyloxycarbonyl, decyloxycarbonyl, dodecyloxycarbonyl, cyclohexyloxycarbonyl, or tolyloxycarbonyl, in particular by methoxycarbonyl or ethoxycarbonyl, and is preferably methyl or ethyl, in particular methyl, each of which is substituted by methoxycarbonyl, ethoxycarbonyl or in particular butoxycarbonyl.

-CONR³R⁴-substituted C_1 - C_{18} alkyl R^1 is, for example, methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl or octadecyl, each of which is substituted by dimethylaminocarbonyl, diethylaminocarbonyl, dibutylaminocarbonyl or ethylmethylaminocarbonyl, in particular dimethyl- or diethylaminocarbonyl, and is preferably methyl, ethyl or propyl, each of which is substituted by dimethylaminocarbonyl or diethylaminocarbonyl, in particular propyl which is substituted by dimethylaminocarbonyl.

CN-substituted C_1 - C_{18} alkyl R^1 is, for example, cyanomethyl, cyanoethyl, cyanopropyl, cyanobutyl, cyanopentyl, cyanoethyl, cyanoethyl, cyanoethyl, cyanoethyl, cyanoethyl or cyanoethyl, in particular cyanoethyl.

C_2 - C_{18} Alkyl R^1 which is interrupted by -O-, -S- or -NR⁵- units contain, for example, the structural units -CH₂-CH₂-O-, -CH₂-CH₂-S- or -CH₂-CH₂-NR⁵-. The -NR⁵-, -O- or -S- groups can occur once or more than once in the chain. Other examples of C_2 - C_{18} alkyl R^1 which is interrupted by -O-, -S- or -NR⁵- units are methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl or octadecyl, each of which is substituted by methoxy, ethoxy, propoxy, butoxy, methylthio, ethylthio, propylthio, butylthio, dimethylamino, diethylamino, dipropylamino, etc, in particular methoxy or ethoxy,

preferably ethyl which is substituted by methoxy.

C₅-C₁₂Cycloalkyl R¹, R², R³, R⁴ and R⁵ may be, for example, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclodecyl or cyclododecyl, preferably cyclopentyl or cyclohexyl, in particular cyclohexyl.

Phenyl-C₁-C₄alkyl R¹, R², R³, R⁴ and R⁵ are, for example, benzyl, 1-phenylethyl, 2-phenylethyl, 3-phenylpropyl, α-methylbenzyl, α,α-dimethylbenzyl, etc, preferably benzyl or 1-phenylethyl.


An aromatic radical R^1 is preferably phenyl.

Substituted phenyl R¹ preferably contains 1 to 3 substituents, in particular 1 or 2 substituents, and is, for example, chlorophenyl, dichlorophenyl, trichlorophenyl, fluorophenyl, difluorophenyl, tolyl, dimethylphenyl, mesityl, ethylphenyl, diethylphenyl, isopropylphenyl, tert-butylphenyl, benzylphenyl, phenylethylphenyl, di-t-butylphenyl, methyl-di-tert-butylphenyl, dodecylphenyl, methoxyphenyl, dimethoxyphenyl, ethoxyphenyl, hexyloxyphenyl, methoxyethylphenyl or ethoxymethylphenyl, in particular p-tert-butylphenyl. Alkyl and alkoxy as aryl substituents preferably have 1-4 carbon atoms and are, in particular, methyl, tert-butyl or methoxy, preferably tert-butyl.

An aromatic radical R^1 is in particular phenyl which is unsubstituted or substituted by an alkyl group.

Halogen is, in particular, chlorine, bromine or fluorine.

Of particular interest are compounds of the formula I in which, if $x = 1$, R^1 is C_1 - C_{30} alkyl, C_1 - C_{18} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, naphthyl, a radical of the formula




This Sheet Has Been Replaced





THIS SHEET HAS BEEN
REPLACED

if $x = 2$, R^1 is C_2 - C_{18} alkylene, C_2 - C_{18} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,




if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

Other particularly interesting compounds of the formula I are those in which, if $x = 1$, R^1 is C_1 - C_{24} alkyl, C_1 - C_{12} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, naphthyl, a radical of the



if $x = 2$, R^1 is C_2 - C_{12} alkylene, C_2 - C_{12} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,




are hydrogen or C_1 - C_4 alkyl, and,

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

Preference is given to compounds of the formula I in which, if $x = 1$, R^1 is C_1 - C_{20} alkyl, C_1 - C_8 alkyl which is substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_8 alkyl which is interrupted by $-O$ - or $-S$ -, C_3 - C_8 alkenyl, C_5 - C_8 cycloalkyl, phenyl which is unsubstituted



or substituted by C₁-C₁₂alkyl or phenyl-C₁-C₄alkyl, naphthyl, a radical of the formula



hydrogen or methyl, and R⁸ and R⁹ are hydrogen,


if $x = 2$, R^1 is C_7 - C_8 alkylene or C_7 - C_8 alkylene which is interrupted by $-NR^5$ - or $-O$ -, and,

if $x = 3$, R^1 is a $-(CH_2)_2-N-(CH_2)_2-$ radical.

Further interesting compounds of the formula I are those in which, if $x = 1$, R^1 is

C₁-C₁₈alkyl which is unsubstituted or substituted by halogen, -COOR², -CN or -NR³R⁴,

C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₆alkenyl, C₅-C₈cycloalkyl,

phenyl-C₁-C₄alkyl, a radical of the formula

if $x = 2$, R^1 is C_2-C_{12} alkylene, C_2-C_{12} alkylene which is interrupted by $-NR^5-$, $-O-$ or $-S-$,

or is a  $\text{N}-(\text{CH}_2)_2$ radical, and,

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_2-N-(CH_2)_2-$ group.

Preference is given to compounds of the formula I in which $x = 1$, R^1 is C_1 - C_{12} alkyl which is unsubstituted or substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_{12} alkyl which is interrupted by $-NR^5$, $-O-$ or $-S-$, or is phenyl- C_1 - C_4 alkyl or C_5 - C_7 cycloalkyl.




Preference is furthermore given to compounds of the formula I in which R^1 is C_1 - C_4 alkyl.

Particular emphasis should also be attached to compounds of the formula I in which R^1 is as defined above, but is not unsubstituted or C_1 - C_{12} alkyl-, halogen- or C_1 - C_4 alkoxy-substituted phenyl or naphthyl.

Also worthy of mention in particular are compounds of the formula I in which R^1 is C_1 - C_{18} alkyl, C_5 - C_7 cycloalkyl or phenyl- C_1 - C_4 alkyl, in particular C_1 - C_{18} alkyl.

The compounds of the formula I can be obtained by processes which are known per se in chemistry. DE-A-2 950 694 describes a process for the preparation of corresponding compounds by reacting a phosphorus trihalide, a phosphorous acid monoester dihalide or a phosphorous acid diester halide with a phenol in the presence of an alkali metal hydroxide or alkaline earth metal hydroxide.

The compounds according to the invention can accordingly be prepared by substituting the chlorine in the diaryl phosphorochloridite by an alcohol or a phenol in the presence of a base.



R^1 is as defined above.

In order to prepare dimeric and trimeric compounds of the formula I, the corresponding polyols are used.

The bases used can be organic bases or inorganic bases. Examples of organic bases are tertiary amines, eg. trimethylamine, triethylamine, N,N -dimethylaniline, N,N -diethylaniline or pyridine. Examples of inorganic bases are alkali metal hydroxides, for example sodium hydroxide or potassium hydroxide, or alkali metal carbonates, for example sodium carbonate or potassium carbonate.




The substitution reaction temperatures are, for example, from -30°C to $+150^{\circ}\text{C}$, preferably from -10°C to $+70^{\circ}\text{C}$.

Solvents which can be employed are aliphatic and aromatic, simple or halogenated hydrocarbons or ethers. Examples of suitable aromatic hydrocarbons are benzene, toluene and xylene, and an example of a suitable chlorinated aromatic hydrocarbon is chlorobenzene. Examples of aliphatic hydrocarbons which can be used as solvents are hexane, pentane and further petroleum ether fractions. Examples of suitable halogenated aliphatic hydrocarbons are methylene chloride and chloroform. Examples of suitable ethers are diethyl ether, dibutyl ether and tetrahydrofuran.

The diaryl phosphorochloridite (II) and the alcohol R^1OH are expediently employed in equivalent amounts. It is, however, also possible, for example, to use an excess of alcohol, for example 1.05-1.2 equivalents.

A further method of preparing compounds according to the invention is to condense 2 equivalents of 2,4-di-tert-butyl-6-methylphenol with one equivalent of a phosphorus compound $\text{R}^1\text{O-PCl}_2$ in the presence of an organic base.

The invention also relates to the compound of the formula II



and to the use thereof for the preparation of compounds of the formula I.

The preparation of phosphorochloridites is known to persons skilled in the art and is described in numerous publications. The novel phosphorochloridite of the formula II can be prepared by analogous processes. For instance, H.G. Cook et al., J. Chem. Soc. 1949, IV, 2921-2927, and A.J. Razumov et al., Chemical Abstracts 60, 1571g (1964), describe the preparation of corresponding chlorides by reacting phosphorus trichloride with alkanols in the presence of N,N-dimethylaniline or N,N-diethylaniline as acid acceptor. J.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED



Michalski et al., J. Chem. Soc. 1961, 4904, disclose a variant of this process in which the acid acceptor employed is a pyridine/diethylaniline mixture. Reactions of phosphorus trichloride with hindered phenols are disclosed in US-A-3 281 506 and US-A-4 584 146. H.G. Cook et al., J. Chem. Soc., 1949, IV, 2921-2927 indicate a further method of preparing phosphorochloridites analogous to the formula II. They react phosphorus trichloride with symmetrical trialkyl phosphites. A variant of this process is described in US-A-4 079 103.

Bis(2,4-di-tert-butyl-6-methyl) phosphorochloridite can also be prepared directly in the melt without solvents. This allows the preparation of the phosphites of the formula I without isolation of the intermediate.

The compounds of the formula I are highly suitable for stabilising organic materials against photoinduced, thermal and/or oxidative degradation. The invention therefore also relates to compositions comprising an organic material which is sensitive to degradation reactions of this type, and at least one compound of the formula I, and to the use of compounds of the formula I as stabilisers for organic materials against said types of degradation.

Examples of such materials are:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, polymethylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), low density polyethylene (LDPE) and linear low density polyethylene (LLDPE).
2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene-propylene copolymers, linear low density polyethylene (LLDPE) and its mixtures with low density polyethylene (LDPE), propylene-but-1-ene, propylene-isobutylene, ethylene-but-1-ene, ethylene-hexene, ethylene-methylpentene,



ethylene-heptene, ethylene-octene, propylene-butadiene, isobutylene-isoprene, ethylene-alkyl acrylate, ethylene-alkyl methacrylate, ethylene-vinyl acetate or ethylene-acrylic acid copolymers and their salts (ionomers) and terpolymers of ethylene with propylene and a diene, such as hexadiene, dicyclopentadiene or ethylenenorbornene; as well as mixtures of such copolymers and their mixtures with polymers mentioned in 1), for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers, LDPE/ethylene-acrylic acid copolymers, LLDPE/ethylene-vinyl acetate copolymers and LLDPE/ethylene-acrylic acid copolymers.

3a. Hydrocarbon resins (for example C₅-C₉) and hydrogenated modifications thereof (for example tackifiers).

4. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).

5. Copolymers of styrene or α -methylstyrene with dienes or acrylic derivatives, for example styrene-butadiene, styrene-acrylonitrile, styrene-alkyl methacrylate, styrene-butadiene-alkyl acrylate, styrene-maleic anhydride, styrene-acrylonitrile-methyl acrylate; high impact strength mixtures of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene-propylene-diene terpolymer; and block copolymers of styrene, for example styrene-butadiene-styrene, styrene-isoprene-styrene, styrene-ethylene/butylene-styrene or styrene-ethylene/propylene-styrene.

6. Graft copolymers of styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene, styrene and alkyl acrylates or methacrylates on polybutadiene, styrene and acrylonitrile on ethylene-propylene-diene terpolymers, styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate-butadiene copolymers, as well as mixtures thereof with the copolymers mentioned under 5), for instance the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

7. Halogen-containing polymers, such as polychloroprene, chlorinated rubber, chlorinated or chlorosulfonated polyethylene, copolymers of ethylene and chlorinated ethylene,



epichlorohydrin homo- and copolymers, in particular polymers from halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof, for example vinyl chloride-vinylidene chloride, vinyl chloride-vinyl acetate or vinylidene chloride-vinyl acetate copolymers.

8. Polymers derived from α,β -unsaturated acids and derivatives thereof, such as polyacrylates and polymethacrylates, polyacrylamides and polyacrylonitriles.

9. Copolymers from the monomers mentioned under 8) with each other or with other unsaturated monomers, for instance acrylonitrile-butadiene, acrylonitrile-alkyl acrylate, acrylonitrile-alkoxyalkyl acrylate or acrylonitrile-vinyl halide copolymers or acrylonitrile-alkyl methacrylate-butadiene terpolymers.

10. Polymers derived from unsaturated alcohols and amines, or acyl derivatives thereof or acetals thereof, such as polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallylmelamine; and their copolymers with olefins mentioned in 1) above.

11. Homopolymers and copolymers of cyclic ethers, such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

12. Polyacetals, such as polyoxymethylene and those polyoxymethylenes which contain comonomers, for example ethylene oxide; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

13. Polyphenylene oxides and sulfides, and mixtures thereof with styrene polymers or polyamides.

14. Polyurethanes derived from polyethers, polyesters or polybutadienes with terminal hydroxyl groups on the one hand and aliphatic or aromatic polyisocyanates on the other, and precursors thereof.

15. Polyamides and copolyamides which are derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, such as nylon 4, nylon 6, nylon 6/6, 6/10, 6/9, 6/12 and 4/6, nylon 11, nylon 12, aromatic polyamides obtained from



m-xylene, diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic and/or terephthalic acid and optionally an elastomer as modifier, for example poly-2,4,4-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide. Block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, for instance with polyethylene glycol, polypropylene glycol or polytetramethylene glycol. Further, EPDM- or ABS-modified polyamides or copolyamides; and polyamides condensed during processing ("RIM polyamide systems").

16. Polyureas, polyimides, polyamide-imides and polybenzimidazoles.

17. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, such as polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate and polyhydroxybenzoates as well as block polyether-esters derived from polyethers having hydroxyl end groups; also polycarbonate- or MBS-modified polyesters.

18. Polycarbonates and polyester carbonates.

19. Polysulfones, polyether sulfones and polyether ketones.

20. Crosslinked polymers derived from aldehydes on the one hand and phenols, urea or melamine on the other, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

21. Drying and non-drying alkyd resins.

22. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols, and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low inflammability.

23. Crosslinkable acrylic resins, derived from substituted acrylic esters, for example epoxy acrylates, urethane acrylates or polyester acrylates.

24. Alkyd resins, polyester resins or acrylate resins crosslinked with melamine resins, urea resins, polyisocyanates or epoxy resins.



25. Crosslinked epoxy resins derived from polyepoxides, for example from bisglycidyl ethers or from cycloaliphatic diepoxides.

26. Natural polymers, such as cellulose, natural rubber, gelatin and derivatives thereof which are chemically modified in a polymer-homologous manner, such as cellulose acetates, cellulose propionates and cellulose butyrates, or cellulose ethers, such as methylcellulose; and colophony resins and their derivatives.

27. Mixtures (polyblends) of polymers as mentioned above, for example PP/EPDM, polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO.

28. Naturally occurring and synthetic organic substances which are pure monomeric compounds or mixtures thereof, for example mineral oils, animal or vegetable fats, oils and waxes, or oils, waxes and fats based on synthetic esters (for example phthalates, adipates, phosphates or trimellitates), and blends of synthetic esters with mineral oils in any desired weight ratios, as used, for example, as spinning preparations, and aqueous emulsions thereof.

29. Aqueous emulsions of natural or synthetic rubbers, for example natural rubber latex or latexes of carboxylated styrene-butadiene copolymers.

The organic materials to be protected are preferably natural, semisynthetic or preferably synthetic organic materials. Particular preference is given to thermoplastic polymers, in particular PVC or polyolefins, for example polyethylene and polypropylene (PP).

The compositions according to the invention expediently contain the compounds of the formula I in amounts of from 0.01 to 10 % by weight, for example from 0.05 to 5 % by weight, preferably from 0.05 to 3 % by weight, but in particular from 0.1 to 2 % by weight. It is possible for the compositions to contain one or more compounds of the formula I, and the per cent by weight data relate to the total amount of these compounds. The calculation is based on the total weight of the organic material without the compounds of the formula I. Incorporation into the materials can be effected, for example, by mixing



in or applying the compounds of the formula I and, if desired, further additives by methods which are conventional in industry. If the materials are polymers, in particular synthetic polymers, incorporation can take place before or during moulding or by applying the dissolved or dispersed compounds to the polymer, if necessary with subsequent evaporation of the solvent. In the case of elastomers, these may also be stabilised as latexes. A further way of incorporating the compounds of the formula I into polymers is to add them before, during or immediately after the polymerisation of the corresponding monomers or before the crosslinking. The compounds of the formula I can be added as such or in encapsulated form (for example in waxes, oils or polymers). If added before or during the polymerisation, the compounds of the formula I can also act as regulators for the chain length of the polymers (chain terminators).

The compounds of the formula I or mixtures thereof can also be added to the plastics to be stabilised in the form of a masterbatch which contains these compounds, for example, in a concentration of from 2.5 to 25 % by weight.

Incorporation of the compounds of the formula I can expediently be effected by the following methods:

- as an emulsion or dispersion (for example to latexes or emulsion polymers)
- as a dry mix during mixing of the additional components or polymer mixtures
- by direct addition into the processing apparatus (for example extruder, internal mixer, etc)
- as a solution or melt.

Polymer compositions according to the invention can be used in various forms or converted into various products, for example as (into) films, fibres, tapes, moulding compositions, profiles or as binders for surface coatings, adhesives or adhesive cements.

As stated above, the organic materials to be protected are organic, preferably synthetic polymers. Particular preference is given to the protection of thermoplastic materials, in particular polyolefins. The excellent effectiveness of the compounds of the formula I as processing stabilisers (heat stabilisers) should be particularly emphasised. For this purpose, they are advantageously added to the polymer before or during processing thereof.



However, it is also possible to stabilise other polymers (for example elastomers) or lubricants or hydraulic fluids against degradation, for example photoinduced and/or thermooxidative degradation. Elastomers are given in the above list of possible organic materials.

Suitable lubricants and hydraulic fluids are based, for example, on mineral or synthetic oils or mixtures thereof. The lubricants are known to persons skilled in the art and are described in the relevant specialist literature, for example in Dieter Klamann, "Schmierstoffe und verwandte Producte" [Lubricants and Related Products] (Verlag Chemie, Weinheim, 1982), in Schewe-Kobek, "Das Schmiermittel-Taschenbuch" [The Lubricant Handbook] (Dr. Alfred Hüthig-Verlag, Heidelberg, 1974), and in "Ullmanns Enzyklopädie der technischen Chemie" [Ullmann's Encyclopaedia of Industrial Chemistry], Vol. 13, pages 85-94 (Verlag Chemie, Weinheim, 1977).

The invention also relates to the stabilisation of organic materials against oxidative, thermal and/or actinic degradation by adding or applying, as stabilisers, compounds of the formula I to this material.

In addition to the compounds according to the invention, the compositions according to the invention, in particular if they contain organic, preferably synthetic polymers, may also contain further conventional additives. Examples of such additives are:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-di-cyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-di-octadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol and 2,6-di-nonyl-4-methylphenol.

1.2. Alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone and 2,6-diphenyl-4-octadecyloxyphenol.

1.3. Hydroxylated thiodiphenyl ethers, for example



2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol),
4,4'-thiobis(6-tert-butyl-3-methylphenol) and 4,4'-thiobis(6-tert-butyl-2-methylphenol).

1.4. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)-dicyclopentadiene and bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl] terephthalate.

1.5. Benzyl compounds, for example,

1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, bis(3,5-di-tert-butyl-4-hydroxybenzyl) sulfide, isooctyl 3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithiol terephthalate, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) isocyanurate, dioctadecyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate, the calcium salt of monoethyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate and 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl) isocyanurate.

1.6. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide, 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-s-triazine and octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.7. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with monohydric or polyhydric alcohols, for example with methanol, octadecanol, 1,6-hexanediol, neopentyl



glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate and N,N'-bis(hydroxyethyl)oxalamide.

1.8. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with monohydric or polyhydric alcohols, for example with methanol, octadecanol, 1,6-hexanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxy)ethyl isocyanurate and N,N'-bis(hydroxyethyl)oxalamide.

1.9. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with monohydric or polyhydric alcohols, for example with methanol, octadecanol, 1,6-hexanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxy)ethyl isocyanurate and N,N'-bis(hydroxyethyl)oxalamide.

1.10. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid, for example N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine and N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example the 5'-methyl, 3',5'-di-tert-butyl, 5'-tert-butyl, 5'-(1,1,3,3-tetramethylbutyl), 5-chloro-3',5'-di-tert-butyl, 5-chloro-3'-tert-butyl-5'-methyl, 3'-sec-butyl-5'-tert-butyl, 4'-octoxy, 3',5'-di-tert-amyl and 3',5'-bis(α,α -dimethylbenzyl) derivatives.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octoxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted or unsubstituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoylresorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoylresorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate and hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl or isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl or butyl α -cyano- β -methyl-p-methoxycinnamate,



methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5 Nickel compounds, for example nickel complexes of 2,2'-thiobis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 complex or the 1:2 complex, if appropriate with additional ligands, such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of monoalkyl 4-hydroxy-3,5-di-tert-butylbenzylphosphonates, such as the methyl or ethyl ester, nickel complexes of ketoximes, such as 2-hydroxy-4-methylphenyl undecyl ketoxime, and nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, if appropriate with additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethylpiperidyl) sebacate, bis(1,2,2,6,6-pentamethylpiperidyl) sebacate, bis(1,2,2,6,6-pentamethylpiperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensation product formed from 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensation product formed from N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)-hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-s-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl) nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl) 1,2,3,4-butanetetraoate and 1,1'-(1,2-ethanediyl)bis(3,3,5,5-tetramethylpiperazinone).

2.7. Oxalic acid diamides, for example 4,4'-di-octyloxyoxanilide, 2,2'-di-octyloxy-5,5'-di-tert-butyloxanilide, 2,2'-di-dodecyloxy-5,5'-di-tert-butyloxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxalamide, 2-ethoxy-5-tert-butyl-2'-ethyloxanilide and a mixture thereof with 2-ethoxy-2'-ethyl-5,4'-di-tert-butyloxanilide or mixtures of o-methoxy- and p-methoxy-disubstituted oxanilides and of o-ethoxy- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine and



2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxalamide, N-salicylal-N'-salicyloylhydrazine, N,N'-bis(salicyloyl)hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine, 3-salicyloylamino-1,2,4-triazole and bis(benzylidene)oxalodihydrazide.

4. Further phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythrityl diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythrityl diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythrityl diphosphite, tristearyl sorbitol triphosphite, tetrakis-(2,4-di-tert-butylphenyl) 4,4'-biphenylenediphosphonite and 3,9-bis(2,4-di-tert-butylphenoxy)-2,4,8,10-tetraoxa-3,9-diphosphaspiro[5.5]undecane.

5. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl and tridecyl esters, mercaptobenzimidazole, the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide and pentaerythrityl tetrakis(β -dodecylmercapto)propionate.

6. Benzofuranones and indolinones, as described, for example, in WO-A 80/01 566 and EP-A 415 887.

7. Polyamide stabilisers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

8. Basic costabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate and tin pyrocatecholate.

9. Nucleating agents, for example 4-tert-butylbenzoic acid, adipic acid and diphenylacetic acid.

10. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres,



asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black and graphite.

11. Other additives, for example plasticisers, lubricants, emulsifiers, pigments, optical brighteners, flameproofing agents, antistatic and blowing agents.

The examples below illustrate the invention in greater detail. Parts and percentages, as in the claims and the remainder of the description, are by weight, unless stated otherwise.

Example 1: Preparation of bis(2,4-di-tert-butyl-6-methylphenyl) phosphorochloridite

890.3 g (4 mol) of 2,4-di-tert-butyl-6-methylphenol, 4.2 g of dimethylformamide and 170.0 g of xylene are introduced into a four-neck flask which has been flushed with nitrogen and is fitted with a thermometer, dropping funnel, reflux condenser and distillation attachment. 274.9 g (2 mol) of phosphorus trichloride are added dropwise with stirring over the course of 1.5 hours at a temperature of 50°C. The reaction mixture is warmed to 130°C and refluxed at this temperature for 1 hour. The reaction mixture is kept at 120°C for 1 hour under a vacuum of 0.15 bar. Xylene is subsequently removed by distillation under a greater vacuum. After the vacuum has been broken using nitrogen, 959.5 g (1.9 mol) of the title compound are obtained as supercooled, yellow-orange, clear melt.

Purity: 98 % (determined using ^{31}P -NMR)

Purification: distillation at 204°C/0.0002 bar.

Example 2: Preparation of bis(2,4-di-tert-butyl-6-methylphenyl) methyl phosphite


300 g (1.36 mol) of 2,4-di-tert-butyl-6-methylphenol are introduced into a 1500 ml sulfonation flask fitted with thermometer, stirrer and reflux condenser, and the reactor is flushed with nitrogen. The mixture is warmed to 55°C in order to melt the phenol, and 1.5 g of dimethylformamide are added to the melt. 102.7 g (0.75 mol) of phosphorus trichloride are added dropwise over the course of 1.5 hours at the same temperature. The hydrochloric acid gas produced is neutralised by means of a 30 % aqueous sodium hydroxide solution. When the addition is complete, the reaction mixture is heated to 140°C over the course of 4 hours and stirred at this temperature for a further hour. A slight vacuum (0.55 bar) is then applied, and the mixture is stirred at 130°C for a further 4 hours. The clear yellow-orange melt obtained (= bis(2,4-di-tert-butyl-6-methyl) phosphoro-

chloridite) is then allowed to cool to about 80°C in a nitrogen atmosphere and is diluted with 500 ml of petroleum ether (80-100°C). The solution is cooled to -5°C, and 89.3 g (0.884 mol) of triethylamine are added over the course of 15 minutes. 32.8 g (1.02 mol) of methanol are then added dropwise over the course of 1 hour, during which the temperature rises to +5°C and the triethylamine hydrochloride precipitates. This mixture is allowed to warm slowly (about 1 hour) to room temperature with stirring. The precipitate is filtered off and the filtrate is evaporated, giving 328 g of phosphite as a yellow oil (purity determined by high pressure liquid chromatography [HPLC]: 94 %). Recrystallisation of the crude product from ethanol gives 262 g (77 % of theory) of the title compound in the form of a white powder having a melting point of 75-78°C.

Elemental analysis:

P calc.: 6.19 % found: 6.19 %

Examples 3-33: The compounds of Examples 3-33 are prepared analogously to the compound of Example 2 using the alcohol or phenol corresponding to the substituent R¹. The substituents and analytical data are shown in Table 1 below.



This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Table 1:










Example No.	R ₁	Yield [%]	Melting point [°C] Refractive index n_D^{20}	Elemental analysis % P calc. % P found	
3	C ₂ H ₅	65	91	6.02	6.01
4	n-C ₃ H ₇	60	57-58	5.86	5.70
5	i-C ₃ H ₇	64	104-105	5.86	5.80
6	n-C ₆ H ₁₃	99	high viscosity	5.43	5.49
7	$\text{C}_4\text{H}_9\text{-CH-CH}_2\text{-}$ C ₂ H ₅	95	1.5173	5.17	5.16
8	n-C ₁₂ H ₂₅	98	1.5107	4.73	4.71
9	i-C ₁₀ H ₂₁	95	high viscosity	4.94	4.99
10	i-C _{12/13} H _{25/27}	79	high viscosity	4.67	4.65
11	n-C ₁₈ H ₃₇	93	1.5061	4.19	4.19
12	i-C ₁₈ H ₃₇	91	1.5036	4.19	4.10
13	-(CH ₂) ₂ -OCH ₃	70	yellowish oil	5.69	5.44
14	-(CH ₂ CH ₂ -O) ₃ -C ₄ H ₉	97	1.5119	4.59	4.48
15	-(CH ₂) ₂ -S-C ₂ H ₅	98	high viscosity	5.39	5.18
16	-(CH ₂) ₂ -CF ₃	72	72	5.45	5.40
17	-(CH ₂) ₂ -CN	55	139	5.74	5.70
18	-(CH ₂) ₃ -N(CH ₃) ₂	65	yellowish oil	5.42	5.30
19	-CH ₂ CO ₂ - ⁿ C ₄ H ₉	96	high viscosity	5.16	4.90
20	benzyl	97	high viscosity	5.37	5.46
21	-(CH ₂) ₂ -C ₆ H ₅	74	78-80	5.24	5.18
22	cyclohexyl	64	high viscosity	5.45	5.22
23	phenyl	80	96-98	5.50	5.52

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Table 1 (continuation):


Example No.	R ₁	Yield [%]	Melting point [°C] Refractive index n_D^{20}	Elemental analysis % P calc. % P found	
24	naphthyl	83	101-103	5.05	4.97
25		55	154-156	5.00	4.99
26		97	high viscosity	4.50	4.53
27		99	1.5508	4.55	4.30
28		78	117-120	4.59	4.44
29		54	63-70	4.84	4.79
30		32	55-75	4.95	4.81
31		87	69-78	4.62	4.60
32		63	81-82	5.88	5.84
33		25	high viscosity	4.39	4.23

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Examples 34-36:



The compounds of Examples 34-36 are prepared analogously to the compound of Example 2 using the polyol corresponding to the substituent R^1 . Two equivalents of both bis(2,4-di-tert-butyl-6-methyl) phosphorochloridite and base are used for the compounds where $x = 2$, and three equivalents of bis(2,4-di-tert-butyl-6-methyl) phosphorochloridite and three equivalents of base are correspondingly used for the trimeric compound ($x = 3$). The substituents and analytical data are shown in Table 2 below.

Table 2:

Example No.	R_1	x	Yield [%]	Melting point [°C] Refractive index n_D^{20}	Elemental analysis % P calc. % P found	
34	$-(CH_2)_6-$	2	49	168	5.87	5.82
35	$-(CH_2)_2-O-(CH_2)_2-$	2	75	40-50 (amorphous)	5.94	5.36
36	$-(CH_2)_2-\text{HN}-(CH_2)_2-$	3	63	136-137	5.86	5.74

Example 37: Stabilisation of polypropylene

1.3 kg of polypropylene powder (melt flow index 3.2 g/10 min, measured at 230°C/2.16 kg) are mixed with 0.05 % of calcium stearate, 0.05 % of tetrakis[3,5-di-tert-butyl-4-hydroxyphenylpropionyloxymethyl]methane and 0.05 % of the stabiliser indicated in Table 3. This mixture is extruded at 100 rpm in an extruder having a barrel diameter of 20 mm and a length of 400 mm, the 3 heating zones being set at 260°C, 270°C and 280°C. The extrudate is cooled by drawing through a waterbath and is subsequently granulated. The granules obtained are extruded a second and third time. After these three extrusions, the melt flow index is measured at 230°C/2.16 kg. Small values indicate good stabilisation. The results are shown in Table 3.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

Table 3

Compound from Example No.	Melt flow index [g/10 min]
-	17.8
2	6.1
3	6.6
4	5.8
5	10.2
6	6.0
7	6.7
8	5.8
9	6.2
10	8.7
11	7.1
12	7.0
13	8.7
16	9.5

Example 38: Stabilisation of polyethylene

100 parts of unstabilised high-density polyethylene having a molecular weight of about 500,000 in powder form are mixed in the dry state with 0.05 part of tetrakis(3,5-di-tert-butyl-4-hydroxyphenylpropionyloxymethyl)methane and 0.1 part of the stabiliser indicated in Table 4. The mixture is kneaded for 50 minutes at 220°C and 50 rpm in a Brabender Plastograph. During this time, the kneading resistance is recorded continuously as torque. As a consequence of the crosslinking of the polymer, a rapid increase in torque occurs during the kneading time after initially remaining constant. The effectiveness of the stabilisers is apparent from an increase in the time before the torque increases. The values obtained are shown in Table 4.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED


Table 4

Compound from Example No.	Time before increase in torque [min]
-	5.0
2	16.5
3	12.0
4	12.0
5	13.0
6	15.0
7	22.5
8	17.0
9	19.0
10	16.5
11	14.0
12	17.0
13	13.5
16	15.0

This Sheet Has Been Replaced




THIS SHEET HAS BEEN
REPLACED





WHAT IS CLAIMED IS:

1. A compound of the formula I




in which x is 1, 2 or 3, and,

if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl, halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, or R₁ is naphthyl, a radical



R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6, with the proviso that R¹ is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,


if x = 2, R¹ is C₂-C₁₈alkylene, C₂-C₁₈alkylene which is interrupted by -NR⁵-, -O- or -S-,






if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

2. A compound of the formula I according to claim 1, in which, if $x = 1$, R^1 is C_1 - C_{30} alkyl, C_1 - C_{18} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, or R_1 is naphthyl, a radical of the formula




if $x = 2$, R^1 is C_2 - C_{18} alkylene, C_2 - C_{18} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,



if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.


3. A compound of the formula I according to claim 2, in which, if $x = 1$, R^1 is C_1 - C_{24} alkyl, C_1 - C_{12} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, or R_1 is naphthyl, a radical of the formula



if $x = 2$, R^1 is C_2 - C_{12} alkylene, C_2 - C_{12} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,





* C L M S *

or is a  radical, and R^{10} and R^{11} , independently of one another, are hydrogen or C_1 - C_4 alkyl, and,

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.


4. A compound of the formula I according to claim 3, in which, if $x = 1$, R^1 is C_1 - C_{20} alkyl, C_1 - C_8 alkyl which is substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_8 alkyl which is interrupted by $-O-$ or $-S-$, C_3 - C_8 alkenyl, C_5 - C_8 cycloalkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl or phenyl- C_1 - C_4 alkyl, or R_1 is naphthyl, a radical of the




if $x = 2$, R^1 is C_2 - C_8 alkylene or C_2 - C_8 alkylene which is interrupted by $-NR^5-$ or $-O-$, and,

if $x = 3$, R^1 is a $-(CH_2)_m-N-(CH_2)_m-$ radical.


5. A compound of the formula I according to claim 3, in which, if $x = 1$, R^1 is C_1 - C_{18} alkyl which is unsubstituted or substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5-$, $-O-$ or $-S-$, C_3 - C_6 alkenyl, C_5 - C_8 cycloalkyl,



* C L M S *



if $x = 2$, R^1 is $\text{C}_2\text{-C}_{12}$ alkylene, $\text{C}_2\text{-C}_{12}$ alkylene which is interrupted by $-\text{NR}^5$ -, $-\text{O}-$ or $-\text{S}-$,



if $x = 3$, R^1 is $\text{C}_4\text{-C}_{12}$ alkanetriyl or a $-(\text{CH}_2)_m\text{-N-}(\text{CH}_2)_m-$ group.

6. A compound according to claim 5, in which $x = 1$, R^1 is $\text{C}_1\text{-C}_{12}$ alkyl which is unsubstituted or substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$ or $-\text{NR}^3\text{R}^4$, $\text{C}_2\text{-C}_{12}$ alkyl which is interrupted by $-\text{NR}^5$ -, $-\text{O}-$ or $-\text{S}-$, or is phenyl- $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_5\text{-C}_7$ cycloalkyl.

7. A compound according to claim 1, in which R^1 is $\text{C}_1\text{-C}_{18}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl or phenyl- $\text{C}_1\text{-C}_4$ alkyl, in particular $\text{C}_1\text{-C}_{18}$ alkyl.

8. A compound according to claim 7, in which R^1 is $\text{C}_1\text{-C}_4$ alkyl.

9. A composition comprising (a) an organic material which is sensitive to oxidative, thermal and/or photoinduced degradation, and (b) at least one compound of the formula I according to claim 1.

10. A composition according to claim 9, in which component (a) is a natural, semisynthetic or synthetic polymer.

11. A composition according to claim 10, in which component (a) is a thermoplastic polymer.

12. A composition according to claim 10, in which component (a) is a polyolefin.


13. A composition according to claim 10, in which component (a) is a polyvinyl chloride,



a polyethylene or a polypropylene.

14. The use of a compound of the formula I according to claim 1 for stabilising organic materials which are sensitive to oxidative, thermal and/or actinic degradation.

15. The compound of the formula II



16. The use of the compound according to claim 15 for the preparation of a compound of the formula I according to claim 1.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED

03 DEC 1996

- 1 -


Asymmetric aryl phosphites

The invention relates to novel phosphites, to the use thereof as stabilisers, to a novel phosphorochloridite as intermediate, and to compositions containing said phosphites.

A number of patent applications, eg. JP-A-54/039 455, JP-A-54/036 363, JP-A-54/055 043 and JP-A-62/086 036, disclose principally symmetrically substituted triaryl phosphites as stabilisers, and JP-A-54/041 948 uses these phosphites together with other stabilisers in synthetic resin compositions. One of the concrete examples given here is tris(2,4-di-tert-butyl-6-methylphenyl) phosphite. Phosphites containing at least one aryl radical are disclosed in JP-A-55/005 927, JP-A-54/163 938, US-A-4 348 308 and US-A-3 558 554. The aryl radical in US-A-3 558 554 is preferably tert-butyl-substituted p-cresyl. US-A-4 348 308 discloses, for example, compounds such as bis(2,4-di-tert-butylphenyl) cyclohexyl phosphite and bis(2-tert-butylphenyl) isodecyl phosphite. US-A-4 444 929 uses compounds such as bis(2-tert-butyl-4-methylphenyl) 2,6-di-tert-butyl-4-methylphenyl phosphite in stabiliser mixtures. Analogues of the intermediate for the preparation of the compounds according to the invention have already been disclosed in the literature. Thus, US-A-4 584 146 and US-A-4 444 929 disclose bis(2,6-di-tert-butyl-4-methylphenyl) phosphorochloridite as an intermediate in the preparation of phosphites. US-A-4 233 208 uses bis(2,6-di-tert-butyl-4-methylphenyl) phosphorochloridite and similar chlorides and hydroxides as stabilisers.

There continues to be a demand for effective stabilisers for organic materials which are sensitive to photoinduced and/or thermooxidative degradation.

The invention relates to compounds of the formula I





03 DEC 1996

- 2 -


in which x is 1, 2 or 3, and,

if $x = 1$, R^1 is C_1 - C_{30} alkyl, C_1 - C_{18} alkyl substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$, $-\text{NR}^3\text{R}^4$ or by $-\text{CONR}^3\text{R}^4$, C_2 - C_{18} alkyl which is interrupted by $-\text{NR}^5$ -, $-\text{O}$ - or $-\text{S}$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, naphthyl, a radical of the



R_2 , R_3 , R_4 and R_5 , independently of one another, are hydrogen, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl or phenyl- C_1 - C_4 alkyl, R^6 is hydrogen, methyl, allyl or benzyl, R^7 is hydrogen or $-\text{OR}^9$, R^8 is hydrogen or methyl, R^9 is hydrogen or C_1 - C_{30} alkyl, R^{10} and R^{11} , independently of one another, are hydrogen or C_1 - C_8 alkyl, and n is 3-6, with the proviso that R^1 is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,


if $x = 2$, R^1 is C_2 - C_{18} alkylene, C_2 - C_{18} alkylene which is interrupted by $-\text{NR}^5$ -, $-\text{O}$ - or $-\text{S}$ -,



if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(\text{CH}_2)_m-\text{N}-(\text{CH}_2)_m-$ group in which m is 1-4.

C_1 - C_{30} alkyl R^1 may be linear or branched and is, for example, methyl, ethyl, isomers of propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl, tetradecyl, heptadecyl, octadecyl, icosyl, tetracosyl or triacontyl. Alkyl R^1 is in particular C_1 - C_{24} alkyl, very particularly C_1 - C_{18} alkyl, preferably C_1 - C_{12} alkyl, eg. C_1 - C_4 alkyl.

C_1 - C_{18} alkyl R^2 , R^3 , R^4 and R^5 may be linear or branched and are defined, for example, as for C_1 - C_{30} alkyl R^1 apart from the corresponding number of carbon atoms. Preference is



given to C_1 - C_{12} alkyl, in particular C_1 - C_4 alkyl.

Halogen-substituted C_1 - C_{18} alkyl R^1 may be linear or branched and monosubstituted or polysubstituted, eg. monosubstituted to trisubstituted, in particular monosubstituted or disubstituted, and is, for example, chloromethyl, dichloromethyl, trichloromethyl, chloroethyl, dichloroethyl, chloropropyl, fluoromethyl, trifluoromethyl, trifluoroethyl, trifluoropropyl, etc.

-COOR²-substituted C_1 - C_{18} alkyl R^1 is, for example, methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl or octadecyl, each of which is substituted by methoxycarbonyl, ethoxycarbonyl, isomers of propoxycarbonyl, butoxycarbonyl, pentoxycarbonyl, hexyloxycarbonyl, heptyloxycarbonyl, ethylhexyloxycarbonyl, decyloxycarbonyl, dodecyloxycarbonyl, cyclohexyloxycarbonyl, or tolyloxycarbonyl, in particular by methoxycarbonyl or ethoxycarbonyl, and is preferably methyl or ethyl, in particular methyl, each of which is substituted by methoxycarbonyl, ethoxycarbonyl or in particular butoxycarbonyl.

-CONR³R⁴-substituted C_1 - C_{18} alkyl R^1 is, for example, methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl or octadecyl, each of which is substituted by dimethylaminocarbonyl, diethylaminocarbonyl, dibutylaminocarbonyl or ethylmethylaminocarbonyl, in particular dimethyl- or diethylaminocarbonyl, and is preferably methyl, ethyl or propyl, each of which is substituted by dimethylaminocarbonyl or diethylaminocarbonyl, in particular propyl which is substituted by dimethylaminocarbonyl.

CN-substituted C_1 - C_{18} alkyl R^1 is, for example, cyanomethyl, cyanoethyl, cyanopropyl, cyanobutyl, cyanopentyl, cyanoethyl, cyanoheptyl, cyanoethyl, cyanodecyl, cyanododecyl or cyanoethyl, in particular cyanoethyl.

C_2 - C_{18} Alkyl R^1 which is interrupted by -O-, -S- or -NR⁵- units contain, for example, the structural units -CH₂-CH₂-O-, -CH₂-CH₂-S- or -CH₂-CH₂-NR⁵-. The -NR⁵-, -O- or -S- groups can occur once or more than once in the chain. Other examples of C_2 - C_{18} alkyl R^1 which is interrupted by -O-, -S- or -NR⁵- units are methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl or octadecyl, each of which is substituted by methoxy, ethoxy, propoxy, butoxy, methylthio, ethylthio, propylthio, butylthio, dimethylamino, diethylamino, dipropylamino, etc, in particular methoxy or ethoxy,

preferably ethyl which is substituted by methoxy.

C_5 - C_{12} Cycloalkyl R^1 , R^2 , R^3 , R^4 and R^5 may be, for example, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclodecyl or cyclododecyl, preferably cyclopentyl or cyclohexyl, in particular cyclohexyl.

Phenyl- C_1 - C_4 alkyl R^1 , R^2 , R^3 , R^4 and R^5 are, for example, benzyl, 1-phenylethyl, 2-phenylethyl, 3-phenylpropyl, α -methylbenzyl, α,α -dimethylbenzyl, etc, preferably benzyl or 1-phenylethyl.


An aromatic radical R^1 is preferably phenyl.

Substituted phenyl R^1 preferably contains 1 to 3 substituents, in particular 1 or 2 substituents, and is, for example, chlorophenyl, dichlorophenyl, trichlorophenyl, fluorophenyl, difluorophenyl, tolyl, dimethylphenyl, mesityl, ethylphenyl, diethylphenyl, isopropylphenyl, tert-butylphenyl, benzylphenyl, phenylethylphenyl, di-*t*-butylphenyl, methyl-di-*tert*-butylphenyl, dodecylphenyl, methoxyphenyl, dimethoxyphenyl, ethoxyphenyl, hexyloxyphenyl, methoxyethylphenyl or ethoxymethylphenyl, in particular *p*-*tert*-butylphenyl. Alkyl and alkoxy as aryl substituents preferably have 1-4 carbon atoms and are, in particular, methyl, *tert*-butyl or methoxy, preferably *tert*-butyl.


An aromatic radical R^1 is in particular phenyl which is unsubstituted or substituted by an alkyl group.

Halogen is, in particular, chlorine, bromine or fluorine.

Of particular interest are compounds of the formula I in which, if $x = 1$, R^1 is C_1 - C_{30} alkyl, C_1 - C_{18} alkyl substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$, $-\text{NR}^3\text{R}^4$ or by $-\text{CONR}^3\text{R}^4$, C_2 - C_{18} alkyl which is interrupted by $-\text{NR}^5$ -, $-\text{O}$ - or $-\text{S}$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, naphthyl, a radical of the formula





if $x = 2$, R^1 is C_2 - C_{18} alkylene, C_2 - C_{18} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,




if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

Other particularly interesting compounds of the formula I are those in which, if $x = 1$, R^1 is C_1 - C_{24} alkyl, C_1 - C_{12} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, naphthyl, a radical of the



if $x = 2$, R^1 is C_2 - C_{12} alkylene, C_2 - C_{12} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,




are hydrogen or C_1 - C_4 alkyl, and,

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

Preference is given to compounds of the formula I in which, if $x = 1$, R^1 is C_1 - C_{20} alkyl, C_1 - C_8 alkyl which is substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_8 alkyl which is interrupted by $-O$ - or $-S$ -, C_3 - C_8 alkenyl, C_5 - C_8 cycloalkyl, phenyl which is unsubstituted

or substituted by C_1 - C_{12} alkyl or phenyl- C_1 - C_4 alkyl, naphthyl, a radical of the formula



hydrogen or methyl, and R^8 and R^9 are hydrogen,


if $x = 2$, R^1 is C_2 - C_8 alkylene or C_2 - C_8 alkylene which is interrupted by $-NR^5-$ or $-O-$, and,

if $x = 3$, R^1 is a $-(CH_2)_2-N-(CH_2)_2-$ radical.


Further interesting compounds of the formula I are those in which, if $x = 1$, R^1 is

C_1 - C_{18} alkyl which is unsubstituted or substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$,

C_2 - C_{18} alkyl which is interrupted by $-NR^5-$, $-O-$ or $-S-$, C_3 - C_6 alkenyl, C_5 - C_8 cycloalkyl,



if $x = 2$, R^1 is C_2 - C_{12} alkylene, C_2 - C_{12} alkylene which is interrupted by $-NR^5-$, $-O-$ or $-S-$,



if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_2-N-(CH_2)_2-$ group.

Preference is given to compounds of the formula I in which $x = 1$, R^1 is C_1 - C_{12} alkyl which is unsubstituted or substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_{12} alkyl which is interrupted by $-NR^5-$, $-O-$ or $-S-$, or is phenyl- C_1 - C_4 alkyl or C_5 - C_7 cycloalkyl.

03 DEC 1996

- 7 -


Preference is furthermore given to compounds of the formula I in which R^1 is C_1 - C_4 alkyl.

Particular emphasis should also be attached to compounds of the formula I in which R^1 is as defined above, but is not unsubstituted or C_1 - C_{12} alkyl-, halogen- or C_1 - C_4 alkoxy-substituted phenyl or naphthyl.

Also worthy of mention in particular are compounds of the formula I in which R^1 is C_1 - C_{18} alkyl, C_5 - C_7 cycloalkyl or phenyl- C_1 - C_4 alkyl, in particular C_1 - C_{18} alkyl.

The compounds of the formula I can be obtained by processes which are known per se in chemistry. DE-A-2 950 694 describes a process for the preparation of corresponding compounds by reacting a phosphorus trihalide, a phosphorous acid monoester dihalide or a phosphorous acid diester halide with a phenol in the presence of an alkali metal hydroxide or alkaline earth metal hydroxide.

The compounds according to the invention can accordingly be prepared by substituting the chlorine in the diaryl phosphorochloridite by an alcohol or a phenol in the presence of a base.



R^1 is as defined above.

In order to prepare dimeric and trimeric compounds of the formula I, the corresponding polyols are used.

The bases used can be organic bases or inorganic bases. Examples of organic bases are tertiary amines, eg. trimethylamine, triethylamine, N,N -dimethylaniline, N,N -diethylaniline or pyridine. Examples of inorganic bases are alkali metal hydroxides, for example sodium hydroxide or potassium hydroxide, or alkali metal carbonates, for example sodium carbonate or potassium carbonate.

03 DEC 1996

- 8 -


The substitution reaction temperatures are, for example, from -30°C to $+150^{\circ}\text{C}$, preferably from -10°C to $+70^{\circ}\text{C}$.

Solvents which can be employed are aliphatic and aromatic, simple or halogenated hydrocarbons or ethers. Examples of suitable aromatic hydrocarbons are benzene, toluene and xylene, and an example of a suitable chlorinated aromatic hydrocarbon is chlorobenzene. Examples of aliphatic hydrocarbons which can be used as solvents are hexane, pentane and further petroleum ether fractions. Examples of suitable halogenated aliphatic hydrocarbons are methylene chloride and chloroform. Examples of suitable ethers are diethyl ether, dibutyl ether and tetrahydrofuran.

The diaryl phosphorochloridite (II) and the alcohol R^1OH are expediently employed in equivalent amounts. It is, however, also possible, for example, to use an excess of alcohol, for example 1.05-1.2 equivalents.

A further method of preparing compounds according to the invention is to condense 2 equivalents of 2,4-di-tert-butyl-6-methylphenol with one equivalent of a phosphorus compound $\text{R}^1\text{O}-\text{PCl}_2$ in the presence of an organic base.

The invention also relates to the compound of the formula II



and to the use thereof for the preparation of compounds of the formula I.

The preparation of phosphorochloridites is known to persons skilled in the art and is described in numerous publications. The novel phosphorochloridite of the formula II can be prepared by analogous processes. For instance, H.G. Cook et al., J. Chem. Soc. 1949, IV, 2921-2927, and A.J. Razumov et al., Chemical Abstracts 60, 1571g (1964), describe the preparation of corresponding chlorides by reacting phosphorus trichloride with alkanols in the presence of N,N-dimethylaniline or N,N-diethylaniline as acid acceptor. J.

03 DEC 1996

- 9 -

Michalski et al., J. Chem. Soc. 1961, 4904, disclose a variant of this process in which the acid acceptor employed is a pyridine/diethylaniline mixture. Reactions of phosphorus trichloride with hindered phenols are disclosed in US-A-3 281 506 and US-A-4 584 146. H.G. Cook et al., J. Chem. Soc., 1949, IV, 2921-2927 indicate a further method of preparing phosphorochloridites analogous to the formula II. They react phosphorus trichloride with symmetrical trialkyl phosphites. A variant of this process is described in US-A-4 079 103.

Bis(2,4-di-tert-butyl-6-methyl) phosphorochloridite can also be prepared directly in the melt without solvents. This allows the preparation of the phosphites of the formula I without isolation of the intermediate.

The compounds of the formula I are highly suitable for stabilising organic materials against photoinduced, thermal and/or oxidative degradation. The invention therefore also relates to compositions comprising an organic material which is sensitive to degradation reactions of this type, and at least one compound of the formula I, and to the use of compounds of the formula I as stabilisers for organic materials against said types of degradation.

Examples of such materials are:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybut-1-ene, polymethylpent-1-ene, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high density polyethylene (HDPE), low density polyethylene (LDPE) and linear low density polyethylene (LLDPE).
2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, for example ethylene-propylene copolymers, linear low density polyethylene (LLDPE) and its mixtures with low density polyethylene (LDPE), propylene-but-1-ene, propylene-isobutylene, ethylene-but-1-ene, ethylene-hexene, ethylene-methylpentene,

ethylene-heptene, ethylene-octene, propylene-butadiene, isobutylene-isoprene, ethylene-alkyl acrylate, ethylene-alkyl methacrylate, ethylene-vinyl acetate or ethylene-acrylic acid copolymers and their salts (ionomers) and terpolymers of ethylene with propylene and a diene, such as hexadiene, dicyclopentadiene or ethylidenenorbornene; as well as mixtures of such copolymers and their mixtures with polymers mentioned in 1), for example polypropylene/ethylene-propylene copolymers, LDPE/ethylene-vinyl acetate copolymers, LDPE/ethylene-acrylic acid copolymers, LLDPE/ethylene-vinyl acetate copolymers and LLDPE/ethylene-acrylic acid copolymers.


3a. Hydrocarbon resins (for example C₅-C₉) and hydrogenated modifications thereof (for example tackifiers).

4. Polystyrene, poly(p-methylstyrene), poly(α -methylstyrene).

5. Copolymers of styrene or α -methylstyrene with dienes or acrylic derivatives, for example styrene-butadiene, styrene-acrylonitrile, styrene-alkyl methacrylate, styrene-butadiene-alkyl acrylate, styrene-maleic anhydride, styrene-acrylonitrile-methyl acrylate; high impact strength mixtures of styrene copolymers and another polymer, for example a polyacrylate, a diene polymer or an ethylene-propylene-diene terpolymer; and block copolymers of styrene, for example styrene-butadiene-styrene, styrene-isoprene-styrene, styrene-ethylene/butylene-styrene or styrene-ethylene/propylene-styrene.

6. Graft copolymers of styrene or α -methylstyrene, for example styrene on polybutadiene, styrene on polybutadiene-styrene or polybutadiene-acrylonitrile; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and maleic anhydride on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene and maleimide on polybutadiene, styrene and alkyl acrylates or methacrylates on polybutadiene, styrene and acrylonitrile on ethylene-propylene-diene terpolymers, styrene and acrylonitrile on polyalkyl acrylates or polyalkyl methacrylates, styrene and acrylonitrile on acrylate-butadiene copolymers, as well as mixtures thereof with the copolymers mentioned under 5), for instance the copolymer mixtures known as ABS, MBS, ASA or AES polymers.

7. Halogen-containing polymers, such as polychloroprene, chlorinated rubber, chlorinated or chlorosulfonated polyethylene, copolymers of ethylene and chlorinated ethylene,



epichlorohydrin homo- and copolymers, in particular polymers from halogen-containing vinyl compounds, for example polyvinyl chloride, polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof, for example vinyl chloride-vinylidene chloride, vinyl chloride-vinyl acetate or vinylidene chloride-vinyl acetate copolymers.

8. Polymers derived from α,β -unsaturated acids and derivatives thereof, such as polyacrylates and polymethacrylates, polyacrylamides and polyacrylonitriles.

9. Copolymers from the monomers mentioned under 8) with each other or with other unsaturated monomers, for instance acrylonitrile-butadiene, acrylonitrile-alkyl acrylate, acrylonitrile-alkoxyalkyl acrylate or acrylonitrile-vinyl halide copolymers or acrylonitrile-alkyl methacrylate-butadiene terpolymers.

10. Polymers derived from unsaturated alcohols and amines, or acyl derivatives thereof or acetals thereof, such as polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallylmelamine; and their copolymers with olefins mentioned in 1) above.

11. Homopolymers and copolymers of cyclic ethers, such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bisglycidyl ethers.

12. Polyacetals, such as polyoxymethylene and those polyoxymethylenes which contain comonomers, for example ethylene oxide; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

13. Polyphenylene oxides and sulfides, and mixtures thereof with styrene polymers or polyamides.

14. Polyurethanes derived from polyethers, polyesters or polybutadienes with terminal hydroxyl groups on the one hand and aliphatic or aromatic polyisocyanates on the other, and precursors thereof.

15. Polyamides and copolyamides which are derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, such as nylon 4, nylon 6, nylon 6/6, 6/10, 6/9, 6/12 and 4/6, nylon 11, nylon 12, aromatic polyamides obtained from

m-xylene, diamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic and/or terephthalic acid and optionally an elastomer as modifier, for example poly-2,4,4-trimethylhexamethylene terephthalamide or poly-m-phenylene isophthalamide. Block copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, for instance with polyethylene glycol, polypropylene glycol or polytetramethylene glycol. Further, EPDM- or ABS-modified polyamides or copolyamides; and polyamides condensed during processing ("RIM polyamide systems").

16. Polyureas, polyimides, polyamide-imides and polybenzimidazoles.

17. Polyesters derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, such as polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate and polyhydroxybenzoates as well as block polyether-esters derived from polyethers having hydroxyl end groups; also polycarbonate- or MBS-modified polyesters.

18. Polycarbonates and polyester carbonates.

19. Polysulfones, polyether sulfones and polyether ketones.

20. Crosslinked polymers derived from aldehydes on the one hand and phenols, urea or melamine on the other, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

21. Drying and non-drying alkyd resins.

22. Unsaturated polyester resins derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols, and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low inflammability.

23. Crosslinkable acrylic resins, derived from substituted acrylic esters, for example epoxy acrylates, urethane acrylates or polyester acrylates.

24. Alkyd resins, polyester resins or acrylate resins crosslinked with melamine resins, urea resins, polyisocyanates or epoxy resins.

25. Crosslinked epoxy resins derived from polyepoxides, for example from bisglycidyl ethers or from cycloaliphatic diepoxides.

26. Natural polymers, such as cellulose, natural rubber, gelatin and derivatives thereof which are chemically modified in a polymer-homologous manner, such as cellulose acetates, cellulose propionates and cellulose butyrates, or cellulose ethers, such as methylcellulose; and colophony resins and their derivatives.

27. Mixtures (polyblends) of polymers as mentioned above, for example PP/EPDM, polyamide/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ABS, PBTP/ABS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPO/HIPS, PPO/PA 6.6 and copolymers, PA/HDPE, PA/PP, PA/PPO.

28. Naturally occurring and synthetic organic substances which are pure monomeric compounds or mixtures thereof, for example mineral oils, animal or vegetable fats, oils and waxes, or oils, waxes and fats based on synthetic esters (for example phthalates, adipates, phosphates or trimellitates), and blends of synthetic esters with mineral oils in any desired weight ratios, as used, for example, as spinning preparations, and aqueous emulsions thereof.

29. Aqueous emulsions of natural or synthetic rubbers, for example natural rubber latex or latexes of carboxylated styrene-butadiene copolymers.

The organic materials to be protected are preferably natural, semisynthetic or preferably synthetic organic materials. Particular preference is given to thermoplastic polymers, in particular PVC or polyolefins, for example polyethylene and polypropylene (PP).

The compositions according to the invention expediently contain the compounds of the formula I in amounts of from 0.01 to 10 % by weight, for example from 0.05 to 5 % by weight, preferably from 0.05 to 3 % by weight, but in particular from 0.1 to 2 % by weight. It is possible for the compositions to contain one or more compounds of the formula I, and the per cent by weight data relate to the total amount of these compounds. The calculation is based on the total weight of the organic material without the compounds of the formula I. Incorporation into the materials can be effected, for example, by mixing

in or applying the compounds of the formula I and, if desired, further additives by methods which are conventional in industry. If the materials are polymers, in particular synthetic polymers, incorporation can take place before or during moulding or by applying the dissolved or dispersed compounds to the polymer, if necessary with subsequent evaporation of the solvent. In the case of elastomers, these may also be stabilised as latexes. A further way of incorporating the compounds of the formula I into polymers is to add them before, during or immediately after the polymerisation of the corresponding monomers or before the crosslinking. The compounds of the formula I can be added as such or in encapsulated form (for example in waxes, oils or polymers). If added before or during the polymerisation, the compounds of the formula I can also act as regulators for the chain length of the polymers (chain terminators).

The compounds of the formula I or mixtures thereof can also be added to the plastics to be stabilised in the form of a masterbatch which contains these compounds, for example, in a concentration of from 2.5 to 25 % by weight.

Incorporation of the compounds of the formula I can expediently be effected by the following methods:

- as an emulsion or dispersion (for example to latexes or emulsion polymers)
- as a dry mix during mixing of the additional components or polymer mixtures
- by direct addition into the processing apparatus (for example extruder, internal mixer, etc)
- as a solution or melt.

Polymer compositions according to the invention can be used in various forms or converted into various products, for example as (into) films, fibres, tapes, moulding compositions, profiles or as binders for surface coatings, adhesives or adhesive cements.

As stated above, the organic materials to be protected are organic, preferably synthetic polymers. Particular preference is given to the protection of thermoplastic materials, in particular polyolefins. The excellent effectiveness of the compounds of the formula I as processing stabilisers (heat stabilisers) should be particularly emphasised. For this purpose, they are advantageously added to the polymer before or during processing thereof.

However, it is also possible to stabilise other polymers (for example elastomers) or lubricants or hydraulic fluids against degradation, for example photoinduced and/or thermooxidative degradation. Elastomers are given in the above list of possible organic materials.

Suitable lubricants and hydraulic fluids are based, for example, on mineral or synthetic oils or mixtures thereof. The lubricants are known to persons skilled in the art and are described in the relevant specialist literature, for example in Dieter Klamann, "Schmierstoffe und verwandte Produkte" [Lubricants and Related Products] (Verlag Chemie, Weinheim, 1982), in Schewe-Kobek, "Das Schmiermittel-Taschenbuch" [The Lubricant Handbook] (Dr. Alfred Hüthig-Verlag, Heidelberg, 1974), and in "Ullmanns Enzyklopädie der technischen Chemie" [Ullmann's Encyclopaedia of Industrial Chemistry], Vol. 13, pages 85-94 (Verlag Chemie, Weinheim, 1977).

The invention also relates to the stabilisation of organic materials against oxidative, thermal and/or actinic degradation by adding or applying, as stabilisers, compounds of the formula I to this material.

In addition to the compounds according to the invention, the compositions according to the invention, in particular if they contain organic, preferably synthetic polymers, may also contain further conventional additives. Examples of such additives are:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-di-cyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-di-octadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol and 2,6-di-nonyl-4-methylphenol.

1.2. Alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone and 2,6-diphenyl-4-octadecyloxyphenol.

1.3. Hydroxylated thiodiphenyl ethers, for example

2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol),
4,4'-thiobis(6-tert-butyl-3-methylphenol) and 4,4'-thiobis(6-tert-butyl-2-methylphenol).

1.4. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol),
2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-
6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol),
2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol),
2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-
4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol],
2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-
tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol),
1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-
2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-
2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-
3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-
4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)-
dicyclopentadiene and bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-
butyl-4-methylphenyl] terephthalate.

1.5. Benzyl compounds, for example,

1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene,
bis(3,5-di-tert-butyl-4-hydroxybenzyl) sulfide, isooctyl
3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate,
bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)dithiol terephthalate,
1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate,
1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) isocyanurate, dioctadecyl
3,5-di-tert-butyl-4-hydroxybenzylphosphonate, the calcium salt of monoethyl
3,5-di-tert-butyl-4-hydroxybenzylphosphonate and
1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl) isocyanurate.

1.6. Acylaminophenols, for example 4-hydroxylauranilide, 4-hydroxystearanilide,
2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-s-triazine and octyl
N-(3,5-di-tert-butyl-4-hydroxyphenyl)carbamate.

1.7. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with monohydric or
polyhydric alcohols, for example with methanol, octadecanol, 1,6-hexanediol, neopentyl

glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxyethyl) isocyanurate and N,N'-bis(hydroxyethyl)oxalamide.

1.8. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with monohydric or polyhydric alcohols, for example with methanol, octadecanol, 1,6-hexanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxy)ethyl isocyanurate and N,N'-bis(hydroxyethyl)oxalamide.

1.9. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with monohydric or polyhydric alcohols, for example with methanol, octadecanol, 1,6-hexanediol, neopentyl glycol, thiodiethylene glycol, diethylene glycol, triethylene glycol, pentaerythritol, tris(hydroxy)ethyl isocyanurate and N,N'-bis(hydroxyethyl)oxalamide.

1.10. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid, for example N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine and N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

2. UV absorbers and light stabilisers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example the 5'-methyl, 3',5'-di-tert-butyl, 5'-tert-butyl, 5'-(1,1,3,3-tetramethylbutyl), 5-chloro-3',5'-di-tert-butyl, 5-chloro-3'-tert-butyl-5'-methyl, 3'-sec-butyl-5'-tert-butyl, 4'-octoxy, 3',5'-di-tert-amyl and 3',5'-bis(α,α -dimethylbenzyl) derivatives.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octoxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of substituted or unsubstituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoylresorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoylresorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate and hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl or isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl or butyl α -cyano- β -methyl-p-methoxycinnamate,

methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5 Nickel compounds, for example nickel complexes of

2,2'-thiobis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 complex or the 1:2 complex, if appropriate with additional ligands, such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of monoalkyl 4-hydroxy-3,5-di-tert-butylbenzylphosphonates, such as the methyl or ethyl ester, nickel complexes of ketoximes, such as 2-hydroxy-4-methylphenyl undecyl ketoxime, and nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, if appropriate with additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethylpiperidyl) sebacate, bis(1,2,2,6,6-pentamethylpiperidyl) sebacate, bis(1,2,2,6,6-pentamethylpiperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensation product formed from 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensation product formed from N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)-hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-s-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl) nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl) 1,2,3,4-butanetetraoate and 1,1'-(1,2-ethanediyl)bis(3,3,5,5-tetramethylpiperazinone).

2.7. Oxalic acid diamides, for example 4,4'-di-octyloxyoxanilide, 2,2'-di-octyloxy-5,5'-di-tert-butyloxanilide, 2,2'-di-dodecyloxy-5,5'-di-tert-butyloxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxalamide, 2-ethoxy-5-tert-butyl-2'-ethyloxanilide and a mixture thereof with 2-ethoxy-2'-ethyl-5,4'-di-tert-butyloxanilide or mixtures of o-methoxy- and p-methoxy-disubstituted oxanilides and of o-ethoxy- and p-ethoxy-disubstituted oxanilides.

2.8. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine and

2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxalamide, N-salicylal-N'-salicyloylhydrazine, N,N'-bis(salicyloyl)hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine, 3-salicyloylamino-1,2,4-triazole and bis(benzylidene)oxalodihydrazide.

4. Further phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythrityl diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythrityl diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythrityl diphosphite, tristearyl sorbitol triphosphite, tetrakis-(2,4-di-tert-butylphenyl) 4,4'-biphenylenediphosphonite and 3,9-bis(2,4-di-tert-butylphenoxy)-2,4,8,10-tetraoxa-3,9-diphosphaspiro[5.5]undecane.

5. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl and tridecyl esters, mercaptobenzimidazole, the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide and pentaerythrityl tetrakis(β -dodecylmercapto)propionate.

6. Benzofuranones and indolinones, as described, for example, in WO-A 80/01 566 and EP-A 415 887.

7. Polyamide stabilisers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

8. Basic costabilisers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate and tin pyrocatecholate.

9. Nucleating agents, for example 4-tert-butylbenzoic acid, adipic acid and diphenylacetic acid.

10. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres,

asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black and graphite.

11. Other additives, for example plasticisers, lubricants, emulsifiers, pigments, optical brighteners, flameproofing agents, antistatic and blowing agents.

The examples below illustrate the invention in greater detail. Parts and percentages, as in the claims and the remainder of the description, are by weight, unless stated otherwise.

Example 1: Preparation of bis(2,4-di-tert-butyl-6-methylphenyl) phosphorochloridite

890.3 g (4 mol) of 2,4-di-tert-butyl-6-methylphenol, 4.2 g of dimethylformamide and 170.0 g of xylene are introduced into a four-neck flask which has been flushed with nitrogen and is fitted with a thermometer, dropping funnel, reflux condenser and distillation attachment. 274.9 g (2 mol) of phosphorus trichloride are added dropwise with stirring over the course of 1.5 hours at a temperature of 50°C. The reaction mixture is warmed to 130°C and refluxed at this temperature for 1 hour. The reaction mixture is kept at 120°C for 1 hour under a vacuum of 0.15 bar. Xylene is subsequently removed by distillation under a greater vacuum. After the vacuum has been broken using nitrogen, 959.5 g (1.9 mol) of the title compound are obtained as supercooled, yellow-orange, clear melt.

Purity: 98 % (determined using ^{31}P -NMR)

Purification: distillation at 204°C/0.0002 bar.

Example 2: Preparation of bis(2,4-di-tert-butyl-6-methylphenyl) methyl phosphite


300 g (1.36 mol) of 2,4-di-tert-butyl-6-methylphenol are introduced into a 1500 ml sulfonation flask fitted with thermometer, stirrer and reflux condenser, and the reactor is flushed with nitrogen. The mixture is warmed to 55°C in order to melt the phenol, and 1.5 g of dimethylformamide are added to the melt. 102.7 g (0.75 mol) of phosphorus trichloride are added dropwise over the course of 1.5 hours at the same temperature. The hydrochloric acid gas produced is neutralised by means of a 30 % aqueous sodium hydroxide solution. When the addition is complete, the reaction mixture is heated to 140°C over the course of 4 hours and stirred at this temperature for a further hour. A slight vacuum (0.55 bar) is then applied, and the mixture is stirred at 130°C for a further 4 hours. The clear yellow-orange melt obtained (= bis(2,4-di-tert-butyl-6-methyl) phosphoro-

chloridite) is then allowed to cool to about 80°C in a nitrogen atmosphere and is diluted with 500 ml of petroleum ether (80-100°C). The solution is cooled to -5°C, and 89.3 g (0.884 mol) of triethylamine are added over the course of 15 minutes. 32.8 g (1.02 mol) of methanol are then added dropwise over the course of 1 hour, during which the temperature rises to +5°C and the triethylamine hydrochloride precipitates. This mixture is allowed to warm slowly (about 1 hour) to room temperature with stirring. The precipitate is filtered off and the filtrate is evaporated, giving 328 g of phosphite as a yellow oil (purity determined by high pressure liquid chromatography [HPLC]: 94 %). Recrystallisation of the crude product from ethanol gives 262 g (77 % of theory) of the title compound in the form of a white powder having a melting point of 75-78°C.

Elemental analysis:

P calc.: 6.19 % found: 6.19 %

Examples 3-33: The compounds of Examples 3-33 are prepared analogously to the compound of Example 2 using the alcohol or phenol corresponding to the substituent R¹. The substituents and analytical data are shown in Table 1 below.















Table 1:

Example No.	R ₁	Yield [%]	Melting point [°C] Refractive index n_D^{20}	Elemental analysis % P calc. % P found	
3	C ₂ H ₅	65	91	6.02	6.01
4	n-C ₃ H ₇	60	57-58	5.86	5.70
5	i-C ₃ H ₇	64	104-105	5.86	5.80
6	n-C ₆ H ₁₃	99	high viscosity	5.43	5.49
7	$\text{C}_4\text{H}_9\text{-CH-CH}_2\text{-}$ C ₂ H ₅	95	1.5173	5.17	5.16
8	n-C ₁₂ H ₂₅	98	1.5107	4.73	4.71
9	i-C ₁₀ H ₂₁	95	high viscosity	4.94	4.99
10	i-C _{12/13} H _{25/27}	79	high viscosity	4.67	4.65
11	n-C ₁₈ H ₃₇	93	1.5061	4.19	4.19
12	i-C ₁₈ H ₃₇	91	1.5036	4.19	4.10
13	-(CH ₂) ₂ -OCH ₃	70	yellowish oil	5.69	5.44
14	-(CH ₂ CH ₂ -O) ₃ -C ₄ H ₉	97	1.5119	4.59	4.48
15	-(CH ₂) ₂ -S-C ₂ H ₅	98	high viscosity	5.39	5.18
16	-(CH ₂) ₂ -CF ₃	72	72	5.45	5.40
17	-(CH ₂) ₂ -CN	55	139	5.74	5.70
18	-(CH ₂) ₃ -N(CH ₃) ₂	65	yellowish oil	5.42	5.30
19	-CH ₂ CO ₂ - ⁿ C ₄ H ₉	96	high viscosity	5.16	4.90
20	benzyl	97	high viscosity	5.37	5.46
21	-(CH ₂) ₂ -C ₆ H ₅	74	78-80	5.24	5.18
22	cyclohexyl	64	high viscosity	5.45	5.22
23	phenyl	80	96-98	5.50	5.52


03 DEC 1996

- 23 -

Table 1 (continuation):

Example No.	R ₁	Yield [%]	Melting point [°C] Refractive index n_D^{20}	Elemental analysis % P calc. % P found	
24	naphthyl	83	101-103	5.05	4.97
25		55	154-156	5.00	4.99
26		97	high viscosity	4.50	4.53
27		99	1.5508	4.55	4.30
28		78	117-120	4.59	4.44
29		54	63-70	4.84	4.79
30		32	55-75	4.95	4.81
31		87	69-78	4.62	4.60
32		63	81-82	5.88	5.84
33		25	high viscosity	4.39	4.23

Examples 34-36:



The compounds of Examples 34-36 are prepared analogously to the compound of Example 2 using the polyol corresponding to the substituent R¹. Two equivalents of both bis(2,4-di-tert-butyl-6-methyl) phosphorochloridite and base are used for the compounds where x = 2, and three equivalents of bis(2,4-di-tert-butyl-6-methyl) phosphorochloridite and three equivalents of base are correspondingly used for the trimeric compound (x = 3). The substituents and analytical data are shown in Table 2 below.

Table 2:

Example No.	R ₁	x	Yield [%]	Melting point [°C] Refractive index _D ²⁰	Elemental analysis % P calc. % P found	
34	-(CH ₂) ₆ -	2	49	168	5.87	5.82
35	-(CH ₂) ₂ -O-(CH ₂) ₂ -	2	75	40-50 (amorphous)	5.94	5.36
36	$\begin{array}{c} \\ \text{-(CH}_2\text{)}_2\text{ -HN - (CH}_2\text{)}_2\text{ -} \end{array}$	3	63	136-137	5.86	5.74

Example 37: Stabilisation of polypropylene

1.3 kg of polypropylene powder (melt flow index 3.2 g/10 min, measured at 230°C/2.16 kg) are mixed with 0.05 % of calcium stearate, 0.05 % of tetrakis[3,5-di-tert-butyl-4-hydroxyphenylpropionyloxymethyl]methane and 0.05 % of the stabiliser indicated in Table 3. This mixture is extruded at 100 rpm in an extruder having a barrel diameter of 20 mm and a length of 400 mm, the 3 heating zones being set at 260°C, 270°C and 280°C. The extrudate is cooled by drawing through a waterbath and is subsequently granulated. The granules obtained are extruded a second and third time. After these three extrusions, the melt flow index is measured at 230°C/2.16 kg. Small values indicate good stabilisation. The results are shown in Table 3.

Table 3

Compound from Example No.	Melt flow index [g/10 min]
-	17.8
2	6.1
3	6.6
4	5.8
5	10.2
6	6.0
7	6.7
8	5.8
9	6.2
10	8.7
11	7.1
12	7.0
13	8.7
16	9.5

Example 38: Stabilisation of polyethylene

100 parts of unstabilised high-density polyethylene having a molecular weight of about 500,000 in powder form are mixed in the dry state with 0.05 part of tetrakis(3,5-di-tert-butyl-4-hydroxyphenylpropionyloxymethyl)methane and 0.1 part of the stabiliser indicated in Table 4. The mixture is kneaded for 50 minutes at 220°C and 50 rpm in a Brabender Plastograph. During this time, the kneading resistance is recorded continuously as torque. As a consequence of the crosslinking of the polymer, a rapid increase in torque occurs during the kneading time after initially remaining constant. The effectiveness of the stabilisers is apparent from an increase in the time before the torque increases. The values obtained are shown in Table 4.

03 DEC 1996

- 26 -

Table 4


Compound from Example No.	Time before increase in torque [min]
-	5.0
2	16.5
3	12.0
4	12.0
5	13.0
6	15.0
7	22.5
8	17.0
9	19.0
10	16.5
11	14.0
12	17.0
13	13.5
16	15.0



03 DEC 1996



WHAT IS CLAIMED IS:

1. A compound of the formula I



in which x is 1, 2 or 3, and,


if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl, halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, or R₁ is naphthyl, a radical



R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6,

with the proviso that R¹ is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,

if x = 2, R¹ is C₂-C₁₈alkylene, C₂-C₁₈alkylene which is interrupted by -NR⁵-, -O- or -S-,






- 28 -

REPLACEMENT SHEET


03 DEC 1996

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

2. A compound of the formula I according to claim 1, in which, if $x = 1$, R^1 is C_1 - C_{30} alkyl, C_1 - C_{18} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, or R_1 is naphthyl, a radical of the formula




if $x = 2$, R^1 is C_2 - C_{18} alkylene, C_2 - C_{18} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,



if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

3. A compound of the formula I according to claim 2, in which, if $x = 1$, R^1 is C_1 - C_{24} alkyl, C_1 - C_{12} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl, halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, or R_1 is naphthyl, a radical of the formula



if $x = 2$, R^1 is C_2 - C_{12} alkylene, C_2 - C_{12} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,

This Sheet Has Been Replaced




THIS SHEET HAS BEEN
REPLACED



REPLACEMENT SHEET

03 DEC 1996



- 29 -

or is a  $(\text{CH}_2)_2^\cdot$ radical, and R^{10} and R^{11} , independently of one another, are

hydrogen or C_1 - C_4 alkyl, and,

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(\text{CH}_2)_m\text{-N-}(\text{CH}_2)_m^\cdot$ group in which m is 1-4.


4. A compound of the formula I according to claim 3, in which, if $x = 1$, R^1 is C_1 - C_{20} alkyl, C_1 - C_8 alkyl which is substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$ or $-\text{NR}^3\text{R}^4$, C_2 - C_8 alkyl which is interrupted by $-\text{O}-$ or $-\text{S}-$, C_3 - C_8 alkenyl, C_5 - C_8 cycloalkyl, phenyl which is unsubstituted or substituted by C_1 - C_{12} alkyl or phenyl- C_1 - C_4 alkyl, or R^1 is naphthyl, a radical of the



if $x = 2$, R^1 is C_2 - C_8 alkylene or C_2 - C_8 alkylene which is interrupted by $-\text{NR}^5-$ or $-\text{O}-$, and,

if $x = 3$, R^1 is a $-(\text{CH}_2)_m\text{-N-}(\text{CH}_2)_m^\cdot$ radical.

5. A compound of the formula I according to claim 3, in which, if $x = 1$, R^1 is C_1 - C_{18} alkyl which is unsubstituted or substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$ or $-\text{NR}^3\text{R}^4$, C_2 - C_{18} alkyl which is interrupted by $-\text{NR}^5-$, $-\text{O}-$ or $-\text{S}-$, C_3 - C_6 alkenyl, C_5 - C_8 cycloalkyl,



This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED




* C L N S *


REPLACEMENT SHEET

03 DEC 1996

- 30 -



if $x = 2$, R^1 is $\text{C}_2\text{-C}_{12}$ alkylene, $\text{C}_2\text{-C}_{12}$ alkylene which is interrupted by $-\text{NR}^5-$, $-\text{O}-$ or $-\text{S}-$,



if $x = 3$, R^1 is $\text{C}_4\text{-C}_{12}$ alkanetriyl or a $-(\text{CH}_2)_m\text{-N-(CH}_2)_m-$ group.

6. A compound according to claim 5, in which $x = 1$, R^1 is $\text{C}_1\text{-C}_{12}$ alkyl which is unsubstituted or substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$ or $-\text{NR}^3\text{R}^4$, $\text{C}_2\text{-C}_{12}$ alkyl which is interrupted by $-\text{NR}^5-$, $-\text{O}-$ or $-\text{S}-$, or is phenyl- $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_5\text{-C}_7$ cycloalkyl.

7. A compound according to claim 1, in which R^1 is $\text{C}_1\text{-C}_{18}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl or phenyl- $\text{C}_1\text{-C}_4$ alkyl, in particular $\text{C}_1\text{-C}_{18}$ alkyl.

8. A compound according to claim 7, in which R^1 is $\text{C}_1\text{-C}_4$ alkyl.

9. A composition comprising (a) an organic material which is sensitive to oxidative, thermal and/or photoinduced degradation, and (b) at least one compound of the formula I according to claim 1.

10. A composition according to claim 9, in which component (a) is a natural, semisynthetic or synthetic polymer.

11. A composition according to claim 10, in which component (a) is a thermoplastic polymer.

12. A composition according to claim 10, in which component (a) is a polyolefin.

13. A composition according to claim 10, in which component (a) is a polyvinyl chloride,

This Sheet Has Been Replaced

THIS SHEET HAS BEEN
REPLACED



- 31 -


REPLACEMENT SHEET

03 DEC 1996

a polyethylene or a polypropylene.

14. The use of a compound of the formula I according to claim 1 for stabilising organic materials which are sensitive to oxidative, thermal and/or actinic degradation.

15. The compound of the formula II



16. The use of the compound according to claim 15 for the preparation of a compound of the formula I according to claim 1.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED


24 MAY 1999

- 27 -

WHAT IS CLAIMED IS:



REPLACEMENT SHEET

1. A compound of the formula I




in which x is 1, 2 or 3, and,

if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, or R₁ is naphthyl, a radical




R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6, with the proviso that R¹ is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,

if x = 2, R¹ is C₂-C₁₈alkylene which is interrupted by -NR⁵-, -O- or -S-,




if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

2. A compound of the formula I according to claim 1, in which, if $x = 1$, R^1 is C_1 - C_{30} alkyl, C_1 - C_{18} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, or R_1 is naphthyl, a radical of the formula




if $x = 2$, R^1 is C_2 - C_{18} alkylene, which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,



if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.

3. A compound of the formula I according to claim 2, in which, if $x = 1$, R^1 is C_1 - C_{24} alkyl, C_1 - C_{12} alkyl substituted by halogen, $-COOR^2$, $-CN$, $-NR^3R^4$ or by $-CONR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -, C_3 - C_{18} alkenyl, C_5 - C_{12} cycloalkyl, phenyl- C_1 - C_4 alkyl, phenyl which is unsubstituted or substituted by halogen, phenyl- C_1 - C_4 alkyl and/or C_1 - C_4 alkoxy, or R_1 is naphthyl, a radical of the formula




if $x = 2$, R^1 is C_2 - C_{12} alkylene which is interrupted by $-NR^5$ -, $-O$ - or $-S$ -,



24 MAY 1999



- 29 -

REPLACEMENT SHEET

or is a  radical, and R^{10} and R^{11} , independently of one another, are hydrogen or C_1 - C_4 alkyl, and,

if $x = 3$, R^1 is C_4 - C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4.


4. A compound of the formula I according to claim 3, in which, if $x = 1$, R^1 is C_1 - C_{20} alkyl, C_1 - C_8 alkyl which is substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_8 alkyl which is interrupted by $-O-$ or $-S-$, C_3 - C_8 alkenyl, C_5 - C_8 cycloalkyl, phenyl which is unsubstituted or substituted by phenyl- C_1 - C_4 alkyl, or R_1 is naphthyl, a radical of the




if $x = 2$, R^1 is C_2 - C_8 alkylene which is interrupted by $-NR^5-$ or $-O-$, and,


if $x = 3$, R^1 is a $-(CH_2)_m-N-(CH_2)_m-$ radical.

5. A compound of the formula I according to claim 3, in which, if $x = 1$, R^1 is C_1 - C_{18} alkyl which is unsubstituted or substituted by halogen, $-COOR^2$, $-CN$ or $-NR^3R^4$, C_2 - C_{18} alkyl which is interrupted by $-NR^5-$, $-O-$ or $-S-$, C_3 - C_6 alkenyl, C_5 - C_8 cycloalkyl,





if $x = 2$, R^1 is $\text{C}_2\text{-C}_{12}$ alkylene, which is interrupted by $-\text{NR}^5$ -, $-\text{O}-$ or $-\text{S}-$,



if $x = 3$, R^1 is $\text{C}_4\text{-C}_{12}$ alkanetriyl or a $-(\text{CH}_2)_m\text{-N-(CH}_2)_m-$ group.

6. A compound according to claim 5, in which $x = 1$, R^1 is $\text{C}_1\text{-C}_{12}$ alkyl which is unsubstituted or substituted by halogen, $-\text{COOR}^2$, $-\text{CN}$ or $-\text{NR}^3\text{R}^4$, $\text{C}_2\text{-C}_{12}$ alkyl which is interrupted by $-\text{NR}^5$ -, $-\text{O}-$ or $-\text{S}-$, or is phenyl- $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_5\text{-C}_7$ cycloalkyl.

7. A compound according to claim 1, in which R^1 is $\text{C}_1\text{-C}_{18}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl or phenyl- $\text{C}_1\text{-C}_4$ alkyl, in particular $\text{C}_1\text{-C}_{18}$ alkyl.

8. A compound according to claim 7, in which R^1 is $\text{C}_1\text{-C}_4$ alkyl.

9. A composition comprising (a) an organic material which is sensitive to oxidative, thermal and/or photoinduced degradation, and (b) at least one compound of the formula I according to claim 1.

10. A composition according to claim 9, in which component (a) is a natural, semisynthetic or synthetic polymer.

11. A composition according to claim 10, in which component (a) is a thermoplastic polymer.

12. A composition according to claim 10, in which component (a) is a polyolefin.

13. A composition according to claim 10, in which component (a) is a polyvinyl chloride,



24 MAY 1999


REPLACEMENT SHEET

- 31 -

a polyethylene or a polypropylene.

14. The use of a compound of the formula I according to claim 1 for stabilising organic materials which are sensitive to oxidative, thermal and/or actinic degradation.

15. The compound of the formula II




16. The use of the compound according to claim 15 for the preparation of a compound of the formula I according to claim 1.



Asymmetric aryl phosphites



Abstract of the disclosure

Compounds of the formula I



in which x is 1, 2 or 3, and,


if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl, halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, naphthyl, a radical of the




R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6,

with the proviso that R^1 is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,

if $x = 2$, R^1 is C_2-C_{18} alkylene, C_2-C_{18} alkylene which is interrupted by $-NR^5-$, $-O-$ or $-S-$,




if $x = 3$, R^1 is C_4-C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4, are suitable as stabilisers for organic materials which are sensitive to thermal, oxidative and/or photoinduced degradation.



A-18591/A/CGM 390



Asymmetric aryl phosphitesAbstract of the disclosure

Compounds of the formula I



in which x is 1, 2 or 3, and,


if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl, halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, naphthyl, a radical of the



R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6,

with the proviso that R^1 is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,

if $x = 2$, R^1 is C_2-C_{18} alkylene, C_2-C_{18} alkylene which is interrupted by $-NR^5-$, $-O-$ or $-S-$,



if $x = 3$, R^1 is C_4-C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4, are suitable as stabilisers for organic materials which are sensitive to thermal, oxidative and/or photoinduced degradation.

This Sheet Has Been Replaced




THIS SHEET HAS BEEN
REPLACED

03 DEC 1996

Asymmetric aryl phosphites



Abstract of the disclosure

Compounds of the formula I



in which x is 1, 2 or 3, and,

if x = 1, R¹ is C₁-C₃₀alkyl, C₁-C₁₈alkyl substituted by halogen, -COOR², -CN, -NR³R⁴ or by -CONR³R⁴, C₂-C₁₈alkyl which is interrupted by -NR⁵-, -O- or -S-, C₃-C₁₈alkenyl, C₅-C₁₂cycloalkyl, phenyl-C₁-C₄alkyl, phenyl which is unsubstituted or substituted by C₁-C₁₂alkyl, halogen, phenyl-C₁-C₄alkyl and/or C₁-C₄alkoxy, naphthyl, a radical of the




R₂, R₃, R₄ and R₅, independently of one another, are hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl or phenyl-C₁-C₄alkyl, R⁶ is hydrogen, methyl, allyl or benzyl, R⁷ is hydrogen or -OR⁹, R⁸ is hydrogen or methyl, R⁹ is hydrogen or C₁-C₃₀alkyl, R¹⁰ and R¹¹, independently of one another, are hydrogen or C₁-C₈alkyl, and n is 3-6,

This Sheet Has Been Replaced




THIS SHEET HAS BEEN
REPLACED



with the proviso that R^1 is not a phenyl radical which is substituted in both ortho-positions to the carbon atom bonded to the oxygen atom,

if $x = 2$, R^1 is C_2-C_{18} alkylene, C_2-C_{18} alkylene which is interrupted by $-NR^5-$, $-O-$ or $-S-$,



if $x = 3$, R^1 is C_4-C_{12} alkanetriyl or a $-(CH_2)_m-N-(CH_2)_m-$ group in which m is 1-4, are suitable as stabilisers for organic materials which are sensitive to thermal, oxidative and/or photoinduced degradation.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN
REPLACED