

METHOD FOR GROWING MONOCRYSTALLINE DIAMONDS

Field of the invention

5 The invention relates to growing mono-crystalline diamonds. In particular, the invention relates to growing diamonds by chemical vapour deposition (CVD) processes.

Background of the invention

10 Poly-crystalline, as well as mono-crystalline, diamond has been grown using variety of CVD techniques. Poly-crystalline diamond, in spite of having similar properties as mono-crystalline diamonds, is not a potential material
15 for new applications.

For example, thermal conductivity of the poly-crystalline diamond still does not surpass thermal conductivity of natural diamond. Indeed, in poly-crystalline diamond, the
20 grain boundaries inhibit exhibition of superior properties unique to diamond because the grain boundaries act as scattering centres for phonons thereby deteriorating thermal and other properties. The presence of large angle as well as small angle grain boundaries are a major
25 drawback in applications of poly-crystalline diamond.

While there is a clear preference for using mono-crystalline diamonds in applications, mono-crystalline diamonds are difficult to grow with the same texture,
30 clarity, purity and finish as natural diamond. Although, mono-crystalline diamond has superior properties compared to poly-crystalline diamond, microscopic and macroscopic graphitic and non-graphitic inclusions, feathers (long line defects) are very common in CVD grown mono-

crystalline diamond. As a result, the potential of CVD grown mono-crystals of diamond to be used as a gem quality product is diminished.

5 Detailed characterization of defects in mono-crystalline CVD grown diamond by Raman spectroscopy and X-ray diffraction (XRD) reveals that the defects comprise graphitic regions having a size in the range of submicrons and several microns in otherwise mono-crystalline diamond.

10

Another difficulty in growing mono crystalline CVD diamond is the growth rates. Although the growth rates of 70-100 microns per hour are possible with addition of nitrogen to CVD gases, but defects are prevalent and generally defect density increases with the growth rate.

15

For example, Derwent abstract of Japanese publication number JP 07277890 discloses a method for synthesizing diamond for use as semi-conductor, electronic or optical components or use in cutting tools. Specifically, the method disclosed in JP 07277890 involves growing diamond in the presence of gas containing nitrogen in a ratio of nitrogen to hydrogen of 3 to 1000 ppm or containing oxygen in a ratio of oxygen to carbon of 3 to 100% to increase growth rates.

25

A technical paper by Yan et. al. (PNAS, 1 October 2002, Vol. 99, no. 20, 12523-12525) discloses a method or producing mono-crystalline diamond by microwave plasma chemical vapour deposition (MPCVD) at growth rates in the range of 50 to 150 microns per hour.

30

The method involves a CVD process carried out at 150 torr and involves adding nitrogen to CVD gases to provide a ratio of nitrogen to methane of 1 to 5% N_2/CH_4 . Yan et. al.

35

believe that nitrogen in the stated ratio enhances growth rates because more available growth sites are created. This is believed to be a result of causing growth to change from <111> crystal planes to <100> crystal planes.

5

The importance of nitrogen content in CVD gases is recognised in United States patent 5,015,494 (Yamazaki) which teaches a method of growing diamond with customized properties for dedicated applications.

10

Yamazaki discloses forming diamond by electron cyclotron resonance CVD and discloses adding nitrogen to "prevent lattice defects from growing by virtue of external or internal stress". Nitrogen is added in a ratio of

15

nitrogen-compound gas to carbon-compound gas of 0.1 to 5%. The resultant diamond has a nitrogen concentration of 0.01 to 1 wt%.

20

Additionally, Yamazaki discloses a requirement to add boron gas to the CVD gases to form boron nitride which deposits on a substrate to improve adhesion to the substrate of formed diamond.

25

Nitrogen, according to Yan et. al. and Yamazaki, is required for two purposes. Specifically, nitrogen is used to enhance growth rates of CVD grown mono-crystalline diamond and to prevent lattice defects in electron cyclotron resonance CVD grown mono-crystalline diamond.

30

Summary of the invention

It is an object of the present invention to provide a CVD process for growing mono-crystalline diamonds substantially free of defects.

35

The applicants have carried out extensive experimental work on the role that nitrogen plays in CVD processes for

growing mono-crystalline diamond. The experimental work has surprisingly found that using nitrogen in quantities proposed in Yan et. al. and Yamazaki results in growing diamonds that exhibit nitrogen-based defects. The
5 experimental work has also found that only very small amounts of nitrogen gas in CVD gases will result in substantially defect-free mono-crystalline diamonds of very high quality that is useful for gems and the amount of nitrogen determined by the applicants to be beneficial
10 are considerably less than the nitrogen to carbon ratio disclosed in Yamazaki.

Specifically, the applicants have found that CVD gases containing more than relatively small amounts of nitrogen
15 result in diamond being formed with nitrogen-based inclusions in the diamond crystal structure. The inclusions comprise aggregates and the platelets of nitrogen atoms. Owing to the difference in bond length between nitrogen-carbon and carbon-carbon, the inclusions
20 operate as defects, such as phonon scattering centres, thereby diminishing the electrical, optical and mechanical properties of the formed mono-crystalline diamond.

The form of the inclusions is believed to be dependent on
25 the concentration of nitrogen in the CVD gases.

Additionally, the applicants have found that, although a relatively small amount of nitrogen is required, there must be at least some nitrogen present in the CVD gases to
30 increase growth rate and advantageously prevent graphitic inclusions forming in diamond deposited by a CVD process.

The invention provides a method of forming mono-crystalline diamond by chemical vapour deposition, the
35 method comprising the steps of:

- (a) providing at least one diamond seed;

- (b) exposing the seed to conditions for growing diamond by chemical vapour deposition, including supplying reaction gases that include a carbon-containing gas for growing diamond and include a nitrogen-containing gas; and
- (c) controlling the quantity of nitrogen-containing gas relative to other gases in the reaction gases such that diamond is caused to grow by step-growth.

The applicants have found that using relatively small quantities of nitrogen gas in CVD gases cause the growth mechanism of diamond to be a step-growth mechanism, in which a layer of diamond having an edge, defined by a step, grows at the edge as a front. This growth mechanism differs from a layer-growth mechanism that is typical of CVD process and that the applicants found to result from utilising relatively high quantities of nitrogen in CVD gases.

The mono crystalline diamonds grown by the step-growth mechanism with the quantities of nitrogen detailed in the application are free of microscopic and macroscopic graphitic inclusions and defects that are associated with growth of diamond by layer-growth, most notably nitrogen-based inclusions. As a result, diamonds grown by step-growth mechanism have enhanced optical, electrical and mechanical properties compared to diamonds grown by other CVD processes.

There must be at least some nitrogen included in the CVD gases to avoid graphitic inclusions forming in the grown diamond.

Preferably, the quantity of nitrogen-containing gas in the

CVD gases is in the range of 0.001 to 0.02 vol%.

Preferably, the nitrogen-containing gas is selected from any one or more of the following group: N₂ in hydrogen, N₂ in oxygen, N₂ in helium or N₂ in nitrous oxide.

Preferably, chemical vapour deposition conditions comprise maintaining the seed at a temperature in the range of 750 to 1200°C.

Preferably, the chemical vapour deposition conditions comprise maintaining the seed at a pressure in the range of 120 to 160 mbar.

Preferably, the carbon-containing gas comprises methane.

Preferably, the reactions gases comprise helium and/or hydrogen.

Preferably, chemical vapour deposition occurs in the presence of microwave plasma and occurs with hydrogen in the reactions gases.

Preferably, the reaction gases are in the following relative quantities: The methane 20-80 sccm, hydrogen 300-800 sccm, nitrogen 0.0005- 0.2 sccm, oxygen 1-10 sccm. The invention also provides a mono-crystalline diamond of gem quality formed in accordance with the method of the invention.

Preferably, the method is characterised by producing gem quality diamonds.

Brief description of the drawings

A preferred embodiment of the invention will now be described, by way of example only, with reference to the

accompanying drawings, in which:

Figure 1 is a Fourier transform infra-red (FTIR) spectrum of diamond deposited in a CVD process utilising nitrogen
5 in the CVD gases in the range of 0.0002 to 0.002 %.

Figure 2 is an FTIR spectrum of diamond deposited in a CVD process utilising nitrogen in the CVD gases in the range of 0.02 to 2.0 %.

10

Figure 3 is a photoluminescence spectrum of diamond deposited in a CVD process in accordance with the invention and utilising nitrogen in the CVD gases in the range of 0.0002 to 0.002 vol%.

15

Figures 4 to 6 are scanning electron microscope images of diamond grown in a CVD process including 0.03% nitrogen in accordance with the invention and showing step-growth of diamond.

20

Figures 7 and 8 are optical micrographs of diamond deposited in a CVD process utilising nitrogen in the CVD gases in the amounts of 0.0005 vol% and 0.0008 vol% respectively. The Optical micrographs also show the step
25 growth mechanism of the growth of diamond.

Figure 9 is an optical micrograph of diamond deposited in a CVD process utilising nitrogen in the CVD gases in the amount of 0.0012 vol% in accordance with the invention.

30

Detailed description of an embodiment

A method of growing mono-crystalline diamond in accordance with the invention involves a CVD process that utilises
35 microwave plasma.

Diamond is grown on a substrate comprising a diamond seed

that may vary in size between 3 x 3mm and 5 x 5mm. The method is carried out in a microwave plasma chamber. Depending on the size of the chamber, multiple seeds may be used to grow diamond during a single run of the
5 invention.

The crystallographic orientation of the seeds is determined and seeds having an orientation other than (100) are rejected. Seeds having an orientation of (100)
10 are polished to optical finish with roughness of the order of a micron in preparation for the CVD process.

Once the seeds are located in the chamber, the temperature inside the chamber is increased from ambient temperature
15 to a temperature in the range of 750 to 1200°C and the pressure inside the chamber is reduced to a pressure in the range of 120 to 160 mbar.

The chamber is supplied with gases for growing diamond and the gases comprise methane (CH₄), hydrogen (H₂), nitrogen (N₂), and helium (He) and are passed through the chamber at a gas flow rate of 30 l/hr. However, the nitrogen gas may be delivered to the chamber in combination with oxygen, hydrogen and helium
25

Nitrogen gas is supplied in a quantity that comprises 0.0002 to 0.002 vol% of the gases for growing diamond.

An electrical field is applied to surround the seeds such that plasma is generated from the gases in the chamber.
30 The electrical field is generated by a magnetron operating at 6000 Watt and at 2.45 GHz. The generated electrical field causes the hydrogen gas to ionise, thereby forming plasma in the vicinity of the diamond seeds. Under these
35 process conditions, diamond is caused to grow on the diamond seeds.

The growth pattern of diamond, as shown in Figures 3 to 5, is step-wise and therefore enables diamond to grow that is substantially defect and impurity free.

5 By way of comparison, the same process conditions were used with the supply of nitrogen being altered to comprise 0.02 to 2 vol% of the supplied gases, i.e. nitrogen comprises at least ten times the amount of nitrogen supplied in accordance with the invention.

10

FTIR analysis of samples is used to determine the concentration and bonding of nitrogen in samples. The FTIR spectra of samples grown in accordance with the invention and in accordance with the altered nitrogen supply are shown in Figures 1 and 2, respectively.

15

The FTIR spectrum (Figure 1) of the diamonds grown in accordance with the invention shows dominant C-C modes at 1978 cm^{-1} , 2026 cm^{-1} and 2160 cm^{-1} in the two phonon region.

20

The interesting result, however, is that no nitrogen related bands are observed in the FTIR spectrum of these samples.


The FTIR spectrum (Figure 2) of samples grown with nitrogen in the range of 0.02 to 2% show clear and strong signatures of the nitrogen centres in the samples.

25

Specifically, intense bands related to nitrogen centres are evident at 478 cm^{-1} , 1014 cm^{-1} , 1175 cm^{-1} , 1280 cm^{-1} and 1370 cm^{-1} along with the C-C bands at 1978 cm^{-1} , 2026 cm^{-1} and 2160 cm^{-1} . The intense bands of nitrogen in the samples correspond to "A" aggregates, "B" aggregates and platelet configurations of nitrogen detailed below, along with single atom substitution of nitrogen for carbon:


30

35 • Single atom substitution:



The characteristics peaks in FTIR spectra exist at 1130 and 1350 cm^{-1} and EPR gives a "g" value of 2.0024 for this centre. These peaks do not appear in FTIR for samples
5 produced in accordance with the invention.

- "A" aggregate:




10

480-490 cm^{-1} and 1282 cm^{-1} are the characteristic peaks of A-aggregate in FTIR. These peaks are evident in Figure 2 for samples produced with concentrations of nitrogen greater than for the invention.


15

- "B" aggregate:



20 1010 cm^{-1} , 1096 cm^{-1} and 1175 to 1185 cm^{-1} are the characteristic peaks of B-aggregate in FTIR spectra of diamond. It is believed to consist of 4 / 8 nitrogen atoms in pair with carbon atoms. These peaks are evident in Figure 2 for samples produced with concentrations of
25 nitrogen greater than for the invention.

- N3 Centre:



30

N3 centre is not FTIR active and, accordingly, does not appear in Figures 1 and 2. However, N3 centres show a sharp band at 415 nm in photoluminescence (PL) and UV spectroscopy. This centre consists of three nitrogen atom
5 surrounding a vacancy (V).

- Platelets:

Platelets consist of one or two extra atomic layers
10 inserted in the diamond lattice. The nature of the platelets is still be analyzed in detail in diamond lattice. However, the fact that the corresponding IR band is observed only in diamonds containing an appreciable amount of nitrogen suggests that platelet contain
15 nitrogen, and probably consist either partly or entirely of nitrogen. The position of the platelet peak varied from 1354-1384 cm^{-1} from sample to sample. This variation of position is attributed to the susceptibility of the platelets to strain induced into the crystal by the A and
20 B-aggregates defects. The presence of the platelet absorption indicates A-aggregates start to diffuse to form B-aggregates. The platelet peak position is inversely correlated to platelet size. Accordingly, the presence of platelets at 1370 cm^{-1} is a strong indication that the size
25 of the platelets is large.

From the results described above we can conclude that in the samples grown with the flow rates of nitrogen in the range 0.02% to 2 % the nitrogen is present in the form of
30 A-, B-aggregates and platelets.

Photoluminescence spectroscopy was performed on samples produced with a nitrogen gas flow of 0.0002 to 0.002 vol%.

The spectroscopy results are shown in Figure 3 and show peaks at 1.945 and 2.14eV which correspond to N-V and (N-V)⁻ centres of nitrogen. Accordingly, the samples produced in accordance with the invention are not nitrogen-free,
5 but have substantially less nitrogen centre defects than result from using relatively high concentrations of nitrogen in CVD gas in accordance with Yamazaki.

Scanning electron microscopy of samples grown at nitrogen
10 concentrations in the range according to the invention are shown in images in Figures 4 and 5. The images are taken in the range of magnification 500-5000 and the step-wise growth of diamond is evident from the surface of diamond shown in the images.

15 Figure 4 is the image of a sample of diamond grown with 0.03 % flow of nitrogen in the flow of the CVD gases. Steps in the growing crystal are evident in Figure 4. The steps are the lines along which the diamond grows in
20 accordance with the invention. The surface morphology of the same sample is evident in Figure 5 in which the high density of the growth steps is clearly evident.

A high density of the growth steps on the surface of a
25 sample grown with nitrogen flow in accordance with the invention is also evident in Figure 6. These growth steps are present due to the screw dislocation observed in the crystal growth process of a number of materials and are a clear signature that the diamond in accordance with the
30 invention system grows with the help of dislocations and with a step growth mechanism.

Selecting a relatively small quantity of nitrogen in CVD

gases ensures that the purity and quality of the diamond is maintained. Selection of a relatively small quantity of nitrogen also causes diamond growth in a step-wise manner, i.e. with a layer of diamond having an edge that grows as
5 a front defined by a step. The occurrence of step-growth is evident in Figures 4 to 6.

In the circumstances that less than 0.001 vol% nitrogen is present in CVD gases, diamond grows with graphitic
10 inclusions that detrimentally affect properties of the diamond.

For example, Figures 7 and 8 show graphitic (dark) inclusions in CVD grown diamond with 0.0005 vol% and
15 0.0008 vol% nitrogen respectively. In each of Figures 7 and 8, steps in the layers of diamond are irregular and defective and are believed to be the cause of the graphitic inclusions.

20 In contrast, CVD diamond grown in gas including 0.0012 vol% nitrogen in accordance with the invention includes regular equidistant steps and is substantially free of graphitic inclusions as shown in Figure 9. It is believed that such diamond results from a CVD process including
25 0.001 vol% or more nitrogen in CVD gas.

Specifically, this threshold volume of nitrogen is believed to be essential to cause the diamond growth with steps clear of impurity and defects.

30

A concentration of nitrogen higher than 0.02 vol% in the gas phase results in A- and B-aggregates and platelets forming in the diamonds and result in microscopic and macroscopic graphitic inclusions. Such inclusions and
35 defects adversely affect the properties of the formed diamond.

The step-growth mechanism, however, is advantageous because it is less susceptible to incorporating defects and inclusions in the formed diamond, with the result that formed diamond is substantially free of defects and
5 inclusions. Such formed diamond is gem quality and has superior electrical, optical and mechanical properties compared to other forms of diamond grown by CVD and properties that approach the properties of natural diamond.

10

Reference to any prior art in the specification is not, and should not be taken as, an acknowledgment or any form of suggestion that this prior art forms part of the common general knowledge in Australia or any other country.

15

Many modifications may be made to the preferred embodiment of the present invention as described above without departing from the spirit and scope of the present invention.

20

It will be understood that the term "comprises" or its grammatical variants as used in this specification and claims is equivalent to the term "includes" and is not to be taken as excluding the presence of other features or
25 elements.