

Abstract

5 Provided is a polypropylene resin composition which is good in extrusion property, which is good in appearance and low in variation in thickness when formed into a film, which is well-balanced in dynamic characteristics, and which has high heat resistance. A polypropylene resin composition satisfying the following requirements (1) to (3): (1) a melt flow rate (MFR) measured under a load of 2.16 kg at 230°C according to ASTM D1238 is 1 to 10 g/10 min; (2) a pentad isotactic fraction measured using ^{13}C -NMR is 0.930 or more; and (3) M_z is 600000 to 1400000, and M_w/M_n is 6.5 to 14.0.