Claims:

1. A method for producing hydrogel contact lenses, comprising the steps of:
(1) obtain a first polymerizable fluid composition and a second polymerizable fluid composition, wherein the first polymerizable fluid composition comprises at least one first free-radical initiator, at least one first polymerizable material, and at least one photochromic compound, wherein said at least one first polymerizable material comprises at least one first polysiloxane vinylic crosslinker that has a weight-averaged molecular weight of about 5000 Daltons or higher and is present in the first polymerizable composition in an amount of about 40% by weight or more, wherein the second polymerizable fluid composition comprises said at least one second free-radical initiator and at least one second polymerizable material and is free of any photochromic compound;
(2) obtaining a lens mold, wherein the lens mold comprises a male mold half (104) having a first molding surface defining the posterior surface of a contact lens (100) to be molded and a female mold half (102) having a second molding surface defining the anterior surface of the contact lens to be molded, wherein the female and male mold halves are configured to receive each other such that a mold cavity is formed between the first and second molding surfaces when the mold is closed;
(3) applying a drop of the first polymerizable fluid composition onto the geometrial center of the first molding of the male mold half, wherein the drop has a volume of about 5µL or less;
(4) dispensing an amount of the second polymerizable fluid composition on the second molding surface of the female mold half;
(5) closing the female mold half with the male mold half having the drop adhered thereon to form a molding assembly comprising the second polymerizable composition and the drop of the first polymerizable composition within the mold cavity;
(6) curing the second polymerizable fluid composition and the drop of the first polymerizable composition to form an unprocessed silicone hydrogel contact lens having a central photochromic zone (112) that has a diameter of about 13 mm or less, is concentric with the central axis (101) of the unprocessed silicone hydrogel contact lens;
(7) separating the molding assembly into the male and female mold halves, with the unprocessed silicone hydrogel contact lens adhered onto a lens-adhered mold half which is one of the male and female mold halves;
(8) removing the unprocessed silicone hydrogel contact lens from the lens-adhered mold half; and

(9) subjecting the unprocessed silicone hydrogel contact lens to post-molding processes including a hydration process and one or more other processes selected from the group consisting of extraction, surface treatment, packaging, sterilization, and combinations thereof.

2. The method of claim 1, wherein the step of (6) curing is carried out thermally, wherein said at least one first and second free-radical initiators comprise a thermal free-radical initiator.
3. The method of claim 1, wherein the step of (6) curing is carried out actinically, wherein said at least one first and second free-radical initiators comprise a free-radical photoinitiator.
4. The method of any one of claims 1 to 3, wherein the first polymerizable fluid composition further comprises at least one visible light free-radical photoinitiator, wherein the drop of the first polymerizable fluid composition is irradiated with a visible light for about 10 second or less before dispensing the second polymerizable fluid composition.
5. The method of any one of claims 1 to 4, wherein said at least one first and second polymerizable materials independent of each other comprises: (a) at least one silicone-containing vinylic monomer, (b) at least one second polysiloxane vinylic crosslinker, at least one non-silicone vinylic crosslinker, or combinations thereof, (c) at least one hydrophilic vinylic monomer, and optionally (d) at least one component selected from the group consisting of a non-silicone hydrophobic vinylic monomer, a UV-absorbing vinylic monomer, and combinations thereof,

   wherein said at least one hydrophilic vinylic monomer comprises: (i) at least one hydrophilic (meth)acrylamido monomer having 3 to 8 carbon atoms; (ii) at least one hydrophilic (meth)acryloxy monomer; (iii) at least one hydrophilic N-vinyl amide monomer; or (iv) combinations thereof.

   wherein said at least one silicone-containing vinylic monomer comprises: (i) at least one silicone-containing vinylic monomer containing a tris(trialkylsiloxy)silyl group and one sole ethylenically-unsaturated group selected from the group consisting of a (meth)acryloyloxy group, a (meth)acryloylamino group, a vinyl carbonate group, and a vinylcarbamate group; (ii) at least one silicone-containing vinylic monomer containing a bis(trialkylsilyloxy)-alkylsilyl group and one sole ethylenically-unsaturated group selected from the group consisting of a (meth)acryloyloxy group, a (meth)acryloylamino group, a vinyl carbonate group, and a vinylcarbamate group; (iii) at least silicone-containing vinylic monomer containing a) one sole ethylenically-unsaturated group selected from the group consisting of a (meth)acryloyloxy group, a (meth)acryloylamino group, a vinyl carbonate group, and a vinylcarbamate group and b) a polysiloxane chain

having 2 to 30 siloxane units and terminated with an alkyl, hydroxyalkyl or methoxyalkyl group; or (iv) combinations thereof.

6. The method of claim 5, wherein the sum of the amounts of components (a), (b) and (c) in the monomer mixture is at least about 60% by weight relative to the total weight of all polymerizable materials present in the monomer mixture.
7. The method of claim 5 or 6, wherein said at least one first and second polymerizable materials independent of each other comprise at least one second polysiloxane vinylic crosslinker.
8. The method of any one of claims 1 to 7, wherein said at least one first and second polymerizable materials independent of each other comprises: at least one non-silicone vinylic crosslinker; at least one non-silicone hydrophobic vinylic monomer; at least one UV-aborbing vinylic monomer; or combinations thereof.
9. The method of any one of claims 1 to 8, wherein said at least one photochromic compound comprises a naphthopyran, an indeno-fused naphthopyran (i.e., indeno-naphthopyran), a heterocyclic ring-fused naphthopyrian, a benzopyran, a phenanthropyran, a quinopyran, a quinolinopyran, a fluoroanthenopyran, an anthracene-fused pyran, a tetracene-fused pyran, a spiro(benzindoline) naphthopyran, a spiro(indoline)naphthopyran, a spiro(indoline)benzopyran, a spiro(indoline)quinopyran, a spiro(indoline)pyran, a naphthoxazine, a spirobenzopyran, a spirobenzothiopyran, a naphthacenedione, a benzoxazine, a spirooxazine, a naphthoxazine, a spiro(benzindoline)naphthoxazine, a spiro(indoline)naphthoxazine, a spiro(indoline)pyrido-benzoxazine, a spiro(indoline)benzoxazine, a spiro(benzindoline) benzoxazine, a spiro(benzindoline)pyridobenzoxazine, a spiro(indoline) fluoranthenoxazine, a spiro(indoline)-quinoxazine, a spiropiperidine-naphthopyran, a piro(indoline)pyronobenzoxazinone, a benzospiropyran, a naphthospiropyran, a spirobenzoxazine-pyrrolopyridine, a spironaphthoxazine-pyrrolopyrridine, a spiro-oxazepin-benzoxazine, a spiro-oxazepin-naphthoxazine, a spiro(indoline) benzothiazoloxazine, a spiro(indoline)benzopyrroloxazine, a spiro(indoline)quinazolino-oxazine, a spiro(indoline)-anthracenobenzoxazine, a benzofurobenzopyran, a benzothienobenzopyran, a naphthofurobenzopyran, a benzopyrano-fused naphthopyran, a spiro(isoindoline)-naphthoxazine, a spiro(isoindoline)benzoxazine, or a mixture thereof.
10. The method of any one of claims 1 to 9, wherein said at least one photochromic compound is polymerizable (i.e., comprising an ethylenicaly-unsaturated group).
11. The method of claim 10, wherein said at least one photochromic compound is a coupling reaction product of a reactive (meth)acrylamido or (meth)acryloxy monomer having a first reactive functional group and a reactive photochromic compound have a

second reactive functional group in the absence or presence of a coupling agent under coupling reaction, wherein the first reactive functional group is selected from the group consisting of –COCl, –COBr, –COOH, –NHR_{N2}, –NCO, –OH, –CHO, , , or ; wherein the second reactive functional group is selected from the group consisting of –COOH, –NHR_{N2}, , , , –NCO, –OH, –SH, –CHO, , , or , wherein R_0 is hydrogen or methyl and R_{N2} is hydrogen, a linear or branched C_1-C_{15} alkyl, cyclohexyl, cyclopentyl, a substituted or unsubstituted phenyl, or a substituted- or unsubstituted-phenyl-C_1-C_6 alkyl.

12. The method of claim 11, wherein the reactive (meth)acrylamido or (meth)acryloxy monomer is selected from the group consisting of (meth)acryloyl halides (CH_2=CH–COX or CH_2=CCH_3–COX, X= Cl or Br), N-hydroxysuccinimide ester of (meth)acrylic acid, glycidyl (meth)acrylate, isocyanato- C_2-C_6 alkyl (meth)acrylate, amino–C_2-C_6 alkyl (meth)acrylamide, C_1-C_6 alkylamino–C_2-C_6 alkyl (meth)acrylamide, (meth)acrylic acid, C_2-C_4 alkylacrylic acid (e.g., ethylacrylic acid, propylacrylic acid, butylacrylic acid), N-2-acrylamidoglycolic acid, 3-(acryloylxy)propanoic acid, C_2-C_6 hydroxylalkyl (meth)acrylate, C_2-C_6 hydroxyalkyl (meth)acrylamide, azlactone-containing vinylic monomers (e.g., 2-vinyl-4,4-dimethyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-1,3-oxazolin-5-one, 2-vinyl-4-methyl-4-ethyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-butyl-1,3-oxazolin-5-one, 2-vinyl-4,4-dibutyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-dodecyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-diphenyl-1,3-oxazolin-5-one, 2-isopropenyl-4,4-pentamethylene-1,3-oxazolin-5-one, 2-isopropenyl-4,4-tetramethylene-1,3-oxazolin-5-one, 2-vinyl-4,4-diethyl-1,3-oxazolin-5-one, 2-vinyl-4-methyl-4-nonyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-phenyl-1,3-oxazolin-5-one, 2-isopropenyl-4-methyl-4-benzyl-1,3-oxazolin-5-one, 2-vinyl-4,4-pentamethylene-1,3-oxazolin-5-one, and 2-vinyl-4,4-dimethyl-1,3-oxazolin-6-one, with 2-vinyl-4,4-dimethyl-1,3-oxazolin-5-one (VDMO) and 2-isopropenyl-4,4-dimethyl-1,3-oxazolin-5-one (IPDMO) as preferred azlactone-containing vinylic monomers), aziridinyl C_1-C_{12} alkyl (meth)acrylate (e.g., 2-(1-aziridinyl) ethyl (meth)acrylate, 3-(1-aziridinyl) propyl (meth)acrylate, 4-(1-aziridinyl) butyl (meth)acrylate, 6-(1-aziridinyl) hexyl (meth)acrylate, or 8-(1-aziridinyl) octyl (meth)acrylate), acrolein, methacrolein, crotonaldehyde, and combinations thereof.

13. The method of claim 11 or 12, wherein the reactive photochromic compound is: 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-

b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxy-13-phenyl-3H,13H-indeno [2',3':3,4] naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-propyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxy-13-propyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-10,11-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-10,11-dimethoxy-13-(2-hydroxycarbonylethyl)carboxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-hydroxymethyl-13-methyl-3H,13H-indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-(2-hydroxycarbonylethyl)carboxymethyl-13-methyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-hydroxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-7-methoxy-11-phenyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno-[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-phenyl-13-hydroxy-13-methyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-phenyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,7,10,11-tetramethyl-13-(2-hydroxycarbonylethyl)carboxy-13-methyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-11-(4-(4,5-diphenyl-1H-imidazol-2-yl)phenyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6-methoxy-7-(3-hydroxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1.2-b]pyran; 3,3-di(4-methoxyphenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl)-carboxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1.2-b]pyran; 3,3-di(4-methoxyphenyl)-6,7-dimethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11,13-trimethyl-13-(2-(2-hydroxyethoxy)-ethoxy)-indeno[2,1-f]naptho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11,13-trimethyl-13-(2-(2-(2-(2-hydroxyethoxy)ethoxy)ethoxy)ethoxy)-indeno[2,1-f]naptho[1,2-b]pyran; 3,3-diphenyl-13-hydroxy-13-(2-oxo-2-ethoxyethyl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-(2-oxo-2-ethoxyethyl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-6,11-dimethyl-13-butyl-13-hydroxy-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13,13-diethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-

methoxy-11-phenyl-13,13-dipropyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-hydroxyphenyl)-7-methoxy-11-phenyl-13-carbomethoxy-13-methyl-3H,13H-indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-diphenyl-6,7-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxy-ethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3,3-diphenyl-6,7,10,11-tetramethoxy-13-ethyl-13-methyl-13-hydroxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho [1,2-b]pyran; 6,7-dimthoxy-2,2-diphenyl-13-hydroxy-13-butyl-2H,13H-indeno[1',2':4,3] naphtho[1,2-b]pyran; 6,7-dimthoxy-2,2-diphenyl-13-hydroxy-13-methyl-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 6,7-dimthoxy-2,2-diphenyl-13-hydroxy-2H,13H-indeno[1',2':4,3]naphtho[1,2-b]pyran; 3-(4-allyloxyphenyl)-3-(4-morpholinophenyl)-7-methoxy-11-phenyl-13,13-dimethy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(piperazin-1-yl)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3:4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(4-hydroxybenzamido)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3:4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-vinyl-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3:4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-butoxyphenyl)-10-(carboxylic acid)-6-trifluoromethyl-13,13-dimethyl-3H,13H-indeno[2',3':3:4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-methoxyphenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-methoxyphenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-fluorophenyl)-3-(4-morpholinophenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1.2-b]pyran; 3-(4-fluorophenyl)-3-(4-morpholinophenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4] naphtho[1.2-b]pyran; 3-(4-hydroxyethoxyphenyl)-3-(4-methoxyphenyl)-11-(4-(N,N-dimethylamino)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,4-dimethoxyphenyl)-phenyl-6,11-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(3-methyl-4-methoxyphenyl)-13-hydroxy-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7,10,11-tetramethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno [2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-6,7-dimethoxy-13-hydroxy-13-methyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-13-oxo-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-phenyl-6-methoxy-7-

mprphlino-13-methyl-13-methyl-13-hydroxyethoxyethoxyethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-phenyl-6,11-dimethoxy-13-methyl-13-methyl-13-hydroxyethoxy-ethoxy-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-(4-morpholinophenyl)-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b] pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-hydroxy-13-ethyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-hydroxy-13-butyl-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-morpholinophenyl)-3-phenyl-6,7-dimethoxy-13-oxo-3H,13H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyethoxyphenyl)-6-methoxy-7-morpholino-13,13-dimethyl-3H,13H-indeno-[2',3':3,4] naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonylethyl)carboxyethoxy-phenyl)-6-methoxy-7-morpholino-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxyethoxy)phenyl)-6-methoxy-7-piperidino-13,13-dimethy-3H,13H-indene[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-(2-hydroxycarbonylethyl)-carboxyethoxy)phenyl)-6-methoxy-7-piperidino-13,13-dimethy-3H,13H-indene[2',3':3,4] naphtho[1,2-b]pyran; 3-phenyl-3-(4-hydroxyphenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[I,2-b]pyran; 3-phenyl-3-(4-hydroxyethoxy)phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]-naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonylethyl)carboxyethoxy)phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(2-hydroxycarbonylethyl)carboxy-phenyl)-6,7-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[I,2-b]pyran; 3-phenyl-3-(4-(4-(2-hydroxyethyl)piperazin-1-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-(2-(2-hydroxycarbonylethyl)-carboxyethyl)piperazin-1-yl)phenyl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-piperazinyl-13,13-dimethyl-3H,13H-indene[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(3-hydroxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3":3.4]naphtho[1.2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl) carboxymethylenepiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3":3.4]naphtho[1.2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(4-hydroxypipendin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl)-carboxypipendin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-methoxyphenyl-piperazin-1-yl)phenyl)-13,13-dimethyl-6-methoxy-7-hydroxy-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-methoxyphenyl-piperazin-1-yl)phenyl)-13,13-dimethyl-6-methoxy-7-(2-hydroxy-2-methyl-3-butyn-4-yl)-indeno[2',3':3,4]naphtho [1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-hydroxymethylene-

piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-(2-hydroxycarbonyl-ethyl)carboxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3.4]-naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(3-(2-hydroxycarbonylethyl)carboxymethylene-piperidin-1-yl)-13,13-dimethyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1.2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl)-carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4] naphtho[1.2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6-methoxy-7-piperazinyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho [1.2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-6,11-dimethyl-13-hydroxy-13-(1-oxo-methoxyprop-2-yl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(4-phenylpiperazino)-phenyl)-6-methoxy-7-(4-hydroxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4] naphtho[1.2-b]pyran; 3-phenyl-3-(4-(4-phenylpiperazino)phenyl)-6-methoxy-7-(4-(2-hydroxycarbonylethyl) carboxypiperidin-1-yl)-13,13-dimethyl-3H,13H-indeno[2',3':3,4] naphtho[1.2-b]pyran; 3-phenyl-3-(4-piperazinylphenyl)-6,11-dimethoxy-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho-[1,2-b]pyran; 3-phenyl-3-(4-piperazinylphenyl)-6-methoxy-7-piperidinyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-(3-methylpiperazin-1-yl)phenyl)-6-methoxy-7-(decahydroisoquinolin-2-yl)-11-*tert*-butyl-13,13-dimethyl-3H,13H-indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(4-morpholinophenyl)-16-(ethoxycarnobyl)methyl-16-hydroxy-3,16-dihydrobenzofuro-[2',3':7,8] indeno[2',3':3,4]naphtho[1,2-b]pyran; 3-phenyl-3-(4-methoxyphenyl)-16-(ethoxycarnobyl)-methyl-16-hydroxy-3,16-dihydrobenzofuro [2",3":6',7']indeno-[3',2':4,3]naphtho[1,2-b]pyran; 3-phenyl-3-(4-morpholinophenyl)-16-(ethoxycarnobyl)-methyl-16-hydroxy-3,16-dihydrobenzofuro[2",3":6',7']indeno[3',2':4,3] naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-(ethoxycarbonyl)methyl-16-hydroxy-3,16-dihydro-benzofuro[2',3':7,8]indeno[2',3':3,4] naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16-ethyl-16H-benzofuro[2',3':7,8] indeno[2',3':3,4]naphtho [1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16H-benzofuro [2",3":6,7]indeno [3',2':4,3]naphtho-[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-16-hydroxy-16-ethyl-16H-benzofuro[2",3":6,7]-indeno[3',2':4,3]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,3-diydrobenzofur-5-yl)-13-hydroxy-13-methyl-indeno[2,1-f]naphtho[1,2-b]pyran; 3-(4-methoxyphenyl)-3-(2,3-dihydrobenzofur-5-yl)-6,11-difluoro-13-hydroxy-13-(1-oxo-methoxyprop-2-yl)-1H-indeno[2,1-f]naphtho[1,2-b]pyran, or a mixture thereof.

14. The method of claim 11 or 12, wherein the reactive photochromic compound is 2,2-di(4-fluorophenyl)-5-hydroxycarbonyl-6-phenyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methylphenyl)-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-

methoxyphenyl)-5-methoxycarbonyl-6-hydroxy-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxyethoxycarbonyl-6-methyl-8-vinyl-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxyethoxycarbonyl-6-methyl-8-hydroxycarbonyl-2H-naphtho [1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-(2-hydroxyethoxy)ethoxy-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-phenyl-9-(2-hydroxyethoxy)-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxy-carbonyl-6-(4-(2-hydroxyethoxy)phenyl)-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-diphenylmethylol-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-diphenylmethylol-6-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-hydroxyethoxylcarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-hydroxyethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-(2-hydroxyethoxy)ethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-(2-(2-(2-(2-hydroxyethoxy)ethoxy)ethoxy)-ethoxycarbonyl)-6-phenyl-[2H]-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-methyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-phenyl-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-hydroxymethyl-6-methoxy-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-methoxycarbonyl-6-(3-aminophenyl)-2H-naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-2,5,7-trihydro-7-methylidine-5-oxo-furo-[3',4':3,4]naphtho[1,2-b]pyran; 2,2-bis(4-methoxyphenyl)-5-phenylthio-6-hydroxy-2H-naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-13-hydroxy-13-methyl-indeno[2,1-f]naphtho[1,2-b]pyran; 3,3-di(4-methoxyphenyl)-9-methoxycarbonyl-8-(2-hydroxyethoxy)ethoxy-[3H]-naptho[1,2-b]pyran; 2,2-diphenyl-5-hydroxycarbonyl-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxycarbonyl-8,9-dimethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-morpholinocarbonyl-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-carbomethoxy-9-methoxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-hydroxy-6-morpholinocarbonyl-2H-naphtho[1,2-b]pyran; 2,2-diphenyl-5-methylol-6-(3-dimethylaminopropyl)methylamino-2H-naphtho[1,2-b]pyran;2,2-diphenyl-2,5,7-trihydro-7-methyliden-5-oxofuro-[3',4':3,4]naphtho[1,2-b]pyran; 2,2-spiroadamantylene-5-phenylthio-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-diphenyl)-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2,2-spiro-admamtylene-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran, 3,3-diphenyl-8-hydroxy-9-carbopropoxy-3H-naphtho[2,1-b]pyran; 2,2,5-triphenyl-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2,2,6-triphenyl-5-(2-(2-(2-(2-hydroxyethoxy)ethoxy)-ethoxy)ethoxy)carbonyl-[2H]-naphtho[1,2-b]pyran; 2,2,6-triphenyl-5-(2-(2-(2-oxiran-2-ylmethoxy)ethoxy)ethoxy)-ethoxycarbonyl)-

[2H]-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-(4-morpholinophenyl)-5-hydroxy-6-carboethoxy-2H-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-tert-butyl-5-methoxy-carbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-methoxyphenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-(2-(2-hydroxyethoxy)ethoxy)-ethoxyphenyl)-2-phenyl-5-methoxycarbonyl-6-methyl-9-methoxy-[2H]-naphtho[1,2-b]pyran; 2-(4-(2-(2-hydroxyethoxy)ethoxy)phenyl)- 2-phenyl-5-methoxycarbonyl-6-(2-(2-methylprop-2-enoxyloxy)ethoxy)-[2H]-naphtho[1,2-b]pyran; 3-(4-(2-(2-hydroxyethoxy)-ethoxy)ethoxyphenyl)-3-phenyl-9-methoxycarbonyl-8-methoxy-[3H]-naptho[1,2-b]pyran; 2-(4-morpholinophenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(9-ethylcarbazol-2-yl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(9-phenylcarbazol-2-yl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 2-(4-dimethylaminophenyl)-2-phenyl-5-methoxycarbonyl-6-hydroxy-2H-naphtho[1,2-b]pyran; 3-(2-flurophenyl)-3-(4-methoxyphenyl-8-hydroxy-9-carbopropoxy-3H-naphtho[2,1-b]pyran; 3-(2-flurophenyl)-3-(4-methoxyphenyl-8-hydroxy-9-carbomethoxy-3H-naphtho[2,1-b]pyran; 3-(2,4-dimethoxyphenyl)-3-(4-methoxyphenyl-8-hydroxy-9-carbomethoxy-3H-naphtho[2,1-b]pyran; 3-(2,4,6-triflurophenyl)-3-(2,4,6-trimethoxy-1-naphthyl)-8-acetyl-9-carboniloyl-3H-naphtho[2,1-b]pyran; 3-(4-methoxyphenyl)-3-(2-methyl-2,3-dihydrobenzofur-5-yl)-6-methoxy-12-hydroxymethyl-11-phenyl-3H-phenanthro[1,2-b]pyran; 5,5-bis(4-methoxyphenyl)-8-methylol-5H-fluorantheno[3,2-b]pyran; or a mixture thereof.

15. The method of claim 11 or 12, wherein the reactive photochromic compound is 1-hydroxyethyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-hydroxypropyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-aminoethyl-3,3-dimethyl-5-chlorospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-hydroxyethyl-3,3-dimethyl-8'-methoxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-(p-vinylphenyl)-3,3-dimethyl-5,6-dichlorospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-5'-hydroxymethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-9'-aminospiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,3,3-trimethyl-5-chloro-8'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-benzyl-3,3-dimethyl-9'-vinylbenzoyloxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-benzyl-3,3-dimethyl-5'-hydroxymethylpiperidinospironaphthooxazine; 1,3,3-trimethyl-9'-hydroxyspiro[indoline-2,3'-[3H]-pyrido-[2,1-b][1,4]benzooxazine]; 5-hydroxy-6'-cyano-1,3,3-trimethyl-spiro-[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-hydroxy-6'-phenylsulfonyl-1,3,3-trimethyl-spiro-[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5'formyl-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine; 1,3-dihydro-6'-piperazino-

1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine; 1,3-dihydro-6'-(4-hydroxyethyl)piperazino-1,3,3-trimethyl spiro [2H indole-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine; 1,3-dihydro-9'-hydroxy-1,3,3-trimethyl spiro 92H indole-2,3'-[3H]-naphtho[2,1-b][1,4] oxazine; 1,3,3,4,5-pentamethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1,3,3,5,6-pentamethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-propyl-3,3,4,5-tetramethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-propyl-3,3,5,6-tetramethyl-9'-methoxycarbonyl-8'-hydroxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-methoxyethyl-3,3-dimethyl-9'-allyloxycarbonyl-8'-chloroactoxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 1-allyl-3,3-spirocyclohexyl-9'-benzyloxycarbonyl-8'-chloroactoxy-spiro[indoline-2,3'-[3H]naphth[2,1-b][1,4]oxazine; 5-amino-1,3,3-trimethyl-spiro[indoline-2,3'-[3H]-pyrido[3,4-f][1,4]benzoxazine; 6-hydroxy-1',3',3',4',5'-pentamethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 6-hydroxy-1',3',3',5',6'-pentamethylspiro[2H-1,4-benzoxazine-2,2'-indoline]; 5,7-dimethoxy-1'-hydroxy-carbonylethyl-3',3'-dimethylspiro[2H-1,4-bezoxazine-2,2'-indoline]; 7-methoxy-1'-hydroxy-ethyl-3',3'-dimethylspiro[2H-1,4-bezoxazine-2,2'-indoline]; 9'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 5-chloro-9'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-5-methoxy-1-methylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 8'-hydroxy-1,4,5-trimethylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-isopropylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-hexadecyl-spiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 9'-hydroxy-1-octadecylspiro[indoline-2,3'-(3H)-naphtho(2,1-b)-1,4-oxazine]; 1,1"-(1,5-pentanediyl)bis[3,3-dimethyl]-9'-hydroxy-spiro[indoline-2,3'-[3H]-naphtho[2,1-b] [1,4]oxazine]; 1,1"-[1,4-phenylenebis(methylene)] bis[3,3-dimethyl]-5'-hydroxymethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b] [1,4]oxazine]; 1,1"-(1,4-butanediyl)bis[5,6-dichloro-3,3-dimethyl]-8'-hydroxyspiro[indoline-2,3'-[3H]-naphtho[2,1-b] [1,4]oxazine]; 1,3,3-trimethyl-9'-hydroxypiperidinospironaphthooxazine; 3-carboxyethyl-1,1-dimethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1-carboxyethyl-3,3-dimethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 1,1-dimethyl-3-hydroxyethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 3,3-dimethyl-1-hydroxyethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 3-carboxyethyl-1,1-dimethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 1-carboxyethyl-3,3-dimethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 1,1-dimethyl-3-hydroxyethyl-9'-methoxyspiro[benz[e]-indoline-2,3'-

[3H]-pyrido[2,1-b][1,4]benzoxazine]; 3,3-dimethyl-1-hydroxyethyl-9'-methoxyspiro[benz[g]-indoline-2,3'-[3H]-pyrido[2,1-b][1,4]benzoxazine]; 5-amino-5'-(2-benzthiazolyl)-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-amino-5'-(5'-(2-hydroxyphenyl)-2-oxadiazolyl)-1-isopropyl-3,3-dimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; 5-amino-5'-(5'-phenyl-2-oxadiazolyl)-1,3,3-trimethylspiro[indoline-2,3'-[3H]-naphtho[2,1-b][1,4]oxazine]; or a mixture thereof.

16. The method of claim 11 or 12, wherein the reactive photochromic compound is 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-(2-hydroxycarbonylethyl)carboxyethoxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; 3,3-bis(4-methoxyphenyl)-6,11-dimethyl-13-hydroxy-13-phenyl-3H,13H-indeno [2',3':3,4]naphtho[1,2-b]pyran; or a mixture thereof.
17. The method of any one of claims 1 to 16, wherein said at least one first and second polymerizable materials independent of each other comprises at least one polymerizable UV/HEVL-absorbing compound.