

WETTABLE SILICONE HYDROGEL COMPOSITIONS
AND METHODS FOR THEIR MANUFACTURE

BACKGROUND OF THE INVENTION

This application is a continuation-in-part application of copending application Ser. No. 07/788,013 filed November 5, 1991.

Field of the Invention

The present invention relates to improved wettable polymeric hydrogel compositions useful for the production of biomedical devices, especially contact lenses.

Background

Hydrogels have been a desirable class of material for the preparation of biomedical devices, and have been known since at least Wichterle, et al U.S. Patent No. 3,220,960 which disclosed hydrogels comprising a hydrated polymer of a hydroxyalkyl acrylate or methacrylate crosslinked with a corresponding diester (poly 2-hydroxyethyl methacrylate, known as poly-HEMA).

A hydrogel is a hydrated crosslinked polymeric system that contains water in an equilibrium state. The physical properties of hydrogels can vary widely and are mostly determined by their water content. Since hydrogels exhibit excellent biocompatibility, there has

REPLACED SHEETS SG

- ☒ Description : paged to paged 27...
☒ Claim(s) : paged 28 to paged 44...
☐ Drawing(s) : paged to paged
☐ Abstract : paged to paged

This Sheet Has Been Replaced



been extensive interest in the use of hydrogels for biomedical devices, especially contact lenses.

In the field of contact lenses, various factors must combine to yield a material that has appropriate characteristics. Oxygen permeability, wettability, material strength and stability are but a few of the factors which must be carefully balanced to achieve a useable end-result contact lens. Since the cornea receives its oxygen supply exclusively from contact with the atmosphere, good oxygen permeability is a critical characteristic for any contact lens material.

It was discovered that certain crosslinked polymeric materials could be hydrated and retain their water content. It was further found that the higher the water content within contact lenses made from these crosslinked hydrogel polymers, the greater was the oxygen permeability through the lens to the cornea.

High water-containing hydrogels have at times exhibited undesirable mechanical properties. For example, such hydrogels are often not easily formed into hydrolytically stable lenses. Further such materials have at times exhibited tearing or other breakage as a result of poor tensile strength. What was needed was a highly oxygen permeable material that was durable and

This Sheet Has Been Replaced



highly wettable. Wettability is important in that, if the lens is not sufficiently wettable, it does not remain lubricated and therefore cannot be worn comfortably in the eye. The optimum contact lens would have not only excellent oxygen permeability, but also excellent tear fluid wettability.

Silicone-containing materials were tried as viable contact lens materials and displayed very good oxygen permeability and durability. However, most silicone-containing materials are largely hydrophobic and therefore not sufficiently wettable. Further, it is believed that such hydrophobicity causes enhanced deposit problems, which may also result in discomfort when wearing contact lenses made from certain silicone-containing polymers.

Therefore, an optimal hydrogel material for biomedical devices, such as contact lenses, would have ideal rigidity, high oxygen permeability and a high degree of wettability.

SUMMARY OF THE INVENTION

In accordance with this invention, the surface wettability of hydrogels, such as silicone-containing

This Sheet Has Been Replaced



hydrogels, and more specifically polyurethane-silicone hydrogels and ethylenically terminated polysiloxane hydrogels such as (poly)organosiloxane hydrogels, are significantly enhanced by incorporating both at least one vinyl-containing hydrophilic monomer and at least one acrylic-containing hydrophilic monomer into the monomer mix along with the silicone-containing monomer or prepolymer.

Further, in accordance with the present invention, a method for making a wettable silicone-containing hydrogel composition is disclosed comprising the steps of a) combining at least one vinyl-containing monomer, at least one acrylic-containing monomer and at least one silicone-containing monomer or prepolymer into a monomer mix and b) curing the monomer mix resulting from step a) to form a silicone-containing hydrogel composition.

It is believed that the combined vinyl-containing and acrylic-containing monomers act as wetting agents, and interact with the predominantly hydrophobic silicone-containing monomers and prepolymers in the monomer mix to produce highly wettable hydrogels with ideal rigidity. Such resultant hydrogels are especially well-suited for use as contact lens materials.

This Sheet Has Been Replaced



BRIEF DESCRIPTION OF THE DRAWINGS

Figures 1 and 2 depict the effect on modulus of polyurethane films as the composition ratio of NVP to DMA is changed.

Figure 3 depicts the effect on modulus of methacrylate-capped polysiloxane films as the composition ratio of NVP to DMA is changed.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to improved wettability of hydrogels, especially silicone-containing hydrogels with ideal rigidity suitable for biomedical applications such as contact lenses.

The silicone-containing hydrogels of the present invention display improved wettability as a result of the combined presence in the monomer mix of at least one acrylic-containing monomer and at least one vinyl-containing monomer.

Silicone hydrogels (i.e., hydrogels containing silicone) are usually prepared by polymerizing a mixture containing at least one silicone-containing monomer and

This Sheet Has Been Replaced



at least one hydrophilic monomer. Either the silicone-containing monomer or the hydrophilic monomer may function as a crosslinking agent (a crosslinker being defined as a monomer having multiple polymerizable functionalities) or a separate crosslinker may be employed.

The term "vinyl-containing" is meant to refer to non-acrylic monomers having the vinyl grouping ($\text{CH}_2=\text{CH}-$) which are generally highly reactive. Such vinyl groups are known to polymerize relatively easily. "Acrylic-containing" monomers are those compounds containing the acrylic grouping ($\text{CH}_2=\text{C}(\text{COX})$) which are also generally reactive.

The vinyl-containing monomers used in the present invention include hydrophilic monomers such as N-vinyl pyrrolidone, N-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, N-vinyl formamide, with N-vinyl pyrrolidone (NVP) being the most preferred.


The acrylic-containing monomers used in the present invention include hydrophilic monomers such as 2-hydroxyethyl methacrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, N,N-dimethyl (meth)acrylamide, diacetone acrylamide, methacrylic acid

This Sheet Has Been Replaced



54

2

$$\begin{array}{c} A'a' \\ | \\ R_1' \\ \swarrow \quad \searrow \\ S_a' \quad V_v' \end{array}$$
 γ denotes
$$\begin{array}{c} \text{R}_5' \quad \text{R}_6' \\ \diagdown \quad \diagup \\ \text{C}=\text{C} \\ \diagup \quad \diagdown \\ -\text{Z}-\text{C} \quad \text{R}_7' \\ \parallel \\ \text{O} \end{array}$$
$$\begin{array}{cc} R_8' & R_9' \\ & \diagdown \quad \diagup \\ & C=C \\ & \diagup \quad \diagdown \\ R_{10}' & Q- \end{array}$$


[REDACTED]

- R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;
- $R_2'-R_{10}'$ are independently H, or alkyl of 1 to 5 carbon atoms;
- Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;
- $X, Y, \text{ and } Z$ are independently O, NH or S;
- v' is 1, or higher; and
- a', s' independently are greater than or equal to 0, and $a' + s' \geq 1$.

The addition of crosslinking agents of Formula I assists in the copolymerization of the vinyl-and acrylic-containing monomers with each other as well as with other monomers and prepolymers present in the monomer mix, such as the relatively non-polar ring-containing oxazolone compounds of the general formula (II):

This Sheet Has Been Replaced





where

R₁₁ and R₁₂ independently denote H or CH₃; and
R₁₃ and R₁₄ independently denote methyl or
cyclohexyl radicals.

These ring-containing monomers which may be incorporated into the silicone-containing hydrogels of the present invention specifically include 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one (IPDMO), 2-vinyl-4,4-dimethyl-2-oxazolin-5-one (VDMO), cyclohexane spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one) (IPCO), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) (VCO), and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one (PDMO). The preferred oxazolones are prepared by known reaction sequences set forth in commonly assigned U.S. Patent No. 4,810,764. The amount of crosslinker used is about 0.01 to about 5% of the vinyl-containing monomer weight present in a useful formulation.

We have observed that silicone-containing hydrogels containing NVP as a wetting agent have a much higher

This Sheet Has Been Replaced



modulus as compared with silicone hydrogels that incorporate acrylic-containing monomers, such as glycerol methacrylate and, N,N-dimethylacrylamide (DMA). We observed, and this invention contemplates, that the incorporation of a vinyl-containing hydrophilic monomer with an acrylic-containing hydrophilic monomer as wetting agents into silicone-containing formulations results in hydrogels suitable for biomedical applications, especially contact lenses.

Any known silicone-containing prepolymer may be used to form the silicone hydrogels of this invention, as will be apparent to one skilled in the art. The monomers added to the monomeric mixture may be monomers or prepolymers. A "prepolymer" is a reaction intermediate polymer of medium molecular weight having polymerizable groups. Thus it is understood that the terms "silicone-containing monomers" and "hydrophilic monomers" include prepolymers. Examples of such monomers may be found in United States Patent Nos. 4,136,250; 4,153,641; 4,740,533; 5,034,461; and 5,070,215.


Further, notations such as "(meth)acrylate or "(meth)acrylamide are used herein to denote optional methyl substitution. Thus, for example, methyl (meth)acrylate includes both methyl acrylate and methyl

This Sheet Has Been Replaced



methacrylate and N-alkyl (meth)acrylamide includes both N-alkyl acrylamide and N-alkyl methacrylamide.

One preferred class of suitable silicone-containing monomers are bulky polysiloxanylalkyl (meth)acrylic monomers represented by the formula (III):



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and


each R¹ is independently a lower alkyl or phenyl group; and

f is 1 or 3 to 10.

Such bulky monomers include methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.



A further preferred class of silicone-containing monomers are the poly(organo-siloxane) prepolymers represented by the formula (IV):



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R^3 - R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.

A further preferred class of silicone-containing monomers are the monomers having the following schematic representations:



where

This Sheet Has Been Replaced




D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A" denotes a divalent polymeric radical of formula (VII):




wherein: R^B and $R^{B'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula (VIII):





wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;

w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.

A preferred urethane monomer is represented by formula (IX):





R^{16} is a diradical of a diisocyanate after removal of the isocyanate group, and is most preferably the diradical of isophorone diisocyanate, and m, p and a are the same as previously defined. Preferably, the sum of m and a is 3 or 4, and more preferably, a is 1 and m is 3 or 4. Preferably, p is at least 30.

The wettable silicone-containing hydrogels of the present invention, when used in contact lens applications, can produce a wide variety of types of hydrogel contact lenses. As is understood in the field, in general, hydrogel contact lenses should have oxygen

permeabilities with DK values greater than about $20 \times 10^{-11} \text{ cm}^3 \times \text{cm/sec} \times \text{cm}^2 \times \text{mmHg}$ (or 20 DK units) and preferably greater than about 60 DK. They should have a Young's modulus of elasticity in the range of about 5 to 400 g/mm^2 , preferably greater than about 20 g/mm^2 as measured by ASTM test method D1938. Their water content should be between about 10 and 80 %, and preferably between 20 and 60%. The contact angle, which is a measurement of the wettability of the lens, should be less than about 80 degrees and should preferably be less than about 40 degrees.

The preferred range of the combined vinyl-containing and acrylic-containing hydrophilic wetting monomer concentration is from about 5 weight percent of the polymeric hydrogel mix to about 80 weight percent, and more preferably from about 20 weight percent to about 60 weight percent. The weight ratio of vinyl-containing monomer to acrylic-containing monomer is from about 40:1 to about 1:40, and is preferably higher than 1:1.

The present invention further provides articles of manufacture which can be used for biomedical devices, such as, contact lenses, surgical devices, heart valves, vessel substitutes, intrauterine devices, membranes and other films, diaphragms, surgical implants, blood

This Sheet Has Been Replaced



vessels, artificial ureters, artificial breast tissue and membranes intended to come into contact with body fluid outside of the body, e.g., membranes for kidney dialysis and heart/lung machines and the like, catheters, mouth guards, denture liners, intraocular devices, and especially contact lenses.

It is known that blood, for example, is readily and rapidly damaged when it comes into contact with artificial surfaces. The design of a synthetic surface which is antithrombogenic and nonhemolytic to blood is necessary for prostheses and devices used with blood.

The terms "shaped articles for use in biomedical applications" or "biomedical devices" mean the materials disclosed herein have physicochemical properties rendering them suitable for prolonged contact with living tissue, blood and the mucous membranes.

Although the exact mechanisms are not fully understood at the present time, the wetting agents of the present invention appear to reduce the deposition problems normally associated with, and believed to be caused by, the high hydrophobicity of the hydrophobic silicone-containing monomers.

This Sheet Has Been Replaced



Further, the wetting agents of the present invention significantly reduce the contact angle of the surface - a clear indication to those skilled in the field that enhanced wetting has occurred. The resulting novel hydrogels comprising the wetting agents of the present invention were unexpectedly hydrolytically stable, within an acceptable range, while collecting only an acceptable level of deposits.

Two preferred classes of silicone-containing monomers contemplated by the present invention are urethane-containing prepolymers, and ethylenically terminated polysiloxane containing monomers as previously described herein, such as, most preferably α, ω bis(methacryloxyalkyl)polysiloxane.

The resulting polymers and copolymers disclosed herein can be boiled and/or autoclaved in water without being damaged whereby sterilization may be achieved. Thus, an article formed from the disclosed polymers and copolymers may be used, for example, in surgery where an article is needed which is compatible with living tissue or with the mucous membranes.

The monomer mixes employed in this invention, can be readily cured to cast shapes by conventional methods such as UV polymerization, or thermal polymerization, or

This Sheet Has Been Replaced



combinations thereof, as commonly used in polymerizing ethylenically unsaturated compounds. Representative free radical thermal polymerization initiators are organic peroxides, such as acetal peroxide, lauroyl peroxide, decanoyl peroxide, stearyl peroxide, benzoyl peroxide, tertiarybutyl peroxyphthalate, peroxydicarbonate, and the like, employed in a concentration of about 0.01 to 1 percent by weight of the total monomer mixture. Representative UV initiators are those known in the field such as, benzoin methyl ether, benzoin ethyl ether, Darocure 1173, 1164, 2273, 1116, 2959, 3331 (EM Industries) and Irgacure 651 and 184 (Ciba-Geigy).

Polymerization of the monomer mix of this invention may be performed in the presence of a diluent. The polymerization product will then be in the form of a gel. If the diluent is nonaqueous, the diluent must be removed from the gel and replaced with water through the use of extraction and hydration protocols well known to those skilled in the art.

It is also possible to perform the polymerization in the absence of diluent to produce a xerogel. These xerogels may then be hydrated to form the hydrogels as is well known in the art.

This Sheet Has Been Replaced



In addition to the above-mentioned polymerization initiators, the copolymer of the present invention may also include other monomers as will be apparent to one skilled in the art. For example, the monomer mix may include additional hydrophilic monomers, colorants, curing agents, or UV-absorbing and toughening agents such as those known in the contact lens art.

The polymers of this invention can be formed into contact lenses by spincasting processes (such as those disclosed in U.S. Pat. Nos. 3,408,429 and 3,496,254), cast molding processes (such as those disclosed in U.S. Pat. Nos. 4,034,459 and 4,197,266), combinations of methods thereof, or any other known method for making contact lenses. Polymerization may be conducted either in a spinning mold, or a stationary mold corresponding to a desired contact lens shape. The lens may be further subjected to mechanical finishing, as occasion demands. Polymerization may also be conducted in an appropriate mold or vessel to form buttons, plates or rods, which may then be processed (e.g., cut or polished via lathe or laser) to give a contact lens having a desired shape.

The hydrogels the present invention are oxygen transporting, hydrolytically stable, biologically inert, and transparent. The monomers and prepolymers employed

This Sheet Has Been Replaced



in accordance with this invention, are readily polymerized to form three dimensional networks which permit the transport of oxygen and are optically clear, strong and hydrophilic.

The relative softness or hardness of the contact lenses fabricated from the resulting polymer of this invention can be varied by decreasing or increasing the molecular weight of the polysiloxane prepolymer end-capped with the activated unsaturated group or by varying the percent of the comonomer. As the ratio of polysiloxane units to end-cap units increases, the softness of the material increases.

The following examples serve only to further illustrate aspects of the present invention and should not be construed as limiting the invention.

The following abbreviations are defined as follows:

NVP	is N-vinyl pyrrolidone
DMA	is N,N-dimethyl acrylamide
HEMAVC	is methacryloxyethyl vinyl carbonate
TRIS	is methacryloxypropyl tris(trimethylsiloxy)silane
IDS3H	is a urethane prepolymer derived from isophorone diisocyanate, diethylene

This Sheet Has Been Replaced



glycol, polysiloxanediol encapped with 2-hydroxyethyl methacrylate

M_2D_x is an α,ω -bis(methacryloxyalkyl)-polysiloxane

VDMO is 2-vinyl-4,4-dimethyl-2-oxazoline-5-one

EXAMPLES 1-6

Polyurethane-silicone Hydrogels

Six polyurethane hydrogel films containing the following ingredients, were prepared:

- a) IDS3H, 30 parts;
- b) TRIS, 30 parts;
- c) NVP, varied from 0 to 40 parts;
- d) DMA, varied from 40 to 0 parts (NVP + DMA = 40 parts)
- e) Methacryloxyethylvinyl carbonate (HEMAVC crosslinker) at 0.3% of NVP amount;
- f) n-Hexanol 40 parts;
- g) Darocur-1173, (UV initiator), 0.2 part.

These formulations were UV cured, followed by ethanol extraction and boiling water hydration, as is known in the art, to give resultant hydrogel films with the following properties (water content and modulus). Figure 1 depicts the resultant films of Examples 1-6 with one plotted point for each film respectively.



Table 1

EXAMPLE	1	2	3	4	5	6
NVP/DMA ratio	40/0	38/2	35/5	30/10	20/20	0/40
% water	35	46	44	41	41	37
Modulus	430	281	150	80	79	63

The modulus/composition relationship is depicted in Figure 1.

EXAMPLE 7

Polyurethane Hydrogel

A formulation was prepared containing the same ingredients and same weight ratios as those in Example 4, except that 3 parts of NVP and 1 part of DMA was replaced by 1 part of VDMO. The formulation was cast onto films and processed as done in Examples 1-6. The resulting hydrogel films had the following properties: water content, 40%; modulus 110 g/mm².

EXAMPLES 8-11

Polyurethane-silicone Hydrogels

Polyurethane formulations of the ingredients as in Examples 1-6 but of different relative parts, as shown in Table 2, were prepared.

This Sheet Has Been Replaced



- a) IDS3H & b) TRIS, 34 parts each;
c) NVP & d) DMA, 32 parts combined;
e) n-Hexanol, f) HEMAvc and g) Darocure-1173, same parts as in Examples 1-6.

The formulations were cast and processed in the same manner as in Examples 1-6, with the water content and modulus data shown in Table 2. Figure 2 depicts the resultant films of Examples 8-11, with one plotted point representing each film respectively.

Table 2				
EXAMPLE	8	9	10	11
NVP/DMA ratio	32/0	24/8	16/16	0/32
water %	25	26	31	25
Modulus	610	275	107	87

The modulus/composition relationship is further shown in Figure 2.

EXAMPLES 12-15

M₂D₂-based Hydrogel Films

The following silicone hydrogel formulations were prepared and cast processed into hydrogel films by the procedure of Examples 8-11. Figure 3 depicts the resultant films of Examples 8-11, with one plotted point representing each film respectively. The ingredients in the formulation were:

This Sheet Has Been Replaced



- a) M_2D_x , 13 parts
- b) TRIS, 47 parts
- c) NVP & d) DMA, 40 parts combined
- e) n-Hexanol, 40 parts
- f) HEMAvc, 0.3 part of NVP amount
- g) Darocur, 0.2 part

The modulus-composition relationship is depicted in Figure 3.

EXAMPLE 16

Hydrogel Lens Casting

A monomer mix of the formulation as described in Examples 4, 9, 12 was filtered through a disposable 1.2 micron millipore filter into a clean vial. Under an inert nitrogen atmosphere, 60-90 μ l of the mix was injected onto a clean plastic mold half and then covered with a second plastic mold half. The molds were then compressed and cured for 90 minutes in the presence of UV light (4200 microwatts/cm²). The molds were then opened mechanically and put into a beaker containing aqueous ethanol. The lenses were released from the molds within 1 hour, then extracted with ethanol for 48 hours, and boiled in distilled water for 4 hours. The resultant lenses were inspected for cosmetic quality, cytotoxicity and dimensions. Lenses passing inspection

This Sheet Has Been Replaced



were thermally disinfected in phosphate buffered saline prior to on-eye evaluation.

EXAMPLE 17

Clinical Evaluations

The cast-molded polyurethane lenses described in Example 12 were evaluated on six to ten patients. In each test, a poly(HEMA) control lens was worn on one eye and the test lens on the other eye. The lenses were analyzed after a minimum of one hour, and preferably 5 hours or longer for wettability and surface deposition study. The surface wettability rating scale was 0-4 with 0 representing 2/3 of the anterior surface unwetted by the tear film, and 4 representing complete wetting. The deposition scale was also 0-4 with 0 representing no surface deposits and 4 representing multiple deposits of 0.5 mm diameter or larger. The results for the lenses of the control formulation (according to Example 4) was 3.0 for wetting and 0.4 for deposits after five hours of wear. For lenses comprising 1 part of VDMO (Example 7 formulation), the results showed a wettability rating of 3.3 and a deposit rating of 0.7 after 5 hours of wear.

Many other modifications and variations of the present invention are possible to the skilled practitioner in the field in light of the teachings herein. It is therefore understood that, within the

This Sheet Has Been Replaced



scope of the claims, the present invention can be practiced other than as herein specifically described.

This Sheet Has Been Replaced





We Claim:

1. A method for making a silicone-containing hydrogel composition comprising the steps of a) combining at least one vinyl-containing monomer, at least one acrylic-containing monomer and at least one silicone-containing prepolymer into a monomer mix and b) curing the monomer mix resulting from step a) to form a silicone-containing hydrogel composition.
2. The method of Claim 1 wherein said silicone-containing prepolymer is a urethane-containing prepolymer.
3. The method of Claim 1 wherein said silicone-containing prepolymer is an ethylenically terminated polysiloxane-containing prepolymer.
4. The method of Claim 1 wherein said vinyl-containing monomer may be selected from the group consisting of: N-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, and N-vinyl formamide.
5. The method of Claim 1 wherein said vinyl-containing monomer is N-vinyl pyrrolidone.
6. The method of Claim 1 wherein said acrylic-containing monomer is selected from the group consisting

This Sheet Has Been Replaced






of: 2-hydroxyethyl methacrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, diacetone acrylamide, methacrylic acid and acrylic acid.

7. The method of Claim 1 wherein said acrylic-containing monomer is N,N-dimethylacrylamide.

8. The method of Claim 1 wherein said silicone-containing prepolymer is a poly(organosiloxane) prepolymer represented by the formula:



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R³-R⁶ is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R⁷ is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and


n is 0 or an integer greater than or equal to 1.

This Sheet Has Been Replaced





9. The method of Claim 1 wherein said silicone-containing prepolymer is a bulky polysiloxanyalkyl (meth)acrylic monomer having the formula:



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R^1 is independently a lower alkyl or phenyl group; and

f is 1 or 3 to 10.


10. The method of Claim 9 wherein said bulky polysiloxanyalkyl (meth)acrylate monomer is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

This Sheet Has Been Replaced





11. The method of Claim 1 wherein said silicone-containing prepolymer is a urethane-containing prepolymer having the following schematic representations:



wherein


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:



wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon






atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula:



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;

w is 0 to 6;


x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.

12. The method of Claim 11 wherein said urethane-containing prepolymer is represented by formula:

This Sheet Has Been Replaced



wherein:

R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m , p and n are the same as previously defined.

13. The method of Claim 1 wherein said silicone-containing hydrogel composition comprises (a) bis(methacryloxyalkyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

14. The method of Claim 1 wherein said silicone-containing hydrogel comprises a urethane-containing


This Sheet Has Been Replaced




15. The method of Claim 1 wherein said silicone-containing hydrogel composition further comprises a relatively non-polar ring-containing compound selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

16. The method of Claim 1 wherein said silicone-containing hydrogel comprises an ethylenically terminated polysiloxane-containing monomer, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

17. The method of Claim 1 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation




γ denotes






A' denotes



S denotes



R₁' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R₂'-R₁₀' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

s', s' are independently greater than or equal to 0, and s' + s' ≥ 1.

18. The method of Claim 17 wherein said said crosslinking agent is methacryloxyethyl vinyl carbonate.

This Sheet Has Been Replaced





19. A silicone-containing hydrogel composition formed by curing a monomer mix comprising at least one acrylic-containing monomer, at least one vinyl-containing monomer and at least one silicone-containing prepolymer.

20. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a urethane-containing prepolymer.

21. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is an ethylenically terminated polysiloxane-containing monomer.

22. The hydrogel composition of Claim 19 wherein said vinyl-containing monomer may be selected from the group consisting of N-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, and N-vinyl formamide.

23. The hydrogel composition of Claim 19 wherein said vinyl-containing monomer is N-vinyl pyrrolidone.

24. The hydrogel composition of Claim 19 wherein said acrylic-containing monomer is selected from the group consisting of 2-hydroxyethyl methacrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, diacetone amrylamide, methacrylic acid and acrylic acid.

This Sheet Has Been Replaced





25. The hydrogel composition of Claim 19 wherein said acrylic-containing monomer is N,N-dimethylacrylamide.

26. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a poly(organosiloxane) prepolymer represented by the formula:



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R^3 - R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;


and

n is 0 or an integer greater than or equal to 1.

27. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a bulky polysiloxanylalkyl (meth)acrylic monomer having the formula:

This Sheet Has Been Replaced





wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group; and

f is 1 or 3 to 10.

28. The hydrogel composition of Claim 27 wherein said bulky polysiloxanyalkyl (meth)acrylate is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyl di(trimethylsiloxy)methacryloxymethyl silane.

29. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a urethane-containing

This Sheet Has Been Replaced





prepolymer having the following schematic representations:



wherein

D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:



wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and


p provides a moiety weight of 400 to 10,000;

This Sheet Has Been Replaced





E and E' independently denote a polymerizable unsaturated organic radical represented by formula:



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1 - C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;

w is 0 to 6;

x is 0 or 1;


y is 0 or 1; and

z is 0 or 1.

30. The hydrogel composition of Claim 29 wherein said urethane-containing prepolymer is represented by the formula:

This Sheet Has Been Replaced





wherein:

R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and n , p and a are the same as previously defined.

31. The hydrogel composition of Claim 22 wherein said silicone-containing prepolymer is α, ω bis(methacryloxyalkyl) polysiloxane, said acrylic-containing hydrophilic wetting monomer is N,N-dimethylacrylamide and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

This Sheet Has Been Replaced





32. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a urethane-containing prepolymer, said acrylic-containing monomer is N,N-dimethylacrylamide and said vinyl-containing monomer is N-vinyl pyrrolidone.

33. The hydrogel composition Claim 19 wherein said silicone-containing hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

34. The hydrogel composition of Claim 19 wherein said silicone-containing hydrogel composition is an ethylenically terminated polysiloxane-containing monomer said acrylic-containing hydrophilic wetting monomer is N,N-dimethylacrylamide and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

35. The hydrogel composition of Claim 19 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation:


This Sheet Has Been Replaced






wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

$R_2', -R_{10}'$ are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

This Sheet Has Been Replaced





a' , s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

36. The hydrogel composition of Claim 35 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

37. A biomedical device made from the hydrogel composition of Claim 19.

38. A contact lens made from the hydrogel composition of Claim 19.

39. The contact lens of Claim 38 wherein said hydrogel composition comprises a, a bis(methacryloxybutyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

40. The contact lens of Claim 38 wherein said hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

This Sheet Has Been Replaced






41. The contact lens of Claim 38 wherein said hydrogel composition further comprises a crosslinking agent having the general schematic representation




wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

This Sheet Has Been Replaced





X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

a', s' are independently greater than or equal to

0, and $a' + s' \geq 1$.

42. The contact lens of Claim 41 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

This Sheet Has Been Replaced



Date 07 OCT 1996

**WETTABLE SILICONE HYDROGEL COMPOSITIONS
AND METHODS FOR THEIR MANUFACTURE****BACKGROUND OF THE INVENTION**

This application is a continuation-in-part application of copending application Ser. No. 07/788,013 filed November 5, 1991.

Field of the Invention

The present invention relates to improved wettable polymeric hydrogel compositions useful for the production of biomedical devices, especially contact lenses.

Background

Hydrogels have been a desirable class of material for the preparation of biomedical devices, and have been known since at least Wichterle, et al U.S. Patent No. 3,220,960 which disclosed hydrogels comprising a hydrated polymer of a hydroxyalkyl acrylate or methacrylate crosslinked with a corresponding diester (poly 2-hydroxyethyl methacrylate, known as poly-HEMA).

A hydrogel is a hydrated crosslinked polymeric system that contains water in an equilibrium state. The physical properties of hydrogels can vary widely and are mostly determined by their water content. Since hydrogels exhibit excellent biocompatibility, there has

REPLACED SHEETS SG

- ☐ Description : paged to paged
☒ Claim(s) : paged 26. to paged 46.
☐ Drawing(s) : paged to paged
☐ Abstract : paged to paged

REPLACEMENT SHEETS SG

- ☒ Description : paged 1. to paged 27.
☒ Claim(s) : paged 28. to paged 46.
☐ Drawing(s) : paged to paged
☒ Abstract : paged 47. to paged

- 7 OCT 1996
DATE OF RECEIPT

been extensive interest in the use of hydrogels for biomedical devices, especially contact lenses.

In the field of contact lenses, various factors must combine to yield a material that has appropriate characteristics. Oxygen permeability, wettability, material strength and stability are but a few of the factors which must be carefully balanced to achieve a useable end-result contact lens. Since the cornea receives its oxygen supply exclusively from contact with the atmosphere, good oxygen permeability is a critical characteristic for any contact lens material.

It was discovered that certain crosslinked polymeric materials could be hydrated and retain their water content. It was further found that the higher the water content within contact lenses made from these crosslinked hydrogel polymers, the greater was the oxygen permeability through the lens to the cornea.

High water-containing hydrogels have at times exhibited undesirable mechanical properties. For example, such hydrogels are often not easily formed into hydrolytically stable lenses. Further such materials have at times exhibited tearing or other breakage as a result of poor tensile strength. What was needed was a highly oxygen permeable material that was durable and

This is the replacement sheet

07 OCT 1996

Date:

highly wettable. Wettability is important in that, if the lens is not sufficiently wettable, it does not remain lubricated and therefore cannot be worn comfortably in the eye. The optimum contact lens would have not only excellent oxygen permeability, but also excellent tear fluid wettability.

Silicone-containing materials were tried as viable contact lens materials and displayed very good oxygen permeability and durability. However, most silicone-containing materials are largely hydrophobic and therefore not sufficiently wettable. Further, it is believed that such hydrophobicity causes enhanced deposit problems, which may also result in discomfort when wearing contact lenses made from certain silicone-containing polymers.

Therefore, an optimal hydrogel material for biomedical devices, such as contact lenses, would have ideal rigidity, high oxygen permeability and a high degree of wettability.

SUMMARY OF THE INVENTION

In accordance with this invention, the surface wettability of hydrogels, such as silicone-containing

This is the replacement sheet

Date

07 OCT 1996

hydrogels, and more specifically polyurethane-silicone hydrogels and ethylenically terminated polysiloxane hydrogels such as (poly)organosiloxane hydrogels, are significantly enhanced by incorporating both at least one vinyl-containing hydrophilic monomer and at least one acrylic-containing hydrophilic monomer into the monomer mix along with the silicone-containing monomer or prepolymer.

Further, in accordance with the present invention, a method for making a wettable silicone-containing hydrogel composition is disclosed comprising the steps of a) combining at least one vinyl-containing monomer, at least one acrylic-containing monomer and at least one silicone-containing monomer or prepolymer into a monomer mix and b) curing the monomer mix resulting from step a) to form a silicone-containing hydrogel composition.

It is believed that the combined vinyl-containing and acrylic-containing monomers act as wetting agents, and interact with the predominantly hydrophobic silicone-containing monomers and prepolymers in the monomer mix to produce highly wettable hydrogels with ideal rigidity. Such resultant hydrogels are especially well-suited for use as contact lens materials.

This is the replacement sheet

Date: 07 OCT 1986

BRIEF DESCRIPTION OF THE DRAWINGS

Figures 1 and 2 depict the effect on modulus of polyurethane films as the composition ratio of NVP to DMA is changed.

Figure 3 depicts the effect on modulus of methacrylate-capped polysiloxane films as the composition ratio of NVP to DMA is changed.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to improved wettability of hydrogels, especially silicone-containing hydrogels with ideal rigidity suitable for biomedical applications such as contact lenses.

The silicone-containing hydrogels of the present invention display improved wettability as a result of the combined presence in the monomer mix of at least one acrylic-containing monomer and at least one vinyl-containing monomer.

Silicone hydrogels (i.e., hydrogels containing silicone) are usually prepared by polymerizing a mixture containing at least one silicone-containing monomer and

This is the replacement sheet

Date: 07 OCT 1996

at least one hydrophilic monomer. Either the silicone-containing monomer or the hydrophilic monomer may function as a crosslinking agent (a crosslinker being defined as a monomer having multiple polymerizable functionalities) or a separate crosslinker may be employed.

The term "vinyl-containing" is meant to refer to non-acrylic monomers having the vinyl grouping ($\text{CH}_2=\text{CH}-$) which are generally highly reactive. Such vinyl groups are known to polymerize relatively easily. "Acrylic-containing" monomers are those compounds containing the acrylic grouping ($\text{CH}_2=\text{C}(\text{R})\text{COX}$) which are also generally reactive.

The vinyl-containing monomers used in the present invention include hydrophilic monomers such as N-vinyl pyrrolidone, N-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, N-vinyl formamide, with N-vinyl pyrrolidone (NVP) being the most preferred.

The acrylic-containing monomers used in the present invention include hydrophilic monomers such as 2-hydroxyethyl methacrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, N,N-dimethyl (meth)acrylamide, diacetone acrylamide, methacrylic acid

This is the replacement sheet

Date:

07 OCT 1953

and acrylic acid with N,N-dimethylacrylamide (DMA) being the most preferred.


When both vinyl- and acrylic-containing monomers are present within one monomer mixture, it is preferable to add a crosslinking composition containing at least one vinyl-containing polymerizable group and at least one acrylic- or styrene-containing polymerizable group disclosed in copending and commonly assigned U.S. Application No. 07/788,071 filed November 5, 1991 and having the following general schematic representation (I):

(I)




wherein:

V denotes



A' denotes



S denotes



This is the replacement sheet

Date: 07 OCT 1996

R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

$R_2' - R_{10}'$ are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

$X, Y, \text{ and } Z$ are independently C, NH or S;

v' is 1, or higher; and


a', s' independently are greater than or equal to 0, and $a' + s' \geq 1$.

The addition of crosslinking agents of Formula I assists in the copolymerization of the vinyl-and acrylic-containing monomers with each other as well as with other monomers and prepolymers present in the monomer mix, such as the relatively non-polar ring-containing oxazolone compounds of the general formula (II):

This is the replacement sheet

Date:

07 OCT 1955



where

R₁₁ and R₁₂ independently denote H or CH₃; and
R₁₃ and R₁₄ independently denote methyl or
cyclohexyl radicals.

These ring-containing monomers which may be incorporated into the silicone-containing hydrogels of the present invention specifically include 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one (IPDMO), 2-vinyl-4,4-dimethyl-2-oxazolin-5-one (VDMO), cyclohexane spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one) (IPCO), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) (VCO), and 2-(-1-propenyl)-4,4-dimethyl-oxazol-5-one (PDMO). The preferred oxazolones are prepared by known reaction sequences set forth in commonly assigned U.S. Patent No. 4,810,764. The amount of crosslinker used is about 0.01 to about 5% of the vinyl-containing monomer weight present in a useful formulation.

We have observed that silicone-containing hydrogels containing NVP as a wetting agent have a much higher

This is the replacement sheet

Date 07 OCT 1996

modulus as compared with silicone hydrogels that incorporate acrylic-containing monomers, such as glycerol methacrylate and, N,N-dimethylacrylamide (DMA). We observed, and this invention contemplates, that the incorporation of a vinyl-containing hydrophilic monomer with an acrylic-containing hydrophilic monomer as wetting agents into silicone-containing formulations results in hydrogels suitable for biomedical applications, especially contact lenses.

Any known silicone-containing prepolymer may be used to form the silicone hydrogels of this invention, as will be apparent to one skilled in the art. The monomers added to the monomeric mixture may be monomers or prepolymers. A "prepolymer" is a reaction intermediate polymer of medium molecular weight having polymerizable groups. Thus it is understood that the terms "silicone-containing monomers" and "hydrophilic monomers" include prepolymers. Examples of such monomers may be found in United States Patent Nos. 4,136,250; 4,153,641; 4,740,533; 5,034,461; and 5,070,215.

Further, notations such as "(meth)acrylate or "(meth)acrylamide are used herein to denote optional methyl substitution. Thus, for example, methyl (meth)acrylate includes both methyl acrylate and methyl


This is the replacement sheet

Date

07 OCT 1995

methacrylate and N-alkyl (meth)acrylamide includes both N-alkyl acrylamide and N-alkyl methacrylamide.

One preferred class of suitable silicone-containing monomers are bulky polysiloxanylalkyl (meth)acrylic monomers represented by the formula (III):



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group; and


f is 1 or 3 to 10.

Such bulky monomers include methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

This is the replacement sheet

Date: 07 OCT 1993

A further preferred class of silicone-containing monomers are the poly(organoosiloxane) prepolymers represented by the formula (IV):



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R^3-R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.

A further preferred class of silicone-containing monomers are the monomers having the following schematic representations:



where

This is the replacement sheet

Date:

07 OCT 1995


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

Aⁿ denotes a divalent polymeric radical of formula (VII):



wherein: R^S and R^{S'} independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;


m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula (VIII):

This is the replacement sheet

Date: 07 OCT 1996



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-X-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 20 carbon atoms;

w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and


z is 0 or 1.

A preferred urethane monomer is represented by formula (IX):

This is the replacement sheet

07 OCT 1963

Date:



wherein:

R^{16} is a diradical of a diisocyanate after removal of the isocyanate group, and is most preferably the diradical of isophorone diisocyanate, and m , p and a are the same as previously defined. Preferably, the sum of m and a is 3 or 4, and more preferably, a is 1 and m is 3 or 4. Preferably, p is at least 30.

The wettable silicone-containing hydrogels of the present invention, when used in contact lens applications, can produce a wide variety of types of hydrogel contact lenses. As is understood in the field, in general, hydrogel contact lenses should have oxygen

This is the replacement sheet

107 OCT 1995

Date:

permeabilities with DK values greater than about $20 \times 10^{-11} \text{ cm}^3 \times \text{cm/sec} \times \text{cm}^2 \times \text{mmHg}$ (or 20 DK units) and preferably greater than about 60 DK. They should have a Young's modulus of elasticity in the range of about 5 to 400 g/mm^2 , preferably greater than about 20 g/mm^2 as measured by ASTM test method D1938. Their water content should be between about 10 and 80 %, and preferably between 20 and 60%. The contact angle, which is a measurement of the wettability of the lens, should be less than about 80 degrees and should preferably be less than about 40 degrees.

The preferred range of the combined vinyl-containing and acrylic-containing hydrophilic wetting monomer concentration is from about 5 weight percent of the polymeric hydrogel mix to about 80 weight percent, and more preferably from about 20 weight percent to about 60 weight percent. The weight ratio of vinyl-containing monomer to acrylic-containing monomer is from about 40:1 to about 1:40, and is preferably higher than 1:1.

The present invention further provides articles of manufacture which can be used for biomedical devices, such as, contact lenses, surgical devices, heart valves, vessel substitutes, intramartine devices, membranes and other films, diaphragms, surgical implants, blood

This is the replacement sheet

Date: 07 OCT 1996

vessels, artificial ureters, artificial breast tissue and membranes intended to come into contact with body fluid outside of the body, e.g., membranes for kidney dialysis and heart/lung machines and the like, catheters, mouth guards, denture liners, intraocular devices, and especially contact lenses.

It is known that blood, for example, is readily and rapidly damaged when it comes into contact with artificial surfaces. The design of a synthetic surface which is antithrombogenic and nonhemolytic to blood is necessary for prostheses and devices used with blood.

The terms "shaped articles for use in biomedical applications" or "biomedical devices" mean the materials disclosed herein have physicochemical properties rendering them suitable for prolonged contact with living tissue, blood and the mucous membranes.

Although the exact mechanisms are not fully understood at the present time, the wetting agents of the present invention appear to reduce the deposition problems normally associated with, and believed to be caused by, the high hydrophobicity of the hydrophobic silicone-containing monomers.

This is the replacement sheet

Date: 07 OCT 1986

Further, the wetting agents of the present invention significantly reduce the contact angle of the surface - a clear indication to those skilled in the field that enhanced wetting has occurred. The resulting novel hydrogels comprising the wetting agents of the present invention were unexpectedly hydrolytically stable, within an acceptable range, while collecting only an acceptable level of deposits.

Two preferred classes of silicone-containing monomers contemplated by the present invention are urethane-containing prepolymers, and ethylenically terminated polysiloxane containing monomers as previously described herein, such as, most preferably α,ω bis(methacryloxyalkyl)polysiloxane.

The resulting polymers and copolymers disclosed herein can be boiled and/or autoclaved in water without being damaged whereby sterilization may be achieved. Thus, an article formed from the disclosed polymers and copolymers may be used, for example, in surgery where an article is needed which is compatible with living tissue or with the mucous membranes.

The monomer mixes employed in this invention, can be readily cured to cast shapes by conventional methods such as UV polymerization, or thermal polymerization, or

This is the replacement sheet

Date: 07 OCT 1996

combinations thereof, as commonly used in polymerizing ethylenically unsaturated compounds. Representative free radical thermal polymerization initiators are organic peroxides, such as acetal peroxide, lauroyl peroxide, decanoyl peroxide, stearoyl peroxide, benzoyl peroxide, tertiarybutyl peroxyphthalate, peroxydicarbonate, and the like, employed in a concentration of about 0.01 to 1 percent by weight of the total monomer mixture. Representative UV initiators are those known in the field such as, benzoin methyl ether, benzoin ethyl ether, Darocure 1173, 1164, 2273, 1116, 2959, 3331 (EM Industries) and Igracure 651 and 184 (Ciba-Gaigey).

Polymerization of the monomer mix of this invention may be performed in the presence of a diluent. The polymerization product will then be in the form of a gel. If the diluent is nonaqueous, the diluent must be removed from the gel and replaced with water through the use of extraction and hydration protocols well known to those skilled in the art.

It is also possible to perform the polymerization in the absence of diluent to produce a xerogel. These xerogels may then be hydrated to form the hydrogels as is well known in the art.

This is the replacement sheet

Date:

07 OCT 1996

In addition to the above-mentioned polymerization initiators, the copolymer of the present invention may also include other monomers as will be apparent to one skilled in the art. For example, the monomer mix may include additional hydrophilic monomers, colorants, curing agents, or UV-absorbing and toughening agents such as those known in the contact lens art.

The polymers of this invention can be formed into contact lenses by spincoating processes (such as those disclosed in U.S. Pat. Nos. 3,408,429 and 3,496,254), cast molding processes (such as those disclosed in U.S. Pat. Nos. 4,084,459 and 4,197,266), combinations of methods thereof, or any other known method for making contact lenses. Polymerization may be conducted either in a spinning mold, or a stationary mold corresponding to a desired contact lens shape. The lens may be further subjected to mechanical finishing, as occasion demands. Polymerization may also be conducted in an appropriate mold or vessel to form buttons, plates or rods, which may then be processed (e.g., cut or polished via lathe or laser) to give a contact lens having a desired shape.

The hydrogels the present invention are oxygen transporting, hydrolytically stable, biologically inert, and transparent. The monomers and prepolymers employed

This is the replacement sheet

Date: 07 OCT 1996

in accordance with this invention, are readily polymerized to form three dimensional networks which permit the transport of oxygen and are optically clear, strong and hydrophilic.

The relative softness or hardness of the contact lenses fabricated from the resulting polymer of this invention can be varied by decreasing or increasing the molecular weight of the polysiloxane prepolymer end-capped with the activated unsaturated group or by varying the percent of the comonomer. As the ratio of polysiloxane units to end-cap units increases, the softness of the material increases.

The following examples serve only to further illustrate aspects of the present invention and should not be construed as limiting the invention.

The following abbreviations are defined as follows:

NVP	is N-vinyl pyrrolidone
DMA	is N,N-dimethyl acrylamide
HEMAVC	is methacryloxyethyl vinyl carbonate
TRIS	is methacryloxypropyl tris(trimethylsiloxy)silane
IDS3H	is a urethane prepolymer derived from isophorone diisocyanate, diethylene

This is the replacement sheet

Date: 07 OCT 1996

glycol, polysiloxanediol encapped with 2-hydroxyethyl methacrylate

M₂D_x is an α,ω -bis(methacryloxyalkyl)-polysiloxane

VDMD is 2-vinyl-4,4-dimethyl-2-oxazoline-5-one

EXAMPLES 1-6

Polyurethane-silicone Hydrogels

Six polyurethane hydrogel films containing the following ingredients, were prepared:

- a) IDS3H, 30 parts;
- b) TRIS, 30 parts;
- c) NVP, varied from 0 to 40 parts;
- d) DMA, varied from 40 to 0 parts (NVP + DMA = 40 parts)
- e) Methacryloxyethylvinyl carbonate (HEMAVC crosslinker) at 0.3% of NVP amount;
- f) n-Hexanol 40 parts;
- g) Darocur-1173, (UV initiator), 0.2 part.

These formulations were UV cured, followed by ethanol extraction and boiling water hydration, as is known in the art, to give resultant hydrogel films with the following properties (water content and modulus). Figure 1 depicts the resultant films of Examples 1-6 with one plotted point for each film respectively.

This is the replacement sheet

Date:

07 OCT 1993

Table 1

EXAMPLE	1	2	3	4	5	6
NVP/DMA ratio	40/0	38/2	35/5	30/10	20/20	0/40
% water	35	46	44	41	41	37
Modulus	430	281	150	80	79	63

The modulus/composition relationship is depicted in Figure 1.

EXAMPLE 7

Polyurethane Hydrogel

A formulation was prepared containing the same ingredients and same weight ratios as those in Example 4, except that 3 parts of NVP and 1 part of DMA was replaced by 1 part of VDMO. The formulation was cast onto films and processed as done in Examples 1-6. The resulting hydrogel films had the following properties: water content, 40%; modulus 110 g/mm².

EXAMPLES 8-11

Polyurethane-silicone Hydrogels

Polyurethane formulations of the ingredients as in Examples 1-6 but of different relative parts, as shown in Table 2, were prepared.

This is the replacement sheet

07 OCT 1996

Date:

- a) IDS3H & b) TRIS, 34 parts each;
c) NVP & d) DMA, 32 parts combined;
e) n-Hexanol, f) HEMAvc and g) Darocure-1173, same parts as in Examples 1-6.

The formulations were cast and processed in the same manner as in Examples 1-6, with the water content and modulus data shown in Table 2. Figure 2 depicts the resultant films of Examples 8-11, with one plotted point representing each film respectively.

Table 2				
EXAMPLE	8	9	10	11
NVP/DMA ratio	32/0	24/8	16/16	0/32
water %	25	26	31	25
Modulus	610	275	107	87

The modulus/composition relationship is further shown in Figure 2.

EXAMPLES 12-15

M₂D_x-based Hydrogel Films

The following silicone hydrogel formulations were prepared and cast processed into hydrogel films by the procedure of Examples 8-11. Figure 3 depicts the resultant films of Examples 8-11, with one plotted point representing each film respectively. The ingredients in the formulation were:

This is the replacement sheet

Date: 07 OCT 1996

- a) M_2D_x , 13 parts
- b) TRIS, 47 parts
- c) NVP & d) DMA, 40 parts combined
- e) n-Hexanol, 40 parts
- f) HEMAvc, 0.3 part of NVP amount
- g) Darocur, 0.2 part

The modulus-composition relationship is depicted in Figure 3.

EXAMPLE 16

Hydrogel Lens Casting

A monomer mix of the formulation as described in Examples 4, 9, 12 was filtered through a disposable 1.2 micron millipore filter into a clean vial. Under an inert nitrogen atmosphere, 60-90 μ l of the mix was injected onto a clean plastic mold half and then covered with a second plastic mold half. The molds were then compressed and cured for 90 minutes in the presence of UV light (4200 microwatts/cm²). The molds were then opened mechanically and put into a beaker containing aqueous ethanol. The lenses were released from the molds within 1 hour, then extracted with ethanol for 48 hours, and boiled in distilled water for 4 hours. The resultant lenses were inspected for cosmetic quality, cytotoxicity and dimensions. Lenses passing inspection

This is the replacement sheet

Date: 07 OCT 1996

were thermally disinfected in phosphate buffered saline prior to on-eye evaluation.

EXAMPLE 17

Clinical Evaluations

The cast-molded polyurethane lenses described in Example 12 were evaluated on six to ten patients. In each test, a poly(HEMA) control lens was worn on one eye and the test lens on the other eye. The lenses were analyzed after a minimum of one hour, and preferably 5 hours or longer for wettability and surface deposition study. The surface wettability rating scale was 0-4 with 0 representing 2/3 of the anterior surface unwetted by the tear film, and 4 representing complete wetting. The deposition scale was also 0-4 with 0 representing no surface deposits and 4 representing multiple deposits of 0.5 mm diameter or larger. The results for the lenses of the control formulation (according to Example 4) was 3.0 for wetting and 0.4 for deposits after five hours of wear. For lenses comprising 1 part of VDMO (Example 7 formulation), the results showed a wettability rating of 3.3 and a deposit rating of 0.7 after 5 hours or wear.

Many other modifications and variations of the present invention are possible to the skilled practitioner in the field in light of the teachings herein. It is therefore understood that, within the

This is the replacement sheet

Date:

07 OCT 1996

scope of the claims, the present invention can be practiced other than as herein specifically described.

This is the replacement sheet

07 OCT 1955

Date:



We Claim:

1. A method for making a silicone-containing hydrogel composition comprising the steps of a) combining at least one vinyl-containing monomer, at least one acrylic-containing monomer and at least one silicone-containing prepolymer into a monomer mix and b) curing the monomer mix resulting from step a) to form a silicone-containing hydrogel composition.
2. The method of Claim 1 wherein said silicone-containing prepolymer is a urethane-containing prepolymer.
3. The method of Claim 1 wherein said silicone-containing prepolymer is an ethylenically terminated polysiloxane-containing prepolymer.
4. The method of Claim 1 wherein said vinyl-containing monomer may be selected from the group consisting of: N-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, and N-vinyl formamide.
5. The method of Claim 1 wherein said vinyl-containing monomer is N-vinyl pyrrolidone.
6. The method of Claim 1 wherein said acrylic-containing monomer is selected from the group consisting

This Sheet Has Been Replaced



This is the replacement sheet

Date: 07 OCT 1993



of: 2-hydroxyethyl methacrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, diacetone acrylamide, methacrylic acid and acrylic acid.

7. The method of Claim 1 wherein said acrylic-containing monomer is N,N-dimethylacrylamide.

8. The method of Claim 1 wherein said silicone-containing prepolymer is a poly(organosiloxane) prepolymer represented by the formula:



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R^3 - R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.

This Sheet Has Been Replaced




This is the replacement sheet

Date: 07 OCT 1996



9. The method of Claim 1 wherein said silicone-containing prepolymer is a bulky polysiloxanyalkyl (meth)acrylic monomer having the formula:



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R^1 is independently a lower alkyl or phenyl group; and

f is 1 or 3 to 10.

10. The method of Claim 9 wherein said bulky polysiloxanyalkyl (meth)acrylate monomer is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

This is the replacement sheet

This Sheet Has Been Replaced




Date:

07 OCT 1996



11. The method of Claim 1 wherein said silicone-containing prepolymer is a urethane-containing prepolymer having the following schematic representations:



wherein


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:



wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon

This Sheet Has Been Replaced



This is the replacement sheet

Date: 07 OCT 1996




atoms which may contain ether linkages between carbon atoms;

n is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula:



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;

w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.


12. The method of Claim 11 wherein said urethane-containing prepolymer is represented by formula:

This Sheet Has Been Replaced



This is the replacement sheet

Date: 07 OCT 1996



wherein:

R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m , p and a are the same as previously defined.

13. The method of Claim 1 wherein said silicone-containing hydrogel composition comprises α, ω bis(methacryloxyalkyl) polysiloxane, N,N -dimethylacrylamide and N -vinyl pyrrolidone.

14. The method of Claim 1 wherein said silicone-containing hydrogel comprises a urethane-containing

This is the replacement sheet

Date:

07 OCT 1993

This Sheet Has Been Replaced




...

17. The method of Claim 1 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation



V dates




100

07 OCT 1996


Date: _____



A' denotes



S denotes



R₁' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R₂'-R₁₀' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

y' is 1, or higher; and

a', s' are independently greater than or equal to 0, and a' + s' ≥ 1.

18. The method of Claim 17 wherein said said crosslinking agent is methacryloxyethyl vinyl carbonate.

This Sheet Has Been Replaced



This is the replacement sheet

Date:

07 OCT 1996



19. A silicone-containing hydrogel composition formed by curing a monomer mix comprising at least one acrylic-containing monomer, at least one vinyl-containing monomer and at least one silicone-containing prepolymer.

20. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a urethane-containing prepolymer.

21. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is an ethylenically terminated polysiloxane-containing monomer.

22. The hydrogel composition of Claim 19 wherein said vinyl-containing monomer may be selected from the group consisting of N-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, and N-vinyl formamide.

23. The hydrogel composition of Claim 19 wherein said vinyl-containing monomer is N-vinyl pyrrolidone.

24. The hydrogel composition of Claim 19 wherein said acrylic-containing monomer is selected from the group consisting of 2-hydroxyethyl methacrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, diacetone acrylamide, methacrylic acid and acrylic acid.

This Sheet Has Been Replaced




This is the replacement sheet

Date: 07 OCT 1996



25. The hydrogel composition of Claim 19 wherein said acrylic-containing monomer is N,N-dimethylacrylamide.

26. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a poly(organosiloxane) prepolymer represented by the formula:



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R^3 - R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.


27. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a bulky polysiloxanylalkyl (meth)acrylic monomer having the formula:

This Sheet Has Been Replaced



This is the replacement sheet

Date: 07 OCT 1996



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group; and

f is 1 or 3 to 10.

28. The hydrogel composition of Claim 27 wherein said bulky polysiloxanyalkyl (meth)acrylate is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

29. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a urethane-containing

This Sheet Has Been Replaced

This is the replacement sheet

Date: 07 OCT 1996



prepolymer having the following schematic representations:



wherein


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:



wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

This Sheet Has Been Replaced




This is the replacement sheet

Date:

07 OCT 1996



E and E' independently denote a polymerizable unsaturated organic radical represented by formula:



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;

w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.

30. The hydrogel composition of Claim 29 wherein said urethane-containing prepolymer is represented by the formula:


This Sheet Has Been Replaced



This is the replacement sheet

Date:

07 OCT 1955



wherein:

R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m , p and a are the same as previously defined.

31. The hydrogel composition of Claim 22 wherein said silicone-containing prepolymer is α, ω bis(methacryloxyalkyl) polysiloxane, said acrylic-containing hydrophilic wetting monomer is N,N-dimethylacrylamide and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

This Sheet Has Been Replaced



This is the replacement sheet

07 OCT 1995

Date:



32. The hydrogel composition of Claim 19 wherein said silicone-containing prepolymer is a urethane-containing prepolymer, said acrylic-containing monomer is N,N-dimethylacrylamide and said vinyl-containing monomer is N-vinyl pyrrolidone.

33. The hydrogel composition Claim 19 wherein said silicone-containing hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

34. The hydrogel composition of Claim 19 wherein said silicone-containing hydrogel composition is an ethylenically terminated polysiloxane-containing monomer said acrylic-containing hydrophilic wetting monomer is N,N-dimethylacrylamide and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

35. The hydrogel composition of Claim 19 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation:

This Sheet Has Been Replaced




This is the replacement sheet
07 OCT 1996
Date:




wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

This Sheet Has Been Replaced



This is the replacement sheet

Date:

07 OCT 1995



a', s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

36. The hydrogel composition of Claim 35 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

37. A biomedical device made from the hydrogel composition of Claim 19.

38. A contact lens made from the hydrogel composition of Claim 19.

39. The contact lens of Claim 38 wherein said hydrogel composition comprises a, a bis(methacryloxybutyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

40. The contact lens of Claim 38 wherein said hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

This is the replacement sheet

This Sheet Has Been Replaced



Date:

07 OCT 1986




41. The contact lens of Claim 38 wherein said hydrogel composition further comprises a crosslinking agent having the general schematic representation




wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

This Sheet Has Been Replaced



This is the replacement sheet

Date:

07 OCT 1996



X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

a', s' are independently greater than or equal to
0, and $a' + s' \geq 1$.

42. The contact lens of Claim 41 wherein said
crosslinking agent is methacryloxyethyl vinyl carbonate.

This Sheet Has Been Replaced



This is the replacement sheet

Date: 07 OCT 1996

Abstract**Wettable Silicone Hydrogel Compositions and Methods for their
Manufacture**

Improved silicone-containing hydrogels are disclosed with enhanced wettability comprising a silicone-containing monomer, at least one acrylic-containing hydrophilic monomer, and at least one vinyl-containing hydrophilic monomer.

This is the replacement sheet


Date: 07 OCT 1995



We Claim:

1. A method for improving the wettability of silicone-containing hydrogels comprising the steps of a) combining at least one silicone-containing monomer and N,N-dimethylacrylamide with a vinyl-containing monomer selected from the group consisting of n-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, and N-vinyl formamide in a monomer mix and b) curing the monomer mix of step a) to form a silicone-containing hydrogel with improved wetting properties.
2. The method of Claims 1 or 2 wherein said vinyl-containing monomer is N-vinylpyrrolidone.
3. The method of Claims 1 or 2 wherein said silicone-containing monomer is a urethane-containing prepolymer.
4. The method of Claims 1 or 2 wherein said silicone-containing monomer is an ethylenically terminated polysiloxane-containing prepolymer.
5. The method of Claims 1 or 2 wherein said silicone-containing monomer is a poly(organosiloxane) prepolymer represented by the formula:

This Sheet Has Been Replaced



- 1 DEC 1997

- 29 -



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;


each R^3 - R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.

6. The method of Claims 1 or 2 wherein said silicone-containing monomer is a bulky polysiloxanylalkyl (meth)acrylic monomer having the formula:



This Sheet Has Been Replaced



- 1 DEC 1997

wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group;

and

f is 1 or 3 to 10.

7. The method of Claim 6 wherein said bulky polysiloxanyalkyl (meth)acrylate monomer is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

8. The method of Claims 1 or 2 wherein said silicone-containing monomer is a urethane-containing prepolymer having the following schematic representations:



wherein

D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an






alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

Aⁿ denotes a divalent polymeric radical of formula:




wherein: R^S and R^{S'} independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula:




wherein: R¹⁴ denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R¹² denotes H or CH₃;

R¹³ denotes H, a (C₁-C₆) alkyl radical or a -CO-Y-R¹⁵ group wherein Y is -O-, -S- or -NH- and R¹⁵ is a alkyl radical having 1 to 12 carbon atoms;

X is -CO- or -OCO-;

This Sheet Has Been Replaced





Z is -O- or -NH-;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;


w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.

9. The method of Claim 8 wherein said urethane-containing prepolymer is represented by formula:



wherein:

This Sheet Has Been Replaced



REPLACEMENT SHEET

- 1 DEC 1997



R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m, p and a are the same as previously defined.

10. The method of Claims 1 or 2 wherein said silicone-containing hydrogel composition comprises α,ω bis(methacryloxyalkyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

11. The method of Claim 1 or 2 wherein said silicone-containing hydrogel comprises a urethane-containing prepolymer, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

12. The method of Claims 1 or 2 wherein said silicone-containing hydrogel further comprises a relatively non-polar ring-containing compound selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

13. The method of Claims 1 or 2 wherein said silicone-containing hydrogel comprises an ethylenically terminated polysiloxane-containing monomer, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

This Sheet Has Been Replaced



REPLACEMENT SHEET

- 1 DEC 1997




14. The method of Claims 1 or 2 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation




wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

This Sheet Has Been Replaced



REPLACEMENT SHEET

- 1 DEC 1997



Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;
X, Y, and Z are independently O, NH or S;
v' is 1, or higher; and
a', s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

15. The method of Claim 14 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

16. A silicone-containing hydrogel composition formed by curing a monomer mix comprising at least one silicone-containing monomer and N,N-dimethylacrylamide with a vinyl-containing monomer selected from the group consisting of n-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, N-vinyl formamide and N-vinyl pyrrolidone.

17. The hydrogel composition of Claim 16 wherein said vinyl-containing monomer is N-vinylpyrrolidone.

18. The hydrogel composition of Claims 15 or 16 wherein said silicone-containing monomer is a urethane-containing prepolymer.

This Sheet Has Been Replaced



REPLACEMENT SHEET

- 1 DEC 1997



19. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is an ethylenically terminated polysiloxane-containing monomer.

20. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a poly(organosiloxane) prepolymer represented by the formula:



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;

each R³-R⁶ is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;


R⁷ is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.


21. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a bulky polysiloxanylalkyl (meth)acrylic monomer having the formula:

This Sheet Has Been Replaced





- 1 DEC 1997



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group;

and


f is 1 or 3 to 10.

22. The hydrogel composition of Claim 21 wherein said bulky polysiloxanyalkyl (meth)acrylate is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

23. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a urethane-containing prepolymer having the following schematic representations:

This Sheet Has Been Replaced





$E(*D*A''*D*G)_a*D*A''*D*E'$; or

$E(*D*G*D*A'')_a*D*G*D*E'$;

wherein


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:




wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula:





wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1 - C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;



w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and


z is 0 or 1.

24. The hydrogel composition of Claim 23 wherein said urethane-containing prepolymer is represented by the formula:



This Sheet Has Been Replaced





R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m, p and a are the same as previously defined.

25. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is α,ω bis(methacryloxyalkyl) polysiloxane and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

26. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a urethane-containing





prepolymer and said vinyl-containing monomer is N-vinyl pyrrolidone.

27. The hydrogel composition Claims 16 or 17 wherein said silicone-containing hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.


28. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing hydrogel composition is an ethylenically terminated polysiloxane-containing monomer and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

29. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation:




wherein

This Sheet Has Been Replaced







V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

a' , s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

This Sheet Has Been Replaced



REPLACEMENT SHEET

- 1 DEC 1997



30. The hydrogel composition of Claim 29 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

31. A biomedical device made from the hydrogel composition of Claims 16 or 17.


32. A contact lens made from the hydrogel composition of Claims 16 or 17.

33. The contact lens of Claim 33 wherein said hydrogel composition comprises α,ω bis(methacryloxybutyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

34. The contact lens of Claim 32 wherein said hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

35. The contact lens of Claim 32 wherein said hydrogel composition further comprises a crosslinking agent having the general schematic representation


This Sheet Has Been Replaced






wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;


R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

This Sheet Has Been Replaced






- 45 -

a' , s' are independently greater than or equal to
0, and $a' + s' \geq 1$.

36. The contact lens of Claim 35 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

This Sheet Has Been Replaced






We Claim:

1. A method for improving the wettability of silicone-containing hydrogels comprising the steps of a) combining at least one silicone-containing monomer and N,N-dimethylacrylamide with a vinyl-containing monomer selected from the group consisting of n-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, and N-vinyl formamide in a monomer mix and b) curing the monomer mix of step a) to form a silicone-containing hydrogel with improved wetting properties.
2. The method of Claims 1 or 2 wherein said vinyl-containing monomer is N-vinylpyrrolidone.
3. The method of Claims 1 or 2 wherein said silicone-containing monomer is a urethane-containing prepolymer.
4. The method of Claims 1 or 2 wherein said silicone-containing monomer is an ethylenically terminated polysiloxane-containing prepolymer.
5. The method of Claims 1 or 2 wherein said silicone-containing monomer is a poly(organosiloxane) prepolymer represented by the formula:

This is the replacement sheet

Date: 27 MAY 1998



wherein:

A is an activated unsaturated group, such as an ester or amide of an acrylic or a methacrylic acid;


each R^3 - R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;

and

n is 0 or an integer greater than or equal to 1.

6. The method of Claims 1 or 2 wherein said silicone-containing monomer is a bulky polysiloxanylalkyl (meth)acrylic monomer having the formula:



This is the replacement sheet

Date: 27 MAY 1988



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group;

and

f is 1 or 3 to 10.

7. The method of Claim 6 wherein said bulky polysiloxanyalkyl (meth)acrylate monomer is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

8. The method of Claims 1 or 2 wherein said silicone-containing monomer is a urethane-containing prepolymer having the following schematic representations:



wherein

D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an

This is the replacement sheet

Date: 27 MAY 1998




alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:




wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula:



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

This is the replacement sheet

Date: 27 MAY 1998



Z is -O- or -NH-;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;


w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and

z is 0 or 1.

9. The method of Claim 8 wherein said urethane-containing prepolymer is represented by formula:



wherein:

This is the replacement sheet

Date: 27 MAY 1998



R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m, p and a are the same as previously defined.

10. The method of Claims 1 or 2 wherein said silicone-containing hydrogel composition comprises α,ω bis(methacryloxyalkyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

11. The method of Claim 1 or 2 wherein said silicone-containing hydrogel comprises a urethane-containing prepolymer, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

12. The method of Claims 1 or 2 wherein said silicone-containing hydrogel further comprises a relatively non-polar ring-containing compound selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

13. The method of Claims 1 or 2 wherein said silicone-containing hydrogel comprises an ethylenically terminated polysiloxane-containing monomer, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

~~This is the replacement sheet~~

Date:

27 MAY 1998




14. The method of Claims 1 or 2 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation




wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

$R_2'-R_{10}'$ are independently H, or alkyl of 1 to 5 carbon atoms;

This is the replacement sheet

Date: 27 MAY 1998



Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;
X, Y, and Z are independently O, NH or S;
v' is 1, or higher; and
a', s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

15. The method of Claim 14 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

16. A silicone-containing hydrogel composition formed by curing a monomer mix comprising at least one silicone-containing monomer and N,N-dimethylacrylamide with a vinyl-containing monomer selected from the group consisting of n-vinyl-N-methyl acetamide, N-vinyl-N-ethyl acetamide, N-vinyl-N-methyl formamide, N-vinyl formamide and N-vinyl pyrrolidone.

17. The hydrogel composition of Claim 16 wherein said vinyl-containing monomer is N-vinylpyrrolidone.

18. The hydrogel composition of Claims 15 or 16 wherein said silicone-containing monomer is a urethane-containing prepolymer.

This is the replacement sheet

Date: 27 MAY 1988



19. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is an ethylenically terminated polysiloxane-containing monomer.

20. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a poly(organosiloxane) prepolymer represented by the formula:



wherein:

A is an activated unsaturated group, such as an ester or anide of an acrylic or a methacrylic acid;

each R^3-R^6 is independently selected from the group consisting of a monovalent hydrocarbon radical or a halogen substituted monovalent hydrocarbon radical having 1 to 18 carbon atoms which may have ether linkages between carbon atoms;

R^7 is a divalent hydrocarbon radical having from 1 to 22 carbon atoms;


and

n is 0 or an integer greater than or equal to 1.

21. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a bulky polysiloxanylalkyl (meth)acrylic monomer having the formula:

This is the replacement sheet

Date: 27 MAY 1988



wherein:

X is O or NR;

each R is independently hydrogen or methyl; and

each R¹ is independently a lower alkyl or phenyl group;

and


f is 1 or 3 to 10.

22. The hydrogel composition of Claim 21 wherein said bulky polysiloxanyalkyl (meth)acrylate is selected from the group consisting of methacryloxypropyl tris(trimethylsiloxy)silane, pentamethyldisiloxanylmethylmethacrylate, tris(trimethylsiloxy)methacryloxy propylsilane, phenyltetramethyldisiloxanylethyl acetate, and methyldi(trimethylsiloxy)methacryloxymethyl silane.

23. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a urethane-containing prepolymer having the following schematic representations:

This is the replacement sheet

Date: 27 MAY 1996



wherein


D denotes an alkyl diradical, an alkyl cycloalkyl diradical, a cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 6 to 30 carbon atoms;

G denotes an alkyl diradical, a cycloalkyl diradical, an alkyl cycloalkyl diradical, an aryl diradical or an alkylaryl diradical having 1 to 40 carbon atoms and which may contain ether, thio or amine linkages in the main chain;

* denotes a urethane or ureido linkage;

a is at least 1;

A'' denotes a divalent polymeric radical of formula:




wherein: R^S and $R^{S'}$ independently denote an alkyl or fluoro-substituted alkyl group having 1 to 10 carbon atoms which may contain ether linkages between carbon atoms;

m is at least 1; and

p provides a moiety weight of 400 to 10,000;

E and E' independently denote a polymerizable unsaturated organic radical represented by formula:



This is the replacement sheet

Date: 27 MAY 1998



wherein: R^{14} denotes a divalent alkylene radical having 1 to 10 carbon atoms;

R^{12} denotes H or CH_3 ;

R^{13} denotes H, a (C_1-C_6) alkyl radical or a $-CO-Y-R^{15}$ group wherein Y is $-O-$, $-S-$ or $-NH-$ and R^{15} is a alkyl radical having 1 to 12 carbon atoms;

X is $-CO-$ or $-OCO-$;

Z is $-O-$ or $-NH-$;

Ar denotes an aromatic radical having 6 to 30 carbon atoms;

w is 0 to 6;

x is 0 or 1;

y is 0 or 1; and


z is 0 or 1.

24. The hydrogel composition of Claim 23 wherein said urethane-containing prepolymer is represented by the formula:

This is the replacement sheet

Date:

27 MAY 1998



wherein:

R^{16} is a diradical of a diisocyanate after removal of the isocyanate group and m, p and a are the same as previously defined.

25. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is α,ω bis(methacryloxyalkyl) polysiloxane and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

26. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing monomer is a urethane-containing

This is the replacement sheet

Date: 27 MAY 1998



prepolymer and said vinyl-containing monomer is N-vinyl pyrrolidone.

27. The hydrogel composition Claims 16 or 17 wherein said silicone-containing hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

28. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing hydrogel composition is an ethylenically terminated polysiloxane-containing monomer and said vinyl-containing hydrophilic wetting monomer is N-vinyl pyrrolidone.

29. The hydrogel composition of Claims 16 or 17 wherein said silicone-containing hydrogel further comprises a crosslinking agent having the general schematic representation:




wherein

This is the replacement sheet


Date: 27 MAY 1998




V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

$R_2', \dots, R_{10}'$ are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

a', s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

This is the replacement sheet

Date:

27 MAY 1998



30. The hydrogel composition of Claim 29 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

31. A biomedical device made from the hydrogel composition of Claims 16 or 17.

32. A contact lens made from the hydrogel composition of Claims 16 or 17.

33. The contact lens of Claim 33 wherein said hydrogel composition comprises α,ω bis(methacryloxybutyl) polysiloxane, N,N-dimethylacrylamide and N-vinyl pyrrolidone.

34. The contact lens of Claim 32 wherein said hydrogel composition further comprises a relatively non-polar ring-containing compound is selected from the group consisting of 2-vinyl-4,4-dimethyl-2-oxazolin-5-one, 2-isopropenyl-4,4-dimethyl-2-oxazolin-5-one, cyclohexane-spiro-4'-(2'-isopropenyl-2'-oxazol-5'-one), cyclohexane-spiro-4'-(2'-vinyl-2'-oxazol-5'-one) and 2-(1-propenyl)-4,4-dimethyl-oxazol-5-one.

35. The contact lens of Claim 32 wherein said hydrogel composition further comprises a crosslinking agent having the general schematic representation


This is the replacement sheet

Date: 27 MAY 1998




wherein


V denotes



A' denotes



S denotes



R_1' is an alkyl radical derived from substituted and unsubstituted hydrocarbons, polyalkylene oxide, poly(perfluoro) alkylene oxide, dialkyl-capped polydimethylsiloxane, dialkyl-capped polydimethylsiloxane modified with fluoroalkyl or fluoroether groups;

R_2' - R_{10}' are independently H, or alkyl of 1 to 5 carbon atoms;

Q is an organic group containing aromatic moieties having 6 to 30 carbon atoms;

X, Y, and Z are independently O, NH or S;

v' is 1, or higher; and

This is the replacement sheet

Date: 27 MAY 1998



- 45 -

a' , s' are independently greater than or equal to 0, and $a' + s' \geq 1$.

36. The contact lens of Claim 35 wherein said crosslinking agent is methacryloxyethyl vinyl carbonate.

This is the replacement sheet

Date: 27 MAY 1993