

**CATALYST COMPOSITIONS AND PROCESSES
FOR MAKING AND USING SAME**

CROSS-REFERENCE TO RELATED APPLICATIONS

- 5 [0001] This application claims priority to and the benefit of U.S. Provisional Application No. 63/286,312 having a filing date of December 06, 2021, and U.S. Provisional Application No. 63/329,042 having a filing date of April 08, 2022, the disclosures of both of which are incorporated herein by reference in their entireties.

FIELD

- 10 [0002] This disclosure relates to catalysts and processes for making and using same.

BACKGROUND

- [0003] Catalytic reforming or dehydrogenation, dehydroaromatization, and/or dehydrocyclization of alkane and/or alkyl aromatic hydrocarbons are industrially important chemical conversion processes that are endothermic and equilibrium-limited.
- 15 The reforming or dehydrogenation, dehydroaromatization, and/or dehydrocyclization of alkanes, *e.g.*, C₁-C₁₂ alkanes, and/or alkyl aromatics, *e.g.*, ethylbenzene, can be done through a variety of different catalyst compositions such as the Pt-based, Ni-based, Pd-based, Ru-based, Re-based, Cr-based, Ga-based, V-based, Zr-based, In-based, W-based, Mo-based, Zn-based, and Fe-based systems.
- 20 [0004] Precious metals used on a catalyst can be expensive and they can contribute significantly to the capital operating expenses and/or operating expenses of a chemical plant. There is a need, therefore, to reduce the concentration of precious metal(s) used to make a catalyst. This disclosure satisfies this and other needs.

SUMMARY

- 25 [0005] Catalyst compositions and processes for making and using same are provided. In some embodiments, the catalyst composition can include up to 0.025 wt% of Pt and up to 10 wt% of a promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on a support. The support can include at least 0.5 wt% of a Group 2 element. All weight percent values are based on the weight of the support.
- 30 [0006] In some embodiments, the process for making a catalyst composition can include: (I) preparing a slurry or gel that can include a compound containing a Group 2 element and a liquid medium. The process can also include (II) spray drying the slurry or the gel to produce spray dried particles that include the Group 2 element. The process can also

include (III) calcining the spray dried particles under an oxidative atmosphere to produce calcined support particles that include the Group 2 element. The process can also include at least one of (i), (ii), and (iii): (i) Pt can be present in the slurry or the gel in the form of a Pt-containing compound and the catalyst composition can include catalyst particles that include the calcined support particles having Pt disposed thereon, (ii) Pt can be deposited on the spray dried particles by contacting the spray dried particles with a Pt-containing compound to produce Pt-containing spray dried particles and the catalyst composition can include catalyst particles that include the calcined support particles having Pt disposed thereon, and (iii) Pt can be deposited on the calcined support particles by contacting the calcined support particles with a Pt-containing compound to produce Pt-containing calcined support particles and the process can further include (IV) calcining the Pt-containing calcined support particles to produce re-calcined support particles having Pt disposed thereon, where the catalyst composition includes the re-calcined support particles. The process can also include at least one of (iv), (v), and (vi): (iv) a compound that includes a promoter element can be present in the slurry or the gel and the catalyst composition can include catalyst particles that include the calcined support particles having the promoter element disposed thereon, (v) a compound that includes a promoter element can be deposited on the spray dried particles to produce promoter-containing spray dried particles and the catalyst composition can include catalyst particles that include the calcined support particles having the promoter element disposed thereon, and (vi) a compound that includes a promoter element can be deposited on the calcined support particles to produce promoter-containing calcined support particles and the process can further include (V) calcining the promoter-containing calcined support particles to produce re-calcined support particles having the promoter element disposed thereon, where the catalyst composition includes the re-calcined support particles. The promoter element can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof. The catalyst particles can include the Pt in an amount up to 0.025 wt% and the promoter element in an amount of up to 10 wt% based on the weight of the calcined support particles or the re-calcined support particles. The catalyst particles can include at least 0.5 wt% of the Group 2 element based on the weight of the calcined support particles or the re-calcined support particles.

[0007] In some embodiments, a process for upgrading a hydrocarbon can include (I) contacting a hydrocarbon-containing feed with a catalyst composition that can include Pt and a promoter disposed on a support to effect one or more of dehydrogenation,

dehydroaromatization, and dehydrocyclization of at least a portion of the hydrocarbon-containing feed to produce a coked catalyst composition and an effluent that can include one or more upgraded hydrocarbons and molecular hydrogen. The hydrocarbon-containing feed can include one or more of C₂-C₁₆ linear or branched alkanes, or one or
5 more of C₄-C₁₆ cyclic alkanes, or one or more C₈-C₁₆ alkyl aromatics, or a mixture thereof. The hydrocarbon-containing feed and the catalyst composition can be contacted at a temperature in a range of from 300°C to 900°C, for a time period of ≤ 3 hours, under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics
10 in the hydrocarbon-containing feed. The support can include at least 0.5 wt% of a Group 2 element based on the weight of the support. The catalyst composition can include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter based on the weight of the support. The promoter can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof. The one or more upgraded hydrocarbons can include at least one of a dehydrogenated
15 hydrocarbon, a dehydroaromatized hydrocarbon, and a dehydrocyclized hydrocarbon.

BRIEF DESCRIPTION OF THE DRAWING

[0008] The Figure shows a catalyst composition (Catalyst 6) maintained its performance for 204 cycles.

DETAILED DESCRIPTION

20 [0009] Various specific embodiments, versions and examples of the invention will now be described, including preferred embodiments and definitions that are adopted herein for purposes of understanding the claimed invention. While the following detailed description gives specific preferred embodiments, those skilled in the art will appreciate that these embodiments are exemplary only, and that the invention may be practiced in
25 other ways. For purposes of determining infringement, the scope of the invention will refer to any one or more of the appended claims, including their equivalents, and elements or limitations that are equivalent to those that are recited. Any reference to the “invention” may refer to one or more, but not necessarily all, of the inventions defined by the claims.

[0010] In this disclosure, a process is described as comprising at least one “step.” It
30 should be understood that each step is an action or operation that may be carried out once or multiple times in the process, in a continuous or discontinuous fashion. Unless specified to the contrary or the context clearly indicates otherwise, multiple steps in a process may be conducted sequentially in the order as they are listed, with or without overlapping with one or more other steps, or in any other order, as the case may be. In

addition, one or more or even all steps may be conducted simultaneously with regard to the same or different batch of material. For example, in a continuous process, while a first step in a process is being conducted with respect to a raw material just fed into the beginning of the process, a second step may be carried out simultaneously with respect to

5 an intermediate material resulting from treating the raw materials fed into the process at an earlier time in the first step. Preferably, the steps are conducted in the order described.

[0011] Unless otherwise indicated, all numbers indicating quantities in this disclosure are to be understood as being modified by the term “about” in all instances. It should also be understood that the precise numerical values used in the specification and claims

10 constitute specific embodiments. Efforts have been made to ensure the accuracy of the data in the examples. However, it should be understood that any measured data inherently contains a certain level of error due to the limitation of the technique and/or equipment used for acquiring the measurement.

[0012] Certain embodiments and features are described herein using a set of numerical upper limits and a set of numerical lower limits. It should be appreciated that ranges including the combination of any two values, e.g., the combination of any lower value with any upper value, the combination of any two lower values, and/or the combination of any two upper values are contemplated unless otherwise indicated.

15 [0013] The indefinite article “a” or “an”, as used herein, means “at least one” unless specified to the contrary or the context clearly indicates otherwise. Thus, embodiments using “a reactor” or “a conversion zone” include embodiments where one, two or more reactors or conversion zones are used, unless specified to the contrary or the context clearly indicates that only one reactor or conversion zone is used.

[0014] The term “hydrocarbon” means (i) any compound consisting of hydrogen and carbon atoms or (ii) any mixture of two or more such compounds in (i). The term “C_n hydrocarbon,” where n is a positive integer, means (i) any hydrocarbon compound comprising carbon atom(s) in its molecule at the total number of n, or (ii) any mixture of two or more such hydrocarbon compounds in (i). Thus, a C₂ hydrocarbon can be ethane, ethylene, acetylene, or mixtures of at least two of these compounds at any proportion. A

25 “C_m to C_n hydrocarbon” or “C_m-C_n hydrocarbon,” where m and n are positive integers and m < n, means any of C_m, C_{m+1}, C_{m+2}, ..., C_{n-1}, C_n hydrocarbons, or any mixtures of two or more thereof. Thus, a “C₂ to C₃ hydrocarbon” or “C₂-C₃ hydrocarbon” can be any of ethane, ethylene, acetylene, propane, propene, propyne, propadiene, cyclopropane, and any mixtures of two or more thereof at any proportion between and among the

30

- components. A “saturated C2-C3 hydrocarbon” can be ethane, propane, cyclopropane, or any mixture thereof of two or more thereof at any proportion. A “C_n+ hydrocarbon” means (i) any hydrocarbon compound comprising carbon atom(s) in its molecule at the total number of at least n, or (ii) any mixture of two or more such hydrocarbon compounds in (i). A “C_n- hydrocarbon” means (i) any hydrocarbon compound comprising carbon atoms in its molecule at the total number of at most n, or (ii) any mixture of two or more such hydrocarbon compounds in (i). A “C_m hydrocarbon stream” means a hydrocarbon stream consisting essentially of C_m hydrocarbon(s). A “C_m-C_n hydrocarbon stream” means a hydrocarbon stream consisting essentially of C_m-C_n hydrocarbon(s).
- 10 [0015] For the purposes of this disclosure, the nomenclature of elements is pursuant to the version of the Periodic Table of Elements (under the new notation) as provided in Hawley’s Condensed Chemical Dictionary, 16th Ed., John Wiley & Sons, Inc., (2016), Appendix V. For example, a Group 2 element includes Mg, a Group 8 element includes Fe, a Group 9 element includes Co, a Group 10 element includes Ni, and a Group 13 element includes Al. The term “metalloid”, as used herein, refers to the following elements: B, Si, Ge, As, Sb, Te, and At. In this disclosure, when a given element is indicated as present, it can be present in the elemental state or as any chemical compound thereof, unless it is specified otherwise or clearly indicated otherwise by the context.
- 15 [0016] The term “alkane” means a saturated hydrocarbon. The term “cyclic alkane” means a saturated hydrocarbon comprising a cyclic carbon ring in the molecular structure thereof. An alkane can be linear, branched, or cyclic.
- [0017] The term “aromatic” is to be understood in accordance with its art-recognized scope, which includes alkyl substituted and unsubstituted mono- and polynuclear compounds.
- 25 [0018] The term “rich” when used in phrases such as “X-rich” or “rich in X” means, with respect to an outgoing stream obtained from a device, e.g., a conversion zone, that the stream comprises material X at a concentration higher than in the feed material fed to the same device from which the stream is derived. The term “lean” when used in phrases such as “X-lean” or “lean in X” means, with respect to an outgoing stream obtained from a device, e.g., a conversion zone, that the stream comprises material X at a concentration lower than in the feed material fed to the same device from which the stream is derived.
- 30 [0019] The term “mixed metal oxide” refers to a composition that includes oxygen atoms and at least two different metal atoms that are mixed on an atomic scale. For example, a “mixed Mg/Al metal oxide” has O, Mg, and Al atoms mixed on an atomic

scale and is substantially the same as or identical to a composition obtained by calcining an Mg/Al hydrotalcite that has the general chemical formula $[Mg_{(1-x)}Al_x(OH)_2](A_{\frac{x}{n}}^{n-}) \cdot mH_2O]$, where A is a counter anion of a negative charge n, x is in a range of from > 0 to < 1 , and m is ≥ 0 . A material consisting of nm sized MgO particles and nm sized Al_2O_3 particles mixed together is not a mixed metal oxide because the Mg and Al atoms are not mixed on an atomic scale but are instead mixed on a nm scale.

[0020] The term “selectivity” refers to the production (on a carbon mole basis) of a specified compound in a catalytic reaction. As an example, the phrase “an alkane hydrocarbon conversion reaction has a 100% selectivity for an olefin hydrocarbon” means that 100% of the alkane hydrocarbon (carbon mole basis) that is converted in the reaction is converted to the olefin hydrocarbon. When used in connection with a specified reactant, the term “conversion” means the amount of the reactant consumed in the reaction. For example, when the specified reactant is propane, 100% conversion means 100% of the propane is consumed in the reaction. In another example, when the specified reactant is propane, if one mole of propane converts to one mole of methane and one mole of ethylene, the selectivity to methane is 33.3% and the selectivity to ethylene is 66.7%. Yield (carbon mole basis) is conversion times selectivity.

[0021] In this disclosure, “A, B, ... or a combination thereof” means “A, B, ... or any combination of any two or more of A, B, ...” “A, B, ..., or a mixture thereof” means “A, B, ..., or any mixture of any two or more of A, B, ...”

Catalyst Composition

[0022] In some embodiments, the catalyst composition can include up to 0.025 wt% of Pt disposed on a support, based on the weight of the support. In some embodiments, the catalyst composition can include 0.001 wt%, 0.002 wt%, 0.003 wt%, 0.004 wt%, 0.005 wt%, 0.006 wt%, 0.007 wt%, 0.008 wt%, or 0.009 wt% to 0.01 wt%, 0.011 wt%, 0.012 wt%, 0.013 wt%, 0.014 wt%, 0.015 wt%, 0.016 wt%, 0.017 wt%, 0.018 wt%, 0.019 wt%, 0.02 wt%, 0.021 wt%, 0.022 wt%, 0.023 wt%, 0.024 wt%, or 0.025 wt% of Pt disposed on the support, based on the weight of the support. In some embodiments, the catalyst composition can optionally also include Ni, Pd, or a combination thereof, or a mixture thereof disposed on the support. If Ni, Pd, a combination thereof, or a mixture thereof is also disposed on the support the catalyst composition can include 0.001 wt%, 0.002 wt%, 0.003 wt%, 0.004 wt%, 0.005 wt%, 0.006 wt%, 0.007 wt%, 0.008 wt%, or 0.009 wt% to 0.01 wt%, 0.011 wt%, 0.012 wt%, 0.013 wt%, 0.014 wt%, 0.015 wt%, 0.016 wt%, 0.017 wt%, 0.018 wt%, 0.019 wt%, 0.02 wt%, 0.021 wt%, 0.022 wt%, 0.023 wt%, 0.024 wt%,

or 0.025 wt% of a combined amount of Pt and any Ni and/or any Pd disposed on the support, based on the weight of the support. In some embodiments, an active component of the catalyst composition that can be capable of effecting one or more of reforming or dehydrogenation, dehydroaromatization, and dehydrocyclization of a hydrocarbon-containing feed can include the Pt or the Pt and Ni and/or Pd.

[0023] In some embodiments, the catalyst composition can also include a promoter in an amount of up to 10 wt% disposed on the support, based on the weight of the support. In some embodiments, the catalyst composition can include 0.01 wt%, 0.1 wt%, 0.2 wt%, 0.25 wt%, 0.3 wt%, 0.4 wt%, 0.5 wt%, 0.6 wt%, 0.7 wt%, 0.8 wt%, 0.9 wt%, or 1 wt% to 2 wt%, 3 wt%, 4 wt%, 5 wt%, 6 wt%, 7 wt%, 8 wt%, 9 wt%, or 10 wt% of the promoter disposed on the support, based on the weight of the support. The promoter can be or can include, but is not limited to, Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof. In some embodiments, the promoter can be associated with the Pt and/or, if present, the Ni and/or Pd. For example, the promoter and the Pt disposed on the support can form Pt-promoter clusters that can be dispersed on the support. The promoter can improve the selectivity/activity/longevity of the catalyst composition for a given upgraded hydrocarbon. In some embodiments, the promoter can improve the propylene selectivity of the catalyst composition when the hydrocarbon-containing feed includes propane.

[0024] In some embodiments, the catalyst composition can optionally include one or more alkali metal elements in an amount of up to 5 wt% disposed on the support, based on the weight of the support. In some embodiments, the catalyst composition can include 0.01 wt%, 0.1 wt%, 0.2 wt%, 0.3 wt%, 0.4 wt%, 0.5 wt%, 0.6 wt%, 0.7 wt%, 0.8 wt%, 0.9 wt%, or 1 wt% to 2 wt%, 3 wt%, 4 wt%, or 5 wt% of the alkali metal element disposed on the support, based on the weight of the support. The alkali metal element, if present, can be or can include, but is not limited to, Li, Na, K, Rb, Cs, or a combination thereof, or a mixture thereof. In at least some embodiments, the alkali metal element can be or can include K and/or Cs. In some embodiments, the alkali metal element, if present, can improve the selectivity of the catalyst composition for a given upgraded hydrocarbon.

[0025] The support can be or can include, but is not limited to, one or more Group 2 elements, a combination thereof, or a mixture thereof. In some embodiments, the Group 2 element can be present in its elemental form. In other embodiments, the Group 2 element can be present in the form of a compound. For example, the Group 2 element can be present as an oxide, a phosphate, a halide, a halate, a sulfate, a sulfide, a borate, a nitride, a carbide, an aluminate, an aluminosilicate, a silicate, a carbonate, metaphosphate, a

selenide, a tungstate, a molybdate, a chromite, a chromate, a dichromate, or a silicide. In some embodiments, a mixture of any two or more compounds that include the Group 2 element can be present in different forms. For example, a first compound can be an oxide and a second compound can be an aluminate where the first compound and the second compound include the same or different Group 2 element, with respect to one another.

[0026] The support can include ≥ 0.5 wt%, ≥ 1 wt%, ≥ 2 wt%, ≥ 3 wt%, ≥ 4 wt%, ≥ 5 wt%, ≥ 6 wt%, ≥ 7 wt%, ≥ 8 wt%, ≥ 9 wt%, ≥ 10 wt%, ≥ 11 wt%, ≥ 12 wt%, ≥ 13 wt%, ≥ 14 wt%, ≥ 15 wt%, ≥ 16 wt%, ≥ 17 wt%, ≥ 18 wt%, ≥ 19 wt%, ≥ 20 wt%, ≥ 21 wt%, ≥ 22 wt%, ≥ 23 wt%, ≥ 24 wt%, ≥ 25 wt%, ≥ 26 wt%, ≥ 27 wt%, ≥ 28 wt%, ≥ 29 wt%, ≥ 30 wt%, ≥ 35 wt%, ≥ 40 wt%, ≥ 45 wt%, ≥ 50 wt%, ≥ 55 wt%, ≥ 60 wt%, ≥ 65 wt%, ≥ 70 wt%, ≥ 75 wt%, ≥ 80 wt%, ≥ 85 wt%, or ≥ 90 wt% of the Group 2 element, based on the weight of the support. In some embodiments, the support can include the Group 2 element in a range of from 0.5 wt%, 1 wt%, 2 wt%, 2.5 wt%, 3 wt%, 5 wt%, 7 wt%, 10 wt%, 11 wt%, 13 wt%, 15 wt%, 17 wt%, 19 wt%, 21 wt%, 23 wt%, or 25 wt% to 30 wt%, 35 wt%, 40 wt%, 45 wt%, 50 wt%, 55 wt%, 60 wt%, 65 wt%, 70 wt%, 75 wt%, 80 wt%, 85 wt%, 90 wt%, or 92.34 wt% based on the weight of the support.

[0027] In some embodiments, a molar ratio of the Group 2 element to the Pt or the Pt and any Ni and/or Pd present can be in a range from 0.24, 0.5, 1, 10, 50, 100, 300, 450, 600, 800, 1,000, 1,200, 1,500, 1,700, or 2,000 to 3,000, 3,500, 4,000, 4,500, 5,000, 5,500, 6,000, 6,500, 7,000, 7,500, 8,000, 8,500, 9,000, 9,500, 10,000, 15,000, 20,000, 25,000, 30,000, 35,000, 40,000, 45,000, 50,000, 55,000, 60,000, 65,000, 70,000, 75,000, 80,000, 85,000, 90,000, 95,000, 100,000, 200,000, 300,000, 400,000, 500,000, 600,000, 700,000, 800,000, or 900,000.

[0028] In some embodiments, the support can include the Group 2 element and Al and can be in the form of a mixed Group 2 element/Al metal oxide that has O, Mg, and Al atoms mixed on an atomic scale. In some embodiments the support can be or can include the Group 2 element and Al in the form of an oxide or one or more oxides of the Group 2 element and Al_2O_3 that can be mixed on a nm scale. In some embodiments, the support can be or can include an oxide of the Group 2 element, e.g., MgO, and Al_2O_3 mixed on a nm scale.

[0029] In some embodiments, the support can be or can include a first quantity of the Group 2 element and Al in the form of a mixed Group 2 element/Al metal oxide and a second quantity of the Group 2 element in the form of an oxide of the Group 2 element. In such embodiment, the mixed Group 2 element/Al metal oxide and the oxide of the

Group 2 element can be mixed on the nm scale and the Group 2 element and Al in the mixed Group 2 element/Al metal oxide can be mixed on the atomic scale.

[0030] In other embodiments, the support can be or can include a first quantity of the Group 2 element and a first quantity of Al in the form of a mixed Group 2 element/Al metal oxide, a second quantity of the Group 2 element in the form of an oxide of the Group 2 element, and a second quantity of Al in the form of Al_2O_3 . In such embodiment, the mixed Group 2 element/Al metal oxide, the oxide of the Group 2 element, and the Al_2O_3 can be mixed on a nm scale and the Group 2 element and Al in the mixed Group 2 element/Al metal oxide can be mixed on the atomic scale.

[0031] In some embodiments, when the support includes the Group 2 element and Al, a weight ratio of the Group 2 element to the Al in the support can be in a range from 0.001, 0.005, 0.01, 0.05, 0.1, 0.15, 0.2, 0.3, 0.5, 0.7, or 1 to 3, 6, 12.5, 25, 50, 75, 100, 200, 300, 400, 500, 600, 700, 800, 900, or 1,000. In some embodiments, when the support includes Al, the inorganic support can include Al in a range from 0.5 wt%, 1 wt%, 1.5 wt%, 2 wt%, 2.1 wt%, 2.3 wt%, 2.5 wt%, 2.7 wt%, 3 wt%, 4 wt%, 5 wt%, 6 wt%, 7 wt%, 8 wt%, 9 wt%, 10 wt%, or 11 wt% to 15 wt%, 20 wt%, 25 wt%, 30 wt%, 40 wt%, 45 wt%, or 50 wt%, based on the weight of the support.

[0032] In some embodiments, the Group 2 element can include Mg and at least a portion of the Group 2 element can be in the form of MgO or a mixed metal oxide that includes Mg. In some embodiments, the support can be or can include, but is not limited to, a mixed Mg/Al metal oxide. In some embodiments, the support can be or can include a mixed Mg/Al metal oxide produced or obtained by calcining hydrotalcite. In some embodiments, the support can be or can include a mixed Mg/Al metal oxide having the same or similar structure of the compound produced or obtained by calcining hydrotalcite but made via an alternative process. In some embodiments, when the support is a mixed Mg/Al metal oxide, the support can have a weight ratio of Mg to Al in a range of from 0.001, 0.005, 0.01, 0.05, 0.1, 0.5, 1, 1.5, 2, 2.5, 3, 3.5, 4, 4.5, or 5 to 6, 10, 12.5, 25, 50, 75, 100, 150, 200, 250, 300, 350, 400, 450, 500, 550, 600, 650, 700, 750, 800, 850, 900, 950, or 1,000.

[0033] In some embodiments, the support can be or can include, but is not limited to, one or more of the following compounds: $\text{Mg}_w\text{Al}_2\text{O}_{3+w}$, where w is a positive number; $\text{Ca}_x\text{Al}_2\text{O}_{3+x}$, where x is a positive number; $\text{Sr}_y\text{Al}_2\text{O}_{3+y}$, where y is a positive number; $\text{Ba}_z\text{Al}_2\text{O}_{3+z}$, where z is a positive number. BeO , MgO , CaO , BaO , SrO , BeCO_3 , MgCO_3 , CaCO_3 , SrCO_3 , BaCO_3 , CaZrO_3 , $\text{Ca}_7\text{ZrAl}_6\text{O}_{18}$, CaTiO_3 , $\text{Ca}_7\text{Al}_6\text{O}_{18}$, $\text{Ca}_7\text{HfAl}_6\text{O}_{18}$.

BaCeO₃, one or more magnesium chromates, one or more magnesium tungstates, one or more magnesium molybdates, combinations thereof, and/or mixtures thereof.

[0034] The Mg_wAl₂O_{3+w}, where w is a positive number, if present as the support or as a component of the support can have a molar ratio of Mg to Al in a range from 0.5, 1, 2, 3, 4, or 5 to 6, 7, 8, 9, or 10. In some embodiments, the Mg_wAl₂O_{3+w} can include MgAl₂O₄, Mg₂Al₂O₅, or a mixture thereof. The Ca_xAl₂O_{3+x}, where x is a positive number, if present as the support or as a component of the support can have a molar ratio of Ca to Al in a range from 1:12, 1:4, 1:2, 2:3, 5:6, 1:1, 12:14, or 1.5:1. In some embodiments, the Ca_xAl₂O_{3+x} can include tricalcium aluminate, dodecacalcium hepta-aluminate, monocalcium aluminate, monocalcium dialuminate, monocalcium hexa-aluminate, dicalcium aluminate, pentacalcium trialuminate, tetracalcium trialuminate, or any mixture thereof. The Sr_yAl₂O_{3+y}, where y is a positive number, if present as the support or as a component of the support can have a molar ratio of Sr to Al in a range from 0.05, 0.3, or 0.6 to 0.9, 1.5, or 3. The Ba_zAl₂O_{3+z}, where z is a positive number, if present as the support or as a component of the support can have a molar ratio of Ba to Al 0.05, 0.3, or 0.6 to 0.9, 1.5, or 3.

[0035] In some embodiments, the support can also include, but is not limited to, at least one metal element and/or at least one metalloid element selected from Groups other than Group 2 and Group 10 and/or at least one compound thereof, where the at least one metal element and/or at least one metalloid element is not Li, Na, K, Rb, Cs, Sn, Cu, Au, Ag, or Ga. If the support also includes a compound that includes the metal element and/or metalloid element selected from Groups other than Group 2 and Group 10, where the at least one metal element and/or at least one metalloid element is not Li, Na, K, Rb, Cs, Sn, Cu, Au, Ag, or Ga, the compound can be present in the support as an oxide, a phosphate, a halide, a halate, a sulfate, a sulfide, a borate, a nitride, a carbide, an aluminate, an aluminosilicate, a silicate, a carbonate, metaphosphate, a selenide, a tungstate, a molybdate, a chromite, a chromate, a dichromate, or a silicide. In some embodiments, the at least one metal element and/or at least one metalloid element selected from Groups other than Group 2 and Group 10 and/or at least one compound thereof, where the at least one metal element and/or at least one metalloid element is not Li, Na, K, Rb, Cs, Sn, Cu, Au, Ag, or Ga can be or can include, but is not limited to, one or more rare earth elements, i.e., elements having an atomic number of 21, 39, or 57 to 71.

[0036] If the support includes the at least one metal element and/or at least one metalloid element selected from Groups other than Group 2 and Group 10 and/or at least one

compound thereof, where the at least one metal element and/or at least one metalloid element is not Li, Na, K, Rb, Cs, Sn, Cu, Au, Ag, or Ga, the at least one metal element and/or at least one metalloid element can, in some embodiments, function as a binder and can be referred to as a "binder". Regardless of whether or not the at least one metal element and/or at least one metalloid element selected from Groups other than Group 2 and Group 10 and/or at least one compound thereof, where the at least one metal element and/or at least one metalloid element is not Li, Na, K, Rb, Cs, Sn, Cu, Au, Ag, or Ga, the at least one metal element and/or at least one metalloid element selected from Groups other than Group 2 and Group 10 will be further described herein as a "binder" for clarity and ease of description. In some embodiments, the support can include the binder in a range of from 0.01 wt%, 0.05 wt%, 0.1 wt%, 0.5 wt%, 1 wt%, 5 wt%, 10 wt%, 15 wt%, 20 wt%, 25 wt%, 30 wt%, 35 wt% or 40 wt% to 50 wt%, 60 wt%, 70 wt%, 80 wt%, or 90 wt% based on the weight of the support.

[0037] In some embodiments, suitable compounds that can be used as the binder can be or can include, but are not limited to, one or more of the following: B_2O_3 , $AlBO_3$, Al_2O_3 , SiO_2 , ZrO_2 , TiO_2 , SiC , Si_3N_4 , an aluminosilicate, zinc aluminate, ZnO , VO , V_2O_3 , VO_2 , V_2O_5 , Ga_2O_3 , In_2O_3 , Mn_2O_3 , Mn_3O_4 , MnO , one or more molybdenum oxides, one or more tungsten oxides, one or more zeolites, where s, t, u, and v are positive numbers and mixtures and combinations thereof. If the Group 2 element is in the form of a mixed metal oxide, e.g., a mixed Mg/Al metal oxide, the additional metal(s) in the mixed metal oxide is/are not considered to be part of a binder. For example, the support may include a mixed Mg/Al metal oxide, such as those obtained by calcining an Mg/Al hydrotalcite, and a binder that is Al_2O_3 .

[0038] It has been surprisingly and unexpectedly discovered that the amount of Pt or the amount of Pt and Ni and/or Pd disposed on the support can be significantly reduced below an amount thought necessary to produce a catalyst composition with sufficient activity. More particularly, it has been surprisingly and unexpectedly discovered that the amount of Pt or the amount of Pt and Ni and/or Pd disposed on the support that includes at least 0.5 wt% of the Group 2 element can be ≤ 0.025 wt% while still maintaining a sufficient level of activity, which was not believed to be possible. The conventional thought was that the amount of Pt or the amount of Pt and Ni and/or Pd needed to be at least 0.05 wt% based on the weight of the support. For example, see, U.S. Patent Nos: 6,967,182; 5,922,925; 6,582,589; 6,313,063 and 5,817,596; U.S. Patent Application

Publication Nos.: 2003/0139637; 2004/0029729; 2005/0003960; and EP Patent Application Nos.: EP1016641 and EP1073516.

[0039] In some embodiments, the catalyst composition can include 0.001 wt%, 0.005 wt%, 0.01 wt%, 0.015 wt%, 0.02 wt%, 0.025 wt%, 0.03 wt%, 0.06 wt%, 0.08 wt%, 0.1 wt%, 0.2 wt%, 0.5 wt%, or 1 wt% to 2 wt%, 3 wt%, 4 wt%, 5 wt%, or 6 wt% of the Pt or the Pt and Ni and/or Pd disposed on the support that includes at least 0.5 wt% of the Group 2 element, where all weight percent values are based on the weight of the support, and where the promoter is optional. In such embodiments, at least a portion of the Group 2 element in the support can be in the form of a mixed Group 2 element/Al metal oxide. When at least a portion of the Group 2 element in the support is in the form of a mixed Group 2 element/Al metal oxide, it has been surprisingly and unexpectedly discovered that the presence of Si in the catalyst composition in an amount of 0.1 wt% or more has a detrimental impact on the stability of the performance of the catalyst. For example, when the support includes a mixed Mg/Al metal oxide the presence of Si in an amount of 0.1 wt% or more has a detrimental impact on the stability of the performance of the catalyst. As such, when at least a portion of the Group 2 element in the support is in the form of a mixed Group 2 element/Al metal oxide, where the promoter is optional, the catalyst composition can include < 0.1 wt%, < 0.09 wt%, < 0.08 wt%, < 0.07 wt%, < 0.06 wt%, < 0.05 wt%, < 0.04 wt%, < 0.03 wt%, < 0.02 wt%, < 0.01 wt%, < 0.007 wt%, < 0.005 wt%, or < 0.001 wt% of Si. In other embodiments, when at least a portion of the Group 2 element in the support is in the form of a mixed Group 2 element/Al metal oxide, where the promoter is optional, the catalyst composition can be free of any Si. In other embodiments, however, the support can be in the form of a mixed Group 2 element/Si metal oxide, where the promoter is optional, and the catalyst composition can include < 0.1 wt%, < 0.09 wt%, < 0.08 wt%, < 0.07 wt%, < 0.06 wt%, < 0.05 wt%, < 0.04 wt%, < 0.03 wt%, < 0.02 wt%, < 0.01 wt%, < 0.007 wt%, < 0.005 wt%, or < 0.001 wt% of Al.

[0040] In some embodiments, the catalyst composition can be in the form of catalyst particles or a monolithic structure. If the catalyst composition is in the form of catalyst particles, the catalyst particles can have a median particle size in a range of from 1 μm , 5 μm , 10 μm , 20 μm , 40 μm , or 60 μm to 80 μm , 100 μm , 115 μm , 130 μm , 150 μm , 200 μm , 300 μm or 400, or 500 μm . The catalyst particles can have an apparent loose bulk density in a range from 0.3 g/cm³, 0.4 g/cm³, 0.5 g/cm³, 0.6 g/cm³, 0.7 g/cm³, 0.8 g/cm³, 0.9 g/cm³, or 1 g/cm³ to 1.1 g/cm³, 1.2 g/cm³, 1.3 g/cm³, 1.4 g/cm³, 1.5 g/cm³, 1.6 g/cm³, 1.7 g/cm³, 1.8 g/cm³, 1.9 g/cm³, or 2 g/cm³, as measured according to ASTM D7481-18

modified with a 10, 25, or 50 mL graduated cylinder instead of a 100 or 250 mL graduated cylinder. In some embodiments, the catalyst particles can have an attrition loss after one hour of ≤ 5 wt%, ≤ 4 wt%, ≤ 3 wt%, ≤ 2 wt%, ≤ 1 wt%, ≤ 0.7 wt%, ≤ 0.5 wt%, ≤ 0.4 wt%, ≤ 0.3 wt%, ≤ 0.2 wt%, ≤ 0.1 wt%, ≤ 0.07 wt%, or ≤ 0.05 wt%, as measured according to
 5 ASTM D5757-11(2017). The morphology of the particles can be largely spherical so that they are suitable to run in a fluid bed reactor. In some embodiments, the catalyst particles can have a size and density that is consistent with a Geldart A or Geldart B definition of a fluidizable solid.

[0041] In some embodiments, the catalyst particles can have a surface area in a range
 10 from 0.1 m²/g, 1 m²/g, 10 m²/g, or 100 m²/g to 500 m²/g, 800 m²/g, 1,000 m²/g, or 1,500 m²/g. The surface area of the catalyst particles can be measured according to the Brunauer-Emmett-Teller (BET) method using adsorption-desorption of nitrogen (temperature of liquid nitrogen, 77 K) with a Micromeritics 3flex instrument after degassing of the powders for 4 hrs at 350°C. More information regarding the method can
 15 be found, for example, in "Characterization of Porous Solids and Powders: Surface Area, Pore Size and Density," S. Lowell et al., Springer, 2004.

First Process for Making Catalyst Particles

[0042] The process for making the catalyst composition can include preparing a slurry or gel that can include, milling, mixing, blending, combining, or otherwise contacting, but
 20 is not limited to, a compound containing a Group 2 element and a liquid medium. In some embodiments, preparation of the slurry or gel can also include contacting, but is not limited to, the compound containing a Group 2 element, the liquid medium, and one or more additives. In other embodiments, the preparing the slurry or gel can include contacting, but is not limited to, the compound containing a Group 2 element, the liquid
 25 medium, a binder or binder precursor, and, optionally, one or more additives.

[0043] The compound containing a Group 2 element can be in the form of an oxide, a hydroxide, a hydrated carbonate, a salt, a clay containing a Group 2 element, a layered double hydroxide, a phosphate, a halide, a halate, a sulfate, a sulfide, a borate, a nitride, a carbide, an aluminate, an aluminosilicate, a silicate, a carbonate, metaphosphate, a
 30 selenide, a tungstate, a molybdate, a chromite, a chromate, a dichromate, a silicide, or a mixture thereof. In some embodiments, the Group 2 element can be or can include Mg and the compound containing the Group 2 element can be in the form of a magnesium oxide, a magnesium hydroxide, hydromagnesite (a hydrated magnesium carbonate mineral, Mg₅(CO₃)₄(OH)₂•4H₂O), a magnesium salt, a magnesium-containing clay,

hydrotalcite (a layered double hydroxide), an organo-magnesium compound or a mixture thereof.

- [0044] The liquid medium can be or can include, but is not limited to, water, alcohols, acetone, chloroform, methylene chloride, dimethyl formamide, dimethyl sulfoxide, glycerin, ethyl acetate, or any mixture thereof. Illustrative alcohols can be or can include, but are not limited to methanol, ethanol, isopropanol, or any mixture thereof. The binder, if present, can be or can include the binders described above. The binder precursor, if present, can be or can include, but is not limited to, $\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4$ (Kaolin clay), aluminum chlorohydrate, boehmite, pseudoboehmite, gibbsite, bayerite, aluminum nitrate, aluminum chloride, sodium aluminate, alumina sol, silica sol, or any mixture thereof. It is known that in literature, some of the compounds herein referred to as “binders” may also be referred to as fillers, matrix, additive, etc. The one or more additives, if present, can be or can include, but is not limited to, acids such as formic acid, lactic acid, citric acid, acetic acid, HNO_3 , HCl , oxalic acid, stearic acid, carbonic acid, etc.; bases such as ammonia solution, NaOH , KOH , etc.; inorganic salts such as nitrates, carbonates, bicarbonates, chlorides, etc.; organic salts such as acetates, oxalates, formates, citrates, etc.; polymers such as polyvinyl alcohol, polysaccharide, etc., or any mixture thereof. The additives can help to improve the chemical/physical property of the spray dried material and/or to improve the rheological property of the slurry/gel to facilitate spray drying.
- [0045] The slurry or gel can be spray dried to produce spray dried particles that include the Group 2 element. Spray drying refers to the process of producing a dry particulate solid product from the slurry or the gel. The process can include spraying or atomizing the slurry or gel, e.g., forming small droplets, into a temperature-controlled gas stream to evaporate the liquid medium from the atomized droplets and produce the particulate solid product. For example, in the spray drying process, the slurry or gel can be atomized to small droplets and mixed with hot air or a hot inert gas, e.g., nitrogen, to evaporate the liquid from the droplets. The temperature of the slurry or gel during the spray drying process can usually be close to or greater than the boiling temperature of the liquid. An outlet air temperature of about 60°C to about 120°C can be common.
- [0046] The slurry or gel can be atomized with one or more pressure nozzles (e.g., a fluid nozzle atomizer), one or more pulse atomizers, one or more high speed spinning discs (e.g., centrifugal or rotary atomizer), or any other known process. The median particle size, liquid (e.g., water) concentration, apparent loose bulk density, or any combination thereof, of the particulate solid product prepared via spray drying can be controlled,

adjusted, or otherwise influenced by one or more operating conditions and/or parameters of the spray dryer. Illustrative operating conditions can include, but are not limited to, the feed rate and temperature of the gas stream, the atomizer velocity, the feed rate of the slurry or gel via the atomizer, the temperature of the slurry or gel, the size and/or solids concentration of the droplets, the spray dryer dimensions, or any combination thereof. It is well-known in the art that the various operating conditions will vary depending on the particular spray drying apparatus that is used and can be readily determined by persons having ordinary skill in the art.

[0047] The spray dried particles can, optionally, be calcined under an oxidative atmosphere, e.g., air, to produce calcined support particles that include the Group 2 element. In some embodiments, the spray dried particles can be calcined at a temperature in a range of from 450°C, 500°C, 525°C, 550°C, 575°C, 600°C, 625°C, 650°C, or 675°C to 700°C, 725°C, 750°C, 775°C, 800°C, 850°C, 900°C, or 950°C. In some embodiments, the spray dried particles can be calcined at a temperature of $\leq 950^{\circ}\text{C}$, $\leq 900^{\circ}\text{C}$, $\leq 850^{\circ}\text{C}$, $\leq 800^{\circ}\text{C}$, $\leq 750^{\circ}\text{C}$, $\leq 700^{\circ}\text{C}$, $\leq 650^{\circ}\text{C}$, $\leq 600^{\circ}\text{C}$, or $\leq 550^{\circ}\text{C}$, $\leq 525^{\circ}\text{C}$, $\leq 500^{\circ}\text{C}$, $\leq 475^{\circ}\text{C}$, or $\leq 460^{\circ}\text{C}$. In some embodiments, the spray dried particles can be calcined for a time period of ≤ 240 minutes ≤ 180 minutes ≤ 120 minutes ≤ 90 minutes, ≤ 60 minutes, ≤ 45 minutes, ≤ 30 minutes, ≤ 25 minutes, ≤ 20 minutes, or ≤ 15 minutes. In some embodiments, the spray dried particles can be calcined in the presence of oxygen, e.g., air. In some embodiments, the spray dried particles can be calcined at a temperature in a range of from 550°C to 900°C or 550°C to 850°C for a time period of ≤ 240 minutes ≤ 180 minutes ≤ 120 minutes ≤ 90 minutes, ≤ 60 minutes, ≤ 45 minutes, ≤ 30 minutes, ≤ 25 minutes, ≤ 20 minutes, or ≤ 15 minutes. In other embodiments, the spray dried particles are calcined at a temperature of $\leq 550^{\circ}\text{C}$, $\leq 540^{\circ}\text{C}$, $\leq 530^{\circ}\text{C}$, $\leq 520^{\circ}\text{C}$, $\leq 510^{\circ}\text{C}$, or $\leq 500^{\circ}\text{C}$ for a time period of ≤ 240 minutes ≤ 180 minutes ≤ 120 minutes ≤ 90 minutes, ≤ 60 minutes, ≤ 45 minutes, ≤ 30 minutes, ≤ 25 minutes, ≤ 20 minutes, or ≤ 15 minutes.

[0048] The Pt present in the catalyst particles can be introduced via one or more ways. In some embodiments, the process for making the catalyst composition can include (i) contacting at least the compound containing the Group 2 element and the liquid medium with a Pt-containing compound such that the Pt can be present in the slurry or the gel and the catalyst composition can include catalyst particles that include the calcined support particles having Pt disposed thereon. In other embodiments, the process for making the catalyst composition can include (ii) depositing Pt on the spray dried particles by contacting the spray dried particles with a Pt-containing compound to produce Pt-

containing spray dried particles and the catalyst composition can include catalyst particles that include the calcined support particles having Pt disposed thereon. In other embodiments, the process for making the catalyst composition can include (iii) depositing Pt on the calcined support particles if the spray dried particles are optionally calcined by contacting the calcined support particles with a Pt-containing compound to produce Pt-containing calcined support particles and the process can, optionally, further include calcining the Pt-containing calcined support particles to produce re-calcined support particles having Pt disposed thereon, where the catalyst composition can include the re-calcined support particles. In some embodiments, the catalyst composition can include the Pt-containing calcined support particles without the optional additional calcination step. In other embodiments, the process for making the catalyst composition can include option (i), (ii), (iii), (i) and (ii), (i) and (iii), (ii) and (iii), or (i), (ii), and (iii). The Pt-containing compound can be or can include, but is not limited to, chloroplatinic acid hexahydrate, tetraammineplatinum(II) nitrate, platinum(II) acetylacetonate, platinum(II) bromide, platinum(II) iodide, platinum(II) chloride, platinum(IV) chloride, platinum(II)diammine dichloride, ammonium tetrachloroplatinate(II), tetraammineplatinum(II) chloride hydrate, tetraammineplatinum(II) hydroxide hydrate, or any mixture thereof.

[0049] The promoter present in the catalyst particles can be introduced via one or more ways. In some embodiments, the process for making the catalyst composition can include (iv) contacting at least the compound containing the Group 2 element and the liquid medium with a compound that includes a promoter element such that the promoter element is present in the slurry or the gel and the catalyst composition can include catalyst particles that include the calcined support particles having the promoter element disposed thereon. In other embodiments, the process for making the catalyst composition can include (v) depositing a compound that includes a promoter element on the spray dried particles to produce promoter-containing spray dried particles and the catalyst composition can include catalyst particles that include the calcined support particles having the promoter element disposed thereon. In other embodiments, the process for making the catalyst composition can include (vi) depositing a compound that includes a promoter element on the calcined support particles if the spray dried particles are optionally calcined to produce promoter-containing calcined support particles and the process can further include, optionally, calcining the promoter-containing calcined support particles to produce re-calcined support particles having the promoter element

disposed thereon, where the catalyst composition includes the re-calcined support particles. In some embodiments, the catalyst composition can include the promoter-containing calcined support particles without the optional additional calcination step. In other embodiments, the process for making the catalyst composition can include option
5 (iv), (v), (vi), (iv) and (v), (iv) and (vi), (v) and (vi), or (iv), (v), and (vi). In other embodiments, the process can include any one or more of options (i), (ii), and (iii) and any one or more of options (iv), (v), and (iv). The compound that includes the promoter element can be or can include, but is not limited to, tin(II) oxide, tin(IV) oxide, tin(IV) chloride pentahydrate, tin(II) chloride dihydrate, tin(II) bromide, tin(IV) bromide, tin(II)
10 acetylacetonate, tin(II) acetate, tin(IV) acetate, tin(II) oxalate, silver(I) nitrate, gold(III) nitrate, copper(II) nitrate, gallium(III) nitrate, or any mixture thereof.

[0050] The alkali metal element, if present in the catalyst particles, can be introduced via one or more ways. In some embodiments, the process for making the catalyst composition can include (vii) contacting at least the compound containing the Group 2
15 element and the liquid medium with a compound that includes an alkali metal element such that the alkali metal element is present in the slurry or the gel and the catalyst composition can include catalyst particles that include the calcined support particles having the alkali metal element disposed thereon. In other embodiments, the process for making the catalyst composition can include (viii) depositing a compound that includes
20 an alkali metal element on the spray dried particles to produce alkali metal element-containing spray dried particles and the catalyst composition can include catalyst particles that include the calcined support particles having the alkali metal element disposed thereon. In other embodiments, the process for making the catalyst composition can include (ix) depositing a compound that includes an alkali metal element on the calcined
25 support particles if the spray dried particles are optionally calcined to produce alkali metal element-containing calcined support particles and the process can further include, optionally, calcining the alkali metal element-containing calcined support particles to produce re-calcined support particles having the alkali metal element disposed thereon, where the catalyst composition includes the re-calcined support particles. In other
30 embodiments, the process for making the catalyst composition can include option (vii), (viii), (ix), (vii) and (viii), (vi) and (ix), (viii) and (ix), or (vii), (viii), and (iv). In other embodiments, the process can include any one or more of options (i), (ii), and (iii), any one or more of options (iv), (v), and (iv), and any one or more of options (vii), (viii), and (ix). The compound that includes the alkali metal element can be or can include, but are

not limited to, lithium nitrate, sodium nitrate, potassium nitrate, rubidium nitrate, cesium nitrate, or any mixture thereof.

[0051] In some embodiments, the process for making the catalyst composition can optionally include hydrating the calcined support particles to produce hydrated support particles. For example, the calcined support particles can be contacted with water to produce the hydrated support particles. In such embodiment, the process can also include calcining the hydrated support particles to produce the catalyst composition that includes re-calcined support particles. Hydrating the calcined support can be carried out at a temperature in a range of from 20°C, 40°C, or 60°C to 80°C, 120°C, 140°C, 160°C, 180°C, or 200°C. The calcined support can be contacted with the water for a time period in a range of from 1 minutes, 5 minutes, or 10 minutes to 20 minutes, 40 minutes, 80 minutes, 160 minutes, 6 hours, 12 hours, 24 hours, or 48 hours. In some embodiments, an anion such as chloride, nitrate, carbonate, bicarbonate, acetate, oxalate, formate, and/or citrate can be present during hydration.

[0052] In some embodiments, the process for making the catalyst composition can optionally include hydrating the spray dried particles to produce hydrated spray dried particles. For example, the spray dried particles can be contacted with water to produce the hydrated spray dried particles. In such embodiment, the process can also include calcining the hydrated spray dried particles to produce the catalyst composition that includes calcined support particles. Hydrating the spray dried particles can be carried out at a temperature in a range of from 20°C, 40°C, or 60°C to 80°C, 120°C, 140°C, 160°C, 180°C, or 200°C. The spray dried particles can be contacted with the water for a time period in a range of from 1 minutes, 5 minutes, or 10 minutes to 20 minutes, 40 minutes, 80 minutes, 160 minutes, 6 hours, 12 hours, 24 hours, or 48 hours. In some embodiments, an anion such as chloride, nitrate, carbonate, bicarbonate, acetate, oxalate, formate, and/or citrate can be present during hydration.

[0053] In some embodiments, the process for making the catalyst composition can optionally include hydrating the spray dried particles to produce hydrated spray dried particles, calcining the hydrated spray dried particles to produce calcined support particles, hydrating the calcined support particles to produce hydrated calcined support particles, and calcining the hydrated calcined support particles to produce re-calcined support particles. As such, the catalyst composition can include the spray dried particles, the calcined support particles, the hydrated spray dried particles, the hydrated spray dried

particles that can be calcined, the hydrated calcined support particles, the hydrated calcined support particles that can be re-calcined, or any mixture thereof.

[0054] In some embodiments, catalysts particles produced by hydrating the calcined support particles or the spray dried particles and then calcining the hydrated calcined support particles or the hydrated spray dried particles can produce catalyst particles that have an attrition loss after one hour that is less than an attrition loss after one hour of the initially calcined particles or the spray dried particles produced before the hydration step, as measured according to ASTM D5757-11(2017). In some embodiments, catalysts particles produced by hydrating the calcined support particles or the spray dried particles and then calcining the hydrated support particles or the hydrated support particles can produce catalyst particles that have an attrition loss after one hour that is 10% less, 30% less, 50% less, 70% less, 90% less, or 100% less, than an attrition loss after one hour of the initially calcined particles produced before the hydration step, as measured according to ASTM D5757-11(2017).

15 Second Process for Making Catalyst Particles

[0055] In some embodiments, the catalyst composition can be catalyst particles produced through only the spray drying step such that the slurry is prepared and spray dried particles are produced therefrom with the Pt and promoter added to the slurry, the spray dried particles, or a combination thereof. Accordingly, in some embodiments the process for making a catalyst composition, can include preparing the slurry or gel that can include the compound containing a Group 2 element and a liquid medium and optionally one or more additives as described above and spray drying the slurry or the gel to produce spray dried support particles that include the Group 2 element. At least one of (i) and (ii) can be met: (i) Pt can be present in the slurry or the gel in the form of the Pt-containing compound and the catalyst composition can include catalyst particles that include the spray dried support particles having Pt disposed thereon, and (ii) Pt can be deposited on the spray dried support particles by contacting the spray dried support particles with the Pt-containing compound to produce Pt-containing spray dried support particles and the catalyst composition can include catalyst particles that can include the spray dried support particles having Pt disposed thereon. At least one of (iii) and (iv) can also be met: (iii) the compound that includes the promoter element can be present in the slurry or the gel and the catalyst composition can include catalyst particles that include the spray dried support particles having the promoter element disposed thereon, and (iv) the compound that can include the promoter element can be deposited on the spray dried support particles to

produce promoter-containing spray dried support particles and the catalyst composition can include catalyst particles that include the spray dried support particles having the promoter element disposed thereon, where the promoter element includes Sn, Cu, Au, Ag, Ga, or a combination thereof, or a mixture thereof. In some embodiments, the optional
5 alkali metal element(s) and/or binders can also be added during the synthesis of the catalyst particles as described above.

[0056] In some embodiments, the catalyst particles can be further processed or activated in-situ by adding the catalyst particles into a hydrocarbon upgrading process that subjects the catalyst particles to higher severity conditions to produce catalyst particles having a
10 greater level of activation than just the spray dried particles have upon preparation thereof. In some embodiments, when the catalyst particles include catalyst particles only subjected to the spray drying step such that the slurry is prepared and spray dried support particles are produced therefrom with the Pt and promoter added to the slurry, the spray dried support particles, or a combination thereof, the catalyst particles can be introduced into a
15 reaction zone, a combustion zone, a reduction zone, or any other location within a fluidized hydrocarbon upgrading process some of which are further described below.

[0057] The preparation of the catalyst composition and processes for adding Pt, the promoter(s) such as Sn, the optional alkali metal element(s), and the optional rare earth metal element(s) to the catalyst composition has been described above. In some
20 embodiments, the preparation of the slurry or gel, spray drying the slurry, calcination of the spray dried particles and/or the hydrated calcined particles, and/or hydration of the Group 2 metal containing calcined support particles or the spray-dried particles can also be performed using one of the known methods reported in literature, such as U.S. Patent Nos. 4,866,019; 6,028,023; 6,589,902; 6,593,265; 6,800,578; 7,361,264; and 7,417,005;
25 U.S. Patent Application Publication Nos. 2004/0029729; 2005/000396; and 2016/0082424; WO Publication No. WO2008083563A1; and journal publications Wang et al., *Ind. Eng. Chem. Res.* 2008, 47, 5746–5750; Chubar et al., *Chem. Eng. J.* 2013, 234, 284-299; Valente et al., *Energy Environ. Sci.*, 2011, 4, 4096-4107; and Julklang et al., *Mater. Lett.* 2017, 209, 429-432.

30 A First Process for Upgrading a Hydrocarbon

[0058] The first process for upgrading a hydrocarbon can include contacting a hydrocarbon-containing feed (first hydrocarbon-containing feed) with the catalyst composition that includes Pt and the promoter disposed on the support to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a

portion of the first hydrocarbon-containing feed to produce a coked catalyst composition and an effluent that can include one or more upgraded hydrocarbons and molecular hydrogen. The catalyst composition and the first hydrocarbon-containing feed can be contacted with one another within any suitable environment such as one or more reaction
5 or conversion zones disposed within one or more reactors to produce the effluent and the coked catalyst composition. The reaction or conversion zone can be disposed or otherwise located within one or more fixed bed reactors, one or more fluidized or moving bed reactors, one or more reverse flow reactors, or any combination thereof.

[0059] The first hydrocarbon-containing feed and catalyst composition can be contacted
10 at a temperature in a range from 300°C, 350°C, 400°C, 450°C, 500°C, 550°C, 600°C, 620°C, 650°C, 660°C, 670°C, 680°C, 690°C, or 700°C to 725°C, 750°C, 760°C, 780°C, 800°C, 825°C, 850°C, 875°C, or 900°C. In some embodiments, the first hydrocarbon-containing feed and the catalyst composition can be contacted at a temperature of at least 620°C, at least 650°C, at least 660°C, at least 670°C, at least 680°C, at least 690°C, or at
15 least 700°C to 725°C, 750°C, 760°C, 780°C, 800°C, 825°C, 850°C, 875°C, or 900°C. The first hydrocarbon-containing feed can be introduced into the reaction or conversion zone and contacted with the catalyst composition therein for a time period of ≤ 3 hours, ≤ 2.5 hours, ≤ 2 hours, ≤ 1.5 hours, ≤ 1 hour, ≤ 45 minutes, ≤ 30 minutes, ≤ 20 minutes, ≤ 10 minutes, ≤ 5 minutes, ≤ 1 minute, ≤ 30 seconds, ≤ 10 seconds, ≤ 5 seconds, or ≤ 1
20 second or ≤ 0.5 second. In some embodiments, the first hydrocarbon-containing feed can be contacted with the catalyst composition for a time period in a range from 0.1 seconds, 0.5 seconds, 0.7 seconds, 1 second, 30 second, 1 minute, 5 minutes, or 10 minutes to 30 minutes, 50 minutes, 70 minutes, 1.5 hours, 2 hours, or 3 hours.

[0060] The first hydrocarbon-containing feed and the catalyst composition can be
25 contacted under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed. In some embodiments, the hydrocarbon partial pressure during contact of the first hydrocarbon-containing feed and the catalyst composition can be in a range from 20 kPa-absolute, 50 kPa-absolute, 100
30 kPa-absolute, at least 150 kPa, at least 200 kPa 300 kPa-absolute, 500 kPa-absolute, 750 kPa-absolute, or 1,000 kPa-absolute to 1,500 kPa-absolute, 2,500 kPa-absolute, 4,000 kPa-absolute, 5,000 kPa-absolute, 7,000 kPa-absolute, 8,500 kPa-absolute, or 10,000 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed. In other

embodiments, the hydrocarbon partial pressure during contact of the hydrocarbon-containing feed and the catalyst composition can be in a range from 20 kPa-absolute, 50 kPa-absolute, 100 kPa-absolute, 150 kPa-absolute, 200 kPa-absolute, 250 kPa-absolute, or 300 kPa-absolute to 500 kPa-absolute, 600 kPa-absolute, 700 kPa-absolute, 800 kPa-absolute, 900 kPa-absolute, or 1,000 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed.

[0061] In some embodiments, the first hydrocarbon-containing feed can include at least 60 vol%, at least 65 vol%, at least 70 vol%, at least 75 vol%, at least 80 vol%, at least 85 vol%, at least 90 vol%, at least 95 vol%, or at least 99 vol% of a single C₂-C₁₆ alkane, e.g., propane, based on a total volume of the first hydrocarbon-containing feed. The first hydrocarbon-containing feed and the catalyst composition can be contacted under a single C₂-C₁₆ alkane, e.g., propane, pressure of at least 20 kPa-absolute, at least 50 kPa-absolute, at least 100 kPa-absolute, at least 150 kPa-absolute, at least 250 kPa-absolute, at least 300 kPa-absolute, at least 400 kPa-absolute, at least 500 kPa-absolute, or at least 1,000 kPa-absolute.

[0062] The first hydrocarbon-containing feed can be contacted with the catalyst composition within the reaction or conversion zone at any weight hourly space velocity (WHSV) effective for carrying out the upgrading process. In some embodiments, the WHSV can be 0.01 hr⁻¹, 0.1 hr⁻¹, 1 hr⁻¹, 2 hr⁻¹, 5 hr⁻¹, 10 hr⁻¹, 20 hr⁻¹, 30 hr⁻¹, or 50 hr⁻¹ to 100 hr⁻¹, 250 hr⁻¹, 500 hr⁻¹, or 1,000 hr⁻¹. In some embodiments, when the hydrocarbon upgrading process includes a fluidized or otherwise moving catalyst composition, a ratio of the catalyst composition circulation mass flow rate to a combined amount of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics mass flow rate can be in a range from 1, 3, 5, 10, 15, 20, 25, 30, or 40 to 50, 60, 70, 80, 90, 100, 110, 125, or 150 on a weight to weight basis.

[0063] When the activity of the coked catalyst composition decreases below a desired minimum amount, the coked catalyst composition or at least a portion thereof can be subjected to a regeneration process to produce a regenerated catalyst composition. More particularly, the coked catalyst composition can be contacted with one or more oxidants to effect combustion of at least a portion of the coke to produce a regenerated catalyst composition lean in coke and a combustion gas. Regeneration of the coked catalyst composition can occur within the reaction or conversion zone or within a combustion zone that is separate and apart from the reaction or conversion zone, depending on the particular

reactor configuration, to produce a regenerated catalyst composition. For example, regeneration of the coked catalyst composition can occur within the reaction or conversion zone when a fixed bed or reverse flow reactor is used, or within a separate combustion zone that can be separate and apart from the reaction or conversion zone when a fluidized bed reactor or other circulating or fluidized type reactor is used.

5 [0064] In some embodiments the process can optionally include contacting at least a portion of the regenerated catalyst composition with a reducing gas to produce a regenerated and reduced catalyst composition. An additional quantity of the hydrocarbon-containing feed can be contacted with at least a portion of the regenerated catalyst composition and/or at least a portion of any regenerated and reduced catalyst composition to produce a re-coked catalyst composition and additional effluent.

10 [0065] In some embodiments, a cycle time from contacting the hydrocarbon-containing feed with the catalyst composition to contacting the additional quantity of the hydrocarbon-containing feed with the regenerated catalyst composition can be ≤ 5 hours.

15 The first cycle begins upon contact of the catalyst composition with the first hydrocarbon-containing feed, followed by contact with at least the oxidative gas to produce the regenerated catalyst composition or at least the oxidative gas and the optional reducing gas to produce the regenerated catalyst composition, and the first cycle ends upon contact of the regenerated catalyst composition with the additional quantity of the first hydrocarbon-containing feed. If one or more additional feeds (described in more detail below) are utilized between flows of the first hydrocarbon-containing feed and the oxidative gas, between the oxidative gas and the reducing gas (if used), between the oxidative gas and the additional quantity of the first hydrocarbon-containing feed, and/or between the reducing gas (if used) and the additional quantity of the first hydrocarbon-containing feed, the period of time such stripping gas(es) is/are utilized would be included in the period included in the cycle time. As such, the cycle time from contacting the first hydrocarbon-containing feed with the catalyst composition in step to the contacting the additional quantity of the hydrocarbon-containing feed with the regenerated catalyst composition, in some embodiments, can be ≤ 5 hours.

25 [0066] The oxidant can be or can include, but is not limited to, O_2 , O_3 , CO_2 , H_2O , or a mixture thereof. In some embodiments, an amount of oxidant in excess of that needed to combust 100% of the coke on the catalyst composition can be used to increase the rate of coke removal from the catalyst composition, so that the time needed for coke removal can be reduced and lead to an increased yield in the upgraded product produced within a given

period of time. The use of pure O₂ as an oxidant can facilitate the capturing and sequestration of CO₂ made during combustion in one or more downstream CO₂ recovery systems.

[0067] The coked catalyst composition and oxidant can be contacted with one another at a temperature in a range from 500°C, 550°C, 600°C, 650°C, 700°C, 750°C, or 800°C to 900°C, 950°C, 1,000°C, 1,050°C, or 1,100°C to produce the regenerated catalyst composition. In some embodiments, the coked catalyst composition and oxidant can be contacted with one another at a temperature in a range from 500°C to 1,100°C, 600°C to 1,000°C, 650°C to 950°C, 700°C to 900°C, or 750°C to 850°C to produce the regenerated catalyst composition.

[0068] The coked catalyst composition and oxidant can be contacted with one another for a time period of ≤ 2 hours, ≤ 1 hour, ≤ 30 minutes, ≤ 10 minutes, ≤ 5 minutes, ≤ 1 min, ≤ 30 seconds, ≤ 10 seconds, ≤ 5 seconds, or ≤ 1 second. For example, the coked catalyst composition and oxidant can be contacted with one another for a time period in a range from 2 seconds to 2 hours. In some embodiments, the coked catalyst composition and oxidant can be contacted for a time period sufficient to remove ≥ 50 wt%, ≥ 75 wt%, or ≥ 90 wt% or > 99 % of any coke disposed on the catalyst composition.

[0069] In some embodiments, the time period the coked catalyst composition and oxidant contact one another can be less than the time period the catalyst composition contacts the hydrocarbon-containing feed to produce the effluent and the coked catalyst composition. For example, the time period the coked catalyst composition and oxidant contact one another can be at least 90%, at least 60%, at least 30%, or at least 10% less than the time period the catalyst composition contacts the hydrocarbon-containing feed to produce the effluent. In other embodiments, the time period the coked catalyst composition and oxidant contact one another can be greater than the time period the catalyst composition contacts the hydrocarbon-containing feed to produce the effluent and the coked catalyst composition. For example, in some embodiments, the coked catalyst composition and oxidant can contact one another for a time period that can be at least 50%, at least 100%, at least 300%, at least 500%, at least 1,000%, at least 10,000%, at least 30,000%, at least 50,000%, at least 75,000%, at least 100,000%, at least 250,000%, at least 500,000%, at least 750,000%, at least 1,000,000%, at least 1,250,000%, at least 1,500,000%, or at least 1,800,000% greater than the time period the catalyst composition contacts the hydrocarbon-containing feed to produce the effluent.

[0070] The coked catalyst composition and oxidant can be contacted with one another under an oxidant partial pressure in a range from 20 kPa-absolute, 50 kPa-absolute, 100 kPa-absolute, 300 kPa-absolute, 500 kPa-absolute, 750 kPa-absolute, or 1,000 kPa-absolute to 1,500 kPa-absolute, 2,500 kPa-absolute, 4,000 kPa-absolute, 5,000 kPa-absolute, 7,000 kPa-absolute, 8,500 kPa-absolute, or 10,000 kPa-absolute. In other
5 embodiments, the oxidant partial pressure during contact with the coked catalyst composition can be in a range from 20 kPa-absolute, 50 kPa-absolute, 100 kPa-absolute, 150 kPa-absolute, 200 kPa-absolute, 250 kPa-absolute, or 300 kPa-absolute to 500 kPa-absolute, 600 kPa-absolute, 700 kPa-absolute, 800 kPa-absolute, 900 kPa-absolute, or
10 1,000 kPa-absolute to produce the regenerated catalyst composition.

[0071] Without wishing to be bound by theory, it is believed that at least a portion of the Pt and, if present, and Ni and/or Pd, disposed on the coked catalyst composition can be agglomerated as compared to the catalyst composition prior to contact with the first hydrocarbon-containing feed. It is believed that during combustion of at least a portion
15 of the coke on the coked catalyst composition that at least a portion of the Pt and, if present, any Ni and/or Pd can be re-dispersed about the support. Re-dispersing at least a portion of any agglomerated Pt and, if present, Ni and/or Pd can improve the stability of the catalyst composition over many cycles.

[0072] In some embodiments, at least a portion of the Pt and, if present, Ni and/or Pd in
20 the regenerated catalyst composition can be at a higher oxidized state as compared to the Pt and, if present, Ni and/or Pd in the catalyst composition contacted with the first hydrocarbon-containing feed and as compared to the Pt and, if present, Ni and/or Pd in the coked catalyst composition. As such, as noted above, in some embodiments the process can optionally include contacting at least a portion of the regenerated catalyst
25 composition with a reducing gas to produce a regenerated and reduced catalyst composition. Suitable reducing gases (reducing agent) can be or can include, but are not limited to, H₂, CO, CH₄, C₂H₆, C₃H₈, C₂H₄, C₃H₆, steam, or a mixture thereof. In some embodiments, the reducing agent can be mixed with an inert gas such as Ar, Ne, He, N₂, CO₂, H₂O or a mixture thereof. In such embodiments, at least a portion of the Pt and, if
30 present Ni and/or Pd, in the regenerated and reduced catalyst composition can be reduced to a lower oxidation state, e.g., the elemental state, as compared to the Pt and, if present, Ni and/or Pd in the regenerated catalyst composition. In this embodiment, the additional quantity of the hydrocarbon-containing feed can be contacted with at least a portion of the

regenerated catalyst composition and/or at least a portion of the regenerated and reduced catalyst composition.

[0073] In some embodiments, the regenerated catalyst composition and the reducing gas can be contacted at a temperature in a range from 400°C, 450°C, 500°C, 550°C, 600°C, 620°C, 650°C, or 670°C to 720°C, 750°C, 800°C, or 900°C. The regenerated catalyst composition and the reducing gas can be contacted for a time period in a range from 1 second, 5 seconds, 10 seconds, 20 seconds, 30 seconds, or 1 minute to 10 minutes, 30 minutes, or 60 minutes. The regenerated catalyst composition and reducing gas can be contacted at a reducing agent partial pressure of 20 kPa-absolute, 50 kPa-absolute, or 100 kPa-absolute, 300 kPa-absolute, 500 kPa-absolute, 750 kPa-absolute, or 1,000 kPa-absolute to 1,500 kPa-absolute, 2,500 kPa-absolute, 4,000 kPa-absolute, 5,000 kPa-absolute, 7,000 kPa-absolute, 8,500 kPa-absolute, or 10,000 kPa-absolute. In other embodiments, the reducing agent partial pressure during contact with the regenerated catalyst composition can be in a range from 20 kPa-absolute, 50 kPa-absolute, 100 kPa-absolute, 150 kPa-absolute, 200 kPa-absolute, 250 kPa-absolute, or 300 kPa-absolute to 500 kPa-absolute, 600 kPa-absolute, 700 kPa-absolute, 800 kPa-absolute, 900 kPa-absolute, or 1,000 kPa-absolute to produce the regenerated catalyst composition.

[0074] At least a portion of the regenerated catalyst composition, the regenerated and reduced catalyst composition, new or fresh catalyst composition, or a mixture thereof can be contacted with an additional quantity of the first hydrocarbon-containing feed within the reaction or conversion zone to produce additional effluent and additional coked catalyst composition. As noted above, in some embodiments, the cycle time from the contacting the hydrocarbon-containing feed with the catalyst composition to the contacting the additional quantity of the hydrocarbon-containing feed with at least a portion of the regenerated catalyst composition, and/or the regenerated and reduced catalyst composition, and optionally with new or fresh catalyst composition can be ≤ 5 hours.

[0075] In some embodiments, as noted above, one or more additional feeds, e.g., one or more sweep fluids, can be utilized between flows of the first hydrocarbon-containing feed and the oxidant, between the oxidant and the optional reducing gas if used, between the oxidant and the additional first hydrocarbon-containing feed, and/or between the reducing gas and the additional first hydrocarbon-containing feed. The sweep fluid can, among other things, purge or otherwise urge undesired material from the reactors, such as non-combustible particulates including soot. In some embodiments, the additional feed(s) can

be inert under the dehydrogenation, dehydroaromatization, and dehydrocyclization, combustion, and/or reducing conditions. Suitable sweep fluids can be or can include, but are not limited to, N₂, He, Ar, CO₂, H₂O, CH₄, or a mixture thereof. In some embodiments, if the process utilizes a sweep fluid the duration or time period the sweep fluid is used can be in a range from 1 second, 5 seconds, 10 seconds, 20 seconds, 30 seconds, or 1 minute to 10 minutes, 30 minutes, or 60 minutes.

[0076] In some embodiments, the catalyst composition can remain sufficiently active and stable after many cycles, e.g., at least 15, at least 20, at least 30, at least 40, at least 50, at least 60, at least 70, at least 100 cycles, at least 125 cycles, at least 150 cycles, at least 175 cycles, or at least 200 cycles with each cycle time lasting for ≤ 5 hours, ≤ 4 hours, ≤ 3 hours, ≤ 2 hours, ≤ 1 hour, ≤ 50 minutes, ≤ 45 minutes, ≤ 30 minutes, ≤ 15 minutes, ≤ 10 minutes, ≤ 5 minutes, ≤ 1 minute, ≤ 30 seconds, or ≤ 10 seconds. In some embodiments, the cycle time can be from 5 seconds, 30 seconds, 1 minute or 5 minutes to 10 minutes, 20 minutes, 30 minutes, 45 minutes, 50 minutes, 70 minutes, 2 hours, 3 hours, 4 hours, or 5 hours. In some embodiments, after the catalyst performance stabilizes (sometimes the first few cycles can have a relatively poor or a relatively good performance, but the performance can eventually stabilize), the process can produce a first upgraded hydrocarbon product yield, e.g., propylene when the hydrocarbon-containing feed includes propane, at an upgraded hydrocarbon selectivity, e.g., propylene, of $\geq 75\%$, $\geq 80\%$, $\geq 85\%$, $\geq 90\%$, $\geq 93\%$, or $\geq 95\%$ when initially contacted with the first hydrocarbon-containing feed, and can have a second upgraded hydrocarbon product yield upon completion of the last cycle (at least 15 cycles total) that can be at least 90%, at least 93%, at least 95%, at least 97%, at least 98%, at least 99%, at least 99.5%, or at least 100% of the first upgraded hydrocarbon product yield at an upgraded hydrocarbon selectivity, e.g., propylene, of $\geq 75\%$, $\geq 80\%$, $\geq 85\%$, or $\geq 90\%$, $\geq 93\%$, or $\geq 95\%$.

[0077] In some embodiments, when the first hydrocarbon-containing feed includes propane and the upgraded hydrocarbon includes propylene, contacting the hydrocarbon-containing feed with the catalyst composition can produce a propylene yield of $\geq 52\%$, $\geq 53\%$, $\geq 55\%$, $\geq 57\%$, $\geq 60\%$, $\geq 62\%$, $\geq 63\%$, $\geq 64\%$, $\geq 65\%$, or $\geq 66\%$ at a propylene selectivity of $\geq 75\%$, $\geq 80\%$, $\geq 85\%$, $\geq 90\%$, $\geq 93\%$, or $\geq 95\%$ for at least 15, at least 20, at least 30, at least 40, at least 50, at least 60, at least 70, at least 100 cycles, at least 125 cycles, at least 150 cycles, at least 175 cycles, or at least 200 cycles. In other embodiments, when the hydrocarbon-containing feed includes at least 70 vol% of propane, based on a total volume of the first hydrocarbon-containing feed, is contacted under a propane partial

pressure of at least 20 kPa-absolute, a propylene yield of $\geq 52\%$, $\geq 53\%$, $\geq 55\%$, $\geq 57\%$, $\geq 60\%$, $\geq 62\%$, $\geq 63\%$, $\geq 64\%$, $\geq 65\%$, or $\geq 66\%$ at a propylene selectivity of $\geq 75\%$, $\geq 80\%$, $\geq 85\%$, $\geq 90\%$, $\geq 93\%$, or $\geq 95\%$ can be obtained for at least 15, at least 20, at least 30, at least 40, at least 50, at least 60, at least 70, at least 100 cycles, at least 125 cycles, at least 150 cycles, at least 175 cycles, or at least 200 cycles. It is believed that the propylene yield can be further increased to $\geq 67\%$, $\geq 68\%$, $\geq 70\%$, $\geq 72\%$, $\geq 75\%$, $\geq 77\%$, $\geq 80\%$, or $\geq 82\%$ at a propylene selectivity of $\geq 75\%$, $\geq 80\%$, $\geq 85\%$, $\geq 90\%$, $\geq 93\%$, or $\geq 95\%$ for ≥ 15 cycles, ≥ 20 cycles, ≥ 30 cycles, ≥ 40 cycles, ≥ 50 cycles, ≥ 60 cycles, ≥ 70 cycles, ≥ 100 cycles, ≥ 125 cycles, ≥ 150 cycles, ≥ 175 cycles, or ≥ 200 cycles by further optimizing the composition of the support and/or adjusting one or more process conditions. In some embodiments, the propylene yield can be obtained when the catalyst composition is contacted with the hydrocarbon-containing feed at a temperature of $\geq 620^\circ\text{C}$, $\geq 630^\circ\text{C}$, $\geq 640^\circ\text{C}$, $\geq 650^\circ\text{C}$, $\geq 655^\circ\text{C}$, $\geq 660^\circ\text{C}$, $\geq 670^\circ\text{C}$, $\geq 680^\circ\text{C}$, $\geq 690^\circ\text{C}$, $\geq 700^\circ\text{C}$, or $\geq 750^\circ\text{C}$ for ≥ 15 cycles, ≥ 20 cycles, ≥ 30 cycles, ≥ 40 cycles, ≥ 50 cycles, ≥ 60 cycles, ≥ 70 cycles, ≥ 100 cycles, ≥ 125 cycles, ≥ 150 cycles, ≥ 175 cycles, or ≥ 200 cycles.

[0078] Systems suitable for carrying out the processes disclosed herein can include systems that are well-known in the art such as the fixed bed reactors disclosed in WO Publication No. WO2017078894; the fluidized riser reactors and/or downer reactors disclosed in U.S. Patent Nos. 3,888,762; 7,102,050; 7,195,741; 7,122,160; and 8,653,317; and U.S. Patent Application Publication Nos. 2004/0082824; 2008/0194891; and the reverse flow reactors disclosed in U.S. Patent No. 8,754,276; U.S. Patent Application Publication No. 2015/0065767; and WO Publication No. WO2013169461.

[0079] The first hydrocarbon-containing feed can be or can include, but is not limited to, one or more alkane hydrocarbons, e.g., $\text{C}_2\text{-C}_{16}$ linear or branched alkanes and/or $\text{C}_4\text{-C}_{16}$ cyclic alkanes, and/or one or more alkyl aromatic hydrocarbons, e.g., $\text{C}_8\text{-C}_{16}$ alkyl aromatics. In some embodiments, the first hydrocarbon-containing feed can optionally include 0.1 vol% to 50 vol% of steam, based on a total volume of any $\text{C}_2\text{-C}_{16}$ alkanes and any $\text{C}_8\text{-C}_{16}$ alkyl aromatics in the hydrocarbon-containing feed. In other embodiments, the first hydrocarbon-containing feed can include < 0.1 vol% of steam or can be free of steam, based on the total volume of any $\text{C}_2\text{-C}_{16}$ alkanes and any $\text{C}_8\text{-C}_{16}$ alkyl aromatics in the hydrocarbon-containing feed.

[0080] The $\text{C}_2\text{-C}_{16}$ alkanes can be or can include, but are not limited to, ethane, propane, n-butane, isobutane, n-pentane, isopentane, n-hexane, 2-methylpentane, 3-methylpentane, 2,2-dimethylbutane, n-heptane, 2-methylhexane, 2,2,3-trimethylbutane, cyclopentane,

cyclohexane, methylcyclopentane, ethylcyclopentane, n-propylcyclopentane, 1,3-dimethylcyclohexane, or a mixture thereof. For example, the first hydrocarbon-containing feed can include propane, which can be dehydrogenated to produce propylene, and/or isobutane, which can be dehydrogenated to produce isobutylene. In another example, the first hydrocarbon-containing feed can include liquid petroleum gas (LP gas), which can be in the gaseous phase when contacted with the catalyst composition. In some embodiments, the first hydrocarbon in the hydrocarbon-containing feed can be composed of substantially a single alkane such as propane. In some embodiments, the hydrocarbon-containing feed can include ≥ 50 mol%, ≥ 75 mol%, ≥ 95 mol%, ≥ 98 mol%, or ≥ 99 mol% of a single C₂-C₁₆ alkane, e.g., propane, based on a total moles of all hydrocarbons in the first hydrocarbon-containing feed. In some embodiments, the first hydrocarbon-containing feed can include at least 50 vol%, at least 55 vol%, at least 60 vol%, at least 65 vol%, at least 70 vol%, at least 75 vol%, at least 80 vol%, at least 85 vol%, at least 90 vol%, at least 95 vol%, at least 97 vol%, or at least 99 vol% of a single C₂-C₁₆ alkane, e.g., propane, based on a total volume of the first hydrocarbon-containing feed.

[0081] The C₈-C₁₆ alkyl aromatics can be or can include, but are not limited to, ethylbenzene, propylbenzene, butylbenzene, one or more ethyl toluenes, or a mixture thereof. In some embodiments, the hydrocarbon-containing feed can include ≥ 50 mol%, ≥ 75 mol%, ≥ 95 mol%, ≥ 98 mol%, or ≥ 99 mol% of a single C₈-C₁₆ alkyl aromatic, e.g., ethylbenzene, based on a total weight of all hydrocarbons in the first hydrocarbon-containing feed. In some embodiments, the ethylbenzene can be dehydrogenated to produce styrene. As such, in some embodiments, the first process for upgrading a hydrocarbon disclosed herein can include propane dehydrogenation, butane dehydrogenation, isobutane dehydrogenation, pentane dehydrogenation, pentane dehydrocyclization to cyclopentadiene, naphtha reforming, ethylbenzene dehydrogenation, ethyltoluene dehydrogenation, and the like.

[0082] In some embodiments, the first hydrocarbon-containing feed can be diluted, e.g., with one or more diluents such as one or more inert gases. Suitable inert gases can be or can include, but are not limited to, Ar, Ne, He, N₂, CO₂, CH₄, or a mixture thereof. If the hydrocarbon containing-feed includes a diluent, the hydrocarbon-containing feed can include 0.1 vol%, 0.5 vol%, 1 vol%, or 2 vol% to 3 vol%, 8 vol%, 16 vol%, or 32 vol% of the diluent, based on a total volume of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the hydrocarbon-containing feed.

[0083] In some embodiments, the first hydrocarbon-containing feed can also include H₂. In some embodiments, when the first hydrocarbon-containing feed includes H₂, a molar ratio of the H₂ to a combined amount of any C₂-C₁₆ alkane and any C₈-C₁₆ alkyl aromatic can be in a range from 0.1, 0.3, 0.5, 0.7, or 1 to 2, 3, 4, 5, 6, 7, 8, 9, or 10.

5 [0084] In some embodiments, the first hydrocarbon-containing feed can be substantially free of any steam, e.g., < 0.1 vol% of steam, based on a total volume of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the hydrocarbon-containing feed. In other embodiments, the first hydrocarbon-containing feed can include steam. For example, the first hydrocarbon-containing feed can include 0.1 vol%, 0.3 vol%, 0.5 vol%, 0.7 vol%, 1 vol%,
10 3 vol%, or 5 vol% to 10 vol%, 15 vol%, 20 vol%, 25 vol%, 30 vol%, 35 vol%, 40 vol%, 45 vol%, or 50 vol% of steam, based on a total volume of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed. In other embodiments, the first hydrocarbon-containing feed can include ≤ 50 vol%, ≤ 45 vol%, ≤ 40 vol%, ≤ 35 vol%, ≤ 30 vol%, ≤ 25 vol%, ≤ 20 vol%, or ≤ 15 vol% of steam, based on a total volume
15 of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed. In other embodiments, the first hydrocarbon-containing feed can include at least 1 vol%, at least 3 vol%, at least 5 vol%, at least 10 vol%, at least 15 vol%, at least 20 vol%, at least 25 vol%, or at least 30 vol% of steam, based on a total volume of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed.

20 [0085] In some embodiments, the first hydrocarbon-containing feed can include sulfur. For example, the first hydrocarbon-containing feed can include sulfur in a range from 0.5 ppm, 1 ppm, 5 ppm, 10 ppm, 20 ppm, 30 ppm, 40 ppm, 50 ppm, 60 ppm, 70 ppm, or 80 ppm to 100 ppm, 150 ppm, 200 ppm, 300 ppm, 400 ppm, or 500 ppm. In other embodiments, the first hydrocarbon-containing feed can include sulfur in a range from 1
25 ppm to 10 ppm, 10 ppm to 20 ppm, 20 ppm to 50 ppm, 50 ppm to 100 ppm, or 100 ppm to 500 ppm. The sulfur, if present in the first hydrocarbon-containing feed, can be or can include, but is not limited to, H₂S, dimethyl disulfide, as one or more mercaptans, or any mixture thereof.

[0086] In some embodiments, the first hydrocarbon-containing feed can be substantially
30 free or free of molecular oxygen. In some embodiments, the first hydrocarbon-containing feed can include ≤ 5 mol%, ≤ 3 mol%, or ≤ 1 mol% of molecular oxygen (O₂). It is believed that providing a first hydrocarbon-containing feed substantially-free of molecular oxygen substantially prevents oxidative reactions that would otherwise consume at least a portion of the alkane and/or the alkyl aromatic in the first hydrocarbon-containing feed.

A Second Process for Upgrading a Hydrocarbon

[0087] In some embodiments, the process for upgrading a hydrocarbon can include the upgrading processes disclosed in U.S. Patent Application Publication No. 2021/0276932. For example, the process for upgrading a hydrocarbon can include (I) contacting the first hydrocarbon-containing feed with the catalyst composition that includes Pt and the promoter disposed on the support to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a portion of the first hydrocarbon-containing feed to produce a coked catalyst composition and an effluent that can include one or more upgraded hydrocarbons and molecular hydrogen. The first hydrocarbon-containing feed can include one or more of C₂-C₁₆ linear or branched alkanes, or one or more of C₄-C₁₆ cyclic alkanes, or one or more C₈-C₁₆ alkyl aromatics, or a mixture thereof. The first hydrocarbon-containing feed and catalyst composition can be contacted at a temperature in a range from 300°C to 900°C, for a time period of ≤ 3 hours, under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed. The catalyst composition can include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on the support, the support including at least 0.5 wt% of the Group 2 element, where all weight percent values are based on the weight of the support. The one or more upgraded hydrocarbons can include at least one of a dehydrogenated hydrocarbon, a dehydroaromatized hydrocarbon, and a dehydrocyclized hydrocarbon. The process can also include (II) contacting at least a portion of the coked catalyst composition with an oxidant to effect combustion of at least a portion of the coke to produce a regenerated catalyst composition lean in coke and a combustion gas. The process can also include (III) contacting an additional quantity of the first hydrocarbon-containing feed with at least a portion of the regenerated catalyst composition to produce a re-coked catalyst composition and additional effluent. A cycle time from the contacting the first hydrocarbon-containing feed with the catalyst composition in step (I) to the contacting the additional quantity of the first hydrocarbon-containing feed with the regenerated catalyst composition in step (III) can be ≤ 5 hours.

[0088] In some embodiments, at least a portion of the Pt in the regenerated catalyst can be at a higher oxidized state as compared to the Pt in the catalyst contacted with the first hydrocarbon-containing feed and the process can further include, after step (II) and before step (III), the following step (IIa) contacting at least a portion of the regenerated catalyst

with a reducing gas to produce a regenerated and reduced catalyst, where at least a portion of the Pt in the regenerated and reduced catalyst is reduced to a lower oxidation state as compared to the Pt in the regenerated catalyst, and where the additional quantity of the hydrocarbon-containing feed can be contacted with at least a portion of the regenerated and reduced catalyst.

A Third Process for Upgrading a Hydrocarbon

[0089] In some embodiments, the process for upgrading a hydrocarbon can include the upgrading processes disclosed in U.S. Patent Application Publication No. 2021/0276002. For example, the process for upgrading a hydrocarbon can include (I) contacting the first hydrocarbon-containing feed with fluidized catalyst particles that can include the Pt and the promoter disposed on the support within a conversion zone to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a portion of the first hydrocarbon-containing feed to produce a conversion effluent that can include coked catalyst particles, one or more upgraded hydrocarbons, and molecular hydrogen. The first hydrocarbon-containing feed can include one or more of C₂-C₁₆ linear or branched alkanes, one or more of C₄-C₁₆ cyclic alkanes, one or more of C₈-C₁₆ alkyl aromatic hydrocarbons, or a mixture thereof. The first hydrocarbon-containing feed and the fluidized catalyst particles can be contacted at a temperature in a range from 300°C to 900°C, for a time period in a range from 0.1 seconds to 2 minutes, and under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatic hydrocarbons in the first hydrocarbon-containing feed. The catalyst particles can include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The one or more upgraded hydrocarbons can include a dehydrogenated hydrocarbon, a dehydroaromatized hydrocarbon, a dehydrocyclized hydrocarbon, or a mixture thereof. The process can also include (II) obtaining from the conversion effluent a first gaseous stream rich in the one or more upgraded hydrocarbons and the molecular hydrogen and a first particle stream rich in the coked catalyst particles. The process can also include (III) contacting at least a portion of the coked catalyst particles in the first particle stream with an oxidant in a combustion zone to effect combustion of at least a portion of the coke to produce a combustion effluent that can include regenerated catalyst particles lean in coke and a combustion gas. The process can

also include (IV) obtaining from the combustion effluent a second gaseous stream rich in the combustion gas and a second particle stream rich in the regenerated catalyst particles. The process can also include (V) contacting an additional quantity of the first hydrocarbon-containing feed with fluidized regenerated catalyst particles to produce
5 additional conversion effluent comprising re-coked catalyst particles, additional one or more upgraded hydrocarbons, and additional molecular hydrogen.

[0090] In some embodiments, the process can further include, after step (IV) and before step (V), the following step (IVa) contacting at least a portion of the regenerated catalyst particles with a reducing gas to produce regenerated and reduced catalyst particles, where
10 the additional quantity of the hydrocarbon-containing feed can be contacted with fluidized regenerated and reduced catalyst particles in step (V).

A Fourth Process for Upgrading a Hydrocarbon

[0091] In some embodiments, the process for upgrading a hydrocarbon can include a first multi-stage upgrading processes disclosed in WO Publication No. 2021/225747. For
15 example, the upgrading process can be a multi-stage hydrocarbon upgrading process that can include (I) contacting the first hydrocarbon-containing feed with a first catalyst composition that can include the Pt and the promoter disposed on the support within a first conversion zone to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of a portion of the first hydrocarbon-containing feed to produce a first
20 conversion zone effluent that can include one or more upgraded hydrocarbons, molecular hydrogen, and unconverted first hydrocarbon-containing feed. The process can also include (II) contacting the first conversion zone effluent with a second catalyst composition that can include the Pt and the promoter disposed on the support within a second conversion zone to effect one or more of dehydrogenation, dehydroaromatization,
25 and dehydrocyclization of at least a portion of the unconverted first hydrocarbon-containing feed to produce a second conversion zone effluent that can include an additional quantity of one or more upgraded hydrocarbons and molecular hydrogen. The first hydrocarbon-containing feed can include one or more of C₂-C₁₆ linear or branched alkanes, one or more of C₄-C₁₆ cyclic alkanes, one or more of C₈-C₁₆ alkyl aromatic
30 hydrocarbons, or a mixture thereof. The first hydrocarbon-containing feed and the first catalyst composition can be contacted for a time period in a range from 0.1 seconds to 3 hours, under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatic hydrocarbons in the first hydrocarbon-containing feed. The first

conversion zone effluent and the second catalyst composition can be contacted for a time period in a range from 0.1 seconds to 3 hours, under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatic hydrocarbons in the first conversion zone effluent. The first conversion zone effluent can have a temperature in a range from 300°C to 850°C. The second conversion zone effluent can have a temperature in a range from 350°C to 900°C. A temperature of the second conversion zone effluent can be greater than a temperature of the first conversion zone effluent. The first catalyst composition and the second catalyst composition can have the same composition or a different composition. The first catalyst composition and the second catalyst composition each include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The one or more upgraded hydrocarbons can include a dehydrogenated hydrocarbon, a dehydroaromatized hydrocarbon, a dehydrocyclized hydrocarbon, or a mixture thereof.

[0092] In some embodiments, at least one of the first catalyst composition and the second catalyst composition can be disposed within a fixed bed. In some embodiments, the first conversion zone and the second conversion zone can be disposed within a fixed-bed reactor. In some embodiments, the first conversion zone and the second conversion zone can be disposed within a reverse-flow reactor. In some embodiments, at least one of the first catalyst and the second catalyst can be in the form of fluidized catalyst particles. In some embodiments, the first catalyst and the second catalyst can be in the form of fluidized catalyst particles. In some embodiments, the first and second conversion zones can be substantially adiabatic.

[0093] In some embodiments, the process can further include, after step (I) and before step (II), the following step: (Ia) contacting the first conversion zone effluent with one or more intermediate catalyst compositions that can include the Pt and the promoter disposed on the support within one or more intermediate conversion zones to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of a portion of the unconverted hydrocarbon-containing feed in the first conversion zone effluent to produce one or more coked intermediate catalysts and one or more intermediate conversion zone effluents having one or more intermediate temperatures that can include unconverted hydrocarbon-containing feed and an additional quantity of one or more upgraded

hydrocarbons and molecular hydrogen, where a last intermediate conversion zone effluent is contacted with the second catalyst in the second conversion zone in step (II). In some embodiments, if the process includes the optional step (Ia), the one or more intermediate temperatures of the one or more intermediate conversion zone effluents can be greater than the temperature of the first conversion zone effluent, and the temperature of the second conversion zone effluent can be greater than the one or more intermediate temperatures of the one or more intermediate conversion zone effluents.

[0094] In some embodiments, contacting the hydrocarbon-containing feed with the first catalyst can produce a coked first catalyst and contacting the first conversion zone effluent with the second catalyst can produce a coked second catalyst, and the process can further include step (III) that can include contacting the coked first catalyst, the coked second catalyst, or the coked first catalyst and the coked second catalyst with an oxidant to effect combustion of at least a portion of the coke to produce a combustion gas and a regenerated first catalyst, a regenerated second catalyst, or a regenerated first catalyst and a regenerated second catalyst. In some embodiments, in step (III) the coked first catalyst particles, the coked second catalyst particles, or the coked first catalyst particles and the coked second catalyst particles and oxidant can be contacted at a temperature in a range from 580°C to 1,100°C, preferably from 650°C to 1,000°C, more preferably from 700°C to 900°C, or more preferably from 750°C to 850°C. In some embodiments, the process can also include (IV) contacting at least a portion of any regenerated first catalyst, at least a portion of any regenerated second catalyst, or at least a portion of any regenerated first catalyst and at least a portion of any regenerated second catalyst with a reducing gas to produce a regenerated and reduced first catalyst, a regenerated and reduced second catalyst, or a regenerated and reduced first catalyst and a regenerated and reduced second catalyst.

A Fifth Process for Upgrading a Hydrocarbon

[0095] In other embodiments, the process for upgrading a hydrocarbon can include a second multi-stage upgrading processes disclosed in WO Publication No. 2021/225747. For example, the multi-stage hydrocarbon upgrading process can include (I) contacting the first hydrocarbon-containing feed with a first plurality of fluidized catalyst particles that can include the Pt and the promoter disposed on the support within a first conversion zone to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of a first portion of the first hydrocarbon-containing feed to produce a first conversion zone effluent that can include coked first catalyst particles, one or more

upgraded hydrocarbons, molecular hydrogen, and unconverted first hydrocarbon-containing feed. The process can also include (II) contacting the first conversion zone effluent with a second plurality of fluidized catalyst particles that can include the Pt and the promoter disposed on the support within a second conversion zone to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a portion of the unconverted first hydrocarbon-containing feed to produce a second conversion zone effluent that can include coked second catalyst particles, an additional quantity of upgraded hydrocarbons, and an additional quantity of molecular hydrogen. The first hydrocarbon-containing feed can include one or more of C₂-C₁₆ linear or branched alkanes, one or more of C₄-C₁₆ cyclic alkanes, one or more of C₈-C₁₆ alkyl aromatic hydrocarbons, or a mixture thereof. The first hydrocarbon-containing feed and the first plurality of fluidized catalyst particles can be contacted for a time period in a range from 0.1 seconds to 2 minutes, under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatic hydrocarbons in the first hydrocarbon-containing feed. The first conversion zone effluent and the second plurality of fluidized catalyst particles can be contacted for a time period in a range from 0.1 seconds to 2 minutes, under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatic hydrocarbons in the first conversion zone effluent. The first conversion zone effluent can have a temperature in a range from 300°C to 850°C. The second conversion zone effluent can have a temperature in a range from 350°C to 900°C. A temperature of the second conversion zone effluent can be greater than a temperature of the first conversion zone effluent. The first plurality of fluidized catalyst particles and the second plurality of fluidized catalyst particles can each include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The one or more upgraded hydrocarbons can include a dehydrogenated hydrocarbon, a dehydroaromatized hydrocarbon, a dehydrocyclized hydrocarbon, or a mixture thereof. The process can also include (III) obtaining from the second conversion zone effluent a first gaseous stream rich in the upgraded hydrocarbons and molecular hydrogen and a first particle stream rich in the coked first catalyst particles and the coked second catalyst particles. The process can also include (IV) splitting the first particle

stream into a second particle stream and a third particle stream. The process can also include (V) recycling the second particle stream to the first conversion zone as the first plurality of fluidized particles. The process can also include (VI) contacting the third particle stream with an oxidant in a combustion zone to effect combustion of at least a portion of the coke to produce a combustion effluent that can include regenerated catalyst particles lean in coke and a combustion gas. The process can also include (VII) obtaining from the combustion effluent a second gaseous stream rich in the combustion gas and a fourth particle stream rich in the regenerated catalyst particles. The process can also include (VIII) recycling the fourth particle stream to the second conversion zone as the second plurality of fluidized catalyst particles.

[0096] In some embodiments, the process can also include, after step (VII) and before step (VIII), the following step (VIIa) contacting at least a portion of the fourth particle stream with a reducing gas to produce regenerated and reduced catalyst particles, where the regenerated and reduced catalyst particles can be recycled to the second conversion zone as the second plurality of fluidized catalyst particles in step (VIII). In some embodiments, step (IV) can optionally include separating a fifth particle stream from the first particle stream and the process can optionally include contacting the fourth particle stream with the fifth particle stream to produce a combined particle stream.

[0097] In some embodiments, the process can optionally include, after step (I) and before step (II), the following step (Ia) contacting the first conversion zone effluent with one or more intermediate pluralities of fluidized catalyst particles that include the Pt and the promoter disposed on the support within one or more intermediate conversion zones to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of a portion of the unconverted hydrocarbon-containing feed in the first conversion zone effluent to produce one or more coked intermediate pluralities of fluidized catalyst particles and one or more intermediate conversion zone effluents that can have one or more intermediate temperatures that can include unconverted hydrocarbon-containing feed and an additional quantity of one or more upgraded hydrocarbons and molecular hydrogen, where a last intermediate conversion zone effluent can be contacted with the second catalyst in the second conversion zone in step (II).

A Sixth Process for Upgrading a Hydrocarbon

[0098] In some embodiments, the process for upgrading a hydrocarbon can include the upgrading processes disclosed in U.S. Patent Application No. 63/062,084. For example, the upgrading process can include (I) introducing the first hydrocarbon-containing feed

that can include one or more of C₂-C₁₆ linear or branched alkanes, one or more of C₄-C₁₆ cyclic alkanes, one or more of C₈-C₁₆ alkyl aromatics, or a mixture thereof into a reaction zone. The process can also include (II) contacting the first hydrocarbon-containing feed with a catalyst composition disposed within the reaction zone to effect at least one of

5 dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a portion of the first hydrocarbon-containing feed to produce a coked catalyst composition and a first effluent that can include one or more upgraded hydrocarbons and molecular hydrogen. The first hydrocarbon-containing feed and the catalyst composition can be contacted at a temperature in a range from 300°C to 900°C, for a time period of 1 minute to 90 minutes,

10 under a hydrocarbon partial pressure of at least 20 kPa-absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the hydrocarbon-containing feed. The catalyst composition can include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The process can also include (III) halting introduction of the first hydrocarbon-containing feed into the reaction zone; (IV) introducing an oxidant into the reaction zone; (V) contacting the oxidant with the coked catalyst composition to effect combustion of at least a portion of the coke to produce a regenerated catalyst composition

20 lean in coke and a second effluent comprising a combustion gas, wherein the oxidant and the coked catalyst composition are contacted for a time period of 1 minute to 90 minutes; and (VI) halting introduction of the oxidant into the reaction zone. The process can also include (VII) introducing a reducing gas into the reaction zone; (VIII) contacting the reducing gas with the regenerated catalyst composition to produce a regenerated and reduced catalyst composition and a third effluent, wherein the reducing gas and the regenerated catalyst composition are contacted for a time period of 0.1 seconds to 90 minutes; and (IX) halting introduction of the reducing gas into the reaction zone. The process can also include (X) introducing an additional quantity of the first hydrocarbon-containing feed into the reaction zone and (XI) contacting the additional quantity of the

30 first hydrocarbon-containing feed with the regenerated and reduced catalyst composition to produce a re-coked catalyst composition and additional first effluent. The additional quantity of the first hydrocarbon-containing feed and the regenerated and reduced catalyst composition can be contacted at a temperature in a range from 300°C to 900°C, for a time period of 1 minute to 90 minutes, under a hydrocarbon partial pressure of at least 20 kPa-

absolute, where the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the first hydrocarbon-containing feed.

[0099] In some embodiments, the process can optionally include, after step (III) and before step (IV), the following step (III_{a1}) introducing a stripping gas into the reaction zone to remove at least a portion of any residual hydrocarbon-containing feed, first effluent, or both from the reaction zone; (III_{a2}) removing at least a portion of any residual hydrocarbon containing feed, effluent, or both from the reaction zone by subjecting the reaction zone to a pressure of less than atmospheric pressure; or a combination of steps (III_{a1}) and (III_{a2}). In some embodiments, the process can optionally include, after step (VI) and before step (VII), the following step: (VI_{a1}) introducing a stripping gas into the reaction zone to remove at least a portion of any residual oxidant, second effluent, or both from the reaction zone; (VI_{a2}) removing at least a portion of any residual oxidant, second effluent, or both from the reaction zone by subjecting the reaction zone to a pressure of less than atmospheric pressure; or a combination of steps (VI_{a1}) and (VI_{a2})

[0100] In some embodiments, the process can optionally include, after step (IX) and before step (X), the following step (IX_{a1}) introducing a stripping gas into the reaction zone to remove at least a portion of any residual reducing gas, third effluent, or both from the reaction zone; (IX_{a2}) removing at least a portion of any residual reducing gas, third effluent, or both from the reaction zone by subjecting the reaction zone to a pressure of less than atmospheric pressure; or a combination of steps (IX_{a1}) and (IX_{a2}). In some embodiments, step (IV) of the process can optionally include introducing a fuel with the oxidant into the reaction zone; and combusting at least a portion of the fuel within the reaction zone to produce heat that heats the reaction zone to a temperature of $\geq 580^{\circ}\text{C}$, $\geq 620^{\circ}\text{C}$, $\geq 650^{\circ}\text{C}$, $\geq 680^{\circ}\text{C}$, $\geq 710^{\circ}\text{C}$, $\geq 740^{\circ}\text{C}$, $\geq 770^{\circ}\text{C}$, $\geq 800^{\circ}\text{C}$, $\geq 850^{\circ}\text{C}$, $\geq 900^{\circ}\text{C}$, or $\geq 1,000^{\circ}\text{C}$.

25 A Seventh Process for Upgrading a Hydrocarbon

[0101] In some embodiments, the process for upgrading a hydrocarbon can include the upgrading processes disclosed in U.S. Patent Application No. 63/195,966. For example, the process can include (I) contacting the first hydrocarbon-containing feed with the catalyst composition that can include the Pt and the promoter disposed on the support to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a portion of the hydrocarbon-containing feed to produce an at least partially deactivated catalyst composition that can include the Pt, the promoter, the support, and a contaminant and an effluent that can include one or more upgraded hydrocarbons and molecular hydrogen. The first hydrocarbon-containing feed can include one or more of

C₂-C₁₆ linear or branched alkanes, or one or more of C₄-C₁₆ cyclic alkanes, one or more C₈-C₁₆ alkyl aromatics, or a mixture thereof. The catalyst composition can include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The first hydrocarbon-containing feed and the catalyst composition can be contacted at a temperature in a range from 300°C to 900°C. The one or more upgraded hydrocarbons can include at least one of a dehydrogenated hydrocarbon, a dehydroaromatized hydrocarbon, and a dehydrocyclized hydrocarbon. The process can also include (II) heating the at least partially deactivated catalyst composition using a heating gas mixture that can include H₂O at a concentration of greater than 5 mol%, based on the total moles in the heating gas mixture to produce a precursor catalyst composition. The process can also include (III) providing an oxidative gas that can include no greater than 5 mol% of H₂O, based on the total moles in the oxidative gas. The process can also include (IV) contacting the precursor catalyst composition at an oxidizing temperature in a range of from 620°C to 1,000°C with the oxidative gas for a duration of at least 30 seconds to produce an oxidized precursor catalyst composition. The process can also include (V) obtaining a regenerated catalyst composition from the oxidized precursor catalyst composition. The process can also include (VI) contacting an additional quantity of the first hydrocarbon-containing feed with at least a portion of the regenerated catalyst composition to produce additional at least partially deactivated catalyst composition and additional effluent. In some embodiments, the heating gas mixture can be produced by combusting a fuel with an oxidizing gas. In some embodiments, the fuel can include at least one of H₂, CO, and a hydrocarbon and the oxidizing gas can include O₂. In some embodiments, the oxidative gas can be or can include, but is not limited to, O₂, O₃, CO₂, or a mixture thereof and can include no greater than 5 mol% of H₂O.

An Eighth Process for Upgrading a Hydrocarbon

[0102] In some embodiments, the process for upgrading a hydrocarbon can include the upgrading processes disclosed in U.S. Patent Application No. 63/232,959. For example, the process for upgrading a hydrocarbon can include (I) contacting the first hydrocarbon-containing feed with fluidized dehydrogenation catalyst particles in a conversion zone to effect dehydrogenation of at least a portion of the hydrocarbon-containing feed to produce a conversion effluent that can include coked catalyst particles and one or more dehydrogenated hydrocarbons. The fluidized dehydrogenation catalyst particles can

include up to 0.025 wt% of the Pt and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof, disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The first hydrocarbon-containing feed can include

5 one or more of C₂-C₁₆ linear or branched alkanes, one or more of C₄-C₁₆ cyclic alkanes, one or more of C₈-C₁₆ alkyl aromatic hydrocarbons, or a mixture thereof. The first hydrocarbon-containing feed can contact the catalyst particles at a weight hourly space velocity in a range from 0.1 hr⁻¹ to 1,000 hr⁻¹, based on the weight of any C₂-C₁₆ alkanes and any C₈-C₁₆ aromatic hydrocarbons in the first hydrocarbon-containing feed. A weight

10 ratio of the fluidized dehydrogenation catalyst particles to a combined amount of any C₂-C₁₆ alkanes and any C₈-C₁₆ aromatic hydrocarbons can be in a range from 3 to 100. The first hydrocarbon-containing feed and the catalyst particles can be contacted at a temperature in a range from 600°C to 750°C. The process can also include (II) separating from the conversion effluent a first particle stream rich in the coked catalyst particles and

15 a first gaseous stream rich in the one or more dehydrogenated hydrocarbons. The process can also include (III) contacting at least a portion of the coked catalyst particles in the first particle stream with an oxidant and a fuel in a combustion zone to effect combustion of at least a portion of the coke to produce a combustion effluent that can include catalyst particles lean in coke and a combustion gas. A dehydrogenation activity of the catalyst

20 particles lean in coke can be less than a dehydrogenation activity of the coked catalyst particles. The process can also include (IV) separating a second particle stream rich in the catalyst particles lean in coke and a second gaseous stream rich in the combustion gas from the combustion effluent. The process can also include (V) contacting at least a portion of the catalyst particles lean in coke in the second particle stream with an oxidative

25 gas in an oxygen soak zone at an oxidizing temperature in a range from 620°C to 1,000°C for a duration of at least 30 seconds to produce conditioned catalyst particles having an activity that can be less than the coked catalyst particles. The process can also include (VI) contacting at least a portion of the conditioned catalyst particles with a reducing gas in a reduction zone to produce regenerated catalyst particles having a dehydrogenation

30 activity that can be greater than the coked catalyst particles. The process can also include (VII) contacting an additional quantity of the hydrocarbon-containing feed with at least a portion of the regenerated catalyst particles in the conversion zone to produce an additional quantity of the conversion effluent that can include re-coked catalyst particles and an additional quantity of the one or more dehydrogenated hydrocarbons. The process

can also include (VIII) cooling the first gaseous stream to produce a cooled gaseous stream. The process can also include (IX) compressing at least a portion of the cooled gaseous stream to produce a compressed gaseous stream. The process can also include (X) separating a plurality of products from the compressed gaseous stream.

- 5 [0103] In some embodiments, the first gaseous stream rich in the one or more dehydrogenated hydrocarbons can further include entrained coked catalyst particles. In such embodiment, step (VIII) can include: (VIIIa) contacting the first gaseous stream with a first quench medium, indirectly transferring heat from the first gaseous stream to a first heat transfer medium, or a combination thereof, to produce the cooled gaseous stream,
- 10 and (VIIIb) contacting the cooled gaseous stream with a second quench medium within a quench tower, (VIIIc) recovering a third gaseous stream that can include the one or more dehydrogenated hydrocarbons and a slurry stream that can include at least a portion of the second quench medium in a liquid phase and the entrained coked catalyst particles from the quench tower, and step (IX) can include compressing at least a portion of the third
- 15 gaseous stream to produce the compressed gaseous stream. In some embodiments, the conversion effluent can further include benzene, and the process can further include (XI) withdrawing a benzene product stream from the quench tower.

A Ninth Process for Upgrading a Hydrocarbon

- [0104] In some embodiments, the process for upgrading alkanes and/or alkyl aromatic
- 20 hydrocarbons can include the processes disclosed in U.S. Patent Application No. 63/231,939. For example, the process for upgrading a hydrocarbon can include (I) contacting the first hydrocarbon-containing feed with fluidized dehydrogenation catalyst particles in a conversion zone to effect dehydrogenation of at least a portion of the first hydrocarbon-containing feed to produce a conversion effluent that can include coked
- 25 catalyst particles and one or more dehydrogenated hydrocarbons. The fluidized dehydrogenation catalyst particles can include a contaminant, up to 0.025 wt% of the Pt, and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof, disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the
- 30 support. The process can also include (II) separating from the conversion effluent a first stream rich in the coked catalyst particles and lean in the one or more dehydrogenated hydrocarbons and a second stream rich in the one or more dehydrogenated hydrocarbons and containing entrained coked catalyst particles. The process can also include (III) contacting the second stream with a first quench medium to produce a cooled second

stream. The process can also include (IV) contacting the cooled second stream with a second quench medium within a quench tower. The process can also include (V) recovering a gaseous stream that can include the one or more dehydrogenated hydrocarbons, a condensed first quench medium stream, and a slurry stream that can include at least a portion of the second quench medium in a liquid phase and the entrained coked catalyst particles from the quench tower. The process can also include (VI) recycling at least a portion of the condensed first quench medium to step (III). The process can also include (VII) separating at least a portion of the entrained coked catalyst particles from the slurry stream to provide a recovered second quench medium stream and a recovered entrained coked catalyst particles stream. The process can also include (VIII) recycling at least a portion of the recovered second quench medium stream to step (IV).

[0105] In some embodiments, the process can also include (IX) contacting at least a portion of the coked catalyst particles in the first stream and at least a portion of the coked catalyst particles in the recovered entrained catalyst particles stream with an oxidant and optionally a fuel in a combustion zone to effect combustion of at least a portion of the coke and, if present, the fuel to produce a combustion effluent that can include regenerated catalyst particles lean in coke and a combustion gas; (X) separating a combustion gas stream and a regenerated catalyst particles stream; and (XI) contacting an additional quantity of the first hydrocarbon-containing feed with fluidized regenerated catalyst particles from the regenerated catalyst particles stream to produce additional conversion effluent comprising re-coked catalyst particles and additional one or more dehydrogenated hydrocarbons.

[0106] In some embodiments, the process can optionally further include (XII) conveying at least a portion of the recovered entrained catalyst particles stream to a metal reclamation facility; and (XIII) recovering at least a portion of the Pt and, if present, Ni and/or Pd, from the coked catalyst particles in the recovered entrained coked catalyst particles stream. In some embodiments, the process can further include (XIV) cooling the slurry stream prior to step (VII) to produce a cooled slurry stream. In some embodiments, the conversion effluent can also include benzene and the process can further include (XV) withdrawing a benzene product stream from the quench tower.

A Tenth Process for Upgrading a Hydrocarbon

[0107] In some embodiments, the process for upgrading alkanes can include the processes disclosed in U.S. Patent Application No. 63/222,733. For example, a process for dehydrogenating an alkane can include introducing the first hydrocarbon-containing

feed that includes one or more alkanes, e.g., propane, into a reactor that can include a catalyst composition disposed therein. The catalyst composition can include a contaminant, up to 0.025 wt% of the Pt, and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof, disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. The process can also include contacting the first hydrocarbon-containing feed with the catalyst composition in the reactor to form a high temperature dehydrogenated product, the high temperature dehydrogenated product including at least a portion of the catalyst composition. The process can also include separating at least a portion of the catalyst composition from the high temperature dehydrogenated product in a primary separation device and a secondary separation device downstream of and in fluid communication with the primary separation device. The process can also include following the exit of high temperature dehydrogenation product from the secondary separation device, combining the high temperature dehydrogenation product with a quench stream, to cool the high temperature dehydrogenation product and form an intermediate temperature dehydrogenation product, where the quench stream includes a hydrocarbon. The process can also include cooling the intermediate temperature dehydrogenation product to form a cooled dehydrogenation product.

[0108] In some embodiments, the quench stream can include a liquid hydrocarbon and the intermediate temperature product can be completely in a vapor phase. In some embodiments, the combining of the high temperature dehydrogenation product with the quench stream can occur within a plenum section of the reactor. In some embodiments, the process can further include further cooling, downstream of the reactor, the cooled dehydrogenation product with a heat exchanger or a secondary quench stream, where the quench stream can include at least a portion of the cooled dehydrogenation product after having been further cooled by the heat exchanger or the secondary quench stream.

[0109] It should be understood that the second through the tenth processes for upgrading a hydrocarbon can include the same or similar process conditions such as operating temperatures, pressures, time intervals for certain steps, WHSV, etc. as described with regard to the first process for upgrading a hydrocarbon, as will be apparent to those skilled in the art.

Recovery and Use of the First Upgraded Hydrocarbon

[0110] In some embodiments, the first upgraded hydrocarbon produced via any one of the first through the tenth hydrocarbon upgrading processes can include at least one

upgraded hydrocarbon, e.g., an olefin, water, unreacted hydrocarbons, molecular hydrogen, etc. The first upgraded hydrocarbon can be recovered or otherwise obtained via any convenient process, e.g., by one or more conventional processes. One such process can include cooling and/or compressing the effluent to condense at least a portion of any water and any heavy hydrocarbon that may be present, leaving the olefin and any unreacted alkane or alkyl aromatic primarily in the vapor phase. Olefin and unreacted alkane or alkyl aromatic hydrocarbons can then be removed from the reaction product in one or more separator drums. For example, one or more splitters or distillation columns can be used to separate the dehydrogenated product from the unreacted first hydrocarbon-containing feed.

[0111] In some embodiments, a recovered olefin, e.g., propylene, can be used for producing polymer, e.g., recovered propylene can be polymerized to produce polymer having segments or units derived from the recovered propylene such as polypropylene, ethylene-propylene copolymer, etc. Recovered isobutene can be used, e.g., for producing one or more of: an oxygenate such as methyl tert-butyl ether, fuel additives such as diisobutene, synthetic elastomeric polymer such as butyl rubber, etc.

A Process for Regenerating a Catalyst

[0112] In some embodiments, a process for regenerating the catalyst composition can include the regenerating processes disclosed in U.S. Patent Application No. 63/195,966. For example, the regenerating process that can be used to regenerate an at least partially deactivated catalyst composition that can include a contaminant, up to 0.025 wt% of the Pt, and up to 10 wt% of the promoter that can include Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof, disposed on the support, the support including at least 0.5 wt% of a Group 2 element, where all weight percent values are based on the weight of the support. In some embodiments, the contaminant can be or can include coke. The process can include (I) heating the at least partially deactivated catalyst composition using a heating gas mixture that can include H₂O at a concentration of greater than 5 mol%, based on the total moles in the heating gas mixture to produce a precursor catalyst composition. The process can also include (II) providing an oxidative gas that can include no greater than 5 mol% of H₂O, based on the total moles in the oxidative gas. The process can also include (III) contacting the precursor catalyst composition at an oxidizing temperature in a range of from 620°C to 1,000°C with the oxidative gas for a duration of at least 30 seconds, preferably at least 1 minute, preferably at least 5 minutes, to produce an oxidized precursor catalyst composition. The process can also include (IV) obtaining a regenerated

catalyst composition from the oxidized precursor catalyst composition. In some embodiments, the heating gas mixture can be produced by combusting a fuel with an oxidizing gas. In some embodiments, the fuel can include at least one of H₂, CO, and a hydrocarbon and the oxidizing gas can include O₂. In some embodiments, the oxidative gas can be or can include, but is not limited to, O₂, O₃, CO₂, or a mixture thereof and can include no greater than 5 mol% of H₂O.

An Eleventh Process for Upgrading a Hydrocarbon

[0113] The eleventh process for upgrading a hydrocarbon can include contacting a hydrocarbon-containing feed (a second hydrocarbon-containing feed) with the catalyst composition that includes Pt and the promoter disposed on the support to effect reforming of at least a portion of the second hydrocarbon-containing feed to produce a coked catalyst composition and an effluent that can include carbon monoxide and molecular hydrogen. The catalyst composition and the second hydrocarbon-containing feed can be contacted with one another within any suitable environment such as one or more reaction or conversion zones disposed within one or more reactors to produce the effluent and the coked catalyst composition. The reaction or conversion zone can be disposed or otherwise located within one or more fixed bed reactors, one or more fluidized or moving bed reactors, one or more reverse flow reactors, or any combination thereof. For clarity and ease of description, the reforming reaction will be discussed in the context of a fluidized bed reactor, but it should be understood that fixed bed reactors, reverse flow or moving bed reactors, or any other reactor can be used to carry out the reforming of the second hydrocarbon-containing feed.

[0114] The reforming reaction can be used to produce reformed hydrocarbons via a continuous reaction process or a discontinuous reaction process. In some embodiments, the reaction process can include a reforming step, and a regeneration step, e.g., an exothermic reaction, that operate continuously while the fluidized catalyst composition is transported in-between the reforming and regeneration zone of the reactor. The endothermic reaction can include hydrocarbon reforming in the presence of the catalyst composition. Fresh hydrocarbon and regenerated fluidized catalyst particles can enter the reforming zone. After spending some time in the reforming zone, the hydrocarbon can be at least partially converted to a reforming product that can exit the reforming zone together with the spent catalyst composition. The reforming product and unreacted feed can be separated from the spent catalyst by one or more separating devices. While the reforming product and unreacted feed from the separating devices go downstream for further

purification, the spent catalyst can be sent to the regeneration zone for regeneration. The exothermic regeneration reaction can be the reaction of an oxidant and, optionally a fuel, under combustion conditions to produce a regenerated catalyst and a flue gas. After regeneration, the regenerated catalyst can be separated from the flue gas by one or more separating devices and can be transported back to the reforming zone, joining more hydrocarbon feed to enter the reforming zone to initiate more reforming reaction. The reforming step can convert CO₂ and/or H₂O and hydrocarbons, e.g., CH₄, to a synthesis gas that includes H₂ and CO. The regeneration step can combust reactants, e.g., coke disposed on the spent catalyst and/or the optional fuel and an oxidant, to generate heat that heats up the regenerated catalyst that can provide heat that can be used to drive the reforming reaction. In some embodiments, the catalyst can be heated to an average temperature in a range of from 600°C, 700°C, or 800°C to 1,000°C, 1,300°C, or 1,600°C during the regeneration step.


[0115] Illustrative fuels can be or can include, but are not limited to, hydrocarbons, e.g., methane, ethane, propane, butane, pentane, or hydrocarbon containing streams, e.g., natural gas, molecular hydrogen, and/or other combustible compounds. The oxidant can be or can include O₂. In some embodiments, the oxidant can be or can include air, O₂ enriched air, O₂ depleted air, or any other suitable O₂ containing stream.

[0116] The regeneration of the catalyst can correspond to removal of coke from the catalyst particles. In some embodiments, during reforming, a portion of the feed introduced into the reforming zone can form coke. This coke can potentially block access to the catalytic sites (such as metal sites) of the catalyst. During regeneration at least a portion of the coke generated during reforming can be removed as CO or CO₂. The regeneration of the catalyst can also correspond to re-dispersion of any agglomerated active phase of the catalyst such as Pt.

[0117] The second hydrocarbon-containing feed can be or can include, but is not limited to, one or more reformable C₁-C₁₆ hydrocarbons such as alkanes, alkenes, cycloalkanes, alkylaromatics, or any mixture thereof. In some embodiments, the second hydrocarbon-containing stream can be or can include methane, ethane, propane, butane, pentane, or a mixture thereof. In some embodiments, the second hydrocarbon-containing feed can be exposed to the catalyst composition under a pressure of less than 35 kPa-a. For example, the second hydrocarbon-containing feed can be exposed to the catalyst composition under a pressure in a range of from 0.7 kPa-a, 2 kPa-a, 3.5 kPa-a, 5 kPa-a, or 10 kPa-a to 15 kPa-a, 20 kPa-a, 25 kPa-a, or 30 kPa-a. In other embodiments, the second hydrocarbon-



containing feed can be exposed to the catalyst composition under a pressure in a range of from 35 kPa-a to 15 MPa-a. In still other embodiments, the second hydrocarbon-containing feed can be exposed to the catalyst composition under a pressure in a range of from 0.7 kPa-a, 2 kPa-a, 5 kPa-a, 20 kPa-a, 35 kPa-a, 50 kPa-a, or 100 kPa-a to 200 kPa-a, 1 MPa-a, 3 MPa-a, 5 MPa-a, 10 MPa-a, or 15 MPa-a. In still other embodiments, the second hydrocarbon-containing feed can be exposed to the catalyst composition under a pressure of less than 2.8 MPa-a, less than 2.5 MPa-a, less than 2.2 MPa-a, or less than 2 MPa-a.

[0118] The reforming reaction of the second hydrocarbon-containing feed, e.g., CH₄, can occur in the presence of H₂O (steam-reforming), in the presence of CO₂ (dry-reforming), or in the presence of both H₂O and CO₂ (bi-reforming). Examples of stoichiometry for steam, dry, and bi-reforming of CH₄ are shown in equations (1) – (3).



[0119] As shown in equations (1) – (3), dry reforming can produce lower ratios of H₂ to CO than steam reforming. Reforming reactions performed with only steam can generally produce a synthesis gas having a H₂:CO molar ratio of around 3, such as 2.5 to 3.5. In contrast, reforming reactions performed with only CO₂ can generally produce a synthesis gas having a H₂:CO molar ratio of roughly 1 or even lower. By using a combination of CO₂ and H₂O during reforming, the reforming reaction can be controlled to generate a wide variety of H₂ to CO ratios in a resulting synthesis gas.

[0120] The reforming reaction of the second hydrocarbon-containing feed can also be performed or partially performed in the presence of O₂, which is often referred to as the partial oxidation reaction. Examples of stoichiometry for partial and complete oxidation are shown in equations (4) and (5).



[0121] During partial oxidation of methane, a certain degree of complete oxidation of methane may be unavoidable. In such reaction, the CO₂ and H₂O made during the complete oxidation of methane may further reform methane via one or more of reactions (1) to (3).

[0122] It should be noted that the ratio of H₂ to CO in a synthesis gas can also be dependent on the water gas shift equilibrium. Although the stoichiometry in Equations

product of a process using biomass as the feed. The fuels described in this work can also be derived either from fossil fuel or non-fossil fuel resources. For example, methane or H₂ can be a product or by-product of a process using biomass as the feed. The fuels described in this work can also be made from renewable energy such as renewable electricity. For example, renewable electricity can be used to produce H₂ through water electrolysis. The energy used in the processes described herein can also be provided by renewable electricity, instead of a fuel.

Examples:

[0127] The foregoing discussion can be further described with reference to the following non-limiting examples. Catalyst compositions 1-12 were prepared according to the following procedures.

[0128] Catalyst compositions 1-14 were prepared according to the following procedure. For each catalyst composition PURALOX® MG 80/150 (3 grams) (Sasol), which was a mixed Mg/Al metal oxide that contained 80 wt% of MgO and 20 wt% of Al₂O₃ and had a surface area of 150 m²/g, was calcined under air at 550°C for 3 hours to form a support. Solutions that contained a proper amount of tin (IV) chloride pentahydrate when used to make the catalyst composition (Acros Organics) and/or chloroplatinic acid when used to make the catalyst composition (Sigma Aldrich), and 1.8 ml of deionized water were prepared in small glass vials. The calcined PURALOX® MG 80/150 supports (2.3 grams) for each catalyst composition were impregnated with the corresponding solution. The impregnated materials were allowed to equilibrate in a closed container at room temperature (RT) for 24 hours, dried at 110°C for 6 hours, and calcined at 800°C for 12 hours. Table 1 shows the nominal Pt and Sn content of each catalyst composition based on the weight of the support.

25

Table 1		
Catalyst	Pt (wt%)	Sn (wt%)
1	0.4	1
2	0.3	1
3	0.2	1
4	0.1	1
5	0.05	1
6	0.025	1
7	0.0125	1
8	0	1
9	0.1	0.5
10	0.1	1
11	0.1	2
12	0.0125	0
13	0.0125	0.5
14	0.0125	2

Examples using the catalysts described above.

[0129] Fixed bed experiments were conducted at approximately 100 kPa-absolute that used the catalyst compositions 1-8 (Examples 1-8, respectively). A gas chromatograph (GC) was used to measure the composition of the reactor effluents. The concentrations of each component in the reactor effluents were then used to calculate the C_3H_6 yield and selectivity. The C_3H_6 yield and selectivity, as reported in these examples, were calculated on the carbon mole basis.

[0130] In each example, 0.3 g of the catalyst composition was mixed with an appropriate amount of quartz diluent and loaded into a quartz reactor. The amount of diluent was determined so that the catalyst bed (catalyst + diluent) overlapped with the isothermal zone of the quartz reactor and the catalyst bed was largely isothermal during operation. The dead volume of the reactor was filled with quartz chips/rods.

[0131] The C_3H_6 yield and the selectivity at the beginning of t_{rxn} and at the end of t_{rxn} is denoted as Y_{ini} , Y_{end} , S_{ini} , and S_{end} , respectively, and reported as percentages in Tables 2 and 3 below.

[0132] The process steps for Examples 1-8 were as follows: 1. The system was flushed with an inert gas. 2. Dry air at a flow rate of 83.9 sccm was passed through a by-pass of the reaction zone, while an inert was passed through the reaction zone. The reaction zone was heated to a regeneration temperature of 800°C. 3. Dry air at a flow rate of 83.9 sccm was then passed through the reaction zone for 10 min to regenerate the catalyst. 4. The

- system was flushed with an inert gas. 5. A H₂ containing gas with 10 vol% H₂ and 90 vol % Ar at a flow rate of 46.6 sccm was passed through the by-pass of the reaction zone for a certain period of time, while an inert gas was passed through the reaction zone. This is then followed by flowing the H₂ containing gas through the reaction zone at 800°C for 3 seconds. 6. The system was flushed with an inert gas. During this process, the temperature of the reaction zone was changed from 800°C to a reaction temperature of 670°C. 7. A hydrocarbon-containing (HCgas) feed that included 81 vol% of C₃H₈, 9 vol% of inert gas (Ar or Kr) and 10 vol% of steam at a flow rate of 35.2 sccm was passed through the by-pass of the reaction zone for a certain period of time, while an inert gas was passed through the reaction zone. The hydrocarbon-containing feed was then passed through the reaction zone at 670°C for 10 min. GC sampling of the reaction effluent started as soon as the feed was switched from the by-pass of the reaction zone to the reaction zone.
- [0133] The above process steps were repeated in cycles until stable performance was obtained. Tables 2 and 3 show that Catalyst 6 that contained only 0.025 wt% of Pt and 1 wt% of Sn had both a similar yield and a similar selectivity as compared to Catalyst 1 that contained 0.4 wt% of Pt and 1 wt% of Sn, which was surprising and unexpected. Catalyst 8 that did not include any Pt did not show an appreciable propylene yield.

Table 2					
		Catalyst 1	Catalyst 2	Catalyst 3	Catalyst 4
Performance	Y _{ini}	61.7	61.7	60.7	63.7
	Y _{end}	55.2	55.7	54.2	56.7
	S _{ini}	97.3	97.2	97.0	97.1
	S _{end}	98.1	98.0	97.7	98.3

Table 3					
		Catalyst 5	Catalyst 6	Catalyst 7	Catalyst 8
Performance	Y _{ini}	62.4	62.0	56.7	2.0
	Y _{end}	57.2	54.6	45.7	1.7
	S _{ini}	96.7	97.3	96.9	64.2
	S _{end}	97.7	98.0	97.6	49.5

[0134] Catalysts 9-14 were also tested using the same process steps 1-7 described above. Table 4 shows that the level of Sn should not be too low or too high for optimal propylene yield for the catalyst compositions that included 0.1 wt% of Pt based on the weight of the support.

Table 4					
		Catalyst 9	Catalyst 4	Catalyst 10	Catalyst 11
		0.5 wt% Sn	1 wt% Sn	1 wt% Sn	2 wt% Sn
Performance	Y _{ini}	58.4	63.7	63.4	56.5
	Y _{end}	49.5	56.7	55.5	47.7
	S _{ini}	96.9	97.1	97.2	97.8
	S _{end}	97.6	98.3	98.1	98.2

[0135] Table 5 shows that the level of Sn should not be too high or too low for optimal propylene yield for the catalyst compositions that included 0.0125 wt% of Pt based on the weight of the support.

Table 5					
		Catalyst 12	Catalyst 13	Catalyst 7	Catalyst 14
		0 wt% Sn	0.5 wt% Sn	1 wt% Sn	2 wt% Sn
Performance	Y _{ini}	2.6	44	56.7	55.4
	Y _{end}	1.7	24.4	45.7	44.1
	S _{ini}	63.9	96.7	96.9	96.8
	S _{end}	61.1	95.6	97.6	97.6

[0136] Catalyst 6 that contained only 0.025 wt% of Pt and 1 wt% of Sn was also subjected to a longevity test using the same process steps 1-7 described above, except a flow rate of 17.6 sccm was used instead of 35.2 sccm in step 7. The Figure shows that

Catalyst 6 maintained performance for 204 cycles (x-axis is time, y-axis is C₃H₆ yield and selectivity to C₃H₆, both in carbon mole %).

Listing of Embodiments

[0137] This disclosure may further include the following non-limiting embodiments.

- 5 [0138] A1. A process for upgrading a hydrocarbon, comprising: (I) contacting a hydrocarbon-containing feed with a catalyst composition comprising Pt and a promoter disposed on a support to effect reforming of at least a portion of the hydrocarbon-containing feed to produce a coked catalyst composition and a synthesis gas comprising H₂ and CO, wherein: the hydrocarbon-containing feed comprises one or more C₁-C₁₆
- 10 hydrocarbons and H₂O, CO₂, or a mixture of H₂O and CO₂, the hydrocarbon-containing feed and catalyst composition are contacted at a temperature of 400°C or more, the support comprises at least 0.5 wt% of a Group 2 element, the catalyst composition comprises up to 0.025 wt% of the Pt and up to 10 wt% of the promoter based on the weight of the support, and the promoter comprises Sn, Cu, Au, Ag, Ga, a combination thereof, or a
- 15 mixture thereof.
- [0139] A2. The process of A1, further comprising (II) contacting at least a portion of the coked catalyst composition with an oxidant to effect combustion of at least a portion of the coke to produce a regenerated catalyst composition lean in coke and a combustion gas.
- 20 [0140] A3. The process of A2, further comprising (III) contacting a fuel with the oxidant and the catalyst composition to effect combustion of at least a portion of the fuel.
- [0141] A4. The process of A2 or A3, further comprising (IV) contacting an additional quantity of the hydrocarbon-containing feed with at least a portion of the regenerated catalyst composition to produce a re-coked catalyst composition and additional effluent.
- 25 [0142] A5. The process of any of A1 to A4, wherein the hydrocarbon-containing feed is contacted with the catalyst composition in a fluidized bed reactor.
- [0143] A6. The process of any of A1 to A4, wherein the hydrocarbon-containing feed is contacted with the catalyst composition in a fixed bed reactor.
- [0144] A7. The process of any of A1 to A4, wherein the hydrocarbon-containing feed
- 30 is contacted with the catalyst composition in a reverse flow reactor.
- [0145] A8. The process of any of A1 to A7, wherein the catalyst composition comprises 0.001 wt%, 0.005 wt%, or 0.007 wt% to 0.01 wt%, 0.015 wt%, 0.018 wt%, 0.02 wt%, 0.022 wt%, or 0.025 wt% of the Pt based on the weight of the support.

- [0146] A9. The process of any of A1 to A8, wherein the catalyst composition comprises 0.25 wt%, 0.5 wt%, or 1 wt% to 3 wt%, 5 wt%, or 10 wt% of the promoter based on the weight of the support.
- [0147] A10. The process of any of A1 to A9, wherein the catalyst composition further
5 comprises an alkali metal element comprising Li, Na, K, Rb, Cs, a combination thereof, or a mixture thereof disposed on the support in an amount of up to 5 wt% based on the weight of the support.
- [0148] A11. The process of any of A1 to A10, wherein the catalyst composition is in the form of particles having a size and particle density that is consistent with a Geldart A
10 or Geldart B definition of a fluidizable solid.
- [0149] A12. The process of any of A1 to A11, wherein: the Group 2 element comprises Mg, and at least a portion of the Group 2 element is in the form of MgO or a mixed metal oxide comprising Mg.
- [0150] A13. The process of any of A1 to A12, wherein: the Group 2 element comprises
15 Mg, and at least a portion of the Group 2 element is in the form of a mixed Mg/Al metal oxide.
- [0151] A14. The process of any of A1 to A13, wherein: the support further comprises a Group 13 element, the Group 2 element comprises Mg and the Group 13 element comprises Al, the support comprises a mixed Mg/Al metal oxide, and a weight ratio of the
20 Mg to the Al in the mixed Mg/Al metal oxide is in a range from 0.001, 0.01, 0.1, or 1 to 6, 12.5, 100, or 1,000
- [0152] A15. The process of any of A1 to A14, wherein: the support further comprises a Group 13 element, the promoter comprises Sn, the Group 2 element comprises Mg, and the Group 13 element comprises Al, the catalyst composition comprises 0.001 wt%, 0.005
25 wt%, or 0.007 wt% to 0.01 wt%, 0.015 wt%, 0.018 wt%, 0.02 wt%, 0.022 wt%, or 0.025 wt% of Pt and 0.25 wt%, 0.5 wt%, or 1 wt% to 3 wt%, 5 wt%, or 10 wt% of Sn based on the weight of the support, the support comprises a mixed Mg/Al metal oxide, and a weight ratio of the Mg to the Al in the mixed Mg/Al metal oxide is in a range from 0.001 to 1,000, 0.01 to 100, 0.1 to 12.5, or 1 to 6.
- [0153] A16. The process of any of A1 to A15, further comprising at least one of:
30 reacting at least a portion of the synthesis gas under effective Fischer-Tropsch conditions in the presence of a Fischer-Tropsch catalyst to produce an upgraded product, wherein the Fischer-Tropsch catalyst comprises a shifting Fischer-Tropsch catalyst or a non-shifting Fischer-Tropsch catalyst; subjecting at least a portion of the synthesis gas to a

fermentation process to produce an alcohol, an organic acid, or a mixture thereof; contacting at least a portion of the synthesis gas with a catalyst to produce at least one C₁-C₄ alcohol; and separating H₂ from the synthesis gas to produce a H₂-rich product.

- [0154] B1. A process for making a catalyst composition, comprising: (I) preparing a slurry or gel comprising a compound containing a Group 2 element and a liquid medium; and (II) spray drying the slurry or the gel to produce spray dried support particles comprising the Group 2 element, wherein, at least one of (i) and (ii) is met: (i) Pt is present in the slurry or the gel in the form of a Pt-containing compound and the catalyst composition comprises catalyst particles comprising the spray dried support particles having Pt disposed thereon, and (ii) Pt is deposited on the spray dried support particles by contacting the spray dried particles with a Pt-containing compound to produce Pt-containing spray dried support particles and the catalyst composition comprises catalyst particles comprising the spray dried support particles having Pt disposed thereon, and wherein, at least one of (iii) and (iv) is met: (iii) a compound comprising a promoter element is present in the slurry or the gel and the catalyst composition comprises catalyst particles comprising the spray dried support particles having the promoter element disposed thereon, and (iv) a compound comprising a promoter element is deposited on the spray dried support particles to produce promoter-containing spray dried support particles and the catalyst composition comprises catalyst particles comprising the spray dried support particles having the promoter element disposed thereon, wherein: the promoter element comprises Sn, Cu, Au, Ag, Ga, or a combination thereof, or a mixture thereof, the catalyst particles comprise up to 0.025 wt% of the Pt and up to 10 wt% of the promoter element based on the weight of the spray dried support particles, and the catalyst particles comprise at least 0.5 wt% of the Group 2 element based on the weight of the spray dried support particles.

[0155] B2. The process of B1, wherein the Pt-containing compound is present in the slurry or the gel.

[0156] B3. The process of B1 or B2, wherein the Pt-containing compound is deposited on the spray dried support particles.

- [0157] B4. The process of any of B1 to B3, wherein the compound comprising the promoter element is present in the slurry or the gel.

[0158] B5. The process of any of B1 to B4, wherein the compound comprising the promoter element is deposited on the spray dried support particles.

[0159] B6. The process of any of B1 to B5, wherein: the Group 2 element comprises Mg, and at least a portion of the Group 2 element in the spray dried support particles is in the form of a mixed Mg/Al metal oxide.

5 [0160] B7. The process of any of B1 to B6, further comprising: (III) calcining the spray dried support particles under an oxidative atmosphere to produce calcined support particles, wherein the catalyst composition comprises catalyst particles comprising the calcined support particles comprising the Group 2 element and having Pt and the promoter element disposed thereon.

10 [0161] B8. The process of B7, further comprising: (IV) hydrating the calcined support particles after step (III) to produce hydrated support particles; and (V) calcining the hydrated support particles to produce the catalyst composition comprising re-calcined support particles, wherein the catalyst particles produced via steps (IV) and (V) have an attrition loss after one hour that is less than an attrition loss after one hour of the calcined particles produced in step (III), as measured according to ASTM D5757-11(2017).

15 [0162] Various terms have been defined above. To the extent a term used in a claim is not defined above, it should be given the broadest definition persons in the pertinent art have given that term as reflected in at least one printed publication or issued patent. Furthermore, all patents, test procedures, and other documents cited in this application are fully incorporated by reference to the extent such disclosure is not inconsistent with this application and for all jurisdictions in which such incorporation is permitted.

20 [0163] While the foregoing is directed to embodiments of the present invention, other and further embodiments of the invention may be devised without departing from the basic scope thereof, and the scope thereof is determined by the claims that follow.

CLAIMS:

What is claimed is:

1. A catalyst composition comprising up to 0.025 wt% of Pt and up to 10 wt% of a promoter comprising Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof disposed on a support, the support comprising at least 0.5 wt% of a Group 2 element, wherein all weight percent values are based on the weight of the support.
2. The catalyst composition of claim 1, wherein the catalyst composition comprises 0.001 wt% to 0.025 % of the Pt based on the weight of the support.
3. The catalyst composition of claim 1 or 2, wherein the promoter comprises Sn.
4. The catalyst composition of any of claims 1 to 3, further comprising an alkali metal element comprising Li, Na, K, Rb, Cs, or a combination thereof, or a mixture thereof disposed on the support in an amount of up to 5 wt% based on the weight of the support.
5. The catalyst composition of any of claims 1 to 4, wherein the catalyst composition is in the form of particles having a size and particle density that is consistent with a Geldart A or Geldart B definition of a fluidizable solid.
6. The catalyst composition of any of claims 1 to 5, wherein:
the Group 2 element comprises Mg, and
at least a portion of the Group 2 element is in the form of MgO or a mixed metal oxide comprising Mg.
7. The catalyst composition of any of claims 1 to 6, wherein:
the Group 2 element comprises Mg, and
at least a portion of the Group 2 element is in the form of a mixed Mg/Al metal oxide.

8. The catalyst composition of any of claims 1 to 7, wherein:
the support further comprises a Group 13 element,
the Group 2 element comprises Mg and the Group 13 element comprises Al,
the support comprises a mixed Mg/Al metal oxide, and
a weight ratio of the Mg to the Al in the mixed Mg/Al metal oxide is in a range from 0.001 to 1,000.
9. The catalyst composition of any of claims 1 to 8, wherein:
the support further comprises a Group 13 element,
the promoter comprises Sn, the Group 2 element comprises Mg, and the Group 13 element comprises Al,
the catalyst composition comprises 0.001 wt% to 0.025 wt% of the Pt and 0.25 wt% to 10 wt% of the Sn based on the weight of the support,
the support comprises a mixed Mg/Al metal oxide, and
a weight ratio of the Mg to the Al in the mixed Mg/Al metal oxide is in a range from 0.001 to 1,000.
10. A process for making a catalyst composition, comprising:
(I) preparing a slurry or a gel comprising a compound containing a Group 2 element and a liquid medium;
(II) spray drying the slurry or the gel to produce spray dried particles comprising the Group 2 element; and
(III) calcining the spray dried particles under an oxidative atmosphere to produce calcined support particles comprising the Group 2 element,
wherein, at least one of (i), (ii), and (iii) is met:
(i) Pt is present in the slurry or the gel in the form of a Pt-containing compound and the catalyst composition comprises catalyst particles comprising the calcined support particles having Pt disposed thereon,
(ii) Pt is deposited on the spray dried particles by contacting the spray dried particles with a Pt-containing compound to produce Pt-containing spray dried particles and the catalyst composition comprises catalyst particles comprising the calcined support particles having Pt disposed thereon, and
(iii) Pt is deposited on the calcined support particles by contacting the calcined support particles with a Pt-containing compound to produce Pt-

containing calcined support particles and the process further comprises (IV) calcining the Pt-containing calcined support particles to produce re-calcined support particles having Pt disposed thereon, wherein the catalyst composition comprises the re-calcined support particles, and wherein, at least one of (iv), (v), and (vi) is met:

(iv) a compound comprising a promoter element is present in the slurry or the gel and the catalyst composition comprises catalyst particles comprising the calcined support particles having the promoter element disposed thereon,

(v) a compound comprising a promoter element is deposited on the spray dried particles to produce promoter-containing spray dried particles and the catalyst composition comprises catalyst particles comprising the calcined support particles having the promoter element disposed thereon, and

(vi) a compound comprising a promoter element is deposited on the calcined support particles to produce promoter-containing calcined support particles and the process further comprises (V) calcining the promoter-containing calcined support particles to produce re-calcined support particles having the promoter element disposed thereon, wherein the catalyst composition comprises the re-calcined support particles,

wherein:

the promoter element comprises Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof,

the catalyst particles comprise the Pt in an amount of up to 0.025 wt% and the promoter element in an amount of up to 10 wt% based on the weight of the calcined support particles or the re-calcined support particles, and

the catalyst particles comprise at least 0.5 wt% of the Group 2 element based on the weight of the calcined support particles or the re-calcined support particles.

11. The process of claim 10, wherein the spray dried particles are calcined at a temperature in a range of from 550°C to 900°C for a time period of ≤ 45 minutes.

12. The process of claim 10, wherein the spray dried particles are calcined at a temperature of $< 550^\circ\text{C}$ for a time period of ≤ 45 minutes.

13. The process of any of claims 10 to 12, wherein the Pt-containing compound is present in the slurry or the gel.
14. The process of any of claims 10 to 13, wherein the Pt-containing compound is deposited on the spray dried particles.
15. The process of any of claims 10 to 14, wherein the Pt-containing compound is deposited on the calcined support particles and the process further comprises step (IV).
16. The process of any of claims 10 to 15, wherein the compound comprising the promoter element is present in the slurry or the gel.
17. The process of any of claims 10 to 16, wherein the compound comprising the promoter element is deposited on the spray dried particles.
18. The process of any of claims 10 to 17, wherein the compound comprising the promoter element is deposited on the calcined support particles and the process further comprises step (V).
19. The process of any of claims 10 to 18, further comprising:
(VI) hydrating the calcined support particles after step (III) to produce hydrated support particles; and
(VII) calcining the hydrated support particles to produce the catalyst composition comprising re-calcined support particles, wherein the re-calcined support particles produced via steps (VI) and (VII) have an attrition loss after one hour that is less than an attrition loss after one hour of the calcined support particles produced in step (III), as measured according to ASTM D5757-11(2017).

20. The process of any of claims 11 to 19, wherein:
the Group 2 element comprises Mg, and
at least a portion of the Group 2 element is in the form of MgO or a mixed metal oxide comprising Mg.
21. A process for upgrading a hydrocarbon, comprising:
(I) contacting a hydrocarbon-containing feed with a catalyst composition comprising Pt and a promoter disposed on a support to effect one or more of dehydrogenation, dehydroaromatization, and dehydrocyclization of at least a portion of the hydrocarbon-containing feed to produce a coked catalyst composition and an effluent comprising one or more upgraded hydrocarbons and molecular hydrogen, wherein:
the hydrocarbon-containing feed comprises one or more of C₂-C₁₆ linear or branched alkanes, or one or more of C₄-C₁₆ cyclic alkanes, or one or more C₈-C₁₆ alkyl aromatics, or a mixture thereof,
the hydrocarbon-containing feed and catalyst composition are contacted at a temperature in a range of from 300°C to 900°C, for a time period of ≤3 hours, under a hydrocarbon partial pressure of at least 20 kPa-absolute, wherein the hydrocarbon partial pressure is the total partial pressure of any C₂-C₁₆ alkanes and any C₈-C₁₆ alkyl aromatics in the hydrocarbon-containing feed,
the support comprises at least 0.5 wt% of a Group 2 element based on the weight of the support,
the catalyst composition comprises up to 0.025 wt% of the Pt and up to 10 wt% of the promoter based on the weight of the support,
the promoter comprises Sn, Cu, Au, Ag, Ga, a combination thereof, or a mixture thereof, and
the one or more upgraded hydrocarbons comprise at least one of a dehydrogenated hydrocarbon, a dehydroaromatized hydrocarbon, and a dehydrocyclized hydrocarbon.

22. The process of claim 21, further comprising:

(II) contacting at least a portion of the coked catalyst composition with an oxidant to effect combustion of at least a portion of the coke to produce a regenerated catalyst composition lean in coke and a combustion gas; and

(III) contacting an additional quantity of the hydrocarbon-containing feed with at least a portion of the regenerated catalyst composition to produce a re-coked catalyst composition and additional effluent, wherein a cycle time from contacting the hydrocarbon-containing feed with the catalyst composition in step (I) to contacting the additional quantity of the hydrocarbon-containing feed with the regenerated catalyst composition in step (III) is ≤ 5 hours.

23. The process of claim 21 or claim 22, wherein the hydrocarbon-containing feed comprises propane, and wherein contacting the hydrocarbon-containing feed with the catalyst composition in step (I) has a propylene yield of at least 52 % at a propylene selectivity of $\geq 85\%$.

24. The process of any of claims 21 to 23, wherein:

the Group 2 element comprises Mg, and

at least a portion of the Group 2 element is in the form of MgO or a mixed metal oxide comprising Mg.