

DESCRIPTION

Method for Producing Lactic Acid and Method for Producing Polylactic acid

TECHNICAL FIELD

[0001]

The present invention relates to a method for producing lactic acid, in which a microorganism having an ability of lactic acid fermentation is cultured and lactic acid produced in the obtained fermentation broth is separated, and a method for producing a polylactic acid using the lactic acid obtained by the method for producing lactic acid. The present invention also relates to the lactic acid and the polylactic acid obtained by these production methods.

BACKGROUND ART

[0002]

Lactic acid is widely used for food, pharmaceuticals and the like, and also widely applied to industrial uses as a monomer material for polylactic acid, which is a biodegradable plastic, so that its demand is increasing. Lactic acid is known to be produced by fermentation by microorganisms which convert carbohydrate-containing substrates represented by glucose into lactic acid.

[0003]

In order to obtain lactic acid as a raw material for polylactic acid, a highly productive production method of lactic acid is required since the necessary amount of lactic acid is large. For enhancement of the productivity of lactic acid, a high yield relative to sugar consumption in the microbial fermentation as well as a high production rate of lactic acid per unit time per unit volume are indispensable, and, in Patent Document 1, a method of enhancement of the production rate by a culture apparatus using a porous membrane is disclosed.

[0004]

A polylactic acid can be produced by a method by ring-opening polymerization of lactide, which is a cyclic dimer of lactic acid, or a method by direct polymerization of a raw material lactic acid. In the lactide method, lactic acid is once oligomerized and then depolymerized while isolating lactide produced, which is then subjected to ring-opening polymerization in the presence of a catalyst. In this method, the polymerization process is complicated and hence requires much labor and cost. Since, in this process, impurities in the raw material lactic acid can be removed by the operation of lactide isolation, a raw material lactic acid of relatively low quality can be used. However, since impurities in the raw material lactic acid, such as inorganic ions, cause decrease in the yield of lactide to be isolated, the raw material lactic acid needs to be relatively free from impurities. On the other hand, in the direct polymerization method, the raw material lactic acid is subjected to direct dehydration polycondensation in the presence of a catalyst. In this method, simplification of the process can be expected compared to the lactide method, but impurities that inhibit the polymerization need to be preliminarily removed from the raw material lactic acid, to provide a high-quality raw material lactic acid. Thus, the purification efficiency of lactic acid influences the enhancement of productivity of lactide and polylactic acid.

[0005]

Production of lactic acid by microbial fermentation is carried out while adding an alkaline substance to the culture medium to maintain the optimum pH for the microbial fermentation, and examples of the alkaline substance to be added to the culture medium include calcium hydroxide. In cases where calcium hydroxide was used, the lactic acid produced by microbial fermentation exists in the culture medium as calcium lactate. By adding an acidic substance (e.g., sulfuric acid) to the culture medium after completion of the culture, a solution of free lactic acid can be obtained, but a calcium salt (e.g., calcium sulfate) is by-produced as an impurity.

[0006]

As a method for separating lactic acid by removing the by-produced calcium salt, in cases where an insoluble calcium salt such as calcium sulfate precipitates, a method by filtration through qualitative filter paper or the like is used, but a small amount of the calcium salt dissolved in the solution cannot be removed, and remains in the lactic acid-containing solution. Therefore, in cases where this filtrate containing lactic acid is, for example, concentrated in a later purification step, the calcium salt and other soluble inorganic acids deposit (precipitate) in the solution containing free lactic acid, which has been problematic. It is known that, if the lactic acid-containing solution from which inorganic ions have not been sufficiently removed is heated by an operation such as distillation, the inorganic ions allow racemization and oligomerization of lactic acid to proceed.

[0007]

Examples of the method of removal of small amounts of inorganic ions from a lactic acid-containing solution include methods using ion-exchange resins (e.g., see Patent Document 2). However, in order to maintain the ion-exchange performance of the ion-exchange resin, the ion-exchange resin must be regenerated periodically. Further, since regeneration of an ion-exchange resin is carried out by using large amounts of an aqueous sodium hydroxide solution and an aqueous hydrochloric acid solution, a large amount of waste fluid is discharged during the regeneration, so that a large amount of cost is required for waste liquid disposal, which has been problematic. Further, repeated regeneration of an ion-exchange resin results in decrease in the regeneration rate of the ion-exchange resin, as well as decrease in the ion-exchange performance, leading to decrease in the removal rate of inorganic acids, which have been problematic.

[0008]

Further, methods of removal of small amounts of inorganic ion components

such as calcium components from a lactic acid-containing solution using an
electrodialyzer with a bipolar membrane are also known (e.g., see Patent Document
3). However, the bipolar membrane used in these methods is expensive and the
efficiency of removal of inorganic salts such as calcium salts is not necessarily high,
5 which have been problematic.

[0009]

Further, methods of removal of inorganic salts from a lactic acid-containing
solution using a nanofiltration membrane have been disclosed (e.g., see Patent
Documents 4 to 6). However, a step of recovery of lactic acid by distillation, the
10 effect of distillation on the yield of lactic acid, and the possibility of application of
the obtained lactic acid to industrial-scale production of a polylactic acid by direct
polymerization have not been disclosed.

[0010]

Further, in Patent Documents 7 to 10, the fact that the amounts of particular
15 impurities need to be less than particular levels in order to obtain a high-molecular-
weight polylactic acid has been disclosed, but the influences of impurities on the
thermal stability, mechanical strength and hue, which are important factors for the
processability of polylactic acids, have not been disclosed.

PRIOR ART DOCUMENTS

20 Patent Documents

[0011]

[Patent Document 1] WO2007/097260

[Patent Document 2] Japanese Translated PCT Patent Application Laid-open No.
2001-506274

25 [Patent Document 3] JP 2005-270025 A

[Patent Document 4] US 5503750

[Patent Document 5] US 5681728

[Patent Document 6] US 2004/0033573

[Patent Document 7] JP 6-279577 A

[Patent Document 8] JP 7-133344 A

[Patent Document 9] JP 8-188642 A

5 [Patent Document 10] JP 9-31170 A

SUMMARY OF THE INVENTION

PROBLEMS TO BE SOLVED BY THE INVENTION

[0012]

One of the objects of the present invention is to provide a method for
10 producing lactic acid with high productivity, which lactic acid can be applied to
industrial-scale production of a polylactic acid by direct polymerization and can be
used for high-yield synthesis of lactide; and methods for producing lactide and a
polylactic acid using the lactic acid. Further, the present invention aims to obtain a
polylactic acid having excellent thermal stability, mechanical strength and hue, and
15 to provide lactic acid in which the amounts of specific impurities are not more than
certain amount, and lactide and a polylactic acid obtained using the lactic acid as a
raw material.

MEANS FOR SOLVING THE PROBLEMS

[0013]

20 The present inventors intensively studied to solve the above problems and
discovered that culturing of a microorganism having an ability to produce lactic acid
in a continuous culture apparatus using a porous membrane enables to obtain lactic
acid in the permeate at a high yield and at a high production rate, and, by providing
the obtained permeate for a nanofiltration step and a distillation step, lactic acid
25 which is applicable to direct polymerization and allows high-yield synthesis of
lactide can be obtained. Further, the present inventors discovered that, by using
lactic acid, in which the amounts of particular impurities are not more than particular

levels, as a raw material for a polylactic acid, lactide having excellent hue and a polylactic acid having excellent thermal stability, mechanical strength and hue can be obtained at high yields, thereby completing the present invention.

[0014]

5 That is, the present invention is constituted by the following (1) to (15).

[0015]

(1) A method for producing lactic acid, the method comprising the Steps (A) to (C) below:

(A) a step of continuous fermentation wherein a fermentation culture medium
10 of a microorganism having an ability of lactic acid fermentation is filtered through a porous membrane having an average pore size of not less than 0.01 μm and less than 1 μm with a transmembrane pressure difference within the range of 0.1 to 20 kPa, and the permeate is collected, while retaining the non-permeated liquid in or returning the non-permeated liquid to the culture medium, and adding a fermentation
15 feedstock to the culture medium;

(B) a step of filtering the permeate obtained in Step (A) through a nanofiltration membrane; and

(C) a step of distilling the permeate obtained in Step (B) under a pressure of not less than 1 Pa and not more than atmospheric pressure, at not less than 25°C and
20 not more than 200°C to recover lactic acid.

[0016]

(2) A method for producing lactic acid according to (1), wherein the pH of the permeate obtained in the Step (A) is adjusted to not less than 2 and not more than 4.5, followed by providing the permeate for the Step (B).

25 [0017]

(3) The method for producing lactic acid according to (1) or (2), wherein the Step (A) is a step of continuous fermentation in the presence of a calcium salt, and a

solution containing lactic acid obtained after Step (D), in which the calcium component in the permeate obtained in the Step (A) is removed as an insoluble sulfate, is provided for the Step (B).

[0018]

- 5 (4) The method for producing lactic acid according to any one of (1) to (3), wherein the ratio of the permeation rate of magnesium sulfate relative to the permeation rate of citric acid through the nanofiltration membrane is not less than 3 at an operation pressure of 0.5 MPa, raw liquid temperature of 25°C and concentration in the raw liquid of 1000 ppm.

10 [0019]

- (5) The method for producing lactic acid according to any one of (1) to (4), wherein the permeation rate of magnesium sulfate through the nanofiltration membrane is not more than 1.5% at an operation pressure of 0.5 MPa, raw liquid temperature of 25°C and concentration in the raw liquid of 1000 ppm.

15 [0020]


- (6) The method for producing lactic acid according to any one of (1) to (5), wherein the membrane material of the nanofiltration membrane comprises a polyamide.

[0021]

- 20 (7) The method for producing lactic acid according to (6), wherein the polyamide comprises a cross-linked piperazine polyamide as a major component and further comprises a constituting component represented by Chemical Formula 1:

[0022]

[Chemical Formula 1]



25

Chemical Formula 1

[0023]

(wherein R represents -H or -CH₃; and n represents an integer of 0 to 3).

(8) A method for producing lactide, wherein lactic acid obtained by the method for producing lactic acid according to any one of (1) to (7) is used as a raw material.

[0024]

(9) A method for producing a polylactic acid, wherein lactide obtained by the method for producing lactide according to (8) is polymerized.

[0025]

(10) A method for producing a polylactic acid, wherein lactic acid obtained by the method for producing lactic acid according to any one of (1) to (7) is polymerized by direct dehydration polycondensation.

[0026]

(11) Lactic acid whose 90% aqueous solution contains methanol at a concentration of not more than 70 ppm, pyruvic acid at a concentration of not more than 500 ppm, furfural at a concentration of not more than 15 ppm, 5-hydroxymethylfurfural at a concentration of not more than 15 ppm, methyl lactate at a concentration of not more than 600 ppm, acetic acid at a concentration of not more than 500 ppm and 2-hydroxybutyric acid at a concentration of not more than 500 ppm.

[0027]

(12) The lactic acid according to (11), having an optical purity of not less than 90%.

[0028]

(13) Lactide obtained by using the lactic acid according to (11) or (12) as a raw material.

[0029]

(14) A polylactic acid obtained by using the lactic acid according to (11) or (12) or the lactide according to (13) as a raw material.

[0030]

5 (15) A polylactic acid obtained by direct dehydration polycondensation using the lactic acid according to (11) or (12) as a raw material.

EFFECT OF THE INVENTION

[0031]

10 By the present invention, high-quality lactic acid can be produced, and the productivity of a polylactic acid, which is a biodegradable general-purpose plastic, can be improved. Further, by using lactic acid, in which the amounts of specific impurities are not more than certain amount, as a raw material for a polylactic acid, a polylactic acid having excellent thermal stability, mechanical strength and hue can be obtained.

15 BRIEF DESCRIPTION OF THE DRAWINGS

[0032]

Fig. 1 is a schematic diagram showing an embodiment of the continuous culture apparatus used in the present invention.

20 Fig. 2 is a diagram showing the concentration of lactic acid accumulated and the production rate of lactic acid during the continuous culture carried out in Example 1 of the present invention.

Fig. 3 is a schematic diagram showing an embodiment of the nanofiltration membrane separation apparatus used in the present invention.

25 Fig. 4 is a schematic diagram showing an embodiment of the cross-sectional view of the cell in which a nanofiltration membrane was placed, in the nanofiltration membrane separation apparatus used in the present invention.

BEST MODE FOR CARRYING OUT THE INVENTION

[0033]

The present invention will now be described in more detail.

[0034]

[Method of Production of Lactic Acid]

5 The method of production of lactic acid of the present invention comprises the Steps (A) to (C) below:

 (A) a step of continuous fermentation wherein a fermentation culture medium of a microorganism having an ability of lactic acid fermentation is filtered through a porous membrane having an average pore size of not less than 0.01 μm and less than
10 1 μm with a transmembrane pressure difference within the range of 0.1 to 20 kPa, and the permeate is collected, while retaining the non-permeated liquid in or returning the non-permeated liquid to the culture medium, and adding a fermentation feedstock to the culture medium;

 (B) a step of filtering the permeate obtained in Step (A) through a
15 nanofiltration membrane; and

 (C) a step of distilling the solution obtained in Step (B) under a pressure of not less than 1 Pa and not more than atmospheric pressure, at not less than 25°C and not more than 200°C to recover lactic acid.

[0035]

20 The microorganism having an ability of lactic acid fermentation, which is used in Step (A) will now be described. The microorganism having an ability of lactic acid fermentation is not restricted as long as it can produce lactic acid, and a lactic acid bacterium or a microorganism to which an ability of lactic acid fermentation was artificially given or whose ability of lactic acid fermentation was
25 enhanced may be preferably used.

[0036]

The lactic acid bacterium may be defined herein as a prokaryotic

microorganism which produces lactic acid with an yield of not less than 50% relative to glucose consumed. Preferred examples of the lactic acid bacterium include those belonging to the genus *Lactobacillus*, genus *Pediococcus*, genus *Tetragenococcus*, genus *Carnobacterium*, genus *Vagococcus*, genus *Leuconostoc*, genus *Oenococcus*,
 5 genus *Atopobium*, genus *Streptococcus*, genus *Enterococcus*, genus *Lactococcus*, genus *Sporolactobacillus* and genus *Bacillus*. By selecting, among these, a lactic acid bacterium showing a high yield of lactic acid relative to sugar consumption, the bacterium can be preferably used in the production of lactic acid. Further, by selecting a lactic acid bacterium showing a high yield of L-lactic acid or D-lactic
 10 acid relative to sugar consumption, the bacterium can be preferably used in production of lactic acid having a high optical purity.

[0037]

Examples of the lactic acid bacterium showing a high yield of L-lactic acid relative to sugar consumption include *Lactobacillus yamanashiensis*, *Lactobacillus*
 15 *animalis*, *Lactobacillus agilis*, *Lactobacillus aviaries*, *Lactobacillus casei*, *Lactobacillus delbruekii*, *Lactobacillus paracasei*, *Lactobacillus rhamnosus*, *Lactobacillus ruminis*, *Lactobacillus salivarius*, *Lactobacillus sharpeae*, *Pediococcus dextrinicus* and *Lactococcus lactis*, which may be selected and used for production of L-lactic acid.

20 [0038]

Examples of the lactic acid bacterium showing a high yield of D-lactic acid relative to sugar consumption include *Sporolactobacillus laebolacticus*, *Sporolactobacillus inulinus*, *Lactobacillus bulgaricus*, *Lactobacillus casei*,
 25 *Lactobacillus delbruekii* and *Lactococcus lactis*, which may be selected and used for production of D-lactic acid.

[0039]

Examples of the microorganism to which an ability of lactic acid

fermentation was artificially given or whose ability of lactic acid fermentation was enhanced include microorganisms obtained by known chemical mutagenesis and microorganisms to which a lactate dehydrogenase (which may be hereinafter referred to as LDH) gene was introduced to give or enhance an ability of lactic acid fermentation. Preferred examples thereof include recombinant microorganisms to which LDH was incorporated intracellularly to enhance an ability of lactic acid fermentation.

Preferred examples of the host of the recombinant microorganisms include prokaryotic cells such as *E. coli* and lactic acid bacteria; and eukaryotic cells such as yeast; and the host is more preferably yeast. The yeast preferably belongs to the genus *Saccharomyces*, and the yeast is more preferably *Saccharomyces cerevisiae*.
[0040]

The LDH gene used in the present invention is not restricted as long as it encodes a protein having an activity to convert reduced nicotinamide adenine dinucleotide (NADH) and pyruvic acid to oxidized nicotinamide adenine dinucleotide (NAD⁺) and lactic acid. For example, an L-LDH gene derived from a lactic acid bacterium showing a high yield of L-lactic acid relative to sugar consumption, or a D-LDH gene derived from a lactic acid bacterium showing a high yield of D-lactic acid relative to sugar consumption may be used. Further, preferred examples of the L-LDH gene include those derived from eukaryotes such as cow, human and frog, and the L-LDH gene is more preferably derived from *Xenopus laevis*. Examples of microorganisms to which an L-LDH gene derived from a frog is incorporated include the recombinant yeast disclosed in JP 2008-029329 A.
[0041]

Examples of the LDH gene used in the present invention also include variants due to genetic polymorphisms and mutagenesis. The term “genetic polymorphism” means partial modification of the base sequence of a gene due to natural mutation

occurred in the gene. The term “mutagenesis” means artificial introduction of a mutation into a gene. Examples of the method of mutagenesis include a method using a site-directed mutagenesis kit (Mutan-K (manufactured by TAKARA BIO INC.)) and a method using a random mutagenesis kit (BD Diversify PCR Random Mutagenesis (manufactured by CLONTECH)). The LDH used in the present invention may have a deletion(s) and/or insertion(s) in a part of its base sequence as long as it encodes a protein having an activity to convert NADH and pyruvic acid to NAD⁺ and lactic acid.

[0042]

The porous membrane used in Step (A) will now be described. The porous membrane used as a separation membrane is preferably less prone to clogging by the microorganism having an ability of lactic acid fermentation, and has a property to stably maintain the filtration performance for a long time. Therefore, it is important for the porous membrane used in the present invention to have an average pore size of not less than 0.01 μm and less than 1 μm . The porous membrane in the present invention has a separation performance and a permeability suitable for the properties and the use of the liquid to be processed, and, in view of the blocking performance, permeability and resistance to dirt, which affects the separation performance, the porous membrane is preferably one having a porous resin layer. As the porous membrane having a porous resin layer, one having a porous resin layer on the surface of a porous base material, which layer acts as a separation function layer, is preferred. The porous base material supports the porous resin layer to strengthen the porous membrane.

[0043]

The porous base material is composed of an organic material, inorganic material and/or the like, and an organic fiber is preferably used. Preferred examples of the porous base material include woven fabrics and non-woven fabrics prepared

using organic fibers such as cellulose fibers, cellulose triacetate fibers, polyester fibers, polypropylene fibers and polyethylene fibers, among which non-woven fabrics are preferably used since their densities can be relatively easily controlled, they can be simply produced, and they are inexpensive.

5 [0044]

As the porous resin layer, which acts as a separation functional layer as mentioned above, an organic polymer membrane may be suitably used. Examples of the material of the organic polymer membrane include polyethylene resins, polypropylene resins, polyvinyl chloride resins, polyvinylidene difluoride resins, polysulfone resins, polyethersulfone resins, polyacrylonitrile resins, polyolefin resins, cellulose resins and cellulose triacetate resins, and the material may be a mixture of resins containing these resins as major components. Here, the major component means that the component is contained in an amount of not less than 50% by weight, preferably not less than 60% by weight. Among these, more preferred examples of the material of the porous membrane include those which can be easily formed by solutions and are excellent in physical durability and chemical resistance, such as polyvinyl chloride resins, polyvinylidene difluoride resins, polysulfone resins, polyethersulfone resins, polyacrylonitrile resins and polyolefin resins, among which polyvinylidene difluoride resins and resins containing these as major components are most preferably used.

20

[0045]

Here, as the polyvinylidene difluoride resin, a homopolymer of vinylidene fluoride is preferably used, and, other than a homopolymer of vinylidene fluoride, a copolymer with vinyl monomers capable of copolymerizing with vinylidene fluoride is also preferably used. Examples of the vinyl monomers capable of copolymerizing with vinylidene fluoride include tetrafluoroethylene, hexafluoropropylene and ethylene fluoride trichloride.

25

[0046]

Examples of the polyolefin resins include polyethylene, polypropylene, chlorinated polyethylene and chlorinated polypropylene, and chlorinated polyethylene is preferably used.

5 [0047]

An overview of the preparation method of the porous membrane used the present invention will now be described. First, on the surface of the above-mentioned porous base material, a coating of a starting solution containing the above-mentioned resin and a solvent is formed, while impregnating the starting
10 solution into the porous base material. Thereafter, only the coated surface of the porous base material having the coating is brought into contact with a coagulation bath containing a nonsolvent to coagulate the resin, while forming a porous resin layer on the surface of the porous base material. The nonsolvent may also be further contained in the starting solution. The temperature of the starting solution is
15 usually preferably selected within the range of 15 to 120°C in view of the film-forming property.

[0048]

To the starting solution, a pore-forming agent may be added. The pore-forming agent is extracted upon immersion in the coagulation bath, to make the resin
20 layer porous. Addition of the pore-forming agent allows regulation of the average pore size. The pore-forming agent preferably has a high solubility in the coagulation bath. Examples of the pore-forming agent which may be used include inorganic salts such as calcium chloride and calcium carbonate. Further examples of the pore-forming agent which may be used include polyoxyalkylenes such as
25 polyethylene glycol and polypropylene glycol; water-soluble macromolecular compounds such as polyvinyl alcohol, polyvinyl butyral and polyacrylic acid; and glycerin.

[0049]

The solvent dissolves the resin. It acts on the resin and the pore-forming agent to promote formation of a porous resin layer by these. Examples of the solvent which may be used include N-methylpyrrolidinone (NMP), N,N-dimethylacetamide (DMAc), N,N-dimethylformamide (DMF), dimethylsulfoxide (DMSO), acetone and methyl ethyl ketone. Among these, NMP, DMAc, DMF and DMSO, in which resins show high solubilities, may be preferably used.

[0050]

Further, a nonsolvent may also be added to the starting solution. A nonsolvent is a liquid which does not dissolve a resin. A nonsolvent has an action of regulating the rate of coagulation of a resin, to regulate the sizes of the pores. Examples of the nonsolvent which may be used include water and alcohols such as methanol and ethanol. Among these, water and methanol are preferred in view of the cost. The nonsolvent may also be a mixture of these.

[0051]

As mentioned above, the porous membrane used in the present invention is preferably a porous membrane formed by a porous base material and a porous resin layer. The porous base material may be either impregnated with the porous resin layer or not impregnated with the porous resin layer, which is selected depending on the use. The average thickness of the porous base material is preferably selected within the range of 50 μm to 3000 μm . In cases where the porous membrane is a hollow fiber membrane, the inner diameter of the hollow fiber is preferably selected within the range of 200 μm to 5000 μm , and the membrane thickness is preferably selected within the range of 20 μm to 2000 μm . A fabric or a knit produced by forming an organic fiber or an inorganic fiber into a cylindrical shape may be contained in the hollow fiber.

[0052]

The porous membrane used in the present invention may be made into a separation membrane element by combining it with a support. The form of the separation membrane element having a porous membrane is not restricted, and a separation membrane element wherein a supporting plate is used as the support and the porous membrane used in the present invention is placed on at least one side of the supporting plate is one preferred embodiment of the separation membrane element having the porous membrane used in the present invention. In cases where it is difficult to secure a large membrane area in this embodiment, placement of the porous membrane on the both sides of the supporting plate to increase the permeability is also a preferred embodiment.

[0053]

The average pore size of the porous membrane used in the present invention is not less than 0.01 μm and less than 1 μm . With an average pore size of the porous membrane within this range, a high blocking performance which does not allow leakage of cells and sludge and a high permeability can both be achieved, and further, clogging is less likely to occur, so that the permeability can be maintained with high accuracy and reproducibility for a long time. The average pore size of the porous membrane is preferably not more than 0.4 μm , and the operation can be more preferably carried out with an average pore size of less than 0.2 μm . In cases where the average pore size is too small, the permeability may decrease, so that the average pore size is not less than 0.01 μm , preferably not less than 0.02 μm , more preferably not less than 0.04 μm in the present invention. Here, the average pore size can be determined by measuring the diameters of all the pores which can be observed within an area of 9.2 $\mu\text{m} \times 10.4 \mu\text{m}$ under the scanning electron microscope at a magnification of 10,000 $\times$, and averaging the measured values.

[0054]

Further, the standard deviation σ of the average pore size is preferably not

more than 0.1 μm . Further, in cases where the standard deviation of the average pore size is small, that is, in cases where the pore sizes are uniform, a uniform permeate is more likely to be obtained and hence simple management of the fermentation operation is possible, so that the standard deviation of the average pore size is preferably as small as possible.

[0055]

The standard deviation σ of the average pore size is calculated according to (Equation 1) below wherein N represents the number of pores observable within the above-mentioned area of $9.2 \mu\text{m} \times 10.4 \mu\text{m}$, X_k represents the respective measured diameters, and $X(\text{ave})$ represents the average of the pore sizes.

[0056]

[Equation 1]

$$\sigma = \sqrt{\frac{\sum_{k=1}^N (X_k - X(\text{ave}))^2}{N}} \quad \cdots \text{ (Equation 1)}$$

[0057]

In the porous membrane used in the present invention, the permeability to culture medium is one of its important properties. As an index of the permeability, the pure water permeability coefficient of the porous membrane before use can be employed. In the present invention, the pure water permeability coefficient of the porous membrane is preferably not less than $2 \times 10^{-9} \text{ m}^3/\text{m}^2/\text{s}/\text{pa}$ when the amount of permeation is measured using purified water at a temperature of 25°C prepared by filtration through a reverse osmosis membrane, with a head height of 1 m, and in cases where the pure water permeability coefficient is from $2 \times 10^{-9} \text{ m}^3/\text{m}^2/\text{s}/\text{pa}$ to $6 \times 10^{-7} \text{ m}^3/\text{m}^2/\text{s}/\text{pa}$, an amount of permeation which is practically sufficient can be obtained.

[0058]

The membrane surface roughness in the porous membrane used in the present invention is a factor that affects clogging of the separation membrane, and, preferably, in cases where the membrane surface roughness is not more than $0.1\ \mu\text{m}$, the detachment coefficient and the membrane resistance of the separation membrane can be suitably suppressed, and hence continuous fermentation can be carried out with a lower transmembrane pressure difference. Therefore, since clogging can be suppressed to allow stable continuous fermentation, the membrane surface roughness is preferably as small as possible.

[0059]

Further, in cases where the membrane surface roughness is small, the shear force generated on the membrane surface during filtration of the microorganism can be expected to be small, and hence destruction of the microorganism may be suppressed and clogging of the porous membrane may be suppressed. Therefore, it is thought that stable filtration is possible for a long time.

[0060]

Here, the membrane surface roughness can be measured using the following atomic force microscope (AFM) under the following conditions.

•Device

Atomic force microscope (Nanoscope IIIa produced by Digital Instruments)

•Conditions

Probe: SiN cantilever (manufactured by Digital Instruments)

Scanning mode: Contact mode (measurement in air)

Underwater tapping mode (underwater measurement)

Scanning area: $10\ \mu\text{m} \times 10\ \mu\text{m}$, $25\ \mu\text{m} \times 25\ \mu\text{m}$ (measurement in air)

$5\ \mu\text{m} \times 5\ \mu\text{m}$, $10\ \mu\text{m} \times 10\ \mu\text{m}$ (underwater measurement)

Scanning resolution: 512×512

•Sample preparation

When the measurement was carried out, the membrane sample was soaked in ethanol at room temperature for 15 minutes and then soaked in RO water for 24 hours, followed by washing and drying it in the air.

[0061]

The membrane surface roughness (d_{rough}) is calculated according to the following (Equation 2) using the above AFM, based on the heights of the respective points in the direction of the z-axis.

[0062]

[Equation 2]

$$d_{\text{rough}} = \sum_{n=1}^N \frac{|Z_n - \bar{Z}|}{N} \cdots \text{(Equation 2)}$$

d_{rough} : Surface roughness (μm)

Z_n : Height in direction of z-axis (μm)

$\bar{Z}$: Average height (μm) in scanned area

N : Number of measured samples

[0063]

The transmembrane pressure difference during the filtration of a microorganism through a porous membrane in Step (A) in the present invention may be one with which the membrane is not easily clogged with the microorganism and medium components, and it is important to carry out the filtration with a transmembrane pressure difference within the range of 0.1 to 20 kPa. The transmembrane pressure difference is preferably within the range of 0.1 to 10 kPa, more preferably within the range of 0.1 to 5 kPa, still more preferably within the range of 0.1 to 2 kPa. In cases where the transmembrane pressure difference is not within the above-described range, clogging with the microorganism and medium components may rapidly occur and the amount of permeation may decrease, causing a trouble during the operation of continuous fermentation.

[0064]

In terms of the driving force of the filtration, a siphon using the liquid level difference (hydraulic head difference) between the fermentation culture medium and the permeate from the porous membrane may be used to generate the transmembrane pressure difference in the porous membrane. Further, as the driving force of the filtration, a suction pump may be placed in the permeate side of the porous membrane, or a pressure pump may be placed in the fermentation culture medium side of the porous membrane. The transmembrane pressure difference can be controlled by changing the liquid level difference between the fermentation culture medium and the permeate from the porous membrane. Further, in cases where a pump is used to generate the transmembrane pressure difference, the transmembrane pressure difference can be controlled by the suction pressure, and further, the transmembrane pressure difference can also be controlled by the pressure of the gas or liquid which is used for introducing the pressure from the fermentation culture medium side. In cases where such pressure control is carried out, the difference between the pressure in the fermentation culture medium side and the pressure in the permeate side of the porous membrane corresponds to the transmembrane pressure difference, and can be used for controlling the transmembrane pressure difference.

[0065]

The continuous fermentation apparatus used in Step (A) is not restricted as long as the above conditions are satisfied, and preferred examples thereof include the ones disclosed in Fig. 1 and Fig. 2 in WO2007/097260. Further, the porous membrane element for filtration of a fermentation culture medium is not restricted as long as the above conditions are satisfied, and preferred examples thereof include the ones disclosed in Fig. 3 and Fig. 4 in WO2007/097260.

[0066]

The fermentation feedstock used in the present invention is not restricted as

long as it promotes the growth of the microorganism having an ability of lactic acid fermentation to be cultured, to allow satisfactory production of the lactic acid of interest. Preferred examples of the fermentation feedstock include conventional liquid media containing carbon sources, nitrogen sources, inorganic salts, and, as
5 appropriate, organic micronutrients such as amino acids and vitamins, when necessary. Examples of the carbon sources include sugars such as glucose, sucrose, fructose, galactose and lactose; saccharified starch solutions containing these sugars; sweet potato molasses; sugar beet molasses; high test molasses; and further, organic acids such as acetic acid; alcohols such as ethanol; and glycerin. Examples of the
10 nitrogen sources include ammonia gas, aqueous ammonia, ammonium salts, urea and nitric acid salts; and other organic nitrogen sources used supplementarily such as oilcakes, soybean-hydrolyzed liquids, casein digests, other amino acids, vitamins, corn steep liquors, yeasts or yeast extracts, meat extracts, peptides such as peptones, and cells of various fermentation microorganisms and hydrolysates thereof.
15 Examples of the inorganic salts which may be added as appropriate include phosphoric acid salts, magnesium salts, calcium salts, iron salts and manganese salts. In cases where the microorganism having an ability of lactic acid fermentation used in the present invention requires particular nutrients for its growth, the nutrients may be added as preparations or natural products containing these. An anti-forming
20 agent may also be added as required. In the present invention, the culture medium means a liquid obtained as a result of growth of a microorganism having an ability of lactic acid fermentation in a fermentation feedstock, and the composition of the fermentation feedstock to be further added may be changed as appropriate from the composition of the fermentation feedstock used at the beginning of the culture, such
25 that the productivity of lactic acid is enhanced.

[0067]

In the continuous culture operation in Step (A), Batch culture or Fed-Batch

culture may be carried out at the initial phase of the culture to increase the microorganism concentration, followed by starting continuous culture (withdrawal), or the cells may be seeded at a high concentration and subjected to continuous culture from the beginning of the culture. It is possible to start supplying the feedstock medium and withdrawing the culture at appropriate timings. The timing of the start of supplying of the feedstock medium and the timing of the start of withdrawing of the culture are not necessarily the same. The supplying of the feedstock medium and the withdrawing of the culture may be carried out either continuously or intermittently. Nutrients as described above necessary for the growth of the cells may be added to the feedstock medium to allow continuous growth of the cells. The concentration of the microorganism in the culture medium is preferably maintained high within the range which does not cause death of the microorganism at a high rate due to an environment of the culture medium which is inappropriate for the growth of the microorganism, in view of achieving efficient production. For example, by maintaining the concentration at not less than 5 g/L in terms of dry weight, a good production efficiency can be obtained.

[0068]

Further, as required, the microorganism may be removed from the fermenter. For example, since, in cases where the microorganism concentration in the fermenter is too high, clogging of the porous membrane is likely to occur, the removal may be carried out in order to avoid the clogging. Further, since the productive performance for lactic acid may change depending on the microorganism concentration in the fermenter, the removal of the microorganism may be carried out using the productive performance as an index, to maintain the productive performance.

[0069]

The operation of continuous culture by allowing the growth of fresh cells

having an ability of lactic acid fermentation is usually preferably carried out in a single fermenter in view of control of the culture. However, the number of the fermenter(s) is not restricted as long as the continuous culture is carried out to produce the product while allowing the growth of cells. A plurality of fermenters may be used because of, for example, a small capacity of each fermenter. In this case, a high productivity of the fermentation product can be obtained even by continuous culture using a plurality of fermenters connected in parallel or in series through pipes.

[0070]

The filtration through a nanofiltration membrane in Step (B) will now be described.

[0071]

The nanofiltration membrane used in the present invention is also called a nanofilter (nanofiltration membrane, NF membrane), and generally defined as “a membrane that allows permeation of monovalent ions, but blocks divalent ions”. The membrane is considered to have fine voids having sizes of about several nanometers, and mainly used to block fine particles, molecules, ions and salts in water.

[0072]

The term “filtration using a nanofiltration membrane” means that the permeate of Step (A) is filtered through a nanofiltration membrane to block or separate inorganic salts dissolved or deposited as solids, while allowing a lactic acid solution to permeate as a filtrate. Here, the inorganic salts include any form of the inorganic salts contained in the culture medium, such as both those dissolved in the permeate of Step (A) and those deposited or precipitated in the permeate of Step (A).

[0073]

In Step (B), it is preferred to adjust the pH of the permeate of Step (A) to not

less than 2.0 and not more than 4.5. It is known that substances ionized in a solution are more likely to be removed or blocked by a nanofiltration membrane than non-ionized substances. Therefore, by adjusting the pH of the permeate of Step (A) to not more than 4.5, the ratio of lactic acid dissociated into lactate ions in the permeate becomes small, and this allows more efficient permeation of lactic acid. Further, in cases where the pH is less than 2.0, the nanofiltration may be damaged. Further, since pKa of lactic acid is 3.86, in cases where the pH is not more than 3.86, lactic acid that has not been dissociated into lactate ions and hydrogen ions is contained in the permeate of Step (A) in a larger amount, so that lactic acid can be efficiently allowed to permeate through the nanofiltration membrane, which is more preferred. The adjustment of the pH of the permeate of Step (A) may be carried out either when the microbial fermentation is carried out or after Step (A). Further, the pH may be adjusted by adding an inorganic or organic acid in cases where the pH of the permeate is to be made more acidic, or by adding an alkaline substance such as calcium hydroxide or aqueous ammonia in cases where the pH is to be made more alkaline.

[0074]

The permeate of Step (A) to be applied to the nanofiltration membrane of Step (B) is preferably prepared by adding an alkaline substance to the culture medium of Step (A) to maintain an optimum pH for microbial fermentation and filtering the obtained culture medium through a porous membrane. The microorganism is usually cultured at a pH of 4 to 8, at a temperature of 20 to 40°C. The alkaline substance to be added is not restricted, and a basic calcium salt is preferably added.

[0075]

In cases where Step (A) is a step of continuous fermentation in the presence of a calcium salt, Step (D), in which the calcium component in the permeate in Step

(A) is removed as an insoluble sulfate, may be introduced before Step (B). More particularly, for example, Step (D) is carried out by adding sulfuric acid to the permeate of Step (A) and precipitating/filtering the calcium component in the permeate of Step (A) as calcium sulfate, which is an insoluble sulfate. By allowing the filtrate (separated liquid containing lactic acid) to pass through the nanofiltration membrane of Step (B), the calcium component can be more efficiently removed or blocked. Examples of the basic calcium salts include calcium hydroxide, calcium carbonate, calcium phosphate, calcium oxide and calcium acetate, and the basic calcium salt is preferably calcium hydroxide. In cases where the calcium component in the permeate of Step (A) is precipitated/filtered as an insoluble sulfate, if the number of equivalents of the sulfuric acid added to the culture medium exceeds the number of equivalents of the calcium (number of equivalents of sulfuric acid > number of equivalents of calcium), the excess sulfuric acid partially permeates through the nanofiltration membrane. If this is followed by exposure of the permeate of Step (B) to a condition under heat such as concentration or distillation, the permeated sulfuric acid may act as a catalyst for promotion of oligomerization of lactic acid, resulting in decrease in the distillation yield. Therefore, in cases where the calcium component in the permeate of Step (A) is precipitated/filtered as an insoluble sulfate, the number of equivalents of the sulfuric acid added is preferably not more than the number of equivalents of the calcium component in the permeate of Step (A). In cases where the number of equivalents of the sulfuric acid added is adjusted based on the pH, the pH is preferably not less than 2.0 since, in this case, the number of equivalents of the sulfuric acid is not more than the number of equivalents of the calcium component.

[0076]

As a step preceding the above Step (D), Step (E), in which organic acids other than lactic acid are removed from the permeate of Step (A) while removing crystals

of calcium lactate, may be introduced. More particularly, the pH is adjusted by addition of basic calcium to the permeate of Step (A), and the resulting permeate is filtered through a nanofiltration membrane equivalent to the one used in Step (B), thereby collecting an aqueous solution containing calcium lactate from the feed side and removing organic acids including acetic acid from the permeate side.

[0077]

In Step (E), the pH of the permeate of Step (A) is preferably adjusted to not less than 6 and not more than 11. Since nanofiltration membranes have a property with which substances ionized (dissociated) in a solution are more likely to be blocked than non-ionized (undissociated) substances, by adjusting the pH of the culture medium to not less than 6, the ratio of lactic acid dissociated into ions in the culture medium (dissociated lactic acid/undissociated lactic acid) becomes higher than the ratio of acetic acid dissociated into ions (dissociated acetic acid/undissociated acetic acid). In this case, an aqueous solution containing calcium lactate can be efficiently collected from the feed side, and organic acids other than lactic acid can be efficiently separated from the permeate side. Further, in cases where the pH of the culture medium is higher than 11, durability of the nanofiltration membrane is adversely affected, which is not preferred.

[0078]

In Step (E), the organic acids other than lactic acid separated from the permeate side of the nanofiltration membrane are those derived from the permeate of Step (A) or from the fermentation feedstock, and acetic acid is preferably separated in the present invention.

[0079]

Examples of the basic calcium preferably added in Step (E) to adjust the pH of the permeate of Step (A) include calcium hydroxide, calcium carbonate, calcium phosphate, calcium oxide and calcium acetate in the forms of solids and aqueous

solutions, and the basic calcium is preferably calcium hydroxide. In cases where an aqueous solution is added, the concentration of the basic calcium is not restricted, and the basic calcium to be added may be in the form of a slurry having a concentration exceeding the saturation solubility.

5 [0080]

Examples of the method for evaluating the extents of removal, blocking and filtration of inorganic salts dissolved or deposited as solids by the nanofiltration membrane used in the present invention include an evaluation method by calculating the removal rates (blocking rates) of inorganic ions, but the method is not restricted to this method. The blocking rate (removal rate) of an inorganic salt can be calculated according to Equation 3 by measuring the concentration of the inorganic salt contained in the raw liquid (culture medium) (raw liquid inorganic salt concentration) and the concentration of the inorganic salt contained in the permeate (lactic acid solution) (permeate inorganic salt concentration) by an analysis represented by ion chromatography.

10

15

[0081]

Inorganic salt removal rate (%) = $(1 - (\text{permeate inorganic salt concentration} / \text{raw liquid inorganic salt concentration})) \times 100$... (Equation 3)

[0082]

20 The membrane separation performance of the nanofiltration membrane used in Step (B) is not restricted, and the ratio of the permeation rate of magnesium sulfate relative to the permeation rate of citric acid through the nanofiltration membrane is preferably not less than 3 at an operation pressure of 0.5 MPa, raw liquid temperature of 25°C and concentration in the raw liquid of 1000 ppm. In cases where the ratio

25 of the permeation rate of magnesium sulfate relative to the permeation rate of citric acid through the nanofiltration membrane under the above conditions is not less than 3, inorganic salts contained in the permeate of Step (A) can be removed and lactic

acid can be allowed to permeate efficiently, which is preferred. Here, the permeation rate of magnesium sulfate can be calculated according to Equation 4 by measuring the concentration of magnesium sulfate contained in the raw liquid (raw liquid magnesium sulfate concentration) and the concentration of magnesium sulfate contained in the permeate (permeate magnesium sulfate concentration) by an analysis represented by ion chromatography. Similarly, the permeation rate of citric acid can be calculated by replacing the magnesium sulfate concentration in Equation 4 with the citric acid concentration and measuring the concentration of citric acid contained in the raw liquid (raw liquid citric acid concentration) and the concentration of citric acid contained in the permeate (permeate citric acid concentration) by an analysis represented by high performance liquid chromatography.

[0083]

Magnesium sulfate permeation rate (%) = (permeate magnesium sulfate concentration)/(raw liquid magnesium sulfate concentration)×100 ... (Equation 4)

[0084]

Further, the permeation rate of magnesium sulfate is preferably not more than 1.5% at an operation pressure of 0.5 MPa, raw liquid temperature of 25°C and concentration in the raw liquid of 1000 ppm. In cases where the permeation rate of magnesium sulfate through the nanofiltration membrane is higher than 1.5% under the above conditions, concentration of the lactic acid solution permeated through the nanofiltration membrane may cause deposition of inorganic salts, and a distillation operation is likely to cause racemization and oligomerization due to the influence of the permeated inorganic salts and may decrease the distillation yield. More preferably, the permeation rate of magnesium sulfate through the nanofiltration membrane is not more than 1.0%.

[0085]

In addition, nanofiltration membranes having removal rates of sodium chloride (500 mg/L) of not less than 45% are preferably used. In terms of the permeation performance of the nanofiltration membrane, a nanofiltration membrane in which the permeation flow rate of sodium chloride (500 mg/L) per unit membrane area ($\text{m}^3/\text{m}^2/\text{day}$) at a filtration pressure of 0.3 MPa is not less than 0.5 and not more than 0.8 is preferably used. The permeation flow rate per unit membrane area (membrane permeation flux) can be evaluated by calculation according to Equation 5, by measuring the amount of the permeated liquid, collection time of the permeated liquid, and the membrane area.

[0086]

Membrane permeation flux ($\text{m}^3/\text{m}^2/\text{day}$) = amount of permeated liquid/membrane area/collection time ... (Equation 5)

[0087]

Examples of the material of the nanofiltration membrane which may be used in the present invention include macromolecular materials such as cellulose acetate polymers, polyamides, polyesters, polyimides and vinyl polymers. The membrane is not restricted to a membrane constituted by only one of the materials, and may be a membrane comprising plural membrane materials. In terms of the structure of the membrane, the membrane may be either an asymmetric membrane, which has a dense layer on at least one side of the membrane and micropores having pore sizes that gradually increase in the direction from the dense layer toward the inside of the membrane or the other side of the membrane, or a composite membrane, which has a very thin functional layer formed by another material on the dense layer of an asymmetric membrane. Examples of the composite membrane which may be used include the composite membrane described in JP 62-201606 A, which has a nanofilter composed of a polyamide functional layer on a support membrane comprising polysulfone as a membrane material.

[0088]

Among these, a composite membrane having a functional layer composed of a polyamide is preferred since it has a high pressure resistance, high permeability and high solute-removal performance, which make the membrane highly potential. For maintenance of durability against operation pressure, high permeability and high blocking performance, a membrane having a structure in which a polyamide is used as a functional layer, which layer is retained by a support comprising a porous membrane and a non-woven fabric, is suitable. Further, as a polyamide semipermeable membrane, a composite nanofiltration membrane having, on a support, a functional layer of a cross-linked polyamide obtained by polycondensation reaction between a polyfunctional amine and a polyfunctional acid halide is suitable.

[0089]

In the nanofiltration membrane having a functional layer composed of a polyamide, preferred examples of the carboxylic acid component of the monomers constituting the polyamide include aromatic carboxylic acids such as trimesic acid, benzophenone tetracarboxylic acid, trimellitic acid, pyromellitic acid, isophthalic acid, terephthalic acid, naphthalene dicarboxylic acid, diphenylcarboxylic acid and pyridinecarboxylic acid. In view of solubility to film-forming solvents, trimesic acid, isophthalic acid and terephthalic acid, and mixtures thereof are more preferred.

[0090]

Preferred examples of the amine component of the monomers constituting the polyamide include primary diamines having an aromatic ring, such as m-phenylenediamine, p-phenylenediamine, benzidine, methylene bis dianiline, 4,4'-diaminobiphenylether, dianisidine, 3,3',4'-triaminobiphenylether, 3,3',4,4'-tetraaminobiphenylether, 3,3'-dioxybenzidine, 1,8-naphthalenediamine, m(p)-monomethylphenylenediamine, 3,3'-monomethylamino-4,4'-diaminobiphenylether, 4,N,N'-(4-aminobenzoyl)-p(m)-phenylenediamine-2,2'-bis(4-

aminophenylbenzimidazole), 2,2'-bis(4-aminophenylbenzooxazole) and 2,2'-bis(4-aminophenylbenzothiazole); and secondary diamines such as piperazine, piperidine and derivatives thereof. Among these, a nanofiltration membrane having a functional layer composed of a cross-linked polyamide comprising piperazine or piperidine as monomers is preferably used since it has heat resistance and chemical resistance in addition to the pressure resistance and the durability. The polyamide more preferably contains as a major component the cross-linked piperazine polyamide or cross-linked piperidine polyamide and further contains a constituting component represented by the Chemical Formula (1), still more preferably contains a cross-linked piperazine polyamide as a major component and further contains a constituting component represented by the Chemical Formula (1). Further, preferably, in the Chemical Formula (1), $n=3$. Examples of the nanofiltration membrane having a functional layer composed of a polyamide containing a cross-linked piperazine polyamide as a major component and further containing a constituting component represented by the Chemical Formula (1) include the one described in JP 62-201606 A, and particular examples thereof include UTC60 manufactured by TORAY INDUSTRIES, INC., which is a cross-linked piperazine polyamide semipermeable membrane having a functional layer composed of a polyamide containing a cross-linked piperazine polyamide as a major component and further containing a constituting component represented by the Chemical Formula (1), wherein $n=3$.

[0091]

A nanofiltration membrane is generally used as a spiral-wound membrane element, and the nanofiltration membrane used in the present invention is also preferably used as a spiral-wound membrane element. Particular preferred examples of the nanofiltration membrane element include GEsepa, which is a cellulose acetate nanofiltration membrane manufactured by GE Osmonics; NF99 and

NF99HF, which are nanofiltration membranes having a functional layer composed of a polyamide, manufactured by Alfa-Laval; NF-45, NF-90, NF-200 and NF-400, which are nanofiltration membranes having a functional layer composed of a cross-linked piperazine polyamide, manufactured by Filmtec Corporation; and SU-210, SU-220, SU-600 and SU-610, which are nanofiltration membrane modules manufactured by TORAY INDUSTRIES, INC., having UTC60 manufactured by the same manufacturer, which has a functional layer composed of a polyamide containing a cross-linked piperazine polyamide as a major component and further containing a constituting component represented by the Chemical Formula (1). The nanofiltration membrane element is more preferably NF99 or NF99HF, which are nanofiltration membranes having a functional layer composed of a polyamide, manufactured by Alfa-Laval; NF-45, NF-90, NF-200 or NF-400, which are nanofiltration membranes having a functional layer composed of a cross-linked piperazine polyamide, manufactured by Filmtec Corporation; or SU-210, SU-220, SU-600 or SU-610, which are nanofiltration membrane modules manufactured by TORAY INDUSTRIES, INC., having UTC60 manufactured by the same manufacturer, which has a functional layer composed of a polyamide containing a cross-linked piperazine polyamide as a major component and further containing a constituting component represented by the Chemical Formula (1). The nanofiltration membrane element is still more preferably SU-210, SU-220, SU-600 or SU-610, which are nanofiltration membrane modules manufactured by TORAY INDUSTRIES, INC., having UTC60 manufactured by the same manufacturer, which has a functional layer composed of a polyamide containing a cross-linked piperazine polyamide as a major component and further containing a constituting component represented by the Chemical Formula (1).

[0092]

The filtration through a nanofiltration membrane in the Step (B) may be

carried out under pressure, and the filtration pressure is preferably within the range of 0.1 MPa to 8 MPa. In cases where the filtration pressure is less than 0.1 MPa, the membrane permeation rate may decrease, while in cases where the filtration pressure is more than 8 MPa, the membrane may be damaged. In cases where the membrane is used at a filtration pressure within the range of 0.5 MPa to 7 MPa, the membrane permeation flux is high, so that the lactic acid solution can be efficiently allowed to permeate and the possibility of damaging the membrane is small, which is more preferred. The membrane is especially preferably used at a filtration pressure within the range of 1 MPa to 6 MPa.

[0093]

The concentration of lactic acid in Step (B) is not restricted, and in cases where the concentration is high, the concentration of lactic acid contained in the permeate of Step (B) is also high, so that the length of time required for the concentration can be shortened, which is preferred in view of cost reduction.

[0094]

The concentrations of the inorganic salts in Step (B) are not restricted, and may be not less than the saturation solubility. That is, in cases where the concentration of an inorganic salt is not more than the saturation solubility, the inorganic salt is dissolved in the culture medium, and in cases where the concentration of the inorganic salt is not less than the saturation solubility, the inorganic salt is partially deposited. However, in Step (B), both inorganic salts dissolved in the permeate of Step (A) and inorganic salts deposited or precipitated in the permeate of Step (A) can be removed or blocked, so that lactic acid can be filtered without restriction by the concentrations of inorganic salts.

[0095]

The permeability of lactic acid through the nanofiltration membrane upon separation of lactic acid contained in the permeate of Step (A) by the above method

can be evaluated by calculating the lactic acid permeation rate. The lactic acid permeation rate can be calculated according to Equation 6 by measuring the concentration of lactic acid contained in the raw liquid (culture medium) (raw liquid lactic acid concentration) and the concentration of the lactic acid contained in the permeate (lactic acid-containing solution) (permeate lactic acid concentration) by an analysis represented by high performance liquid chromatography.

[0096]

Lactic acid permeation rate (%) = (permeate lactic acid concentration/raw liquid lactic acid concentration)×100 ... (Equation 6)

[0097]

In the method for producing lactic acid of the present invention, the permeate of Step (B) is further subjected to distillation in Step (C), to obtain lactic acid with high purity. The distillation step is carried out under a reduced pressure of not less than 1 Pa and not more than atmospheric pressure (normal pressure, about 101 kPa).

In cases where the step is carried out under a reduced pressure of not less than 10 Pa and not more than 30 kPa, the distillation temperature can be lower, which is more preferred. The distillation temperature in the cases where the step is carried out under reduced pressure is not less than 20°C and not more than 200°C, but, in cases where the distillation is carried out at a temperature of not less than 180°C, racemization of lactic acid may be caused by the influence of impurities. Therefore, the distillation of lactic acid may be preferably carried out at a temperature of not less than 50°C and not more than 180°C, more preferably not less than 60°C and not more than 150°C.

[0098]

Before subjecting to the Step (C), the permeate of Step (B) may once be concentrated using a concentrator such as an evaporator, or the permeate of Step (B) may be further subjected to Step (F), wherein the concentration of lactic acid is

increased by filtration through a reverse osmosis membrane. In view of reducing energy for the concentration, Step (F) to increase the concentration of lactic acid by filtration through a reverse osmosis membrane is preferably employed.

The reverse osmosis membrane herein means a filter for removing ions and/or low molecular-weight molecules using as a driving force a pressure difference larger than the osmotic pressure of the liquid to be treated, and examples thereof which can be used include cellulose membranes such as those made of cellulose acetate and membranes prepared by polycondensing a polyfunctional amine compound and a polyfunctional acid halide to provide a separation functional layer made of a polyamide on a microporous support membrane. In order to suppress dirt, that is, fouling, on the surface of the reverse osmosis membrane, a low-fouling reverse osmosis membrane, which is mainly for sewage treatment, may also be preferably employed, which reverse osmosis membrane is prepared by covering the surface of a separation functional layer made of a polyamide with an aqueous solution of a compound having at least one reactive group reactive with an acid halide group, thereby allowing acid halide groups remaining on the surface the separation functional layer to form covalent bonds with the reactive groups. Since most of the divalent calcium ions have been removed in Step (B) of the present invention, stable membrane concentration can be carried out without formation of scale on the surface of the reverse osmosis membrane.

[0099]

Examples of the reverse osmosis membrane preferably used in the present invention include composite membranes having a cellulose acetate polymer as a functional layer (hereinafter referred to as cellulose acetate reverse osmosis membranes) and composite membranes having a polyamide functional layer (hereinafter referred to as polyamide reverse osmosis membranes). Here, examples of the cellulose acetate polymer include polymers prepared with organic acid esters

of cellulose such as cellulose acetate, cellulose diacetate, cellulose triacetate, cellulose propionate and cellulose butyrate, which may be used solely, as a mixture, or as a mixed ester. Examples of the polyamide include linear polymers and cross-linked polymers constituted by aliphatic and/or aromatic diamine monomers.

5 [0100]

Examples of the form of the membrane which may be used as appropriate include the flat membrane, spiral-wound membrane and hollow fiber membrane.

[0101]

Particular examples of the reverse osmosis membrane used in the present invention include polyamide reverse osmosis membrane modules manufactured by
 10 TORAY INDUSTRIES, INC., such as low-pressure type modules SU-710, SU-720, SU-720F, SU-710L, SU-720L, SU-720LF, SU-720R, SU-710P and SU-720P, as well as high-pressure type modules SU-810, SU-820, SU-820L and SU-820FA containing UTC70 as the reverse osmosis membrane; cellulose acetate reverse osmosis
 15 membranes manufactured by the same manufacturer SC-L100R, SC-L200R, SC-1100, SC-1200, SC-2100, SC-2200, SC-3100, SC-3200, SC-8100 and SC-8200; NTR-759HR, NTR-729HF, NTR-70SWC, ES10-D, ES20-D, ES20-U, ES15-D, ES15-U and LF10-D manufactured by Nitto Denko Corporation; RO98pHt, RO99, HR98PP and CE4040C-30D manufactured by Alfa-Laval; GE Sepa manufactured by
 20 GE; and BW30-4040, TW30-4040, XLE-4040, LP-4040, LE-4040, SW30-4040 and SW30HRLE-4040 manufactured by FilmTec Corporation.

[0102]

[Lactic Acid]

The present inventors discovered that the lactic acid obtained by the above
 25 method for producing lactic acid contains only small amounts of impurities and hence the quality of the lactic acid is high enough to be used for production of a polylactic acid by direct polymerization. Further, the present inventors specified

the ranges of the contents of impurities with which high-quality lactide (raw material for polylactic acid) and polylactic acid can be obtained, thereby completing the present invention. The first feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, methanol at a concentration of not more than 70 ppm, preferably not more than 65 ppm, more preferably not more than 50 ppm, still more preferably not more than 30 ppm. The content of methanol in 90% aqueous lactic acid solution can be measured by gas chromatography (GC). In cases where the lactic acid has a content, in 90% aqueous lactic acid solution, of methanol of more than 70 ppm, the polylactic acid obtained by direct dehydration polycondensation of the lactic acid has a low weight average molecular weight and a low mechanical strength, which is not preferred. Further, in cases where lactic acid having a content of methanol of more than 70 ppm was used, the synthetic yield of lactide decreases, which is not preferred.

[0103]

The second feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, pyruvic acid at a concentration of not more than 500 ppm, preferably not more than 400 ppm, more preferably not more than 300 ppm. The content of pyruvic acid in 90% aqueous lactic acid solution can be measured by high performance liquid chromatography (HPLC). In cases where the lactic acid has a content, in 90% aqueous lactic acid solution, of pyruvic acid of more than 500 ppm, undesirable hue is obtained for polylactic acid produced by polymerization of the lactic acid. The hue of a polylactic acid can be evaluated based on the degree of coloration, and, as an index of the degree of coloration, the APHA unit color number may be used. The APHA unit color number (Hazen color number) is a value calculated according to the measurement method of JISK0071-1 (established on October 20, 1998). Further, in cases where lactic acid having a content of pyruvic acid of more than 500 ppm was

used, the synthetic yield of lactide decreases and the APHA unit color number increases, which are not preferred.

[0104]

The third feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, furfural at a concentration of not more than 15 ppm, preferably not more than 10 ppm, more preferably not more than 5 ppm. The content of furfural in 90% aqueous lactic acid solution can be measured by high performance liquid chromatography (HPLC). In cases where the lactic acid has a content, in 90% aqueous lactic acid solution, of furfural of more than 10 ppm, undesirable hue and thermal stability are obtained for polylactic acid produced by polymerization of the lactic acid. The thermal stability of a polylactic acid can be evaluated based on the thermal weight loss rate. Further, in cases where lactic acid having a content of furfural of more than 15 ppm was used, increase in the APHA unit color number occurs in the obtained lactide, which is not preferred.

[0105]

The fourth feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, 5-hydroxymethylfurfural at a concentration of not more than 15 ppm, preferably not more than 10 ppm, more preferably not more than 5 ppm. The content of 5-hydroxymethylfurfural in 90% aqueous lactic acid solution can be measured by high performance liquid chromatography (HPLC). Polylactic acid obtained by polymerization of lactic acid having a content, in 90% aqueous lactic acid solution, of 5-hydroxymethylfurfural of more than 10 ppm has undesirable hue and thermal stability. Further, in cases where lactic acid having a content of 5-hydroxymethylfurfural of more than 15 ppm was used, increase in the APHA unit color number occurs in the obtained lactide, which is not preferred.

[0106]

The fifth feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, methyl lactate at a concentration of not more than 600 ppm, preferably not more than 400 ppm, more preferably not more than 100 ppm. The content of methyl lactate in 90% aqueous lactic acid solution can be measured by gas chromatography (GC). In cases where the lactic acid has a content, in 90% aqueous lactic acid solution, of methyl lactate of more than 600 ppm, the polylactic acid obtained by direct dehydration polycondensation of the lactic acid has a low weight average molecular weight and a low mechanical strength, which is not preferred. Further, in cases where lactic acid having a content of methyl lactate of more than 600 ppm was used, increase in the APHA unit color number occurs in the obtained lactide, which is not preferred.

[0107]

The sixth feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, acetic acid at a concentration of not more than 500 ppm, preferably not more than 400 ppm, more preferably not more than 300 ppm. The content of acetic acid in 90% aqueous lactic acid solution can be measured by high performance liquid chromatography (HPLC). Polylactic acid obtained by polymerization of lactic acid having a content, in 90% aqueous lactic acid solution, of acetic acid of more than 500 ppm has undesirable thermal stability. Further, in cases where lactic acid having a content of acetic acid of more than 500 ppm was used, the synthetic yield of lactide decreases, which is not preferred.

[0108]

The seventh feature of the lactic acid of the present invention is that the lactic acid contains, as an impurity in 90% aqueous lactic acid solution, 2-hydroxybutyric acid at a concentration of not more than 500 ppm, preferably not more than 300 ppm,

more preferably not more than 200 ppm. The content of 2-hydroxybutyric acid in 90% aqueous lactic acid solution can be measured by high performance liquid chromatography (HPLC). Polylactic acid obtained by polymerization of lactic acid having a content, in 90% aqueous lactic acid solution, of 2-hydroxybutyric acid of more than 500 ppm has undesirable thermal stability. Further, in cases where lactic acid having a content of 2-hydroxybutyric acid of more than 500 ppm was used, the synthetic yield of lactide decreases, which is not preferred.

[0109]

The lactic acid of the present invention may be either one of the (L)-body or the (D)-body, or a mixture of the (L)-body and the (D)-body. In cases where the lactic acid is a mixture, the optical purity, which indicates the isomer content of the (L)-body or the (D)-body, is preferably not less than 90% since the melting point of the obtained polylactic acid is high in this case. The optical purity is more preferably not less than 95%, still more preferably not less than 99%, most preferably not less than 99.9%.

[0110]

A lactide produced by using the lactic acid of the present invention as a raw material and the method for producing the lactide; and a polylactic acid produced by using the lactic acid of the present invention as a raw material and the method for producing the polylactic acid; are also included in the present invention.

[0111]

[Lactide]

The lactide of the present invention includes L,L-lactide, D,D-lactide and D,L-lactide, which are composed of L-lactic acid and/or D-lactic acid. The lactide is preferably L,L-lactide or D,D-lactide.

[0112]

The method for producing the lactide is not restricted, and a conventional

method, in which lactic acid is heated under reduced pressure to produce lactic acid oligomers, which are then depolymerized by heating in the presence of a catalyst under reduced pressure, to cause conversion into lactide, may be preferably used.

The catalyst used for the depolymerization of lactic acid oligomers is not restricted, and is usually a catalyst having a metal selected from the group consisting of Group IA, Group IIIA, Group IVA, Group IIB, Group IVB and Group VA in the periodic table, or having a metal compound containing it.

[0113]

Examples of the catalyst having a metal belonging to Group IA include hydroxides of alkali metals (e.g., sodium hydroxide, potassium hydroxide and lithium hydroxide), salts between alkali metals and weak acids (e.g., sodium lactate, sodium acetate, sodium carbonate, sodium octylate, sodium stearate, potassium lactate, potassium acetate, potassium carbonate and potassium octylate), and alkoxides of alkali metals (e.g., sodium methoxide, potassium methoxide, sodium ethoxide and potassium ethoxide).

[0114]

Examples of the catalyst having a metal belonging to Group IIIA include aluminum ethoxide, aluminum isopropoxide, aluminum oxide and aluminum chloride.

[0115]

Examples of the catalyst having a metal belonging to Group IVA include organotin catalysts (tin lactate, tin tartrate, tin dicaprylate, tin dilaurate, tin dipalmitate, tin distearate, tin dioleate, tin α -naphthoate, tin β -naphthoate and tin octylate) as well as tin powder, tin oxide and tin halides.

[0116]

Examples of the catalyst having a metal belonging to Group IIB include zinc powder, zinc halides, zinc oxide, and organozinc compounds.

[0117]

Examples of the catalyst having a metal belonging to Group IVB include titanium compounds such as tetrapropyl titanate; and zirconium compounds such as zirconium isopropoxide.

5 [0118]

Examples of the catalyst having a metal belonging to Group VA include antimony compounds such as antimony trioxide; and bismuth compounds such as bismuth(III) oxide

[0119]

10 Among these, a catalyst having tin or a tin compound is preferred in view of the activity, and tin octylate is especially preferred.

[0120]

The amount of the catalyst to be used is about 0.01 to 20% by weight, preferably about 0.05 to 15% by weight, more preferably about 0.1 to 10% by weight, with respect to the lactic acid oligomers.

15 [0121]

The depolymerization reaction may be carried out using a conventional vertical reaction vessel, or may be carried out using a molecular still. Examples of the molecular still include those of the pot still type, the falling film type and the centrifugal type. The falling film type and centrifugal type apparatuses are continuous process apparatuses, and industrially widely used. A centrifugal type molecular still employs a method in which a film of a vaporized substance is expanded on a heated surface using the centrifugal force, and a falling film type molecular still employs a method in which a vaporized substance is allowed to flow down along a heated surface to form a thin film of the vaporized substance.

25 [0122]

The depolymerization temperature is set to 160 to 300°C, preferably 180 to

260°C, more preferably 190 to 250°C. In cases where the temperature is lower than 160°C, distillation of lactide is difficult, and a considerably high degree of vacuum is required. On the other hand, in cases where the temperature is higher than 300°C, racemization and coloration are likely to occur.

5 [0123]

The pressure inside the depolymerization apparatus is not more than the vapor pressure of lactide at the depolymerization temperature, and usually about 1 to 50 Torr. A lower pressure is preferred since, in this case, the heating temperature may be low. More particularly, the pressure is preferably 1 to 20 Torr, more preferably
10 1 to 10 Torr, still more preferably 1 to 5 Torr.

[0124]

The residence time in the depolymerization apparatus is preferably as short as possible in view of preventing racemization, and usually not more than 1 hour. Use of a molecular still is preferred since, in this case, the time may be not more than 10
15 minutes, preferably not more than 3 minutes, more preferably not more than 1 minute.

[0125]

The lactide produced by the method for producing lactide can be removed to the outside of the depolymerization reaction system as a vapor, and collected. The collection of lactide can be simply carried out using a condenser attached to the
20 depolymerization apparatus.

[0126]

[Polylactic Acid]

The polylactic acid of the present invention includes a homopolymer of L-lactic acid units or D-lactic acid units; a polylactic acid block copolymer constituted
25 by a segment composed of poly-L-lactic acid units and a segment composed of poly-D-lactic acid units; and a copolymer with monomers other than lactic acid. In cases where the polylactic acid is a copolymer, examples of the monomer units other than

lactic acid include glycol compounds such as ethylene glycol, propylene glycol, butanediol, heptanediol, hexanediol, octanediol, nonanediol, decanediol, 1,4-cyclohexanedimethanol, neopentyl glycol, glycerin, pentaerythritol, bisphenol A, polyethylene glycol, polypropylene glycol and polytetramethylene glycol; dicarboxylic acids such as oxalic acid, adipic acid, sebacic acid, azelaic acid, dodecanedioic acid, malonic acid, glutaric acid, cyclohexanedicarboxylic acid, terephthalic acid, isophthalic acid, phthalic acid, naphthalenedicarboxylic acid, bis(p-carboxyphenyl)methane, anthracenedicarboxylic acid, diphenyl ether dicarboxylic acid, sodium sulfoisophthalic acid and tetrabutyl phosphonium isophthalic acid; hydroxycarboxylic acids such as glycolic acid, hydroxypropionic acid, hydroxybutyric acid, hydroxyvaleric acid, hydroxycaproic acid and hydroxybenzoic acid; and lactones such as caprolactone, valerolactone, propiolactone, undecalactone and 1,5-oxepan-2-one. The amount of copolymerization of the above-described other copolymerization components is preferably 0 to 30 mol%, more preferably 0 to 10 mol% with respect to the total monomer components.

[0127]

The method for producing the polylactic acid is not restricted, and a conventional production method for polylactic acid may be used. Particular examples of the known method include the lactide method constituted by two steps, wherein lactide, which is a cyclic dimer, is first produced using lactic acid as a raw material, followed by performing ring-opening polymerization; and the direct polymerization method constituted by a single step, wherein the raw material is subjected to direct dehydration polycondensation in a solvent. Any of these methods may be used.

[0128]

In the lactide method and the direct polymerization method, the length of time required for the polymerization can be shortened by using a catalyst for the

polymerization reaction. Examples of the catalyst include metals such as tin, zinc, lead, titanium, bismuth, zirconium, germanium, antimony and aluminum, and derivatives thereof. The derivatives are preferably metal alkoxides, carboxylates, carbonates, oxides and halides. Particular examples thereof include tin chloride, tin acetate, tin octylate, zinc chloride, lead oxide, lead carbonate, titanium chloride, alkoxytitanium, germanium oxide and zirconium oxide. Among these, tin compounds are preferred, and tin acetate and tin octylate are more preferred.

[0129]

The polymerization reaction may be carried out in the presence of the above catalyst usually at a temperature of 100 to 200°C, although the temperature varies depending on the type of the catalyst. Further, in order to remove water produced by the polymerization reaction, the polymerization reaction is preferably carried out under reduced pressure, and the pressure is preferably not more than 7 kPa, more preferably not more than 1.5 kPa.

[0130]

For the polymerization reaction, a compound having two or more hydroxyl groups or amino groups in the molecule may be used as a polymerization initiator. Examples of the compound to be used as a polymerization initiator, which has two or more hydroxyl groups or amino groups in the molecule, include polyols such as ethylene glycol, propylene glycol, butanediol, hexanediol, octanediol, neopentyl glycol, diethylene glycol, triethylene glycol, polyethylene glycol, polypropylene glycol, glycerin, trimethylolpropane, pentaerythritol, dipentaerythritol, tripentaerythritol, sorbitol, poly(vinyl alcohol), poly(hydroxyethyl methacrylate) and poly(hydroxypropyl methacrylate); and polyvalent amines such as ethylenediamine, propylenediamine, butanediamine, hexanediamine, diethylenetriamine and melamine; among which polyols are more preferred.

[0131]

The amount of the polymerization initiator to be added is not restricted, and preferably 0.001 to 5 parts by weight, more preferably 0.01 to 3 parts by weight with respect to 100 parts by weight of the raw material used (L-lactic acid, D-lactic acid, L,L-lactide or D,D-lactide).

5 [0132]

In cases where the polylactic acid is produced by the direct polymerization method, the lactic acid used as a raw material needs to be highly pure, and the lactic acid of the present invention can be sufficiently applied to the direct polymerization method. The solvent used for the direct polymerization method is not restricted as long as it does not adversely affect the polymerization, and may be water or an organic solvent. Examples of the organic solvent include aromatic hydrocarbons. Examples of the aromatic hydrocarbons include toluene, xylene, naphthalene, chlorobenzene and diphenyl ether. In cases where the polylactic acid is produced by the direct polymerization method, by removing water produced by the condensation reaction to the outside of the system, the polymerization can be promoted. The method of removal to the outside of the system is preferably polymerization under reduced pressure, and the pressure is preferably not more than 7 kPa, more preferably not more than 1.5 kPa.

[0133]

20 The polylactic acid of the present invention characteristically has a weight average molecular weight of not less than 120000, a thermal weight loss rate of less than 6.5% under a nitrogen atmosphere at a constant temperature of 200°C with a heating time of 20 minutes, and an APHA unit color number of not more than 15. In cases where the weight average molecular weight of the polylactic acid is not less than 120000, preferably not less than 140000, the polylactic acid has an excellent mechanical strength; in cases where the thermal weight loss rate is less than 6.5%, preferably not more than 6.0%, the polylactic acid has an excellent thermal stability;

and in cases where APHA is not more than 15, preferably not more than 10, the polylactic acid has an excellent hue; so that the polylactic acid of the present invention that satisfies these physical properties is suitable for various uses such as fibers, films and molded articles.

5 EXAMPLES

[0134]

The present invention will now be described in more detail, but the present invention is not restricted to the Examples below.

[0135]

10 In the present invention, as a microorganism having an ability of L-lactic acid fermentation, *Saccharomyces cerevisiae* to which an L-lactate dehydrogenase gene (L-LDH gene) derived from *Xenopus laevis* having the base sequence shown in SEQ ID NO:1 was introduced to the chromosome was used.

[0136]

15 (Reference Example 1) Preparation of Yeast Strain Having Ability of L-Lactic Acid Fermentation

A strain bred from the B3 strain described in JP 2008-029329 A was used as a yeast strain having an ability of L-lactic acid fermentation. The method of breeding is described below.

20 [0137]

To the B3 strain, the L-LDH gene shown in SEQ ID NO:1 was introduced at the SED1 locus. For the introduction to the SED1 locus, PCR was carried out using pTRS102 described in JP 2008-029329 A as an amplification template, and oligonucleotides (SEQ ID NOs:2 and 3) as a primer set, to amplify a PCR fragment
25 of 1.3 kb containing the L-LDH gene derived from *Xenopus laevis* and the TDH3 terminator sequence. Here, SEQ ID NO:2 was designed such that the sequence corresponding to the sequence of 60 bp in the upstream of the initiation codon of the

SED1 gene was added.

[0138]

Subsequently, by PCR using the plasmid pRS423 as an amplification template, and oligonucleotides (SEQ ID NOs:4 and 5) as a primer set, a PCR
5 fragment of about 1.3 kb containing the HIS3 gene, which is a yeast selection marker, was amplified. Here, SEQ ID NO:5 was designed such that the sequence corresponding to the sequence of 60 bp in the downstream of the stop codon of the SED1 gene was added.

[0139]

10 Each DNA fragment was separated by 1% agarose gel electrophoresis and purified according to a conventional method. PCR was carried out using a mixture of the obtained two types of fragments of about 1.3 kb as an amplification template, and oligonucleotides (SEQ ID NOs:2 and 5) as a primer set, to amplify a PCR
15 fragment of about 2.6 kb in which the L-LDH gene derived from *Xenopus laevis*, the TDH3 terminator and the HIS3 gene are linked together and the sequences corresponding to the sequences of 60 bp in the upstream/downstream of the SED1 gene were added to the 5'-end and 3'-end, respectively.

[0140]

20 The above DNA fragment was separated by 1% agarose gel electrophoresis and purified according to a conventional method. The B3 strain was transformed with the DNA fragment and cultured in a histidine-free medium, to select a transformant in which the L-LDH gene derived from *Xenopus laevis* was introduced to the downstream of the SED1 gene promoter in the chromosome.,

[0141]

25 Confirmation of the fact that the thus obtained transformant is yeast having the L-LDH gene derived from *Xenopus laevis* introduced to the downstream of the SED1 gene promoter in the chromosome was carried out as follows. The genomic

DNA of the transformant was prepared using the genomic DNA extraction kit Dr. GenTLE (manufactured by TAKARA BIO INC.), and PCR was then carried out using the prepared genomic DNA as an amplification template, and oligonucleotides (SEQ ID NOs:6 and 7) as a primer set, to confirm whether an amplified DNA
5 fragment of about 2.9 kb was obtained. In the non-transformed strain, an amplified DNA fragment of about 1.4 kb is obtained by the above PCR. The transformant having the L-LDH gene derived from *Xenopus laevis* introduced to the downstream of the SED1 gene promoter in the chromosome is hereinafter referred to as the B4 strain.

10 [0142]

Subsequently, the yeast SW015 strain described in JP 2008-48726 A, having a temperature-sensitive mutation in the *pdc5* gene, was mated with the B4 strain obtained as described above, to obtain diploid cells. The diploid cells were cultured in an ascus formation medium to allow ascus formation. Asci were dissected using
15 a micromanipulator to obtain the respective haploid cells, which were then studied for auxotrophy. Among the obtained haploid cells, a strain having the L-LDH gene derived from *Xenopus laevis*, which is inserted in the PDC1, SED1 and TDH3 loci, and the temperature-sensitive mutation in the PDC5 gene (nonviable at 34°C) was obtained, and the respective mating types MAT α and MAT a were selected. Among
20 the obtained yeast strains, the one having the mating type of MAT a was designated the SU014-8A strain, and the one having the mating type of MAT α was designated the SU014-3B strain .

[0143]

Subsequently, the lysine auxotrophy of the SU014-8A strain was restored.
25 Using the genomic DNA of BY4741 manufactured by Funakoshi Corporation as a template, and oligonucleotides (SEQ ID NOs:8 and 9) as a primer set, PCR was carried out to amplify a PCR fragment of about 2 kb corresponding to the first half of

the LYS2 gene. The above PCR fragment was separated by 1% agarose gel electrophoresis and purified according to a conventional method. The SU014-8A strain was transformed with the PCR fragment, to cancel the amber mutation of the LYS2 gene. By culturing the resultant in a lysine-free medium, a transformant having a restored lysine synthetic capacity was selected.

[0144]

Confirmation of the fact that the thus obtained transformant is yeast in which the amber mutation of the LYS2 gene was canceled was carried out as follows. First, the obtained transformant was mated with the 20GY77 strain having the wild-type LYS2 gene, to obtain diploid cells. The diploid cells were cultured in an ascus formation medium to allow ascus formation. Asci were dissected using a micromanipulator to obtain the respective haploid cells, which were then studied for auxotrophy. It was confirmed that all the obtained haploid cells have the lysine synthetic capacity. In cases where the lysine synthetic capacity was restored without cancellation of the mutation of LYS2, cells which do not have the lysine synthetic capacity are obtained among the haploid cells obtained as described above. The strain obtained by the restoration of the lysine synthetic capacity of the SU014-8A strain is hereinafter referred to as HI001.

[0145]

Subsequently, the leucine auxotrophy of the SU014-3B strain was restored. Using pRS425 as a template, and oligonucleotides (SEQ ID NOs:10 and 11) as a primer set, PCR was carried out to amplify a PCR fragment of the LEU2 gene of about 2 kb. The above PCR fragment was separated by 1% agarose gel electrophoresis and purified according to a conventional method. The SU014-3B strain was transformed with the PCR fragment, to cancel the mutation of the LEU2 gene. By culturing the resultant in a leucine-free medium, a transformant having a restored leucine synthetic capacity was selected.

[0146]

Confirmation of the fact that the thus obtained transformant is yeast in which the mutation of the LEU2 gene was canceled was carried out as follows. First, the obtained transformant was mated with the 20GY7 strain having the wild-type LEU2 gene, to obtain diploid cells. The diploid cells were cultured in an ascus formation medium to allow ascus formation. Asci were dissected using a micromanipulator to obtain the respective haploid cells, which were then studied for auxotrophy. It was confirmed that all the obtained haploid cells have the leucine synthetic capacity. In cases where the leucine synthetic capacity was restored without cancellation of the mutation of the LEU2 gene, cells which do not have the leucine synthetic capacity are obtained among the haploid cells obtained as described above. The strain obtained by the restoration of the leucine synthetic capacity of the SU014-3B strain is hereinafter referred to as HI002.

[0147]

Subsequently, the thus obtained HI001 strain and HI002 strain were mated with each other to obtain a diploid prototrophic strain, which does not have auxotrophy. The obtained strain is hereinafter referred to as the HI003 strain.

[0148]

Lactic acid was confirmed by measuring the amount of lactic acid by HPLC under the following conditions.

[0149]

Column: Shim-Pack SPR-H (manufactured by Shimadzu Corporation)

Mobile phase: 5 mM p-toluenesulfonic acid (flow rate: 0.8 mL/min.)

Reaction solution: 5 mM p-toluenesulfonic acid, 20 mM Bis-Tris, 0.1 mM

EDTA 2Na (flow rate: 0.8 mL/min.)

Detection method: electric conductivity

Temperature : 45°C

[0150]

Measurement of the optical purity of L-lactic acid or D-lactic acid was carried out by HPLC under the following conditions.

[0151]

5 Column: TSK-gel Enantio L1 (manufactured by Tosoh Corporation)

Mobile phase: 1 mM aqueous copper sulfate solution

Flow rate: 1.0 ml/min.

Detection method: UV 254 nm

Temperature : 30°C

10 [0152]

The optical purity of lactic acid was calculated by the following equation.

[0153]

Optical purity (%) = $100 \times (L-D) \text{ or } (D-L)/(L+D)$

(wherein L represents the concentration of L-lactic acid, and D represents the
15 concentration of D-lactic acid).

[0154]

(Reference Example 2) Production of L-Lactic Acid by Batch Fermentation

Using the HI003 strain prepared in Reference Example 1 and a raw material
sugar medium (70 g/L Yutosei (manufactured by MUSO Co., Ltd.)), a batch
20 fermentation test was carried out. The medium was autoclaved (121°C, 15 minutes)
before use. Evaluation of the concentration of lactic acid, which is the product, was
carried out using HPLC shown in Reference Example 1, and the glucose
concentration was measured using Glucose Test Wako C (manufactured by Wako
Pure Chemical Industries, Ltd.). The operating conditions of the batch fermentation
25 apparatus of Reference Example 2 were as shown below:

[0155]

Fermenter capacity (amount of lactic acid fermentation medium), 2 (L); temperature

adjustment, 32 (°C); ventilation volume for fermenter, 0.1 (L/min.); stirring rate of fermenter, 200 (rpm); pH adjustment, adjusted to pH 5 with 1 N calcium hydroxide.
[0156]

First, the HI003 strain was cultured in 5 ml of the raw material sugar medium in a test tube overnight with shaking (pre-preculture). The pre-preculture medium was inoculated to 100 ml of a fresh raw material sugar medium and subjected to culture in a 500 ml Sakaguchi flask for 24 hours with shaking (preculture). Temperature adjustment and pH adjustment were carried out, and fermentation culture was performed. As a result of the batch fermentation for 50 hours, the concentration of accumulated lactic acid was 45 to 49 g/L, and the optical purity was 99.9% for L-lactic acid.

[0157]

(Reference Example 3) Continuous Fermentation Process

Using the HI003 strain prepared in Reference Example 1, continuous fermentation of lactic acid was carried out with the culture apparatus shown in Fig. 1. Removal of the permeate from the membrane separation vessel was carried out using a Masterflex pump. As a medium, a raw material sugar medium (70 g/L Yutosei (manufactured by MUSO Co., Ltd.), 1.5 g/L ammonium sulfate) was used. This raw material sugar medium was autoclaved at a temperature of 121°C for 15 minutes at a high pressure (2 atm) before use. As a porous membrane element member, a molded article made of stainless steel and a polysulfone resin was used, and, as a porous membrane, a hollow fiber membrane prepared by the method described in Reference Example 13 of WO2007/097260 was used. The operating conditions were as follows.

[0158]

Capacity of culture reactor: 20 (L)

Volume of culture medium in culture reactor: 15 (L)

Porous membrane used: PVDF filtration membrane

Effective filtration area of membrane separation element: 2800 cm^2

Temperature adjustment: $32 \text{ (}^\circ\text{C)}$

Ventilation volume for culture reactor: air, 1 (L/min.)

5 Stirring rate of culture reactor: 800 (rpm)

pH adjustment: adjusted to pH 5 with 5 N calcium hydroxide

Sterilization: 121°C , 0.2 MPa , 20 min. , for all of the culture reactor including porous membrane element, and medium used

Removal rate of culture medium: $0.16 \text{ m}^3/\text{m}^2/\text{d}$

10 [0159]

Removal of culture medium by a Masterflex pump was started 50 hours after the initiation of the culture, and the culture was continued until 500 hours after the initiation of the culture. The results of measurement of the concentration of lactic acid, which is the product, and the lactic acid production rate are shown in Fig. 2.

15 The lactic acid concentration was measured by the method shown in Reference Example 1, and the lactic acid production rate was calculated using the Equation 7 below.

[0160]

Lactic acid production rate (g/L/hr)

20 = concentration of lactic acid accumulated in removed liquid (g/L) $\times$
removal rate of fermentation liquid (L/hr) / operational liquid volume of apparatus
(L) $\cdots$ (Equation 7)

[0161]

25 As a result, the transmembrane pressure difference did not exceed 1 kPa and stable operation was possible, without causing clogging of the membrane. The average lactic acid production rate during the period from 50 hours to 500 hours after the initiation of the culture was 6 g/L/h . Lactic acid obtained from the permeate of

the porous membrane during the period from 400 hours to 500 hours after the initiation of the culture was used in the subsequent Examples (lactic acid concentration: 52 g/L, L-lactic acid optical purity: 99.9%).

[0162]

5 (Reference Example 4) Evaluation of Permeability of Magnesium Sulfate through Nanofiltration Membrane

To 10 L of ultrapure water, 10 g of magnesium sulfate (manufactured by Wako Pure Chemical Industries, Ltd.) was added, and the resulting mixture was stirred at 25°C for 1 hour, to prepare 1000 ppm aqueous magnesium sulfate solution.

10 Subsequently 10 L of the prepared aqueous magnesium sulfate solution was fed to the raw liquid tank 13 of the membrane filtration apparatus shown in Fig. 3. As the 90φ nanofiltration membrane indicated by the symbol 19 in Fig. 4, a cross-linked piperazine polyamide nanofiltration membrane “UTC60” (nanofiltration membrane 1, manufactured by TORAY INDUSTRIES, INC.), a cross-linked piperazine
15 polyamide nanofiltration membrane “NF-400” (nanofiltration membrane 2, manufactured by Filmtec Corporation), a polyamide nanofiltration membrane “NF99” (nanofiltration membrane 3, manufactured by Alfa-Laval) or a cellulose acetate nanofiltration membrane “GEsepa” (nanofiltration membrane 4, manufactured by GE Osmonics) was placed in a cell made of stainless steel
20 (SUS316). The raw liquid temperature was adjusted to 25°C, and the pressure of the high-pressure pump 15 was adjusted to 0.5 MPa, to collect the permeate 16. The concentrations of magnesium sulfate contained in the raw liquid tank 13 and the permeate 16 were analyzed by ion chromatography (manufactured by Dionex Corporation) under the following conditions, thereby calculating the permeation rate
25 of magnesium sulfate.

[0163]

Anion; column (AS4A-SC (manufactured by Dionex Corporation)), eluent

(1.8 mM sodium carbonate/1.7 mM sodium hydrogen carbonate), temperature (35°C).

[0164]

Cation; column (CS12A (manufactured by Dionex Corporation)), eluent (20 mM methanesulfonic acid), temperature (35°C).

5 [0165]

The results are shown in Table 1.

[0166]

[Table 1]

	Trade name (Manufacturer's Name)	Membrane material	Filtration pressure (MPa)	Concentration of magnesium sulfate in raw liquid (ppm)	Concentration of magnesium sulfate in permeate (ppm)	Permeation rate of magnesium sulfate (%)
Nanofiltration membrane 1	UTC60 (TORAY INDUSTRIES, INC.)	Cross-linked piperazine polyamide	0.5	1000	2	0.2
Nanofiltration membrane 2	NF-400 (Filmtec Corporation)	Cross-linked piperazine polyamide	0.5	1000	20	2
Nanofiltration membrane 3	NF99 (Alfa-Laval)	Polyamide	0.5	1000	20	2
Nanofiltration membrane 4	GEsepa (GE Osmonics)	Cellulose acetate	0.5	1000	30	3

[0167]

(Reference Example 5) Evaluation of Permeability of Citric Acid through
Nanofiltration Membrane

To 10 L of ultrapure water, 10 g of citric acid (manufactured by Wako Pure
5 Chemical Industries, Ltd.) was added, and the resulting mixture was stirred at 25°C
for 1 hour, to prepare 1000 ppm aqueous citric acid solution. Subsequently, the
permeates from the nanofiltration membranes 1 to 4 were collected under the same
conditions as in Reference Example 3. The concentrations of citric acid contained
in the raw liquid tank 13 and the permeate 16 were analyzed by high performance
10 liquid chromatography (manufactured by Shimadzu Corporation) under the
following conditions, thereby calculating the permeation rate of citric acid and the
permeation rate of citric acid/permeation rate of magnesium sulfate.

[0168]

Column: Shim-Pack SPR-H (manufactured by Shimadzu Corporation);
15 mobile phase: 5 mM p-toluenesulfonic acid (flow rate: 0.8 mL/min.); reaction
solution: 5 mM p-toluenesulfonic acid, 20 mM Bis-Tris, 0.1 mM EDTA·2Na (flow
rate: 0.8 mL/min.); detection method: electric conductivity; temperature : 45°C.

[0169]

The results are shown in Table 2.

20 [0170]

[Table 2]

	Trade name (Manufacturer's Name)	Membrane material	Filtration pressure (MPa)	Concentration of citric acid in raw liquid (ppm)	Concentration of citric acid in permeate (ppm)	Permeation rate of citric acid (%)	Permeation rate of citric acid / permeation rate of magnesium sulfate
Nanofiltration membrane 1	UTC60 (TORAY INDUSTRIES, INC.)	Cross-linked piperazine polyamide	0.5	1000	180	18	70
Nanofiltration membrane 2	NF-400 (Filmtec Corporation)	Cross-linked piperazine polyamide	0.5	1000	140	14	7
Nanofiltration membrane 3	NF99 (Alfa-Laval)	Polyamide	0.5	1000	160	16	8
Nanofiltration membrane 4	GEsepa (GE Osmonics)	Cellulose acetate	0.5	1000	60	6	2

[0171]

(Reference Examples 6 to 12) Permeation Test of Lactic Acid Fermentation Culture Medium through Nanofiltration Membrane

From the culture medium (2L) obtained as in Reference Example 2, cells
5 were removed by centrifugation, and concentrated sulfuric acid (manufactured by Wako Pure Chemical Industries, Ltd.) was then added dropwise to the culture medium to a pH of 1.9 (Reference Example 6), 2.0 (Reference Example 7), 2.2 (Reference Example 8), 2.6 (Reference Examples 9 to 11) or 4.0 (Reference Example 12), followed by stirring the resulting mixture for 1 hour at 25°C, thereby converting
10 calcium lactate in the culture medium into lactic acid and calcium sulfate.

Subsequently, precipitated calcium sulfate was separated by filtering precipitates using qualitative filter paper No. 2 (manufactured by ADVANTEC) by suction filtration, and 2 L of the filtrate was collected.

[0172]

15 Subsequently, 2 L of each filtrate obtained as described above was injected into the raw liquid tank 13 of the membrane filtration apparatus shown in Fig. 3. As the 90φ nanofiltration membrane indicated by the symbol 19 in Fig. 4, each of the nanofiltration membranes 1 to 4 was placed in a cell made of stainless steel (SUS316). In each case, the pressure of the high-pressure pump 15 was adjusted to
20 4 MPa to collect the permeate 16. The concentrations of the sulfate ions and the calcium ions contained in the raw liquid tank 13 and the permeate 16 were analyzed by ion chromatography (manufactured by Dionex Corporation) under the same conditions as in Reference Example 4, and the lactic acid concentration was analyzed
25 by high performance liquid chromatography (manufactured by Shimadzu Corporation) under the same conditions as in Reference Example 1. The results are shown in Table 3.

[0173]

[Table 3]

	Nanofiltration membrane	pH	Membrane permeation flux ($\text{m}^3/\text{m}^2/\text{d}$)	Calcium ion concentration			Sulfate ion concentration			Lactic acid concentration		
				Raw liquid (mg/L)	Permeate (mg/L)	Removal rate (%)	Raw liquid (mg/L)	Permeate (mg/L)	Removal rate (%)	Raw liquid (mg/L)	Permeate (mg/L)	Removal rate (%)
Reference Example 5	1	1.9	2.54	557	0.8	99.9	1678	428	74.5	45	22.9	50.9
Reference Example 6	1	2	2.54	557	0.8	99.9	1678	428.3	74.5	45	22.9	50.9
Reference Example 7	1	2.2	2.5	811	0.8	99.9	1165	133	88.6	48	24.5	51
Reference Example 8	1	2.6	2.5	1497	1.3	99.9	918	24	97.4	48	24.9	51.9
Reference Example 9	2	2.6	2.12	1497	4.8	99.7	918	26.8	97.1	48	21.2	44.2
Reference Example 10	3	2.6	2.08	1497	6.7	99.6	918	24.3	97.4	48	21.9	45.6
Reference Example 11	4	2.6	1.48	1497	2.1	99.9	918	1.8	99.8	48	21	43.8
Reference Example 12	1	4	2.51	4909	2.9	99.9	402	7.9	98	49	20.9	42.7

[0174]

As shown in Table 3, it was revealed that calcium sulfate was removed with high efficiency at all the pHs. It was further revealed that the permeation rate of lactic acid and the membrane permeation flux were highest with the nanofiltration
5 membrane 1.

[0175]

(Examples 1 to 5) Production Examples of Lactic Acid

To 200 L of the permeate of a porous membrane, which was obtained in Reference Example 3, concentrated sulfuric acid (manufactured by Wako Pure
10 Chemical Industries, Ltd.) was added dropwise to a pH of 1.9 (Example 1), 2.0 (Example 2), 2.2 (Example 3), 2.6 (Example 4) or 4.0 (Example 5), followed by stirring the resulting mixture for 1 hour at 25°C, thereby converting calcium lactate in the culture medium into lactic acid and calcium sulfate. Subsequently, precipitated calcium sulfate was separated by filtering precipitates using qualitative
15 filter paper by suction filtration, and 200 L each of the filtrates was collected.

[0176]

Subsequently, 200 L of each filtrate obtained in the above Examples was injected into the raw liquid tank 13 of the membrane filtration apparatus shown in Fig. 3. The 4-inch nanofiltration module 2 ("UTC60" manufactured by TORAY
20 INDUSTRIES, INC.) of the nanofiltration membrane 1, which showed the highest lactic acid permeation rates in Reference Examples 6 to 12, was placed in a special vessel, and the operation was carried out by adjusting the pressure of the high-pressure pump 15 to 4 MPa, to collect the permeate at each pH. The concentrations of the sulfuric acid ions and the calcium ions contained in the raw liquid tank 13 and
25 the permeate 16 were analyzed by ion chromatography (manufactured by Dionex Corporation) under the same conditions as in Reference Example 4, and the lactic acid concentration was analyzed by high performance liquid chromatography

(manufactured by Shimadzu Corporation) under the same conditions as in Reference Example 1. As a result, it was revealed that calcium sulfate was removed with high efficiency at all the pHs, as in Reference Examples 6 to 12.

[0177]

5 Thereafter, 100 L each of the permeates of the nanofiltration membrane was concentrated by distillation of water using a flash evaporator (manufactured by TOKYO RIKAKIKAI) under reduced pressure (50 hPa). At this time, deposition of calcium sulfate was not observed.

[0178]

10 Thereafter, distillation was carried out under a reduced pressure of 133 Pa at 130°C. To confirm racemization of the distilled lactic acid, the optical purity was measured before and after the distillation, by high performance liquid chromatography. The results are shown in Table 4.

[0179]

15 The obtained purified lactic acid was used for the direct polymerization test in Example 6 and the lactide synthesis test in Example 7, and lactic acid before the distillation was used for the direct polymerization test in Comparative Example 2 and the lactide synthesis test in Comparative Example 3.

[0180]

20 (Comparative Example 1) Production Example of Lactic Acid

 To 200 L of the membrane permeate obtained as in Reference Example 3, concentrated sulfuric acid (manufactured by Wako Pure Chemical Industries, Ltd.) was added dropwise to a pH of 2.0, followed by stirring the resulting mixture for 1 hour at 25°C, thereby converting calcium lactate in the culture medium into lactic
25 acid and calcium sulfate. Subsequently, precipitated calcium sulfate was separated by filtering precipitates using qualitative filter paper by suction filtration, and 200 L of the filtrate was collected. The concentration of calcium sulfate contained in the

filtrate was analyzed by ion chromatography, and the concentration was revealed to be 549 mg/L. Thus, it was revealed that calcium sulfate had not been removed sufficiently.

[0181]

Thereafter, 100 L of the filtrate was concentrated by distillation of water using a flash evaporator under reduced pressure (50 hPa), and this caused deposition of calcium sulfate that had not been removed by the above-described quality filter paper. Subsequently, distillation was carried out under reduced pressure at 133 Pa, at 130°C. To confirm racemization of the distilled lactic acid, the optical purity of lactic acid was measured before and after the distillation, by high performance liquid chromatography under the same conditions as in Reference Example 1. As a result, decrease in the optical purity was observed. Further, in the distillation residue, partially oligomerized lactic acid was observed, and the distillation yield decreased to 30%. These results are shown in Table 4, together with the results of purification through the nanofiltration membrane.

[0182]

[Table 4]

	Optical purity (%)		Distillation yield (%)
	Before distillation	After distillation	
Example 1	99.9	99.9	60
Example 2	99.9	99.9	81
Example 3	99.9	99.9	84
Example 4	99.9	99.9	88
Example 5	99.9	99.9	92
Comparative Example 1	99.9	94.0	30

[0183]

(Example 6) Direct Polymerization Test for Lactic Acid

In a reaction vessel having a stirrer, 150 g of the lactic acid obtained in Example 2 was heated at 800 Pa at 160°C for 3.5 hours, to obtain oligomers. Subsequently, 0.12 g of tin (II) acetate (manufactured by Kanto Chemical Co., Ltd.)

and 0.33 g of methanesulfonic acid (manufactured by Wako Pure Chemical Industries, Ltd.) were added to the oligomers, and the resulting mixture was heated at 500 Pa at 180°C for 7 hours, to obtain a prepolymer. The prepolymer was then crystallized by heating in an oven at 120°C for 2 hours. The obtained prepolymer was pulverized using a hammer mill, and made to pass through a sieve, to obtain pulverulent bodies having an average particle size of 0.1 mm. In the solid phase polymerization step, 150 g of the prepolymer was taken, and fed into an oven to which an oil rotary pump was connected, thereby performing vacuum heat treatment. The pressure was set to 50 Pa, and the heating temperature was set to: 140°C for 10 hours; 150°C for 10 hours; and 160°C for 20 hours. The obtained polylactic acid was subjected to weight average molecular weight analysis with GPC (manufactured by Tosoh Corporation), melting point analysis with DSC (manufactured by SII NanoTechnology Inc.) and thermal weight loss rate analysis with TG (manufactured by SII NanoTechnology Inc.).

[0184]

(Weight Average Molecular Weight Analysis of Polylactic Acid)

The weight average molecular weight (Mw) of the polylactic acid produced by the polymerization is a value of the weight average molecular weight in terms of the standard polymethyl methacrylate measured by gel permeation chromatography (GPC). The GPC measurement was carried out using HLC8320GPC (manufactured by Tosoh Corporation) as a GPC system, and two TSK-GEL SuperHM-M columns (manufactured by Tosoh Corporation) in series. The detection was carried out using a differential refractometer. In terms of the conditions for the measurement, the flow rate was 0.35 mL/min., hexafluoroisopropanol was used as a solvent, and 0.02 mL of a solution with a sample concentration of 1 mg/mL was injected.

[0185]

(Analysis of Melting Point of Polylactic Acid)

The melting point of the polylactic acid produced by the polymerization is a value measured with the differential scanning calorimeter DSC7020 (manufactured by SII NanoTechnology Inc.), and the measurement was carried out with 10 mg of a sample, under nitrogen atmosphere at a heating rate of 20°C/min.

5 [0186]

(Analysis of Thermal Weight Loss Rate of Polylactic Acid)

The thermal weight loss rate of the polylactic acid produced by the polymerization was measured using the thermo gravimetry differential thermal analyzer TG/DTA7200 (manufactured by SII NanoTechnology Inc.). The measurement was carried out with 10 mg of a sample, under nitrogen atmosphere at a constant temperature of 200°C for a heating time of 20 minutes.

[0187]

(Analysis of Degree of Coloration of Polylactic Acid)

In 9.5 g of chloroform, 0.5 g of the polylactic acid produced by the polymerization was dissolved, and the degree of coloration was analyzed using a colorimeter (manufactured by NIPPON DENSHOKU INDUSTRIES CO., LTD.) as an APHA unit color number.

[0188]

The polylactic acid obtained by direct polymerization of lactic acid had a weight average molecular weight of 155000, melting point of 165°C, thermal weight loss rate of 5% and degree of coloration of APHA 10.

[0189]

(Comparative Example 2) Test for Direct Polymerization of Lactic Acid

The lactic acid before the distillation in Example 2 was concentrated with a rotary evaporator to 90% by weight, to obtain 150 g of concentrated lactic acid. Direct polymerization was carried out under the same conditions as in Example 6. The polylactic acid obtained by the direct polymerization had a weight average

molecular weight of 85000, melting point of 160°C, thermal weight loss rate of 15% and degree of coloration of APHA 50. Thus, the quality of the lactic acid was poorer than that of the lactic acid obtained by Example 6, for all the evaluation items. [0190]

5 (Example 7) Test for Synthesis of Lactide

In a reaction vessel having a stirrer, 150 g of the lactic acid obtained in Example 2 was concentrated by heating under atmospheric pressure at 135°C for 30 minutes. Subsequently, under reduced pressure (4500 to 6500 Pa), the liquid temperature was increased in a stepwise manner to 135°C (20 minutes), 150°C (20 minutes) and 160°C (20 minutes), to obtain oligomers. Thereafter, 0.75 g of tin (II) octylate (Nacalai Tesque) was added to the oligomers, and simple distillation was carried out under reduced pressure (1000 to 2000 Pa) at 200°C for 2 hours, to distill lactide. In order to avoid clogging of pipes, the temperature of the condenser was set to 110°C. A lactide fraction was obtained in an amount of 92.3 g. The yield of lactide was 85.4% based on the starting L-lactic acid. [0191]

(Analysis of Chemical Purity of Lactide)

The chemical purity of the synthesized lactide (ratio of LL-lactide in the recovered lactide) was analyzed with the gas chromatography GC2010 (manufactured by Shimadzu Corporation). As a column, the capillary column RT BDEXM (manufactured by RESTEK) was used, and the measurement conditions were: carrier gas (He) flow rate, 69.2 mL/min.; vaporizing chamber temperature, 230°C; column temperature, 150°C; detector (FID) temperature, 230°C; and split ratio, 50. From the peak area ratios of LL-lactide, DD-lactide and DL-lactide, the chemical purity of LL-lactide was calculated. [0192]

(Analysis of Degree of Coloration of Lactide)

Into 20 g of acetone, 6 g of the synthesized lactide was completely dissolved, and the degree of coloration was analyzed using a colorimeter (manufactured by NIPPON DENSHOKU INDUSTRIES CO., LTD.) as an APHA unit color number.
[0193]

5 As a result, the obtained lactide had a chemical purity of 96.2% and degree of coloration of APHA 2.

[0194]

(Comparative Example 3) Test for Synthesis of Lactide

10 The lactic acid before the distillation in Example 2 was concentrated with a rotary evaporator to 90% by weight, to obtain 150 g of concentrated lactic acid. Lactide was synthesized under the same conditions as in Example 7. The lactide was obtained in an amount of 79.1 g in a yield of 73.2%, and had a chemical purity of 93.1% and degree of coloration of APHA 12. Thus, both the yield and the quality of the lactic acid were poorer than those of the lactic acid obtained by
15 Example 7.

[0195]

(Example 8) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

20 Into a reaction vessel having a stirrer, 50 g of the lactide obtained in Example 7 and 0.05 g of stearyl alcohol were fed, and the atmosphere inside of the system was replaced with nitrogen, followed by heating the resulting mixture at 190°C to dissolve the lactide. Subsequently, 0.025 g of tin (II) octylate was added thereto, and polymerization was carried out at 190°C for 2 hours. The obtained polylactic acid was analyzed for its weight average molecular weight, melting point, thermal
25 weight loss rate and degree of coloration by the methods described in Example 6. The weight average molecular weight was 135000; the melting point was 165°C; the thermal weight loss rate was 5.1%; and the degree of coloration was APHA 5.

[0196]

(Comparative Example 4) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization of lactide by the same procedure as in Example 8 except that 50 g of the lactide obtained in Comparative Example 3 was used. The obtained polylactic acid had a weight average molecular weight of 109000, melting point of 162°C, weight loss rate of 6.3 % and degree of coloration of APHA 11. Thus, the quality of the polylactic acid was poorer than that of the polylactic acid obtained by Example 8, for all the evaluation items.

[0197]

(Example 9) Analysis of Impurities in Lactic Acid

Three liters of filtrate obtained in the same manner as in Example 3 was filtered through the nanofiltration membrane module SU-610 (manufactured by TORAY INDUSTRIES, INC.) at an operating pressure of 2.0 MPa, to remove impurities. The aqueous lactic acid solution which had permeated through the nanofiltration membrane module was concentrated using the reverse osmosis membrane module SU-810 (manufactured by TORAY INDUSTRIES, INC.), and further concentrated by distillation of water using a rotary evaporator (manufactured by TOKYO RIKAKIKAI) under reduced pressure (50 hPa), thereby obtaining 80% aqueous lactic acid solution. Subsequently, distillation was carried out under a reduced pressure of 133 Pa at 133°C, to obtain 500 g of lactic acid.

[0198]

(Analysis of Impurities in Lactic Acid)

To the lactic acid obtained as described above, pure water was added to prepare 90% aqueous lactic acid solution. Impurities contained were analyzed by HPLC (high performance liquid chromatography) or GC (gas chromatography) under the following conditions. The results of the analysis are shown in Table 5.

[0199]

(Analysis of Acetic Acid, Pyruvic Acid and 2-Hydroxybutyric Acid by HPLC)

Column: Shim-Pack SPR-H (manufactured by Shimadzu Corporation);

mobile phase: 5 mM p-toluenesulfonic acid (flow rate: 0.8 mL/min.); reaction

5 solution: 5 mM p-toluenesulfonic acid, 20 mM Bis-Tris, 0.1 mM EDTA · 2Na (flow rate: 0.8 mL/min.); detection method: electric conductivity; temperature : 45°C.

[0200]

(Analysis of Furfural and HMF by HPLC)

Column: Synergie HydroRP (manufactured by Phenomenex, Inc.); mobile

10 phase: 5% aqueous acetonitrile solution (flow rate 1.0 mL/min.); detection method: UV (283 nm); temperature : 40°C.

(Analysis of Methanol and Methyl Lactate by GC Method)

Column: DB-5 (0.25 mm × 30 m, manufactured by J&W); column

temperature: 50°C to 250°C (8°C/min.); inlet temperature: 250°C; carrier gas:

15 helium; carrier pressure: 65 kPa.

[0201]

As shown in table 5, the concentrations of all the impurities other than acetic acid and pyruvic acid were 0 ppm (below the detection limit).

[0202]

20 [Table 5]

Name of impurity	Content in 90% lactic acid
Methanol	0 ppm
Acetic acid	200 ppm
Pyruvic acid	200 ppm
2-Hydroxybutyric acid	0 ppm
Furfural	0 ppm
5-Hydroxymethylfurfural	0 ppm
Methyl lactate	0 ppm

[0203]

(Example 10) Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

In a reaction vessel having a stirrer, 150 g of the 90% aqueous lactic acid solution in Example 9 was heated at 800 Pa at 160°C for 3.5 hours, to obtain
5 oligomers. Subsequently, 0.12 g of tin (II) acetate (manufactured by Kanto Chemical Co., Ltd.) and 0.33 g of methanesulfonic acid (manufactured by Wako Pure Chemical Industries, Ltd.) were added to the oligomers, and the resulting mixture was heated at 500 Pa at 180°C for 7 hours, to obtain a prepolymer. The prepolymer was then crystallized by heating in an oven at 120°C for 2 hours. The
10 obtained prepolymer was pulverized using a hammer mill, and made to pass through a sieve, to obtain pulverulent bodies having an average particle size of 0.1 mm. In the solid phase polymerization step, 150 g of the prepolymer was taken, and fed into an oven to which an oil rotary pump was connected, thereby performing vacuum heat treatment. The pressure was set to 50 Pa, and the heating temperature was set to:
15 140°C for 10 hours; 150°C for 10 hours; and 160°C for 20 hours. The weight average molecular weight, melting point, thermal weight loss rate and degree of coloration of the obtained polylactic acid were analyzed by the methods described in Example 6.

[0204]

20 (Example 11) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective
25 components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 30 ppm methanol, 100 ppm formic acid, 200 ppm

pyruvic acid, 100 ppm 2-hydroxybutyric acid, 3 ppm furfural, 2 ppm 5-hydroxymethylfurfural and 100 ppm methyl lactate.

[0205]

(Example 12) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization
5 of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution
10 obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0206]

15 (Comparative Example 5) Analysis of Impurities in Lactic Acid and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective
20 components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 100 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

25 [0207]

(Comparative Example 6) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic

Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 600 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0208]

(Comparative Example 7) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 25 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0209]

(Comparative Example 8) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was

used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 25 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0210]

(Comparative Example 9) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 650 ppm methyl lactate.

[0211]

(Comparative Example 10) Analysis of Impurities in Lactic Acid, Test for Direct Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their

concentrations were adjusted to 70 ppm methanol, 750 ppm 2-hydroxybutyric acid and 500 ppm methyl lactate.

[0212]

(Comparative Example 11) Analysis of Impurities in Lactic Acid, Test for Direct
5 Polymerization of Lactic Acid, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization and analyzed in the same manner as in Example 10 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective
10 components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 600 ppm acetic acid and 300 ppm pyruvic acid.

[0213]

The weight average molecular weights, melting points, thermal weight loss
15 rates and degrees of coloration APHA of the polylactic acids obtained in Examples 10 to 12 and Comparative Examples 5 to 11 are shown in Table 6. In Examples 10 to 12, polylactic acids having excellent physical properties for the weight average molecular weight, thermal weight loss rate and degree of coloration were obtained. However, in Comparative Example 5, the weight average molecular weight was
20 small and hence the mechanical strength was low, and the thermal weight loss rate was high and hence the thermal stability was low; in Comparative Examples 6 to 9, the thermal weight loss rate was high and the degree of coloration was high; and in Comparative Examples 10 and 11, the thermal weight loss rate was high. From these results, it was revealed that, in cases where the amounts of the impurities in
25 lactic acid are not more than predetermined values, polylactic acid having excellent thermal stability, mechanical strength and hue can be obtained.

[0214]

(Example 13) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

In a reaction vessel having a stirrer, 150 g of the lactic acid obtained in Example 9 was concentrated under heat at 135°C under atmospheric pressure for 30 minutes. Subsequently, under reduced pressure (4500 to 6500 Pa), the liquid temperature was increased in a stepwise manner to 135°C (20 minutes), 150°C (20 minutes) and 160°C (20 minutes), to obtain oligomers. Thereafter, 0.75 g of tin (II) octylate (Nacalai Tesque) was added to the oligomers, and simple distillation was carried out under reduced pressure (1000 to 2000 Pa) at 200°C for 2 hours, to distill lactide. In order to avoid clogging of pipes, the temperature of the condenser was set to 110°C. A lactide fraction was obtained in an amount of 93.3 g. The yield of lactide was 87.2% based on the starting L-lactic acid.

[0215]

(Example 14) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 30 ppm methanol, 100 ppm formic acid, 200 ppm pyruvic acid, 100 ppm 2-hydroxybutyric acid, 3 ppm furfural, 2 ppm 5-hydroxymethylfurfural and 100 ppm methyl lactate.

[0216]

(Example 15) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was

prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0217]

(Comparative Example 12) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 100 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0218]

(Comparative Example 13) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 600 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm

methyl lactate.

[0219]

(Comparative Example 14) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

5 Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100
10 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 25 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0220]

(Comparative Example 15) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

15 Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in
20 Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 25 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 350 ppm methyl lactate.

[0221]

25 (Comparative Example 16) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was synthesized in the same manner as in Example 13 except that 150

g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 65 ppm methanol, 100 ppm formic acid, 300 ppm acetic acid, 300 ppm pyruvic acid, 150 ppm 2-hydroxybutyric acid, 5 ppm furfural, 5 ppm 5-hydroxymethylfurfural and 650 ppm methyl lactate.

[0222]

(Comparative Example 17) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was synthesized in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 70 ppm methanol, 750 ppm 2-hydroxybutyric acid and 500 ppm methyl lactate.

[0223]

(Comparative Example 18) Analysis of Impurities in Lactic Acid, and Evaluation of Physical Properties of Lactide

Lactide was produced by polymerization in the same manner as in Example 13 except that 150 g of an aqueous lactic acid solution was used, which aqueous lactic acid solution was prepared by adding the respective components, among the impurities contained in the 90% aqueous lactic acid solution obtained in Example 9, to the lactic acid obtained in Example 9 such that their concentrations were adjusted to 600 ppm acetic acid and 300 ppm pyruvic acid.

[0224]

The yields and the degrees of coloration APHA of the lactides obtained in

Examples 13 to 15 and Comparative Examples 12 to 18 are shown in Table 6. In Examples 13 to 15, excellent results were obtained for the yield of lactide and the degree of coloration. However, in Comparative Examples 12 to 18, the yield was less than 80%; and in Comparative Examples 13 to 15, wherein large amounts of pyruvic acid, furfural and the like were contained, the degree of coloration was high. From these results, it was revealed that, in cases where the amounts of the impurities in lactic acid are not more than predetermined values, lactide showing a high yield and a low degree of coloration can be obtained.

[0225]

(Example 16) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Into a reaction vessel having a stirrer, 50 g of the lactide obtained in Example 13 and 0.05 g of stearyl alcohol were fed, and the atmosphere inside of the system was replaced with nitrogen, followed by heating the resulting mixture at 190°C to dissolve the lactide. Subsequently, 0.025 g of tin (II) octylate was added thereto as a catalyst, and polymerization was carried out at 190°C for 2 hours. The obtained polylactic acid was analyzed for its weight average molecular weight, melting point, thermal weight loss rate and degree of coloration by the methods described in Example 6.

[0226]

(Example 17) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Example 14 was used.

[0227]

(Example 18) Production of Polylactic Acid by Polymerization Using Lactide as

Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Example 15 was used.

5 [0228]

(Comparative Example 19) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Comparative Example 12 was used.

10

[0229]

(Comparative Example 20) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Comparative Example 13 was used.

15

[0230]

(Comparative Example 21) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Comparative Example 14 was used.

20

[0231]

(Comparative Example 22) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

25

Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in

Comparative Example 15 was used.

[0232]

(Comparative Example 23) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

5 Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Comparative Example 16 was used.

[0233]

(Comparative Example 24) Production of Polylactic Acid by Polymerization Using
10 Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

 Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Comparative Example 17 was used.

[0234]

15 (Comparative Example 25) Production of Polylactic Acid by Polymerization Using Lactide as Raw Material, and Evaluation of Physical Properties of Polylactic Acid

 Polylactic acid was produced by polymerization of lactide, and analyzed, by the same procedure as in Example 16 except that 50 g of the lactide obtained in Comparative Example 18 was used.

20 [0235]

 The weight average molecular weights, melting points, thermal weight loss rates and degrees of coloration APHA of the polylactic acids obtained in Examples 16 to 18 and Comparative Examples 19 to 25 are shown in Table 6. In Examples 16 to 18, polylactic acids having excellent physical properties for the weight average
25 molecular weight, thermal weight loss rate and degree of coloration were obtained. However, in Comparative Examples 19 and 20, the weight average molecular weight was small. Further, in Comparative Examples 20 to 22, the weight loss rate was

high and the degree of coloration was high; and in Comparative Examples 23 to 25, the weight loss rate was high.

[0236]

[Table 6]

Lactic acid		Example 10	Example 11	Example 12	Comparative Example 5	Comparative Example 6	Comparative Example 7	Comparative Example 8	Comparative Example 9	Comparative Example 10	Comparative Example 11
Impurity contents (ppm)	Methanol	0	30	65	100	65	65	65	65	70	0
	Acetic acid	200	200	300	300	300	300	300	300	0	600
	Pyruvic acid	200	200	300	300	600	300	300	300	200	200
	2-Hydroxybutyric acid	0	100	150	150	150	150	150	150	750	0
	Furfural	0	3	5	5	5	5	25	5	0	0
	5-	0	2	5	5	5	25	5	5	0	0
	Hydroxymethylfurfural										
	Methyl lactate	0	100	350	350	350	350	350	650	500	0
	Weight average molecular weight (Mw)	175000	156000	145000	115000	128000	153000	144000	118000	149000	161000
	Melting point (°C)	167	165	164	163	164	165	163	162	162	165
Evaluation of direct polymerization	Weight loss rate (%)	4.9	5.5	5.9	6.7	8.5	8.6	7.9	6.5	6.5	6.7
	Degree of coloration (APHA)	7	10	15	16	25	40	20	25	7	8
		Example 13	Example 14	Example 15	Comparative Example 12	Comparative Example 13	Comparative Example 14	Comparative Example 15	Comparative Example 16	Comparative Example 17	Comparative Example 18
		85	81	80	78	73	75	76	75	77	75
Evaluation of lactide	Yield (%)	2	2	6	8	12	10	10	10	6	6
	Degree of coloration (APHA)										
		Example 16	Example 17	Example 18	Comparative Example 19	Comparative Example 20	Comparative Example 21	Comparative Example 22	Comparative Example 23	Comparative Example 24	Comparative Example 25
		135000	133000	122000	118000	109000	124000	123000	130000	129000	131000
Results of evaluation of polymerization	Weight average molecular weight (Mw)										
	Melting point (°C)	165	164	162	162	162	163	162	163	162	163
	Weight loss rate (%)	5.1	5.3	6.2	6.0	6.3	7.4	7.0	7.2	7.5	7.3
	Degree of coloration (APHA)	5	6	8	8	11	14	12	9	8	9

INDUSTRIAL APPLICABILITY

[0237]

The lactic acid obtained by the method of the present invention for producing lactic acid can be suitably used for food and pharmaceuticals, and as a monomer material for polylactic acid, which is a biodegradable general-purpose plastic.

Further, polylactic acid obtained by using the lactic acid as a raw material has excellent thermal stability, mechanical strength and hue, so that the polylactic acid is suitable for various uses such as fibers, films and molded articles.

DESCRIPTION OF SYMBOLS

[0238]

1. Fermentation reactor
2. Membrane separation vessel
3. Separation membrane element
4. Gas supplying apparatus
5. Stirrer
6. Hydraulic head difference controlling apparatus
7. Culture medium supplying pump
8. pH adjustment solution supplying pump
9. pH sensor/controlling apparatus
10. Fermentation liquid circulating pump
11. Level sensor
12. Temperature controller
13. Raw liquid tank
14. Cell equipped with nanofiltration membrane or reverse osmosis membrane
15. High-pressure pump
16. Flow of membrane permeate
17. Flow of membrane concentrate

18. Flow of culture medium sent by high-pressure pump
19. Nanofiltration membrane
20. Supporting plate

CLAIMS

1. A method for producing lactic acid, said method comprising the Steps (A) to (C) below:

5 (A) a step of continuous fermentation wherein a fermentation culture medium of a microorganism having an ability of lactic acid fermentation is filtered through a porous membrane having an average pore size of not less than 0.01 μm and less than 1 μm with a transmembrane pressure difference within the range of 0.1 to 20 kPa, and the permeate is collected, while retaining the non-permeated liquid in or
10 returning the non-permeated liquid to the culture medium, and adding a fermentation feedstock to the culture medium;

(B) a step of filtering the permeate obtained in Step (A) through a nanofiltration membrane; and

(C) a step of distilling the permeate obtained in Step (B) under a pressure of
15 not less than 1 Pa and not more than atmospheric pressure, at not less than 25°C and not more than 200°C to recover lactic acid.

2. The method for producing lactic acid according to claim 1, wherein the pH of the permeate obtained in said Step (A) is adjusted to not less than 2 and not more than 4.5, followed by providing the permeate for said Step (B).

20 3. The method for producing lactic acid according to claim 1 or 2, wherein said Step (A) is a step of continuous fermentation in the presence of a calcium salt, and a solution containing lactic acid obtained after Step (D), in which the calcium component in the permeate obtained in the Step (A) is removed as an insoluble sulfate, is provided for said Step (B).

25 4. The method for producing lactic acid according to any one of claims 1 to 3, wherein the ratio of the permeation rate of magnesium sulfate relative to the permeation rate of citric acid through said nanofiltration membrane is not less than 3


at an operation pressure of 0.5 MPa, raw liquid temperature of 25°C and concentration in the raw liquid of 1000 ppm.

5. The method for producing lactic acid according to any one of claims 1 to 4, wherein the permeation rate of magnesium sulfate through said nanofiltration membrane is not more than 1.5% at an operation pressure of 0.5 MPa, raw liquid temperature of 25°C and concentration in the raw liquid of 1000 ppm.

6. The method for producing lactic acid according to any one of claims 1 to 5, wherein the membrane material of said nanofiltration membrane comprises a polyamide.

7. The method for producing lactic acid according to claim 6, wherein said polyamide comprises a cross-linked piperazine polyamide as a major component and further comprises a constituting component represented by Chemical Formula 1:

[Chemical Formula 1]



Chemical Formula 1

(wherein R represents -H or -CH₃; and n represents an integer of 0 to 3).

8. A method for producing lactide, wherein lactic acid obtained by the method for producing lactic acid according to any one of claims 1 to 7 is used as a raw material.

9. A method for producing a polylactic acid, wherein lactide obtained by the method for producing lactide according to claim 8 is polymerized.

10. A method for producing a polylactic acid, wherein lactic acid obtained by the method for producing lactic acid according to any one of claims 1 to 7 is polymerized by direct dehydration polycondensation.

11. Lactic acid whose 90% aqueous solution contains methanol at a concentration

of not more than 70 ppm, pyruvic acid at a concentration of not more than 500 ppm, furfural at a concentration of not more than 15 ppm, 5-hydroxymethylfurfural at a concentration of not more than 15 ppm, methyl lactate at a concentration of not more than 600 ppm, acetic acid at a concentration of not more than 500 ppm and 2-

5 hydroxybutyric acid at a concentration of not more than 500 ppm.

12. The lactic acid according to claim 11, having an optical purity of not less than 90%.

13. Lactide obtained by using the lactic acid according to claim 11 or 12 as a raw material.

10 14. A polylactic acid obtained by using the lactic acid according to claim 11 or 12 or the lactide according to claim 13 as a raw material.

15. A polylactic acid obtained by direct dehydration polycondensation using the lactic acid according to claim 11 or 12 as a raw material.

09088sequence listing.txt
SEQUENCE LISTING

<110> Toray Industries, Inc.

<120> Manufacturing process for lactatic acid and poly lactatic acid

<130> 09088

<160> 11

<170> PatentIn version 3.1

<210> 1

<211> 999

<212> DNA

<213> Xenopus laevis

<400> 1

atggcaactg tgaaggataa actcatccac aatgtggtca aggaggagtc gctccccag	60
aacaagggtca ccattgtggg tgtgggggccc gtgggcatgg cctgtgccat cagtgtcctg	120
cagaaggatt tggcagatga gcttgcactt gttgatgtga tagaagacaa actgaagggg	180
gaaatgatgg atctccagca tggcagtctg ttccttcgta cccccaagat tgtctcaggg	240
aaagattaca gcgtcactgc aaactccaag ctggtagtgtg tgacggccgg ggcccgtcag	300
caggagggag agagtcgcct gaatctgggt cagcgcaatg tcaacatctt caaattcatc	360
attcccaaca ttgtcaagta cagccccaac tgcacctgc tcatcgtctc caaccagtg	420
gacattctga catatgtggc ctggaagatc agtggattcc ccaaaaaccg tgtcattggc	480
agcggctgca atttggactc tgcccgtttc cgttacctca tggggcagaa gtttgggagc	540
cacaccaga gctgccacgg ttgggtcatt ggggaacacg gagactcgag tgtgccagtg	600
tggagtgggg tgaatgtggc tggcgtgtcc ctgaaaacc tgcacccga tattgggagt	660
gacgcagaca aggagaactg gaaggaggtg cacaagcagg ttgtggacag cgcctatgaa	720
gtgatcaagc tgaagggtc caccctctgg gctattggcc tgtccgtagc tgacctgtct	780
gagagtatcc tgaagaacct ccgccgagtc catccattt ccacaatggt caagggcatg	840
tacggcgtga ataatgatgt tttcctcagt gtcccctgtg tgttgggcaa cttgggcatc	900
acagacgtgg ttaacatgac gctgaaggca gatgaagagg atcgcttacg caagagcgca	960
gacaccctgt gggccatcca gaaggagctg cagttctag	999

<210> 2

<211> 85

<212> DNA

<213> Artificial

<220>

<223> primer

<400> 2

tattgattta tagtcgtaac tacaaagaca agcaaaataa aatacgttcg ctctattaag	60
atggcaactg tgaaggataa actca	85

<210> 3

09088sequence listing.txt

```

<211> 20
<212> DNA
<213> Artificial

<220>
<223> primer

<400> 3
aggcgtatca cgaggccctt                20

<210> 4
<211> 60
<212> DNA
<213> Artificial

<220>
<223> primer

<400> 4
gaattaattc ttgaagacga aagggcctcg tgatacgctt agattgtact gagagtgcac        60

<210> 5
<211> 80
<212> DNA
<213> Artificial

<220>
<223> primer

<400> 5
aaaaaataac ataatactga aagaaagcat taagaaggcg gatgtgtcaa acaccaccgt        60
ctgtgcggta tttcacaccg                80

<210> 6
<211> 20
<212> DNA
<213> Artificial

<220>
<223> primer

<400> 6
tagattggcc gtaggggctg                20

<210> 7
<211> 20
<212> DNA
<213> Artificial

<220>
<223> primer

<400> 7
cacgcaacgc gtaagaaaca                20

<210> 8
<211> 24
<212> DNA
<213> Artificial

<220>
<223> primer

```

09088sequence listing.txt

<400> 8	
gacaattctg gttaggtcca agag	24
<210> 9	
<211> 24	
<212> DNA	
<213> Artificial	
<220>	
<223> primer	
<400> 9	
ttaagctgct gcggagcttc cacg	24
<210> 10	
<211> 22	
<212> DNA	
<213> Artificial	
<220>	
<223> primer	
<400> 10	
atgtctgccc ctaagaagat cg	22
<210> 11	
<211> 24	
<212> DNA	
<213> Artificial	
<220>	
<223> primer	
<400> 11	
ttaagcaagg attttcttaa cttc	24