

FIBER-REINFORCED COMPOSITE DENTAL POST WITH GRADED STIFFNESS

FIELD OF THE INVENTION

The present invention is related to the fiber-reinforced composite dental posts. In particular, the present invention is related to a functionally graded fiber-reinforced composite dental post and processes for making the same.

BACKGROUND OF THE INVENTION

Dental posts are used in reconstruction of endodontically treated teeth. The function of the dental post is to provide retention and lateral stability to the restoration. The restorative material is used to build the core and the crown at the coronal end of the tooth. In order to provide effective lateral stability, the dental post should have high stiffness in the coronal region. Stiffness refers to Young's modulus, which is the resistance of a material to deformation. Another important function of the dental post is to disperse occlusal forces from the coronal region to the remaining tooth structure. In addition, a good dental post should have a long fatigue life and high corrosion resistance.

In view of the above-stated requirements, state-of-the-art dental posts are either made of stainless steel, titanium or other metal alloys, or fiber



166166



G00002

reinforced composites, which have stiffness much higher than that of dentine. Although, the high stiffness is generally recognized as being necessary for the effective support of the restorative material in the coronal region of the tooth in order to prevent loosening of core and crown, it also gives the major
5 drawback of causing stress concentration at the apical end of the tooth. The rigid post stiffens the coronal posted section and shifts the flexure point apically. The effect of this stiffening is to cause the non-posted apical portion of the tooth to deform at the post apex, resulting in a stress increase in that portion of the canal wall. Furthermore, the cyclic loading and unloading during
10 mastication requires consideration of fatigue failure. Since the maximum bending stresses occur in the vicinity of the apex of the post, any inclusions or defects within the wall of the dentine near the apical end of the post would create stress concentration that increases the risk of a fatigue crack formation. Defects and microfractures introduced during endodontic treatment and post
15 access preparation could become areas contributing to stress concentration. As a result, fractures frequently occur at the root of the tooth. Furthermore, the high stress experienced at the post-dentine interface of a high stiffness post often causes loosening at the post-dentine interface.

Various designs have been suggested in the art to address some
20 problems stated above. These include tapered posts (U.S. Patent 5,104,321), and flexible posts (U.S. Patent 5,518,399). For tapered posts, the change in the shape of the post affects the bending stiffness without changing the Young's modulus of the post. Since Young's modulus is a critical parameter in

determining the stress loading at the post-dentine interface, a tapered post does not solve the problem of root stress resulting from the high stiffness of the post. Furthermore, wedging effect occurs at the tip of the tapered end, resulting in vertical fractures. A flexible post has a reduced Young's modulus,
5 which reduces the problem of root stress, but may not give sufficient support to the restoration, resulting in loosening and early failure of the restoration.

OBJECT OF THE INVENTION

It is therefore an object of the present invention to provide a material for
10 a dental post to overcome the shortcomings as stated above.

It is another object to provide a fiber-reinforced composite material with varying stiffness.

SUMMARY OF THE INVENTION

The present invention provides fiber-reinforced composite material with graded stiffness, and method of making the same. The degree of stiffness variation may be controlled via modifications to the fabrication processes.

- 5 Products with varying stiffness along their lengths are described. In one example, a dental post is fabricated from material according to the present invention which has one end with low stiffness adapted for insertion into the root of the tooth, and a high stiffness end suitable to support the restoration.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1A is a schematic diagram to show one method of producing a post in accordance with the present invention.

Figure 1B is a diagram to show a preform produced according to the method
5 shown in Figure 1A.

Figure 2A is a schematic diagram to show a second method of producing a post in accordance with the present invention.

Figure 2B is a photograph of a preform produced by the method shown in Figure 2A.

10 Figure 3 is a schematic diagram to show a third method of producing a post in accordance with the present invention.

Figure 4 is a schematic diagram to show a fourth method of producing a post in accordance with the present invention.

Figure 5 is a finite element analysis showing normal tensile stress levels
15 along post interface.

Figure 6 is a finite element analysis showing normal tensile stress levels along dentine interface.

DESCRIPTION OF THE INVENTION

An important parameter for excellent performance of the dental post is its stiffness. Since stress sharing within a system depends upon the material stiffness of each component, a key to the present invention is the recognition
5 that the ideal dental post is one which gives graded material stiffness along its length. The post should reinforce the coronal region so as to reduce stress in the restoration and associated interfaces. In addition the post should not cause stress concentration at the apical end. This requires the post to take away the stresses from the coronal region and gradually unload them to the
10 dentine. Therefore the segment of the post at the core region must be stiff to take away the stress from the core, while stiffness along the dentine region of the tooth should gradually be reduced to the value of the dentine. Hence, the post according to the present invention comprises segments of varying stiffness along its length. As fiber reinforced composite is used to make the
15 dental post in the present invention, good fatigue and corrosion resistance is also achieved.

For the purpose of understanding the present invention, stiffness refers to Young's modulus. Segments of a post refers to imaginary divisions along the length of a single post for ease of description of graded stiffness, and do
20 not necessarily mean an actual physical separation of the post into different sections. Braiding angle refers to the angle between a braided fiber and the longitudinal axis of a long product. The material may be any conventional composite material such as a combination of ceramic, polymer or metals. The

materials may also be a combination of different polymer or different metals or different ceramic. The following are examples of methods of fabricating a post with graded stiffness.

For a dental post, the preferred stiffness at the apical end is approximately the same as the stiffness of the dentine i.e. 20GPa. The stiffness at the coronal end is preferably much higher than the dentine stiffness, such as 100GPa. The stiffness which can actually be achieved would depend on the material used. For example, a carbon fiber composite dental post may have a stiffness of 150-80 GPa at the coronal end, and 25-15GPa at the apical end. Other stiffness ranges depends on the application, and may be obtained using the methods described below.

EXAMPLE 1

Referring to Figure 1A, spools 20 of metallic, ceramic or polymeric fibers 22 are interlaced into a preform 26 with or without a mandrel or core. After braiding in the braiding machine 28, the preform is transferred to a resin bath 30 containing unreacted resin 32. Once the unreacted resin has impregnated the fibers in the preform, it is transferred to a curing die 34 of the required diameter wherewith the resin is cured to form the polymeric component or matrix of the fiber-reinforced composite post. The polymeric component may be any kind of thermosetting resin such as epoxy, polyester, or molten or solvent dissolved thermoplastic resin.

According to the conventional method, the take-up speed N1 (shown by arrow 24) and spindle speed N2 (shown by arrow 36) has a fixed ratio and hence, the angle of braiding is fixed. According to the present invention, the ratio between the take-up speed N1 (24) and spindle speed N2 (36) is changed continuously in order to vary the angle of braiding. Figure 1B is a schematic drawing of a preform made according to the present invention. This corresponds to section 38 in Figure 1A. The angle of braiding in segment 40 with reference to the longitudinal axis of the post is smaller than the angle of braiding in segment 42. Since it is well known that the stiffness of the fiber-reinforced material is higher when the braiding angle is smaller, varying the take-up and spindle speed ratio would result in a product with varying stiffness. A dental post 46 in accordance with the present invention may then be obtained, for example, by cutting the material at sites 44. Hence post 46 would have one segment 40 which is of higher stiffness than segment 42. It should be understood that using this method, a continuous gradient of stiffness is obtained, and that describing the material as having different segments is merely to facilitate understanding of the inventive concepts.

EXAMPLE 2

Figure 2A shows a variation to the braiding method. In addition to the metallic, polymeric or ceramic reinforcement fibers 48, at least another set of the fibers is a polymeric material 50. During the braiding process, the ratio between the take-up speed N1 24 and spindle speed N2 36 is changed continuously in order to vary the braiding angle. The braided preform 51 is

then transferred to mold 52 for compression molding at required temperature at which specific set of polymeric fibers melt and impregnate the reinforcement fibers. The final product 54 is one having varying stiffness along its length. Section 56 of the preform would have braided fibers similar
5 to the ones shown in Figure 1B, except those additional polymeric fibers are also intertwined. Figure 2B shows a photograph of a preform dental post with a continual variation in the braid angles. Therefore, the stiffness in segment 58 is generally higher than the segment in section 60.

EXAMPLE 3

10 In a conventional filament winding method, a fiber or filament or tape 62 is wound around a core or mandrel 64. The filament may be made of metal, polymer or ceramic. The mandrel may be metal, ceramic or polymer. According to the present invention, the filament is wound at varying orientation with reference to the longitudinal axis of the core. A thermosetting
15 matrix may also be provided according to conventional methods. The resultant product again has smaller angle and higher stiffness in segment 66, and larger angle and lower stiffness in segment 68.

EXAMPLE 4

The stiffness of a composite fiber-reinforced post or long product may
20 also be varied based on the fiber volume fraction. Figure 4 shows a conventional casing 70 and plunger 72 for injection molding. In the conventional injection molding method, short fibers are mixed with a matrix

material in a desired ratio and cured in the casing. In an embodiment of the present invention, mixtures with varying fiber volume fraction (i.e. varying proportions of fibers and matrix material) are transferred to the casing consecutively, and curing allowed to occur together. In the example shown in

5 Figure 4, four mixtures (74, 76, 78, 80) of varying fiber volume fractions are transferred to the casing. After curing, a single post is produced with four segments (74, 76, 78, 80) of varying proportions of fibers. Since it is well known that the stiffness of the product depends on the fiber volume fraction, the resulting product contains corresponding segments of varying stiffness.

10 The fibers may be made of metal, silica, polymer or ceramic. The matrix material is again made from conventional material such as thermosetting resin or thermoplastic resin.

TEST RESULTS

Dental posts with graded stiffness of 20 GPa to 80 GPa were compared

15 with conventional posts using finite element stress analysis. The results of finite element analysis are shown in Figure 5 and 6. A diagram of a restored tooth 82 is shown above the results to indicate the corresponding positions of the each test data at the horizontal axis. The restored core 84 and crown 86, the dental post 88, the dentine 90, the root 91, and the alveolar bone 92 are

20 shown. The vertical axis shows the normal tensile stress levels in MPa.

Figure 5 and 6 shows the tensile stress along the post and dentine respectively at the longitudinal interface. Curves 94 and 95 represents the stress levels for a conventional stainless steel or unidirectionally drawn

carbon fiber post having high fiber volume fraction and 200GPa stiffness. Curves **96** and **97** shows results for a uniform 80Gpa carbon post. Curves **98** and **99** are results for a post with graded stiffness of 20 to 80 GPa in accordance with the present invention. For both post and dentine, the highest stress levels are detected for the conventional high stiffness post. The stress levels are reduced when the post stiffness is reduced to a uniform 80GPa. The post with graded stiffness according to the present invention produces substantially lower stress levels than either of the uniform posts. The graded post shows a maximum of 25 MPa stress levels at the interface, which is only 7% of the 382 MPa peak stress experienced by the stainless steel post. At the dentine side of the interface, the peak stress level of 32 MPa detected using the graded post is only 61% compared to using the stainless steel post. These results are further summarized in Table 1 below.

Post Type	Stiffness	Highest stress level on Post at interface	Residual stress with reference to a 200 GPa post	Highest stress level on dentine at interface	Residual stress with reference to a 200 GPa post
Stainless steel or UD carbon	200 GPa	382 MPa	100%	52 MPa	100%
UD Carbon	80 GPa	114 MPa	30%	42 MPa	81%
Graded stiffness	20-80 GPa	25 MPa	7%	32 MPa	61%

TABLE 1

While the present invention has been described particularly with reference to Figures 1 to 6 with emphasis on a dental post, it should be understood that the figures and the numerical values indicated are for illustration only and should not be taken as limitation on the invention. In
5 addition it is clear that the graded fiber reinforced composite material and the methods of the present invention has utility in many applications, shapes and sizes where graded stiffness and function are required, such as sports equipment, structural elements, biomedical implants and devices etc. It is contemplated that other methods and numerous changes and modifications
10 may be made by one of ordinary skill in the art without departing from the spirit and the scope of the invention described.

CLAIMS

- 1 1. A fiber-reinforced composite dental post with a plurality of segments, a first
2 segment having a stiffness different than a stiffness of a neighboring
3 segment.
- 1 2. A fiber-reinforced composite dental post according to claim 1 further
2 comprising interlaced fibers and a polymeric matrix, said composite post
3 characterized in that the interlacing angles of the fiber in the first segment is
4 greater or smaller than the interlacing angle of the fiber in the neighboring
5 segment.
- 1 3. A fiber-reinforced composite dental post according to claim 2 wherein the
2 fiber is made from metal, polymer or ceramic.
- 1 4. A fiber-reinforced composite dental post according to claim 2 wherein the
2 matrix component is made from polymer, metal or ceramic.
- 1 5. A fiber-reinforced composite dental post according to claim 1 wherein the
2 fiber is a yarn impregnated with matrix wound around a mandrel, said
3 composite post characterized in that the winding angle of said yarn in the
4 first segment is higher or lower than the winding angle of a neighboring
5 segment.
- 1 6. A fiber-reinforced composite dental post according to claim 5 wherein the
2 yarn is a metal, polymer or a ceramic fiber.
- 1 7. A fiber-reinforced composite dental post according to claim 5 wherein the
2 mandrel is made from metal, ceramic or polymer.

- 1 8. A fiber-reinforced composite dental post according to claim 1 further
2 comprising short fibers distributed within a matrix, said composite product
3 characterized in that the fiber volume of the first segment is higher or lower
4 than the fiber volume of a neighbouring segment.
- 1 9. A fiber-reinforced composite dental post according to claim 5 or 8 wherein
2 the matrix is made of thermosetting resin, or thermoplastic resin.
- 1 10. A fiber-reinforced composite dental post according to claim 8 wherein the
2 short fibers are made of metal, polymer or ceramic.
- 1 11. A fiber-reinforced composite dental post according to claim 1 wherein the
2 dental post has a first segment, a last segment and at least one
3 intermediate segment, said first segment having a stiffness of between 150
4 and 80GPa and said last segment having a stiffness of between 25 and
5 15GPa.
- 1 12. A method of making a fiber-reinforced composite dental post, said dental
2 post having a plurality of segments, said dental post further including a
3 plurality of interlaced reinforcement fibers within a matrix, said method
4 comprising the steps of :
- 5 a) braiding said fibers at varying braiding angles to form a preform with
6 a first segment having a different braiding angle than a neighbouring
7 segment;
- 8 b) curing said preform to form a composite dental post.
- 1 13. A method of making a fiber-reinforced composite dental post according to
2 claim 12 wherein an additional step of impregnating the preform with
3 unreacted resin is performed before curing.

- 1 14. A method of making a fiber-reinforced composite dental post according to
2 claim 12 or 13 wherein said fiber is metallic, polymeric or ceramic.
- 1 15. A method of making a fiber-reinforced composite dental post according to
2 claim 12 wherein the fibers contains at least one reinforcement fiber and one
3 polymeric fiber, and said curing step is a compression molding step.
- 1 16. A method of making a fiber-reinforced composite dental post according to
2 any one of claims 12, 13 or 15 wherein said braiding angle is varied by
3 varying a ratio between the take-up speed and the spindle speed in the
4 braiding step.
- 1 17. A method of making a fiber-reinforced composite dental post according to
2 claim 15 wherein said reinforcement fiber is metallic, polymeric or ceramic.
- 1 18. A method of making a fiber-reinforced composite dental post, said dental
2 post having a plurality of segments, said dental post further including at
3 least one wound filament within a matrix, said method comprising the step
4 of winding said filament around a mandrel such that a winding angle of the
5 filament in a first segment is different than a winding angle of the filament in a
6 neighbouring segment.
- 1 19. A method of making a fiber-reinforced composite dental post according to
2 claim 18 wherein said mandrel is metallic, polymeric or ceramic.
- 1 20. A method of making a fiber-reinforced composite dental post according to
2 claim 18 wherein said wound filament is further impregnated with a
3 unreacted resin, followed by a curing step.
- 1 21. A method of making a fiber-reinforced composite dental post according to
2 any one of claims 18-20 wherein said fiber is metallic, polymeric or ceramic.

1 22. A method of making a fiber-reinforced composite dental post with varying
2 stiffness, said method comprising the step of :

3 a) mixing a first pre-determined proportion of fibers and matrix material
4 and transferring to a casing;

5 b) mixing a second pre-determined proportion of fibers and matrix
6 material and transferring to the casing, said second pre-determined
7 proportion having a different fiber volume fraction than said first pre-
8 determined proportion;

9 c) curing mixture (a) and mixture (b) as one integral composite dental
10 post such that the fiber volume fraction of the first pre-determined
11 proportion and the second pre-determined proportion are
12 substantially maintained.

1 23. A method of making a fiber-reinforced composite dental post with varying
2 stiffness according to claim 22 wherein additional mixtures of varying fiber
3 volume fractions are added sequentially to the casing and cured as one
4 integral composite product such that each mixture corresponds to a
5 segment of said product.