

Description

This invention relates to a bonding tool for tape automated bonding, used in a process of producing semiconductor chips, and more particularly, it is concerned with a bonding tool using polycrystalline diamond as a coating of the tool end.

Lately, technical progress in the field of semiconductors has become remarkable and production of the appliances using IC or LSI has shown a yearly increase. In order to draw out the electrical properties these semiconductor elements have, it is required to bond these with metallic fine wires called metal-plated leads or bonding wires. As the metal to be bonded, there is ordinarily used Au or an Au-Sn alloy which is chemically stable and has high electric conductivity and a bonding method comprising thermocompression bonding by means of a bonding tool heated has widely been employed.

The bonding tool used in the above described thermocompression bonding system can broadly be divided into two categories as shown in Fig. 2 and Fig. 1.

Fig. 2 is a schematic view of a pulse heating system, in which nichrome, stainless steel, inconel or molybdenum is used by subjecting to instantaneous heat generation through passage of electric current. In this system, however, such a material meets with a problem that there occur often oxidation, baking and deformation of the lead thereof at a high temperature and accordingly, it is required to clean periodically the end thereof.

Fig. 1 is a schematic view of a constant heating system, in which a polished single crystal diamond or ruby is buried in the end of a shank having a cartridge heater incorporated, and which is characterized by a longer life than that of the tool of the pulse heating system, in particular, in the case of single crystal diamond. The preferential use of diamond is due to that diamond does not meet with marked thermal deterioration in the air at a temperature of up to about 900 °C and has low compatibility and little reactivity with Au-Sn. In a polished diamond single crystal, its surface state is so good as represented by a R_{max} of at most 0.1 μm and is hardly changed because of its high hardness. Because of this character, the alloy of Au-Sn melted during compression bonding hardly adheres to and remains on the surface of the diamond.

When using diamond having the highest thermal conductivity of all the existing materials as a material for the tool of the steady heating system, furthermore, the tool end can be heated at a desired temperature, e.g. 500 to 600 °C without excessively heating the heater, i.e. shank. However, diamond single crystal is expensive and actually, even relatively cheap synthetic one has hardly been obtained with a large size such as several mm or more. It is assumed that in the near future, the step of thermocompression bonding a number of terminals will be increased and in this case, a material with a size of at least 10 mm is required.

A diamond sintered compact having a high heat resistance is disclosed in, for example, Japanese Patent Laid-Open Publication No. 114589/1978, in which an iron group metal binder is extracted by treatment with an acid to form pores. In this case, the surface state cannot be rendered good even by polishing because of the presence of the pores so that an Au-Sn alloy tends to adhere thereto during using.

A pore-free, heat-resisting diamond sintered compact is disclosed in Japanese Patent Laid-Open Publication Nos. 161268/1984 and 33865/1986, in which the binder materials are composed of Si, SiC and Ni-Si alloys. In this case, the surface state after polishing is also unsatisfactory, since the hardness of the binder materials is lower than that of diamond.

A sintered compact containing no binder material and consisting of only polycrystalline diamond is considered most desirable as to heat resistance, hardness, thermal conductivity, surface roughness, etc. Thus, it has been proposed to sinter only diamond powder at an ultra-high pressure, but a composite material of diamond-graphite can only be obtained by this method, since diamond grains themselves are hard to be deformed so that pressure cannot be transmitted to gaps among the grains and consequently, graphitization takes place.

On the other hand, a technique of producing a binder-free polycrystalline diamond compact by a gaseous phase synthesis method has lately made rapid progress and it is considered effective to apply this technique to the bonding tool. As well known in the art, a cutting tool has been put to practice use, which is produced by depositing a thin film of diamond on a substrate of cemented carbide or tungsten by a gaseous phase synthesis method, but even if this is applied to production of the bonding tool, good results cannot be obtained because the bonding strength of the film is too low to prevent this from stripping and occurrence of cracks.

Furthermore, the bonding tool of this kind has other problems. In the bonding tool, a shank and tool end are bonded, for example, by a silver-brazing method, gold-brazing method, thermocompression or sintering bonding method using gold. On the other hand, there are a number of varieties in IC and LSI products, which differ in the number of leads connected and the shape of semiconductors every product. Thus, it is required to prepare an exclusive bonding tool for each IC or LSI product and accordingly, problems arise

that the production cost is increased, more time is taken for exchanging the bonding tool and management of the bonding tool becomes complicated.

JP-A-1021076 discloses a heat resistant sintered contact containing diamond particles onto which is deposited a polycrystalline diamond layer. This material is stated as being useful for bonding tool stock material.

EP-A-0408367, which is a document citable under Article 54(3) EPC, discloses a bonding tool comprising a tool end part and a shank bonded with each other, the tool end part comprising a substrate comprising a member selected from the group consisting of sintered compacts of Si or Si_3N_4 as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, a surface of the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, at least a part of the shank near the tool end part comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides.

It is an object of embodiments of the present invention to provide a bonding tool for TAB, used for the production of a semi-conductor chip.

It is an object of another embodiment of the present invention to provide a bonding tool having a polycrystalline diamond-coated substrate at the end thereof.

In one aspect the present invention provides a bonding tool comprising a tool end part and a shank bonded with each other, the tool end part comprising a substrate comprising a member selected from the group consisting of sintered compacts of Si or Si_3N_4 as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, a surface of the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, at least a part of the shank near the tool end part comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterised in that the tool end part and shank are bonded by a brazing metal.

In another aspect the present invention provides a bonding tool comprising a tool end part and a shank bonded with each other, the tool end part comprising a substrate comprising a member selected from the group consisting of sintered compacts of Si or Si_3N_4 as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, a surface of the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, at least a part of the shank near the tool end part comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterised in that the diamond-coated surface is polished to give a surface roughness as represented by a R_{max} of at most $0.05\mu\text{m}$.

The accompany drawings illustrate embodiments of the present invention in detail.

Fig. 1 is a schematic view of a bonding tool, which is of a constant heating system and is used for bonding a semiconductor element and metallic fine wire.

Fig. 2 is a schematic view of another bonding tool, which is of a pulse heating system and is used for bonding a semiconductor element and metallic fine wire.

Fig. 3 to Fig. 5 are cross-sectional views of three embodiments of the bonding tool according to the present invention to illustrate the mode of bonding a polycrystalline diamond-coated substrate to a shank.

The inventors have made various studies concerning the use of, instead of single crystal diamond, a commercially available sintered diamond compact containing cobalt as a binder with a larger size for the end material of a bonding tool of a constant heating system. This tool was prepared by brazing a blank of such a sintered diamond compact with a shank of stainless steel using a silver braze having a melting point of 750°C and then subjecting to polishing of the end surface and machining of the shank. The thus polished sintered diamond had a good surface state as represented by a R_{max} of $0.06\mu\text{m}$. When the end of the tool was subjected to constant heating at 570°C can repeated thermocompression bonding of IC chips and Au-Sn wires, it was found that the polished end surface gradually became roughened, resulting in the increase of the adhered amount of the melted Au-Sn alloy, and the end diamond compact was loosened or moved at the brazed area.

Deformation of the end surface is probably due to occurrence of fine cracks, caused by the difference in thermal expansion between the cobalt binder and diamond, and due to lowering of the wear resistance, caused by the progress of graphitization of diamond, because of constant heating of the sintered diamond compact. Furthermore, it can be assumed that loosening of the sintered diamond compact is due to that the temperature of the brazed area is exposed to near the melting point during use and the brazing agent tends to be deformed.

Thus, it is found necessary to provide a high heat resistance material to which a brazing agent with a higher melting point can be applied and which is resistant to heating for a long time, since the commercially available sintered diamond compact containing cobalt as a binder material cannot satisfy the requirements of the tool of this kind.

Under the situation, the inventors have made many efforts to obtain more excellent bonding tool materials and consequently, have reached the present invention by choosing a substrate having a good adhesiveness to a coating film.

Accordingly, in one embodiment of the present invention which provides a more excellent bonding tool a tool end part comprises a substrate consisting of a member selected from the group consisting of sintered compacts of Si or Si_3N_4 as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, the substrate being coated with polycrystalline diamond deposited by vapor phase synthesis method, at least a part of the shank near the tool end part comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterised in that the diamond-coated surface is polished to give a surface roughness as represented by a R_{max} of at most $0.05\mu\text{m}$.

Herein, "as predominant component" means "contained in a proportion of about 50 to 99 % by volume".

In the present invention, the coated polycrystalline diamond is preferably oriented in (100) plane and/or (110) plane in the thickness direction from the standpoint of machinability. When the grain diameter of the coated polycrystalline diamond becomes $100\mu\text{m}$ or more, the machinability is deteriorated so that it is not desirable from an economical point of view. A suitable film thickness is in the range of 5 to $300\mu\text{m}$ particularly 10 to $80\mu\text{m}$.

Fig. 1 shows one embodiment of the bonding tool of the present invention, in which the end part thereof is coated with diamond. That is, this bonding tool comprises an end part 3 with a diamond coating layer 7 and a shank 6 with radiating hollows 5 and a cartridge heater holder 4.

The thus obtained bonding tool can mainly be used in the constant heating system, but can also be used in the pulse heating system.

A polycrystalline diamond obtained by a gaseous phase synthesis method generally contains amorphous diamond to some extent and in the present invention, the polycrystalline diamond can contain also amorphous diamond as far as the benefits of the present invention are not unfavorably affected.

In the practice of the present invention, in order to obtain a sintered compact to be an excellent bonding tool material, it is required to select a substrate having a coefficient of thermal expansion similar to that of diamond as well as a good adhesiveness to the coated diamond layer. Furthermore, it is also required for the substrate to have a high heat resistance, since the substrate is exposed to a high temperature, e.g. about 500 to 1000°C in the step of preparing the tool or when used as the tool. The inventors have found, as a result of studies, that sintered compacts of Si or Si_3N_4 as a predominant component, sintered compacts of SiC as a predominant component and sintered compacts of AlN as a predominant component are effective and suitable as a material having these characters. Such a substrate is machined and formed in a desired shape and then coated with polycrystalline diamond by a gaseous phase synthesis method. In this case, the thickness of the substrate is generally, selected in the range of 0.1 to 2.0 mm, depending on the properties of the substrate such as strength and thermal conductivity.

The gaseous phase synthesis method can be carried out by any of known methods, for example, by utilizing thermoelectronic emission or plasma discharge to cause cracking or exciting of a raw material gas or by using a combustion flame to form a film. As the raw material gas, for example, there can generally be used mixed gases of hydrocarbons such as methane, ethane and propane, alcohols such as methanol and ethanol, esters and similar organocarbon compounds with hydrogen, as predominant components. Furthermore, inert gases such as argon, oxygen, carbon monoxide, water, etc. can be contained in the raw material gas in such an amount that the synthetic reaction of carbon and its property cannot be hindered.

The coating film has preferably a thickness of 5 to $300\mu\text{m}$, since if the film thickness is less than $5\mu\text{m}$, cracks tend to occur during polishing the coating surface or during using as a tool, while if more than $300\mu\text{m}$, more time is taken because of a lower deposition speed based on the present technical level, thus resulting in increase of the production cost.

Considering that the upper surface of the coated polycrystalline diamond must be polished and finished in the production of the bonding tool, it is effective to synthesize polycrystalline diamond in such a manner as to be oriented in (100) plane and/or (110) plane in the thickness direction so as to render easy the machinability thereof. In the case of (111) plane, the hardness is too high to improve the machinability. For the same reason, it is preferable to synthesize polycrystalline diamond in such a manner that the grain

diameter of the diamond, on the upper surface of the coating, be 0.1 to 100 μm , since if the grain diameter is too small, the areas at the grain boundaries are increased to result in oxidation or deterioration of the surface upon heating in the air.

In the tool material obtained by the above described method, the diamond-coated surface is further polished and finished in such a manner that the surface state is as represented by a R_{max} of at most 0.05 μm , comparable to that of single crystal diamond.

This surface-polished tool material can exhibit the feature as a bonding tool material by bonding to a tool base material, for example, by means of brazing.

In another embodiment of the present invention, there is provided a bonding tool comprising a tool end part and a shank, bonded with each other, the tool end part consisting of a substrate consisting of a member selected from the group consisting of sintered compacts of Si or Si_3N_4 as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, and the shank partially or wholly consisting of at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterized in that the tool end part and the shank are bonded by a brazing metal.

In this case, the thickness of the substrate is generally selected in the range of 0.5 to 10 mm, preferably 0.5 to 5 mm, depending on the strength of the substrate and the coefficient of linear expansion of the shank.

The gaseous phase synthesis can be carried out by any of known methods in the similar manner to the first embodiment. It is important that the coated polycrystalline diamond has a purity as represented by a non-diamond carbon (Y) to diamond carbon (X) peak ratio (Y/X) of at most 0.2 by Raman spectroscopic analysis, since if this ratio is more than 0.2, i.e. the purity is worse, the quantity of non-diamond carbon contained therein is increased so that the non-diamond carbon is selectively oxidized when heated in the air during using a tool and the surface roughness of the tool end is deteriorated. This is unfavorable.

In the tool material obtained in this way, the diamond-coated surface can further be finished by polishing so that the surface state thereof be comparable to that of diamond single crystal, as represented by a R_{max} of at most 0.05 μm .

The thus surface-polished tool material is bonded to a tool base material, by brazing, thus functioning well as a bonding tool material. Generally, the bonding is effectively carried out by a method comprising using a brazing material with a melting point of at least 600 $^{\circ}\text{C}$ or a method using gold formed by thermocompression bonding.

In the former brazing method, there are preferably used, as a brazing metal, alloys comprising 1 to 40 % by weight of at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table and the balance of at least one element selected from the group consisting of Group VIII elements of Periodic Table, Cu, Ag, Au, B, In and Sn. Alternatively, the end part of a tool, to be bonded, is coated, in order, with a thin film consisting of a metal, alloy or compound comprising at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table and with a thin film consisting of at least one element selected from the group consisting of Group VIII elements of Periodic Table, Cu, Ag, and Au and then bonded to a shank with a brazing metal having a melting point of at least 600 $^{\circ}\text{C}$ via the coated layers. In these methods, the metal, alloy or compound comprising at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table has a function of reacting with polycrystalline diamond to form a carbide and to thus increase the brazing strength.

In the latter gold thermocompression bonding method, it is important for obtaining a high bonding strength that the end part of a tool and/or a shank has a bonding surface coated with, as a bond-strengthening layer, a thin film consisting of a metal, alloy or compound comprising at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table and with, as a diffusion proof layer, a thin film consisting of a metal or alloy comprising at least one element selected from the group consisting of Pt, Pd, W, Mo, Ta and Ni in such a manner that the diffusion proof layer is outside the bond-strengthening layer.

Furthermore, it is important from the standpoint of the bonding strength that at least a part of the shank is composed of a material having a coefficient of thermal expansion similar to that of the tool end part, that is, a metal and/or alloy having a coefficient of linear expansion of at most $7.5 \times 10^{-6} / ^{\circ}\text{C}$ at a temperature of from room temperature to 600 $^{\circ}\text{C}$. As such a material, there can preferably be used Kovar alloys, Invar alloys, molybdenum, tungsten, W-Cu alloys, W-Ni alloys and cemented carbides. If necessary, a thermal stress moderating layer consisting of a soft metal such as Cu or Ni can be arranged as a part of the bonding side of the shank.

The coefficients of linear thermal expansion of these materials are as follows:

Materials	Coefficient of Linear Thermal Expansion ($\times 10^{-6}/\text{deg}$)	Remarks
Diamond Single Crystal	3.1	Co: about 5%
Polycrystalline	3.1	
Mo	5.7	
W	4.6	
Invar	10	
Kovar	6	
Cemented Carbides	4.5	
SUS	12	

The structures of the bonding tool, in cross-section, are shown, for example, in Fig. 3 to Fig. 5 to illustrate the bonding state. In the case of Fig. 3, the shank 6 is fully composed of the above described material and in the case of Fig. 4, only a part A of the shank 6, near the tool end parts, is composed of the above described material. The structure of Fig. 4 is preferably used when the shank material is too expensive or has low machinability, that is, when molybdenum, tungsten or cemented carbides are used as such. In this case, the residual part B of the shank 6, in Fig. 4 can of course be composed of a material having a large coefficient of thermal expansion such as stainless steel. Referring to Fig. 5, the above described soft metal, as a thermal stress moderating layer 41, can be inserted in between the tool end part and shank body 6. The soft metal is subject to plastic deformation to moderate thermal stress and to prevent from lowering of the bonding strength. In any of these structures, the bonding strength reaches a stable value, i.e. at least 10 kg/mm², which is sufficient for use as a bonding tool.

The following examples are given in order to illustrate the present invention in detail without limiting the same.

Example 1

A substrate of SiC sintered compact of 15 mm square and 2 mm thick was fixed to a support base of quartz glass and coated with polycrystalline diamond by a microwave plasma CVD method. A coating of polycrystalline diamond with a thickness of 0.2 mm was obtained for 10 hours under the following conditions:

Raw Material Gas (flow rate): H₂ 200 cc/min, CH₄ 4 cc/min
Ar 50 cc/min
Pressure: 100 Torr
Output of Microwave Oscillator: 800 W

The polycrystalline diamond in the coating layer had a grain diameter of about 15 μm and a surface roughness represented by a Rmax of 8.5 μm .

When the similar procedure was repeated except using Mo as a substrate, on the other hand, polycrystalline diamond was coated with a film thickness of 0.18 mm, grain diameter of 20 μm and surface roughness as represented by a Rmax of 10.5 μm .

In the both cases, the polycrystalline diamonds were oriented in (110) plane in the thickness direction. These coated samples were then subjected to polishing of the coated surface by means of a diamond electrodeposited wheel with a mesh size of No. 200. As a result, in the case of using Mo as a substrate, cracks occurred in the coated film during polishing, resulting in partial stripping thereof, while in the case of using the SiC sintered compact as a substrate, there was obtained such a good surface state as comparable to single crystal diamond and as represented by a Rmax of 0.03 μm without stripping of the film.

The opposite surface of the SiC sintered compact to the thus polished surface was coated, as a pretreatment, with laminated layers of Ti and Ni each having a thickness of 2 μm by a PVD method and then bonded to a tool base material of stainless steel in vacuum at 1100 °C with a brazing metal of an Au-Ta alloy. The thus bonded body was further subjected to polishing and finishing to prepare a bonding tool.

When the bonding tool was fitted to a bonding apparatus and subjected to a durability test, this bonding tool was resistant to use of million times as in the case of a bonding tool prepared using a single crystal diamond of 3 mm square. This example told that the dimension of the bonding surface was enlarged to thus increase the productivity by about 5 times.

Example 2

Bonding tool materials as shown in Table 1 were prepared in the similar manner to Example 1. Comparative samples are also shown in Table 1.

Table 1

Sample No.	Substrate	Coating Method of Diamond	Thickness of Diamond Coating Film (μm)	Orientation Plane of Coated Polycrystalline Diamond	Grain Diameter of Upper Surface of Coating (μm)
1	SiC	microwave plasma CVD method	120	(111)	40
2	Mo	high frequency plasma CVD method	80	(100)	25
3	Si_3N_4	hot filament method	2	(110)	2
4	AlN	microwave plasma CVD method	180	(110)	30
5	Si	hot filament method	280	(100)	15
6	SiC	high frequency plasma CVD method	50	(110)	5
7	Si_3N_4	combustion flame method	250	(110)	80
8	Si_3N_4	microwave plasma CVD method	210	(100)	150
9	Ta	high frequency plasma CVD method	70	(100)	35
10	AlN	hot filament method	220	(100)	10
11	SiC	hot filament method	30	(100)	8

The coated surfaces of these materials and a commercially available sintered diamond compact containing 10 vol % of Co for comparison were subjected to polishing.

Consequently, in the case of Sample No. 3 having a coating thickness of less than 5 μm , cracks occurred during polishing and in the case of Sample Nos. 2 and 9 respectively using Mo and Ta, the coating films were stripped during polishing. Sample No. 1 oriented in (111) plane and Sample 8, in which the grains in the upper surface of the coated polycrystalline diamond were coarse as represented by a diameter of 150 μm , showed such a low machinability that polishing of the overall surface was impossible. The surface roughness of the other samples after polishing is shown in Table 2. These samples were respectively machined to prepare a bonding tool having an end of 20 mm square and then subjected to a durability test in which bonding of IC products each having 1000 pins was repeatedly carried out at an end temperature of 600 °C for a compression time of 2 seconds, thus obtaining results as shown in Table 2. As is evident from the results of Table 2, the bonding tools using the material of embodiments of the present invention were free from marked deterioration.

Table 2

Sample No.	Surface Roughness R_{max} After Polishing	Repetition No. ($\times 10^4$)	Worn State of Tool
4	0.03	120	no marked wear
5	0.05	120	-do-
6	0.04	120	-do-
7	0.03	120	-do-
10	0.03	120	-do-
11	0.04	120	-do-
Sintered Diamond	0.06	40	cavity of 2.5 μm on tool end surface

Example 3

A substrate of SiC sintered compact of 15 mm square and 2 mm thick was fixed to a support base of quartz glass and coated with polycrystalline diamond by a microwave plasma CVD method. A coating of polycrystalline diamond with a thickness of 50 μm was obtained for 10 hours under the following conditions:

Raw Material Gas (flow rate): H₂ 200 cc/min, CH₄ 4 cc/min Ar 50 cc/min
 Pressure: 100 Torr
 Output of Microwave Oscillator: 800 W

The polycrystalline diamond in the coating layer had a grain diameter of about 15 μm and a surface roughness as represented by a R_{max} of 8.5 μm .

When the similar procedure was repeated except using Mo as a substrate, on the other hand, polycrystalline diamond was coated with a film thickness of 45 μm , grain diameter of 20 μm and surface roughness as represented by a R_{max} of 10.5 μm .

In both the cases, the polycrystalline diamonds were oriented in (110) plane in the thickness direction. The polycrystalline diamonds had a non-diamond carbon (Y) to diamond carbon (X) peak ratio (Y/X) of 0.05 by Raman spectroscopic analysis. These coated samples were then subjected to polishing of the coated surface by means of a diamond electrodeposited wheel with a mesh size of No. 200. As a result, in the case of using Mo as a substrate, cracks occurred in the coated film during polishing, resulting in partial stripping thereof, while in the case of using the SiC sintered compact as a substrate, there was obtained such a good surface state as comparable to single crystal diamond and as represented by a R_{max} of 0.03 μm without stripping of the film.

The opposite surface of the SiC sintered compact to the thus polished surface was coated, as a pretreatment, with laminated layers of Ti and Ni each having a thickness of 2 μm by PVD method and then bonded to a shank of Kovar in vacuum of 850 °C with a brazing metal of an Ag-Cu alloy. The thus bonded body was further subjected to polishing and finishing to prepare a bonding tool.

When the bonding tool was fitted to a bonding apparatus and subjected to a durability test, this bonding tool was resistant to use of million times as in the case of a bonding tool prepared using a single crystal diamond of 3 mm square. This example told that the dimension of the bonding surface was enlarged to thus increase the productivity by about 5 times.

Example 4

Bonding tool materials as shown in Table 3 were prepared in the similar manner to Example 3. Comparative samples are also shown in Table 3.

Table 3

Sample No.	Substrate	Coating Method of Diamond	Thickness of Diamond Coating Film(μm)	Orientation Plane of Coated Polycrystalline Diamond	Grain Diameter of Upper Surface of Coating (μm)	Raman Peak Ratio (Y/X)
12	SiC	microwave plasma CVD method	120	(111)	40	0.10
13	Mo	high frequency plasma CVD method	80	(100)	25	0.15
14	Si ₃ N ₄	hot filament method	2	(110)	2	0.08
15	AlN	microwave plasma CVD method	180	(110)	30	0.18
16	Si	hot filament method	280	(100)	15	0.05
17	SiC	high frequency plasma CVD method	50	(110)	5	0.35
18	Si ₃ N ₄	combustion flame method	250	(110)	80	0.07
19	Si ₃ N ₄	microwave plasma CVD method	210	(100)	150	0.13
20	Ta	high frequency plasma CVD method	70	(100)	35	0.17
21	AlN	hot filament method	220	(100)	10	0.04
22	SiC	heat filament method	30	(100)	8	0.16

The coated surfaces of these materials and a commercially available sintered diamond compact containing 10 vol % of Co for comparison were subjected to polishing.

Consequently, in the case of Sample No. 14 having a coating thickness of less than 5 μm , cracks occurred during polishing and in the case of Sample Nos. 13 and 20 respectively using Mo and Ta, the coating films were stripped during polishing. Sample No. 12 oriented in (111) plane and Sample No. 19, in which the grains in the upper surface of the coated polycrystalline diamond were coarse as represented by a diameter of 150 μm , showed such a low machinability that polishing of the overall surface was impossible. The surface roughness of the other samples after polishing is shown in Table 4. These materials were respectively machined and brazed to a shank of Invar alloy in vacuum at 900 °C using a brazing metal consisting of Cu, Ni and Mn in a proportion of 7 : 1 : 2 by weight, after which it was further machined to prepare a bonding tool having an end of 10 mm square. These tools were then subjected to a durability test in which bonding of IC products each having 1000 pins was repeatedly carried out at an end temperature of 520 °C for a compression time of 2 seconds, thus obtaining results as shown in Table 4. As is evident from the results of Table 4, Sample No. 17 having a non-diamond carbon content of more than the preferred range according to the present invention, found by Raman spectroscopic analysis, met with deterioration of the surface roughness, while the bonding tools using the material of embodiments of the present invention were free from marked deterioration.

Table 4

Sample No.	Surface Roughness R_{max} After Polishing	Repetition No. ($\times 10^4$)	Worn State of Tool
15	0.03	120	no marked wear
16	0.05	120	-do-
17	0.04	120	surface roughness deteriorated to R_{max} of 0.25 after using
18	0.03	120	no marked wear
21	0.03	120	-do-
22	0.04	120	-do-
Sintered Diamond	0.06	10	cavity of 2.5 μm

Example 5

Using a linear tungsten filament of 0.5 mm in diameter and 20 mm in length as a thermoelectron emitting material, a raw material gas comprising hydrogen, a carbon source and steam was subjected to cracking and exciting for 20 hours to form polycrystalline diamond on a SiC substrate with a thickness of 3 mm under conditions as shown in Table 5. The properties of the thus resulting polycrystalline diamond are also shown in Table 5. Bonding tools each having the structure of a tool end part shown in Table 6 was prepared and subjected to a durability test to find that all of these samples were resistant to use of million times as a bonding tool. The bonding strength (shearing strength) was measured using the tool after used to obtain results as shown in Table 6. Sample Nos. 23 to 28 of the present invention showed stable and high bonding strengths.

When the sample was brazed directly to SUS 304 for comparison, the brazing strength was considerably lower, i.e. 2 kg/mm².

Table 5

Sample No.	23	24	25	26	27	28
Carbon Source	ethyl alcohol			acetylene		
Carbon Source/H ₂ (vol %)	1.5	2.3	1.8	3.0	2.0	1.6
Amount of H ₂ O added (vol%)	0.3	0	0.01	1.2	0.2	3.5
Gas Flow Rate (SCCM)	600	200	1000	500	300	200
Gas Pressure (Torr)	100	150	120	300	80	200
Substrate Temperature (°C)	900	850	850	780	750	820
Filament Temperature(°C)	2200	2050	2100	2150	2200	2250
Substrate-Filament Distance (mm)	3	5	4	5	6	5
Electron Current Density (A/cm ²)	0.4	1.0	0.3	0.8	0.2	0.4
Polycrystalline Diamond Property						
Thickness (μm)	55	120	30	160	80	70
Grain Diameter (μm)	20	5	15	10	30	20
Raman Peak Ratio (Y/X)	0.01	0.18	0.03	0.15	0.02	0.12
Oriented Plane	(110)	(100)	(110)	(100)	(100)	(110)

Table 6

Sample No.	Tool Structure	Material of Shank	Bonding Method	Bonding Strength (Kg/mm ²)
23	Fig. 1	Invar alloy	U	15
24	Fig. 2	cemented carbide + SUS 304	S	12
25	Fig. 2	W + Kovar	T	20
26	Fig. 3	Ni + Invar alloy	U	18
27	Fig. 1	Kovar	S	25
28	Fig. 3	Cu + Kovar	T	17
29	Fig. 1	SUS 304	S	2
Note Bonding Method: S: using a brazing metal of 60 Ag - 30 Cu - 10 Ti (wt %) T: coating a surface of a tool end, to be bonded, with TiC and Ni layers each having a thickness of 1 μm and brazing with a brazing metal of 70 Ag - 30 Cu (wt %). U: coating surfaces of a tool end and shank, to be bonded, with Ta and Pt layers each having a thickness of 1 μm and compression bonding Au.				

Claims

1. A bonding tool comprising a tool end part (3, 7) and a shank (6) bonded with each other, the tool end part (3, 7) comprising a substrate comprising a member selected from the group consisting of sintered compacts of Si or Si₃N₄ as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, a surface (7) of the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, at least a part of the shank (6) near the tool end part (3, 7) comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterised in that the tool end part (3, 7) and shank (6) are bonded by a brazing metal.
2. The bonding tool as claimed in Claim 1, characterised in that the substrate has a thickness of 0.5 to 10mm.



Table 5

Sample No.	23	24	25	26	27	28
Carbon Source	ethyl alcohol			acetylene		
Carbon Source/H ₂ (vol %)	1.5	2.3	1.8	3.0	2.0	1.6
Amount of H ₂ O added (vol%)	0.3	0	0.01	1.2	0.2	3.5
Gas Flow Rate (SCCM)	600	200	1000	500	300	200
Gas Pressure (Torr)	100	150	120	300	80	200
Substrate Temperature (°C)	900	850	850	780	750	820
Filament Temperature (°C)	2200	2050	2100	2150	2200	2250
Substrate-Filament Distance (mm)	3	5	4	5	6	5
Electron Current Density (A/cm ²)	0.4	1.0	0.3	0.8	0.2	0.4
Polycrystalline Diamond Property						
Thickness (μm)	55	120	30	160	80	70
Grain Diameter (μm)	20	5	15	10	30	20
Raman Peak Ratio (Y/X)	0.01	0.18	0.03	0.15	0.02	0.12
Oriented Plane	(110)	(100)	(110)	(100)	(100)	(110)

Table 6

Sample No.	Tool Structure	Material of Shank	Bonding Method	Bonding Strength (Kg/mm ²)
23	Fig. 1	Invar alloy	U	15
24	Fig. 2	cemented carbide + SUS 304	S	12
25	Fig. 2	W + Kovar	T	20
26	Fig. 3	Ni + Invar alloy	U	18
27	Fig. 1	Kovar	S	25
28	Fig. 3	Cu + Kovar	T	17
29	Fig. 1	SUS 304	S	2
Note Bonding Method: S: using a brazing metal of 60 Ag - 30 Cu - 10 Ti (wt %) T: coating a surface of a tool end, to be bonded, with TiC and Ni layers each having a thickness of 1 μm and brazing with a brazing metal of 70 Ag - 30 Cu (wt %). U: coating surfaces of a tool end and shank, to be bonded, with Ta and Pt layers each having a thickness of 1 μm and compression bonding Au.				

Claims

1. A bonding tool comprising a tool end part (3, 7) and a shank (6) bonded with each other, the tool end part (3, 7) comprising a substrate comprising a member selected from the group consisting of sintered compacts of Si or Si₃N₄ as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, a surface (7) of the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, at least a part of the shank (6) near the tool end part (3, 7) comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterised in that the tool end part (3, 7) and shank (6) are bonded by a brazing metal.
2. The bonding tool as claimed in Claim 1, characterised in that the substrate has a thickness of 0.5 to 10mm.



3. The bonding tool as claimed in Claim 1, characterised in that the polycrystalline diamond has a thickness of 5 to 300µm.
- 5 4. The bonding tool as claimed in Claim 1, characterised in that the coated polycrystalline diamond has a purity as represented by a non-diamond carbon (Y) to diamond carbon (X) peak ratio (Y/X) of at most 0.2 by Raman spectroscopic analysis.
- 10 5. The bonding tool as claimed in Claim 1, characterised in that the coated polycrystalline diamond is oriented in at least one of (100) plane and (110) plane.
- 15 6. The bonding tool as claimed in Claim 1, characterised in that the tool end part (3, 7) and shank (6) are bonded by a brazing metal having a melting point of at least 600 ° C.
- 20 7. The bonding tool as claimed in Claim 1, characterised in that the brazing metal is an alloy consisting of 1 to 40% by weight of at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table and the balance of at least one element selected from the group consisting of Group VIII elements of Periodic Table, Cu, Ag, Au, B, In and Sn.
- 25 8. The bonding tool as claimed in Claim 1, characterised in that the surface of the tool end, to be bonded, is coated, in order, with a thin film consisting of a metal, alloy or compound comprising at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table and with a thin film consisting of at least one element selected from the group consisting of Group VIII elements of Periodic Table, Cu, Ag and Au, and then bonded to a shank with a brazing metal having a melting point of at least 600 ° C through the coated layers.
- 30 9. The bonding tool as claimed in Claim 1, characterised in that the shank (6) is provided with, at a part of the bonding surface thereof, a thermal stress moderating layer consisting of a soft metal such as Cu or Ni.
- 35 10. The bonding tool as claimed in Claim 1, characterised in that the diamond-coated surface is further polished to give a surface roughness as represented by a Rmax of at most 0.05µm.
- 40 11. A bonding tool comprising a tool end part (3, 7) and a shank (6) bonded with each other, the tool end part (3, 7) comprising a substrate comprising a member selected from the group consisting of sintered compacts of Si or Si₃N₄ as a predominant component, sintered compacts of SiC as a predominant component, sintered compacts of AlN as a predominant component and composite compacts thereof, a surface (7) of the substrate being coated with polycrystalline diamond deposited by gaseous phase synthesis method, at least a part of the shank (6) near the tool end part (3, 7) comprising at least one member of a group consisting of Kovar alloys, Invar alloys, Mo, W, W-Cu alloys, W-Ni alloys and cemented carbides, characterised in that the diamond-coated surface (7) is polished to give a surface roughness as represented by a Rmax of at most 0.05µm.
- 45 12. The bonding tool as claimed in Claim 11, characterised in that the substrate has a thickness of 0.5 to 10mm.
- 50 13. The bonding tool as claimed in Claim 11, characterised in that the polycrystalline diamond has a thickness of 5 to 300µm.
- 55 14. The bonding tool as claimed in Claim 11, characterised in that the coated polycrystalline diamond has a purity as represented by a non-diamond carbon (Y) to diamond carbon (X) peak ratio (Y/X) of at most 0.2 by Raman spectroscopic analysis.
15. The bonding tool as claimed in Claim 11, characterised in that the coated polycrystalline diamond is oriented in at least one of (100) plane and (110) plane.
16. The bonding tool as claimed in Claim 11, characterised in that the bonding of the tool end part (3, 7) and shank (6) is carried out by gold formed by thermocompression bonding.



- 5 17. The bonding tool as claimed in Claim 16, characterised in that the surface to be bonded of at least one of the tool end part (3, 7) and shank (6) is coated with, as a bond-strengthening layer, a thin film consisting of a metal, alloy or compound comprising at least one element selected from the group consisting of Group IVa, Va, VIa and VIIa elements of Periodic Table and with, as a diffusion proof layer, a thin film consisting of a metal or alloy comprising at least one element selected from the group consisting of Pt, Pd, W, Mo, Ta and Ni in such a manner that the diffusion proof layer is outside the bond-strengthening layer.
- 10 18. The bonding tool as claimed in Claim 16, characterised in that the shank (6) is provided with, at a part of the bonding surface thereof, a thermal stress moderating layer consisting of a soft metal such as Cu or Ni.

Patentansprüche

- 15 1. Verbindungswerkzeug mit einem Werkzeugendteil (3, 7) und einem Schaft (6), die miteinander verbunden sind, wobei der Werkzeugendteil (3, 7) eine Grundlage mit einer Komponente umfaßt, die aus der aus gesinterten Preßkörpern aus Si oder Si₃N₄ als Hauptkomponente, gesinterten Preßkörpern aus SiC als Hauptkomponente, gesinterten Preßkörpern aus AlN als Hauptkomponente und Verbundpreßkörpern davon bestehenden Gruppe ausgewählt ist, wobei eine Oberfläche (7) der Grundlage mit polykristallinem, durch das Gasphasensyntheseverfahren abgeschiedenem Diamanten beschichtet ist und wobei mindestens ein Teil des Schafts (6) nahe dem Werkzeugendteil (3, 7) mindestens eine Komponente aus der aus Kovar-Legierungen, Invar-Legierungen, Mo, W, W-Cu-Legierungen, W-Ni-Legierungen und Sintercarbiden bestehenden Gruppe umfaßt, dadurch gekennzeichnet, daß der Werkzeugendteil (3, 7) und der Schaft (6) durch ein Hartlötmetall miteinander verbunden sind.
- 20 2. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß die Grundlage 0,5 bis 10 mm dick ist.
- 25 3. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß der polykristalline Diamant 5 bis 300 µm dick ist.
- 30 4. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß der als Beschichtung aufgebraachte polykristalline Diamant eine durch ein Peakverhältnis (Y/X) von nichtdiamantem Kohlenstoff (Y) zu Diamantkohlenstoff (X) von mindestens 0,2 in der Raman Spektroskopanalyse dargestellte Reinheit aufweist.
- 35 5. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß der als Beschichtung aufgebraachte polykristalline Diamant in der (100) und/oder der (110) Ebene ausgerichtet ist.
- 40 6. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß der Werkzeugendteil (3, 7) und der Schaft (6) durch ein Hartlötmetall mit einem Schmelzpunkt von mindestens 600 °C miteinander verbunden sind.
- 45 7. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß das Hartlötmetall eine Legierung ist, die zu 1 bis 40 Gew.-% aus mindestens einem aus der aus Elementen der Gruppe IVa, Va, VIa und VIIa des Periodensystems bestehenden Gruppe ausgewählten Element und ansonsten aus mindestens einem aus der aus Elementen der Gruppe VIII des Periodensystems, Cu, Ag, Au, B, In und Sn bestehenden Gruppe ausgewählten Element besteht.
- 50 8. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß die Oberfläche des zu verbindenden Werkzeugendes nacheinander mit einem dünnen Film aus einem Metall, einer Legierung oder einer Verbindung, das bzw. die mindestens ein aus der aus Elementen der Gruppe IVa, Va, VIa und VIIa des Periodensystems bestehenden Gruppe ausgewähltes Element enthält, und einem dünnen Film, der aus mindestens einem aus der aus Elementen der Gruppe VIII des Periodensystems, Cu, Ag und Au bestehenden Gruppe ausgewählten Element besteht, beschichtet wird und dann mit einem Hartlötmetall mit einem Schmelzpunkt von mindestens 600 °C durch die durch Beschichtung aufgebraachten Schichten mit einem Schaft verbunden wird.
- 55



9. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß der Schaft (6) an einem Teil seiner verbindenden Oberfläche mit einer aus einem weichen Metall wie Cu oder Ni bestehenden, die Wärmebeanspruchung mildernden Schicht versehen ist.
10. Verbindungswerkzeug nach Anspruch 1, dadurch gekennzeichnet, daß die mit Diamant beschichtete Oberfläche außerdem poliert wird, um ihr eine Oberflächenrauheit zu verleihen, die durch ein R_{max} von höchstens $0,05 \mu m$ ausgedrückt wird.
11. Verbindungswerkzeug mit einem Werkzeugenteil (3, 7) und einem Schaft (6), die miteinander verbunden sind, wobei der Werkzeugenteil (3, 7) eine Grundlage mit einer Komponente umfaßt, die aus der aus gesinterten Preßkörpern aus Si oder Si_3N_4 als Hauptkomponente, gesinterten Preßkörpern aus SiC als Hauptkomponente, gesinterten Preßkörpern aus AlN als Hauptkomponente und Verbundpreßkörpern davon bestehenden Gruppe ausgewählt ist, wobei eine Oberfläche (7) der Grundlage mit polykristallinem, durch das Gasphasensyntheseverfahren abgeschiedenem Diamanten beschichtet ist und wobei mindestens ein Teil des Schafts (6) nahe dem Werkzeugenteil (3, 7) mindestens eine Komponente aus der aus Kovar-Legierungen, Invar-Legierungen, Mo, W, W-Cu-Legierungen, W-Ni-Legierungen und Sintercarbiden bestehenden Gruppe umfaßt, dadurch gekennzeichnet, daß die mit Diamant beschichtete Oberfläche (7) poliert wird, um ihr eine Oberflächenrauheit zu verleihen, die durch ein R_{max} von höchstens $0,05 \mu m$ ausgedrückt wird.
12. Verbindungswerkzeug nach Anspruch 11, dadurch gekennzeichnet, daß die Grundlage $0,5$ bis 10 mm dick ist.
13. Verbindungswerkzeug nach Anspruch 11, dadurch gekennzeichnet, daß der polykristalline Diamant 5 bis $300 \mu m$ dick ist.
14. Verbindungswerkzeug nach Anspruch 11, dadurch gekennzeichnet, daß der als Beschichtung aufgebraachte polykristalline Diamant eine durch ein Peakverhältnis (Y/X) von nichtdiamantem Kohlenstoff (Y) zu Diamantkohlenstoff (X) von mindestens $0,2$ in der Raman Spektroskopanalyse dargestellte Reinheit aufweist.
15. Verbindungswerkzeug nach Anspruch 11, dadurch gekennzeichnet, daß der als Beschichtung aufgebraachte polykristalline Diamant in der (100) und/oder der (110) Ebene ausgerichtet ist.
16. Verbindungswerkzeug nach Anspruch 11, dadurch gekennzeichnet, daß das Verbinden des Werkzeugenteils (3, 7) und des Schafts durch Gold erfolgt, das durch Thermokompressionsverbinden gebildet wurde.
17. Verbindungswerkzeug nach Anspruch 16, dadurch gekennzeichnet, daß die zu verbindende Oberfläche des Werkzeugenteils (3, 7) und/oder des Schafts (6) als Bindungsverstärkungsschicht mit einem dünnen Film aus einem Metall, einer Legierung oder Verbindung, das bzw. die mindestens ein aus der aus Elementen der Gruppe IVa, Va, VIa und VIIa des Periodensystems bestehenden Gruppe ausgewähltes Element umfaßt, und als diffusionsfeste Schicht mit einem dünnen Film aus einem Metall oder einer Legierung, das bzw. die mindestens ein aus der aus Pt, Pd, W, Mo, Ta und Ni bestehenden Gruppe ausgewähltes Element umfaßt, so beschichtet wird, daß die diffusionsfeste Schicht außerhalb der bindungsverstärkenden Schicht liegt.
18. Verbindungswerkzeug nach Anspruch 16, dadurch gekennzeichnet, daß der Schaft (6) an einem Teil seiner Verbindungsoberfläche mit einer die Wärmebeanspruchung mildernden Schicht aus einem weichen Metall wie Cu oder Ni versehen ist.

Revendications

1. Outil de liaison comprenant une partie d'extrémité d'outil (3, 7) et une tige (6) liées l'une à l'autre, la partie d'extrémité d'outil (3, 7) comprenant un substrat comportant un élément choisi parmi le groupe constitué des comprimés frittés de Si ou de Si_3N_4 comme composant prédominant, des comprimés frittés de SiC comme composant prédominant, des comprimés frittés d'AlN comme composant prédominant et des comprimés composites de ceux-ci, une surface (7) du substrat étant revêtue de



- 5 diamant polycristallin déposé par un procédé de synthèse en phase gazeuse, au moins une partie de la tige (6) à proximité de la partie d'extrémité d'outil comprenant au moins un élément d'un groupe constitué d'alliages de Kovar, d'alliages d'Invar, de Mo, de W, d'alliages de W-Cu, d'alliages de W-Ni et de carbures cémentés, caractérisé en ce que la partie d'extrémité d'outil (3, 7) et la tige (6) sont liées par un métal de brasage.
2. Outil de liaison suivant la revendication 1, caractérisé en ce que le substrat a une épaisseur de 0,5 à 10 mm.
- 10 3. Outil de liaison suivant la revendication 1, caractérisé en ce que le diamant polycristallin a une épaisseur de 5 à 300 μm .
- 15 4. Outil de liaison suivant la revendication 1, caractérisé en ce que le diamant polycristallin de revêtement présente une pureté telle que celle représentée par un rapport de crête (Y/X) entre du carbone de type non-diamant (Y) et du carbone de type diamant (X) d'au plus 0,2 par une analyse spectroscopique selon Raman.
- 20 5. Outil de liaison suivant la revendication 1, caractérisé en ce que le diamant polycristallin de revêtement est orienté dans au moins un des plans (100) et (110).
- 25 6. Outil de liaison suivant la revendication 1, caractérisé en ce que la partie d'extrémité d'outil (3, 7) et la tige (6) sont liées par un métal de brasage présentant un point de fusion d'au moins 600 °C.
- 30 7. Outil de liaison suivant la revendication 1, caractérisé en ce que le métal de brasage est un alliage constitué de 1 à 40 % en poids d'au moins un élément choisi parmi le groupe comprenant des éléments des groupes IVa, Va, VIa et VIIa du Tableau Périodique, le reste étant formé d'au moins un élément choisi parmi le groupe comprenant des éléments du groupe VIII du Tableau Périodique, Cu, Ag, Au, B, In et Sn.
- 35 8. Outil de liaison suivant la revendication 1, caractérisé en ce que la surface de l'extrémité d'outil à lier est revêtue, dans l'ordre, d'un mince film constitué d'un métal, alliage ou composé comprenant au moins un élément choisi parmi le groupe comprenant des éléments des groupes IVa, Va, VIa et VIIa du Tableau Périodique et d'un mince film constitué d'au moins un élément choisi parmi le groupe comprenant des éléments du groupe VIII du Tableau Périodique, Cu, Ag et Au, et en ce qu'elle est ensuite liée à une tige avec un métal de brasage ayant un point de fusion d'au moins 600 °C par les couches de revêtement.
- 40 9. Outil de liaison suivant la revendication 1, caractérisé en ce que la tige (6) est pourvue, à une partie de sa surface de liaison, d'une couche modérant l'effort thermique, qui est constituée d'un métal doux tel que du Cu ou du Ni.
- 45 10. Outil de liaison suivant la revendication 1, caractérisé en ce que la surface revêtue de diamant est en outre polie pour donner une rugosité de surface telle que représentée par un R_{max} d'au plus 0,05 μm .
- 50 11. Outil de liaison comprenant une partie d'extrémité d'outil (3, 7) et une tige (6) liées l'une à l'autre, la partie d'extrémité d'outil (3, 7) comprenant un substrat comprenant un élément choisi parmi le groupe constitué des comprimés frittés de Si ou de Si_3N_4 comme composant prédominant, des comprimés frittés de SiC comme composant prédominant, des comprimés frittés d'AlN comme composant prédominant, et des comprimés composites de ceux-ci, une surface (7) du substrat étant revêtue de diamant polycristallin déposé par un procédé de synthèse en phase gazeuse, au moins une partie de la tige (6) à proximité de la partie d'extrémité d'outil comprenant au moins un élément d'un groupe constitué d'alliages de Kovar, d'alliages d'Invar, de Mo, de W, d'alliages de W-Cu, d'alliages de W-Ni et de carbures cémentés, caractérisé en ce que la surface revêtue de diamant (7) est polie pour donner une rugosité de surface telle que représentée par un R_{max} d'au plus 0,05 μm .
- 55 12. Outil de liaison suivant la revendication 11, caractérisé en ce que le substrat présente une épaisseur de 0,5 à 10 mm.



13. Outil de liaison suivant la revendication 11, caractérisé en ce que le diamant polycristallin présente une épaisseur de 5 à 300 μm .
14. Outil de liaison suivant la revendication 11, caractérisé en ce que le diamant polycristallin de revêtement présente une pureté telle que représentée par un rapport de crête (Y/X) entre du carbone de type non-diamant (Y) et du carbone de type diamant (X) d'au maximum 0,2 par une analyse spectroscopique selon Raman.
15. Outil de liaison suivant la revendication 11, caractérisé en ce que le diamant polycristallin de revêtement est orienté dans au moins un des plans (100) et (110).
16. Outil de liaison suivant la revendication 11, caractérisé en ce que la liaison entre la partie d'extrémité d'outil (3, 7) et la tige (6) est effectuée par de l'or formé par liaison par thermocompression.
17. Outil de liaison suivant la revendication 16, caractérisé en ce que la surface à lier de la partie d'extrémité d'outil (3, 7) et/ou de la tige (6) est revêtue, à titre de couche de renforcement de liaison, d'un mince film constitué d'un métal, alliage ou composé comprenant au moins un élément choisi parmi le groupe comprenant des éléments des groupes IVa, Va, VIa et VIIa du Tableau Périodique et, en tant que couche à l'épreuve de la diffusion, d'un mince film constitué d'un métal ou alliage comprenant au moins un élément choisi parmi le groupe constitué de Pt, Pd, W, Mo, Ta et Ni, de telle manière que la couche à l'épreuve de la diffusion soit située à l'extérieur de la couche de renforcement de liaison.
18. Outil de liaison suivant la revendication 16, caractérisé en ce que la tige (6) est pourvue, sur une partie de sa surface de liaison, d'une couche de modération d'effort thermique constituée d'un métal doux, tel que du Cu ou du Ni.