

Description

The present invention relates to an improvement in a melting and holding furnace for processing aluminum and other metals.

5 A known melting and holding furnace will be described with reference to Figs. 5 and 6 of the accompanying drawings. In the melting and holding furnace 'A', a raw material of aluminum is fed from a material preheating tower 20' to a melting chamber 21' continuous with the tower for heating and melting the material. Molten aluminum is then transferred to a holding chamber 8' communicating with the melting chamber 21', where the molten aluminum is heated by a sustaining burner 9' to be maintained at a selected temperature. The molten
10 aluminum is removed little by little, for casting, from a well 5' communicating with the holding chamber 8'.

With such a known melting and holding furnace A' used for melting aluminum, the well 5' cannot be integrated with the melting and holding furnace A' since the material preheating tower 20' and melting chamber 21' are provided separately. There is thus the disadvantage of a large overall configuration requiring a large installation space.

15 The melting chamber 21' includes a melting burner 4' which is a gas burner directed horizontally for producing, in elongated forms and with a weak jetting force, red reducing flames having a large infrared content. This prior construction has a disadvantage (1) of low operating efficiency. The material fed is little oxidized because of the reducing flames, but the flames sweep and melt only the faces of the material opposed to the flame jets, with its rear faces of the material being out of reach of the flames. This leaves a large unmolten
20 amount of material at the side remote from the flames. The operator must open a door 22' to the material preheating tower 20' to shove the unmolten material down into the melting chamber 21'. There is also a disadvantage (2) of low thermal efficiency. Because the melting burner 4' has a weak flame jetting force and because the melting burner 4' is directed horizontally, hot air flows contacting the material to be preheated produce little turbulence in the melting chamber 21' and just ascend gently without effectively preheating the material. Further, there is a disadvantage (3) of poor operating efficiency in that the weak flame jetting force results in a slow melting speed, and the long time taken for melting the material in turn results in low thermal efficiency.

DE-U-8800083 discloses a melting and holding furnace having a preheating and melting chamber. The preheating and melting chamber defines a material inlet, a preheating tower section in an upper position for holding
30 and preheating material supplied therinto and a melting section in a lower position for melting the preheated material. A melting burner is mounted on a lower side wall of the preheating tower section for jetting out flames from a lower position of said preheating tower section obliquely downwards into the melting section. A well receives the molten metal and allows the molten metal to be scooped out.

The present invention has been made having regard to the foregoing disadvantages of the prior art, and
35 its object is to provide a melting and holding furnace which is compact and requires a reduced installation space, and which realises improved operating efficiency and thermal efficiency.

According to the present invention, there is provided a melting and holding furnace comprising:

a preheating and melting chamber defining a material inlet, a preheating tower section in an upper position for holding and preheating material supplied therinto, and a melting section in a lower position for melting
40 the preheated material,

a well for receiving the molten metal and allowing the molten metal to be scooped out, and

a melting burner mounted on a lower side wall of said preheating tower section for jetting out flames from a lower position of said preheating tower section obliquely downwardly into said melting section,

characterised by a holding chamber which communicates with said melting chamber for receiving the
45 molten metal from said melting section and maintaining the molten metal at a selected temperature and with which the well communicates, and

in that the holding chamber has banks which are submerged by the molten metal and which cause the molten metal to flow in a zig-zag manner from the melting chamber to the well.

A preferred embodiment of the invention is disclosed in claim 2.

50 With the above construction, a material to be melted is first fed through the material inlet to fill the preheating tower section and melting section. Then, hot and strong reducing flames jet out of the melting burner obliquely downwardly toward the material. The flames reach the deep end of the melting section in a manner to envelope entire peripheries of the material in the melting section, thereby melting the material from the bottom at high speed. The melt thus formed in the melting section is at a low temperature just above the melting
55 point, which flows into the holding chamber. The melt is heated to a selected temperature by a sustaining burner in the holding chamber. The low temperature melt flows zig-zag along the submerged banks, while being heated in the holding chamber, and finally flows into the well. Meanwhile, deposits precipitate along the submerged banks, and occluded gas is released, whereby the melt becomes stabilized before entry into the well. The sta-

bilized melt is scooped little by little out of the well for use in casting. On the other hand, the flames having contacted the material become hot air flows tending to ascend the melting section. However, the strong flames jetting out obliquely downwardly obstruct ascent of the hot gas flows, thereby to produce strong turbulence in the melting section. Subsequently, the hot gas flows ascend the preheating tower section to preheat the material fed thereto.

As described above, the melting and holding furnace according to the present invention comprises a preheating and melting chamber defining a material inlet, a preheating tower section in an upper position for holding and preheating material supplied therinto, and a melting section in a lower position for melting the preheated material. This preheating and holding chamber may be compact. Consequently, the well too may be installed on the same base block and the entire furnace requires about two thirds of the installation area for the first described known melting and holding furnace.

Since the melting burner is mounted on a lower side wall of the preheating tower section for jetting out flames from a lower position of the preheating tower section obliquely downwardly into the melting section, the hot and strong reducing flames jetting out of the melting burner reach the deep end of the melting section in a manner to envelope entire peripheries of the material to be molten, thereby melting the material in the melting section at high speed. Further, since the strong flames jet out obliquely downwardly toward the melting section, these flames obstruct ascent of the hot gas flows in the melting section, thereby to produce strong turbulence in the melting section for promoting high-speed melting of the material. The hot gas flows from the melting section ascend the preheating tower section as agitated under the influence of the turbulence in the melting section, with increased chances of contact with the material to be molten thereby to produce a great preheating effect. These features realise great advantages in promoting the thermal efficiency and melting speed as well as operating efficiency.

A melting and holding furnace embodying the present invention will now be described with reference to the accompanying drawings in which:-

Fig. 1 is a sectional view of the melting and holding furnace;

Fig. 2 is a section taken on line A-A of Fig. 1;

Fig. 3 is a section taken on line B-B of Fig. 1;

Fig. 4 is a section taken on line C-C of Fig. 2;

Fig. 5 is a view in vertical section of a known melting and holding furnace; and

Fig. 6 is a sectional plan view of the known furnace.

Referring to Fig. 1, a melting and holding furnace A comprises a preheating and melting chamber 2 defining a material inlet 1, a preheating tower section 2a in an upper position for holding and preheating material supplied therinto, and a melting section 2b in a lower position for melting the preheated material. The furnace A further comprises a holding chamber 8 communicating with the melting chamber 2 for receiving the molten metal from the melting section 2b and maintaining it at a selected temperature, and a well 5 communicating with the holding chamber 8 for receiving the molten metal and allowing it to be scooped out. To describe their positional relations more particularly, as seen from Fig. 2, the preheating tower section 2a and melting section 2b are vertically integrated, with the preheating tower section 2a located above and the melting section 2b located below. The preheating tower section 2a is open at the top as at 1 defining the material inlet 1, and a cassette tower section 13 may be added thereto from above, as necessary, as shown in phantom lines.

A melting burner 4 is mounted on a lower side wall of the preheating tower section 2a for jetting out flames from a lower position of the preheating tower section 2a obliquely downwardly into the melting section 2b. This melting burner 4 comprises, for example, a high luminous flame burner for producing short and strong reducing flames. The position of the side wall at which the melting burner 4 is installed opens inwardly in a slightly flared way. The bottom of the melting section 2b is inclined downwardly toward the holding chamber 8 for allowing the molten metal to flow naturally into the holding chamber 8. The holding chamber 8 has a bottom at a lower level than the bottom of the melting chamber 2 and, in this embodiment, elongated in a direction substantially perpendicular to the direction of influx from the melting section 2b. In this embodiment, the holding chamber 8 includes submerged banks 11 projecting from the bottom and extending transversely of the holding chamber 8. The submerged banks 11 define staggered flow openings 12.

The holding chamber 8 includes a sustaining burner 9 for producing long red reducing flames having a large infrared content and jetting out from an molten metal inlet end toward an outlet end of the holding chamber 8. The flames sweep over the surface of melt 3 in the holding chamber 8 to maintain the melt 3 at a selected temperature.

A communicating opening 7 is defined in a downstream side wall of the holding chamber 8 to communicate with the well 5. Thus the well 5 is disposed substantially at right angles to the holding chamber 8. The preheating and melting chamber 2, holding chamber 8 and well 5 are provided on the same base 10 of the melting and holding furnace A to realize a very compact construction. The communicating opening 7 from the holding cham-

ber 8 to the well 5 may be defined in a bottom position of the partition wall to be lower than the melt surface as shown in Fig. 4, or may be opened to a higher position than the melt surface as shown in a phantom line, with a skim damper 6 vertically movable according to an operating state. The well 5 includes a device for detecting the level of melt 3 and a temperature sensor to control the surface level and temperature of the melt 3, thereby to ensure quality control for a subsequent process.

The material to be molten usually is, but not limited to, a die cast metal such as aluminum, zinc or copper. An operation will be described hereinafter, taking aluminum melting for example. Of course, the operation is not limited to melting of aluminum. The sustaining burner 9 directs long reducing flames having a large infrared content into the holding chamber 8, so that the flames sweep over the melt 3 in the holding chamber 8 to maintain the melt 3 at the selected temperature. On the other hand, aluminum raw material is fed through the material inlet 1 into the preheating tower section 2a at appropriate times as the melt 3 is scooped out, and is preheated by hot gas flows ascending the preheating tower section 2a. The material fed to be molten fills the preheating tower section 2a and melting section 2b, and the hot and strong reducing flames jetting out of the melting burner 4 reach the deep end of the melting section 2b in a manner to envelope entire peripheries of the material to be molten, thereby melting the material in the melting section 2b at high speed. Since the strong flames jet out obliquely downwardly toward the melting section 2b, these flames obstruct ascent of the hot gas flows in the melting section 2b, thereby to produce strong turbulence in the melting section 2b for promoting high-speed melting of the material. The hot gas flows from the melting section 2b ascend the preheating tower section 2a as agitated under the influence of the turbulence in the melting section 2b, with increased chances of contact with the material to be molten thereby to produce a great preheating effect.

Aluminum thus molten flows down the melting section 2b into the holding chamber 8, flows zigzag along the submerged banks 11, and finally into the well 5. The melt 3 immediately after its formation, whether through direct contact with the flames or through immersion, occludes a large amount of gas such as hydrogen gas. Such occluded gas is released during a long residence time of the melt flowing zigzag in the holding chamber 8 whereby the melt 3 becomes stabilized before entry into the well 5. Further, the melt 3 immediately after its formation is at a low temperature just above the melting point which produces deposits of iron, silicon and so forth on the bottom of the holding chamber 8. However, these deposits are prevented by the submerged banks 11 from flowing into the well 5. Further, the low-temperature melt 3 immediately after its formation flows zigzag along the banks 11 instead of flowing straight into the well 5, whereby the melt is heated to the selected temperature. Thus, there is no lowering of the melt temperature in the well 5.

The melt in the holding chamber 8 has the less weight because of the presence of the submerged banks 11, which results in a reduced area for exposure to the heat. The submerged banks 11 may be provided as appropriate.

The performance of the melting and holding furnace A according to the present invention was compared with that of the known melting and holding furnace A' by using a cold material. The results are shown in the following table:

<u>Starting from</u> <u>cold material</u>	<u>Known</u> <u>Furnace</u>	<u>Furnace of</u> <u>this Invention</u>
melting time	4.75 H	4.25 H
temp. rise time	0.5 H	0.5 H
gas consumption	305,100kcal/5.25H 11.3m ³	260,500kcal/4.25H 9.65m ³
thermal efficiency	20.3%	23.7%

The above results prove that the melting and holding furnace according to the present invention has a high-speed melting performance and produces an outstanding energy-saving effect.

Since integration is made down to the well 5, the entire furnace is very compact and requires two thirds of the installation area for the known melting and holding furnace A'.

Claims

1. A melting and holding furnace comprising:



ber 8 to the well 5 may be defined in a bottom position of the partition wall to be lower than the melt surface as shown in Fig. 4, or may be opened to a higher position than the melt surface as shown in a phantom line, with a skim damper 6 vertically movable according to an operating state. The well 5 includes a device for detecting the level of melt 3 and a temperature sensor to control the surface level and temperature of the melt 3, thereby to ensure quality control for a subsequent process.

The material to be molten usually is, but not limited to, a die cast metal such as aluminum, zinc or copper. An operation will be described hereinafter, taking aluminum melting for example. Of course, the operation is not limited to melting of aluminum. The sustaining burner 9 directs long reducing flames having a large infrared content into the holding chamber 8, so that the flames sweep over the melt 3 in the holding chamber 8 to maintain the melt 3 at the selected temperature. On the other hand, aluminum raw material is fed through the material inlet 1 into the preheating tower section 2a at appropriate times as the melt 3 is scooped out, and is preheated by hot gas flows ascending the preheating tower section 2a. The material fed to be molten fills the preheating tower section 2a and melting section 2b, and the hot and strong reducing flames jetting out of the melting burner 4 reach the deep end of the melting section 2b in a manner to envelope entire peripheries of the material to be molten, thereby melting the material in the melting section 2b at high speed. Since the strong flames jet out obliquely downwardly toward the melting section 2b, these flames obstruct ascent of the hot gas flows in the melting section 2b, thereby to produce strong turbulence in the melting section 2b for promoting high-speed melting of the material. The hot gas flows from the melting section 2b ascend the preheating tower section 2a as agitated under the influence of the turbulence in the melting section 2b, with increased chances of contact with the material to be molten thereby to produce a great preheating effect.

Aluminum thus molten flows down the melting section 2b into the holding chamber 8, flows zigzag along the submerged banks 11, and finally into the well 5. The melt 3 immediately after its formation, whether through direct contact with the flames or through immersion, occludes a large amount of gas such as hydrogen gas. Such occluded gas is released during a long residence time of the melt flowing zigzag in the holding chamber 8 whereby the melt 3 becomes stabilized before entry into the well 5. Further, the melt 3 immediately after its formation is at a low temperature just above the melting point which produces deposits of iron, silicon and so forth on the bottom of the holding chamber 8. However, these deposits are prevented by the submerged banks 11 from flowing into the well 5. Further, the low-temperature melt 3 immediately after its formation flows zigzag along the banks 11 instead of flowing straight into the well 5, whereby the melt is heated to the selected temperature. Thus, there is no lowering of the melt temperature in the well 5.

The melt in the holding chamber 8 has the less weight because of the presence of the submerged banks 11, which results in a reduced area for exposure to the heat. The submerged banks 11 may be provided as appropriate.

The performance of the melting and holding furnace A according to the present invention was compared with that of the known melting and holding furnace A' by using a cold material. The results are shown in the following table:

<u>Starting from</u> <u>cold material</u>	<u>Known</u> <u>Furnace</u>	<u>Furnace of</u> <u>this Invention</u>
melting time	4.75 H	4.25 H
temp. rise time	0.5 H	0.5 H
gas consumption	305,100kcal/5.25H 11.3m ³	260,500kcal/4.25H 9.65m ³
thermal efficiency	20.3%	23.7%

The above results prove that the melting and holding furnace according to the present invention has a high-speed melting performance and produces an outstanding energy-saving effect.

Since integration is made down to the well 5, the entire furnace is very compact and requires two thirds of the installation area for the known melting and holding furnace A'.

Claims

1. A melting and holding furnace comprising:



a preheating and melting chamber (2) defining a material inlet (1), a preheating tower section (2a) in an upper position for holding and preheating material supplied thereto, and a melting section (2b) in a lower position for melting the preheated material,

5 a well (5) for receiving the molten metal and allowing the molten metal to be scooped out, and
a melting burner (4) mounted on a lower side wall of said preheating tower section (2a) for jetting out flames from a lower position of said preheating tower section (2a) obliquely downwardly into said melting section (2b),

10 characterised by a holding chamber (8) which communicates with said melting chamber (2) for receiving the molten metal from said melting section (2b) and maintaining the molten metal at a selected temperature and with which the well (5) communicates, and

in that the holding chamber (8) has banks (11) which are submerged by the molten metal and which cause the molten metal to flow in a zig-zag manner from the melting chamber (2) to the well (5).

15 2. A melting and holding furnace according to claim 1, characterised by a vertically movable skim damper (6) disposed between said holding chamber (8) and said well (5).

Patentansprüche

20 1. Ein Schmelz- und Warmhalteofen mit:

einer Vorheiz- und Schmelzkammer (2), die einen Materialeinlaß (1) festlegt, einem Vorheizturmabschnitt (2a) in einer oberen Lage zur Aufnahme und zum Vorheizen von dort hineingegebenem Material und einem Schmelzabschnitt (2b) in einer unteren Lage zum Schmelzen des vorgewärmten Materials,

25 einer Pfanne (5) zur Aufnahme des geschmolzenen Metalls, die das Herausschöpfen des geschmolzenen Metalls erlaubt, und

einem Schmelzbrenner (4), der an einer unteren Seitenwand des Vorheizturmabschnittes (2a) zum Abstrahlen von Flammen von einer unteren Position des Vorheizturmabschnittes (2a) schräg nach unten in den Schmelzabschnitt (2b) angeordnet ist,

30 gekennzeichnet durch eine Warmhalte- und Schmelzkammer (8), die mit der Schmelzkammer (2) zur Aufnahme des geschmolzenen Metalls von dem Schmelzabschnitt (2b) kommuniziert und das geschmolzene Metall auf einer vorgewählten Temperatur hält und mit der Pfanne (5) kommuniziert, und dadurch,

daß die Warmhalte- und Schmelzkammer (8) Dämme (11) aufweist, die von dem geschmolzenen Metall überflutet sind und das geschmolzene Metall zwingen, in einer Zickzack-Form von der Schmelzkammer (2) zu der Pfanne (5) zu fließen.

35 2. Ein Schmelz- und Warmhalteofen nach Anspruch 1, gekennzeichnet durch einen vertikal bewegbaren Schlackendämpfer (6), der zwischen der Warmhalte- und Schmelzkammer (8) und der Pfanne (5) angeordnet ist.

40 Revendications

1. Four de fusion et de maintien en température comprenant :

45 une chambre (2) de préchauffage et de fusion définissant une entrée de matière (1), un tronçon (2a) de tour de préchauffage à une position supérieure pour contenir et préchauffer de la matière qui lui est fournie, et un tronçon (2b) de fusion à une position inférieure pour la fusion de la matière préchauffée, un puits (5) pour la réception du métal en fusion et pour permettre au métal en fusion d'être prélevé, et

50 un brûleur (4) de fusion monté dans une paroi latérale inférieure du tronçon (2a) de tour de préchauffage pour projeter des flammes obliquement vers le bas dans le tronçon (2b) de fusion à partir d'une position inférieure dudit tronçon (2a) de tour de préchauffage,

caractérisé par une chambre (8) de maintien en température qui communique avec la chambre de fusion (2) pour la réception du métal en fusion en provenance du tronçon (2b) de fusion et pour le maintien de ce métal en fusion à une température sélectionnée et avec laquelle le puits (5) communique, et

55 en ce que la chambre (8) de maintien en température a des cloisons internes (11) qui sont submergées par le métal en fusion et qui obligent ce dernier à couler en zigzag de la chambre (2) de fusion au puits (5).



2. Four de fusion et de maintien en température selon la revendication 1, caractérisé par un barrage (6) mobile en sens vertical pour les scories disposé entre la chambre (8) de maintien en température et le puits (5).

5

10

15

20

25

30

35

40

45

50

55