

Abstract

Provided are a propylene homopolymer composition for a capacitor film, from which a thin film can be easily produced and which can provide a film with excellent high-temperature voltage resistance, a method for producing the same, and a capacitor film. The propylene homopolymer composition for a capacitor film contains 1 % by mass or more and less than 50 % by mass of a propylene homopolymer (A1) having predetermined characteristics and more than 50 % by mass and 99 % by mass or less of a propylene homopolymer (B1) having predetermined characteristics, and has (i) a melt flow rate (MFR) of 1.0 to 10.0 g/10 min and (ii) a chlorine content of 2 ppm by mass or less.