

DESCRIPTION

Co-Cr-Pt-BASED SPUTTERING TARGET AND METHOD FOR PRODUCING SAME

[Technical Field]

[0001] The present invention relates to a sputtering target for forming a granular film of a magnetic recording medium in a vertical magnetic recording HDD (hard disk drive), and particularly relates to a Co-Cr-Pt-based sputtering target with oxides finely dispersed therein.

BACKGROUND

[0002] In the field of magnetic recording as represented by hard disk drives, materials based on Co, Fe or Ni, which are ferromagnetic metals, are being used as materials of a magnetic thin film in a magnetic recording medium.

[0003] As the magnetic thin film of a hard disk drive adopting the vertical magnetic recording method that has been put into practical use in recent years, often used is a composite material configured from a Co-Cr-Pt-based ferromagnetic alloy having Co as its main component and nonmagnetic inorganic particles. In addition, the foregoing magnetic thin film is often produced by sputtering a sintered compact sputtering target made from foregoing materials via a DC magnetron sputtering device in light of its high productivity.

[0004] Meanwhile, when sputtering is performed using a sputtering device, there is a problem in that particles are generated. It is known that most of the particles that are generated during the deposition of a granular film are caused by the oxides in the target structure. In recent years, since the floating height of a magnetic head is decreasing in a hard disk drive pursuant to the increase in recording density, the size and number of particles that are tolerable in a magnetic recording medium are becoming even more strictly regulated.

[0005] Various techniques are known in relation to a sputtering target for forming a granular film and its production method (for instance, Patent Documents 1 to 4). For example, Patent Document 1 discloses a method for suppressing the aggregation of oxide particles, refining the target structure, and reducing the generation of particles by mixing a primary sintered compact powder, which is obtained by mixing, sintering

and pulverizing a part of the raw material powder in advance, upon mixing and pulverizing the raw material powder using a ball mill or the like.

[Prior Art Documents]

[Patent Documents]

- 5 [0006] Patent Document 1: Japanese Patent Application Publication No. 2011-208169
Patent Document 2: Japanese Patent Application Publication No. 2011-174174
Patent Document 3: Japanese Patent Application Publication No. 2011-175725
Patent Document 4: Japanese Patent Application No. 2011-5363231

10

SUMMARY OF THE INVENTION

[Problems to be Solved by the Invention]

[0007] Generally speaking, upon producing a sputtering target for forming a granular film, there are cases where nonmagnetic oxides become aggregated, and particles are generated during sputtering with such aggregated oxides as the source. The conventional technologies described above disperse the oxides in the sputtering target in a parent phase alloy to suppress the generation of particles.

15

[0008] Nevertheless, in cases where Ti (titanium) oxide is used as the nonmagnetic oxide, in certain cases the Ti oxide and metal Cr (chromium) would react during sintering and form coarse complex oxide grains, and, in addition to the aggregation of oxides, these coarse complex oxide grains would also become the cause of the generation of particles.

20

In light of the foregoing problems, an object of this invention is to provide a sputtering target for forming a granular film which suppresses the formation of the foregoing coarse complex oxide grains and generates fewer particles during sputtering.

25

[Means for Solving the Problems]

[0009] In order to achieve the foregoing object, as a result of intense study, the present inventors discovered that the formation of the coarse complex oxide grains can be suppressed by restricting the contact of metal Cr and Ti oxide. The present inventors further discovered that the thus produced sputtering target can reduce the generation of particles since oxides are finely dispersed in the parent phase alloy, and improve the yield during deposition.

30

[0010] Based on the foregoing discovery, the present invention provides the following:

1) A sputtering target containing, as metal components, 0.5 to 45 mol% of Cr and remainder being Co, and containing, as non-metal components, two or more types of oxides including Ti oxide, wherein a structure of the sputtering target is configured from regions where oxides including at least Ti oxide are dispersed in Co (non-Cr-based regions), and a region where oxides other than Ti oxide are dispersed in Cr or Co-Cr (Cr-based region), and the non-Cr-based regions are scattered in the Cr-based region.

2) A sputtering target containing, as metal components, 0.5 to 30 mol% of Cr, 0.5 to 30 mol% of Pt, and remainder being Co, and containing, as non-metal components, two or more types of oxides including Ti oxide, wherein a structure of the sputtering target is configured from regions where oxides including at least Ti oxide are dispersed in Co or Co-Pt (non-Cr-based regions), and a region where oxides other than Ti oxide are dispersed in one or more types of phases of Co-Cr, Cr-Pt, and Co-Cr-Pt (Cr-based region), and the non-Cr-based regions are scattered in the Cr-based region.

3) The sputtering target according to 1) or 2) above, wherein the two or more types of oxides (excluding Ti oxide) are oxides of one or more types of elements selected from B, Mg, Al, Si, Cr, Zr, Nb, and Ta.

4) The sputtering target according to any one of 1) to 3) above, wherein a content of the oxides in the sputtering target is, based on a volume ratio, 20% or more and less than 50%.

5) The sputtering target according to any one of 1) to 4) above, wherein the sputtering target additionally contains, as metal components, one or more types of elements selected from B, Cu, Mo, Ru, Ta, and W.

[0011] 6) A method of producing a sputtering target comprising a step of mixing a metal powder and an oxide powder including Ti oxide and pressing and sintering a resulting mixed powder A in a vacuum or an inert gas atmosphere to produce a sintered compact A, and pulverizing and sieving the sintered compact A to produce a sintered compact powder A corresponding to the non-Cr-based regions, a step of mixing a metal powder and oxide powders other than Ti oxide to produce a mixed powder B corresponding to the Cr-based region, and a step of mixing the sintered compact powder A and the mixed powder B, and thereafter pressing and sintering a

resulting mixed powder in a vacuum or an inert gas atmosphere to produce a secondary sintered compact to be used as a target material.

7) The method of producing a sputtering target according to 6) above, wherein a grain size of the sintered compact powder A is 20 to 200 μm .

[Effect of the Invention]

According to the Co-Cr-Pt-based sputtering target of the present invention, the formation of the coarse complex oxide grains can be inhibited by restricting the reaction of Ti oxide and metal Cr, and the dispersibility of oxides can be improved. Thus, the present invention yields superior effects of being able to reduce the amount of particles that are generated during sputtering, and improve the yield during deposition.

BRIEF DESCRIPTION OF THE DRAWING

[Fig. 1] Fig. 1 is an image of the target structure upon observing the target of Example 3 using an optical microscope.

DETAILED DESCRIPTION OF THE INVENTION

The sputtering target of the present invention is characterized in containing, as metal components, 0.5 to 45 mol% of Cr and remainder being Co, and containing, as non-metal components, two or more types of oxides including Ti oxide, wherein a structure of the sputtering target is configured from regions where oxides including at least Ti oxide are dispersed in Co (non-Cr-based regions), and a region where oxides other than Ti oxide are dispersed in Cr or Co-Cr (Cr-based region), and the non-Cr-based regions are scattered in the Cr-based region.

The sputtering target of the present invention can restrict the formation of coarse complex oxides since Ti oxide and metal Cr (or Cr alloy) will not react during sintering, and thereby suppress the generation of particles caused by the reaction of Ti oxide and metal Cr (or Cr alloy).

Moreover, since the area of these individual oxide particles will affect the generation of particles, the mean area of the individual oxide particles is desirably less than $2.0 \mu\text{m}^2$.

[0015] Moreover, the sputtering target of the present invention contains, as metal components, 0.5 to 30 mol% of Cr, 0.5 to 30 mol% of Pt, and remainder being Co, and contains, as non-metal components, two or more types of oxides including Ti oxide, wherein a structure of the sputtering target is configured from regions where oxides including at least Ti oxide are dispersed in Co or Co-Pt (non-Cr-based regions), and a region where oxides other than Ti oxide are dispersed in one or more types of phases of Co-Cr, Cr-Pt, and Co-Cr-Pt (Cr-based region), and the non-Cr-based regions are scattered in the Cr-based region.

The Cr-based region includes the three types of Co-Cr, Cr-Pt, and Co-Cr-Pt as described above, but includes a state (structure) in which oxides other than Ti oxide are dispersed in one or more such types. The sputtering target of the present invention can restrict the formation of coarse complex oxides since Ti oxide and Cr alloy will not react during sintering, and thereby suppress the generation of particles caused by the reaction of Ti oxide and Cr alloy.

Similar to the above, since the area of these individual oxide particles will affect the generation of particles, the mean area of the individual oxide particles is desirably less than $2.0 \mu\text{m}^2$.

[0016] Moreover, with the sputtering target of the present invention, the two or more types of oxides (excluding Ti oxide) are oxides of one or more types of elements selected from B, Mg, Al, Si, Cr, Zr, Nb, and Ta. Since these nonmagnetic oxides do not react as easily with metal Cr or Cr alloy in comparison to Ti oxide, these oxides may be dispersed in metal Cr or Cr alloy.

Moreover, with the sputtering target of the present invention, the content of nonmagnetic component oxides in the sputtering target is, based on a volume ratio, 20% or more and less than 50%. Favorable magnetic properties can be obtained when the volume ratio of the nonmagnetic oxides is 20% or more and less than 50%.

[0017] Moreover, the sputtering target of the present invention additionally contains, as metal components, one or more types of elements selected from B, Cu, Mo, Ru, Ta, and W. These metal components may be suitably added in accordance with the intended magnetic properties.

Note that, when B is added as a metal component, depending on the target composition, there are cases where B is reduced to another oxide during sintering and forms B_2O_3 , but this is a level that can be quantitatively ignored. Accordingly, it could be said that the B existing in the target derives from the B that was added as a metal

component, and the B_2O_3 existing in the target derives from the B_2O_3 that was added as an oxide.

[0018] The sputtering target of the present invention can be produced, for example, based on the following method.

5 For example, a Co powder, a Cr powder and a Pt powder are prepared as the metal powders, a TiO_2 powder and a SiO_2 powder are prepared as the oxide powders, and, among the foregoing raw material powders, metal powders (Co powder, Pt powder) other than the Cr powder and oxide powders including at least the TiO_2 powder are mixed to obtain a mixed powder (mixed powder A). As described above, 10 with the present invention, it is important that the Ti oxide, which easily reacts with metal Cr or Cr alloy, and metals other than Cr are mixed and caused to react in advance. Here, the mixed powder A refers to a mixed powder obtained by mixing powders (Co, Pt) other than Cr as the metal components, and oxide powders including at least Ti oxide as the non-metal components.

15 [0019] Subsequently, the obtained mixed powder (mixed powder A) is pressed and sintered in a vacuum or an inert gas atmosphere to produce a sintered compact (sintered compact A), and the sintered compact is pulverized and sieved to produce a sintered compact powder (sintered compact powder A) corresponding to the non-Cr-based regions. Here, the sintered compact powder A refers to a powder 20 obtained by mixing and sintering powders (Co, Pt) other than Cr as the metal components, and oxide powders including at least Ti oxide as the non-metal components, and thereafter pulverizing and sieving the obtained sintered compact.

Here, the grain size of the sintered compact powder A is preferably 20 to 200 μm . When the grain size is less than 20 μm , the contact area of the non-Cr regions and the Cr region will increase, and it becomes difficult to suppress the 25 reaction of metal Cr or Cr alloy and Ti oxide during sintering. Meanwhile, when the grain size exceeds 200 μm , it may not be possible to obtain a sputtered film having a uniform composition upon sputtering.

[0020] Subsequently, the Cr powder and the oxide powder (SiO_2 powder) other 30 than the TiO_2 powder are mixed to obtain a mixed powder (mixed powder B) corresponding to the Cr-based region. Here, the mixed powder B refers to a mixed powder obtained by mixing powders including at least Cr as the metal components, and oxide powders other than Ti oxide as the non-metal components.

[0021] Subsequently, the sintered compact powder A and the mixed powder B are mixed, and the obtained mixed powder is thereafter pressed and sintered in a vacuum or an inert gas atmosphere to produce a secondary sintered compact to be used as the target material. The thus obtained secondary sintered compact is processed into an intended shape to produce the sputtering target of the present invention.

[0022] It is thereby possible to produce a Co-Cr-Pt-based sputtering target in which oxides are uniformly and finely dispersed therein and which is free from the formation of coarse complex oxide grains caused by the reaction of Ti oxide and metal Cr or Cr alloy. The thus produced sputtering target of the present invention is useful as a sputtering target for use in depositing a magnetic thin film having a granular structure.

Examples

[0023] The present invention is now explained based on the following Examples and Comparative Examples. Note that these Examples are merely illustrative, and the present invention is not limited in any way by these Examples. In other words, the present invention is limited only based on its scope of claims, and the present invention covers various modifications other than the Examples included herein.

[0024] (Example 1)

A Co powder having an average grain size of 3 μm and a Cr powder having an average grain size of 5 μm were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of 1 μm and a SiO_2 powder having an average grain size of 1 μm were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 1600 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 90.5Co-9.5 TiO_2 (mol%)

(Mixed powder B): 72.36Co-20.73Cr-6.91 SiO_2 (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and

thereafter sieved using sieves having a sieve opening of 50 μm and 150 μm to obtain a sintered compact powder A having a grain size of 50 to 150 μm .

[0025] Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 726.7 g and the mixed powder B was weighed to be 944.1 g, so that the composition of the overall sputtering target resulted in the following composition ratio. (Target composition): 80Co-12Cr-4TiO₂-4SiO₂ (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1050°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.2% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0026] Upon observing the microstructure of the sputtering target of Example 1, it was confirmed that the structure included regions (non-Cr-based regions) in which TiO₂ is dispersed in Co, and a region (Cr-based region) in which SiO₂ is dispersed in a Co-Cr alloy, and the non-Cr-based regions are scattered in the Cr-based region. In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm $\times$ 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 1.1 μm^2 .

[0027] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 5 particles.

[0028] (Comparative Example 1)

A Co powder having an average grain size of 3 μm and a Cr powder having an average grain size of 5 μm were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of 1 μm and a SiO_2 powder having an average grain size of 1 μm were prepared as oxide raw material powders. Subsequently, these powders were weighed to be 1670.7 g in total so that the composition of the overall sputtering target resulted in the following composition ratio. (Target composition): 80Co-12Cr-4 TiO_2 -4 SiO_2 (mol%)

The weighed powders were placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. The thus obtained mixed powder was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1050°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.2% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

Upon observing the microstructure of the sputtering target of Comparative Example 1, it was confirmed that TiO_2 and SiO_2 were dispersed in a Co-Cr alloy. In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 $\mu\text{m} \times 75 \mu\text{m}$ at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 2.1 μm^2 , and the oxides had coarsened in comparison to Example 1.

Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 13 particles, and the number of particles had increased in comparison to Example 1.

(Example 2)

A Co powder having an average grain size of 3 μm , a Cr powder having an average grain size of 5 μm and a Pt powder having an average grain size of 2 μm were prepared as metal raw material powders, and a TiO_2 powder having an average

grain size of 1 μm , a SiO_2 powder having an average grain size of 1 μm and a Cr_2O_3 powder having an average grain size of 3 μm were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 68.15Co-22.29Pt-4.78TiO₂-4.78Cr₂O₃ (mol%)

(Mixed powder B): 59.68Co-32.26Cr-8.06SiO₂ (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of 38 μm and 106 μm to obtain a sintered compact powder A having a grain size of 38 to 106 μm .

Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 1550.6 g and the mixed powder B was weighed to be 550.6 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-14Pt-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1100°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 97.9% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

Upon observing the microstructure of the sputtering target of Example 2, it was confirmed that the structure included regions (non-Cr-based regions) in which TiO₂ and Cr₂O₃ are dispersed in Co-Pt, and a region (Cr-based region) in which SiO₂ is dispersed in a Co-Cr alloy, and the non-Cr-based regions are scattered in the Cr-based region. In addition, the structure of the polished surface of the target was

photographed in a visual field size of $100\ \mu\text{m} \times 75\ \mu\text{m}$ at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was $1.4\ \mu\text{m}^2$.

5 [0034] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the
10 substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 3 particles.

[0035] (Example 3)

A Co powder having an average grain size of $3\ \mu\text{m}$, a Cr powder having an average grain size of $5\ \mu\text{m}$ and a Pt powder having an average grain size of $2\ \mu\text{m}$
15 were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1\ \mu\text{m}$, a SiO_2 powder having an average grain size of $1\ \mu\text{m}$ and a Cr_2O_3 powder having an average grain size of $3\ \mu\text{m}$ were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

20 (Mixed powder A): 81.76Co-9.12Pt-4.56TiO₂-4.56Cr₂O₃ (mol%)

(Mixed powder B): 32.75Co-35.09Cr-23.39Pt-8.77SiO₂ (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon
25 mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of $38\ \mu\text{m}$ and $106\ \mu\text{m}$ to obtain
30 a sintered compact powder A having a grain size of 38 to $106\ \mu\text{m}$.

[0036] Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 1312.0 g and the mixed powder B was weighed to be 788.0 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-14Pt-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1100°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 97.6% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0037] Upon observing the microstructure of the sputtering target of Example 3, it was confirmed that the structure included regions (non-Cr-based regions) in which TiO₂ and Cr₂O₃ are dispersed in Co-Pt, and a region (Cr-based region) in which SiO₂ is dispersed in a Co-Cr-Pt alloy, and the non-Cr-based regions are scattered in the Cr-based region. The photograph of the structure of the target of Example 3 is shown in Fig. 1. In Fig. 1, the area inside the thick frame is Co-Pt-TiO₂-Cr₂O₃ (non-Cr-based regions), and the area outside the thick frame is Co-Cr-Pt-SiO₂ (Cr-based region).

In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 1.5 μm².

[0038] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 2 particles.

[0039] (Comparative Example 2)

A Co powder having an average grain size of 3 μm, a Cr powder having an average grain size of 5 μm and a Pt powder having an average grain size of 2 μm were prepared as metal raw material powders, and a TiO₂ powder having an average grain size of 1 μm, a SiO₂ powder having an average grain size of 1 μm and a Cr₂O₃ powder

having an average grain size of 3 μm were prepared as oxide raw material powders. Subsequently, these powders were weighed to be 2100.0 g in total so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-14Pt-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

5 The weighed powders were placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. The thus obtained mixed powder was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1100°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.6% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0040] Upon observing the microstructure of the sputtering target of Comparative Example 2, it was confirmed that TiO₂, SiO₂ and Cr₂O₃ were dispersed in a Co-Cr-Pt alloy. In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 2.3 μm^2 , and the oxides had coarsened in comparison to Examples 2 and 3.

20 [0041] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 15 particles, and the number of particles had increased in comparison to Examples 2 and 3.

[0042] (Comparative Example 3)

30 A Co powder having an average grain size of 3 μm , a Cr powder having an average grain size of 5 μm and a Pt powder having an average grain size of 2 μm were prepared as metal raw material powders, and a TiO₂ powder having an average grain size of 1 μm , a SiO₂ powder having an average grain size of 1 μm and a Cr₂O₃ powder having an average grain size of 3 μm were prepared as oxide raw material

powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 81.76Co-9.12Pt-4.56TiO₂-4.56Cr₂O₃ (mol%)

(Mixed powder B): 32.75Co-35.09Cr-23.39Pt-8.77SiO₂ (mol%)

5 The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, to
10 obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter classified using an air classifier to obtain a sintered compact powder A having an average grain size of 18 μm.

[0043] Subsequently, the sintered compact powder A and the mixed powder B
15 were respectively weighed; specifically, the sintered compact powder A was weighed to be 1312.0 g and the mixed powder B was weighed to be 788.0 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-14Pt-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

20 The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of
25 1100°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 97.6% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0044] Upon observing the microstructure of the sputtering target of Comparative
30 Example 3, the structure did not enable the confirmation of a clear differentiation of regions (non-Cr-based regions) in which TiO₂ and Cr₂O₃ are dispersed in Co-Pt, and a region (Cr-based region) in which SiO₂ is dispersed in a Co-Cr-Pt alloy.

 In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was

binarized using image processing software to obtain a mean area per oxide particle, whereby the result was $2.1 \mu\text{m}^2$, and the oxides had coarsened in comparison to Examples 2 and 3.

[0045] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 10 particles, and the number of particles had increased in comparison to Examples 2 and 3.

[0046] (Comparative Example 4)

A Co powder having an average grain size of $3 \mu\text{m}$, a Cr powder having an average grain size of $5 \mu\text{m}$ and a Pt powder having an average grain size of $2 \mu\text{m}$ were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1 \mu\text{m}$, a SiO_2 powder having an average grain size of $1 \mu\text{m}$ and a Cr_2O_3 powder having an average grain size of $3 \mu\text{m}$ were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 75.34Co-16.44Pt-4.11SiO₂-4.11Cr₂O₃ (mol%)

(Mixed powder B): 37.04Co-44.44Cr-7.41Pt-11.11TiO₂ (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1100°C, holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of $38 \mu\text{m}$ and $106 \mu\text{m}$ to obtain a sintered compact powder A having a grain size of 38 to $106 \mu\text{m}$.

[0047] Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 1619.9 g and the mixed powder B was weighed to be 480.1 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-14Pt-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.1% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0048] Upon observing the microstructure of the sputtering target of Comparative Example 4, it was confirmed that the structure included regions in which SiO₂ and Cr₂O₃ are dispersed in Co-Pt, and a region in which TiO₂ is dispersed in a Co-Cr-Pt alloy, and the regions in which SiO₂ and Cr₂O₃ are dispersed in Co-Pt are scattered in the region in which TiO₂ is dispersed in a Co-Cr-Pt alloy.

In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 2.6 μm², and the oxides had coarsened in comparison to Examples 2 and 3.

[0049] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 18 particles, and the number of particles had increased in comparison to Examples 2 and 3.

[0050] (Example 4)

A Co powder having an average grain size of 3 μm, a Cr powder having an average grain size of 5 μm, a Pt powder having an average grain size of 2 μm and a B powder having an average grain size of 10 μm were prepared as metal raw material powders, and a TiO₂ powder having an average grain size of 1 μm and a SiO₂ powder

having an average grain size of 1 μm were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 80.96Co-9.52Pt-9.52TiO₂ (mol%)

(Mixed powder B): 53.45Co-20.69Cr-13.79Pt-5.17B-6.9SiO₂ (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of 38 μm and 106 μm to obtain a sintered compact powder A having a grain size of 38 to 106 μm .

Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 1217.8 g and the mixed powder B was weighed to be 882.2 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-12Pt-3B-4TiO₂-4SiO₂ (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 96.5% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

Upon observing the microstructure of the sputtering target of Example 4, it was confirmed that the structure included regions (non-Cr-based regions) in which TiO₂ is dispersed in Co-Pt, and a region (Cr-based region) in which SiO₂ is dispersed in a Co-Cr-Pt-B alloy, and the non-Cr-based regions are scattered in the Cr-based region.

In addition, the structure of the polished surface of the target was photographed in a visual field size of $100\ \mu\text{m} \times 75\ \mu\text{m}$ at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was $1.8\ \mu\text{m}^2$.

[0053] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 6 particles.

[0054] (Comparative Example 5)

A Co powder having an average grain size of $3\ \mu\text{m}$, a Cr powder having an average grain size of $5\ \mu\text{m}$, a Pt powder having an average grain size of $2\ \mu\text{m}$ and a B powder having an average grain size of $10\ \mu\text{m}$ were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1\ \mu\text{m}$ and a SiO_2 powder having an average grain size of $1\ \mu\text{m}$ were prepared as oxide raw material powders. Subsequently, these powders were weighed to be 2100.0 g in total so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 65Co-12Cr-12Pt-3B-4 TiO_2 -4 SiO_2 (mol%)

The weighed powders were placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. The thus obtained mixed powder was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C , holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 96.2% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0055] Upon observing the microstructure of the sputtering target of Comparative Example 5, it was confirmed that TiO_2 and SiO_2 were dispersed in a Co-Cr-Pt-B alloy. In addition, the structure of the polished surface of the target was photographed in a visual field size of $100\ \mu\text{m} \times 75\ \mu\text{m}$ at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image

processing software to obtain a mean area per oxide particle, whereby the result was $2.5 \mu\text{m}^2$, and the oxides had coarsened in comparison to Example 4.

[0056] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 19 particles, and the number of particles had increased in comparison to Example 4.

[0057] (Example 5)

A Co powder having an average grain size of $3 \mu\text{m}$, a Cr powder having an average grain size of $5 \mu\text{m}$, a Pt powder having an average grain size of $2 \mu\text{m}$ and a Ru powder having an average grain size of $10 \mu\text{m}$ were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1 \mu\text{m}$, a SiO_2 powder having an average grain size of $1 \mu\text{m}$ and a Cr_2O_3 powder having an average grain size of $3 \mu\text{m}$ were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 89.29Co-10.71 TiO_2 (mol%)

(Mixed powder B): 54.16Co-16.67Cr-13.89Pt-6.94Ru-4.17 SiO_2 -4.17 Cr_2O_3 (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C , holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of $38 \mu\text{m}$ and $106 \mu\text{m}$ to obtain a sintered compact powder A having a grain size of 38 to $106 \mu\text{m}$.

[0058] Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 465.5 g and the mixed powder B was weighed to be 1634.5 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 64Co-12Cr-10Pt-5Ru-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1100°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.8% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0059] Upon observing the microstructure of the sputtering target of Example 5, it was confirmed that the structure included regions (non-Cr-based regions) in which TiO₂ is dispersed in Co, and a region (Cr-based region) in which SiO₂ and Cr₂O₃ are dispersed in a Co-Cr-Pt-Ru alloy, and the non-Cr-based regions are scattered in the Cr-based region.

In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 1.1 μm².

[0060] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 2 particles.

[0061] (Comparative Example 6)

A Co powder having an average grain size of 3 μm, a Cr powder having an average grain size of 5 μm, a Pt powder having an average grain size of 2 μm, and a Ru powder having an average grain size of 10 μm were prepared as metal raw material powders, and a TiO₂ powder having an average grain size of 1 μm, a SiO₂ powder having an average grain size of 1 μm and a Cr₂O₃ powder having an average grain size of 3 μm were prepared as oxide raw material powders. Subsequently, these

powders were weighed to be 2100.0 g in total so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 64Co-12Cr-10Pt-5Ru-3TiO₂-3SiO₂-3Cr₂O₃ (mol%)

5 The weighed powders were placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. The thus obtained mixed powder was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1100°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.9% was obtained. In addition, the obtained
10 sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0062] Upon observing the microstructure of the sputtering target of Comparative Example 6, it was confirmed that TiO₂, SiO₂ and Cr₂O₃ were dispersed in a Co-Cr-Pt-Ru alloy. In addition, the structure of the polished surface of the target was
15 photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 2.0 μm², and the oxides had coarsened in comparison to Example 5.

20 [0063] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the
25 substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 12 particles, and the number of particles had increased in comparison to Example 5.

[0064] (Example 6)

30 A Co powder having an average grain size of 3 μm, a Cr powder having an average grain size of 5 μm, and a Pt powder having an average grain size of 2 μm were prepared as metal raw material powders, and a TiO₂ powder having an average grain size of 1 μm, a SiO₂ powder having an average grain size of 1 μm and a B₂O₃ powder having an average grain size of 10 μm were prepared as oxide raw material

powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 89.29Co-10.71TiO₂ (mol%)

(Mixed powder B): 61.11Co-16.67Cr-13.89Pt-4.17SiO₂-4.17B₂O₃ (mol%)

5 The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C, holding time of 2 hours, and pressure of 30 MPa, to
10 obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of 38 μm and 106 μm to obtain a sintered compact powder A having a grain size of 38 to 106 μm.

[0065] Subsequently, the sintered compact powder A and the mixed powder B
15 were respectively weighed; specifically, the sintered compact powder A was weighed to be 471.4 g and the mixed powder B was weighed to be 1528.6 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 69Co-12Cr-10Pt-3TiO₂-3SiO₂-3B₂O₃ (mol%)

20 The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of
25 850°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.3% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0066] Upon observing the microstructure of the sputtering target of Example 6, it
30 was confirmed that the structure included regions (non-Cr-based regions) in which TiO₂ is dispersed in Co, and a region (Cr-based region) in which SiO₂ and B₂O₃ are dispersed in a Co-Cr-Pt alloy, and the non-Cr-based regions are scattered in the Cr-based region.

 In addition, the structure of the polished surface of the target was photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected

locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was $1.9 \mu\text{m}^2$.

[0067] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 6 particles.

[0068] (Comparative Example 7)

A Co powder having an average grain size of $3 \mu\text{m}$, a Cr powder having an average grain size of $5 \mu\text{m}$, and a Pt powder having an average grain size of $2 \mu\text{m}$ were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1 \mu\text{m}$, a SiO_2 powder having an average grain size of $1 \mu\text{m}$ and a B_2O_3 powder having an average grain size of $10 \mu\text{m}$ were prepared as oxide raw material powders. Subsequently, these powders were weighed to be 2000.0 g in total so that the composition of the overall sputtering target resulted in the following composition ratio. (Target composition): 69Co-12Cr-10Pt-3TiO₂-3SiO₂-3B₂O₃ (mol%)

The weighed powders were placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. The thus obtained mixed powder was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 850°C , holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.7% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0069] Upon observing the microstructure of the sputtering target of Comparative Example 7, it was confirmed that TiO_2 and SiO_2 and B_2O_3 were dispersed in a Co-Cr-Pt alloy. In addition, the structure of the polished surface of the target was photographed in a visual field size of $100 \mu\text{m} \times 75 \mu\text{m}$ at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle,

whereby the result was $3.1 \mu\text{m}^2$, and the oxides had coarsened in comparison to Example 6.

[0070] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 18 particles, and the number of particles was larger in comparison to Example 6.

[0071] (Example 7)

A Co powder having an average grain size of $3 \mu\text{m}$, a Cr powder having an average grain size of $5 \mu\text{m}$, and a Pt powder having an average grain size of $2 \mu\text{m}$ were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1 \mu\text{m}$, a SiO_2 powder having an average grain size of $1 \mu\text{m}$ and a MnO powder having an average grain size of $3 \mu\text{m}$ were prepared as oxide raw material powders. In addition, the respective powders were each weighed to be 2000 g based on the following composition ratio to prepare a mixed powder A and a mixed powder B.

(Mixed powder A): 89.29Co-10.71 TiO_2 (mol%)

(Mixed powder B): 61.10Co-16.67Cr-13.89Pt-2.78 SiO_2 -5.56MnO (mol%)

The weighed powders were respectively placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. Thereafter, only the mixed powder A was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 1000°C , holding time of 2 hours, and pressure of 30 MPa, to obtain a sintered compact (sintered compact A). Subsequently, the obtained sintered compact was pulverized using a jaw crusher and a stone mill-type grinder, and thereafter sieved using sieves having a sieve opening of $38 \mu\text{m}$ and $106 \mu\text{m}$ to obtain a sintered compact powder A having a grain size of 38 to $106 \mu\text{m}$.

[0072] Subsequently, the sintered compact powder A and the mixed powder B were respectively weighed; specifically, the sintered compact powder A was weighed to be 470.2 g and the mixed powder B was weighed to be 1529.8 g, so that the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 69Co-12Cr-10Pt-3 TiO_2 -2 SiO_2 -4MnO (mol%)

The weighed powders were placed in a planetary-screw mixer having a ball capacity of approximately 7 liters, and mixed for 20 minutes to obtain a mixed powder for preparing a secondary sintered compact. The thus obtained mixed powder for preparing a secondary sintered compact was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 950°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.2% was obtained. In addition, the obtained sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0073] Upon observing the microstructure of the sputtering target of Example 7, it was confirmed that the structure included regions (non-Cr-based regions) in which TiO_2 is dispersed in Co, and a region (Cr-based region) in which SiO_2 and MnO are dispersed in a Co-Cr-Pt alloy, and the non-Cr-based regions are scattered in the Cr-based region.

In addition, the structure of the polished surface of the target was photographed in a visual field size of $100\ \mu\text{m} \times 75\ \mu\text{m}$ at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was $1.6\ \mu\text{m}^2$.

[0074] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 6 particles.

[0075] (Comparative Example 8)

A Co powder having an average grain size of $3\ \mu\text{m}$, a Cr powder having an average grain size of $5\ \mu\text{m}$, and a Pt powder having an average grain size of $2\ \mu\text{m}$ were prepared as metal raw material powders, and a TiO_2 powder having an average grain size of $1\ \mu\text{m}$, a SiO_2 powder having an average grain size of $1\ \mu\text{m}$ and a MnO powder having an average grain size of $3\ \mu\text{m}$ were prepared as oxide raw material powders. Subsequently, these powders were weighed to be 2000.0 g in total so that

the composition of the overall sputtering target resulted in the following composition ratio.

(Target composition): 69Co-12Cr-10Pt-3TiO₂-2SiO₂-4MnO (mol%)

5 The weighed powders were placed in a ball mill pot having a capacity of 10 liters together with zirconia balls as the grinding medium, and mixed by being rotated for 20 hours. The thus obtained mixed powder was filled in a carbon mold, and hot pressed in a vacuum atmosphere under the following conditions; namely, temperature of 950°C, holding time of 2 hours, and pressure of 30 MPa, whereby a sintered compact having a relative density of 98.7% was obtained. In addition, the obtained
10 sintered compact was machined with a lathe to obtain a disk-shaped sputtering target having a diameter of 180 mm, and a thickness of 5 mm.

[0076] Upon observing the microstructure of the sputtering target of Comparative Example 8, it was confirmed that TiO₂ and SiO₂ and MnO were dispersed in a Co-Cr-Pt alloy. In addition, the structure of the polished surface of the target was
15 photographed in a visual field size of 100 μm × 75 μm at 8 arbitrarily selected locations on the target structure surface, and the captured structure photograph was binarized using image processing software to obtain a mean area per oxide particle, whereby the result was 2.9 μm², and the oxides had coarsened in comparison to Example 6.

20 [0077] Subsequently, this target was mounted on a DC magnetron sputtering device and sputtered. The sputtering conditions were a sputtering power of 1 kw and an Ar gas pressure of 1.5 Pa, and, after performing pre-sputtering at 2 kWhr, a film was sputtered on a silicon substrate having a 4-inch diameter with a target film thickness of 1000 nm. In addition, the number of particles that adhered onto the
25 substrate was measured using a particle counter. Consequently, the number of particles on the silicon substrate was 13 particles, and the number of particles was larger in comparison to Example 6.

[0078]

[Table 1]

	Target Composition (mol%)	Mixed Powder A (mol%)	Mixed Powder B (mol%)	Grain Size of Sintered Compact Powder A (μm)	Mean Area of Oxide (μm^2)	Number of Particles (Particles)
Example 1	80Co-12Cr-4TiO ₂ -4SiO ₂	90.5Co-9.5TiO ₂	72.36Co-20.73Cr-6.91SiO ₂	50-150	1.1	5
Comparative Example 1	80Co-12Cr-4TiO ₂ -4SiO ₂	-	80Co-12Cr-4TiO ₂ -4SiO ₂	-	2.1	13
Example 2	65Co-12Cr-14Pt-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	68.15Co-22.29Pt-4.78TiO ₂ -4.78Cr ₂ O ₃	59.68Co-32.26Cr-8.06SiO ₂	38-106	1.4	3
Example 3	65Co-12Cr-14Pt-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	81.76Co-9.12Pt-4.56TiO ₂ -4.56Cr ₂ O ₃	32.75Co-35.09Cr-23.39Pt-8.77SiO ₂	38-106	1.5	2
Comparative Example 2	65Co-12Cr-14Pt-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	-	65Co-12Cr-14Pt-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	-	2.3	15
Comparative Example 3	65Co-12Cr-14Pt-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	81.76Co-9.12Pt-4.56TiO ₂ -4.56Cr ₂ O ₃	32.75Co-35.09Cr-23.39Pt-8.77SiO ₂	18	2.1	10
Comparative Example 4	65Co-12Cr-14Pt-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	75.34Co-16.44Pt-4.11SiO ₂ -4.11Cr ₂ O ₃	37.04Co-44.44Cr-7.41Pt-11.11TiO ₂	38-106	2.6	18
Example 4	65Co-12Cr-12Pt-3B-4TiO ₂ -4SiO ₂	80.96Co-9.52Pt-9.52TiO ₂	53.45Co-20.69Cr-13.79Pt-5.17B-6.9SiO ₂	38-106	1.8	6
Comparative Example 5	65Co-12Cr-12Pt-3B-4TiO ₂ -4SiO ₂	-	65Co-12Cr-12Pt-3B-4TiO ₂ -4SiO ₂	-	2.5	19
Example 5	64Co-12Cr-10Pt-5Ru-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	89.29Co-10.71TiO ₂	54.16Co-16.67Cr-13.89Pt-6.94Ru-4.17SiO ₂ -4.17Cr ₂ O ₃	38-106	1.1	2
Comparative Example 6	64Co-12Cr-10Pt-5Ru-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	-	64Co-12Cr-10Pt-5Ru-3TiO ₂ -3SiO ₂ -3Cr ₂ O ₃	-	2.0	12
Example 6	69Co-12Cr-10Pt-3TiO ₂ -3SiO ₂ -3B ₂ O ₃	89.29Co-10.71TiO ₂	61.1Co-16.67Cr-13.89Pt-4.17SiO ₂ -4.17B ₂ O ₃	38-106	1.9	6
Comparative Example 7	69Co-12Cr-10Pt-3TiO ₂ -3SiO ₂ -3B ₂ O ₃	-	69Co-12Cr-10Pt-3TiO ₂ -3SiO ₂ -3B ₂ O ₃	-	3.1	18
Example 7	69Co-12Cr-10Pt-3TiO ₂ -2SiO ₂ -4MnO	89.29Co-10.71TiO ₂	61.1Co-16.67Cr-13.89Pt-2.78SiO ₂ -5.56MnO	38-106	1.6	6
Comparative Example 8	69Co-12Cr-10Pt-3TiO ₂ -2SiO ₂ -4MnO	-	69Co-12Cr-10Pt-3TiO ₂ -2SiO ₂ -4MnO	-	2.9	13

[0079] In all cases of Examples 1 to 7, the mean area of individual oxide particles was less than $2.0 \mu\text{m}^2$, and it was confirmed that the oxides are finely dispersed. It should be easy to understand that this kind of structure plays an extremely important role for suppressing the amount of particles that are generated during sputtering, and improving the yield during deposition.

[Industrial Applicability]

[0080] Since the sputtering target and production method thereof according to the present invention can suppress the formation of coarse complex oxide grains and improve the dispersibility of oxides, the present invention yields superior effects of being able to reduce the amount of particles that are generated during sputtering, and improve the yield during deposition. Accordingly, the present invention is useful as a sputtering target for forming a granular film.

CLAIMS

1. A sputtering target containing, as metal components, 0.5 to 45 mol% of Cr and remainder being Co, and containing, as non-metal components, two or more types of oxides including Ti oxide, wherein a structure of the sputtering target is configured from regions where oxides including at least Ti oxide are dispersed in Co (non-Cr-based regions), and a region where oxides other than Ti oxide are dispersed in Cr or Co-Cr (Cr-based region), and the non-Cr-based regions are scattered in the Cr-based region.

2. A sputtering target containing, as metal components, 0.5 to 30 mol% of Cr, 0.5 to 30 mol% of Pt, and remainder being Co, and containing, as non-metal components, two or more types of oxides including Ti oxide, wherein a structure of the sputtering target is configured from regions where oxides including at least Ti oxide are dispersed in Co or Co-Pt (non-Cr-based regions), and a region where oxides other than Ti oxide are dispersed in one or more types of phases of Co-Cr, Cr-Pt, and Co-Cr-Pt (Cr-based region), and the non-Cr-based regions are scattered in the Cr-based region.

3. The sputtering target according to claim 1 or claim 2, wherein the two or more types of oxides (excluding Ti oxide) are oxides of one or more types of elements selected from B, Mg, Al, Si, Cr, Zr, Nb, and Ta.

4. The sputtering target according to any one of claims 1 to 3, wherein a content of the oxides in the sputtering target is, based on a volume ratio, 20% or more and less than 50%.

5. The sputtering target according to any one of claims 1 to 4, wherein the sputtering target additionally contains, as metal components, one or more types of elements selected from B, Cu, Mo, Ru, Ta, and W.

6. A method of producing a sputtering target comprising a step of mixing a metal powder and an oxide powder including Ti oxide and pressing and sintering a resulting mixed powder A in a vacuum or an inert gas atmosphere to produce a sintered compact A, and pulverizing and sieving the sintered compact A to produce a sintered compact powder A corresponding to the non-Cr-based regions, a step of mixing a metal powder and oxide powders other than Ti oxide to produce a mixed powder B corresponding to the Cr-based region, and a step of mixing the sintered compact powder A and the mixed powder B, and thereafter pressing and sintering a

resulting mixed powder in a vacuum or an inert gas atmosphere to produce a secondary sintered compact to be used as a target material.

7. The method of producing a sputtering target according to claim 6, wherein a grain size of the sintered compact powder A is 20 to 200 μm .