

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
23 September 2004 (23.09.2004)

PCT

(10) International Publication Number
WO 2004/080659 A3

(51) International Patent Classification⁷: **B25B 9/02**, C08K 3/04, 7/06, H01L 21/68, H05K 13/00, 13/04, C08K 3/00

(21) International Application Number:
PCT/US2004/006924

(22) International Filing Date: 3 March 2004 (03.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2003-060136 6 March 2003 (06.03.2003) JP

(71) Applicant (for all designated States except US): **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **OKADA, Yukihisa** [JP/JP]; 3-8-8, Minami Hashimoto, Sagamihara, Kanagawa 229-1185 (JP). **NUMAGUCHI, Toshikazu** [JP/JP]; 3-8-8, Minami Hashimoto, Sagamihara, Kanagawa 229-1185 (JP).

(74) Agents: **FLORCZAK, Yen, T.** et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).


Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:
4 November 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ANTISTATIC COMPOSITION AND PART HOLDER



(57) Abstract: An antistatic composition containing a heat-resistant resin binder with a softening temperature (T_s) of 160-410°C and carbon blacks and/or carbon nanofibers added as an antistatic agent to the binder is spread on a base material, such as the holding part of a holder such as tweezers, and is heat-treated at a temperature of 200-450°C, so that a film is formed. This film has a surface resistance value of preferably 10³-10¹⁰ Ω/sq.

WO 2004/080659 A3