

**POLYMERIZATION INITIATING SYSTEM AND METHOD TO PRODUCE
HIGHLY REACTIVE OLEFIN FUNCTIONAL POLYMERS**

The invention is directed to a method for consistently producing highly
5 reactive olefin polymers wherein at least 50 mol% of the polymer chains have
terminal double bonds, from isobutylene, or a mixed C₄ hydrocarbyl feedstock
containing isobutylene.

BACKGROUND OF THE INVENTION

10 Catalyst systems for cationic polymerization of isobutylene (IB) or C₄ streams
containing isobutylene (IB) (e.g. Raffinate 1) that can produce olefinic polymers of
M_n=500-3000 with a reactive vinylidene at the terminus (HR-PIB) are of high
commercial value. Catalysts based on BF₃ complexes with alcohols or ethers have
been used commercially, but they generally require low temperature and highly
15 purified feed (US 7,411,104 B2). Lewis acid-Lewis base complexes of aluminum
halides or alkyl aluminum halides and ethers have also been disclosed in a range of
media and with a variety of co-initiators. The initiators are primarily alkyl halides,
H₂O, HCl or ROH (e.g. *Macromolecules* 2010, 43(13), pp 5503-5507, *Polymer* 2010,
51, pp 5960-5969).

20 Getting high monomer conversions and high vinylidene in an apolar medium
(suitable for commercial scale-up) using a continuous process without elaborate feed
clean-up has been elusive. Catalysts that work well in a polar medium such as
dichloromethane, often do not work in an apolar saturated hydrocarbon medium
(*Macromolecules*, 2012, 45, pp 3318-3325).

25 One of the advances highlighted recently is that ethers with one or more
electron-withdrawing groups (e.g. bis-2-chloro-ethyl ether, CEE) were particularly
useful in enabling alkyl aluminum dichloride to initiate cationic polymerization in the
presence of t-butyl chloride as co-initiator giving a high yield of HR-PIB (US
9,156,924 B2). In the absence of the electron withdrawing groups, dialkyl ethers
30 inhibited polymerization in an apolar medium (*Macromolecules*, 2014, 47 (6), pp
1959–1965) either because the Lewis acid-Lewis base complexes were too strong
(high binding energy) or the resulting t-butyl oxonium ions were too stable. This
made the rate of polymerization too slow to be commercially viable.

Even with complexes of the appropriate binding energy, it has been found that polymerization yield and terminal vinylidene content can be inconsistent and vary with the properties of the IB, and IB-containing feedstock. Applicants have found that the presence of a small amount of water surprisingly ameliorates these

5 inconsistencies in polymerizations carried out using alkylAlCl₂ • CEE as catalyst and alkyl halide as initiator. The present method enables lower cost processes that can use a broader range of feedstocks. Though water itself can normally act as initiator for the polymerization of IB (US 2016/0333123 A1), the presence of alkyl halide as co-initiator is necessary to control the reaction and get reasonable monomer conversions.

10 The amount of water is also critical. Typically when water is used as an initiator for IB polymerizations, it is generally present at concentrations of 5-100, e.g 10-50 mM (US 2016/0333123 A1). However, in the presence of alkyl halide, this amount of water can cause a decrease in vinylidene end-group selectivity. On the other hand, too little water does not eliminate the inconsistent yield and terminal vinylidene

15 content of the desired HR-PIB product.

DETAILED DESCRIPTION OF THE INVENTION

Lewis acids useful in the practice of the present invention include Lewis acids of the formula R'AlCl₂, wherein R' is a hydrocarbyl group, preferably a hydrocarbyl

20 group having 1 to 12 carbon atoms, more preferably an alkyl group having 1 to 12 carbons. As used herein, the term "hydrocarbyl" means a chemical group of a compound that contains hydrogen and carbon atoms and that are bonded to the remainder of the compound directly via a carbon atom. The group may contain one or more atoms other than carbon and hydrogen ("hetero atoms"), provided such hetero

25 atoms do not affect the essentially hydrocarbyl nature of the group.

Useful Lewis bases are dihydrocarbyl ethers wherein each hydrocarbyl group is independently selected from hydrocarbyl groups having 1 to 8 carbon atoms. The hydrocarbyl groups of the ether may be branched, straight-chained or cyclic. Where the hydrocarbyl groups of the ether are branched or straight-chained, the hydrocarbyl

30 groups are preferably alkyl groups, more preferably alkyl groups having 1 to 4 carbon atoms. One or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with an electron withdrawing group, particularly a halogen atom, preferably a chlorine atom.

The Lewis acid and Lewis base can be complexed by, for example, by dissolving the Lewis acid in a solvent selected from liquid, apolar, non-halogenated aliphatics, and liquid aromatics, such as benzene, chlorobenzene, toluene and xylene, to form a solution and then adding the Lewis base to the solution, while the solution is stirred. The complex may be added to the polymerization medium with the solvent; alternatively, the solvent may be removed prior to the addition of the complex to the polymerization medium. Preferably, the solvent is a non-halogenated aliphatic or aromatic solvent, and is more preferably xylene or toluene or mixed C₄ to C₁₂ linear and/or branched hydrocarbons (e.g., ISOPARTM, available from ExxonMobil Corporation), most preferably toluene or mixed C₄ to C₁₂ linear and/or branched hydrocarbons. When the Lewis acid and Lewis Base are complexed in xylene or toluene, it is preferable to dissolve the Lewis base in the xylene or toluene solvent to form a solution, and then add the Lewis acid to the Lewis base solution, while the solution is stirred.

The molar ratio of Lewis acid to Lewis base in the complex will typically be maintained within a range of from about 1:1 to about 1:8, preferably from about 1:1 to about 1:8, more preferably from about 1:1 to about 1:6, such as about 1:1 to about 1:3 (e.g. about 1:1.5).

An "initiator" is defined as a compound that can initiate polymerization, in the presence or absence of adventitious water and in the presence of a proton trap. The initiator of the present invention (RX) comprises a hydrocarbyl R group, preferably an alkyl or aryl-alkyl group, wherein the carbon linking group R to X is tertiary, benzylic or allylic, preferably tertiary, which hydrocarbyl group can form a stable carbocation (e.g., t-butyl⁺); and an X group, which is a halide, preferably chlorine.

The polymerization medium must be a substantially or completely apolar polymerization medium, such as a mixture of saturated and unsaturated C₄ hydrocarbons.

In the polymerization process of the present invention, the feedstock may be pure isobutylene or a mixed C₄ hydrocarbyl feedstock containing isobutylene, such as a C₄ cut resulting from the thermal or catalytic cracking operation of, for example, naphtha. Thus, suitable feedstocks will typically contain at least 10%, and up to 100% isobutylene, by mass (e.g. 20-50%, based on the total mass of the feed). In addition to isobutylene, conventional C₄ cuts suitable for use as feedstocks that are of

industrial importance typically will contain between about 5% and about 50% butene-1, between about 2% and about 40% butene-2, between about 2% and about 60% isobutane, between about 2% and about 20% n-butane, and up to about 0.5% butadiene, all percentages being by mass, based on the total feed mass. Feedstocks containing
5 isobutylene may also contain other non-C₄ polymerizable olefin monomers in minor amounts, e.g., typically less than 10%, preferably less than about 5%, and most preferably less than 1%, such as propadiene, propylene and C₅ olefins. The feedstock may contain various polar feed impurities such as acetone, methanol, acetonitrile, propionic acid, but will preferably be purified so that the feedstock contains less than
10 5 ppm, such as less than 4 ppm or 3 ppm or 2 ppm or 1 ppm or 0.5 ppm of polar impurities.

The term "polybutene", as employed herein is intended to include not only homopolymers of isobutylene, but also copolymers of isobutylene and one or more other C₄ polymerizable monomers of conventional C₄ cuts as well as non-C₄
15 ethylenically unsaturated olefin monomers containing 5 carbon atoms, provided such copolymers contain typically at least 50 mass %, preferably at least 65 mass %, and most preferably at least 80 mass% isobutylene units, based on the polymer number average molecular weight ($\overline{M}_n$).

The amount of the Lewis acid-Lewis base complex employed in the process of
20 the present invention can be controlled, in conjunction with the concentration of initiator and monomer, reaction time and temperature, to achieve the target $\overline{M}_n$ of the polybutene polymer product, the conversion of iso-butene and yield of polybutene. In view of the above, the Lewis acid-Lewis base complex is typically employed in an amount sufficient to contact the butene monomer in a liquid phase reaction mixture at
25 a concentration of millimoles of Lewis acid-Lewis base complex per liter of reaction mixture of from about 0.2 mM to about 200 mM, such as from about 1 mM to about 200 mM, preferably from about 5 mM to about 100 mM, and more preferably from about 10 mM to about 50 mM, such as about 10 mM to about 30 mM.

The initiator will typically be employed in a liquid phase reaction mixture
30 comprising the iso-butene monomer at a concentration of millimoles of initiator per liter of medium, and independent from the amount of Lewis acid-Lewis base complex, of from about 1mM to about 500 mM, preferably from about 2 mM to about 300 mM,

and more preferably from about 2 mM to about 200 mM, such as about 10 mM to about 30 mM.

Water can be added at different stages of the process. It can be added with the catalyst, the initiator or the monomer itself. The presence of a small amount of aromatic solvent such as toluene can facilitate the addition of water due to the increased solubility of water in that medium relative to an all aliphatic medium. Too much toluene, however, can result in unwanted side reactions. The total amount of toluene in the final medium is preferably 0 to about 20%, more preferably, 0 to about 15%, such as 0 to about 10%. A guard bed containing molecular sieves or CaCl_2 to dry the feed prior to the reaction can be useful to ensure that the proper amount of water is added to the reaction. Alternatively, the water content of the feedstock can be controlled by mixing wet and dry feedstocks (that have been passed through a drying column), in a ratio required to provide the desired water content. The molar composition of water present/added to the feedstock should be less than the molar concentration that causes a decrease in vinylidene end-group selectivity, such as less than 10mM, preferably less than 5mM per liter of feedstock. More specifically, the amount of water present/added to the feedstock is from about 0.05 mM to less than 5 mM, preferably from about 0.1 mM to about 3 mM, more preferably from about 0.2 to about 2 mM, such as from about 0.3 mM to about 1 mM per liter of feedstock.

In an alternative embodiment of the present invention, water can be added to the Lewis acid/Lewis base complex, which is then allowed to age for a period of time before being brought into contact with the feedstock. In this embodiment (see Example 1), water may be added to the Lewis acid/Lewis base complex in an amount of from about 0.02 to about 10 equivalents of water per equivalent of Lewis acid, preferably from about 0.03 to about 0.2 (such as from about 0.05 to about 0.15) equivalents of water per equivalent of Lewis acid. Once water is added, the Lewis acid/Lewis base complex is allowed to sit for a period of time before being brought into contact with the feedstock in order to allow the water to “activate” the complex. Activation times may be from 1 minute to one day, preferably from about 2 minutes to about 3 hours, such as from about 5 minutes to about 60 minutes. Preferably, during activation, the complex is maintained at a temperature of from about -10°C to about 20°C .

The polymerization reaction can be performed as a batch or continuous process. On an industrial scale, the polymerization reaction is preferably conducted continuously. The continuous process can be carried out in tubular reactors, tube-bundle reactors or loop reactors, or tube or tube-bundle reactors with continuous
5 circulation of the reaction material, or in a stirred tank reactor (glass, carbon steel or Monel preferred), a pump around loop, a plugged flow reactor or a combination thereof.

The polymerization reaction is conducted in the liquid phase to induce linear or chain-type polymerization, as opposed to ring or branch formation. Thus, if a feed
10 is used that is gaseous under ambient temperature, it is preferred to control the reaction pressure and/or dissolve the feed in an inert solvent or liquid diluent, in order to maintain the feed in the liquid phase. Typical C₄ cuts comprising the feed are liquid under pressure and do not require a solvent or diluent. Typical diluents suitable for use with the process include C₃ to C₆ alkanes, such as propane, butane, pentane
15 and isobutane.

The Lewis acid-Lewis base complex is typically introduced into the reactor as a liquid partially or completely dissolved in a solvent, or as a solid. Polymerization is preferably conducted at a pressure sufficient to maintain the C₄ feed in a liquid state at the reaction temperature, or at higher pressures. The initiator may be introduced to
20 the monomer feed or the reaction mixture in liquid form together with the Lewis acid-Lewis base complex or, preferably, is introduced to the monomer feed or the reaction mixture in liquid form by a line separate from the Lewis acid-Lewis base complex addition line.

The liquid phase reaction mixture temperature is controlled by conventional
25 means to be typically from about -30°C to about +50°C, preferably from about -10°C to about +30°C, more preferably from about -5°C to about +20°C, such as about 0°C to about +15°C to minimize refrigeration costs and unwanted side reactions.

In order to insure even distribution of the catalyst within the reactor, turbulent flow of the reactor contents (Reynolds number >100, preferably >1000) can be
30 generated by mixing, or with suitable baffles, such as baffle plates or oscillating baffles, or by dimensioning the reactor tube cross sections so that a suitable flow velocity is established.

The steady state residence time of the butene to be polymerized may be from about 1 to about 300 minutes, such as 2 to about 120 minutes, preferably from about 4 to about 60 minutes or from about 5 to about 45 minutes (e.g., from about 6 to about 30 minutes).

- 5 The process of the present invention is typically conducted in a manner achieving an isobutylene conversion in the range of from about 20% up to about 100%, preferably from about 50% to about 100%, and more preferably from about 70% to about 100%, such as 80% to 100%, 90% to 100% or 95% to 100%. The combined use of temperature control and catalyst feed rate permits formation of
- 10 polybutenes having a $\overline{M}_n$ of from about 400 Daltons to about 4000 Daltons, preferably from about 700 Daltons to about 3000 Daltons, more preferably from about 1000 Daltons to about 2500 Daltons; a molecular weight distribution (MWD) of typically from about 1.1 to about 4.0, preferably from about 1.5 to about 3.0, an exo-olefin content of greater than 50 mol. %, preferably greater than 60 mol. %, more
- 15 preferably greater than 70 mol. %, such as from about 80 mol.% to about 95 mol. %; a tetra-substituted olefin content of less than about 20 mol. %, such as less than about 15 mol. %, preferably less than about 10 mol. %, more preferably less than about 5 mol. %; and a chlorine content of less than about 10 mol. %, such as less than about 5 mol. %, preferably less than about 2 mol. %, more preferably less than about 1 mol. %
- 20 based on the total moles of polymer.

- Once the target molecular weight of the polymer is achieved, the polymer product can be discharged from the reactor and passed into a medium that deactivates the polymerization catalyst and terminates the polymerization. Suitable deactivation media include water, amines, alcohols and caustics. The polyisobutylene product can
- 25 then be separated by distilling off the remaining C₄ hydrocarbons and low molecular weight oligomers. Preferably residual amounts of catalyst are removed, usually by washing with water or caustic.

- In one commercially preferred embodiment (from a standpoint of performance, environmental impact and cost), the Lewis acid is R'AlCl₂, wherein R' is C₁ to C₄
- 30 hydrocarbyl, specifically, MeAlCl₂, EtAlCl₂ (EADC), iso-BuAlCl₂ or n-BuAlCl₂, the Lewis base is a chlorinated dihydrocarbyl ether (CEE), the solvent is ISOPAR or toluene, and the complex is formed by dissolving the Lewis base in the solvent to form a solution and then adding the Lewis acid to the Lewis base solution in an

amount such that the molar ratio of Lewis acid to Lewis base in the complex is from about 1:1 to about 1:1.5.

This invention will be further understood by reference to the following examples, which are not intended, and should not be construed as listing all possible
5 embodiments within the scope of the invention.

EXAMPLES (results summarized in Table 1)

Example 1

Ethyl aluminum dichloride (EADC) • chlorinated dihydrocarbyl ether (CEE)
10 complex was prepared in a N₂ atmosphere glove box. An appropriate amount of EADC in hexane (1M) was mixed with CEE in a 1:2 molar ratio. Toluene containing 0.075 equivalents of H₂O relative to EADC was added to the complex to form a 0.1M complex solution. The catalyst solution was delivered to the CSTR via a SS syringe pump. The initiator was delivered as a tBuCl solution in hexane via another SS
15 Syringe pump. The feed, synthetic Raffinate-1 containing 40% IB, was passed through a 3A and AZ300 column before introduction into the CSTR. The Raffinate-1 feed had less than 0.5 ppm polar (oxygenate) impurities, as determined by ASTM D7423. The initial concentrations of reagents were [H₂O] = 0.73 mM, [EADC] = 0.01M, [CEE] = 0.02M, [tBuCl] = 0.0025M, before reaching a final steady state
20 concentration of IB of 28% after three residence times of 38 minutes. Mixing in the reactor was provided by a rotating 1000 rpm impeller. The pressure in the reactor was maintained to 50 psig and the polymerization temperature was 4°C. The reaction mixture at the CSTR exit was quenched at 4°C with a mixture of isopropanol/water (80/20, v/v). 72 % monomer conversion was observed, Mn(GPC) = 1900, PDI = 3.1,
25 Exo-olefin functionality was 82%, determined by ¹³C NMR.

Example 2 (Comparative)

Example 2 was performed as in Example 1, except that no H₂O was added to the EADC•CEE complex. Conversion of IB of only about 1% was observed at steady
30 state.

Example 3 (Comparative)

Example 3 was performed with the Example 1 reagent concentrations, in a 60 minute minibatch run. EADC•CEE was 1:1.5, water was added to the feed $[H_2O] = 0.48$ mM, and no tBuCl initiator was added. No yield was observed.

5

Example 4 (Comparative)

Example 4 was performed with the Example 1 reagent concentrations, in a 60 minute minibatch run. EADC•CEE was 1:1.5, water was added to the feed $[H_2O] = 1.2$ mM, and no tBuCl initiator was added. 6% IB conversion was observed.

10

Example 5

Example 5 was performed in the same manner as Example 1, except that $[tBuCl] = 0.01M$. 84% monomer conversion was observed and the final HR PIB had $M_n = 1315$, $PDI = 2.5$, and exo-olefin functionality of 79% determined by ^{13}C NMR.

15

Example 6

Example 6 was performed in the same manner as Example 5, except that EADC and CEE concentrations were twice as high. 76% IB conversion was observed, and the final HR PIB product had $M_n=1300$, $PDI=2.5$, and exo-olefin content of 82% determined by ^{13}C NMR.

20

Example 7

Example 7 was performed in the same manner as Example 5 except that EADC and CEE concentrations were three times lower. 84 % IB conversion was observed, and the final HR PIB product had $M_n=2014$, $PDI=2.9$, and exo-olefin content of 71% determined by ^{13}C NMR.

25

30

Table 1

Ex.	Added H ₂ O (mM)	[EADC] (M)	[CEE] (M)	[tBuCl] (M)	IB conv (%)	Exo(%) [*] (NMR)	Mn (NMR)	Mn (GPC)	PDI (GPC)
1	0.73	0.01	0.02	0.0025	72	82	2300	1900	3.1
2	0	0.01	0.02	0.01	1	n.d.	n.d.	n.d.	n.d.
3	0.48	0.01	0.015	0	0	n.d.	n.d.	n.d.	n.d.
4	1.2	0.01	0.015	0	6	n.d.	n.d.	n.d.	n.d.
5	0.73	0.01	0.02	0.01	84	79	1550	1315	2.5
6	0.73	0.02	0.04	0.01	76	82	1300	1140	2.5
7	0.73	0.0033	0.066	0.01	84	71	2600	2014	2.9

While certain representative embodiments and details have been provided to illustrate the invention, it will be apparent to the skilled artisan that various product and process changes from those disclosed herein may be made without departing from the scope of the present invention. The appended claims define the scope of the invention

All cited patents, test procedures, priority documents, and other cited documents are fully incorporated by reference to the extent that such material is consistent with this specification and for all jurisdictions in which such incorporation by reference is permitted.

Certain features of the present invention are described in terms of a set of numerical upper limits and a set of numerical lower limits. This specification discloses all ranges formed by any combination of these limits. It is to be understood that the upper limits and lower limits, as well as range and ratio limits set forth herein may be independently combined, and that all combinations of these limits are within the scope of the invention unless otherwise indicated.

What is claimed is:

1. A process for the preparation of polybutene having an exo-olefin content of at least 50 mol. % from an isobutane or an isobutene-containing monomer feedstock, which process comprises contacting said isobutene or isobutane-containing feedstock, with a Lewis acid catalyst complexed with a Lewis base, in a substantially or completely apolar polymerization medium, and initiating polymerization of said isobutane or isobutene-containing feedstock with an initiator, wherein said Lewis acid catalyst is a Lewis acid of the formula $R'AlCl_2$, wherein R' is a hydrocarbyl group; said Lewis base is a dihydrocarbyl ether wherein each hydrocarbyl group is independently selected from hydrocarbyl groups having 1 to 8 carbon atoms and one or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with an electron withdrawing group and the initiator is a compound of the formula RX , wherein X is a halide; R is a hydrocarbyl group capable of forming a stable carbocation, and wherein the carbon linking group R to group X is tertiary, benzylic or allylic; wherein the amount of water in said feedstock is controlled to be from about 0.05 mM to less than 5 mM per liter of feedstock.

2. The process of claim 1, wherein R' is an alkyl group having 1 to 12 carbons.

3. The process of claim 1, wherein said Lewis base is dihydrocarbyl ether wherein each hydrocarbyl group is independently selected from hydrocarbyl groups having 1 to 8 carbon atoms and one or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with a chlorine atom.

4. The process of claim 3, wherein said Lewis base is a dihydrocarbyl ether wherein each hydrocarbyl group is independently selected from alkyl groups having 1 to 4 carbon atoms and one or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with a chlorine atom.

5. The process of claim 1, wherein the Lewis acid and Lewis base are complexed in a solvent selected from a liquid, apolar, non-halogenated aliphatic solvent or a liquid, aromatic solvent.

6. The process of claim 5, wherein said solvent is mixed C_4 to C_{12} linear and/or branched hydrocarbons, toluene or xylene.

7. The process of claim 1, wherein said apolar polymerization medium is selected from saturated C₄ hydrocarbons, unsaturated C₄ hydrocarbons, and mixtures thereof.

8. The process of claim 1, wherein said isobutene or isobutene-containing feedstock is selected from pure isobutene; a C₄ refinery cut containing between about 20-50% isobutene, between 5% and about 50% butene-1, between about 2% and about 40% butene-2, between about 2% and about 60% iso-butane, between about 2% and about 20% n-butane, and up to about 0.5% butadiene, wherein all percentages are by mass, based on the total mass of the C₄ refinery cut; and mixtures of pure isobutene and said C₄ refinery cut.

9. The process of claim 1, wherein the amount of water in said feedstock is controlled to be an amount of from about 0.2 to about 2 mM per liter of feedstock.

10. The process of claim 1, wherein said complex is contacted with said isobutene or isobutene-containing feedstock at a concentration of millimoles of Lewis acid-Lewis base complex per liter of feedstock of from about 0.2 mM to about 200 mM.

11. The process of claim 1, wherein the polymerization process is conducted continuously.

12. The process of claim 1, wherein said polybutene product has an exo-olefin content of at least 70 mol. %.

13. The process of claim 1, wherein said polybutene product has a number average molecular weight (M_n) of from about 400 Daltons to about 4000 Daltons.

14. A process for the preparation of polybutene having an *exo*-olefin content of at least 50 mol. % from an isobutene or an isobutene-containing monomer feedstock, which process comprises contacting said isobutene or isobutene-containing feedstock, with a Lewis acid catalyst complexed with a Lewis base, in a substantially or completely apolar polymerization medium, and initiating polymerization of said isobutene or isobutene-containing feedstock with an initiator, wherein said Lewis acid catalyst is a Lewis acid of the formula $R'AlCl_2$, wherein R' is a hydrocarbyl group; said Lewis base is a dihydrocarbyl ether wherein each hydrocarbyl group is independently selected from hydrocarbyl groups having 1 to 8 carbon atoms and one or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with an electron withdrawing group and the initiator is a compound of the formula RX , wherein X is a halide; R is a hydrocarbyl group capable of forming a stable carbocation, and wherein the carbon linking group R to group X is tertiary, benzylic or allylic; wherein from about 0.02 to about

10 equivalents of water per equivalent of Lewis acid is added to the Lewis acid/Lewis base complex at least one minute prior to the introduction of the Lewis acid/Lewis base complex into said feedstock.

15. The process of claim **14**, wherein R' is an alkyl group having 1 to 12 carbons.

16. The process of claim **14**, wherein said Lewis base is dihydrocarbyl ether wherein each hydrocarbyl group is independently selected from hydrocarbyl groups having 1 to 8 carbon atoms and one or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with a chlorine atom.

17. The process of claim **16**, wherein said Lewis base is a dihydrocarbyl ether wherein each hydrocarbyl group is independently selected from alkyl groups having 1 to 4 carbon atoms and one or both hydrocarbyl groups of the dihydrocarbyl ether are substituted with a chlorine atom.

18. The process of claim 14, wherein the Lewis acid and Lewis base are complexed in a solvent selected from a liquid, apolar, non-halogenated aliphatic solvent or a liquid, aromatic solvent.

19. The process of claim 18, wherein said solvent is mixed C₄ to C₁₂ linear and/or branched hydrocarbons, toluene or xylene.

20. The process of claim 14, wherein said apolar polymerization medium is selected from saturated C₄ hydrocarbons, unsaturated C₄ hydrocarbons, and mixtures thereof.

21. The process of claim 14, wherein said isobutene or isobutene-containing feedstock is selected from pure isobutene; a C₄ refinery cut containing between about 20-50% isobutene, between 5% and about 50% butene-1, between about 2% and about 40% butene-2, between about 2% and about 60% iso-butane, between about 2% and about 20% n-butane, and up to about 0.5% butadiene, wherein all percentages are by mass, based on the total mass of the C₄ refinery cut; and mixtures of pure isobutene and said C₄ refinery cut.

22. The process of claim 14, wherein from about 0.03 to about 0.2 equivalents of water per equivalent of Lewis acid is added to the Lewis acid/Lewis base complex at least one minute prior to the introduction of the Lewis acid/Lewis base complex into said feedstock.

23. The process of claim 14, wherein said complex is contacted with said isobutene or isobutene-containing feedstock at a concentration of millimoles of Lewis acid-Lewis base complex per liter of feedstock of from about 0.2 mM to about 200 mM.

24. The process of claim 14, wherein the polymerization process is conducted continuously.

25. The process of claim 14, wherein said polybutene product has an exo-olefin content of at least 70 mol. %.

26. The process of claim 14, wherein said polybutene product has a number average molecular weight (M_n) of from about 400 Daltons to about 4000 Daltons.