

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 March 2012 (01.03.2012)

(10) International Publication Number
WO 2012/026980 A2

PCT

(51) International Patent Classification:
B29C 70/44 (2006.01) **B29C 70/48** (2006.01)

(21) International Application Number:
PCT/US2011/001488

(22) International Filing Date:
23 August 2011 (23.08.2011)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/376,253 23 August 2010 (23.08.2010) US
61/497,880 16 June 2011 (16.06.2011) US

(71) Applicant (for all designated States except US): **MATERIA, INC.** [US/US]; 60 N. San Gabriel Blvd., Pasadena, CA 91107 (US).

(72) Inventors; and

(71) Applicants (for all designated States except US): **CORRAL, Sergio** [US/US]; 1960 Peck Rd., Apt. B, Monrovia, CA 91016 (US). **CRANE, Stephen** [US/US]; 163 N. Lake Grove Rd., Camano Island, WA 98282 (US). **STEPHEN, Anthony, R.** [US/US]; 1505 Fair Oaks #B, South Pasadena, CA 91030 (US). **CRUCE, Christopher, J.** [US/US]; 13545 Del Poniente Rd., Poway, CA 92064 (US). **FLORES, Everardo, García**; 5026 Rangeview Avenue, Los Angeles, CA 90042 (US).

(74) Agent: **WARZEL, Mark, L.**; Materia, Inc., 60 N. San Gabriel Blvd., Pasadena, CA 91107 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) Title: VARTM FLOW MODIFICATIONS FOR LOW VISCOSITY RESIN SYSTEMS

(57) Abstract: A vacuum-assisted resin transfer molding (VARTM) method is disclosed, the method comprising: providing a vacuum-assisted resin transfer mold assembly comprising a mold having a first mold surface and a second mold surface arranged to enclose a laminate assembly within a space between the first and second mold surfaces when the laminate assembly is placed on the first mold surface; providing a laminate assembly comprising a laminate pre-form, a peel ply, and a resin distribution media pervious to the flow of a resin, the laminate pre-form having first and second surfaces, the first surface of the pre-form positioned to be in contact with the first mold surface, the peel ply positioned such that the second surface of the laminate pre-form is in contact with the peel ply, and the resin distribution media positioned to be contained within the first and second mold surfaces; positioning at least one resin flow control structure to modify the flow of resin within the resin distribution media; providing at least one inlet and at least one outlet in the laminate assembly such that the resin can be introduced into the assembly through the inlet; arranging and sealing the second mold surface to enclose the laminate assembly within the space between the first and second mold surfaces such that a vacuum can be pulled on the laminate assembly contained within the space between the first and second mold surfaces; applying a vacuum to the mold assembly; allowing the resin to flow into the laminate assembly through the at least one inlet such that the resin flows into the resin distribution media; allowing the resin to flow out of the laminate assembly through the at least one outlet; and allowing the resin to cure in the laminate assembly to form a laminate material. An article of manufacture made by said VARTM method.



WO 2012/026980 A2