

REPLACED SHEETS		SG
☒	Description : paged 01 to paged 15	
☒	Claim(s) : paged 16 to paged 21	
☒	Drawing(s) : paged - to paged -	
☒	Abstract : paged 22 to paged -	

TITLE OF THE INVENTION

Coated Hard Tool Having Multi-Layer Coating

BACKGROUND OF THE INVENTION

Field of the Invention

5 The present invention relates to a coated hard tool used as a cutting tool requiring wear resistance, or other wear resistant tool. More specifically, the present invention relates to an improvement of wear resistance and seizure resistance of the tool.

10 Description of the Background Art

Conventionally, a super hard alloy has been used for a cutting tool. Such a super hard alloy may include a WC-Co alloy to which a carbide, a nitride, a nitrided carbide or the like of Ti, Ta, Nb or the like are added, for

15 example.

Recently, as the speed of cutting increases, a type of coated hard tool has come to be frequently used, in which a hard coating having a thickness of about 3 to about 20 μ m is formed by PVD (Physical Vapor Deposition) on

20 a surface of a hard base material such as a super hard alloy, a cermet, an alumina based ceramic, a silicon nitride based ceramic or the like. A film containing a carbide, a nitride, a nitrided carbide, a nitrided boride or an oxide of an element in group 4A, 5A or 6A of the

25 periodic table or of Al may be used as the hard coating.



The hard coating deposited by the PVD method improves the wear resistance of the base material while not deteriorating the strength of the base material. Therefore, the hard coating is widely used for cutting tools which
5 require strength, such as drills, end mills and throwaway tips (exchangeable, disposable tips) for milling.

Japanese Patent Laying-Open No. 8-127862 discloses a coated hard tool including a hard coating of multi-layered structure. Fig. 3 is a schematic cross section of a part
10 of the coated hard tool containing such a multi-layered hard coating. The coated hard tool of Fig. 3 includes a hard coating 2' deposited on a hard base material 1'. In the hard coating 2', a plurality of layers of two or more types are repeatedly stacked periodically, with each layer
15 having a thickness in the range of about 1 to about 100 nm. Each layer included in the hard coating 2' may include one or more compounds selected from a nitride, a carbide, a nitrided carbide and an oxide containing at least one element selected from periodic group 4A elements, periodic
20 group 5A elements, Al, B and the like.

In the hard coating 2', adjacent layers of different types have crystal lattice constants that are slightly different from each other, and include a crystal lattice structure partially continuing at interfaces therebetween.
25 In such a multi-layered film including crystal lattice



structure partially continuing at the interfaces between the layers, considerable internal strain is generated by an elastic complementary effect between the layers, and as a result, a greater hardness than the inherent hardness of each single layer is obtained.

Fig. 4 is a schematic cross section of another example of a coated hard tool including a hard coating of multi-layered structure. The coated hard tool of Fig. 4 is similar to that of Fig. 3, except that an intermediate layer 3' is interposed between hard base material 1' and multi-layered coating 2' in Fig. 4. Intermediate layer 3' is provided to improve adhesion between hard base material 1' and multi-layered coating 2'. A nitride, a carbide, a nitrided carbide or the like of periodic group 4A element may be used as the intermediate layer 3'.

As described above, very high hardness is obtained because of interaction between layers in such a multi-layered coating 2' as shown in Fig. 3 or Fig. 4. However, unless strain matching between layers is stabilized appropriately, the coating 2' may be subjected to embrittlement because of too high an internal stress. Particularly, the internal strain increases as the thickness of multi-layered coating 2' increases. Therefore, when the coating is too thick, coating 2' may suffer from brittle fracture because of shock experienced during



cutting.

SUMMARY OF THE INVENTION

In view of the problems of the prior art, an object of the present invention is to provide a coated hard tool having superior wear resistance and superior seizure
5 resistance, by improving characteristics of a hard multi-layered coating.

The coated hard tool in accordance with the present invention includes a hard base material and a hard coating
10 layer formed on a surface of the base material. The coating layer includes a plurality of sublayers of types A and B. On the surface of the base material, starting from type A or type B, a total of at least four, but preferably ten or more sublayers are stacked with the types A and B
15 alternating with each other. The sublayer of type A has a thickness within a range of 100 to 5000 nm, and includes a plurality of types of secondary sublayers stacked in a periodically repeated manner. Each secondary sublayer of each type includes at least one type of compound selected
20 from a nitride, a carbide, a nitrided carbide and an oxide including at least one element selected from periodic group 4A elements, periodic group 5A elements, Al and B, and has a thickness within the range of 1 to 50 nm. The sublayer of type B is formed of a single layer containing
25 one or more compounds selected from a nitride, a carbide,



a nitrided carbide and an oxide including at least one element selected from periodic group 4A elements, periodic group 5A elements, Al and B, and has a thickness in the range of 100 to 5000 nm.

5 It is preferred in the coated hard tool in accordance with the present invention, that the coating layer as a whole has a thickness of 0.5 to 10 μ m.

 Preferably, the coated hard tool in accordance with the present invention further includes an intermediate
10 layer additionally interposed at an interface between the surface of the base material and the sublayer, which intermediate layer includes one compound selected from a nitride, a carbide, a nitrided carbide and an oxide of a periodic group 4A element and has a thickness of 0.5 to
15 10 μ m. More preferably, the coating layer and the intermediate layer have a thickness of 1 to 14 μ m in total.

 The foregoing and other objects, features, aspects and advantages of the present invention will become more apparent from the following detailed description of the
20 present invention when taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

 Fig. 1 is a schematic cross section of a part of a coated hard tool in accordance with one embodiment of the
25 present invention.



Fig. 2 is a schematic cross section of a part of the coated hard tool in accordance with another embodiment of the present invention.

Fig. 3 is a schematic cross section of a part of a
5 hard tool in accordance with a prior art example.

Fig. 4 is a schematic cross section of a part of a coated hard tool in accordance with another prior art example.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

10 Fig. 1 schematically shows a cross section of a part of the coated hard tool in accordance with one example of the present invention. The coated hard tool includes a hard coating layer 4 stacked on a hard base material 1. Coating layer 4 includes a plurality of sublayers 4A of
15 type A, as well as a plurality of sublayers 4B of type B. The sublayers 4A and 4B of types A and B respectively are stacked alternately on the surface of base material 1, to provide a total of at least ten layers. The alternate repeated stacked layers are shown as starting from
20 sublayer 4A of type A in Fig. 1. However, the stacking may start from sublayer 4B of type B.

Sublayer 4A of type A has a thickness in the range of 100 to 5000 nm, and includes a plurality of secondary sublayers 4A1, 4A2, etc. of two or more types successively
25 stacked periodically and repeatedly. Each of the secondary



sublayers may include at least one compound selected from a nitride, a carbide, a nitrided carbide and an oxide including at least one element selected from periodic group 4A elements, periodic group 5A elements, Al and B, and preferably has a thickness in the range of about 1 to about 50 nm.

By contrast, sublayer 4B of type B is formed of a single layer. Sublayer 4B may include at least one compound selected from a nitride, a carbide, a nitrided carbide and an oxide including at least one element selected from periodic group 4A elements, periodic group 5A elements, Al and B, and preferably its thickness is in the range of about 100 to about 5000 nm.

It is preferred that the thickness of hard coating layer 4 as a whole is within the range of about 0.5 to about 10 μ m. When the thickness of coating layer 4 is smaller than 0.5 μ m, a sufficient improvement in wear resistance is not ensured, and when the thickness exceeds 10 μ m, the coating layer 4 tends to be abraded.

The inventors have found that the coated hard tool such as shown in Fig. 1 has a stable and superior wear resistance and seizure resistance. As described with reference to the prior art, sublayer 4A of type A exhibits an extremely high hardness because of interaction between each of the plurality of very thin secondary sublayers 4A1,



4A2, etc. included therein. However, the thickness of each sublayer 4A is limited to at most 5000 nm, and hence the internal strain in each sublayer 4A does not become extremely high. Further, sublayer 4B, which is a single layer with large thickness inserted between the plurality of sublayers 4A, functions to relax the internal strain in sublayer 4A. As a result, the coating layer 4 of the coated hard tool shown in Fig. 1 achieves a high hardness without embrittlement, enabling stable and superior wear resistance and seizure resistance.

Fig. 2 schematically shows a cross section of a part of a coated hard tool in accordance with another example of the present invention. Though the coated hard tool of Fig. 2 is generally similar to that of Fig. 1 and a redundant description is omitted, in the example of Fig. 2 an intermediate layer 3 of a single layer is inserted between hard base material 1 and hard coating layer 4 which includes sublayers 4A and 4B of types A and B respectively. Intermediate layer 3 may include a compound selected from a nitride, a carbide, a nitrided carbide and an oxide of periodic group 4A elements, and it has a thickness respectively greater than both sublayers 4A and 4B of types A and B. Preferably, the thickness is in the range of about 0.5 to about 2 μ m.

Such a thick intermediate layer 3 improves the



adhesion between coating layer 4 and base material 1, and in addition, it functions to relax the internal strain of coating layer 4 as a whole. Therefore, when intermediate layer 3 is provided, the thickness of coating layer 4 can be increased to some extent, and it is preferred that the total thickness of intermediate layer 3 and coating layer 4 is within the range of about 1 to about 14 μ m.

Each sublayer of hard coating layer 4, and intermediate layer 3 as described above may be deposited by an ordinary PVD method. However, deposition by arc ion plating or sputtering is more preferable.

Table 1 shows samples A1 to A7 of the present invention corresponding to Fig. 1, and comparative samples B1 to B7 corresponding to the prior art of Fig. 3. In all of the coated hard tools in accordance with the samples of the present invention and the comparative samples, a super hard alloy of ISO-P30 having the shape designated as SDKN42MT was used as base material 1, and various hard coating layers were deposited by arc ion plating.



Table 1

Samples of the Invention	No.	Layer 4	Layer 4A	Layer 4B	Amount of Wear
	A1	4 μ m	TiN:1nm AlN:1nm Total:500nm	TiN 500nm	0.115mm
	A2	10.2 μ m	TiN:50nm AlN:50nm Total:5000nm	TiN 100nm	0.122mm
	A3	3.1 μ m	HfC:20nm NbO:20nm Total:120nm	TiC 500nm	0.232mm
	A4	10.2 μ m	ZrCN:5nm TaN:5nm Total:120nm	SiC 5000nm	0.265mm
	A5	6 μ m	VN:8nm BN:8nm Total:1000nm	TiC 200nm	0.264mm
	A6	1 μ m	Al ₂ O ₃ :1nm TiCN:1nm Total:100nm	TaCN 100nm	0.245mm
	A7	2 μ m	TiAlN:2nm TiN:2nm Total:150nm	TiN 150nm	0.154mm
Comparative Samples	No.	Layer 2'	Sublayer		Amount of Wear
	B1	4 μ m	TiN:1nm AlN:1nm		0.444mm
	B2	10.2 μ m	TiN:50nm AlN:50nm		0.325mm
	B3	3.1 μ m	HfC:20nm NbO:20nm		0.432mm
	B4	10.2 μ m	ZrCN:5nm TaN:5nm		0.369mm
	B5	6 μ m	VN:8nm BN:8nm		0.367mm
	B6	1 μ m	Al ₂ O ₃ :1nm TiCN:1nm		0.301mm
	B7	2 μ m	TiAlN:2nm TiN:2nm		0.258mm



Referring to Table 1, in sample A1 of the present invention, coating layer 4 having an entire or total thickness of $4\mu\text{m}$ is deposited on base material 1. Sublayer 4A contained in coating layer 4 has a thickness of 500 nm as a whole, in which a sublayer 4a1 of TiN having a thickness of 1 nm and a sublayer 4a2 of AlN having a thickness of 1 nm are stacked alternately and repeatedly. Another sublayer 4B contained in coating layer 4 is formed of a single layer of TiN and has a thickness of 500 nm.

In comparative sample B1 which is to be compared with sample A1 of the present invention, coating layer 2' has a thickness of $4\mu\text{m}$, similar to coating layer 4 of sample A1 of the present invention. However, the comparative sample does not contain any sublayer which corresponds to the sublayer 4B. More specifically, coating layer 2' of comparative sample B1 simply includes a sublayer of TiN having a thickness of 1 nm and a sublayer of Al having a thickness of 1 nm stacked alternately and repeatedly to a large number. This corresponds to the single sublayer 4A of sample A1 of the present invention with the thickness increased.

As for samples A2 to A7 of the present invention and corresponding comparative samples B2 to B7, these have respective thicknesses and compositions as shown in Table 1, similar to the case of sample A1 and comparative sample

B1.

Using the samples of the present invention and comparative samples shown in Table 1 as cutting tips, a cutting test of cutting alloyed steel blocks was performed under the following conditions, and a resulting flank wear amount of each sample was measured.

(Conditions of cutting test)

Cut material: SCM435 (hardness: HB250)

Method of cutting: milling

10 Manner of cutting: dry

Speed of cutting: 200 m/min

Depth of cutting: 1.5 mm

Feed of milling: 0.25 mm/blade

Cutting length: 2 m

15 Table 1 also shows the flank wear amount measured for each sample, as a result of the cutting test described above. As is apparent from comparison of the flank wear amounts of samples A1 to A7 and comparative samples B1 to B7 in Table 1, samples of the present invention have a
20 stable wear resistance and hence the amount of wear is remarkably reduced, as compared with the comparative samples.



Table 2

Samples of the Invention	No.	Layer 4	Layer 4A	Layer 4B	Intermediate Layer	Amount of Wear
	C1	4 μ m	TiN:1nm AlN:1nm Total:500nm	TiN 500nm	TiN 1 μ m	0.032mm
	C2	10.2 μ m	TiN:50nm AlN:50nm Total:5000nm	TiN 100nm	TiN 1 μ m	0.045mm
	C3	3.1 μ m	HfC:20nm NbO:20nm Total:120nm	TiC 500nm	HfO 0.5 μ m	0.125mm
	C4	10.2 μ m	ZrCN:5nm TaN:5nm Total:120nm	SiC 5000nm	TiCN 0.5 μ m	0.135mm
	C5	6 μ m	VN:8nm BN:8nm Total:1000nm	TiC 200nm	TiZrN 2 μ m	0.119mm
	C6	1 μ m	Al ₂ O ₃ :1nm TiCN:1nm Total:100nm	TaCN 100nm	TaC 0.5 μ m	0.125mm
	C7	2 μ m	TiAlN:2nm TiN:2nm Total:150nm	TiN 150nm	TiN 0.5 μ m	0.098mm
Comparative Samples	No.	Layer 2	Sublayer		Intermediate Layer	Amount of Wear
	D1	4 μ m	TiN:1nm AlN:1nm		TiN 1 μ m	0.325mm
	D2	10.2 μ m	TiN:50nm AlN:50nm		TiN 1 μ m	0.225mm
	D3	3.1 μ m	HfC:20nm NbO:20nm		HfO 0.5 μ m	0.398mm
	D4	10.2 μ m	ZrCN:5nm TaN:5nm		TiCN 0.5 μ m	0.321mm
	D5	6 μ m	VN:8nm BN:8nm		TiZrN 2 μ m	0.310mm
	D6	1 μ m	Al ₂ O ₃ :1nm TiCN:1nm		TaC 0.5 μ m	0.299mm
	D7	2 μ m	TiAlN:2nm TiN:2nm		TiN 0.5 μ m	0.248mm



Table 2 shows inventive sample numbers C1 to C7 corresponding to Fig. 2, and comparative sample numbers D1 to D7 corresponding to the prior art of Fig. 4. Though sample C1 of the present invention shown in Table 2 is otherwise similar to sample A1 of Table 1, it additionally includes an intermediate layer 3 having a thickness of 1 μ m and formed of TiN. Similarly, samples C2 to C7 of the present invention shown in Table 2 are otherwise similar to samples A2 to A7 of Table 1, and additionally include intermediate layers as shown in Table 2. Comparative samples D1 to D7 of Table 2 are otherwise similar to comparative samples B1 to B7 of Table 1, and additionally include intermediate layers as shown in Table 2.

A similar cutting test as that performed with the samples of Table 1 was performed using the samples of the present invention and the comparative samples shown in Table 2. Table 2 also shows the flank wear amount of each sample measured as a result of the test. As is apparent from comparison of the respective flank wear amount of samples C1 to C7 of the present invention and of comparative samples D1 to D7 of Table 2, the samples of the present invention have a stable wear resistance and the amount of wear is remarkably reduced, as compared with the comparative samples. As is apparent from comparison between samples A1 to A7 of the present invention shown in



Table 1 which do not include any intermediate layer and samples C1 to C7 of the present invention shown in Table 2 having intermediate layers, the samples of the invention with intermediate layers have a further stabilized wear resistance and hence the amount of wear is further reduced,
5 as compared with samples of the invention not including any intermediate layer.

As described above, in the coated hard tool of the present invention, the wear resistance of the surface
10 layer is stabilized, the amount of wear is remarkably reduced and hence the life of the tool can be made longer.

Although the present invention has been described and illustrated in detail, it is clearly understood that the same is by way of illustration and example only and is not
15 to be taken by way of limitation, the spirit and scope of the present invention being limited only by the terms of the appended claims.





WHAT IS CLAIMED IS:

1. A coated hard tool including a hard base material (1) and a hard coating (4) on a surface of said base material (1), wherein

5 said coating (4) includes a total of at least four type A sublayers (4A) and type B sublayers (4B) stacked alternately starting with a type A sublayer (4A) or a type B sublayer (4B) at least indirectly on said surface of said base material (1),

10 said type A sublayer (4A) has a thickness in a range of 100 to 5000 nm, and includes a plurality of at least first secondary sublayers (4A1) and second secondary sublayers (4A2) successively stacked periodically and repeatedly with each other, wherein said first secondary sublayers (4A1) respectively have a first composition
15 including at least one compound selected from a nitride, a carbide, a nitrided carbide and an oxide containing at least one element selected from periodic group 4A elements, periodic group 5A elements, Al and B, wherein said second secondary sublayers (4A2) respectively have a second
20 composition different from said first composition and including at least one compound selected from a nitride, a carbide, a nitrided carbide and an oxide containing at least one element selected from periodic group 4A elements,



periodic group 5A elements, Al and B, and wherein each
25 said secondary sublayer (4A1, 4A2) has a thickness in a
range of 1 to 50 nm,

said type B sublayer (4B) consists of a single layer
containing at least one compound selected from a nitride,
a carbide, a nitrided carbide and an oxide containing at
30 least one element selected from periodic group 4A elements,
periodic group 5A elements, Al and B, and having a
thickness in a range of 100 to 5000 nm.

2. The coated hard tool according to claim 1, wherein
said coating (4) as a whole has a total thickness in a
range of 0.5 to 10 μ m.

3. The coated hard tool according to claim 1, further
comprising an intermediate layer (3) interposed between
said surface of said base material (1) and said coating
(4), wherein said intermediate layer (3) contains a
5 compound selected from a nitride, a carbide, a nitrided
carbide and an oxide of a periodic group 4A element, and
has a thickness in a range of 0.5 to 10 μ m, and wherein
said coating (4) and said intermediate layer (3) together
have a total thickness in a range of 1 to 14 μ m.

4. The coated hard tool according to claim 3, wherein





said intermediate layer (3) consists essentially of a single layer of one of TiN, TiCN, TiZrN, TaC, and HfO.

5 5. The coated hard tool according to claim 4, wherein said type B sublayer (4B) consists essentially of one of TiN, TiC, TaCN and SiC, and said first and second secondary sublayers (4A1, 4A2) of said type A sublayer respectively consist essentially of combinations of compounds selected from TiN/AlN, TiN/TiAlN, TiCN/Al₂O₃, HfC/NbO, ZrCN/TaN and VN/BN.

6. The coated hard tool according to claim 3, wherein said thickness of said intermediate layer (3) is not less than said thickness of said type A sublayer (4A) and is not less than said thickness of said type B sublayer (4B).

7. The coated hard tool according to claim 3, wherein said thickness of said intermediate layer (3) is at least 1 μ m.

8. The coated hard tool according to claim 3, wherein said thickness of said intermediate layer (3) is not greater than 2 μ m.

9. The coated hard tool according to claim 1, wherein



said coating (4) is arranged directly on and in contact with said surface of said base material (1).

10. The coated hard tool according to claim 1, wherein said coating (4) consists of said type A sublayers (4A) and said type B sublayers (4B).

11. The coated hard tool according to claim 10, wherein each one of said type A sublayers (4A) consists of said first secondary sublayers (4A1) and said second secondary sublayers (4A2).

12. The coated hard tool according to claim 1, wherein said type B sublayer (4B) consists essentially of one of TiN, TiC, TaCN and SiC, and said first and second secondary sublayers (4A1, 4A2) of said type A sublayer (4A) respectively consist essentially of combinations of compounds selected from TiN/AlN, TiN/TiAlN, TiCN/Al₂O₃, HfC/NbO, ZrCN/TaN and VN/BN.

13. The coated hard tool according to claim 1, wherein said hard base material (1) comprises one of a cermet, an alumina based ceramic, a silicon nitride based ceramic, and a superhard alloy selected from a WC-Co alloy, and a WC-Co alloy containing WC, Co, and at least one of a





carbide, a nitride, and a nitrided carbide of at least one of Ti, Ta, and Nb.

14. The coated hard tool according to claim 1, wherein said coating (4) includes at least 8 of said type A and type B sublayers (4A, 4B).

15. The coated hard tool according to claim 1, wherein said coating (4) includes at least 10 of said type A and type B sublayers (4A, 4B).

16. The coated hard tool according to claim 1, wherein said coating (4) includes at least 13 of said type A and type B sublayers (4A, 4B).

17. The coated hard tool according to claim 1, wherein each said type A sublayer (4A) includes at least 24 of said first and second secondary sublayers (4A1, 4A2).

18. The coated hard tool according to claim 1, wherein each said type A sublayer (4A) includes at least 75 of said first and second secondary sublayers (4A1, 4A2).

19. The coated hard tool according to claim 1, wherein each said type A sublayer (4A) includes at least





100 of said first and second secondary sublayers (4A1,
4A2).