CLAIMS

1. A primer composition comprising:

an alkoxysilane polymer comprising a unit derived from a silane-based monomer containing at least two amino or imino groups and a unit derived from a trialkoxysilane-based monomer;

an acrylic resin comprising at least one selected from units derived from non-functional acrylate monomers; and

a hydrogenated rosin resin,

wherein the hydrogenated rosin resin comprises at least one selected from hydrogenated rosin ester-based resins and derivatives thereof,

wherein the hydrogenated rosin resin is contained in an amount of 5 to 30 parts by weight, based on 100 parts by weight of the alkoxysilane polymer.

~~2. The primer composition according to claim 1, wherein the hydrogenated rosin resin comprises at least one selected from hydrogenated rosin ester-based resins and derivatives thereof.~~

~~3~~2. The primer composition according to claim 1, wherein the alkoxysilane polymer comprises an alkoxysilane polymer obtained by reacting the trialkoxysilane-based monomer and the silane-based monomer containing at least two amino or imino groups in a weight ratio of greater than 1:1 and 5:1 or less.

~~4~~3. The primer composition according to claim 1, wherein the acrylic resin further comprises a unit derived from a functional acrylate monomer, and

the functional acrylate monomer comprises at least one selected from a glycidyl group-containing acrylate monomer and a hydroxyl group-containing acrylate monomer.

~~5~~4. The primer composition according to claim ~~4~~3, wherein the acrylic resin comprises an acrylic resin obtained by reacting the non-functional acrylate monomer and the functional acrylate monomer in a weight ratio of 5:1 to 25:1.

~~6~~5. The primer composition according to claim 1, wherein the acrylic resin is contained in an amount of 20 to 50 parts by weight, ~~and the hydrogenated rosin resin is contained in an amount of 5 to 30 parts by weight,~~ based on 100 parts by weight of the alkoxysilane polymer.

~~7~~6. The primer composition according to claim 1, further comprising an epoxy resin.

~~8~~7. The primer composition according to claim ~~7~~6, wherein the sum of the total weight of the hydrogenated rosin resin and the epoxy resin is 10 to 50 parts by weight based on 100 parts by weight of the alkoxy silane polymer.