



EP 0 134 305 B1

Description

Field of the invention and background

The present invention relates to high-performance permanent magnet materials based on rare earth elements and iron, which make no use of Co that is rare and expensive.

Magnetic materials and permanent magnets are one of the important electric and electronic materials applied in an extensive range from various electrical appliances for domestic use to peripheral terminal devices of large-scaled computers. In view of recent needs for miniaturization and high efficiency of electric and electronic equipment, there has been an increasing demand for upgrading of permanent magnets and in general magnetic materials.

Now, referring to the permanent magnets, typical permanent magnet materials currently in use are alnico, hard ferrite and rare earth-cobalt magnets. With a recent unstable supply of cobalt, there has been a decreasing demand for alnico magnets containing 20—30 wt.% of cobalt. Instead, inexpensive hard ferrite containing iron oxides as the main component has showed up as major magnet materials. Rare earth-cobalt magnets are very expensive, since they contain 50—65 wt.% of cobalt and make use of Sm that is not much found in rare earth ores. However, such magnets have often been used primarily for miniaturized magnetic circuits of high added value, because they are by much superior to other magnets in magnetic properties.

In order to make it possible to inexpensively and abundantly use high-performance magnets such as rare earth-cobalt magnets in wider fields, it is required that one does not substantially rely upon expensive cobalt, and uses mainly as rare earth metals light rare earth elements such as neodymium and praseodymium which occur abundantly in ores.

In an effort to obtain permanent magnets as an alternative to such rare earth-cobalt magnets, studies have first been made of binary compounds based on rare earth elements and iron.

Existing compounds based on rare earth elements and iron are limited in number and kind compared with the compounds based on rare earth elements and cobalt, and are generally low in Curie temperature (point). For that reason, any attempts have resulted in failure to obtain magnets from the compounds based on rare earth elements and iron by casting or powder metallurgical technique used for the preparation of magnets from the compounds based on rare earth elements and cobalt. Regarding the following explanations, it is to be noted that the unit $1 \text{ G} = 10^{-4} \text{ T}$ and that the unit $1 \text{ Oe} = 0.0796 \text{ k} \cdot \text{A/m}$ and that the unit $1 \text{ MGOe} = 7.96 \text{ K J/m}^3$.

A. E. Clark discovered that sputtered amorphous TbFe_2 had a coercive force, H_c , of as high as 30 kOe at 4.2°K , and showed H_c of 3.4 kOe and a maximum energy product, $(\text{BH})_{\text{max}}$, of 7 MGOe at room temperature upon heat-treating at 300 to 350°C (Appl. Phys. Lett. 23(11), 1973, 642—645).

J. J. Croat et al have reported that H_c of 7.5 kOe is obtained with the melt-quenched ribbons of NdFe and PrFe wherein light rare earth elements Nd and Pr are used. However, such ribbons show B_r of 5 kG or below and $(\text{BH})_{\text{max}}$ of barely 3—4 MGOe (Appl. Phys. Lett. 37, 1980, 1096; J. Appl. Phys. 53, (3) 1982, 2404—2406).

Thus, two manners, one for heat-treating the previously prepared amorphous mass and the other for melt-quenching it, have been known as the most promising means for the preparation of magnets based on rare earth elements and iron.

However, the materials obtained by these methods are in the form of thin films or strips so that they cannot be used as the magnet materials for ordinary electric circuits such as loud speakers or motors.

Furthermore, N. C. Koon et al discovered that H_c of 9 kOe was reached upon heat treated ($B_r = 5 \text{ kG}$) with melt-quenched ribbons of heavy rare earth element-containing FeB base alloys to which La was added, say, $(\text{Fe}_{0.82}\text{B}_{0.18})_{0.9}\text{Tb}_{0.05}\text{La}_{0.05}$ (Appl. Phys. Lett. 39(10), 1981, 840—842).

In view of the fact that certain FeB base alloys are made easily amorphous, L. Kabacoff et al prepared the melt-quenched ribbons of $(\text{Fe}_{0.8}\text{B}_{0.2})_{1-x}\text{Pr}_x$ ($x=0-0.3$ in atomic ratio), but they showed H_c of only several Oe at room temperature (J. Appl. Phys. 53(3) 1982, 2255—2257).

The magnets obtained from such sputtered amorphous thin film or melt-quenched ribbons are thin and suffer limitations in view of size, and do not provide practical permanent magnets which can be used as such for general magnetic circuits. In other words, it is impossible to obtain bulk permanent magnets of any desired shape and size such as the prior art ferrite and rare earth-cobalt magnets. Since both the sputtered thin films and the melt-quenched ribbons are magnetically isotropic by nature, it is indeed almost impossible to obtain therefrom magnetically anisotropic permanent magnets of high performance.

Recently, the permanent magnets have increasingly been exposed to even severer circumstances—strong demagnetizing fields incidental to the thinning tendencies of magnets, strong inverted magnetic fields applied through coils or other magnets, high processing rates of current equipment, and high temperatures incidental to high loading—and, in many applications, now need possess a much higher coercive force for the stabilization of their properties. It is generally noted in this connection that the iH_c of permanent magnets decreases with increases in temperature. For that reason, they will be demagnetized upon exposure to high temperatures, if their iH_c is low at room temperature. However, if iH_c is sufficiently high at room temperature, such demagnetization will then not substantially occur.

Ferrite or rare earth-cobalt magnets make use of additive elements or varied composition systems to obtain a high coercive force; however, there are generally drops of saturation magnetization and $(\text{BH})_{\text{max}}$.



EP 0 134 305 B1

Summary of the disclosure

An essential object of the present invention is to provide novel permanent magnets and magnet materials, from which the disadvantages of the prior art are substantially eliminated.

As a result of studies made of a number of systems for the purpose of preparing compound magnets based on R-Fe binary systems, which have a high Curie point and are stable at room temperature, it has already been found that FeBR and FeBRM base compounds are especially suited for the formation of magnets (Europ. Patent Application Nos. 83106573.5 filed on July 5, 1983, 83 113 252 and 83 113 253).

A symbol R is here understood to indicate at least one of rare earth elements inclusive of Y and, preferably, refer to light rare earth elements such as Nd and Pr. B denotes boron, and M stands for at least one element selected from the group consisting of Al, Ti, V, Cr, Mn, Zr, Hf, Nb, Ta, Mo, Ge, Sb, Sn, Bi, Ni and W.

The FeBR magnets have a practically sufficient Curie point of as high as 300°C or more. In addition, these magnets can be prepared by the powder metallurgical procedures that are alike applied to ferrite or rare earth-cobalt systems, but not successfully employed for R-Fe binary systems.

The FeBR base magnets can mainly use as R relatively abundant light rare earth elements such as Nd and/or Pr, do not necessarily contain expensive Co or Sm, and can show (BH)max of as high as 36 MGOe or more that exceeds largely the highest (BH)max value (31 MGOe) of the prior art rare earth-cobalt magnets.

It has further been found that the magnets based on these FeBR and FeBRM system compounds exhibit crystalline X-ray diffraction patterns that are sharply distinguished over those of the conventional amorphous strips or melt-quenched ribbons, and contain as the major phase a novel crystalline structure of the tetragonal system (Europ. Patent Application No. 83106573.5).

In general, these FeBR and FeBRM base alloys have a Curie point ranging from about 300°C to 370°C.

More specifically, the present invention has for its object to increase the thermal properties, particularly iHc while retaining a maximum energy product, (BH)max, which is identical with, or larger than, that obtained with the aforesaid FeBR and FeBRM base magnets.

According to the present invention, it is possible to markedly increase the iHc of FeBR and FeBRM base magnets wherein as R light rare earth elements such as Nd and/or Pr are mainly used, while maintaining the (BH)max thereof at a high level, by incorporating thereto R₁ forming part of R, said R₁ representing at least one of rare earth elements selected from the group consisting of Dy, Tb, Gd, Ho, Er, Tm and Yb.

Namely, R₁ is mainly comprised of heavy rare earth elements.

That is to say, the permanent magnets according to the present invention are as follows.

Magnetically anisotropic sintered permanent magnets are comprised of the FeBR system in which R represents the sum of R₁ and R₂ wherein:

R₁ is at least one of rare earth elements selected from the group consisting of Dy, Tb, Gd, Ho, Er, Tm and Yb, and

R₂ includes a total of 80 at % or more of Nd and/or Pr relative to the entire R₂, and contains at least one of other rare earth elements exclusive of R₁ but inclusive of Y,

said system consisting essentially of, by atomic percent, 0.05 to 5% of R₁, 12.5 to 20% of R, 4 to 20% of B, and the balance being Fe.

The other aspect of the present invention provides an anisotropic sintered permanent magnet of the FeBRM system.

Brief description of the drawings

Fig. 1 is a graph showing the B-H demagnetization curves at 20°C and 100°C of the R-Co magnet with the permeance coefficient B/H;

Fig. 2 is a graph showing changes in iHc (kOe) and (BH)max (MGOe) of one embodiment of the present invention wherein Dy is replaced for Nd (the abscissa-logarithmic scale, x—at % Dy);

Fig. 3 is a graph showing the demagnetization curves of the magnets according to the present invention;

Fig. 4 is a graph showing the B-H demagnetization curves of the magnets according to the present invention with the permeance coefficient; and

Fig. 5 is a graph showing the demagnetizing factor of the present magnet and the Sm₂Co₁₇ type magnet upon exposure to the atmosphere of 100°C×1 hr and cooling down to room temperature (the abscissa—permeance coefficient B/H, logarithmic scale).

Detailed description of the preferred embodiments

In the present disclosure, % denotes atomic percent if not otherwise specified.

Magnetically anisotropic sintered permanent magnets comprise FeBRM systems in which R represents the sum of R₁ and R₂, and M represents one or more additional elements to be added in amounts of no more than the values as specified below wherein:

R₁ is at least one of rare earth elements selected from the group consisting of Dy, Tb, Gd, Ho, Er, Tm and Yb,

R₂ includes a total of 80% or more of Nd and/or Pr and contains at least one of light rare earth elements exclusive of R₁ but inclusive of Y, and M is

EP 0 134 305 B1



3%	Ti,	3.3%	Zr,	3.3%	Hf,
4.5%	Cr,	5%	Mn,	6%	Ni,
7%	Ta,	3.5%	Ge,	1.5%	Sn,
1%	Sb,	5%	Bi,	5.2%	Mo,
9%	Nb,	5%	Al,	5.5%	V,
and 5%	W,				

5 said systems essentially consisting of, by atomic percent, 0.05 to 5% of R₁, 12.5 to 20% of R, 4 to 20% of B and the balance being Fe, provided that, when two or more additional elements M are included, the sum of
 10 M should be no more than the maximum value among those specified above of said elements M actually added.

It is noted that the allowable limits of typical impurities to be included in the end products should be no higher than the following values by atomic percent:

15	2%	Cu,	2%	C,	2%	P,
	4%	Ca,	4%	Mg,	2%	O,
	5%	Si, and	2%	S,		

It is noted, however, that the sum of impurities should be no more than 5%.

20 Such impurities are expected to be originally present in the starting material, or to come from the process of production, and the inclusion thereof in amounts exceeding the aforesaid limits would result in deterioration of properties. Among these impurities, Si serves both to increase Curie points and to improve corrosion resistance, but incurs decreases in iHc in an amount exceeding 5%. Ca and Mg may abundantly be contained in the R raw material, and has an effect upon increases in iHc. However, it is unpreferable to
 25 use Ca and Mg in larger amounts, since they deteriorate the corrosion resistance of the end products.

Having the composition as mentioned above, the permanent magnets show a coercive force, iHc, of as high as 10 kOe or more, while they retain a maximum energy product, (BH)max, of 20 MGOe or more.

The present invention will now be explained in detail.

30 As mentioned above, the FeBR base magnets possess high (BH)max, but their iHc was only similar to that of the Sm₂Co₁₇ type magnet which was typical one of the conventional high-performance magnets (5 to 10 kOe). This proves that the FeBR magnets are easily demagnetized upon exposure to strong demagnetizing fields or high temperatures, say, they have no good stability. The iHc of magnets generally decreases with increases in temperature. For instance, the Sm₂Co₁₇ type magnets or the FeBR base magnets have a coercive force of barely 5 kOe at 100°C (see Table 4).

35 Any magnets having such iHc cannot be used for magnetic disc actuators for computers or automobile motors, since they tend to be exposed to strong demagnetizing fields or high temperatures. To obtain even higher stability at elevated temperatures, it is required to further increase iHc at temperatures near room temperature.

40 It is generally known that magnets having higher iHc are more stable even at temperatures near room temperature against deterioration with the lapse of time (changes with time) and physical disturbances such as impacting and contacting.

Based on the above-mentioned knowledge, further detailed studies were mainly focused on the FeBR componental systems. As a result, it has been found that a combination of at least one of rare earth elements Dy, Tb, Gd, Ho, Er, Tm and Yb with light rare earth elements such as Nd and Pr can provide a high
 45 coercive force that cannot possibly be obtained with the FeBR and FeBRM base magnets.

Furthermore, the compositional systems according to the present invention have an effect upon not only increases in iHc but also improvements in the loop squareness of demagnetization curves, i.e., further increases in (BH)max. Various studies made to increase the iHc of the FeBR base magnets have revealed that the following procedures are effective.

50 (1) Increasing the amount of R or B, and (2) adding additional element(s) M.

However, it is recognized that increasing the amount of R or B serves to enhance iHc, but, as that amount increases, Br decreases with the values of (BH)max decreasing as a result.

It is also true that the additional element(s) M is effective to increase iHc, but, as the amount of M increases, (BH)max drops again, thus not giving rise to any noticeable improvements.

55 In accordance with the permanent magnets of the present invention, an increase in iHc by aging is remarkable owing to the inclusion of R₁ that is rare earth elements, especially heavy rare earth elements, the main use of Nd and Pr as R₂, and the specific composition of R and B. It is thus possible to increase iHc without having an adverse influence upon the value of Br by aging the magnetically anisotropic sintered bodies comprising alloys having the specific composition as mentioned above. Besides, the loop
 60 squareness of demagnetization curves is improved, while (BH)max is maintained at the same or higher level. It is noted in this connection that, when the composition of R and B and the amount of Nd plus Pr are within the specified ranges, iHc of about 10 kOe or higher is already reached prior to aging. Post-aging thus gives rise to a more favorable effect in combination with the incorporation of a given amount of R₁ into R.

That is to say, the present invention provides high-performance magnets which, while retaining
 65 (BH)max of 20 MGOe or higher, with sufficient stability to be expressed in terms of iHc of 10 kOe or higher,



EP 0 134 305 B1

and can find use in applications wider than those in which the conventional high-performance magnets have found use.

The maximum values of $(BH)_{\max}$ and iH_c are 38.4 MGOe (see No. 19 in Table 3 given later) and 20 kOe or more (see No. 8 in Table 2 and Nos. 14, 22 and 23 in Table 3), respectively.

(It is here noted that the reason why the value of iH_c is shown as 20 kOe or more is that measuring could not be performed with a demagnetization tester of the ordinary electromagnet type).

In the permanent magnets according to the present invention, R represents the sum of R_1 and R_2 , and encompasses Y as well as rare earth elements Nd, Pr, La, Ce, Tb, Dy, Ho, Er, Eu, Sm, Gd, Pm, Tm, Yb and Lu. Out of these rare earth elements, at least one of seven elements Dy, Tb, Gd, Ho, Er, Tm and Yb is used as R_1 . R_2 represents rare earth elements except the above-mentioned seven elements and, especially, includes a sum of 80 at % or more of Nd and Pr in the entire R_2 , Nd and Pr being light rare earth elements.

The rare earth elements used as R may or may not be pure, and those containing impurities entrained inevitably in the process of production (other rare earth elements, Ca, Mg, Fe, Ti, C, O, S and so on) may be used alike, as long as one has commercially access thereto. Also alloys of those rare earth elements with other component elements such as Nd-Fe alloy, Pr-Fe alloy, Dy-Fe alloy or the like may be used.

As boron (B), pure- or ferro-boron may be used, including those containing as impurities Al, Si, C and so on.

When composed of 0.05—5 at % R_1 , 12.5—20 at % R representing the sum of $R_1 + R_2$, 4—20 at % B, and the balance being Fe, the permanent magnets according to the present invention show a high coercive force (iH_c) on the order of no less than about 10 kOe, a high maximum energy product ($(BH)_{\max}$) on the order of no less than 20 MGOe and a residual magnetic flux density (Br) on the order of no less than 9 kG.

The composition of 0.2—3 at % R_1 , 13—19 at % R, 5—11 at % B, and the balance being Fe are preferable in that they show $(BH)_{\max}$ of 30 MGOe or more.

As R_1 , particular preference is given to Dy and Tb.

The reason for placing the lower limit of R upon 12.5 at % is that, when the amount of R is below that limit, Fe precipitates from the alloy compounds based on the present systems, and causes a sharp drop of coercive force. The reason for placing the upper limit of R upon 20 at % is that, although a coercive force of no less than 10 kOe is obtained even in an amount exceeding 20 at %, yet Br drops to such a degree that the required $(BH)_{\max}$ of no less than 20 MGOe is not attained.

Referring now to the amount of R_1 forming part of R, H_c increases even by the substitution of 0.1% R_1 for a part of R, as will be understood from No. 2 in Table 2. The loop squareness of demagnetization curves is also improved with increases in $(BH)_{\max}$. The lower limit of R_1 is placed upon 0.05 at %, taking into account the effects upon increases in both iH_c and $(BH)_{\max}$ (see Fig. 2). As the amount of R_1 increases, iH_c increases (Nos. 2 to 8 in Table 2), and $(BH)_{\max}$ decreases bit by bit after showing a peak at 0.4 at %.

However, for example, even 3 at % addition gives $(BH)_{\max}$ of 30 MGOe or higher (see Fig. 2). In applications for which stability is especially needed, the higher the iH_c , say, the more the amount of R_1 , the better the results will be. However, the elements constituting R_1 are contained in rare earth ores to only a slight extent, and are very expensive. This is the reason why the upper limit of R_1 is fixed at 5 at %. When the amount of B is 4 at % or less, iH_c decreases to 10 kOe or less. Like R, B serves to increase iH_c , as its amount increases, but there is a drop of Br. To give $(BH)_{\max}$ of 20 MGOe or more the amount of B should be no more than 20 at %.

The additional element(s) M serves to increase iH_c and improve the loop squareness of demagnetization curves. However, as the amount of M increases, Br decreases. Br of 9 kG or more is thus needed to obtain $(BH)_{\max}$ of 20 MGOe or more. This is the reason why the upper limits of M to be added are fixed as mentioned in the foregoing. When two or more additional elements M are included, the sum of M should be no more than the maximum value among those specified in the foregoing of said elements M actually added. For instance, when Ti, Ni and Nb are added, the sum of these elements is no more than 9 at %, the upper limit of Nb. Preferable as M are V, Nb, Ta, Mo, W, Cr and Al. It is noted that, except some M such as Sb or Sn, the amount of M is preferably within about 2 at %.

The permanent magnets of the present invention are obtained as sintered bodies. It is then important that the sintered bodies have a mean crystal grain size of 1 to 80 μm (microns), for the FeBR systems and 1 to 90 μm (microns) for the FeBRM system. For both systems, the mean crystal grain size preferably amounts to 2—40 μm (microns) and more preferably about 3—10 μm (microns). Sintering may be carried out at a temperature of 900 to 1200°C. Aging following sintering can be carried out at a temperature between 350°C and the sintering temperature, preferably between 450 and 800°C. The alloy powders for sintering have appropriately a mean particle size of 0.3 to 80 μm (microns), preferably 1 to 40 μm (microns), more preferably 2—20 μm (microns). Sintering conditions, etc. are disclosed in a parallel European application to be filed by the same assignee with this application based on Japanese Patent Application Nos. 58-88373 and 58-90039.

The embodiments and effects of the present invention will now be explained with reference to examples, which are given for the purpose of illustration alone, and are not intended to limit the scope of the present invention.

Samples were prepared by the following steps (purity is given by weight).

(1) Alloys were melted by high-frequency melting and cast in a water-cooled copper mold. As the starting materials for Fe, B and R use was made of 99.9% electrolytic iron, ferroboration alloys of 19.38% B,

5.32% Al, 0.74% Si, 0.03% C and the balance Fe, and a rare earth element or elements having a purity of 99.7% or higher with the impurities being mainly other rare earth elements, respectively.

(2) Pulverization: The castings were coarsely ground in a stamp mill until they passed through a 0.420 mm (35-mesh) sieve, and then finely pulverized in a ball mill for 3 hours to 3–10 μm (microns).

(3) The resultant powders were aligned in a magnetic field of 10 kOe and compacted under a pressure of 1471 bar (1.5 t/cm²).

(4) The resultant compacts were sintered at 1000–1200°C for one hour in an argon atmosphere and, thereafter, allowed to cool.

The samples were processed, polished, and tested to determine their magnetic properties in accordance with the procedures for measuring the magnetic properties of electromagnets.

Example 1

Prepared were alloys containing as R a number of combinations of Nd with other rare earth elements, from which magnets were obtained by the above-mentioned steps. The results are shown in Table 1. It has been found that, among the rare earth elements R, there are certain elements R₁ such as Gd, Ho, Er, Yb and so on, which have a marked effect on improvements in iHc, as seen from Nos. 6 to 9. Nos. *1 to *5 show comparison examples.

Example 2

In accordance with the foregoing procedures, magnets were obtained using light rare earth elements, mainly Nd and Pr, in combination with the rare earth elements, which were chosen in a wider selection than as mentioned in Example 1 and applied in considerably varied amounts. To increase further iHc, heat treatment was applied at 600 to 700°C for two hours in an argon atmosphere. The results are set forth in Table 2.

In Table 2, No. *1 is a comparison example wherein only Nd was used as the rare earth element. Nos. 2 to 8 are examples wherein Dy was replaced for Nd. iHc increases gradually with increases in the amount of Dy, and (BH)_{max} reaches a maximum value when the amount of Dy is about 0.4 at %. See also Fig. 2.

Fig. 2 (with the abscissa expressed in the term of a log scale) indicates that Dy begins to affect iHc from 0.05 at %, and enhance its effect from 0.1 to 0.3 at %. Although Gd (No. 10), Ho (No. 9), Tb (No. 11), Er (No. 12), Yb (No. 13), etc. have a similar effect, yet a particularly large effect on increases in iHc is obtained with Dy and Tb. The elements represented by R₁, other than Dy and Tb, also give iHc exceeding largely 10 kOe and high (BH)_{max}. Any magnets materials having (BH)_{max} of as high as 30 MGOe or higher which can provide such a high iHc have not been found until now.

Fig. 3 shows a demagnetization curve of 3% Dy (No. 8 in Table 2) having typical iHc, from which it is recognized that iHc is sufficiently high compared with that of the Fe-B-Nd base sample (No. *1 in Table 2).

Fig. 4 shows the B-H demagnetization curves at 20°C and 100°C of Fe-8B-13.5Nd-1.5Dy (No. 7 in Table 2) obtained according to the present invention.

Compared with the demagnetization curve of the 30 MGOe-grade rare earth-cobalt magnet of Fig. 1, the B-H curves of the invented alloy of Fig. 4 are extending almost linearly in the secondary quadrant even at 100°C. This indicates that the invented alloy is more stable at both 20°C and 100°C against extraneous demagnetizing fields, etc. that the rare earth-cobalt magnet of Fig. 1 whose B-H curve bends in the vicinity of a permeance coefficient (B/H) of 1.

To substantially compare two types of magnets with each other in respect of stability, prepared were samples with the permeance coefficient being about 0.5, 2 and 4, which were in turn subjected to atmospheric exposure testing at 100°C for one hour after magnetization and cooled down to room temperature to measure their irreversible loss magnetic flux. Fig. 5 shows the results, from which it has been found that the invented magnets are more stable than the prior art magnets.

Observation of demagnetization of magnets upon exposure to high temperatures is generally known as one method for acceleration testing of stability at room temperature (changes with time). From the results, the magnets according to the present invention are expected to possess sufficient stability at room temperature.

Example 3

As the additional elements M use was made of Ti, Mo, Bi, Mn, Sb, Ni, Ta, Sn and Ge, each having a purity of 99%, W having a purity of 98%, Al having a purity of 99.9%, Hf having a purity of 95%, ferrovanadium (serving as V) containing 81.2% of V, ferroniobium (serving as Nb) containing 67.6% of Nb, ferrochromium (serving as Cr) containing 61.9% of Cr and ferrozirconium (serving as Zr) containing 75.5% of Zr, wherein the purity is given by weight percent.

The starting materials were alloyed and sintered in accordance with the foregoing procedures, followed by aging at 500–700°C. The results are shown in Table 3.

It has been ascertained that the FeBRM base alloys prepared by adding the additional elements M to the FeBR base systems have also sufficiently high iHc. For example, compare Nos. 15, 18 and 13 with Nos. 29, 30 and 31 respectively, in Table 3.



EP 0 134 305 B1**TABLE 1**

No.	Alloy composition (at %)	iHc (kOe)	Br (KG)	(BH) _{max} (MGOe)
*1	Fe-8B-15Nd	7.3	12.1	32.1
*2	Fe-8B-14Nd-2Y	8.8	11.9	31.8
*3	Fe-8B-10.5Nd-4.5Ce	5.7	10.7	22.4
*4	Fe-8B-10.5Nd-4.5Pr	8.9	11.4	26.9
*5	Fe-8B-14Nd-1Sm	5.4	12.3	27.0
6	Fe-8B-10.5Nd-4.5Yb	10.4	11.7	27.4
7	Fe-8B-10.5Nd-4.5Er	9.8	10.6	25.8
8	Fe-8B-10.5Nd-4.5Gd	11.4	10.3	25.0
9	Fe-8B-10.5Nd-4.5Ho	14.3	10.1	23.9

N.B.: *refers to reference tests

This Sheet Has Been Replaced



EP 0 134 305 B1

TABLE 2

No.	Alloy Composition (at %)	iHc (kOe)	Br (kG)	(BH)max (MGOe)
*1	Fe-8B-15Nd	11.4	12.3	34.0
2	Fe-8B-14.9Nd-0.1Dy	11.8	12.4	35.0
3	Fe-8B-14.8Nd-0.2Dy	12.0	12.6	36.2
4	Fe-8B-14.6Nd-0.4Dy	12.8	12.7	38.0
5	Fe-8B-14.2Nd-0.8Dy	16.1	12.0	34.2
6	Fe-8B-13.8Nd-1.2Dy	18.0	11.5	31.3
7	Fe-8B-13.5Nd-1.5Dy	18.6	11.7	31.5
8	Fe-8B-12Nd-3Dy	>20	11.4	30.3
9	Fe-8B-13.5Nd-1.5Ho	13.8	11.95	33.8
10	Fe-8B-13.5Nd-1.5Gd	13.8	11.75	32.1
11	Fe-8B-13.5Nd-1.5Tb	18.3	11.3	33.2
12	Fe-8B-13.5Nd-1.5Er	14.8	11.5	31.0
13	Fe-8B-13.5Nd-1.5Yb	13.1	12.3	35.0
14	Fe-6B-6Nd-6Pr-1.5Dy	16.3	11.2	25.2
15	Fe-10B-13Pr-1.5Dy	17.6	10.9	26.1
16	Fe-10B-10Nd-3Ce-2Dy	11.8	10.2	24.3
17	Fe-10B-11Nd-2La-1Dy-1Gd	14.2	10.7	25.5
*18	Fe-3.5B-15Nd-3Dy	5.6	9.2	18.5
*19	Fe-10B-9.5Nd-2Dy	<5	<5	<5
*20	Fe-10B-30Nd-1.5Dy	13.0	<5	<5
*21	Fe-30B-15Nd-2Dy	12.2	<5	<5

This Sheet Has Been Replaced



EP 0 134 305 B1

TABLE 3-(1)

No.	Alloy composition (at %)	iHc (kOe)	Br (kG)	(BH)max (MGOe)
1	Fe-8B-13.5Nd-1.5Dy	18.6	11.7	31.6
2	Fe-8B-13.5Nd-1.5Dy-1Ti	17.2	11.8	32.1
3	Fe-8B-13.5Nd-1.5Dy-1Zr	13.9	11.6	31.8
4	Fe-8B-13.5Nd-1.5Dy-1Hf	13.0	11.9	30.0
5	Fe-8B-13.5Nd-1.5Dy-1Cr	17.8	11.2	29.5
6	Fe-8B-13.5Nd-1.5Dy-1Mn	17.6	11.1	28.6
7	Fe-8B-13.5Nd-1.5Dy-1Ni	12.4	11.3	30.0
8	Fe-8B-13.5Nd-1.5Dy-1Ta	18.6	11.6	31.4
9	Fe-8B-13.5Nd-1.5Dy-1Ge	15.6	11.3	29.7
10	Fe-8B-13.5Nd-1.5Dy-1Sn	12.8	10.7	26.7
11	Fe-8B-13.5Nd-1.5Dy-1Sb	17.3	9.6	21.5
12	Fe-8B-13.5Nd-1.5Dy-1Bi	12.8	11.6	31.2
13	Fe-8B-13.5Nd-1.5Dy-1Mo	17.6	11.5	30.7
14	Fe-8B-13.5Nd-1.5Dy-1Nb	20	11.8	32.3
15	Fe-8B-13.5Nd-1.5Dy-1Al	19.4	11.6	31.4
16	Fe-8B-13.5Nd-1.5Dy-1V	18.7	11.5	31.0
17	Fe-8B-13.5Nd-1.5Dy-1W	19.0	11.4	30.6
18	Fe-8B-12.5Nd-1.5Dy-1Nb	17.4	11.9	33.0
19	Fe-7B-13.5Nd-0.4Dy-1Nb	12.8	12.8	38.4
20	Fe-7B-12.5Nd-1.5Dy-1Nb	16.9	12.3	35.4

This Sheet Has Been Replaced



EP 0 134 305 B1

TABLE 3-(2)

No.	Alloy composition	iHc (kOe)	Br (kG)	(BH)max (MGOe)
21	Fe-8B-11.5Nd-1.5Dy-1Nb	16.3	12.2	34.8
22	Fe-7B-13.5Nd-1.5Dy-1Al	20	11.2	30.2
23	Fe-7B-14.5Nd-1.5Dy-1Nb	20	11.3	30.8
24	Fe-7B-13.5Nd-1.5Dy-1V	17.9	11.65	32.4
25	Fe-8B-13.5Nd-1.5Dy-1W	18.8	11.45	31.4
26	Fe-7B-16.2Nd-0.8Dy-1Nb	17.2	11.0	28.6
27	Fe-8B-13.5Nd-1.5Dy-1Si**	13.6	11.5	30.8
28	Fe-8B-13.5Nd-1.5Dy-1S**	14.0	12.1	34.2
*29	Fe-8B-15Nd-1Al	11.8	11.7	31.2
*30	Fe-8B-15Nd-1Nb	12.2	11.9	32.7
*31	Fe-8B-15Nd-1Mo	12.0	11.9	33.8

NB: **refers to other elements than M

TABLE 4

	Room temperature (22°C)		100°C	
	iHc (kOe)	(BH)max (MGOe)	iHc (kOe)	(BH)max (MGOe)
R-Co (2—17 type) magnet	6.2	29.3	5.2	26.4
Fe-8B-15Nd	11.4	34.0	5.6	26.8
Fe-8B-13.5Nd-1.5Dy	18.6	31.5	9.8	27.0

Claims

1. A magnetically anisotropic sintered permanent magnet of the FeBR system in which R represents the sum of R₁ and R₂ wherein:

R₁ is at least one of rare earth elements selected from the group consisting of Dy, Tb, Gd, Ho, Er, Tm and Yb, and

R₂ consists of a total of 80 at % or more of Nd and/or Pr relative to the entire R₂, and the balance of at least one of other rare earth elements exclusive of R₁ but inclusive of Y,

said system consisting essentially of, by atomic percent, 0.05 to 5% of R₁, 12.5 to 20% of R, 4 to 20% of B, and the balance being Fe.

2. A magnet according to claim 1 characterized by containing at least one of the additional elements M in the amount of no more than the values as specified hereinbelow, M being:

3%	Ti,	3.3%	Zr,	3.3%	Hf,
4.5%	Cr,	5%	Mn,	6%	Ni,
7%	Ta,	3.5%	Ge,	1.5%	Sn,
1%	Sb,	5%	Bi,	5.2%	Mo,
9%	Nb,	5%	Al,	5.5%	V,
and 5%	W,				

This Sheet Has Been Replaced





TABLE 3-(2)

No.	Alloy composition	iHc (kOe)	Br (kG)	(BH)max (MGOe)
21	Fe-8B-11.5Nd-1.5Dy-1Nb	16.3	12.2	34.8
22	Fe-7B-13.5Nd-1.5Dy-1Al	20	11.2	30.2
23	Fe-7B-14.5Nd-1.5Dy-1Nb	20	11.3	30.8
24	Fe-7B-13.5Nd-1.5Dy-1V	17.9	11.65	32.4
25	Fe-8B-13.5Nd-1.5Dy-1W	18.8	11.45	31.4
26	Fe-7B-16.2Nd-0.8Dy-1Nb	17.2	11.0	28.6
27	Fe-8B-13.5Nd-1.5Dy-1Si**	13.6	11.5	30.8
28	Fe-8B-13.5Nd-1.5Dy-1S**	14.0	12.1	34.2
*29	Fe-8B-15Nd-1Al	11.8	11.7	31.2
*30	Fe-8B-15Nd-1Nb	12.2	11.9	32.7
*31	Fe-8B-15Nd-1Mo	12.0	11.9	33.8

NB: **refers to other elements than M

TABLE 4

	Room temperature (22°C)		100°C	
	iHc (kOe)	(BH)max (MGOe)	iHc (kOe)	(BH)max (MGOe)
R-Co (2—17 type) magnet	6.2	29.3	5.2	26.4
Fe-8B-15Nd	11.4	34.0	5.6	26.8
Fe-8B-13.5Nd-1.5Dy	18.6	31.5	9.8	27.0

Claims

1. A magnetically anisotropic sintered permanent magnet of the FeBR system in which R represents the sum of R₁ and R₂ wherein:

R₁ is at least one of rare earth elements selected from the group consisting of Dy, Tb, Gd, Ho, Er, Tm and Yb, and

R₂ consists of a total of 80 at % or more of Nd and/or Pr relative to the entire R₂, and the balance of at least one of other rare earth elements exclusive of R₁ but inclusive of Y,

said system consisting essentially of, by atomic percent, 0.05 to 5% of R₁, 12.5 to 20% of R₂, 4 to 20% of B, and the balance being Fe.

2. A magnet according to claim 1 characterized by containing at least one of the additional elements M in the amount of no more than the values as specified hereinbelow, M being:

3%	Ti,	3.3%	Zr,	3.3%	Hf,
4.5%	Cr,	5%	Mn,	6%	Ni,
7%	Ta,	3.5%	Ge,	1.5%	Sn,
1%	Sb,	5%	Bi,	5.2%	Mo,
9%	Nb,	5%	Al,	5.5%	V,
and 5%	W,				

This Sheet Has Been Replaced





EP 0 134 305 B1

provided that, when two or more additional elements M are included, the total amount of M is limited to the highest value of one of the individual elements M added.

3. A permanent magnet according to Claim 1 or 2, wherein, by atomic percent, R_1 is 0.2—3%, R is 13—19%, and B is 5—11%.
- 5 4. A permanent magnet according to Claim 1 or 2, wherein R_1 comprises Dy and/or Tb.
5. A permanent magnet according to Claim 1 or 2, wherein R_1 is Dy.
6. A permanent magnet according to Claim 1 or 2, wherein R_1 is 0.1 at % or more.
7. A permanent magnet according to Claim 1 or 2, wherein R_1 is about 0.4 at %.
8. A permanent magnet according to Claim 1 or 2, wherein R_1 is about 1.5 at %.
- 10 9. A permanent magnet according to Claim 2, wherein the additional elements M comprises one or more selected from the group consisting of V, Nb, Ta, Mo, W, Cr and Al.
10. A permanent magnet according to Claim 9, wherein M is no more than about 2 at %.
11. A permanent magnet according to Claim 1 or 2, which has been subjected to aging after sintering at a temperature between 350°C and a sintering temperature.
- 15 12. A permanent magnet according to Claim 1 or 2, which has a maximum energy product (BH)_{max} of 160 kJ/m³ (20 MGOe) or more.
13. A permanent magnet according to Claim 3, which has a maximum energy product (BH)_{max} of 240 kJ/m³ (30 MGOe) or more.
14. A permanent magnet according to Claim 1 or 2, which has an intrinsic coercive force iH_c of 800 k·A/m (10 kOe) or more.
- 20 15. A permanent magnet according to Claim 11, which has a maximum energy product (BH)_{max} of 200 kJ/m³ (25 MGOe) or more.
16. A permanent magnet according to Claim 15, which has (BH)_{max} of 260 kJ/m³ (33 MGOe) or more.
17. A permanent magnet according to Claim 7, which has (BH)_{max} of 260 kJ/m³ (33 MGOe) or more.
- 25 18. A permanent magnet according to Claim 17, which has (BH)_{max} of 280 kJ/m³ (35 MGOe) or more.
19. A permanent magnet according to Claim 11 which has an intrinsic coercive force iH_c of 1000 k·A/m (13 kOe) or more.
20. A permanent magnet according to Claim 19, which has iH_c of 1200 k·A/m (15 kOe) or more.
21. A permanent magnet according to Claim 20, which has iH_c of 1400 k·A/m (17 kOe) or more.
- 30 22. A permanent magnet according to Claim 8, which has iH_c of 1200 k·A/m (15 kOe) or more.
23. A permanent magnet according to Claim 22, which has iH_c of 1400 k·A/m (17 kOe) or more.

Patentansprüche

- 35 1. Magnetisch anisotroper gesinterter Permanentmagnet des FeBR-Systems, in dem R die Summe aus R_1 und R_2 darstellt, wobei R_1 mindestens eines der Seltenerdmetalle Dy, Tb, Gd, Ho, Er, Tm und Yb bedeutet, sowie R_2 aus insgesamt 80 Atom-% oder mehr Nd und/oder Pr, bezogen auf das gesamte R_2 , und als Rest der Atomprozent aus mindestens einem anderen Seltenelement, ausgenommen R_1 , aber einschließlich Y, besteht, und wobei das genannte System im wesentlichen aus 0,05 bis 5% R_1 , 12,5 bis 20% R, 4 bis 20% B, jeweils angegeben in Atom-%, und als Rest Eisen besteht.
2. Magnet nach Anspruch 1, dadurch gekennzeichnet, daß er mindestens eines der zusätzlichen
- 45 Elemente M in einer Menge, welche die nachfolgenden Werte nicht übersteigt, enthält, wobei M

3%	Ti,	3,3%	Zr	3,3%	Hf,
4,5%	Cr,	5%	Mn,	6%	Ni,
7%	Ta,	3,5%	Ge,	1,5%	Sn,
1%	Sb,	5%	Bi,	5,2%	Mo,
50 9%	Nb,	5%	Al,	5,5%	V,
und 5%	W				

- bedeutet, mit der Maßgabe, daß beim Vorliegen von zwei oder mehr der zusätzlichen Elemente M die Gesamtmenge von M auf den höchsten Wert eines der zugegebenen einzelnen Elemente M begrenzt ist.
- 55 3. Permanentmagnet nach Anspruch 1 oder 2, worin R_1 einen Wert von 0,2 bis 3%, R einen Wert von 13 bis 19% und B einen Wert von 5 bis 11%, jeweils angegeben in Atom-%, aufweisen.
4. Permanentmagnet nach Anspruch 1 oder 2, worin R_1 die Bedeutung von Dy und/oder Tb hat.
5. Permanentmagnet nach Anspruch 1 oder 2, worin R_1 die Bedeutung von Dy hat.
- 60 6. Permanentmagnet nach Anspruch 1 oder 2, worin R_1 einen Wert von 0,1 Atom-% oder mehr aufweist.
7. Permanentmagnet nach Anspruch 1 oder 2, worin R_1 einen Wert von etwa 0,4 Atom-% aufweist.
8. Permanentmagnet nach Anspruch 1 oder 2, worin R_1 einen Wert von etwa 1,5 Atom-% aufweist.
9. Permanentmagnet nach Anspruch 2, worin die zusätzlichen Elemente M mindestens eines der
- 65 Elemente V, Nb, Ta, Mo, W, Cr und Al bedeuten.

This Sheet Has Been Replaced





EP 0 134 305 B1

10. Permanentmagnet nach Anspruch 9, worin M in einer Menge von nicht mehr als etwa 2 Atom-% vorliegt.
11. Permanentmagnet nach Anspruch 1 oder 2, der nach dem Sintern bei einer Temperatur zwischen 350°C und einer Sintertemperatur einem Altern unterworfen worden ist.
12. Permanentmagnet nach Anspruch 1 oder 2, der ein Maximalenergieprodukt (BH)_{max} von 160 kJ/m³ (20 MGOe) oder mehr aufweist.
13. Permanentmagnet nach Anspruch 3, der ein Maximalenergieprodukt (BH)_{max} von 240 kJ/m³ (30 MGOe) oder mehr aufweist.
14. Permanentmagnet nach Anspruch 1 oder 2, der eine Induktionskoerzitivkraft iH_c von 800 kA/m (10 kOe) oder mehr aufweist.
15. Permanentmagnet nach Anspruch 11, der ein Maximalenergieprodukt (BH)_{max} von 200 kJ/m³ (25 MGOe) oder mehr aufweist.
16. Permanentmagnet nach Anspruch 15, der ein (BH)_{max} von 260 kJ/m³ (33 MGOe) oder mehr aufweist.
17. Permanentmagnet nach Anspruch 7, der ein (BH)_{max} von 260 kJ/m³ (33 MGOe) oder mehr aufweist.
18. Permanentmagnet nach Anspruch 17, der ein (BH)_{max} von 280 kJ/m³ (35 MGOe) oder mehr aufweist.
19. Permanentmagnet nach Anspruch 11, der eine Induktionskoerzitivkraft iH_c von 1000 kA/m (13 kOe) oder mehr aufweist.
20. Permanentmagnet nach Anspruch 19, der eine iH_c von 1200 kA/m (15 kOe) oder mehr aufweist.
21. Permanentmagnet nach Anspruch 20, der eine iH_c von 1400 kA/m (17 kOe) oder mehr aufweist.
22. Permanentmagnet nach Anspruch 8, der eine iH_c von 1200 kA/m (15 kOe) oder mehr aufweist.
23. Permanentmagnet nach Anspruch 22, der eine iH_c von 1400 kA/m (17 kOe) oder mehr aufweist.

Revendications

1. Aimant permanent fritté magnétiquement anisotrope du système FeBR, R représentant la somme de R₁ et R₂, dans lequel:
- R₁ représente au moins un élément faisant partie des terres rares, choisi dans le groupe comprenant Dy, Tb, Gd, Ho, Er, Tm et Yb, et
- R₂ comprend une quantité totale égale ou supérieure à 80% at. de Nd et/ou Pr, par rapport à la quantité totale de R₂, le reste étant constitué d'au moins un autre élément faisant partie des terres rares, à l'exclusion de R₁ mais y compris Y,
- ledit système consistant essentiellement, en pourcentage atomique, en 0,05 à 5% de R₁, 12,5 à 20% de R, 4 à 20% de B, le reste étant du Fe.
2. Aimant suivant la revendication 1, caractérisé en ce qu'il contient au moins l'un des éléments supplémentaires M en une quantité non supérieure aux valeurs mentionnées ci-dessous, M étant:

3%	Ti,	3,3%	Zr,	3,3%	Hf,
4,5%	Cr,	5%	Mn,	6%	Ni,
7%	Ta,	3,5%	Ge,	1,5%	Sn,
1%	Sb,	5%	Bi,	5,2%	Mo,
9%	Nb,	5%	Al,	5,5%	V
et 5%	W				

sous réserve que, lorsque deux ou plus de deux éléments M supplémentaires sont incorporés, la quantité totale de M soit limitée à la valeur la plus élevée de l'un des différents éléments M ajoutés.

3. Aimant permanent suivant la revendication 1 ou 2, dans lequel, en pourcentage atomique, R₁ est présent en une quantité de 0,2 à 3%, R est présent en une quantité de 13 à 19% et B est présent en une quantité de 5 à 11%.
4. Aimant permanent selon la revendication 1 ou 2, dans lequel R₁ consiste en Dy et/ou Tb.
5. Aimant permanent suivant la revendication 1 ou 2, dans lequel R₁ représente Dy.
6. Aimant permanent suivant la revendication 1 ou 2, dans lequel R₁ est présent en une quantité égale ou supérieure à 0,1% at.
7. Aimant permanent suivant la revendication 1 ou 2, dans lequel R₁ est présent en une quantité d'environ 0,4% at.
8. Aimant permanent suivant la revendication 1 ou 2, dans lequel R₁ est présent en une quantité d'environ 1,5% at.
9. Aimant permanent suivant la revendication 2, dans lequel les éléments M supplémentaires consistent en un ou plusieurs éléments choisis dans le groupe comprenant V, Nb, Ta, Mo, W, Cr et Al.
10. Aimant permanent suivant la revendication 9, dans lequel M est présent en une quantité non supérieure à environ 2% at.
11. Aimant permanent suivant la revendication 1 ou 2, qui a été soumis à un vieillissement après frittage à une température comprise dans l'intervalle de 350°C à la température de frittage.





EP 0 134 305 B1

12. Aimant permanent suivant la revendication 1 ou 2, qui possède un facteur maximal d'énergie (BH)max égal ou supérieur à 160 kJ/m^3 (20 MGOe).
13. Aimant permanent suivant la revendication 3, qui possède un facteur maximal d'énergie (BH)max égal ou supérieur à 240 kJ/m^3 (30 MGOe).
- 5 14. Aimant permanent suivant la revendication 1 ou 2, qui possède une force coercitive intrinsèque iHc égale ou supérieure à $800 \text{ k} \cdot \text{A/m}$ (10 kOe).
15. Aimant permanent suivant la revendication 11, qui possède un facteur maximal d'énergie (BH)max égal ou supérieur à 200 kJ/m^3 (25 MGOe).
- 10 16. Aimant permanent suivant la revendication 15, qui possède un (BH)max égal ou supérieur à 260 kJ/m^3 (33 MGOe).
17. Aimant permanent suivant la revendication 7, qui possède un (BH)max égal ou supérieur à 260 kJ/m^3 (33 MGOe).
18. Aimant permanent suivant la revendication 17, qui possède un (BH)max égal ou supérieur à 280 kJ/m^3 (35 MGOe).
- 15 19. Aimant permanent suivant la revendication 11, qui possède une force coercitive intrinsèque iHc égale ou supérieure à $1000 \text{ k} \cdot \text{A/m}$ (13 kOe).
20. Aimant permanent suivant la revendication 19, qui possède une iHc égale ou supérieure à $1200 \text{ k} \cdot \text{A/m}$ (15 kOe).
21. Aimant permanent suivant la revendication 20, qui possède une iHc égale ou supérieure à $1400 \text{ k} \cdot \text{A/m}$ (17 kOe).
- 20 22. Aimant permanent suivant la revendication 8, qui possède une iHc égale ou supérieure à $1200 \text{ k} \cdot \text{A/m}$ (15 kOe).
23. Aimant permanent suivant la revendication 22, qui possède une iHc égale ou supérieure à $1400 \text{ k} \cdot \text{A/m}$ (17 kOe).

25

30

35

40

45

50

55

60

65

This Sheet Has Been Replaced

