

**PELLETIZED BROMINATED ANIONIC STYRENIC POLYMERS AND
THEIR PREPARATION AND USE**

BACKGROUND

[0001] Brominated anionic styrenic polymers are excellent flame retardants. Very desirable methods for preparing such polymeric flame retardants are described in U.S. Pat. Nos. 5,677,390; 5,686,538; 5,767,203; 5,852,131; 5,916,978; and 6,207,765.

[0002] A characteristic of brominated anionic styrenic polymers such as brominated anionic polystyrene is its propensity to form substantial amounts of small particles and powders when attempts are made to pelletize the product. It appears that upon formation the pellets, unless bound together by an extraneous binding agent or the like, tend to break apart and to revert to small particles and finely-divided powder, typically referred to as "fines". Because of this characteristic, various conventional pelletizing procedures are unsuitable for producing brominated anionic styrenic polymers essentially free of fines. As can be readily appreciated, the existence of fines in a product of this type is not only detrimental to the appearance of the pelletized product but in addition is undesired by the consumer.

[0003] In order to effectively use brominated anionic styrenic polymers as flame retardants in certain thermoplastic polymers, the use of binding agents or other extraneous materials to maintain the integrity of the flame retardant in pelletized form, is also deemed undesirable by the consumer. Thus, there is a need for a way of producing unadulterated pelletized brominated anionic styrenic polymers that do not form undesirable amounts of fines during their preparation and packaging.

BRIEF SUMMARY OF THE INVENTION

[0004] Pursuant to this invention brominated anionic styrenic polymers can now be produced and packaged in unadulterated pelletized form essentially free of fines. Moreover preferred embodiments of this invention make this beneficial result possible on an economical basis since only relatively small amounts of fines are produced in the operation. In fact, in preferred processes of this invention small amounts of dry fines that may form can be recycled in the operation without much expense or difficulty.

[0005] Thus pursuant to one of its embodiments this invention provides pellets of unadulterated brominated anionic styrenic polymer having a bromine content of at least about 50 wt% and in which at least about 70 wt% (preferably at least about 75 wt%) of the pellets are retained on a standard US No. 40 sieve and no more than about 30 wt% (preferably no more than about 25 wt%) are retained on a standard US No. 5 sieve. In preferred embodiments such pelletized anionic styrenic polymer is brominated anionic polystyrene having a bromine content of at least about 67 wt%, *e.g.*, in the range of about 67 to about 71 wt%. Also preferred are pelletized brominated anionic styrenic polymers in which the melt flow index (ASTM D 1238-

99) is at least about 4 g/10 min at 220°C and 2.16 kg and more preferably is at least about 5 g/10 min at 220°C and 2.16 kg. If properly handled, the pellets as produced and packaged are substantially free of fines, *i.e.*, particles that pass through a standard US No. 40 sieve.

[0006] Another embodiment of this invention is a method of preparing pelletized unadulterated brominated anionic styrenic polymer which method comprises:

- A) forming strands of molten unadulterated brominated anionic styrenic polymer;
- B) submitting said strands to cooling and downwardly directed forced air flow on a porous conveyor belt whereby said strands are broken into pellets; and
- C) causing said pellets to drop into a classifier that removes fines from the pellets.

By the term "unadulterated" is meant that no extraneous ingredients such as binders (*e.g.*, waxes or other polymeric or oligomeric substances), inorganic salts, or the like are added to the brominated anionic styrenic polymer prior to or during the foregoing method of preparing the pellets. Instead, the brominated anionic styrenic polymer contains only residual impurities that remain in the brominated polymer after its preparation.

[0007] These and other embodiments of this invention will be still further apparent from the ensuing description, accompanying drawings, and appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] Fig. 1 is a schematic frontal view of a mechanical system found effective in producing pursuant to the methods of this invention, pelletized brominated anionic styrenic polymers of this invention.

[0009] Fig. 2 is a schematic plan view of the system of Fig. 1 with elements 10 and 12 removed for the sake of simplicity.

FURTHER DETAILED DESCRIPTION OF THE INVENTION


Brominated Anionic Styrenic Polymer

[0010] The polymers which are converted into pelletized form pursuant to this invention, are one, or a blend of more than one, brominated anionic styrenic polymer, *i.e.*, (i) at least one anionically-produced styrenic homopolymer that has been brominated or (ii) at least one anionically-produced copolymer of two or more styrenic monomers that has been brominated, or (iii) both of (i) and (ii). The bromine content of such polymer should be at least about 50 percent by weight. Preferred brominated anionic styrenic polymers, especially brominated anionic polystyrene, have a bromine content of at least about 60 wt%, and more preferred brominated anionic styrenic polymers, especially brominated anionic polystyrene, have a bromine content of at least about 64 wt%. Particularly preferred brominated anionic styrenic polymers, especially brominated anionic polystyrene, have a bromine content in the range of about 67 to about 69 wt%. The bromine content of brominated anionic styrenic polymers such as

brominated anionic polystyrene will seldom exceed about 71 wt%. Typically the brominated anionic styrenic polymer will have a melt flow index by the ASTM D1238-99 test procedure, conducted at 220°C and 2.16 kg, of at least about 3 g/10 min., preferably at least about 4 g/10 min. and more preferably at least about 5 g/10 min. Typically, such melt flow index will be in the range of about 3 to about 40 g/10 min., and preferably in the range of about 4 to about 35 g/10 min. Most preferred brominated anionic styrenic polymers used in the practice of this invention have a melt flow index under these test conditions in the range of about 5 to about 30 g/10 min. In this connection, these polymers may not "melt" in the sense of reaching a melting point temperature at which they suddenly become transformed from a solid to a liquid. Rather, they tend to be amorphous substances which, when heated, tend to progressively soften as temperature is increased and thus become progressively more pliable and tend to take on characteristics of a liquid such that other substances could be dispersed therewith by use of conventional mixing or blending procedures.

[0011] In all embodiments of this invention the most preferred brominated anionic styrenic polymer used in forming the pellets of this invention is unadulterated brominated anionic polystyrene.

[0012] Anionic styrenic polymers which are brominated to form the brominated anionic styrenic polymers pelletized pursuant to this invention are one or more anionic homopolymers and/or anionic copolymers of at least one vinyl aromatic monomer. Preferred vinyl aromatic monomers have the formula:



wherein R is a hydrogen atom or an alkyl group having from 1 to 4 carbon atoms and Ar is an aromatic group (including alkyl-ring substituted aromatic groups) of from 6 to 10 carbon atoms. Examples of such monomers are styrene, *alpha*-methylstyrene, *ortho*-methylstyrene, *meta*-methylstyrene, *para*-methylstyrene, *para*-ethylstyrene, isopropenyltoluene, vinylnaphthalene, isopropenylnaphthalene, vinylbiphenyl, vinylanthracene, the dimethylstyrenes, and *tert*-butylstyrene. Polystyrene is the preferred reactant. When the brominated anionic styrenic polymer is made by bromination of an anionic copolymer of two or more vinyl aromatic monomers, it is preferred that styrene be one of the monomers and that styrene comprise at least 50 weight percent and preferably at least about 80 weight percent of the copolymerizable vinyl aromatic monomers. It is to be noted that the terms "brominated anionic styrenic polymer" and "brominated anionic polystyrene" as used herein refer to a brominated anionic polymer produced by bromination of a pre-existing anionic styrenic polymer such as anionic polystyrene or an anionic copolymer of styrene and at least one other vinyl aromatic monomer, as distinguished from an oligomer or polymer produced by oligomerization or polymerization of one or more brominated styrenic monomers, the properties of the latter oligomers or polymers being considerably different from brominated anionic polystyrene in a number of respects. Also, the

terms "vinylaromatic" and "styrenic" in connection with monomer(s) or polymer(s) are used interchangeably herein.

[0013] The aromatic pendant constituents of the anionic styrenic polymer can be alkyl substituted or substituted by bromine or chlorine atoms, but in most cases, will not be so substituted. Typically, the anionic styrenic polymers used to produce the brominated anionic styrenic polymers used in the practice of this invention will have a weight average molecular weight (M_w) in the range of about 2000 to about 50,000 and a polydispersity in the range of 1 to about 10. Preferred brominated anionic styrenic polymers used in the practice of this invention are produced from anionic styrenic polymers having a weight average molecular weight (M_w) in the range of about 3000 to about 10,000 and a polydispersity in the range of 1 to about 4, and most preferably these ranges are, respectively, about 3500 to about 4500 and 1 to about 4. The M_w and polydispersity values are both based on gel permeation chromatography (GPC) techniques which are hereinafter described.

[0014] Methods for the preparation of anionic styrenic polymers such as anionic polystyrene are known in the art and reported in the literature. See for example, U.S. Pat. Nos. 3,812,088; 4,200,713; 4,442,273; 4,883,846; 5,391,655; 5,717,040; and 5,902,865, the disclosures of which are incorporated herein by reference. An especially preferred method is described in commonly-owned U.S. Pat. No. 6,657,028, issued December 2, 2003, the disclosure of which method is incorporated herein by reference.

[0015] Bromination processes which can be used for producing a brominated anionic styrenic polymer are disclosed in U.S. Pat. Nos. 5,677,390; 5,686,538; 5,767,203; 5,852,131; 5,916,978; and 6,207,765 which disclosures are incorporated herein by reference.

[0016] Typical properties of preferred brominated anionic polystyrene for use in preparing the pellets of this invention include the following:

Appearance/form - white powder

Bromine Content - 67 to 71 wt%

Melt flow index (220°C. 2.16 kg) - 4 to 35 g/10 min

Tg(°C) - 162

Specific gravity (@ 23°C) - 2.2

TGA (TA instruments model 2950, 10°C/min. under N₂):

1% weight loss, °C - 342

5% weight loss, °C - 360

10% weight loss, °C - 368

50% weight loss, °C - 393

90% weight loss, °C - 423

[0017] If deemed necessary or desirable, any reliable analytical procedure such as reported in the literature can be employed in determining such analysis or properties. In any doubtful or disputed case, the following procedures are recommended:

1) Bromine Content - Since brominated anionic styrenic polymers have good, or at least satisfactory, solubility in solvents such as tetrahydrofuran (THF), the determination of the total bromine content for a brominated anionic styrenic polymer is easily accomplished by using conventional X-Ray Fluorescence techniques. The sample analyzed is a dilute sample, say 0.1 ± 0.05 g brominated anionic polystyrene in 60 mL THF. The XRF spectrometer can be a Phillips PW1480 Spectrometer. A standardized solution of bromobenzene in THF is used as the calibration standard.

[0018] 2) Melt Flow Index - To determine the melt flow index of a brominated anionic styrenic polymer, the procedure and test equipment of ASTM Test Method D1238-99 are used. The extrusion plastometer is operated at 220°C and 2.16 kg applied pressure. The samples used in the tests are composed of 14 to 16 g of brominated anionic polystyrene.

[0019] 3) Weight Average Molecular Weight and Polydispersity - M_w values of anionic styrenic polymers are obtained by GPC using a Waters model 510 HPLC pump and, as detectors, a Waters Refractive Index Detector, Model 410 and a Precision Detector Light Scattering Detector, Model PD2000, or equivalent equipment. The columns are Waters, μ Styragel, 500Å, 10,000Å and 100,000 Å. The autosampler is a Shimadzu, Model Sil 9A. A polystyrene standard ($M_w = 185,000$) is routinely used to verify the accuracy of the light scattering data. The solvent used is tetrahydrofuran, HPLC grade. The test procedure used entails dissolving 0.015-0.020 g of sample in 10 mL of THF. An aliquot of this solution is filtered and 50 μL is injected on the columns. The separation is analyzed using software provided by Precision Detectors for the PD 2000 Light Scattering Detector. The instrument provides results in terms of weight average molecular weight and also in terms of number average molecular weight. Thus, to obtain a value for polydispersity, the value for weight average molecular weight is divided by the value for number average molecular weight.

Production of Pellets

[0020] As noted above, the pelletized brominated anionic styrenic polymers of this invention can be prepared by a method which comprises:

- A) forming strands of molten unadulterated brominated anionic styrenic polymer;
- B) submitting said strands while on a moving porous conveyor belt to cooling and downwardly directed forced air flow whereby at least a portion of said strands are broken into pellets; and
- C) causing said pellets to leave said conveyor belt and drop into a classifier that whereby optionally at least some additional breakage into pellets occurs and whereby the

classifier removes fines from the pellets that are formed in B) and optionally in C).

[0021] In conducting step A) above, various commercially available machines can be successfully used in forming strands of molten or softened brominated anionic styrenic polymer. For example, use can be made of a Buss Ko-Kneader (Coperion GmbH) or a co-rotating intermeshing twin screw extruder such as are available from Coperion GmbH, Berstoff, Century, Leistritz, or JSW Japan Steel Works. The machine is operated at a suitable temperature profile to cause the brominated anionic styrenic polymer to become at least highly softened if not molten. The temperature profile used will thus vary somewhat depending on the makeup of the brominated anionic styrenic polymer being processed. Thus in the case of brominated anionic polystyrene such as SAYTEX[®] HP 3010 having properties such as described above, a temperature profile of 220-240°C was found desirable.

[0022] In step B), the extrudate from the machine is passed through a die plate and the resultant continuous strands are allowed to drop onto a moving porous conveyor belt. The conveyor belt system is provided with a vacuum equipment beneath the porous bed which continuously draws air down onto the strands on the belt and downwardly through the apertures in the belt itself. Above the conveyor belt are disposed a water spray mechanism for cooling the hot polymer strands and downwardly disposed air blowers which apply sufficient force to the cooling strands which typically causes at least some breakage of the strands to occur on the belt. Surviving unbroken strands, if any, typically undergo at least some breakage as they leave the conveyor belt because of the force of gravity acting upon the unsupported strands emerging from the end of the belt.

[0023] In step C), the contents of the belt and any former contents of the conveyor belt that may be emerging from the end of the conveyor belt are caused to drop into a classifier which separates the pellets and the fines from each other. Such droppage onto the classifier may also cause some breakage to occur. The classifier can include, for example, an essentially horizontally disposed mesh which is caused to vibrate back and forth longitudinally. A particularly suitable machine of this type is a Vibratory Classifier such as is available from The Witte Company, Inc.

[0024] In a typical operation of step A), the conveyor belt used was about 14 feet (ca. 4.27 meters) in length and was operated at a speed in the range of about 100 to about 200 ft/min (ca. 60.96 meters/min.). The forced air and the water used in the misting of the strands are typically at ambient room temperatures, but can be heated if desired so as to reduce heat shock. The distance of the drop from the end of the conveyor belt to the screen of the classifier was in the range of about 18 to about 36 inches (ca. 45.7 to ca. 91.4 cm).

[0025] In a properly conducted pelletizing method of this invention, it should be possible to produce a product in which no more than about 5 wt%, preferably no more than about 3 wt%, and more preferably no more than about 1 wt% are fines or dusts that pass through a standard

U.S. No. 40 sieve. Thus, the methods of this invention are highly efficient; only small amounts of such fines are collected and preferably recycled to step A) in the overall pelletizing operation.

[0026] The foregoing illustrative operations of this invention can be still further appreciated by reference to the drawings. Referring now to the preferred system as schematically depicted in Figs. 1 and 2 wherein like numerals depict like parts, brominated anionic styrenic polymer in powder form, preferably brominated anionic polystyrene powder having properties such as those of Saytex HP-3010 polymer (Albemarle Corporation) in powder form is fed from hopper **10** into powder feeder **12** and via hopper **14** into kneader **15**. From kneader **15** the polymer is directed into crosshead extruder **16**. The kneader-extruder combination heats and forms a melt of the brominated anionic styrenic polymer and the melt is discharged through die **18** whereby strands, typically continuous strands, of the polymer are extruded from the die onto moving conveyor belt **20**. In the system depicted, belt **20** is upwardly inclined such that the remote end of the upper portion of the belt is typically about 18 to about 36 inches (ca. 45.7 to ca. 91.4 cm) above vibratory classifier **30**. Spray system denoted generally as **33** forms and dispenses a mist or spray of water onto the hot polymer strands on the upper portion of belt **20** which is traveling in the direction shown by arrow **35**. The cooled strands are then carried by belt **20** under air knives **37,37** which cut or break at least a portion of the strands into pellets. At the underside of belt **20** in proximity to the location of air knives **37,37** are vacuum inlets **39,39** of a conventional vacuum manifold system (not shown) which draws off residual water and fines from the underside of belt **20**. The resultant pellets are discharged at the upper outer end of belt **20** and fall under the influence of gravity onto the operative upper surface of classifier **30** which can be a vibratory classifier such as schematically depicted in Fig. 3. The impact of the fall can result in formation of addition pellets through breakage of larger pieces falling from belt **20**. Thus the pellets in the system depicted in Figs. 1 and 2 are mainly formed in the region extending from the air knives **37,37** to and including classifier **30**. Fines are separated by and collected within classifier **30** which continuously transfers the pellets remaining after the separation onto transfer device **40** such as a segmented conveyor or bucket elevator disposed to receive and convey the pellets forwardly and upwardly to an elevation suitable for feeding the pellets to a suitable heavy duty packaging container **50**, such as a Supersack or Gaylord container. A small amount of pellet breakage, which is typically inconsequential, may occur in such packaging step but if this occurs it can be minimized by reduction in the height of the fall from the transfer device to the packaging container.

[0027] It will be readily appreciated that the system as depicted in Figs. 1 and 2 can be suitably altered to achieve formation of pelletized unadulterated brominated anionic styrenic polymer, that is essentially free of fines. For example, a kneader such as a Buss Ko-kneader and associated crosshead extruder can be replaced by a suitable twin screw extruder, such as for example any twin screw or single screw extruder having a length/diameter (L/D) ratio equal

to or greater than 20/1. It is also possible to replace the strand die, conveyor, and vibratory classifier with a die-face pelletizer or eccentric pelletizer.

Pellets of the Invention

[0028] Pursuant to this invention, pelletized brominated anionic styrenic polymers are produced having as formed and packaged little, if any, fine particles or dusts. Generally speaking the pellets of this invention are composed of unadulterated brominated anionic styrenic polymer having a bromine content of at least about 50 wt% (preferably at least about 60 wt%) and in which at least about 70 wt% (preferably at least about 75 wt%) of the pellets are retained on a standard US No. 40 sieve and no more than about 30 wt% (preferably no more than about 25 wt%) are retained on a standard US No. 5 sieve. In more preferred embodiments the bromine content of the pellets is at least about 64 wt%, and particularly preferred brominated anionic styrenic polymers, have a bromine content in the range of about 67 to about 69 wt%. The bromine content of the pelletized brominated anionic styrenic polymers of this invention such as brominated anionic polystyrene will seldom exceed about 71 wt%, and thus especially preferred are pelletized brominated anionic styrenic polymers of this invention having in the range of about 67 to about 71 wt%. Also preferred are pelletized brominated anionic styrenic polymers in which the melt flow index (ASTM D1238-99) is at least about 4 and preferably is at least about 5.

[0029] Especially preferred pellets of this invention are formed from brominated anionic styrenic polymers having a bromine content in the range of about 67 to about 71 wt% and more preferably in the range of about 67 to about 69 wt% bromine, and wherein at least about 80 wt% (more preferably at least about 85 wt%, and most preferably at least about 90 wt%) of the pellets are retained on a standard U.S. No. 40 sieve and no more than about 20 wt% (more preferably no more than about 15 wt% and most preferably no more than about 10 wt%) are retained on a standard U.S. No. 5 sieve. In all cases the preferred brominated anionic styrenic polymer in all of the foregoing pelletized products is brominated anionic polystyrene.

[0030] Another characteristic of preferred pellets of this invention is that when poured into a 20 mL cylindrical transparent plastic capped bottle, the interior walls of the bottle remain essentially free of any visibly perceptible dust or powder.

Use of the Pellets as Flame Retardants

[0031] The pellets of this invention can be used as flame retardants in a wide variety of thermoplastic polymers. Among such polymers are thermoplastic polyesters, such as polyethylene terephthalate, polybutylene terephthalate, polytrimethylene terephthalate, polycyclohexylene terephthalate, *etc.*; thermoplastic polyamides, such as nylon 6, nylon 6,6, nylon 6,12, *etc.*; polycarbonates; polyphenylene oxides, such as poly(2,6-dimethylphenylene

oxide); polysulphones; polystyrene or other styrenic homopolymers; copolymers of two or more styrenic monomers such as copolymers of styrene, vinyltoluene, ethylstyrene, tert-butylstyrene, α -methylstyrene, vinylnaphthalene, *etc.*; rubber-modified vinylaromatic homopolymers or copolymers (*e.g.*, high impact polystyrene); acrylate or methacrylate polymers such as ethylene-methylacrylate, ethylene-ethylacrylate, ethylene-butylacrylate, poly(methylmethacrylate), *etc.*; ethylene-vinylacetate copolymers; acrylonitrile-based copolymers and terpolymers such as acrylonitrile-butadiene-styrene (ABS) and styrene-acrylonitrile (SAN), *etc.*; polyolefins, such as polyethylene, polypropylene, poly-(1-butene), and copolymers of ethylene with one or more higher vinyl olefins such as propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene; and blends, alloys, or composites of different polymers such as for example a blend of poly(2,6-dimethylphenylene oxide) and polystyrene, a blend of polycarbonate and polystyrene, and similar blends. Additional polymers that can be flame retarded by use therewith of pelletized flame retardant additives of this invention include rubbery block copolymers such as styrene-ethylene-ethylene-styrene, styrene-ethylene-propylene-styrene, styrene-ethylene-butylene-styrene, *etc.*; polyurethanes; epoxy resins; phenolic resins; elastomers such as natural rubber, butyl rubber, GRS, GRN, EPDM, *etc.*; polysiloxanes; and the like. Further, the polymer may be, where appropriate, cross-linked by chemical means or by radiation. A large number of flame retardant-free polymers suitable for use in the practice of this invention can be obtained from a number of commercial sources.

[0032] A preferred group of substrate polymers that can be effectively flame retarded by use of the pellets of this invention are polyesters. Thermoplastic polyesters, often referred to as polyalkylene terephthalates, are reaction products of aromatic dicarboxylic acid or reactive derivatives thereof, such as methyl esters or anhydrides, and aliphatic, cycloaliphatic, or araliphatic diols, and mixtures of such reaction products. Examples of such thermoplastic polyesters include polyethylene terephthalate, polypropylene terephthalate, polybutylene terephthalate, polycyclohexylene dimethylene terephthalate, and related copolyesters and blends, including blends of one or more thermoplastic polyesters with one or more other thermoplastic polymers such as polycarbonates, and especially aromatic polycarbonates.

[0033] Preferred thermoplastic polyesters contain at least 80% by weight and preferably at least 90% by weight, based on the dicarboxylic acid component, of terephthalic acid and at least 80% by weight and preferably at least 90% by weight, based on the diol component, of ethylene glycol and/or 1,4-butanediol units.

[0034] In addition to terephthalic acid units, the preferred thermoplastic polyesters may contain up to 20 mole % and preferably up to 10 mole % of units of other aromatic or cycloaliphatic C₈₋₁₄ dicarboxylic acids or aliphatic C₄₋₁₂ dicarboxylic acids, such as, for example, units of phthalic acid, isophthalic acid, 2,6-naphthalene dicarboxylic acid, 4,4'-diphenyl

dicarboxylic acid, succinic acid, adipic acid, sebacic acid, azelaic acid, or cyclohexane diacetic acid.

[0035] In addition to ethylene glycol and 1,4-butanediol units, the preferred thermoplastic polyesters may contain up to 20 mole % and preferably up to 10 mole % of other aliphatic C₃₋₁₂ diols or cycloaliphatic C₆₋₁₂ diols, such as, for example, units of 1,3-propanediol, 2-ethylpropane-1,3-diol, neopentyl glycol, 1,5-pentanediol, 1,6-hexanediol, 1,4-cyclohexane-dimethanol, 3-ethylpentane-2,4-diol, 2-methylpentane-2,4-diol, 2,2,3-trimethylpentane-1,3-diol, 2-ethylhexane-1,3-diol, 2,2-diethylpropane-1,3-diol, 2,5-hexanediol, 2,2-bis(4-hydroxy-cyclohexyl)propane, 2,4-dihydroxy-1,1,3,3-tetramethylcyclobutane, 2,2-bis[4-(2-hydroxy-ethoxy)phenyl]propane, or 2,2-bis-[4-hydroxypropoxy]phenyl]propane.

[0036] Polyalkylene terephthalates may be branched by incorporation of relatively small quantities of trihydric or tetrahydric alcohols or tribasic or tetrabasic carboxylic acids. In this connection see, for example, U.S. Pat. No. 3,692,744. Examples of preferred branching agents are trimesic acid, trimellitic acid, trimethylol ethane and propane and pentaerythritol.

[0037] Particularly preferred thermoplastic polyesters are those produced solely from terephthalic acid or a reactive derivative thereof such as a dialkyl ester, and ethylene glycol and/or 1,4-butane diol, and mixtures of these polyalkylene terephthalates. Preferred polyalkylene terephthalate mixtures contain 1 to 50% by weight of polyethylene terephthalate and 99 to 50 wt% of polybutylene terephthalate. Particularly preferred mixtures contain 1 to 30 wt% of polyethylene terephthalate and 99 to 70% by weight of polybutylene terephthalate.

[0038] The polyalkylene terephthalates preferably used generally have an intrinsic viscosity of 0.4 to 1.5 dl/g, preferably 0.5 to 1.3 dl/g and more preferably 0.55 to 1.2 dl/g, as measured in phenol/o-dichlorobenzene (1:1 parts by weight) at 25°C. using an Ubbelohde viscosimeter. Polyethylene terephthalate and polybutylene terephthalate of these intrinsic viscosity ranges, and mixtures thereof, are most preferred. As is well known, polyethylene terephthalate engineering resin producers compound their products from either virgin PET (typically 0.55-0.70 IV) or reclaimed PET from industrial scrap, polyester film scrap, bottles and, rarely polyester fiber scrap.

[0039] Additional thermoplastic polyesters which may be utilized in the practice of this invention include, for example, polyetheresters, polyester-polycarbonate blends or alloys, polyester-ABS blends or alloys, polyester-MBS blends or alloys, and impact-modified thermoplastic polyesters.

[0040] Polyalkylene terephthalates may be produced by known methods. See, for example, *Encyclopedia of Polymer Science and Technology*, Vol. 11, pages 62-128, John Wiley & Sons, Inc., copyright 1969; and Kirk-Othmer, *Encyclopedia of Chemical Technology*, 4th Ed., Vol. 19, pages 609-653, John Wiley & Sons, Inc., copyright 1996.

[0041] Another group of preferred thermoplastic polymers which can be effectively flame retarded by use of the pellets of this invention are polyamides, which are sometimes referred to as nylon polymers. Such polyamide substrate polymer can be any amorphous and/or partly crystalline, predominately aliphatic/cycloaliphatic or partially aromatic thermoplastic polyamide. Typically such materials are produced by polycondensation and/or polymerization processes from diamines which are predominately or entirely aliphatic or cycloaliphatic in structure, or which are partially or entirely aromatic in structure, and carboxylic acids or lactams which are predominantly or entirely aliphatic or cycloaliphatic in structure, or which are partially or entirely aromatic in structure. Typical amines used in forming polyamides include such diamines as hexamethylenediamine, tetramethylenediamine, 2,2,4- and 2,4,4-trimethyl-hexamethylenediamine, diaminodicyclohexylmethane (isomers), diaminodicyclohexylpropane (isomers) and isophoronediamine (isomers), and xylylenediamine. Also used as source materials are aminocarboxylic acids such as ϵ -aminocaproic acid, or ω -aminocarboxylic acids such as ω -aminolauric acid and ω -aminoundecanoic acid. Typically, the carboxylic acid used are aliphatic or mixed aliphatic-aromatic dicarboxylic acids having less than 50% by weight aromatic constituents such as adipic acid, 2,2,4- and 2,4,4-trimethyladipic acid, azelaic acid, sebacic acid, decanedicarboxylic acid, dodecanedicarboxylic acid, cyclohexanedicarboxylic acid, hexahydroterephthalic acid, isophthalic acid and terephthalic acid.

[0042] Copolyamides from the majority of the known monomers can also be used.

[0043] Illustrative polyamides which may be used in the practice of this invention are such polyamides as nylon 6, nylon 6,6, nylon 6,9, nylon 6,10, nylon 6,12, nylon 11, nylon 12, nylon 12,12, nylon 6/6,6 copolymer, and high temperature nylons such as nylon 4,6, and partially aromatic nylons (e.g., Ixef polyarylamide PA MXD6 from Solvay, Zytel HTN from DuPont, and Amodel polyarylamide from Solvay). Other polyamides which may be used include Arlen modified polyamide 6T from Mitsui Chemicals, Inc., Genestar PA9T polyamide resins from Kuraray Company, Stanyl polyamide 46 from DSM, Vydyne polyamide 6/66 copolymers from Monsanto, polyamide 612 (Vestamid D from Creanova), and similar polyamides. Of the various nylon polymers, nylon 6 and nylon 6,6 are the preferred substrate polymers.

[0044] This invention is also applicable to thermoplastic blends or alloys of one or more polyamides such as, for example, polyamide-polyolefin blends or alloys, polyamide-ionomer blends or alloys, polyamide-ABS blends or alloys, polyamide-EPDM blends or alloys, polyamide-polyphenylene oxide blends or alloys, or impact-modified polyamides.

[0045] Methods for producing polyamide polymers are known and described in the literature. See, for example, *Encyclopedia of Polymer Science and Technology*, Vol. 10, pages 460-482, John Wiley & Sons, Inc., copyright 1969; and Kirk-Othmer, *Encyclopedia of Chemical Technology*, 4th Ed., Vol. 19, pages 559-584, John Wiley & Sons, Inc., copyright 1996.

[0046] The following examples illustrate the practice and advantages of this invention. These examples are not intended to place limitations upon the generic scope of this invention.

EXAMPLE 1

[0047] The excellent results achievable pursuant to this invention, were demonstrated in an operation in which a system as schematically depicted in Figs. 1 and 2 was used. In such system, the following equipment was used:

- a) The extruder system was a 140 mm Buss Ko-kneader **15** having an L/D of 11/1 (but which can be 7.1 or greater) fitted with crosshead extruder **16**. The screw profile of the kneader contained kneading elements.
- b) Die **18** was a 20-hole die with holes of 4 mm diameter.
- c) Conveyor belt **20** was a Scheer-Bay conveyor having a length of 14 feet (ca. 4.3 meters), a width of 15 inches (ca. 38.1 cm), and 3-inch (ca. 7.6-centimeter) diameter rollers. The mesh belt was upwardly inclined at an angle of about 12°.
- d) Classifier **30** was a Witte model no 200 Classifier.

The vertical distance between the drop from the end of belt **20** to the top of classifier **30** was about 24 inches (ca. 61 cm), and the vertical distance between the end of transfer device **40** and the bottom of shipping container **50** when empty was about 60 inches (ca. 152 cm).

[0048] The operating conditions in the system were as follows:

The extruder system was operated at barrel and melt temperatures of 220-240°C. During operation, a vacuum of 6-8 inches of mercury (ca. 0.21-0.28 kg/sq cm) was applied to both the kneader and the crosshead extruder. The conveyor traveled at a rate of 150 to 175 ft/min (ca. 45.7 to ca. 53.3 meters/minute). The water mist was fed at a rate of about 1 gallon per minute (ca. 3.79 liters per minute). The air knives were operated at a pressure of 10-25 psig and were disposed at about 5 inches (ca. 12.7 cm) above the surface of the conveyor belt. The vacuum applied beneath the conveyor belt was at about 2200 cubic feet per minute (ca. 62.3 cubic meters per minute) and the vacuum was applied directly to the proximate surface of the conveyor belt by two vacuum applicators disposed transverse to the belt with the mouth of each individual applicator having an area of 45 square inches (ca. 114.3 square centimeters).

[0049] During an operating period of 4 hours periodically samples of the brominated anionic polystyrene pellets being produced were withdrawn from the system and subjected to sieving and in some cases to melt index determinations. In the sieving operation 100 gram samples were placed on a stack of 3 members, the top being a standard U.S. No. 5 sieve, the next lower member being a standard U.S. No. 40 sieve, and the bottom member being a collection pan for fines. After the samples were placed on the upper sieve, the entire stack was struck 10 times by hand with as uniform a force as possible. Then the contents of the 3 members were weighed

thereby yielding values for wt% of pellets retained on the No. 5 sieve, on the No. 40 sieve, and in the collection pan for fines.

[0050] In the melt flow determinations, samples of the pellets were used in the standardized procedure.

[0051] Table 1 summarizes the data obtained in this operation.

TABLE 1

Sample No.	% Volatiles	Melt Flow Index	% Retained on No. 5 Sieve	% Retained on No. 40 Sieve	% Fines Passing Through No. 40 Sieve
1	0.04	5.6	8.5	91.2	0.4
2	0.04	--	8.3	91.5	0.2
3	0.04	7.4	19.4	80.2	0.4
4	0.03	--	20.3	79.1	0.6
5	0.04	--	12.0	87.6	0.3
6	0.04	7.5	4.4	94.3	1.3
7	0.04	--	12.1	87.5	0.3

EXAMPLE 2

[0052] The same equipment, operating conditions, and sample evaluation as in Example 1 were used except that the Buss Ko-kneader and the crosshead extruder were replaced by a 90 mm twin screw compounding extruder which is a co-rotating intermeshing twin screw extruder Model no. ZSK-90 manufactured by Werner Pfleiderer. This extruder was operated at a rate of 1200 lbs/hr (ca. 543 kilograms/hour) with a temperature profile of 220-240°C. In this operation the samples were taken periodically during an operation period of 4 hours. Table 2 summarizes the results of this operation.

TABLE 2

Sample No.	% Volatiles	Melt Flow Index	% Retained on No. 5 Sieve	% Retained on No. 40 Sieve	% Fines Passing Through No. 40 Sieve
1	0.27	5.6	4.1	95.9	0.0
2	0.19	--	3.1	96.3	0.6
3	0.04	6.9	2.7	96.9	0.4
4	0.08	--	3.5	96.0	0.4
5	0.07	--	6.7	92.4	0.9

6	0.04	7.0	2.7	97.1	0.2
7	--	--	4.4	95.2	0.3
8	0.04	8.6	8.3	91.3	0.3
9	--	--	4.8	94.1	1.1
10	0.04	--	4.2	95.2	0.7
11	0.06	6.3	1.6	98.0	0.4
12	0.04	--	3.2	96.4	0.4
13	0.04	6.9	1.7	98.0	0.3
14	0.04	--	4.9	95.1	0.0
15	0.06	--	3.4	95.4	0.0
16	0.06	7.4	2.2	97.1	0.7
17	0.04	--	3.2	96.4	1.0
18	0.08	7.0	0.7	97.4	1.9
19	0.04	--	0.5	98.9	0.6
20	0.04	--	4.1	95.5	0.4
21	0.04	5.4	4.5	95.3	0.2
22	0.08	--	4.2	95.4	0.4
23	0.07	5.3	1.6	95.8	2.6
24	0.07	--	1.3	97.9	0.8
25	0.08	--	2.6	95.9	1.5
26	0.06	7.7	6.1	93.6	0.5
27	0.04	--	4.3	95.4	0.3
28	0.04	5.6	2.8	97.0	0.3
29	0.04	--	2.9	96.4	0.7
30	0.04	--	1.8	96.2	2.1
31	0.04	4.9	2.3	96.0	1.7
32	0.04	--	1.7	96.8	1.5
33	0.04	5.4	2.0	97.4	0.6
34	0.04	--	2.0	96.7	1.4
35	0.08	--	1.8	96.9	1.3
36	0.08	5.8	2.7	95.8	1.5
37	0.04	5.8	2.6	97.0	0.4
38	0.04	--	4.4	95.0	0.6

39	0.04	5.2	4.1	95.7	0.3
40	0.04	--	4.5	95.2	0.3
41	0.02	--	2.2	97.4	0.4
42	0.04	5.5	5.2	94.7	0.1
43	0.04	--	7.1	92.4	0.2
44	0.04	5.4	6.5	93.0	0.4
45	0.04	--	5.3	94.6	0.2
46	0.04	--	1.7	97.9	0.4
47	0.04	5.2	6.5	92.8	0.8
48	0.04	--	4.6	94.8	0.6
49	0.04	9.0	2.6	96.4	1.0
50	0.06	--	2.2	96.8	1.0
51	0.04	--	5.3	94.5	0.2
52	0.04	5.7	7.7	92.2	0.1
53	0.04	--	6.6	93.2	0.2
54	0.04	7.7	4.6	95.4	0.0
55	0.07	--	2.5	97.0	0.5
56	0.06	--	2.4	96.9	0.7
57	0.04	9.2	4.0	93.9	2.2
58	0.04	--	7.6	92.1	0.3
59	0.04	4.6	5.9	93.3	0.8
60	0.04	--	6.3	93.5	0.2
61	0.06	--	5.5	93.5	1.0
62	0.04	7.8	6.6	93.2	0.3
63	0.07	--	6.7	93.1	0.2
64	0.04	5.7	3.6	95.8	0.6
65	0.04	--	3.8	95.4	0.8
66	0.04	--	2.9	96.2	0.9
67	0.04	5.4	3.3	96.1	0.5
68	0.04	--	1.7	98.1	0.2
69	0.04	6.1	2.6	97.0	0.5
70	0.04	--	5.5	94.1	0.5
71	0.04	--	4.2	95.6	0.2

72	0.03	--	10.3	88.7	1.0
73	0.04	--	7.0	92.7	0.3
74	0.00	5.2	6.0	93.9	0.1
75	0.04	--	5.9	93.2	0.8
76	0.04	--	3.5	95.9	0.6
77	0.04	5.8	5.2	93.3	1.5
78	0.06	--	5.1	94.7	0.2
79	0.11	6.8	5.1	94.6	0.2
80	0.06	--	5.2	94.4	0.4
81	0.06	--	4.2	94.9	0.9
82	0.04	5.8	3.3	96.0	0.7
83	0.04	--	11.5	88.3	0.3
84	0.04	6.2	7.2	90.8	0.1
85	0.04	--	8.9	90.7	0.4
86	0.00	--	8.5	91.0	0.5
87	0.00	7.2	15.0	84.8	0.2
88	0.06	--	11.0	88.7	0.2
89	0.04	6.9	9.1	90.8	0.1
90	0.04	--	6.7	93.2	0.1
91	0.04	--	8.4	91.3	0.3
92	0.04	6.2	7.3	92.6	0.1
93	0.04	--	--	--	--
94	0.04	6.0	9.0	90.8	0.2
95	0.06	--	3.3	96.3	0.4
96	0.04	--	8.4	91.4	0.2
97	0.04	6.1	3.6	96.0	0.4
98	0.04	--	2.9	97.0	0.1
99	0.04	5.8	4.2	95.4	0.4
100	0.04	--	7.9	91.8	0.3
101	0.04	--	8.0	91.8	0.2
102	0.04	7.3	5.3	94.4	0.3
103	0.04	--	9.0	90.6	0.4
104	0.04	6.2	3.7	96.0	0.4

105	0.03	--	4.1	95.0	0.9
106	0.04	--	8.6	91.1	0.3
107	0.04	6.0	8.2	91.4	0.4
108	0.00	--	6.1	93.7	0.2
109	0.04	--	6.9	92.9	0.2
110	0.04	--	5.4	94.6	0.0
111	0.04	--	5.4	94.2	0.4
112	0.06	6.3	7.1	92.8	0.2
113	0.04	--	3.4	96.2	0.5
114	0.04	--	8.9	90.5	0.6
115	0.04	--	7.9	91.5	0.6
116	0.03	--	6.7	92.3	1.0
117	0.04	6.3	9.8	90.0	0.2
118	0.04	--	11.4	88.2	0.4
119	0.04	6.1	8.7	90.9	0.4
120	0.04	--	8.1	91.5	0.4
121	0.03	--	10.3	89.5	0.2
122	0.04	6.2	7.4	92.2	0.4
123	0.04	--	7.8	91.8	0.5
124	0.04	5.9	7.5	92.2	0.3
125	0.04	--	9.1	90.8	0.1
126	0.10	--	3.2	96.6	0.2
127	0.04	5.9	4.0	95.4	0.6
128	0.04	--	12.8	85.5	1.8
129	0.00	5.6	5.8	93.5	0.6
130	0.00	--	7.9	91.7	0.4
131	0.00	--	8.9	90.4	0.7
132	0.04	5.2	7.2	92.6	0.2
133	0.04	--	7.0	92.5	0.5
134	0.04	6.6	7.0	92.6	0.4
135	0.04	--	8.9	90.7	0.4
136	0.04	--	5.0	94.2	0.8
137	0.04	7.7	4.5	93.7	1.9

[0053] Within 3 sigma statistical limits, the results tabulated in Tables 1 and 2 relative to percentages retained on No. 5 and No. 40 sieves show that for the No. 5 sieve the percentage retained is between 0 and 16 wt%, whereas 83-100 wt% were retained on the No. 40 sieve. On the same statistical basis, from 0-2 wt% of fines would pass through the No. 40 sieve. Thus, the process was found statistically to provide yields of desired products in the range of 98 to 100%.

[0054] Except as may be expressly otherwise indicated, the article "a" or "an" if and as used herein is not intended to limit, and should not be construed as limiting the description to a single element to which the article refers. Rather, the article "a" or "an" if and as used herein is intended to cover one or more such elements, unless the text expressly indicates otherwise.

[0055] Each and every patent or publication referred to in any portion of this specification is incorporated into this disclosure by reference, as if set forth herein.

[0056] This invention is susceptible to considerable variation within the spirit and scope of the appended claims. Therefore the foregoing description is not intended to limit, and should not be construed as limiting, the invention to the particular exemplifications presented hereinabove. Rather, what is intended to be covered is as set forth in the ensuing claims and the equivalents thereof permitted as a matter of law.

CLAIMS:

1. Pellets of unadulterated brominated anionic styrenic polymer having a bromine content of at least about 50 wt% and in which at least about 70 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 30 wt% are retained on a standard US No. 5 sieve.
2. Pellets as in Claim 1 wherein said bromine content is at least about 60 wt%.
3. Pellets as in Claim 1 wherein said bromine content is at least about 64 wt%.
4. Pellets as in Claim 1 wherein said bromine content is in the range of about 67 to about 71 wt%.
5. Pellets as in Claim 1 wherein said bromine content is in the range of about 67 to about 69 wt%.
6. Pellets as in any of Claims 1-5 having a melt flow index of at least 4.5.
7. Pellets as in Claim 6 wherein said melt flow index is at least 5.5.
8. Pellets as in any of Claims 1-5 wherein at least about 75 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 25 wt% are retained on a standard US No. 5 sieve.
9. Pellets as in any of Claims 1-5 wherein at least about 80 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 20 wt% are retained on a standard US No. 5 sieve.
10. Pellets as in any of Claims 1-5 wherein at least about 85 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 15 wt% are retained on a standard US No. 5 sieve.
11. Pellets as in any of Claims 1-5 wherein at least about 90 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 10 wt% are retained on a standard US No. 5 sieve.
12. Pellets as in any of Claims 1-5 wherein at least about 75 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 25 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 4.5.
13. Pellets as in any of Claims 1-5 wherein at least about 80 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 20 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 4.5.
14. Pellets as in any of Claims 1-5 wherein at least about 85 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 15 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 4.5.
15. Pellets as in any of Claims 1-5 wherein at least about 90 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 10 wt% are retained on a

standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 4.5.

16. Pellets as in any of Claims 1-5 wherein at least about 75 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 25 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 5.5.

17. Pellets as in any of Claims 1-5 wherein at least about 80 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 20 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 5.5.

18. Pellets as in any of Claims 1-5 wherein at least about 85 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 15 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 5.5.

19. Pellets as in any of Claims 1-5 wherein at least about 90 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 10 wt% are retained on a standard US No. 5 sieve, and wherein said pellets have a melt flow index of at least 5.5.

20. Pellets of unadulterated brominated anionic polystyrene having a bromine content of at least about 50 wt% and in which at least about 70 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 30 wt% are retained on a standard US No. 5 sieve.

21. Pellets as in Claim 20 wherein at least about 80 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 20 wt% are retained on a standard US No. 5 sieve, wherein said bromine content is at least about 60 wt%, and wherein said polystyrene has a melt flow index of at least 4.5.

22. Pellets as in Claim 20 wherein at least about 90 wt% of the pellets are retained on a standard US No. 40 sieve and no more than about 10 wt% are retained on a standard US No. 5 sieve, wherein said bromine content is in the range of about 67 to about 71 wt%, and wherein said polystyrene has a melt flow index of at least 5.5.

23. A method of preparing pelletized unadulterated brominated anionic styrenic polymer which method comprises:

- A) forming strands of molten unadulterated brominated anionic styrenic polymer;
- B) submitting said strands to cooling and downwardly directed forced air flow on a porous conveyor belt whereby said strands are broken into pellets; and
- C) causing said pellets to drop into a classifier that removes fines from the pellets.

24. A method as in Claim 23 wherein the unadulterated brominated anionic styrenic polymer used in A) is unadulterated brominated anionic polystyrene.

25. A method as in Claim 23 wherein said method produces no more than about 2 wt% of fines that pass through a standard U.S. No. 40 sieve.

26. A method as in any of Claims 23-25 wherein the polymer used has a melt flow index of at least about 4.5.

27. A method as in any of Claims 23-25 wherein the polymer used has a melt flow index of at least about 5.5.

28. A method as in any of Claims 23-25 wherein the polymer used has a bromine content of at least 50 wt%.

29. A method as in any of Claims 23-25 wherein the polymer used has a bromine content of at least 60 wt%.

30. A method as in any of Claims 23-25 wherein the polymer used has a bromine content in the range of about 67 to about 71 wt%.

31. A method as in any of Claims 23-25 wherein the polymer used has a bromine content of at least 60 wt% and a melt flow index of about 4.5.

32. A method as in any of Claims 23-25 wherein the polymer used has a bromine content in the range of about 67 to about 71 wt% and a melt flow index of about 5.5.