

RECOMBINANT HUMAN TYPE XVII COLLAGEN, AND PREPARATION METHOD AND USE THEREOF

Technical Field

The present disclosure relates to a recombinant human type XVII collagen, and a preparation method and use thereof, and belongs to the technical field of genetic engineering.

Background

As an important native biological protein, collagen can be widely used in many fields such as chemical industry, medicine, food, and cosmetics, and is especially suitable for the manufacture of various biological devices. Collagen is the most ideal biological material source and has promising application prospects. Collagen sold currently on the market is mainly a collagen extract obtained by treating an animal tissue through acid, alkali, and enzymatic hydrolysis. During the processing of such an extract, a native structure of collagen is basically destroyed and is severely degraded, making its biological activity lost; extracted collagen peptides have different lengths, heterogeneous properties, and unstable qualities, and may be infected by a virus; and an amino acid sequence of animal-derived collagen is quite different from an amino acid sequence of human-derived collagen, which can lead to immune rejection and allergic symptoms.

Human type XVII collagen is a transmembrane non-fibroblast collagen, which is a homogeneous trimer composed of three identical $\alpha 1$ (XVII) chains and is divided into three major domains: intracellular, transmembrane, and extracellular domains. Human type XVII collagen is a component of hemidesmosomes in cells, plays an important role in an interaction between epithelial cells and a basement membrane, can regulate the adhesion, separation, development, and differentiation of epithelial cells, and is important for the differentiation and regeneration of keratinocytes. Because a content of human type XVII collagen in the human body is very low and a content of type XVII collagen in an animal is also extremely low, type XVII collagen is very difficult to extract and cannot be mass-produced. Moreover, animal-derived collagen products inevitably have immunogenicity and potential biological safety hazards such as viruses and epidemics, and thus are not widely used. Limited by legal and ethical constraints, human type XVII collagen can only be used in scientific research, and thus there are currently no commercial human-derived or animal-derived type XVII collagen products on the market, which further limits the research and application of human type XVII collagen. A main way for solving such problems now is to produce collagen through a biotechnology such as genetic engineering.

Existing recombinant proteins are mainly produced by the following four expression systems: prokaryotic (*Escherichia coli* (*E. coli*)) expression system, *Pichia pastoris* (*P. pastoris*) expression system, mammalian cell expression system, and insect cell (baculovirus) expression system. There are few studies on the expression of human type XVII collagen in mammalian cells, which are all in an experimental investigation stage. The prokaryotic expression system (such as *E. coli* and pGEX expression vector) was first used in the production of a fusion protein of a non-helical region NC16 sequence, and there is no report on the successful expression of human type XVII collagen by the remaining expression systems, especially the *P. pastoris* expression system.

The expression in mammalian cells involves a high expression cost and a low yield, and thus mammalian cells are mostly used for the expression and production of high-value pharmaceutical proteins. When human type XVII collagen is expressed in mammalian cells either by transient transfection or stable transfection, an expression level of the protein is extremely low, and a medium used is expensive such that only the need of trace consumption in scientific research can be met. The insect cell (baculovirus) expression system not only has a high cost and a low yield, but also shows a huge difference from human cells in post-translation. Therefore, these two methods are generally not used for the mass production of collagen. Collagen obtained by the prokaryotic expression system (*E. coli* expression system) has no post-translational modification. The prokaryotic expression with the prospect of large-scale amplification can only be achieved intracellularly, such that bacterial lysis is required and a large amount of impurity protein will be mixed with the target protein, which presents extremely high requirements on a purification process. Moreover, the prokaryotic expression system naturally carries the components of a bacterial cell wall such as endotoxin and peptidoglycan, which require complicated purification processes to remove.

Collagen products from the above expression systems have sequence singleness and low biological activity, for example, the sequence selection is relatively single, and collagen peptides are all expressed independently, but an extracellular domain of the human type XVII collagen includes nearly 1,000 amino acids (divided into 15 triple-helix regions and 15 non-triple-helix regions), which results in sequence abundance. Among the biological activities of collagen, the cell adhesion activity is merely the most basic one, and the remaining biological activities are not involved. Moreover, whether the mammalian cell expression or the *E. coli* expression is only used in the small-volume laboratory-level cultivation and production, and does not involve no large-scale production. However, the application of recombinant collagen is enabled on the premise of large-scale, high-density, and high-expression fermentation production and purification, and generally, after the verification of a 500 L pilot fermentation experiment, it is

possible to achieve industrial-scale and large-scale production.

There are some difficulties in the expression of human type XVII collagen. The human type XVII collagen is a transmembrane collagen, which has an intracellular region, a transmembrane region, and an extracellular region. Generally, when expressed in eukaryotic cells, transmembrane proteins are mostly not secreted extracellularly, but are fixed on a cell membrane. In addition, with a very long amino acid sequence (1,497 amino acids) and a large protein molecular weight (180 kDa), the human type XVII collagen is theoretically difficult to be effectively secreted extracellularly and easy to be degraded. Therefore, the selection of relevant sequences is required for successful expression. At present, little research on the amino acid sequence, structure, and function of the human type XVII collagen is known. Therefore, how to select an amino acid sequence that can achieve abundant biological functions on the premise of retaining the advantages of the *P. pastoris* expression system (especially the secretory expression) is a prominent difficulty, which is also a difficulty for the expression of human type XVII collagen in other expression systems (including *E. coli*).

Summary

The present disclosure is intended to overcome some technical problems in the prior art that how to achieve the optimal selection of a recombinant human type XVII collagen sequence (non-singleness) and the efficient secretory expression of the recombinant human type XVII collagen sequence in *P. pastoris*, the existing recombinant human type XVII collagen has only cell adhesion activity, and the existing recombinant human type XVII collagen cannot be produced on a large scale.

In view of this, the present disclosure provides a collagen, a polynucleotide encoding the collagen, a recombinant vector that carries the polynucleotide encoding the collagen, an engineered bacterium, a preparation method of the collagen, a composition including the collagen, and use of the collagen. In the present disclosure, it is confirmed that the collagen is a human type XVII collagen that can undergo efficient secretory and soluble expression in eukaryotic host cells such as *P. pastoris*, exhibits more excellent cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity than commercial native human collagen, and can be used industrially.

The present disclosure provides a collagen that has cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity.

The collagen consists of an amino acid sequence shown in (A)_n or includes the amino acid

sequence shown in $(A)_n$, where A is an amino acid sequence set forth in SEQ ID NO: 2, an amino acid sequence undergoing a modification such as amino acid replacement, insertion, substitution, addition, or deletion to a predetermined extent based on SEQ ID NO: 2, or an amino acid sequence that has more than 80% homology with SEQ ID NO: 2; n is an integer greater than or equal to 1; and A represents a basic unit, and when there are two or more basic units, the two or more basic units are identical or different and are directly connected in tandem through a peptide bond.

Further, according to an embodiment of the present disclosure, the collagen consists of an amino acid sequence shown in $(A)_n$ or includes the amino acid sequence shown in $(A)_n$, where A is an amino acid sequence set forth in SEQ ID NO: 2; n is an integer greater than or equal to 1; and A represents a basic unit, and when there are two or more basic units, the two or more basic units are identical and are directly connected in tandem through a peptide bond.

Further, according to an embodiment of the present disclosure, the collagen consists of an amino acid sequence shown in $(A)_n$, where when n is 1, the collagen has an amino acid sequence set forth in SEQ ID NO: 2, which is denoted as 170801 in the present disclosure; and when n is 2, the collagen has an amino acid sequence set forth in SEQ ID NO: 3, which is denoted as 170802 in the present disclosure.

Further, according to the present disclosure, the collagen of the present disclosure consists of an amino acid sequence shown in $(A)_n$ or includes the amino acid sequence shown in $(A)_n$, where A is an amino acid sequence undergoing a modification such as amino acid insertion, substitution, addition, or deletion to a predetermined extent based on SEQ ID NO: 2 or an amino acid sequence that has more than 80% homology with SEQ ID NO: 2; n is an integer greater than or equal to 1; and A represents a basic unit, and when there are two or more basic units, the two or more basic units are identical or different and are directly connected in tandem through a peptide bond.

The present disclosure also provides a polynucleotide encoding the collagen, specifically a polynucleotide sequence encoding the collagen represented by $(A)_n$. Preferably, when *P. pastoris* is used as a host cell, the polynucleotide includes a nucleotide sequence selected from the group consisting of SEQ ID NO: 6 and SEQ ID NO: 7 or consists of a nucleotide sequence selected from the group consisting of SEQ ID NO: 6 and SEQ ID NO: 7.

According to an embodiment of the present disclosure, the A is SEQ ID NO: 2, and when n is 1, the polynucleotide is a nucleotide sequence set forth in SEQ ID NO: 6. According to an embodiment of the present disclosure, the A is SEQ ID NO: 2, and when n is 2, the polynucleotide encoding the $(A)_n$ is a nucleotide sequence set forth in SEQ ID NO: 7.

The collagen of the present disclosure has a combined sequence obtained after optimization

and screening of multiple helix region sequences of human type XVII collagen such as the 15th helix region, the carboxyl terminus region, and the middle region, which is 100% identical to a corresponding part of an amino acid sequence of human type XVII collagen. The recombinant collagen of the present disclosure can undergo efficient secretory and soluble expression in eukaryotic host cells such as *P. pastoris*, and exhibits more excellent cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity than commercial native human collagen. Such a combined sequence enables the integration of functions of the respective region sequences, such that the respective region sequences are not expressed separately but expressed as a whole, which avoids the sequence singleness of the recombinant collagen.

The present disclosure also provides a recombinant expression vector that carries the polynucleotide encoding the collagen.

According to an embodiment of the present disclosure, during a construction process of the recombinant expression vector of the present disclosure, the polynucleotide encoding the collagen represented by (A)_n is modified first, by adding a DNA sequence encoding a Strep-Tag II to an amino terminus of the amino acid sequence of the collagen, and adding a DNA sequence encoding a 6×His Tag to a carboxyl terminus of the amino acid sequence of the collagen, such that the collagen contains bispecific affinity purification tags, which enables the purification by affinity chromatography and the immunological antibody detection based on the two tag sequences, and then the labeled sequence is ligated into an expression vector pPIC9K to construct the recombinant expression vector (represented by pPIC9K-170801 and pPIC9K-170802 in the examples).

The present disclosure also provides an engineered bacterium constructed from the recombinant expression vector, and a host cell for the engineered bacterium is preferably *P. pastoris*. The engineered bacterium was deposited in the China General Microbiological Culture Collection Center (CGMCC) located at No. 1, West Beichen Road, Chaoyang District, Beijing, China on September 9, 2020, with an accession number of CGMCC NO. 20626 or CGMCC NO. 20627 and a taxonomic name of *Pichia pastoris*.

It should be noted that the host cell can be a eukaryotic cell, such as a fungal cell, a yeast cell, and a plant cell; a prokaryotic cell, such as *Enterobacteriaceae*, such as *E. coli*; or an animal cell, such as a mammalian cell such as a CHO cell line and an HEK293 cell line or an insect cell. It should be understood that those skilled in the art can use another expression host as an expression host instead of the above *P. pastoris* to express a collagen with the same amino acid sequence.

The present disclosure also provides a preparation method of the collagen, including the

following steps:

(1) cultivation and screening of engineered bacteria

constructing and screening engineered bacteria, and conducting inducible expression with a Buffered Glycerol-complex Medium (BMGY medium) to obtain an engineered bacterium with high expression, where the engineered bacterium with high expression screened out is *P. pastoris* with an accession number of CGMCC No. 20626 or CGMCC No. 20627; and

(2) large-scale high-density fermentation, cultivation, and protein purification

conducting linked fed-batch fermentation in a 50 L to 500 L fermentation tank to obtain a fermentation supernatant, and purifying the fermentation supernatant to obtain a high-purity collagen.

According to an embodiment of the present disclosure, the recombinant expression vector is linearized with Sac I and then electrotransformed into *P. pastoris* competent cells to construct engineered bacteria. The engineered bacteria are transferred to an MD plate for primary screening and then screened on YPD plates with different G418 concentrations, and then colonies are picked and inoculated into a BMGY medium and then subjected to inducible expression in a Buffered Methanol-complex Medium (BMMY medium), and multiple strains are picked, and the engineered bacterium with high expression is selected for subsequent experiments. In the present disclosure, the expressed protein is preliminarily identified by sodium dodecyl sulfate-polyacrylamide gel electrophoresis (SDS-PAGE) and Western Blot to determine the efficient secretory expression ability, and the results show that the recombinant human type XVII collagen of the present disclosure can undergo efficient secretory expression, while the full-length human type XVII collagen is mainly concentrated in cells and cannot be effectively secreted extracellularly, and a target band obtained by electrophoresis is subjected to nanoscale high-performance liquid chromatography coupled to tandem mass spectrometry (Nano-HPLC-MS/MS), and the results show that a peptide in the target band is derived from the optimally selected region in the human type XVII collagen sequence, and the recombinant human type XVII collagens 170801 and 170802 of the present disclosure are successfully expressed.

When a 50 L to 500 L fermentation tank is used to conduct inducible expression for 48 h, yields of the collagens (quantification by UV spectrometry) of the present disclosure can reach 12 g/L and 11 g/L, respectively.

In the present disclosure, a molecular weight is determined by matrix-assisted laser desorption ionization time-of-flight mass spectrometry (MALDI-TOF MS), and the determination results show that a molecular weight of collagen 170801 is 23811.6797 Da (theoretical value: 23800 Da), and a molecular weight of collagen 170802 is 45689.5781 Da

(theoretical value: 45400 Da), and while there are post-translational modification and systematic errors in molecular weight determination after expression in *P. pastoris*, the actually expressed collagen has a molecular weight consistent with the theoretical value. The collagen is subjected to infrared (IR) spectroscopy, and it can be seen that wave numbers of amide A, amide B, amide I, amide II, and amide III of the collagen are all in line with the structural characteristics of the recombinant collagen. A purified lyophilized collagen sponge is subjected to scanning electron microscopy, and it can be seen that the collagen sponge has a lamellar structure and has the potential to be used in the field of biomedical materials.

According to an embodiment of the present disclosure, the biological activity of the obtained collagen is detected by *in vitro* cell experiments, and it is verified that the collagen has cell adhesion activity and cell migration-promoting activity. Animal experiments are conducted for the biological activity of the obtained collagen, and a rabbit ear scar model experiment shows that the collagen can effectively promote rabbit ear scar healing and tissue regeneration, and particularly exhibits extremely excellent activity to promote hair follicle repair and regeneration.

In view of this, the present disclosure also provides use of the collagen described above in the promotion of tissue regeneration or hair follicle repair.

The present disclosure also provides a composition including the collagen described above or a collagen prepared by the preparation method described above.

The present disclosure also provides an article including the collagen described above or a collagen prepared by the preparation method described above or the composition described above. The article includes, but is not limited to, a drug, a pharmaceutical composition, a medical device, a biological material, a tissue-engineered product, a cosmetic, and a health product.

The present disclosure also provides use of the collagen, the polynucleotide, the recombinant expression vector, the engineered bacterium, or the composition in the manufacture of a product, including but not limited to, a drug, a pharmaceutical composition, a medical device, a biological material, a tissue-engineered product, a cosmetic, and a health product.

The present disclosure also provides use of the collagen, the polynucleotide, the recombinant expression vector, the engineered bacterium, or the composition in the manufacture of a product for promoting scar healing, tissue repair, or hair follicle repair. According to an embodiment of the present disclosure, the product is an external preparation, preferably an external preparation for a topical application, and more preferably a gel.

The present disclosure has the following beneficial effects.

(1) The present disclosure adopts the *P. pastoris* expression system. *P. pastoris* is a eukaryotic microorganism with all organelles of a eukaryote, which can perform a

post-translational modification (especially a glycosylation modification) on a translated protein to effectively support the realization of biological functions of the protein. The expression system established using *P. pastoris* has large-scale industrial production advantages of the microorganism expression system such as high-density fermentation production, extremely-low cultivation cost, short cycle, and high expression, the expressed protein can be secreted extracellularly in the expression system, which can completely avoid impurity proteins caused by bacterial lysis, and the cell wall of *P. pastoris* does not contain endotoxin and peptidoglycan.

(2) An amino acid sequence of the recombinant human type XVII collagen in the present disclosure is a combination of sequences screened and optimized, and has 100% homology with the corresponding part of the amino acid sequence of the native collagen. Therefore, the recombinant human type XVII collagen has no immunogenicity, and can be widely used in the fields of medicine, medical devices, biological materials, tissue engineering, cosmetics, and the like.

(3) It is experimentally verified that the recombinant human type XVII collagen in the present disclosure has the same or better cell adhesion activity, cell migration-promoting activity, tissue repair-promoting activity, and hair follicle repair and regeneration-promoting activity compared to the commercial native human collagen, and can achieve the purpose of real product application.

(4) The recombinant human type XVII collagen in the present disclosure can undergo efficient secretory expression in the *P. pastoris* expression system, and is easily purified to obtain the high-purity collagen. The DNA sequence of the gene encoding the amino acid sequence is optimized, such that the constructed engineered strain can express the protein at a very high level, and a high yield of the protein can be obtained after high-density fermentation and expression. *P. pastoris* can be easily used for high-density fermentation and expression, and the strain screened out in the present disclosure can achieve the high-density and high-expression fermentation at a 500 L pilot scale, which provides the conditions for industrialized mass production.

(5) The host cell *P. pastoris* in the present disclosure can perform a post-translational modification on the expressed exogenous protein, such as glycosylation.

Brief Description of the Drawings

FIG. 1 is a map of the pPIC9K-170801 vector constructed in the present disclosure.

FIG. 2 is a map of the pPIC9K-170802 vector constructed in the present disclosure.

FIG. 3 is a map of the pPIC9K-col17a1 vector constructed in the present disclosure.

FIG. 4 shows an SDS-PAGE result of the expression of a $\alpha 1$ chain of the recombinant full-length human type XVII collagen, with an apparent molecular weight (AMW) of about 180

kDa.

FIG. 5 shows a Western Blot result of the $\alpha 1$ chain of the recombinant full-length human type XVII collagen, where the Western Blot is conducted with an anti-His tag antibody.

FIG. 6 shows SDS-PAGE results of expression supernatants of engineered bacteria expressing collagens 170801 and 170802 after 24 h of induction.

FIG. 7 shows Western Blot results of expression supernatants of engineered bacteria expressing collagens 170801 and 170802 after 24 h of induction, where the Western Blot is conducted with an anti-His tag antibody.

FIG. 8 shows Western Blot results of expression supernatants of engineered bacteria expressing collagens 170801 and 170802 after 24 h of induction, where the Western Blot is conducted with an anti-Strep-Tag II antibody.

FIG. 9 shows a mass spectrometry (MS) analysis result of an SDS-PAGE band of the collagen 170801 and a sequence alignment result thereof with the native human type XVII collagen.

FIG. 10 shows an MS analysis result of an SDS-PAGE band of the collagen 170802 and a sequence alignment result thereof with the native human type XVII collagen.

FIG. 11 shows a bacterial growth curve and a collagen expression curve of the 171801 collagen-expressing engineered bacterium in a 500 L pilot fermentation tank.

FIG. 12 shows a bacterial growth curve and a collagen expression curve of the 171802 collagen-expressing engineered bacterium in a 500 L pilot fermentation tank.

FIG. 13 shows a high-performance liquid chromatography (HPLC) spectrum of the purified collagen 170801.

FIG. 14 shows an HPLC spectrum of the purified collagen 170802.

FIG. 15 shows an MALDI-TOF MS result of a molecular weight of the collagen 170801.

FIG. 16 shows an MALDI-TOF MS result of a molecular weight of the collagen 170802.

FIG. 17 shows IR spectra of the purified collagens 170801 and 170802.

FIG. 18 shows scanning electron microscopy (SEM) images (200 $\times$) of lyophilized collagen sponge samples: 170801 (left) and 170802 (right).

FIG. 19 shows detection results of cell adhesion activity of collagens 170801 and 170802.

FIG. 20 shows the comparison of actual cell migration in the collagens 170801 and 170802 with the native human collagen.

FIG. 21 shows cell migration rates in the collagens 170801 and 170802 as well as the native human collagen after 24 h and 48 h of cell migration.

FIG. 22 shows gross images of rabbit ear scars intervened with the collagens 170801 and 170802 for 6 weeks and images of scar sections.

Detailed Description of the Embodiments

In order to make those skilled in the art better understand the technical solutions of the present disclosure, the preferred examples of the present disclosure are described in detail below, but the following examples do not limit the protection scope of the present disclosure.

In the examples of the present disclosure, those not described in detail are all implemented by a conventional molecular biology experimental method; and processes such as polymerase chain reaction (PCR), enzyme digestion, ligation, and codon optimization involved in the examples can all be understood and easily implemented by those skilled in the art according to product instructions or basic knowledge in the art, and thus will not be described in detail.

Example 1: Construction, expression, and identification of a recombinant human type XVII collagen

(1) Design of an amino acid sequence of the recombinant human type XVII collagen

In the present disclosure, a sequence of the human type XVII collagen is optimized, and a specific sequence of the human type XVII collagen is as follows: a Uniprot Q9UMD9-1 sequence (<https://www.uniprot.org/uniprot/Q9UMD9>) and an NCBI reference sequence Q9UMD9. 3 (<https://www.ncbi.nlm.nih.gov/protein/Q9UMD9.3>), which are the same, as set forth in SEQ ID NO: 1.

SEQ ID NO: 1:

MDVTKKNKRDGTEVTERIVTETVTTRLTSLPPKGGTSNGYAKTASLGGGSRLKQSL
THGSSGYINSTGSTRGHASTSSYRRAHSPASTLPNSPGSTFERKTHVTRHAYEGSSSGNSS
PEYPRKEFASSSTRGRSQTRESEIRVRLQSASPSTRWTELDDVKRLLKGSRSASVSPTRNS
SNTLPIPKKGTIVETKIVTASSQSVSGTYDATILDANLPSHVWSSTLPAGSSMGTYHNNMT
TQSSSLLNTNAYSAGSVFGVPPNMA SCSP TLHPGLSTSSSVFGMQNNLAPSLTTL SHGTT
TTSTAYGVKKNMPQSPA AVNTGVSTSA ACTTSVQSDDLHKDCKFLILEKDNTPAKKEM
ELLIMTKDSGKVFTASPA SIAATSFSEDTLKKEKQAAYNADSGLKAEANGDLKTVSTKG
KTTTADIHSYGSSGGGGSGGGGGVGGAGGGPWGPAPAWCPCGSCCSWWKWLLGLLLT
WLLLLGLLFG LIALAE EVRKLKARVDELERIRRSILPYGDSMDRIEKDRLQGMAPAAGA
DLDKIGLHSDSQEELWMFVRKKLMMEQENGLR GSPGPKGDMGSPGPKGDRGFPGT
PGIPGPLGHPGPOGPKGOKGSVGDPMEGPMGQREGPMGPRGEAGPPGS GEKG
ERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPOGPPGPVGLQGLRGEVGLPGVKGD
KGPMGPPGPKGDQGEK GPRGLTGEPGMRGLPGAVGEPGAKGAMGPAGPDGHQGPGRG
EQGLTGMPGIRGPPGPSGDPGPKPGLTGPQGPQGLPGTPGRPGIKGEPGAPGKIIVTSEGSS
MLTVPGPPGPPGAMGPPGPPGAPGAPAGLPGHQEVLNLQGPPGPPGPRGPPGPSIPGPP
GPRGPPGEGLPGPPGPPGSFLSNSETFLS GPPGPPGPPGPKGDQGPGRGHQGEQGL

PGFSTSGSSSFGLNLQGPPGPPGPOGPKGDKGDPGVPGALGIPSGPSEGGSSSTMYVS
GPPGPPGPPGPPGSISSSGQEIQYISEYMQSDSIRSYLSGVQGPPGPPGPPGPVTTITGETF
DYSELASHVVSYLRTSGYGVSLFSSSISSEDILAVLQRDDVRQYLRQYLMGPRGPPGPPG
ASGDGSLLSLDYAELSSRILSYMSSSGISIGLPGPPGPPGLPGTSEELLSSLRGSEFRGIVG
PPGPPGPPGIPGNVWSSISVEDLSSYLHTAGLSFIPGPPGPPGPPGPRGPPGVSGALATYAA
ENSDSFRSELISYLTSPDVRSFIVGPPGPPGPQGPPGDSRLLSTDASHSRGSSSSSHSSSVRR
GSSYSSSMSTGGGGAGSLGAGGAFGEAAGDRGPYGTDIGPGGGYGAAAEGGMYAGNG
GLLGADFAGDL DYNELAVRVSESMQRQGLLQGMAYTVQGPPGQPGPQGPPGISKVFSAY
SNVTADLMDFQTYGAIQGPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPRGHKG
EKGDKGDQVYAGR RRRRSIAVKP

The bold and underlined parts in the above sequence SEQ ID NO: 1 are sequences selected by the present disclosure, with 233 amino acids in total. The sequences selected by the present disclosure are obtained through optimization and screening of multiple helix region sequences of human type XVII collagen such as the 15th helix region, the carboxyl terminus region, and the middle region, and are combined to obtain a combined sequence. The combined sequence can undergo efficient secretory and soluble expression in eukaryotic host cells such as *P. pastoris*, and exhibits more excellent cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity than commercial native human collagen. Such a combined sequence enables the integration of functions of the respective region sequences, such that the respective region sequences are not expressed separately but expressed as a whole, which avoids the sequence singleness of the recombinant collagen and is highly innovative. In the present disclosure, the combined sequence is named 170801 and is specifically set forth in SEQ ID NO: 2, which is a preferred sequence of human type XVII collagen.

SEQ ID NO: 2:

GSPGPKGDMGSPGPKGDRGFPGTPGIPGPLGHPGPQGPKGQKGSVGDPMEGPGEK
GERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPQGPPGPVGLQGLRGEVGLPGVKGDKG
PMGPPGPKGDQGEKGPPGPPGPPGPKGDQPPGPRGHQGEQGLPGFSGPPGPPGPQGPK
GDKGDPGVPGALGIPGPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPRGHKGGEKGDKG
DQ

A DNA sequence encoding 170801 is set forth in SEQ ID NO: 6.

SEQ ID NO: 6:

GGTTCTCCTGGTCCAAAAGGTGACATGGGTTCTCCAGGTCCTAAAGGTGACAGA
GGTTTTCTCCTGGTACTCCAGGTATTCCTGGTCCATTGGGTCATCCAGGTCCTCAAGGTC
CAAAAGGTCAAAAGGGTTCTGTTGGTGACCCTGGTATGGAAGGTCCAGGTGAAAAG

GGTGAAAGAGGTGCTGCTGGTGAACCTGGTCCACACGGTCCACCTGGTGTTCAGGT
TCTGTTGGTCCTAAGGGTTCTTCTGGTTCTCCTGGTCCACAAGGTCCTCCTGGTCCAG
TTGGTTTGAAGGTTTGAGAGGTGAAGTTGGTTTGCCAGGTGTAAAGGGTGACAAGG
GTCCAATGGGTCCTCCAGGTCCAAAAGGTGACCAAGGTGAAAAGGGTCCACCTGGT
CCTCCTGGTCCACCTGGTCCAAAGGGTGACCAAGGTCCTCCAGGTCCTAGAGGTCAT
CAAGGTGAACAAGGTTTGCCTGGTTTTCTGGTCCACCAGGTCCTCCAGGTCCACAA
GGTCCTAAAGGTGACAAAGGTGACCCAGGTGTTCTGGTGCTTTGGGTATTCCAGGT
CCACCTGGTCAAAAAGGTGAAATGGGTACTCCAGGTCCTAAGGGTGACAGAGGTCC
AGCTGGTCCACCTGGTCATCCTGGTCCACCAGGTCCAAGAGGTCATAAGGGTGAAAA
AGGTGACAAGGGTGACCAA

The collagen in the present disclosure has an amino acid sequence composed of n basic units connected in tandem, where 170801 is used as a basic unit, and n is an integer greater than or equal to 1.

When 170801 is used as a basic unit, if n is 2, the collagen has an amino acid sequence composed of 2 basic units 170801 connected in tandem, and the collagen has 466 amino acids in total, and is named 170802, and the amino acid sequence of the collagen is specifically set forth in SEQ ID NO: 3.

SEQ ID NO: 3:

GSPGPKGDMGSPGPKGDRGFPGTGIPGPLGHPGPQGPKGQKGSVGDPMEGPGEK
GERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPQGPPGPVGLQGLRGEVGLPGVKGDKG
PMGPPGPKGDQGEKGPPGPPGPPGPKGDQPPGPRGHQGEQGLPGFSGPPGPPGPQGPK
GDKGDPGVPGALGIPGPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPRGHKGEKGDKG
DQGSPGPKGDMGSPGPKGDRGFPGTGIPGPLGHPGPQGPKGQKGSVGDPMEGPGEK
GERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPQGPPGPVGLQGLRGEVGLPGVKGDKG
PMGPPGPKGDQGEKGPPGPPGPPGPKGDQPPGPRGHQGEQGLPGFSGPPGPPGPQGPK
GDKGDPGVPGALGIPGPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPRGHKGEKGDKG
DQ

A DNA sequence encoding 170802 is set forth in SEQ ID NO: 7.

SEQ ID NO: 7:

GGTTCTCCAGGTCCTAAAGGTGACATGGGTTCTCCAGGTCCTAAGGGTGACAGA
GGTTTTCCAGGTACTCCAGGTATTCCAGGTCCTTTGGGTCATCCAGGTCCTCAAGGTC
CTAAAGGTCAAAAAGGTTCTGTTGGTGACCCTGGTATGGAAGGTCCTGGTGAAAAAG
GTGAAAGAGGTGCTGCTGGTGAACCTGGTCCACACGGTCCTCCAGGTGTTCTGGTT
CTGTTGGTCCAAAAGGTTCTTCTGGTTCTCCTGGTCCACAAGGTCCTCCAGGTCCTGT
TGGTTTGAAGGTTTGAGAGGTGAAGTTGGTTTGCCAGGTGTAAAGGTGACAAAGG

TCCAATGGGTCCTCCAGGTCCAAAGGGTGACCAAGGTGAAAAAGGTCCACCTGGTC
CTCCTGGTCCACCAGGTCCAAAAGGTGACCAAGGTCCACCTGGTCCAAGAGGTAC
CAAGGTGAACAAGGTTTGCCTGGTTTTCTGGTCCTCCAGGTCTCCTGGTCCTCAA
GGTCCAAAGGGTGACAAGGGTGACCCTGGTGTTCCAGGTGCTTTGGGTATTCCTGGT
CCTCCAGGTCAAAAGGGTGAGATGGGTACTCCTGGTCCTAAGGGTGACAGAGGTCCA
GCTGGTCCTCCTGGTCACCCAGGTCTCCTGGTCCTAGAGGTGCATAAAGGTGAAAA
GGTGACAAGGGTGACCAAGGTTCTCCAGGTCCAAAGGGTGACATGGGTTCTCCTGGT
CCAAAAGGTGACAGAGGTTTCCCTGGTACTCCAGGTATTCCTGGTCCATTGGGTACCC
CAGGTCCACAAGGTCCAAAAGGTCAAAAAGGTTCTGTTGGTGACCCAGGTATGGAA
GGTCCAGGTGAAAAGGGTGAAAGAGGTGCTGCTGGTGAACCAGGTCTCATGGTCC
ACCAGGTGTTCCAGGTCTGTTGGTCCAAAGGGTTCTTCTGGTTCTCCAGGTCCACA
AGGTCTCCTCAGGTCCAGTTGGTTTGCAAGGTTTGAGAGGTGAAGTTGGTTTGCCTGG
TGTTAAGGGTGACAAAGGTCCTATGGGTCCTCCTGGTCCTAAAGGTGACCAAGGTGA
AAAGGGTCCACCAGGTCTCCTCAGGTCCACCTGGTCCAAAAGGTGACCAAGGTCCAC
CAGGTCTCCTAGAGGTGCATCAAGGTGAACAAGGTTTGCCAGGTTTTCTGGTCCACCAG
GTCCACCAGGTCTCAAGGTCCTAAGGGTGACAAAGGTGACCCAGGTGTTCTCCTGGTG
CTTTGGGTATTCCTGGTCCACCTGGTCAAAAGGGTGAAATGGGTACTCCTGGTCCTAA
AGGTGACAGAGGTCTGCTGGTCCACCTGGTCATCCAGGTCCACCTGGTCCAAGAGG
TCACAAAGGTGAAAAGGGTGACAAGGGTGACCAA

A function of the protein can only be realized through the orderly arrangement of amino acid residues of the protein. All innovative biological activities of the recombinant human type XVII collagen in the present disclosure are based on the amino acid sequence selected through optimization and screening, and a limited sequence modification or a specified percentage of homology (greater than 80%) may still achieve the same or similar biological activities.

Therefore, in the present disclosure, the collagen also includes an amino acid sequence undergoing a modification such as amino acid insertion, substitution, addition, or deletion to a predetermined extent based on SEQ ID NO: 2, or an amino acid sequence that has more than 80% homology with the amino acid sequence set forth in SEQ ID NO: 2, where either of the above amino acid sequences is used as a basic unit, and n basic units are connected in tandem to obtain the amino acid sequence of the collagen, where n is an integer greater than or equal to 1, and the basic units are identical or different if there are two or more basic units.

The homology mentioned in the present disclosure refers to an identity of sequences, which can be a direct quantitative relationship between two sequences, such as a percentage of identical and similar units, or a percentage of identical positions for which the nucleotide or amino acid residue is identical between two sequences. Homologous sequences may be different sequences

obtained through divergent evolution from a common ancestor. The homology can be obtained through sequence information alignment by a conventional bioinformatics method.

The amino acid insertion refers to the insertion of amino acid residues at appropriate positions in an amino acid sequence such as a sequence set forth in SEQ ID NO: 2 or SEQ ID NO: 3, where the inserted amino acid residues are adjacent to each other or some of the inserted amino acid residues are adjacent to each other, or none of the inserted amino acid residues are adjacent to each other. The resulting protein has similar biological activities to collagens 170801 and 170802, including cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity.

The amino acid substitution refers to the substitution of one or more amino acid residues (including consecutive amino acid residues or non-consecutive amino acid residues) at a specified position in an amino acid sequence such as a sequence set forth in SEQ ID NO: 2 or SEQ ID NO: 3 with other amino acid residues. The resulting protein has similar biological activities to collagens 170801 and 170802, including cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity.

The amino acid addition refers to the addition of an amino acid to a C-terminus or N-terminus of an amino acid sequence such as a sequence set forth in SEQ ID NO: 2 or SEQ ID NO: 3. The resulting protein has similar biological activities to collagens 170801 and 170802, including cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity.

The amino acid deletion refers to the deletion of 1, 2, 3, or more amino acids from an amino acid sequence such as a sequence set forth in SEQ ID NO: 2 or SEQ ID NO: 3. The resulting protein has similar biological activities to collagens 170801 and 170802, including cell adhesion activity, cell migration-promoting activity, tissue regeneration-promoting activity, and hair follicle repair and regeneration-promoting activity.

The amino acids mentioned in the present disclosure may preferably be L-amino acids. One or more (such as 2 to 5, 2 to 4, or 2 to 3) amino acids in the polypeptide can also be replaced with D-amino acids, artificially-modified amino acids, naturally-occurring rare amino acids, and the like to improve the bioavailability, stability, and/or antiviral activity of the polypeptide. The D-amino acids refer to amino acids corresponding to L-amino acids that constitute proteins; the artificially-modified amino acids refer to common L-amino acids modified by methylation, phosphorylation, or the like that constitute proteins; and the naturally-occurring rare amino acids include uncommon amino acids that constitute proteins and amino acids that do not constitute proteins, such as 5-hydroxylysine, methylhistidine, gamma-aminobutyric acid (GABA), and

homoserine.

(2) Optimization of amino acid sequences and DNA sequences for the recombinant human type XVII collagen

In the present disclosure, DNA sequences for 170801 and 170802 are modified as follows: a DNA sequence encoding a Strep-Tag II added to an amino terminus of each amino acid sequence and a DNA sequence encoding a 6×His Tag added to a carboxyl terminus are added, such that obtained collagens have bispecific affinity purification tags, which enables the purification by affinity chromatography and the immunological antibody detection based on the two tag sequences. Specifically, based on the amino acid sequences of 170801 and 170802 and gene sequences encoding the same, calculation, splicing, recombination, and optimization are conducted in the codon bias of DNA sequences and the relevant optimization parameters during transcription and translation to synthesize DNA sequences that can be highly expressed in *P. pastoris*.

In the present disclosure, two termini of 170801 are separately modified by adding a DNA sequence encoding a Strep-Tag II to the amino terminus, and adding a DNA sequence encoding a 6×His Tag to the carboxyl terminus, and a protein with the tags is finally expressed, which has 249 amino acids in total. The optimized amino acid sequence of 170801 is set forth in SEQ ID NO: 4. Two termini of 170801 are separately modified by adding a DNA sequence encoding a Strep-Tag II to the amino terminus, and adding a DNA sequence encoding a 6×His Tag, a stop codon (TAA) and a Not I restriction site to the carboxyl terminus. The resulting DNA sequence is set forth in SEQ ID NO: 8.

SEQ ID NO: 4:

YVWSHPQFEKGSPGPKGDMGSPGPKGDRGFPGTPGIPGPLGHPGPQGPKGQKGSVG
DPGMEGPGEKGERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPQGPVGLQGLRGEV
GLPGVKGDKGPMGPPGPKGDQGEKGPPGPPGPPGPKGDQGPGRGHQGEQGLPGFSG
PPGPPGPQGPKGDKGDPGVPGALGIPPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPR
GHKGEKGDQHHHHH

SEQ ID NO: 8:

TACGTATGGTCTCATCCACAATTCGAGAAGGGTTCTCCTGGTCCAAAAGGTGACA
TGGGTTCTCCAGGTCCTAAAGGTGACAGAGGTTTTCCTGGTACTCCAGGTATTCCTGG
TCCATTGGGTCATCCAGGTCCTCAAGGTCCAAAAGGTCAAAAGGGTTCTGTTGGTGA
CCCTGGTATGGAAGGTCCAGGTGAAAAGGGTGAAAGAGGTGCTGCTGGTGAACCTG
GTCCACACGGTCCACCTGGTGTTCAGGTTCTGTTGGTCCTAAGGGTTCTTCTGGTTC
TCCTGGTCCACAAGGTCCTCCTGGTCCAGTTGGTTTGCAAGGTTTGAGAGGTGAAGT
TGGTTTGCCAGGTGTTAAGGGTGACAAGGGTCCAATGGGTCCTCCAGGTCCAAAAGG

TGACCAAGGTGAAAAGGGTCCACCTGGTCCTCCTGGTCCACCTGGTCCAAAGGGTG
ACCAAGGTCCTCCAGGTCCTAGAGGTCATCAAGGTGAACAAGGTTTGCCTGGTTTTT
CTGGTCCACCAGGTCCTCCAGGTCACAAGGTCCTAAAGGTGACAAAGGTGACCCA
GGTGTTCCTGGTGCTTTGGGTATTCCAGGTCACCTGGTCAAAAAGGTGAAATGGGT
ACTCCAGGTCCTAAGGGTGACAGAGGTCAGCTGGTCCACCTGGTCATCCTGGTCCA
CCAGGTCCAAGAGGTCATAAGGGTGAAAAAGGTGACAAGGGTGACCAACACCATCA
TCACCATCATTAAGCGGCCGC

Similarly, two termini of 170802 are separately modified by adding a DNA sequence encoding a Strep-Tag II to the amino terminus, and adding a DNA sequence encoding a 6×His Tag to the carboxyl terminus, and a protein with the tags is finally expressed, which has 482 amino acids in total. The optimized amino acid sequence of 170802 is set forth in SEQ ID NO: 5. Two termini of 170802 are separately modified by adding a DNA sequence encoding a Strep-Tag II to the amino terminus, and adding a DNA sequence encoding a 6×His Tag, a stop codon (TAA) and a Not I restriction site to the carboxyl terminus. The resulting DNA sequence is set forth in SEQ ID NO: 9.

SEQ ID NO: 5:

YVWSHPQFEKGSPGPKGDMGSPGPKGDRGFPGTPGIPGPLGHPGPQGPKGQKGSVG
DPGMEGPGEKGERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPQGPVGLQGLRGEV
GLPGVKGDKGPMGPPGPKGDQGEKGPPGPPGPPGPKGDQGPGRGHQGEQGLPGFSG
PPGPPGPQGPKGDKGDPGVPGALGIPGPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPR
GHKGEKGDKGDQGSPPGPKGDMGSPGPKGDRGFPGTPGIPGPLGHPGPQGPKGQKGSVG
DPGMEGPGEKGERGAAGEPGPHGPPGVPGSVGPKGSSGSPGPQGPVGLQGLRGEV
GLPGVKGDKGPMGPPGPKGDQGEKGPPGPPGPPGPKGDQGPGRGHQGEQGLPGFSG
PPGPPGPQGPKGDKGDPGVPGALGIPGPPGQKGEMGTPGPKGDRGPAGPPGHPGPPGPR
GHKGEKGDKGDQH HHHHHH

SEQ ID NO: 9:

TACGTATGGTCTCATCCTCAATTTGAAAAGGGTTCTCCAGGTCCTAAAGGTGACAT
GGGTTCTCCAGGTCCTAAGGGTGACAGAGGTTTTCCAGGTACTCCAGGTATTCCAGG
TCCTTTGGGTCATCCAGGTCCTCAAGGTCCTAAAGGTCAAAAAGGTTCTGTTGGTGA
CCCTGGTATGGAAGGTCCTGGTGAAAAAGGTGAAAGAGGTGCTGCTGGTGAACCTG
GTCCACACGGTCCTCCAGGTGTTCTGTTGGTCCAAAAGGTTCTTCTGGTTC
TCCTGGTCCACAAGGTCCTCCAGGTCCTGTTGGTTTGCAAGGTTTGAGAGGTGAAGT
TGGTTTGCCAGGTGTTAAAGGTGACAAAGGTCCAATGGGTCCTCCAGGTCCAAAGGG
TGACCAAGGTGAAAAGGTCCACCTGGTCCTCCTGGTCCACCAGGTCCAAAAGGTG
ACCAAGGTCCACCTGGTCCAAGAGGTACCAAGGTGAACAAGGTTTGCCTGGTTTTT

CTGGTCCTCCAGGTCCTCCTGGTCCTCAAGGTCCAAAGGGTGACAAGGGTGACCCTG
GTGTTCCAGGTGCTTTGGGTATTCTGGTCCTCCAGGTCAAAGGGTGAGATGGGTA
CTCCTGGTCCTAAGGGTGACAGAGGTCCAGCTGGTCCTCCTGGTCACCCAGGTCCTC
CTGGTCCTAGAGGTCATAAAGGTGAAAAAGGTGACAAGGGTGACCAAGGTTCTCCA
GGTCCAAAGGGTGACATGGGTCTCCTGGTCCAAAGGTGACAGAGGTTTCCCTGGT
ACTCCAGGTATTCTGGTCCATTGGGTACCCAGGTCCACAAGGTCCAAAAGGTCAA
AAAGGTTCTGTTGGTGACCCAGGTATGGAAGGTCCAGGTGAAAAGGGTGAAAGAGG
TGCTGCTGGTGAACCAGGTCCTCATGGTCCACCAGGTGTTCCAGGTTCTGTTGGTCC
AAAGGGTTCTTCTGGTTCTCCAGGTCCACAAGGTCCTCCAGGTCCAGTTGGTTTGCA
AGGTTTGAGAGGTGAAGTTGGTTTGCCTGGTGTTAAGGGTGACAAAGGTCCTATGGG
TCCTCCTGGTCCTAAAGGTGACCAAGGTGAAAAGGGTCCACCAGGTCCTCCAGGTCC
ACCTGGTCCAAAAGGTGACCAAGGTCCACCAGGTCCTAGAGGTCATCAAGGTGAAC
AAGGTTTGCCAGGTTTTTCTGGTCCACCAGGTCCACCAGGTCCTCAAGGTCCTAAGG
GTGACAAAGGTGACCCAGGTGTTCTGGTGCTTTGGGTATTCTGGTCCACCTGGTC
AAAAGGGTGAAATGGGTACTCCTGGTCCTAAAGGTGACAGAGGTCCTGCTGGTCCAC
CTGGTCATCCAGGTCCACCTGGTCCAAGAGGTCACAAAGGTGAAAAGGGTGACAAG
GGTGACCAACACCATCACCATCATCATTAAGCGGCCGC

In the present disclosure, a DNA sequence encoding the amino acid sequence of the full-length human type XVII collagen (that is, $\alpha 1$ chain of human type XVII collagen) (a restriction site EcoR I and a DNA sequence encoding a Strep-Tag II are added to the amino terminus, and a DNA sequence encoding a 6 $\times$ His Tag, a stop codon (TAA), and a restriction site Not I are added to the carboxyl terminus) is set forth in SEQ ID NO: 10.

SEQ ID NO: 10:

GAATTCTGGAGTCATCCTCAATTCGAAAAAATGGATGTCACTAAAAAGAACAAG
AGAGACGGAAGTGAAGTCACTGAGAGAATCGTTACCGAAACTGTCACCACAAGACT
TACTTCATTACCTCCAAAGGGTGGAAGTTCTAATGGTTACGCAAAGACAGCATCATTA
GGAGGTGGTTCAAGACTTGAGAAACAATCCCTTACTCATGGTTCAAGTGGATACATA
AATTCAACTGGTTCAACAAGAGGACATGCAAGTACTTCTTCTTATAGAAGAGCACATA
GTCCAGCATCAACTTTGCCCAACTCTCCTGGTTCAACATTTGAGAGAAAAACTCATGT
AACCAGACATGCCTATGAGGGTTCTAGTTCTGGTAATTCATCTCCAGAATACCCTAGA
AAAGAGTTTGCATCATCCTCAACTAGAGGTAGATCACAGACTAGAGAATCTGAAATC
AGAGTCAGATTACAATCAGCATCTCCTTCAACTAGATGGACTGAGTTAGACGACGTG
AAAAGATTATTAAAGGGATCAAGAAGTGCAAGTGTTTCCCCTACAAGAAATTCTTCC
AACACCCTTCCCATTCTTAAGAAAGGAACCGTTGAAACTAAAATCGTTACAGCATCAT
CTCAGTCTGTATCCGGAACCTACGACGCTACCATTCTGGACGCCAACTTACCTTCTCA

TGTCTGGTCTTCAACTTTACCCGCAGGTTCTCAATGGGAACTTACCACAATAACATG
ACTACTCAATCAAGTTCTCTTCTGAATACCAATGCATACTCAGCCGGTTCCGTTTTTTGG
AGTCCCTAACAATATGGCCTCTTGCTCCCCAACTCTTCATCCAGGTCTTTCAACCTCAT
CAAGTGTATTTGGTATGCAGAACAACTTAGCCCCCTTCCTTGACAACCCTGTCTCATGG
TACTACTACCACTAGTACAGCATATGGAGTCAAGAAGAACATGCCACAGTCACCTGCT
GCCGTTAACTACTGGAGTTTCAACATCTGCTGCCTGCACTACATCTGTTCAATCAGATG
ATCTTCTGCATAAGGACTGCAAGTTTTTAATTTTAGAGAAAGACAATAACCCCTGCCAA
AAAGGAAATGGAGTTACTTATAATGACCAAAGATTCTGGTAAAGTATTCCTGCTTCT
CCCGCTAGTATCGCCGCAACTTCATTCTCTGAAGATACTTTAAAGAAGGAAAAACAA
GCCGCATACAACGCAGACTCAGGTTTAAAAGCAGAAGCAAACGGTGACCTTAAAAC
AGTGTCAACTAAGGGAAAGACTACAACCGCAGACATCCATTCATATGGTTCTTCAGGT
GGAGGAGGATCTGGAGGAGGTGGTGGAGTGGGAGGTGCTGGAGGAGGTCCATGGG
GTCCTGCACCTGCATGGTGCCCTTGCGGTTCTTGCTGCAGTTGGTGGAAGTGGCTTCT
GGGTTTATTATTAACCTTGGCTGCTTTTACTGGGTCTTTTATTTCGGTCTTATCGCATTAGC
AGAAGAGGTTCAGAAACTTAAGGCCAGAGTTGATGAGTTAGAGAGAATCAGAAGAT
CAATCCTTCCCTATGGAGACTCCATGGACAGAATCGAAAAGGATAGACTTCAGGGTAT
GGCCCCTGCAGCAGGAGCTGATCTGGATAAAATCGGACTTCATTCAGATTCTCAAGA
GGAATTATGGATGTTTGTAGAAAGAACTTATGATGGAGCAGGAGAACGGTAACCT
GAGAGGTTCTCCTGGTCCAAAAGGAGATATGGGTTCACCCGGTCCCAAAGGAGATAG
AGGATTCCCTGGTACTCCAGGTATCCCCGGTCCCCTGGGTACACCTGGACCTCAAGGT
CCTAAAGGTCAAAGGGTTCTGTAGGAGATCCAGGTATGGAGGGTCCCATGGGTGAG
AGAGGTAGAGAAGGTCCCATGGGACCAAGAGGTGAAGCTGGACCTCCCGGAAGTGG
TGAAAAAGGAGAAAGAGGAGCAGCAGGAGAACCTGGACCCCATGGACCTCCAGGA
GTTCTCTGGATCAGTCGGACCCAAAGGTTTCATCCGGTTCTCCTGGACCTCAAGGTCCA
CCAGGACCCGTCGGATTGCAAGGATTGAGAGGAGAAAGTTGGACTTCCCGGAGTTAA
GGGTGACAAGGGTCCTATGGGTCTCCTGGTCCAAAGGGAGATCAGGGTGAAAAGG
GTCCTAGAGGTCTGACTGGTGAACCAGGAATGAGAGGACTTCCCGGTGCCGTGGGTG
AACCCGGTGCAAAAGGAGCAATGGGTCTTGCCGGTCTGATGGACACCAGGGACCC
AGAGGAGAGCAGGGATTAACAGGAATGCCTGGTATCAGAGGTCCCCCAGGTCCCTCA
GGAGACCCAGGAAAGCCAGGACTTACTGGTCCCCAGGGTCCTCAAGGTCTGCCTGG
AACTCCCGGAAGACCCGGAATCAAAGGTGAACCAGGAGCCCCAGGAAAAATCGTTA
CTAGTGAAGGATCTTCAATGCTGACTGTGCCAGGTCCACCTGGTCTCCTGGAGCTAT
GGGTCTTCCCGGTCCCCCTGGAGCACCCGGTCTGTCAGGTCTGCCGGATTACCTGG
ACATCAGGAAGTCTTAAACCTGCAAGGTCCACCAGGTCTCCTGGTCCAAGAGGACC
CCCTGGTCTTCAATCCCTGGTCCACCTGGACCTAGAGGTCCACCCGGAGAGGGACT

TCCCGGACCACCAGGACCTCCTGGATCATTCTGTCTAATTCTGAGACATTTCTTTTCAG
GACCTCCTGGTCTCTCCCGGACCACCTGGACCAAAAGGAGATCAGGGACCACCTGGT
CCCAGAGGACATCAAGGAGAGCAGGGTCTTCCAGGTTTCTCTACTTCTGGATCATCAT
CATTTGGTCTTAATCTTCAAGGTCCTCCTGGACCCCCAGGACCACAGGGACCCAAGG
GTGACAAGGGAGACCCTGGAGTCCCAGGTGCACTGGGAATCCCTTCAGGTCCTTCAG
AAGGTGGTTCATCTTCAACCATGTATGTGTCTGGACCCCCAGGACCTCCCGGACCTCC
AGGTCCTCCTGGTTCAATCTCTTCTTCTGGTCAAGAAATTCAGCAGTATATTTCTGAGT
ACATGCAATCTGACTCTATTAGAAGTTATTTGTCTGGTGTGCAGGGTCCACCAGGTCC
TCCAGGTCCCCCTGGACCAGTCACTACTATCACTGGAGAGACATTTGATTATAGTGAA
TTAGCATCACACGTCGTTTCTTATCTGAGAACTTCAGGTTATGGTGTTCATTATTTTCC
TCCTCAATCTCTTCAGAAGACATCTTAGCCGTA CTGCAGAGAGATGATGTAAGACAGT
ACCTTAGACAATACTTGATGGGTCCAAGAGGACCACCAGGTCCACCCGGTGCATCAG
GAGACGGATCATTATTATCTTTGGATTACGCTGAATTATCATCAAGAATCCTTAGTTACA
TGTCTCTTCTGGTATCTCCATAGGTCTGCCCGGTCTCCTGGTCTCTCCCGGACTTCCT
GGTACTTCTTACGAAGAGCTTCTGTCACTTTTAAGAGGATCTGAGTTTAGAGGTATAG
TTGGTCCCCCAGGACCTCCAGGTCCTCCAGGTATCCAGGTAACGTGTGGTCATCTAT
CTCAGTTGAGGATCTTTCATCTTATCTTACACCGCCGGATTGTCCTTTATACCTGGTC
CTCCAGGACCCCCTGGACCTCCTGGACCCAGAGGTCCTCCAGGAGTATCCGGTGCTT
TAGCAACTTATGCAGCAGAAA ACTCCGATTCTTTTAGATCAGAATTGATCTCCTACCTT
ACTTCTCCTGATGTTAGATCATTCATCGTCGGACCTCCAGGACCACCTGGACCTCAAG
GACCTCCTGGAGATTCAAGATTACTGAGTACAGATGCATCACATTCAAGAGGTTCAAG
TTCTTCTTCTCACTCCTCTTCTGTTAGAAGAGGATCATCATATTCATCAAGTATGTCAA
CTGGTGGAGGAGGAGCTGGTTCATTGGGTGCCGGAGGTGCATTTGGTGAGGCCGCTG
GTGACAGAGGACCTTATGGTACTGACATTGGACCTGGTGGAGGTTATGGTGCAGCAG
CAGAAGGTGGAATGTATGCTGGTAATGGAGGTTTACTGGGAGCCGACTTTGCCGGAG
ACCTGGACTACAACGAGTTAGCTGTTAGAGTGTGAGAGTCAATGCAGAGACAAGGAT
TATTACAGGGTATGGCTTATACAGTTCAGGGACCCCCAGGTCAGCCAGGTCCTCAAGG
ACCCCCTGGTATTTCAAAGTCTTCTCCGCTTATTCTAACGTTACTGCAGACCTGATGG
ATTTCTTCCAGACTTACGGTGCCATCCAAGGTCCTCCAGGACAGAAGGGTGAAATGG
GAACTCCCCGGTCCCAAGGGTGACAGAGGTCCTGCAGGACCTCCTGGTCACCCTGGA
CCACCTGGACCTAGAGGACACAAAGGTGAGAAGGGTGACAAGGGAGACCAGGTTTA
CGCAGGAAGAAGAAGAAGAAGTATTGCCGTCAAGCCTCACCATCACCATCATCA
CTAAGCGGCCGC

(3) Synthesis of DNA sequences and construction of recombinant expression vectors

In the present disclosure, the optimized sequences set forth in SEQ ID NO: 8, SEQ ID NO: 9,

and SEQ ID NO: 10 were synthesized by Nanjing Genscript Biotechnology Co., Ltd., and the three gene fragments were denoted as pUC57-170801, pUC57-170802, and pUC57-col17a1. The synthesized gene fragments set forth in SEQ ID NO: 8 and SEQ ID NO: 9 were subjected to double enzyme digestion with SnaB I and Not I, and target gene fragments obtained after the enzyme digestion were ligated into a pPIC9K empty vector (purchased from Thermo Fisher Scientific) undergoing the same double enzyme digestion. The synthesized gene fragment set forth in SEQ ID NO: 10 was subjected to double enzyme digestion with EcoR I and Not I, and target fragments obtained after the enzyme digestion were ligated into a pPIC9K empty vector undergoing the same double enzyme digestion, which served as a control.

Step a. Amplification of the target genes and expression vector: The fragments of pUC57-170801, pUC57-170802, and pUC57-col17a1 and the plasmid of pPIC9K empty vector were extracted with a plasmid mini kit (purchased from Sangon Biotech (Shanghai) Co., Ltd.), and specific operations were conducted according to instructions of the kit.

Step b. The target gene fragments and the plasmid of pPIC9K vector obtained in step a were subjected to double enzyme digestion at 37°C for 30 min. An enzyme digestion reaction system was as follows (the QuickCut™ restriction enzymes used were purchased from Dalian TaKaRa, and an enzyme digestion process was conducted according to instructions):

Plasmid	3 µg
10×H buffer	5 µL
EcoRI/SnaB I	10 U
NotI	10 U
Sterile water	Making up to 50 µL

The obtained target gene fragments and vector fragments were purified with a PCR product purification kit purchased from Dalian TaKaRa (specific operations were conducted according to instructions of the kit). Target gene fragments and linearized vector pPIC9K fragments obtained after the double enzyme digestion were recovered and subjected to ligation at 16°C for 30 min with a Solution I ligation kit (purchased from Dalian TaKaRa), such that the target gene fragments were accurately inserted into a reading frame of the secretory vector carrying a secretion signal α -factor. A ligation reaction system was as follows (according to instructions of the ligation kit):

Linearized pPIC9K fragments	2 µL
Target gene fragments	3 µL
Solution I ligation reagent	5 µL

A ligation product was transformed into competent *E. coli* DH5 α (purchased from Sangon Biotech (Shanghai) Co., Ltd.), positive clones were screened on an LB resistant plate with Amp, the colony PCR verification was conducted, and the recombinant plasmid was extracted for sequencing (which was entrusted to Sangon Biotech (Shanghai) Co., Ltd.). Positive sequencing results indicated that the recombinant expression vectors pPIC9K-170801, pPIC9K-170802, and pPIC9K-col17a1 were successfully constructed in this example, and relevant plasmid maps were respectively shown in FIG. 1, FIG. 2, and FIG. 3.

(4) Construction of recombinant engineered strains and screening of the engineered strains

10 μ g of each of the recombinant expression vector plasmids obtained in step (3) was digested overnight at 37°C with SacI (the enzyme digestion kit was purchased from Dalian TaKaRa, and specific operations were conducted according to instructions of the kit) for linearization, and then a PCR product purification kit (purchased from Sangon Biotech (Shanghai) Co., Ltd.) was used to recover the linearized plasmid, with a recovery volume controlled at about 10 μ L.

The linearized plasmid was electrotransformed into competent cells of an empty host *P. pastoris* strain GS115 (purchased from China Center of Industrial Culture Collection (CICC)), an electrotransformed bacterial suspension was coated on an MD plate with 100 μ L to 200 μ L for each plate, and the plate was allowed to stand at room temperature for 10 min and invertedly incubated at 30°C for 2 d to 5 d until single colonies (positive transformant) appeared.

2 mL of sterile double-distilled water (DDW) was added to a surface of the MD plate, then His⁺ transformants (positive transformants) on the surface of the plate were gently scraped off with a sterile triangular spreader, transferred to a 50 mL centrifuge tube, and diluted with sterile DDW to obtain a bacterial suspension, the bacterial suspension with 10⁵ cells was coated on a YPD plate with 0.5 mg/mL G418, and the plate was inverted and incubated at 30°C for 3 d to 4 d until single colonies appeared. Colonies were picked from the YPD plate and added to a sterile 96-well plate (with 200 μ L of YPD in each well), and the resulting mixture in each well was thoroughly mixed and incubated at 30°C for 48 h; the resulting bacterial suspension in each well was thoroughly mixed, and 10 μ L of the bacterial suspension was taken, added to a second sterile 96-well plate, and then incubated at 30°C for 24 h; the resulting bacterial suspension in each well was thoroughly mixed, and 10 μ L of the bacterial suspension was taken, added to a third sterile 96-well plate, and then incubated at 30°C for 24 h; and 1 μ L was taken from the third 96-well plate, and spotted on each of YPD plates containing 1.0 mg/mL and 4 mg/mL G418, and further incubated at 30°C for 96 h to 120 h. If *P. pastoris* transformants can grow on a plate with high G418 concentration, it indicates that the transformants carry multiple copies of the target gene, that is, the multiple recombinant fragments have been introduced into *P. pastoris* and have been

integrated into the chromosome of *P. pastoris* through homologous recombination. After the screening in this step, a recombinant *P. pastoris* engineered strain with high copy and high expression was obtained.

The three constructed engineered strain samples respectively carrying pPIC9K-col17a1, pPIC9K-170801, and pPIC9K-170802 were sent to the China General Microbiological Culture Collection Center (CGMCC) at No. 1, West Beichen Road, Chaoyang District, Beijing, China, with accession numbers of CGMCC No. 18659, CGMCC No. 20626, and CGMCC No. 20627, respectively, where the CGMCC No. 18659 was deposited on October 10, 2019, and the CGMCC No. 20626 and CGMCC No. 20627 were deposited on September 9, 2020, and the strains all had a taxonomic name of *Pichia pastoris*.

(5) Inducible expression and identification of recombinant collagen

Single colonies were picked from each of the YPD plates with 1.0 mg/mL and 4 mg/mL G418 in step (4), placed in a 100 mL erlenmeyer flask with 10 mL of a BMGY medium, and cultivated at 28°C to 30°C and 220 rpm until OD₆₀₀ was 2 to 6 (16 h to 18 h). The resulting bacterial suspension was centrifuged at 1,500 g to 3,000 g for 5 min at room temperature to collect bacterial cells, and the bacterial cells were resuspended in a BMMY medium such that OD₆₀₀ was about 2, and then cultivated on a shaker at 28°C to 30°C and 220 rpm for 3 d, during which 100% methanol was added to the medium every 24 h to a final concentration of 1.0%. 1 mL of a bacterial suspension sample was collected at different time points (≥ 24 h, if necessary, 24 h, 48 h, 72 h, and 96 h), placed in a 1.5 mL EP tube, and centrifuged at a maximum speed for 2 min to 3 min, and the resulting expression supernatant and bacterial cells were separately collected. The bacterial cells were lysed through disruption with glass beads (purchased from Sangon Biotech (Shanghai) Co., Ltd.) using a lysis buffer (1 mM PMSF, 10 mM Tris, pH 7.4), and the resulting lysate was centrifuged at 12,000 g and 4°C for 5 min to obtain an intracellular lysis supernatant and a precipitate, the intracellular lysate supernatant was collected, and 8 M urea was added to the precipitate and the resulting mixture was shaken for dissolution. An expression level of the target protein and an optimal harvest time of the bacterial suspension were analyzed. The samples to be tested were stored at -80°C for later use.

A 5× loading buffer (250 mM Tris-HCl, pH 6.8, 10% SDS, 0.5% bromophenol blue (BPB), 50% glycerin, and 5% β -mercaptoethanol) was added to each of the collected expression supernatant, intracellular lysis supernatant, and intracellular precipitate solution, and the resulting mixture was heated in a metal bath at 100°C for 10 min and then subjected to SDS-PAGE. Because the expressed target protein included a Srtep-Tag II at an amino terminus and a 6×His tag at a carboxyl terminus, Western Blot was conducted with an anti-Srtep-Tag II antibody and an anti-6×His Tag antibody (purchased from Nanjing Genscript Biotechnology Co.,

Ltd.).

Expression and identification of a $\alpha 1$ chain of a recombinant full-length human type XVII collagen:

It can be seen from the SDS-PAGE result in FIG. 4 that there was no expected target band (with an AMW of about 180 kDa) in the expression supernatant.

Western Blot was conducted with an anti-6 $\times$ His Tag antibody, and a result was shown in FIG. 5. It was found that only a very small amount of the degraded target protein (an AMW was smaller than the expected one, and was about 120 kDa) was detected in the expression supernatant, and the degraded target protein appeared after a long time of inducible expression; there was a large amount of the degraded target protein in the intracellular lysis supernatant, and an AMW of the degraded target protein was smaller than the expected one and was about 120 kDa (which was consistent with an AMW of the extracellular domain of human type XVII collagen); and only the intracellular precipitate solution included the target protein with the expected AMW (180 kDa). The experimental results show that, as a transmembrane collagen, the protein should be fixed on an intracellular membrane system, and can fall off and be dissolved intracellularly only after being degraded; and the degraded target protein detected in the expression supernatant is most likely released into the expression supernatant after the lysis of cells that have died during the long-term cultivation. In either of the above cases, the full-length recombinant human type XVII collagen cannot be efficiently secreted extracellularly from *P. pastoris*.

Expression and identification of collagens 170801 and 170802:

FIG. 6 shows SDS-PAGE results of expression supernatants of engineered bacteria expressing collagens 170801 and 170802 after 24 h of induction. As shown in FIG. 6, the collagens 170801 and 170802 can undergo efficient secretory expression in extracellular culture supernatants after 24 h of induction; and the 170801 has an AMW of about 30 kDa and the 170802 has an AMW of about 52 kDa.

FIG. 7 shows Western Blot results of expression supernatants of engineered bacteria expressing collagens 170801 and 170802 after 24 h of induction (Anti-His, the antibody is purchased from Sangon Biotech (Shanghai) Co., Ltd., and is a mouse anti-His monoclonal antibody (mAb), with Item No. D199987). FIG. 8 shows Western Blot results of expression supernatants of engineered bacteria expressing collagens 170801 and 170802 after 24 h of induction (Anti-Strep-Tag II, the antibody is purchased from Nanjing Genscript Biotechnology Co., Ltd., and is a rabbit anti-Strep-Tag polyclonal antibody (pAb), with Item No. A00626). It can be seen from the results in FIG. 7 and FIG. 8 (enhanced chemiluminescence (ECL) color development, the fully automatic chemiluminescence image analysis system Tanon 5200

integrates protein molecular mass markers into images) that the Srtep-Tag II tag at the amino terminus and the 6×His tag at the carboxyl terminus can be detected, and a size of the target band is the same as the AMW in SDS-PAGE, indicating that the recombinant human type XVII collagens 170801 and 170802 successfully undergo efficient secretory expression.

Bands of proteins resulting from inducible expression were recovered and digested with trypsin, peptides obtained after trypsin enzymolysis of the recombinant collagens were tested by Nano-HPLC-MS/MS (which was entrusted to Suzhou ProtTech Inc.), and the detected peptides were subjected to sequence alignment (Uniprot database). Results were shown in FIG. 9 and FIG. 10, and it can be seen that the peptides detected after the collagens 170801 and 170802 were enzymatically hydrolyzed were relevant regions of the human type XVII collagen sequences selected during the selection and design of amino acid sequences, indicating that the collagens 170801 and 170802 were successfully expressed.

Example 2: Pilot fermentation of genetically-engineered bacteria and protein purification

(1) Pilot fermentation

The constructed engineered bacteria carrying pPIC9K-170801 and pPIC9K-170802 were each subjected to 50 L to 500 L linked pilot fermentation to obtain a fermentation broth with the recombinant human type XVII collagen, thereby realizing the large-scale expression and production of the recombinant human type XVII collagens 170801 and 170802.

A seed medium YPG (formula: yeast powder: 10 g/L, yeast peptone FP102: 20 g/L, and anhydrous glycerin: 10 g/L); a fermentation medium (formula: $\text{NH}_4\text{H}_2\text{PO}_4$: 190.4 g/L, KH_2PO_4 : 10.06 g/L, $\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$: 1.18 g/L, K_2SO_4 : 18.2 g/L, $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$: 14.9 g/L, and glycerin: 40 g/L); a feed medium (50% W/V glycerin, with 12 mL of PTM₁ per liter); and an induction medium (100% methanol, with 12 mL of PTM₁ per liter) were adopted. The PTM₁ was filtered through a 0.22 μm filter membrane for sterilization and stored at 4°C. The fermentation medium was sterilized at a high temperature and cooled to room temperature, then PTM₁ was added, and a pH was adjusted to 5.0 with ammonia water.

The batch-cultivation and inducible expression of the constructed engineered strains were conducted as follows.

The fed-batch cultivation was conducted at 30°C. The constructed engineered bacteria were inoculated into a 2 L shake flask filled with the seed medium YPG and cultivated at 220 rpm and 30°C for 24 h; the resulting bacterial suspension was inoculated at an inoculum size of 10% into a 50 L seed fermentation tank filled with the fermentation medium such that OD₆₀₀ was 5 after the inoculation, and the expanded cultivation was conducted at a stirring speed of 200 r/min to 600 r/min, an air flux of 2 VVM, and dissolved oxygen (DO) of greater than or equal to 30% until a carbon source was exhausted; and the resulting bacterial suspension was transferred to a

500 L fermentation tank filled with the fermentation medium, and the fermentation cultivation was conducted at a stirring speed of 150 r/min to 500 r/min, a tank pressure of 0 MPa to 0.05 MPa, an air flux of 1 VVM, and DO of greater than or equal to 30%. During the fermentation cultivation, when the DO was increased, the feed medium was fed at a flow to maintain $DO \geq 30\%$, and when OD_{600} grew to 190 to 210, the feeding was stopped, and when the DO was increased to be greater than or equal to 70%, the induction medium was fed, the stirring speed, air flux, tank pressure, and feeding flow were adjusted to make DO greater than or equal to 30%, and the inducible expression was conducted for 40 h to 72 h. When a protein concentration measured by a UV meter did not increase significantly or decreased, the resulting fermentation broth was discharged.

UV protein quantification formula: $C \text{ (mg/mL)} = 0.144 * (A_{215} - A_{225})$, $A_{215} < 1.5$.

After the high-density pilot fermentation of the constructed engineered bacteria, it was found that, after induction for 48 h, a bacterial concentration (OD_{600}) could reach 250 or higher, a bacterial wet weight could reach about 300 g/L, and a protein concentration in a fermentation broth was greater than 10 g/L (UV quantification). The results were shown in FIG. 11 and FIG. 12. It can be seen from FIG. 11 that the engineered bacteria of 171801 grew well; and after induction for 48 h, a bacterial concentration (OD_{600}) could reach 270, a bacterial wet weight could reach 355 g/L, and a protein concentration in a fermentation broth could reach 12 g/L (UV quantification). It can be seen from FIG. 12 that the engineered bacteria of 171802 grew well; and after induction for 48 h, a bacterial concentration (OD_{600}) could reach 250, a bacterial wet weight could reach 293 g/L, and a protein concentration in a fermentation broth could reach 11 g/L (UV quantification).

(2) Purification

Buffers used in this example were as follows:

buffer A: 20 mM KH_2PO_4 , pH 4.0; and

buffer B: 20 mM KH_2PO_4 , 1 M NaCl, pH 4.0.

The fermentation broth of the engineered bacteria was collected, and a ceramic membrane separation system (Jiangsu Jiuwu Hi-Tech Co., Ltd., JWC MF-9) was used to separate bacterial cells and a fermentation supernatant. A cation exchange medium (a chromatography packing was UniGel-80sp produced by Suzhou Nanomicro Technology Co., Ltd., which was loaded in a fully automatic chromatography system produced by Jiangsu Hanbon Science & Technology Co., Ltd.) was equilibrated with buffer A until the A_{215} absorbance value and conductivity value remained unchanged, and then a sample was loaded at a flow rate of 100 μ L/min and a volume of 20 L/time; and the UV A_{215} absorbance was detected, and when it increased, the collection of an effluent was started. When the sample loading was completed, the collection of effluent was stopped, and

then the cation exchange medium was equilibrated with buffer A; when the A215 absorbance decreased, the collection of effluent was started; and when the UV absorbance and conductivity dropped to the minimum and no longer changed, the collection of effluent was stopped. Elution was conducted with each of 500 mM and 1 M sodium chloride, and an eluate was collected. The purified protein in each of the 500 mM eluate and 1 M eluate was detected, then each of the eluate was subjected to dialysis (with ultrapure water (UPW) as a dialysis solution), concentration, and lyophilization, and the resulting lyophilized collagen sponge was collected.

The lyophilized collagen sponges (170801 and 170802) were each dissolved with UPW to 2 mg/mL, the resulting solution was filtered through a 0.22 μ m filter membrane, and 10 μ L of the solution was taken and injected into a Sepax Bio-C18 chromatographic column (HPLC Waters2695 or Agilent LC1260) to analyze a purity of each of the purified collagens 170801 and 170802.

The purification results were shown in FIG. 13 and FIG. 14, and it can be seen that the purified collagens 170801 and 170802 had obvious single peaks and high purities (91.2% and 90%), indicating that the purification method of the present disclosure is reliable and effective and the obtained collagens have a high purity.

In addition to the purification method used in this example, since the collagens 170801 and 170802 each have a Srtep-Tag II at the amino terminus and a 6 $\times$ His tag at the carboxyl terminus, Ni-NTA, Strep-Tactin, and other affinity media can be used for single or dual affinity purification, which can also achieve a similar effect to this example.

(3) Characterization of properties of the recombinant collagens

Molecular weight determination:

The theoretically-predicted molecular weights of the obtained proteins 170801 and 170802 were 23.8 kDa and 45.4 kDa, respectively, and the AMWs detected by SDS-PAGE were larger than the theoretically-predicted values. The lyophilized products of the recombinant human type XVII collagens 170801 and 170802 purified were each subjected to MALDI-TOF MS (AB SCIEX 5800 MALDI-TOF/TOF) to detect their relative molecular weights and determine their actual protein molecular weights, which was entrusted to Sangon Biotech (Shanghai) Co., Ltd. The results were shown in FIG. 15 and FIG. 16, and it can be seen that, as detected by MALDI-TOF MS (charge number + 1), the collagen 170801 had a molecular weight of 23811.6797 Da (theoretical value: 23800 Da) and the collagen 170802 had a molecular weight of 45689.5781 Da (theoretical value: 45400 Da); and due to the post-translational modification after expression in *P. pastoris* and the systematic errors in the molecular weight determination, the actually expressed collagen had a molecular weight consistent with the theoretical value.

Fourier transform infrared spectroscopy (FT-IR) analysis:

The characteristic absorption peaks of groups in the collagen could be detected by FT-IR analysis. A trace amount of each of the purified lyophilized products of the collagens 170801 and 170802 was taken, ground into a powder with KBr, then pressed into a tablet, and scanned in a range of $4,000\text{ cm}^{-1}$ to 400 cm^{-1} at room temperature (Thermo Scientific, Nicolet™ iS™ 10 FT-IR Spectrometer). The method and result analysis could be found in the literature (Jeong, H., J. Venkatesan and S. Kim, Isolation and characterization of collagen from marine fish (*Thunnus obesus*). *Biotechnology and Bioprocess Engineering*, 2013. 18(6): p. 1185-1191.)

From the IR spectra of the purified samples of collagens 170801 and 170802 in FIG. 17, it can be seen that wave numbers of amide A, amide B, amide I, amide II, and amide III were all in line with the structural characteristics of recombinant collagen (as shown in literatures [1]. Chen Jingtao et al., *Infrared Spectroscopy of Recombinant Collagen and Bovine Type I Collagen*. *Materials Reports*, 2008 (03): p. 119-121; [2]. Doyle, B.B., E.G. Bendit and E.R. Blout, *Infrared spectroscopy of collagen and collagen-like polypeptides*. *Biopolymers*, 1975. 14 (5): p. 937-957; and [3]. Zhou Aimei et al., *Isolation, Purification, and Structural Characterization of Recombinant Human Collagen*. *Food and Fermentation Industries*, 2015 (03): p. 46-52.).

SEM analysis of lyophilized collagen sponge samples:

A scanning electron microscope (Hitachi TM3030PLUS) was used to scan a surface of each of the lyophilized collagen sponge samples (170801 and 170802), and results were shown in FIG. 18. It can be seen from the figure that the recombinant human type XVII collagens 170801 and 170802 each have an obvious lamellar structure, which is similar to a lamellar distribution of human type XVII collagen on a basement membrane in the human body. Such a structure indicates that the collagens have the potential to be used in the field of biomedical materials.

Example 3: Detection of cell adhesion activity of recombinant collagens

A method for detecting the cell adhesion activity of the recombinant collagens can be found in the literature: Juming Yao, Satoshi Yanagisawa, Tetsuo Asakura. *Design, Expression and Characterization of Collagen-Like Proteins Based on the Cell Adhesive and Crosslinking Sequences Derived from Native Collagens*, *J Biochem*. 136, 643-649 (2004). The detection of cell adhesion activity was entrusted to the Functional Nanomaterials and Biomedical Testing Laboratory of School of Pharmacy, Changzhou University.

A specific implementation method was as follows:

NIH/3T3 cells purchased from the Cell Bank of the Chinese Academy of Sciences (Item No. GNM6, the cultivation and passage methods were conducted according to instructions of the cells) were cultivated normally. The purified lyophilized protein samples 170801 and 170802, a control sample (native human collagen purchased from Sigma, Item No. C7774), and bovine serum albumin (BSA, purchased from Sangon Biotech (Shanghai) Co., Ltd.) were each taken

and dissolved with UPW or a 1 M HCl solution, then a protein concentration was determined according to a UV protein quantification empirical formula of $C \text{ (mg/mL)} = 0.144 * (A_{215} - A_{225})$, and then the resulting solutions were each diluted to 0.5 mg/mL with phosphate buffered saline (PBS) (pH 7.4). 100 μ L of each of the protein solutions and blank PBS solution was added to a 96-well cell culture plate, and the plate was allowed to stand for 60 min at room temperature; and then 3T3 cells in a well growth state were added at 10^5 cells/well, and incubated at 37°C and 5% CO₂ for 60 min. Cells in each well were washed 4 times with PBS. An LDH detection kit (Roche, 04744926001) was used to detect the absorbance OD_{492nm} (specific operations were conducted with reference to instructions).

The absorbance OD_{492nm} can correspondingly characterize the cell adhesion activity of a collagen sample. The higher the absorbance, the more cells the collagen adheres to and the higher the cell adhesion activity, such that the collagen is more likely to help cells adhere to a wall or adhere to an extracellular matrix in a short time, which is conducive to building an excellent extracellular environment. It can be seen from the results in FIG. 19 that the recombinant human type XVII collagens 170801 and 170802 have higher cell adhesion activity than the commercial native human collagen.

Example 4: Detection of cell migration-promoting activity of recombinant collagens by a scratch method

A method for detecting and analyzing the cell migration-promoting activity of the recombinant collagens can be found in the literature: Bobadilla, A., et al., *In vitro* cell migration quantification method for scratch assays. J R Soc Interface, 2019. 16 (151): p. 20180709. The cell migration-promoting activity detection and analysis was entrusted to the Functional Nanomaterials and Biomedical Testing Laboratory of School of Pharmacy, Changzhou University.

A specific implementation method was as follows.

The purified lyophilized collagen samples 170801 and 170802, a control sample (native human collagen purchased from Sigma, Item No. C7774), and BSA (purchased from Sangon Biotech (Shanghai) Co., Ltd.) were each taken and dissolved with UPW or a 1 M HCl solution, then a protein concentration was determined according to a UV protein quantification empirical formula of $C \text{ (mg/mL)} = 0.144 * (A_{215} - A_{225})$, then the resulting solutions were each diluted to 0.5 mg/mL with a DMEM serum-free medium (GIBCO, Item No. 12800017, pH 7.4), and after the dilution, a pH was adjusted to 7.0 to 7.4. NIH/3T3 cells purchased from the Cell Bank of the Chinese Academy of Sciences (Item No. GNM6, the cultivation and passage methods were conducted according to instructions of the cells) were cultivated and passaged normally. Cells in a well growth state were inoculated into a 6-well plate and cultivated for 36 h, where 2 mL of a

cell suspension with 20,000 cells/mL was inoculated in each well. A scratch was prepared with a 200 μ L pipette tip, and the cells were washed 3 times with PBS to remove the scratched cells. The protein solutions diluted with the DMEM serum-free medium were each added to a well, the cells were further cultivated in a 37°C and 5% CO₂ incubator, and then a sample was collected and photographed at 0 h, 24 h, and 48 h. The Image J software was used to process images of cell migration to obtain the data of initial scratch area and cell-free blank area, and a migration rate was calculated as follows: migration rate = (1 - cell-free blank area/initial scratch area) * 100%.

The *in vitro* cell migration experiment simulated a process of *in vivo* cell migration to some extent, and directly reflected an interaction between cells and an extracellular matrix and an interaction between cells under the influence of the matrix. The cell migration-promoting activity is an index to effectively characterize the biological activity of collagen. The higher the migration rate, the higher the biological activity of the collagen. From the comparison of actual cell migration images taken at different time points (areas between two black lines are scratch wound areas at the beginning and after cell migration) in FIG. 20 and the comparison of the calculated cell migration rates shown in FIG. 21 (a cell-free blank area is calculated by Image J), it can be seen that the recombinant human type XVII collagens 170801 and 170802 have higher cell migration-promoting activity than the commercial native human collagen.

Example 5: Preparation of recombinant collagen gels 170801 and 170802 and rabbit ear scar model experiment

Sodium carboxymethyl cellulose (CMC-Na) and each of purified lyophilized collagen products 170801 and 170802 were separately dissolved in UPW to obtain a 0.01% CMC-Na solution and a 5% collagen solution, and then the 0.01% CMC-Na solution was thoroughly mixed with the 5% collagen solution to prepare a collagen gel. A CMC-Na gel without collagen was adopted as a negative control.

New Zealand white rabbits (purchased from the Experimental Animal Center of the Naval Medical University) each weighing 2 kg to 3 kg were selected and raised in a well-ventilated room at 21°C for 2 weeks before the experiment to adapt to the environment, with a 12 h day-night cycle and single-cage raising. Subsequently, scar models were constructed: The experimental animals were administered with 30 g/L pentobarbital sodium at 1.0 mL/kg (30 mg/kg) for ear vein anesthesia, and after the anesthesia was achieved, the skin was disinfected with alcohol 3 times. A skin biopsy device with a diameter of 1 cm was used to draw a neat skin incision margin at an inner side of a rabbit ear, and ophthalmic scissors were used to cut a full-thickness skin defect wound with a diameter of about 1 cm, which was exposed to a bone surface of an ear cartilage. The wound was covered with sterile vaseline gauze inside and sterile

gauze outside, and then bandaged and fixed. The wound was disinfected and debrided with iodophor and the wound dressing was changed every 2 d to 3 d.

On day 21, after the wound healed, the rabbits were grouped and subjected to a scar intervention treatment. The collagen gels 170801 and 170802 were each applied to the wound in combination with an iodine-containing antibacterial surgical foil (Drape Antimicrob®, Minnesota Mining and Manufacturing Company, USA) and a self-adhesive silicone film dressing (Cica-Care®, Smith&Nephew, England) for scar intervention.

A digital camera and a dermoscope were used to record the scar conditions during the 1-6 week scar intervention experiment. At the 6th week, the rabbits were anesthetized and sacrificed by injecting a supersaturated potassium chloride solution into the ear vein, and ear scar samples were collected, soaked in a fixing solution, subjected to hematoxylin and eosin (HE) staining and MASSON staining, observed under a microscope, and photographed. Specific methods can be found in the following literatures: [1] Liu Tong. Experimental Study on Use of Recombinant Human Collagen Hydrogel and Artificial Dermis as Microskin Graft coverings to Repair Full-Thickness Skin Defects [D]. Naval Medical University, 2019; and [2] Experimental Guidance of Histology and Embryology [M] edited by Li Jicheng, Beijing: People's Medical Publishing House, 2018. 09.

Experimental results were shown in FIG. 22. In the experimental group, after being intervened with the collagen gels 170801 and 170802, the wound at the rabbit ear skin well healed, and there was obvious new hair growth at an inner side of the rabbit ear, indicating that the collagens have obvious biological functions of promoting hair follicle generation and hair growth; and it can be seen from the Masson staining and HE staining results of tissue sections that collagen fibers in the tissue were arranged orderly, a dermal tissue was generated and especially a new hair follicle structure was generated, and there was obviously hair growth (inside a circle indicated by an arrow in the figure), clearly indicating that the collagens have the biological functions to promote dermal tissue repair and hair follicle regeneration (hair generation). In the control group, the prognostic scar still had a large number of regular and dense collagen deposits, which was similar to the scar structure; and no hair follicle structure, no dermal tissue, and no new rabbit hair were generated. The experimental results show that the recombinant human type XVII collagens 170801 and 170802 have excellent biological activities to promote tissue repair and hair follicle repair and regeneration.

Claims

What is claimed is:

1. A recombinant human type XVII collagen, having an amino acid sequence selecting from the group consisting of SEQ ID NO: 2 and SEQ ID NO: 3.
2. The recombinant human type XVII collagen according to claim 1, wherein a protein tag is added to each of an amino terminus and a carboxyl terminus of a peptide chain of the recombinant human type XVII collagen, and a Strep-Tag II is added to the amino terminus and a 6×His Tag is added to the carboxyl terminus.
3. The recombinant human type XVII collagen according to claim 1, wherein the recombinant human type XVII collagen has a cell adhesion activity, a cell migration-promoting activity, a tissue regeneration-promoting activity, and a hair follicle repair and regeneration-promoting activity.
4. A polynucleotide encoding the recombinant human type XVII collagen according to claim 1.
5. The polynucleotide according to claim 4, wherein the polynucleotide has a nucleotide sequence selected from the group consisting of SEQ ID NO: 6 and SEQ ID NO: 7.
6. A recombinant expression vector carrying the polynucleotide according to claim 4 or 5.
7. An engineered bacterium carrying the recombinant expression vector according to claim 6.
8. The engineered bacterium according to claim 7, wherein the engineered bacterium is *Pichia pastoris*.
9. A preparation method of the recombinant human type XVII collagen according to claim 1, comprising the following steps:
 - (1) cultivation and screening of engineered bacteria: constructing and screening engineered bacteria to obtain an engineered bacterium with a high expression; and
 - (2) large-scale high-density fermentation, cultivation, and protein purification: fermenting the engineered bacterium in a fermentation tank to obtain a fermentation supernatant, and purifying the fermentation supernatant to obtain a high-purity collagen.
10. The preparation method according to claim 9, wherein the engineered bacterium with the high expression screened out in step (1) is *Pichia pastoris* with an accession number of CGMCC No. 20626 or CGMCC No. 20627.
11. A composition comprising the recombinant human type XVII collagen according to claim 1 or a recombinant human type XVII collagen prepared by the preparation method according to claim 9.
12. An article comprising the recombinant human type XVII collagen according to claim 1

or a recombinant human type XVII collagen prepared by the preparation method according to claim 9 or the composition according to claim 11, wherein the article is selected from the group consisting of a drug, a medical device, a biological material, a tissue-engineered product, a cosmetic, and a health product.

13. Use of the recombinant human type XVII collagen according to claim 1, the polynucleotide according to claim 4 or 5, the recombinant expression vector according to claim 6, the engineered bacterium according to claim 7, or the composition according to claim 11 in a manufacture of a product, wherein the product is selected from the group consisting of a drug, a medical device, a biological material, a tissue-engineered product, a cosmetic, and a health product.

14. Use of the recombinant human type XVII collagen according to claim 1, the polynucleotide according to claim 4 or 5, the recombinant expression vector according to claim 6, the engineered bacterium according to claim 7, or the composition according to claim 11 in a manufacture of a product for promoting scar healing, tissue repair, or hair follicle repair.

15. The use according to claim 14, wherein the product is an external preparation.

16. The use according to claim 15, wherein the product is the external preparation for a topical application.

17. The use according to claim 16, wherein the product is an external gel for the topical application.

18. A cell carrying the recombinant expression vector according to claim 6.

19. The cell according to claim 18, wherein the cell is *Pichia pastoris*.