



G00002

1

A CATALYST COMPRISING A COMPLEX OF A METAL GROUP VIII BASED ON A
PHOSPHINITE LIGAND, PROCESS FOR HYDROFORMYLATION

5 The present invention relates to a catalyst which comprises at
least one complex of a metal of group VIII, which comprises at
least one uni-, bi- or multidentate phosphinite ligand in which
the phosphorus atom and the oxygen atom of the phosphinite group
are part of a 5- to 8-membered heterocycle, and to processes for
10 the hydroformylation and hydrocyanation of compounds which
contain at least one ethylenically unsaturated [sic] double bond
in the presence of a catalyst of this type.

Hydroformylation or oxo synthesis is an important industrial
15 process and is used to prepare aldehydes from olefins, carbon
monoxide and hydrogen. These aldehydes may, where appropriate, be
hydrogenated with hydrogen in the same operation to give the
corresponding oxo alcohols. The reaction itself is highly
exothermic and generally proceeds under elevated pressure and at
20 elevated temperatures in the presence of catalysts. The catalysts
employed are Co, Rh or Ru compounds or complexes which may be
modified with amine- or phosphine-containing ligands to influence
the activity and/or selectivity. Additional promoters have not to
date achieved any importance in practice. The hydroformylation
25 reaction results, because of the possibility of addition of CO to
each of the two C atoms in a double bond, in the formation of
mixtures of isomeric aldehydes. In addition, when internal
olefins are used, isomerization of the double bond from an
internal toward a terminal position may occur. In these isomeric
30 mixtures, the n aldehyde is generally favored over the iso
aldehyde but, because the n aldehydes have considerably greater
industrial importance, one aim is to optimize the
hydroformylation catalysts to achieve greater n selectivity.

35 A review of hydroformylation processes is given in Beller et al.,
Journal of Molecular Catalysis A, 104 (1995), pages 17-85. None
of the references mentioned therein describes hydroformylation
catalysts based on bi- or multidentate phosphinite ligands where
the phosphinite group is part of a 5- to 8-membered heterocycle.

40

EP-A 0 599 284 describes cycloolefin polymer molding compositions
which are stabilized with an organophosphorus compound against
unwanted oxidative, thermal and photochemical damage. Stabilizers
which can be employed in this case are, inter alia, phosphinites
45 in which the phosphorus and the oxygen atom in the phosphinite
group are part of a 6-membered heterocycle. DE-A 40 21 195 and
WO 92/00306 describe a process for preparing these



166166

2

organophosphorus compounds by Grignard synthesis, and the use thereof for stabilizing plastics. Complex compounds of these organophosphorus compounds and their use as ligands in hydroformylation catalysts are not described.

5

Catalytic hydrocyanation to prepare nitriles from olefins likewise has great industrial importance. This generally involves reacting mono-, di- or polyolefins in the presence of suitable catalysts with hydrogen cyanide to give mono-, di- and
10 polynitriles or mixtures thereof, which are of outstanding importance in particular as amine precursors, e.g. for preparing polyamides.

"Applied Homogeneous Catalysis with Organometallic Compounds",
15 Volume 1, VCH Weinheim, pp. 465 et seq., gives a general description of heterogeneous and homogeneous catalysis for addition of hydrogen cyanide onto olefins. The catalysts used for this are in particular those based on phosphine, phosphite and phosphonite complexes of nickel and palladium.

20

The usual catalysts for the hydrocyanation are, in particular, the nickel(0) phosphite catalysts mentioned above.

C.A. Tolman et al. describe in Organometallics 1984, 3, pp. 33 et
25 seq. the catalytic hydrocyanation of olefins in the presence of nickel(0) phosphite complexes paying special attention to the effects of Lewis acids on the addition of hydrogen cyanide.

Advances in Catalysis, Volume 33, 1985, Academic Press Inc., pp.
30 1 et seq., gives a review-like description of homogeneous nickel-catalyzed hydrocyanation of olefins. The catalysts employed are nickel(0) complexes with phosphine and phosphite ligands.

35 J. Chem. Soc., Chem. Commun., 1991, p. 1292, describes chiral aryl diphosphites as ligands for hydrocyanation catalysts. The phosphite group in these ligands is bonded by two of its oxygen atoms to the 3 and 3' positions of a 2,2'-binaphthyl unit, with which it thus forms a 7-membered heterocycle. It is additionally
40 possible for two of these heterocycles likewise to be linked via a 2,2'-binaphthyl unit to a bidentate chelating ligand.

J. Chem. Soc., Chem. Commun., 1991, pp. 803 et seq., describes chelate diphosphite complexes of nickel(0) and platinum(0)
45 analogous thereto, employing a 2,2'-biphenyl [sic] unit in place of a 2,2'-binaphthyl unit.

3

WO 95/28228 describes a process for the hydrocyanation of aliphatic monoolefins which may additionally have an unconjugated nitrile group or an unconjugated or conjugated ester group. The nickel(0) catalysts employed in this case likewise comprise
5 bidentate phosphite ligands in which the phosphite groups are parts of aryl-fused heterocycles.

WO 95/29153 describes a process for the hydrocyanation of monoolefins employing catalysts based on zero-valent nickel and
10 unidentate phosphite ligands. The phosphite group in these ligands is once again, together with two of its oxygen atoms, part of an aryl-fused 7-membered heterocycle. The third oxygen atom of the phosphite group carries a t-butyl-substituted phenyl radical which may have further substituents.

15 WO 96/11182 describes a process for the hydrocyanation of aliphatic, monoethylenically unsaturated compounds in which the ethylenic double bond is not conjugated with another unsaturated group or in which the ethylenic double bond is conjugated with an
20 ester group. In this case, a nickel(0) catalyst based on a multidentate phosphite ligand is employed in the presence of a Lewis acid as promoter. The phosphite groups in these multidentate ligands are in turn constituents of aryl-fused heterocycles and may be linked together via aryl-fused groups.

25 WO 96/22968 describes a process for the hydrocyanation of diolefinic compounds and for the isomerization of the resulting unconjugated 2-alkyl-3-monoalkenenitriles by reacting an acyclic aliphatic diolefin with a source of hydrogen cyanide. The
30 reaction in this case takes place in the liquid phase. The hydrocyanation catalysts employed are analogous to those described in WO 96/11182.

US-A 5,512,695 has a disclosure content corresponding to that of
35 WO 95/28228.

Apart from the hydrocyanation catalysts based on uni-, bi- and multidentate phosphite ligands described above, catalysts based on phosphinite ligands are also known. J. Am. Chem. Soc., 1994,
40 116, pp. 9869 et seq. and US-A-5,484,902 describe catalysts for the enantioselective hydrocyanation of aromatic vinyl compounds based on a chiral, non-racemic, bidentate chelating phosphinite ligand. The ligand preferably employed in this case is a phenyl
2,3-bis-O-(3,5-bis(trifluoromethyl)phenyl)phosphino-4,6-O-benzyl-
45 idene- β -D-glucopyranoside.

US-A 5,523,453 describes a process for the hydrocyanation of monoolefins which may additionally have a cyano group in the presence of a Lewis acid as promoter and of a nickel(0) catalyst. These catalysts have ligands based on chelating phosphinites where two aryl-substituted phosphinite groups are linked together via their oxygen atom and an aryl-fused alkylene bridge.


None of the abovementioned references describes hydrocyanation catalysts based on phosphinite ligands in which the phosphinite group is part of a 5- to 8-membered heterocycle.

US-A 3,766,237 describes a process for the hydrocyanation of ethylenically unsaturated compounds which may have other functional groups, e.g. nitriles, in the presence of a nickel catalyst. These nickel catalysts have four ligands of the general formula $M(X,Y,Z)$ where X, Y and Z are, independently of one another, a radical R or OR, and R is selected from alkyl and aryl groups having up to 18 carbon atoms. However, only phosphines and phosphites are explicitly mentioned therein and employed in the examples of the hydrocyanation. On the other hand there is no disclosure of the possibility of employing phosphinites in which the phosphinite group is part of a heterocycle as ligands for nickel(0) hydrocyanation catalysts.

It is an object of the present invention to provide novel catalysts based on complexes of a metal of group VIII. They are preferably intended to be suitable for hydroformylation and/or hydrocyanation and to have good catalytic activity.

We have found that this object is achieved by catalysts based on complexes of a metal of group VIII which comprise at least one uni-, bi- or multidentate phosphinite ligand where the phosphinite group is part of a 5- to 8-membered heterocycle.

The present invention thus relates to a catalyst comprising at least one complex of a metal of group VIII with at least one uni-, bi- or multidentate phosphinite ligand of the general formula I



45
in which

5

- A, together with the part of the phosphinite group to which it is bonded, is a 5- to 8-membered heterocycle which is optionally additionally fused once, twice or three times to cycloalkyl, aryl and/or hetaryl, where the fused groups may, independently of one another, each have one, two, three or four substituents selected from alkyl, alkoxy, halogen, nitro, cyano, carboxyl and carboxylate,
- R¹ is alkyl, aryl or hetaryl, each of which optionally has one, two or three substituents selected from alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen, trifluoromethyl, nitro, cyano, carboxyl, carboxylate, acyl, sulfonyl, NE¹E² and alkylene-NE¹E², where E¹ and E² are identical or different and are selected from alkyl, cycloalkyl and aryl; or is a radical of the general formula II

-X-Y (II)


in which

- X is either a C₂-C₈-alkylene bridge which is optionally interrupted by SiR^aR^b, N [sic], NR^c, O or S, in which R^a and R^b are hydrogen, alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, and R^c is hydrogen, alkyl or aryl, where aryl is optionally mono- or disubstituted by alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, optionally has one, two or three double bonds and/or is optionally fused once, twice or three times to aryl and/or hetaryl, where the aryl or hetaryl groups have, independently of one another, optionally one, two, three or four substituents selected from alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen, trifluoromethyl, nitro, cyano, acyl, carboxyl, carboxylate, sulfonyl, sulfonate, NE¹E² and alkylene-NE¹E², where E¹ and E² have the meanings indicated previously, and adjacent fused rings are optionally connected by SiR^aR^b, N [sic], NR^c, O or S or by a C₁-C₆-alkylene bridge which optionally additionally carries a group selected from SiR^aR^b, N [sic], NR^c, O or S, in which R^a, R^b and R^c are as defined above; or

is an optionally substituted metallocene bridge; and

- Y is a radical of the formula III

6



5

in which

10 D has the meanings indicated previously for A, and

m and n are, independently of one another, 0 or 1,

or a salt thereof.

- 15 For the purpose of the present invention, the term "alkyl" comprises straight-chain and branched alkyl groups. These are preferably straight-chain or branched C₁-C₈-alkyl, preferably C₁-C₆-alkyl and particularly preferably C₁-C₄-alkyl groups. Examples of alkyl groups are, in particular, methyl, ethyl,
- 20 propyl, isopropyl, n-butyl, 2-butyl, sec-butyl, tert-butyl, n-pentyl, 2-pentyl, 2-methylbutyl, 3-methylbutyl, 1,2-dimethylpropyl, 1,1-dimethylpropyl, 2,2-dimethylpropyl, 1-ethylpropyl, n-hexyl, 2-hexyl, 2-methylpentyl, 3-methylpentyl, 4-methylpentyl, 1,2-dimethylbutyl, 1,3-dimethylbutyl,
- 25 2,3-dimethylbutyl, 1,1-dimethylbutyl, 2,2-dimethylbutyl, 3,3-dimethylbutyl, 1,1,2-trimethylpropyl, 1,2,2-trimethylpropyl, 1-ethylbutyl, 2-ethylbutyl, 1-ethyl-2-methylpropyl, n-heptyl, 2-heptyl, 3-heptyl, 2-ethylpentyl, 1-propylbutyl, octyl.
- 30 For the purpose of this invention, the term "alkylene" comprises straight-chain, optionally substituted alkylene groups with 1 to 8 carbon atoms. If X is an alkylene bridge, this has 2 to 8, preferably 3 to 6 and particularly preferably 3 to 5 carbon atoms. The alkylene bridge can be interrupted by hetero groups,
- 35 e.g. Si [sic], SiR^aR^b, N [sic], NR^c, O or S, in particular O and NR^c, in which R^a and R^b are hydrogen, alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, and R^c is hydrogen, alkyl or aryl, where aryl is optionally mono- or disubstituted by alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano. Alkylene
- 40 bridges having no heteroatoms are preferred for X. The alkylene bridge may moreover have one, two or three, preferably one or two, double bonds and/or may optionally be fused once, twice or three times, preferably once or twice, to aryl and/or hetaryl, preferably to aryl. Optionally fused aryl or hetaryl groups may
- 45 have, independently of one another, one, two, three or four, preferably one, two or three, substituents selected from alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen,

- have one, two or three, preferably one or two, double bonds and/or may optionally be fused once, twice or three times, preferably once or twice, to aryl and/or hetaryl, preferably to aryl. Optionally fused aryl or hetaryl groups may have,
- 5 independently of one another, one, two, three or four, preferably one, two or three, substituents selected from alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen, trifluoromethyl, nitro, cyano, acyl, carboxyl, carboxylate, NE^1E^2 or
- 10 alkylene- NE^1E^2 , where E^1 and E^2 are identical or different and are selected from alkyl, cycloalkyl and aryl. If an alkylene group carries an NE^1E^2 group, it preferably has 1 to 4 carbon atoms and particularly preferably 1 or 2 carbon atoms, and methylene and ethylene are very particularly preferred. The substituents of the fused aryls and hetaryls are preferably selected from alkyl,
- 15 alkoxy, trifluoromethyl, halogen and carboxylate.

The cycloalkyl group is preferably a C_5 - C_7 -cycloalkyl group such as cyclopentyl, cyclohexyl or cycloheptyl.

- 20 If the cycloalkyl group is substituted, it preferably has 1, 2, 3, 4 or 5, in particular 1, 2 or 3, substituents selected from alkyl, alkoxy or halogen.

- Aryl is preferably phenyl, tolyl, xylyl, mesityl, naphthyl,
- 25 anthryl, phenanthryl, naphthacenyl and, in particular, phenyl or naphthyl.

- Substituted aryl radicals preferably have 1, 2, 3 or 4, in particular 1, 2 or 3, substituents selected from alkyl, alkoxy,
- 30 carboxylate or halogen.

Hetaryl is preferably pyridyl, quinolinyl, acridinyl, pyridazinyl, pyrimidinyl or pyrazinyl.

- 35 Substituted hetaryl radicals preferably have 1, 2 or 3 substituents selected from alkyl, alkoxy or halogen.

- The above statements about alkyl, cycloalkyl and aryl radicals apply correspondingly to alkoxy, cycloalkyloxy and aryloxy
- 40 radicals.

The NE^1E^2 radicals are preferably N,N -dimethyl, N,N -diethyl, N,N -dipropyl, N,N -diisopropyl, N,N -di- n -butyl, N,N -di- $tert$ -butyl, N,N -dicyclohexyl or N,N -diphenylamino.

8

If R^1 is a radical of the general formula II




- 5 then X is preferably selected from 2,3-xylylene, 2,2'-biphenyl-ylene, 2,2'-binaphthyl-ylene, and arylene, in particular phenylene and naphthylene, linked by O, S and NR^c , where R^c has the meaning indicated above. It is moreover possible for each phenyl unit additionally to have 1, 2 or 3 substituents, each naphthyl unit
10 to have 1 to 4, preferably 1 to 3, substituents, selected from alkyl, cycloalkyl, aryl, alkyloxy, halogen, trifluoromethyl, nitro, cyano, acyl, carboxyl and carboxylate, in particular alkyl, alkoxy, trifluoromethyl and carboxylate. The phenyl and naphthyl units may additionally be linked by O, S or NR^c or a C_1 -
15 to C_6 -alkylene bridge, which may be interrupted by O, S or NR^c , where R^c has the meaning already indicated above. Y is preferably a phosphite, phosphonite or phosphinite ligand where the O-P-O ($n=1$) or P-O group ($n=0$) is likewise part of a 5- to 8-membered heterocycle. The statements already made above about the
20 heterocycle of the phosphinite ligand of the formula I according to the invention apply thereto. In particular, the meanings defined previously for A apply to D, and A and D can be identical or different.
- 25 X can, however, also be a metallocene bridge which optionally has one or more other substituents.


The term "metallocene" for the purpose of this invention is a sandwich metal complex with two η^5 - or η^6 -bonded unsaturated or
30 aromatic ring systems which may be arranged parallel or at an angle, depending on the central metal atom. The metals suitable as central metal atom are all those which form stable sandwich complexes with adequate stability also under the conditions of use of the catalysts according to the invention, but especially
35 Fe, Co, Ni, Ru, Os, Rh, Mn, Cr or V, particularly preferably Fe, Co and Ni. The metals in the metallocene complexes preferably have the formal oxidation numbers 0, +1 or +2. Suitable η^5 - and η^6 -complexable unsaturated or aromatic ring systems are cyclopentadienyl, indenyl, fluorenyl, azulenyl, benzene,
40 naphthalene, anthracene and phenanthrene. Said ring systems may have, for example, 1 to 5, preferably 1 to 3, of the abovementioned substituents, in particular alkyl, alkoxy and alkylene- NE^1E^2 and, particularly preferably, methyl, isopropyl and tert-butyl.

45


X is preferably a radical of the formula IV.1, IV.2, IV.3, IV.4, IV.5, IV.6, IV.7 or IV.8




(IV.1)




(IV.2)




(IV.3)



(IV.4)




(IV.5)




(IV.6)

20

25



(IV.7)



(IV.8)

in which

35 R^2 , $R^{2'}$, R^3 and $R^{3'}$ are, independently of one another, hydrogen, alkyl, alkoxy, halogen, trifluoromethyl, nitro, cyano, acyl, carboxyl or carboxylate,

40 R^4 is hydrogen, alkyl, preferably methyl, or aryl, preferably phenyl, which may optionally be substituted by alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, and

45 R^5 , $R^{5'}$, R^6 , $R^{6'}$, R^7 , $R^{7'}$, R^8 , $R^{8'}$, R^{12} , $R^{12'}$, R^{13} and $R^{13'}$ have the meanings mentioned for R^2 and R^3 or are, independently of one another, selected from cycloalkyl, aryl or alkyl, which may be interrupted by an oxygen atom or substituted by a radical of the formula NE^1E^2 , where E^1 and E^2 have the meaning

10

indicated above; or in each case two adjacent substituents R^5 , R^6 , R^7 , R^8 and/or $R^{5'}$, $R^{6'}$, $R^{7'}$, $R^{8'}$ represent, with the part of the cyclopentadienyl ring connecting them, an aromatic or nonaromatic 5- to 7-membered carbocycle or
 5 heterocycle, where the heterocycle has 1, 2 or 3 heterogroups selected from O, N [sic], NR^c and S,

M is Fe, Co, Ni, Ru, Os, Rh, Mn, Cr or V,

10 Z^1 is O, S and NR^c or a C_2 - to C_3 -alkylene bridge which is interrupted by O, S or NR^c ,

Z^2 and Z^3 are, independently of one another, CH_2 , SiR^aR^b , O, S, NR^c or CR^aR^b , where R^a , R^b and R^c each have the meaning indicated
 15 above.

The above statements about preferred A radicals apply correspondingly to preferred D radicals.

20 When one of the radicals R^5 , $R^{5'}$, R^6 , $R^{6'}$, R^7 , $R^{7'}$, R^8 or $R^{8'}$ in IV.7 is alkyl which is interrupted by an oxygen atom in ether linkage, they may be, for example, 2-methoxyethyl, 2-ethoxyethyl, 2-propoxyethyl, 2-butoxyethyl, 2- or 3-methoxypropyl, 2- or 3-ethoxypropyl, 2- or 3-propoxypropyl, 2- or 3-butoxypropyl, 2-
 25 or 4-methoxybutyl, 2- or 4-ethoxybutyl, 2- or 4-butoxybutyl.

When one of the radicals R^5 , $R^{5'}$, R^6 , $R^{6'}$, R^7 , $R^{7'}$, R^8 or $R^{8'}$ in IV.7 is alkyl which is substituted by a radical of the formula NE^1E^2 , they may be, for example, N,N-dimethylaminomethyl,
 30 N,N-dimethylaminoethyl, N,N-diethylaminomethyl, N,N-diethyl-aminoethyl or N,N-dimethylaminopropyl.

When in each case two of the substituents R^5 , R^6 , R^7 , R^8 and/or $R^{5'}$, $R^{6'}$, $R^{7'}$, $R^{8'}$ in adjacent positions in IV.7 represent,
 35 together with the part of the cyclopentadienyl ring connecting them, an aromatic or nonaromatic 5- to 7-membered carbocycle or heterocycle which additionally has 1, 2 or 3 heteroatoms selected from O, N and S, they may be, for example, indenyl, fluorenyl, azulenyl, etc.

40 The two cyclopentadienyl rings in the metallocene of the formula IV.7 may be present in eclipsed or staggered conformation with varying conformational angles. The planes of the cyclopentadienyl rings may be parallel or inclined relative to one another, for
 45 example, depending on the central metal.

11

A preferred embodiment of the invention comprises catalysts which comprise at least one phosphinite ligand of the formula I, where A, together with the part of the phosphinite group to which it is bonded, is a 5- or 6-membered heterocycle which may optionally be
 5 fused once or twice to aryl and/or hetaryl, where the fused groups may have one, two or three of the substituents indicated previously.

The A radical is then, for example, a 2,2'-biphenylylene,
 10 2,2'-binaphthylylene or 2,3-xylylene radical, which may have 1, 2 or 3 substituents selected from alkyl, alkoxy or halogen. Alkyl in this case is preferably C₁-C₄-alkyl and, in particular, t-butyl. Alkoxy in this case is preferably C₁-C₄-alkoxy and, in particular, methoxy. Halogen is, in particular, fluorine,
 15 chlorine or bromine. The above statements about preferred A radicals apply correspondingly to preferred D radicals.

In another preferred embodiment, the catalysts according to the invention comprise at least one phosphinite ligand of the formula
 20 I where

R¹ is phenyl or naphthyl, which may have one, two or three of the following substituents: alkyl, alkoxy, halogen, nitro, cyano, carboxyl or NE¹E² where E¹ and E² have the meanings
 25 indicated previously, or a radical of the formula II in which

X is a C₄-C₅-alkylene bridge which may have one or two double bonds and/or may be fused once or twice to aryl and/or hetaryl, where the aryl or hetaryl groups may have
 30 one, two or three of the following substituents: alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen, nitro, cyano, carboxyl, carboxylate, alkylene-NE¹E² or NE¹E², where E¹ and E² have the meanings indicated previously, and

35 Y is a radical of the formula III in which D is a radical of the formulae IV.1, IV.2, IV.3, IV.4, IV.5, IV.6 or IV.8.


40 If R¹ is phenyl or naphthyl, this preferably has 1, 2 or 3 substituents selected from C₁-C₄-alkyl, C₁-C₄-alkoxy or halogen. The substituents are particularly selected from t-butyl, methoxy, trifluoromethyl, fluorine, chlorine and bromine.

45 If R¹ is a radical of the formula II in which X is a C₄-C₅-alkylene bridge, the latter is preferably fused once or twice to phenyl and/or naphthyl, where the phenyl or naphthyl


12

groups may have 1, 2 or 3 of the following substituents: t-butyl, methoxy, carboxylate, fluorine, chlorine or bromine.


In a suitable embodiment, the phosphinite ligands of the formula 5 I are selected from ligands of the formula Ia to Ii




(Ia)




(Ib)




(Ic)



(Id)




(Ie)




(If)

13




(Ig)

15



(Ih)

30



(Ii)

in which:


45 R^9 and R^{10} are, independently of one another, hydrogen or trifluoromethyl,

14

R^1 is fluorine or trifluoromethyl.

The catalysts according to the invention may have one or more of the phosphinite ligands of the formula I. In addition to the
 5 ligands of the general formula I described previously, they may also have at least one other ligand selected from halides, amines, carboxylates, acetylacetonate, aryl- or alkylsulfonates, hydride, CO, olefins, dienes, cycloolefins, nitriles, N-containing heterocycles, aromatic and heteroaromatic compounds,
 10 ethers, PF_3 , and uni-, bi- and multidentate phosphine, phosphinite, phosphonite and phosphite ligands. These other ligands may likewise be uni-, bi- or multidentate and coordinate to the metal atom of the catalyst complex. Examples of other suitable phosphorus-containing ligands are the usual phosphine,
 15 phosphonite and phosphite ligands.

The phosphinite ligands of the formula I employed according to the invention can be prepared, for example, by reacting a
 20 hydroxyl-containing compound of the formula V with a phosphorus trihalide, preferably PCl_3 , to give a compound of the formula VI. The latter is then reacted with an organometallic compound of the formula $R^1[M(Q)_q]_r$. The latter is prepared from $R^1[(Q)_q]_r$ and employed as the compound generated in situ or previously isolated. The preparation can be illustrated by the following
 25 scheme



where A and R^1 have the meanings indicated previously, and M is lithium or magnesium, X is H, Cl, Br, q is 0 or 1 and r is 1 or
 35 2.

A process of this type for synthesizing phosphinites is described in WO 92/00306, which is incorporated herein by reference.

40 Examples of suitable compounds of the formula V are 2-biphenylol, 2-binaphthylol, 1,1'-biphenyl-4-phenyl-2-ol [sic], 1,1'-biphenyl-3,3',5,5'-tetra-*t*-butyl-2-ol [sic], 1,1'-biphenyl-3,3'-di-*t*-amyl-5,5'-dimethoxy-2-ol [sic], 1,1'-biphenyl-3,3'-di-*t*-butyl-5,5'-dimethoxy-2-ol [sic],
 45 1,1'-biphenyl-3,3'-di-*t*-butyl-2-ol [sic], 1,1'-biphenyl-3,3'-di-*t*-butyl-6,6'-dimethyl-2-ol [sic], 1,1'-biphenyl-3,3',5,5'-tetra-*t*-butyl-6,6'-dimethyl-2-ol [sic],

15

1,1'-biphenyl-3,3'-di-t-butyl-5,5'-di-t-butoxy-2-ol [sic],
 1,1'-biphenyl-3,3'-di-t-hexyl-5,5'-dimethoxy-2-ol [sic],
 1,1'-biphenyl-3-t-butyl-5,5'-dimethoxy-2-ol [sic],
 1,1'-biphenyl-3,3'-di[2-(1,3-dioxacyclohexane)]-5,5'-dimethoxy-2-
 5 ol [sic], 1,1'-biphenyl-3,3'-diformyl-5,5'-dimethoxy-2-ol [sic]
 and 1,1'-biphenanthryl-2-ol, in particular 2-biphenylol and
 2-binaphthylol.

Examples of suitable compounds of the formula $R^1[(Q)_q]_r$ are
 10 unsubstituted aromatic compounds ($Q = H$) such as benzene,
 naphthalene, tetralin, anthracene or phenanthrene, especially
 benzene and naphthalene, monosubstituted aromatic compounds such
 as haloaromatics ($Q = Cl, Br, I$), for example halobenzene,
 halonaphthalene, especially chlorobenzene and bromobenzene, and
 15 monoalkyl- or monoarylaromatics, where alkyl or aryl may have the
 meaning already defined previously, but especially C_1 - C_8 -alkyl
 radicals or unsubstituted or substituted phenyl radicals.
 Examples of suitable monoalkylaromatics ($Q = H$) are toluene,
 ethylbenzene, n-propylbenzene, cumene, n-butylbenzene, sec-
 20 butylbenzene and tert-butylbenzene, especially toluene, cumene
 and tert-butylbenzene. Examples of suitable monoarylaromatics are
 biphenyl and substituted biphenyls.

Compounds of the formula $R^1[(Q)_q]_r$ which are likewise suitable are
 25 polysubstituted aromatic compounds such as alkyl- or
 aryl-substituted haloaromatics, polyalkyl- and/or
 polyaryl-substituted aromatic compounds and substituted or
 unsubstituted metallocenes. Examples of suitable alkyl-
 substituted haloaromatics ($Q = Cl, Br, I$) are 2-alkyl- or
 30 4-alkyl-substituted haloaromatics, where alkyl may have the
 meaning already defined previously and is, in particular,
 C_1 - C_8 -alkyl and, particularly preferably, methyl, ethyl, isopropyl
 and tert-butyl. 2-Methylchlorobenzene, 2-methylbromobenzene,
 4-methylchlorobenzene, 4-methylbromobenzene, 2-tert-butyl-
 35 chlorobenzene, 2-tert-butylbromobenzene, 4-tert-butylchloro-
 benzene and 4-tert-butylbromobenzene are particularly preferred.

Examples of suitable aryl-substituted haloaromatics ($Q = Cl, Br, I$) are 2-aryl- or 4-arylhaloaromatics, where aryl can have the
 40 meaning already defined previously and is, in particular, phenyl
 and substituted phenyl radicals and preferably phenyl, 2-tolyl,
 4-tolyl and 2,4-dimethylphenyl. Biphenyl, 9,9-dimethylxanthene
 and 4,5-dibromo-2,7-di-tert-butyl-9,9-dimethylxanthene are
 particularly preferred.

45

16

The compounds of the formula I can if required be isolated and purified by known methods such as distillation, crystallization, chromatography and the like.

- 5 A preferred area of use of the catalysts according to the invention is for the hydroformylation of olefins.

In general under the hydroformylation conditions there is formation, from the catalysts or catalyst precursors employed in
 10 each case, of catalytically active species of the general formula $H_xM_y(CO)_zL_q$ in which M is a metal of group VIII, L is a phosphonite ligand according to the invention, and q, x, y and z are integers depending on the valency and nature of the metal and on the covalence of the ligand L. It is preferred for z and q
 15 independently of one another to have a value of at least 1, e.g. 1, 2 or 3. The total of z and q is preferably from 2 to 5. It is moreover possible for the complexes to have if required at least one of the other ligands described previously in addition.

- 20 The metal M is preferably cobalt, ruthenium, rhodium, palladium, platinum, osmium or iridium and, in particular cobalt, rhodium and ruthenium.

In a preferred embodiment, the hydroformylation catalysts are
 25 prepared in situ in the reactor employed for the hydroformylation reaction. If required, however, the catalysts according to the invention can also be prepared separately and isolated by conventional processes. To prepare the catalysts according to the invention in situ, at least one phosphinite ligand of the general
 30 formula I, a compound or a complex of a metal of group VIII, where appropriate at least one other additional ligand and, where appropriate, an activator are reacted in an inert solvent under the hydroformylation conditions.

- 35 Examples of suitable rhodium compounds or complexes are rhodium(II) and rhodium(III) salts such as rhodium(III) chloride, rhodium(III) nitrate, rhodium(III) sulfate, potassium rhodium sulfate, rhodium(II) or rhodium(III) carboxylate, rhodium(II) and rhodium(III) acetate, rhodium(III) oxide, salts of rhodium(III)
 40 acid, trisammonium hexachlororhodate(III) etc. Rhodium complexes are also suitable, such as rhodium biscarbonylacetylacetonate, acetylacetonatobisethylenerrhodium(I) etc. Rhodium biscarbonylacetylacetonate or rhodium acetate are preferably employed.

Also suitable are ruthenium salts or compounds. Examples of suitable ruthenium salts are ruthenium(III) chloride, ruthenium(IV), ruthenium(VI) or ruthenium(VIII) oxide, alkali metal salts of ruthenium oxoacids, such as K_2RuO_4 or $KRuO_4$, or
 5 complex compounds of the general formula $RuX^1X^2L^1L^2(L^3)_n$, in which L^1 , L^2 , L^3 and n have the meanings indicated above and X^1 , X^2 have the meanings indicated for X (see above), e.g. $RuHCl(CO)(PPh_3)_3$. It is also possible to use the ruthenium metal carbonyls such as trisruthenium dodecacarbonyl or hexaruthenium octadecacarbonyl,
 10 or mixed forms in which CO is partly replaced by ligands of the formula PR_3 , such as $Ru(CO)_3(PPh_3)_2$, in the process according to the invention.

Examples of suitable cobalt compounds are cobalt(II) chloride,
 15 cobalt(II) sulfate, cobalt(II) carbonate, cobalt(II) nitrate, their amine or hydrate complexes, cobalt carboxylates such as cobalt acetate, cobalt ethylhexanoate, cobalt naphthoate, and the cobalt-caprolactamate complex. In this case too it is possible to employ the carbonyl complexes of cobalt, such as dicobalt
 20 octacarbonyl, tetracobalt dodecacarbonyl and hexacobalt hexadecacarbonyl.

Said compounds of cobalt, rhodium and ruthenium are known in principle and are adequately described in the literature, or they
 25 can be prepared by the skilled worker in analogy to the compounds already known.

Examples of suitable activators are Brönsted acids, Lewis acids such as BF_3 , $AlCl_3$, $ZnCl_2$ and Lewis bases.

30 The solvents preferably employed are the aldehydes which are produced on hydroformylation of the particular olefins, and the higher-boiling products of secondary reactions thereof, e.g. aldol condensation products. Other suitable solvents are aromatic
 35 compounds such as toluene, hydrocarbons or mixtures of hydrocarbons, also for diluting the abovementioned aldehydes and the aldehyde secondary products. Where the ligands are adequately hydrophilized, it is also possible to employ water, alcohols such as methanol, ethanol, n-propanol, isopropanol, n-butanol and
 40 isobutanol, ketones such as acetone and methyl ethyl ketone etc.

The ratio of the molar quantities of phosphinite ligand of the general formula I and of metal of group VIII is generally in the range from about 1:1 to 1000:1.

The invention further relates to a process for the hydroformylation of compounds which contain at least one ethylenically unsaturated [sic] double bond by reaction with carbon monoxide and hydrogen in the presence of at least one of
 5 the hydroformylation catalysts according to the invention.

Suitable substrates for the hydroformylation process according to the invention are in principle all compounds which contain one or more ethylenically unsaturated [sic] double bonds. These include,
 10 for example, olefins such as α -olefins, internal straight-chain and internal branched olefins. Examples of suitable α -olefins are ethylene, propene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene, 1-dodecene etc.

15 Suitable straight-chain internal olefins are preferably C_4 - C_{20} -olefins such as 2-butene, 2-pentene, 2-hexene, 3-hexene, 2-heptene, 3-heptene, 2-octene, 3-octene, 4-octene etc.

Suitable branched internal olefins are preferably C_4 - C_{20} -olefins
 20 such as 2-methyl-2-butene, 2-methyl-2-pentene, 3-methyl-2-pentene, branched internal heptene mixtures, branched internal octene mixtures, branched internal nonene mixtures, branched internal decene mixtures, branched internal undecene mixtures, branched internal dodecene mixtures etc.

25 Suitable olefins for the hydroformylation are additionally C_5 - C_8 -cycloalkenes such as cyclopentene, cyclohexene, cycloheptene, cyclooctene and derivatives thereof, such as their C_1 - C_{20} -alkyl derivatives with 1 to 5 alkyl substituents. Suitable
 30 olefins for the hydroformylation are additionally vinylaromatic compounds such as styrene, α -methylstyrene, 4-isobutylstyrene etc. Suitable olefins for the hydroformylation are additionally α,β -ethylenically unsaturated mono- and/or dicarboxylic acids, and their esters, monoesters and amides, such as acrylic acid,
 35 methacrylic acid, maleic acid, fumaric acid, crotonic acid, itaconic acid, methyl 3-pentenoate, methyl 4-pentenoate, methyl oleate, methyl acrylate, methyl methacrylate, unsaturated nitriles such as 3-pentenitrile, 4-pentenitrile, acrylonitrile, vinyl ethers such as vinyl methyl ether, vinyl
 40 ethyl ether, vinyl propyl ether etc., C_1 - C_{20} -alkenols, -alkenediols and -alkadienols such as 2,7-octadien-1-ol. Suitable substrates are additional di- or polyenes with isolated or conjugated double bonds. These include, for example,
 1,3-butadiene, 1,4-pentadiene, 1,5-hexadiene, 1,6-heptadiene,
 45 1,7-octadiene, vinylcyclohexene, dicyclopentadiene, 1,5,9-cyclododecatriene, and butadiene homo- and copolymers.

The hydroformylation reaction can be carried out continuously, semicontinuously or batchwise.

Reactors suitable for the continuous reaction are known to the skilled worker and are described, for example, in Ullmanns Enzyklopädie der technischen Chemie, Volume 1, 3rd edition, 1951, pp. 743 et seq.

Suitable pressure-resistant reactors are likewise known to the skilled worker and are described, for example, in Ullmanns Enzyklopädie der technischen Chemie, Volume 1, 3rd edition, 1951, pp. 769 et seq. An autoclave will generally be used for the process according to the invention and can, if required, be provided with a stirrer and be lined.

The carbon monoxide and hydrogen synthesis gas employed in the process according to the invention may have a composition varying within wide limits. The molar ratio of carbon monoxide to hydrogen is usually about 5:95 to 70:30, preferably from 40:60 to 60:40. A molar ratio of carbon monoxide to hydrogen in the region of about 1:1 is particularly preferably employed.

The temperature in the hydroformylation reaction is generally in the range from about 20 to 180°C, preferably about 50 to 150°C. The reaction is ordinarily carried out at the partial pressure of the reaction gas at the chosen reaction temperature. The pressure is generally in the range from about 1 to 700 bar, preferably 1 to 600 bar, in particular 1 to 300 bar. The reaction pressure may be varied depending on the activity of the hydroformylation catalyst according to the invention which is employed. The catalysts according to the invention based on phosphinite ligands generally allow reaction in a lower-pressure region, such as in the range from 1 to 100 bar.

The hydroformylation catalysts according to the invention can be removed from the discharge from the hydroformylation reaction by conventional processes known to the skilled worker and can generally be employed anew for the hydroformylation.

The catalysts according to the invention advantageously show high activity so that the appropriate aldehydes are ordinarily obtained in good yields. In addition, on hydroformylation of α -olefins and of internal linear olefins, they show very low selectivity for the hydrogenation product of the olefin employed.

20

The hydroformylation process according to the invention is suitable and preferred for preparing a mixture of isomeric aldehydes, in which case the compound employed for the hydroformylation contains at least one terminal double bond, 5 wherein a mixture of isomeric aldehydes which has an n/iso ratio of at least 3:1, in particular of 5:1, particularly preferably of 8:1, is obtained.

The present invention further relates to the mixture of isomeric 10 aldehydes which has an n/iso ratio of 8:1 or greater and is obtainable by this process.

The catalysts according to the invention which have been described previously and comprise chiral phosphinite ligands of 15 the formula I are suitable for enantioselective hydroformylation.

Another preferred area of use of the catalysts according to the invention is the hydrocyanation of olefins. The hydrocyanation catalysts according to the invention also comprise complexes of a 20 metal of group VIII, in particular cobalt, nickel, ruthenium, rhodium, palladium, platinum, preferably nickel, palladium and platinum, and very particularly preferably nickel. The metal is ordinarily present with a valency of zero in the metal complex according to the invention. The metal complexes can be prepared 25 as already described previously for the use as hydroformylation catalysts. The same applies to the in situ preparation of the hydrocyanation catalysts according to the invention.

Hydrocyanation catalysts according to the invention with 30 nickel(0) as metal can be prepared by reacting at least one phosphinite ligand of the formula I with nickel or a nickel compound in the presence of a reducing agent or with a nickel complex in an inert solvent. Examples of suitable nickel compounds in this case are compounds in which the transition 35 metal assumes an oxidation state of greater than zero, and which are reduced in situ in the reaction with the phosphinite ligand of the formula I, where appropriate in the presence of a suitable reducing agent. These include, for example, the halides, preferably the chlorides, and the acetates of the transition 40 metals mentioned previously. NiCl_2 is preferably employed. Examples of suitable reducing agents are metals, preferably alkali metals, such as Na and K, aluminum, zinc and trialkylaluminum compounds.

45 If complex compounds of the transition metal are employed for preparing the phosphinite-nickel(0) complexes, the transition metal preferably already has a valency of zero in these

compounds. The complexes preferably employed for the preparation have ligands which correspond to the additional ligands which have been mentioned previously in the complexes according to the invention. In this case, preparation takes place by partial or
 5 complete replacement of ligands by the phosphinite ligands of the formula I described previously.

In a suitable embodiment of the process according to the invention, the nickel complex is bis(1,5-cyclooctadiene)-
 10 nickel(0).

Examples of suitable inert solvents for preparing the nickel(0) complexes are aromatic compounds such as benzene, toluene, ethylbenzene, chlorobenzene, ethers, preferably diethyl ether and
 15 tetrahydrofuran, or haloalkanes, for example dichloromethane, chloroform, dichloroethane and trichloroethane. The temperature for this is in the range from -70°C to 150°C, preferably from 0°C to 100°C, particularly preferably at approximately room temperature.

20 If elemental nickel is employed to prepare the phosphinite-nickel(0) complexes, it is preferably in the form of a powder. The reaction of nickel and of phosphonite ligand preferably takes place in a product of the hydrocyanation
 25 reaction as solvent, e.g. in a mixture of monoolefinic C₅-mononitriles or, preferably, in 3-pentenitrile. It is also possible where appropriate to employ the ligand as solvent. The temperature is in the range from about 0 to 150°C, preferably 60 to 100°C.

30 The hydrocyanation catalysts may, where appropriate, be prepared in situ in analogy to the process described for the hydroformylation catalysts.

35 The ratio of the molar quantities of phosphinite ligand of the general formula I and metal of group VIII is generally in the range from about 1:1 to 1000:1.

The invention further relates to a process for preparing nitriles
 40 by catalytic hydrocyanation, wherein the hydrocyanation takes place in the presence of at least one of the catalysts according to the invention described previously. Olefins suitable for the hydrocyanation are generally the olefins mentioned previously as starting materials for the hydroformylation. A specific
 45 embodiment of the process according to the invention relates to the preparation of mixtures of monoolefinic C₅-mononitriles with unconjugated C=C and C≡N bonds by catalytic hydrocyanation of

1,3-butadiene or 1,3-butadiene-containing hydrocarbon mixtures and isomerization/further reaction to saturated C₄-dinitriles, preferably adiponitrile, in the presence of at least one catalyst according to the invention. When hydrocarbon mixtures are used
5 for preparing monoolefinic C₅-mononitriles by the process according to the invention it is preferred to employ a hydrocarbon mixture which has a 1,3-butadiene content of least 10% by volume, preferably at least 25% by volume, in particular at least 40% by volume.

10

To prepare mixtures of monoolefinic C₅-mononitriles which contain, for example, 3-pentenitrile and 2-methyl-3-butenitrile and which are suitable as intermediates for further processing to adiponitrile, it is possible to employ pure butadiene or
15 1,3-butadiene-containing hydrocarbon mixtures.

1,3-Butadiene-containing hydrocarbon mixtures are obtainable on the industrial scale. Thus, for example, the processing of petroleum by steam cracking of naphtha results in a hydrocarbon
20 mixture which is referred to as the C₄ cut and has a high total olefin content, about 40% being 1,3-butadiene and the remainder being monoolefins and polyunsaturated hydrocarbons plus alkanes. These streams always also contain small amounts, generally up to 5%, of alkynes, 1,2-dienes and vinylacetylene.

25

Pure 1,3-butadiene can be isolated from industrially obtainable hydrocarbon mixtures for example by extractive distillation.

The catalysts according to the invention can be employed
30 advantageously for the hydrocyanation of such olefin-containing, in particular 1,3-butadiene-containing, hydrocarbon mixtures, ordinarily even without previous purification of the hydrocarbon mixture by distillation. Olefins which are possibly present and adversely affect the efficiency of the catalysts, such as alkynes
35 or cumulenes, can be removed from the hydrocarbon mixture where appropriate before the hydrocyanation by selective hydrogenation. Suitable processes of selective hydrogenation are known to the skilled worker.

40 The hydrocyanation according to the invention can be carried out continuously, semicontinuously or batchwise. In a suitable variant of the process according to the invention, the hydrocyanation is carried out continuously. Suitable reactors for continuous reaction are known to the skilled worker and are
45 described, for example, in Ullmann's Enzyklopädie der technischen Chemie, Volume 1, 3rd edition, 1951, pp. 743 et seq. A cascade of stirred vessels or a tubular reactor is preferably used for the

continuous variant of the process according to the invention. Suitable, where appropriate pressure-resistant, reactors for the semicontinuous or continuous procedure are known to the skilled worker and are described, for example, in Ullmanns Enzyklopädie
5 der technischen Chemie, Volume 1, 3rd edition, 1951, pp. 769 et seq. An autoclave, which can be provided if required with a stirrer and be lined, is generally used for the process according to the invention.

- 10 The hydrocyanation catalysts according to the invention can be removed from the discharge from the hydrocyanation reaction by conventional processes known to the skilled worker and can generally be employed anew for the hydrocyanation.
- 15 The invention is illustrated in detail by means of the following, nonlimiting examples.

Examples

20 Low-pressure hydroformylation of 1-octene

Example 1:

2.6 mg of rhodium biscarbonylacetylacetonate (0.01 mmol), 80 mg
25 of ligand I.a according to the invention ($R^9, R^{10} = CF_3$, 0.20 mmol), 4.5 g of 1-octene (40 mmol) and 5 ml of Texanol® were reacted in a 50 ml glass autoclave with a CO/H_2 (1:1) synthesis gas mixture at 100°C under 10 bar. After a reaction time of 4 hours, the autoclave was decompressed and emptied. The mixture
30 was analyzed by GC with internal standard. The conversion amounted to 99%. The yield of nonanal isomers was 90%, and the selectivity for nonanal isomers was 90% (90.8% n-nonanal, 9.1% methyloctanal, 0.1% ethylheptanal).

35 Comparative Example 1

2.6 mg of rhodium biscarbonylacetylacetonate (0.01 mmol), 262 mg of triphenylphosphine (1.0 mmol), 10.0 g of 1-octene (90 mmol) and 10 ml of Texanol® were reacted in a 50 ml glass autoclave
40 with a CO/H_2 (1:1) synthesis gas mixture at 100°C under 10 bar. After a reaction time of 4 hours, the autoclave was decompressed and emptied. The mixture was analyzed by GC with internal standard. The conversion amounted to 100%. The yield of nonanal isomers was 88%, and the selectivity for nonanal isomers was 89%
45 (73% n-nonanal, 25% 2-methyloctanal, 2% ethylheptanal).


We claim:

1. A catalyst comprising at least one complex of a metal of group VIII with at least one uni-, bi- or multidentate phosphinite ligand of the general formula I



in which

- 15 A is a 2,2'-biphenylylene, 2,2'-binaphthylylene or 2,3-xylylene radical, which may have 1, 2 or 3 substituents selected from alkyl, alkoxy or halogen,
- 20 R¹ is alkyl, aryl or hetaryl, each of which optionally has one, two or three substituents selected from alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen, trifluoromethyl, nitro, cyano, carboxyl, carboxylate, acyl, sulfonyl, NE¹E² and alkylene-NE¹E², where E¹ and E² are identical or different and are selected from alkyl, cycloalkyl and aryl; or is a radical
- 25 of the general formula II



in which

30


- 35 X is either a C₂-C₈-alkylene bridge which is optionally interrupted by SiR^aR^b, N [sic], NR^c, O or S, in which R^a and R^b are hydrogen, alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, and R^c is hydrogen, alkyl or aryl, where aryl is optionally mono- or disubstituted by alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, optionally has one, two or three double bonds and/or is optionally fused
- 40 once, twice or three times to aryl and/or hetaryl, where the aryl or hetaryl groups have, independently of one another, optionally one, two, three or four substituents selected from alkyl, cycloalkyl, aryl, alkoxy, cycloalkyloxy, aryloxy, halogen, trifluoromethyl, nitro, cyano, acyl, carboxyl, carboxylate, NE¹E² and alkylene-NE¹E², where E¹ and E² have the meanings indicated previously, and adjacent
- 45

25

fused rings are optionally connected by $\text{SiR}^{\text{a}}\text{R}^{\text{b}}$, N
[sic], NR^{c} , O or S or by a $\text{C}_1\text{-C}_6$ -alkylene bridge
which optionally additionally carries a group
selected from $\text{SiR}^{\text{a}}\text{R}^{\text{b}}$, N [sic], NR^{c} , O or S, in which
 R^{a} , R^{b} and R^{c} are as defined above; or

is an optionally substituted metallocene bridge; and

Y is a radical of the formula III



in which


D has the meanings indicated previously for A, and

m and n are, independently of one another, 0 or 1,


or a salt thereof.

- 25 2. A catalyst as claimed in claim 1, in which X is a radical of
the formula IV.1, IV.2, IV.3, IV.4, IV.5, IV.6, IV.7 or IV.8


26




(IV.1)




(IV.2)




(IV.3)




(IV.4)




(IV.5)



(IV.6)



(IV.7)



(IV.8)

30 in which

R^2 , $R^{2'}$, R^3 and $R^{3'}$ are, independently of one another, hydrogen, alkyl, alkoxy, halogen, trifluoromethyl, nitro, cyano, acyl, carboxyl or carboxylate,

35

R^4 is hydrogen, alkyl, or aryl, which may optionally be substituted by alkyl, alkoxy, halogen, trifluoromethyl, nitro or cyano, and

40

R^5 , $R^{5'}$, R^6 , $R^{6'}$, R^7 , $R^{7'}$, R^8 , $R^{8'}$, R^{12} , $R^{12'}$, R^{13} and $R^{13'}$ have the meanings mentioned for R^2 and R^3 or are, independently of one another, selected from cycloalkyl, aryl or alkyl, which may be interrupted by an oxygen atom or substituted by a radical of the formula NE^1E^2 , where E^1 and E^2 have the meaning indicated above; or in each case two adjacent substituents R^5 , R^6 , R^7 , R^8 and/or $R^{5'}$, $R^{6'}$, $R^{7'}$, $R^{8'}$ represent, with the part of the

45

27

cyclopentadienyl ring connecting them, an aromatic or nonaromatic 5- to 7-membered carbocycle or heterocycle, where the heterocycle has 1, 2 or 3 heterogroups selected from O, N [sic], NR^c and S,

5


M is Fe, Co, Ni, Ru, Os, Rh, Mn, Cr or V,

Z^1 is O, S and NR^c or a C_2 - to C_3 -alkylene bridge which is interrupted by O, S or NR^c ,


10

Z^2 and Z^3 are, independently of one another, CH_2 , SiR^aR^b , O, S, NR^c or CR^aR^b , where R^a , R^b and R^c each have the meaning indicated above.


15 3. A catalyst as claimed in either of the preceding claims, where the phosphinite ligand of the formula I is selected from ligands of the formulae Ia to Ii



(Ia)




(Ib)




(Ic)

30



(Id)



(Ie)


40

45

28

5

10




(If)

15

20

25




(Ig)

30


35

40



(Ih)

45



(Ii)

15 in which

R^9 and R^{10} are, independently of one another, hydrogen or trifluoromethyl, and

20 R^{11} is fluorine or trifluoromethyl.

4. A catalyst as claimed in any of the preceding claims, wherein the metal of group VIII is selected from cobalt, nickel, ruthenium, rhodium, palladium and platinum.

25

5. A catalyst as claimed in any of the preceding claims, which additionally comprises at least one other ligand different from ligands of the formula I and selected from halides, amines, carboxylates, acetylacetonate, aryl- or alkylsulfonates, hydride, CO, olefins, dienes, cycloolefins, nitriles, N-containing heterocycles, aromatic and heteroaromatic compounds, ethers, PF_3 , and uni-, bi- and multidentate phosphine, phosphinite, phosphonite and phosphite ligands.

30

35

6. A process for the hydroformylation of compounds which contain at least one ethylenically unsaturated [sic] double bond, by reaction with carbon monoxide and hydrogen in the presence of a hydroformylation catalyst, wherein a catalyst as claimed in any of claims 1 to 5 is employed as hydroformylation catalyst.

40

7. A process as claimed in claim 6, employing for the hydroformylation a compound which contains at least one terminal double bond, wherein a mixture of isomeric aldehydes

45

30

with an n/iso ratio of at least 3:1, in particular 5:1, particularly preferably 8:1, is obtained.

- 5 8. A process for the hydrocyanation of compounds which contain at least one ethylenically unsaturated [sic] double bond, by reaction with hydrogen cyanide in the presence of a hydrocyanation catalyst, wherein a catalyst as claimed in any of claims 1 to 5 is employed as hydrocyanation catalyst.
- 10 9. A process as claimed in either of claims 6 or 8, wherein the hydroformylation catalyst or the hydrocyanation catalyst is prepared in situ, with at least one phosphinite ligand of the general formula I as defined in claims 1 to 5, a compound or a complex of a metal of group VIII and, where appropriate, an
15 activator being reacted in an inert solvent under the hydroformylation or hydrocyanation conditions.
- 20 10. The use of catalysts comprising a phosphinite ligand of the formula I as claimed in any of claims 1 to 5 for the hydroformylation or hydrocyanation of compounds having at least one ethylenically unsaturated [sic] double bond.

25

30

35

40

45