

SPECIFICATION

OS-9401

TITLE OF THE INVENTION

ARTIFICIAL SNOWSEED AND METHOD FOR MAKING ARTIFICIAL SNOW

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

The present invention relates to an artificial snowseed and to a method for making artificial snow. More particularly, the present invention relates to an artificial, spherical, granular snowseed of a super water-absorbing polymer which retains the original spherical form after absorption of water without sticking to each other. The spherical snowseed may be of a dry or a water-swollen form. The snowseed can be used for making artificial snow having an appearance of granules or rice-flour cakes by freezing. The resulting artificial snow exhibits good properties for gliding on skis over the slope covered with such snow, and the snow conditions may be properly adjusted to skiing.

2. Background Art

(Natural snow)

20 There have recently been a marked decrease in snowfall and an accumulation of snow. As a result, the openings of many ski resorts are often hindered. In addition, in order to prepare a well-groomed packed ski slope, the natural snow on ski slopes requires frequent packing by tracksetter because newly fallen natural snow is

25

This Sheet Has Been Replaced



- 1 -

REPLACED SHEETS SG

☒	Description	: paged		to paged	34..
☒	Claim(s)	: paged	35	to paged	36..
☒	Drawing(s)	: paged		to paged	
☒	Abstract	: paged	37	to paged	

too soft and not suitable for smooth gliding on skis. On the other hand, the snow conditions on a tracksetter-groomed trail is not still suitable for a ski racing event, and the trail has to be groomed by treading it underfoot, followed by
5 spraying water on the spread snow.

The slopes recreated by such means are very susceptible to the outside air temperature, and the quality of the snow varies widely from compact to corn with the passage of time. This is caused by sublimation and
10 condensation of water molecules inside the snow layer thereby causing a change in the structure of snow crystals. It is not easy for skiers to glide smoothly on skis over slopes covered with corn snow; thus frequent snow-grooming, e.g. breaking the frozen crust is indispensable. These attempts
15 are however still unsuccessful in giving a satisfactory results.

(Artificial snow)

Installation of snow machines has been popular in many skiing resorts to prolong the overall skiing season.
20 Snow machines fall into two groups consisting mainly of a "gun" type and a "fan" type. A method of making artificial snow by snow machines comprises atomizing compressed water into a subzero atmosphere to make fine ice particles with the aid of adiabatic expansion of compressed air or the aid of
25 cold air. The artificial snow thus produced contains 10% by



weight or more of water, and has a density of about 0.3 to about 0.4 g/cm³, and a mechanical strength of less than 1 kg/cm². The slope covered with such artificial snow is not suitable for skiing without being packed. Such artificial
5 snow changes in quality more frequently than natural snow, and in certain cases, forms corn snow having an average outer diameter of about 1 to 5 mm in a few days. Corn snow is troublesome for skiers; and hence a measure similar to those as described above is necessary to overcome the accompanying
10 problems.

A snow machine capable of shattering ice blocks by means of physical shock to make ice granules or snow flakes is also currently in use; however it is only capable of producing ice shavings or corn snow unpreferably, and it is
15 necessary to take measures to cope with the problems as described above.

Japanese Patent Publication No.63-500526 discloses a method for making artificial snow, which comprises mixing the granules of a water-swellable material, i.e. water-
20 absorbing polymer with water, and aerating the water-swollen granules to the air, followed by freezing. The snow thus produced, has an appearance of fine stiff ice, like "EISBAHN", rather than snow, and has a density of about 0.4 to 0.9 g/cm³ with a mechanical strength of about 10 to
25 several 100 kg/cm², because these properties are highly



susceptible to aerating or freezing conditions. When shattered by means of physical shock to make granular ice or snow flakes, such "Eisbahn"-shaped stiff ice produces only corn snow unpreferably. Therefore, in order to make

5 artificial snow suitable for covering ski slopes by using the above water-swellable material alone, addition of a surfactant, regulation of the particle size and the water content of snow as well as frequent grooming of the slopes are indispensable to prevent the frozen snow particles from

10 further agglomeration. Such snow is too difficult to handle for ski hill operators.

As the snow conditions on outdoor slopes are highly susceptible to the weather, indoor ski resorts that can be opened the year around have recently become popular.

15 Artificial indoor ski slopes are laid with the foregoing artificial snow, artificial ice granules, snow flakes, or artificial snow made from a water-swellable material, e.g. a water-absorbing polymer and water; however the aforesaid problems still remain unsolved in these artificial indoor ski

20 slopes.

Another indoor ski slope is produced by laying a floor with a paste comprising the aforesaid water-swellable material, e.g. water-absorbing polymer and water (blending weight ratio= about 1/80 to 1/100), followed by refrigerating

25 the whole floor to create a surface similar to those of



skating rinks. The surface is thereafter groomed while
scraping off the surface ice to make artificial snow on top
of an ice bed. In addition to the aforesaid problems, indoor
ski slopes created in this way have an inherent problem in
5 that pole plant is not easy because there is an ice layer,
like "Eisbahn", beneath the artificial snow.

The aforesaid problems can be solved by employing
the artificial snow made by refrigerating a water-swollen,
super absorbing polymer (Japanese Patent Laid-Open
10 Application Nos.4-43274 and 4-43275 to the applicant of the
invention). The artificial snow is provided in the form of
frozen granules of a water-swollen super absorbing polymer
itself or in the form of ice crystals similar to ice needles
or frost columns (Photograph 2) which are formed from the
15 water released by the swollen granules upon cooling. In this
case, the kinematic friction factor (μ_k) increases
unpreferably to about 0.04 to 0.10, compared to about 0.02 to
0.05 for natural powdery snow, as a result of the contact of
the ski base with the granules. When the kinematic friction
20 (μ_k) factor is 0.06 or more, it becomes hard to control skis,
e.g. to turn, because of the slowing-down of speed. It gives
a sense of incongruity, and spoils pleasure in gliding.

Some of the problems associated with natural snow
or conventional artificial snow for use in creating a ski
25 slope include the following: i) It is not easy to freely



adjust the snow density or strength so that it matches the particular skill or preference of skier. ii) Snow conditions vary widely over the slope with the passage of time; therefore it is hard to maintain the snow quality at its optimum. iii) Investment and maintenance costs are too high. iv) Conventional artificial snow made from a water-swellaible material (water-absorbing polymer) and water by freezing is provided as ice blocks which should be further shattered for use. v) High kinematic friction factor (μ_k).

It is accordingly an object of the present invention to provide artificial snow which has a kinematic friction factor (μ_k) similar to that of natural powdery snow and good properties for gliding over on skis, and to provide an artificial snowseed for making such snow.

SUMMARY OF THE INVENTION

The applicant of the invention has intensively investigated to solve the above-described problems, and as a result has found a new granular snowseed of a super water-absorbing polymer coated with a fluorine-containing material and/or a silicone oil, wherein the granular snowseed of the polymer can retain the original spherical form after absorption of water without sticking to each other.

In claim 1 the present invention resides in an artificial snowseed comprising granules of a super water-



absorbing polymer coated with a fluorine-containing material and/or a silicone oil, wherein said granules can retain the original spherical form after absorption of water without sticking to each other.

5 In claim 2 the present invention resides in an artificial snowseed of claim 1 wherein said fluorine-containing material is the same dispersant as used in the manufacture of said super water-absorbing polymer by a reversed-phase suspension polymerization.

10 In claim 3 the present invention resides in an artificial snowseed of claim 2 wherein said fluorine-containing material is an acrylic copolymer.

 In claim 4 the present invention resides in an artificial snowseed of claim 3 wherein said acrylic copolymer
15 contains 10 to 90% by weight of an acrylic or methacrylic ester moiety having 3 or more of fluorine atoms.

 In claim 5 the present invention resides in a method for making artificial snow which comprises the steps of: (a) swelling granules of a super water-absorbing polymer
20 in water to provide spherical water-swollen granules having an average diameter of about 0.05 to 2 mm, said water-swella-
ble granules being able to retain the original spherical form after absorption of water without sticking to each other and having a deionized water-absorbing power of
25 about 30 to 500 times its own weight, and said water-



swellable granules being further coated with a fluorine-containing material and/or a silicone oil and having an average diameter of 20 to 500 μm , and (b) freezing the water-swollen granules by at least one means selected from the

5 group consisting of the following steps:

(i) freezing the water-swollen granules on a refrigerated floor laid with refrigeration pipes,

(ii) freezing the water-swollen granules by blending them with at least one coolant selected from the group
10 consisting of dry ice, liquid carbon dioxide, and liquid nitrogen, and

(iii) freezing the water-swollen granules on a refrigerated floor laid with refrigeration pipes after blending them with natural snow, artificial snow made by a
15 snow machine, or icy snow made by shattering ice blocks, or freezing the water-swollen granules on the refrigerated floor after blending them with at least one coolant selected from the group consisting of dry ice, liquid carbon dioxide, and liquid nitrogen.

20

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a microscopic photograph of artificial snow according to the present invention.

Figure 2 is a microscopic photograph of artificial
25 snow made by a conventional process.



DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Examples of the super water-absorbing polymers suitable for the present invention include starch or cellulose base polymers; and synthetic polymers, copolymers
5 or terpolymers of acrylamide, acrylic acid, acrylic acid salt, methacrylic acid salt, styrene, vinyl ether, and the like. Among them, the preferred are a polyacrylic acid salt, a vinyl alcohol-acrylic acid salt copolymer, or a saponified isobutylene-maleic anhydride copolymer, these being provided
10 as spherical granules by a reversed-phase suspension polymerization in the presence of an organic solvent.

Any reversed-phase suspension polymerization may be employed. A typical example is a reversed-phase suspension polymerization of a solution of acrylic acid and a salt
15 thereof. The aqueous solution of acrylic acid and an acrylic acid salt thereof is prepared by partial neutralization of monomeric acrylic acid with an aqueous solution of an alkali metal salt such as sodium hydroxide, potassium hydroxide, or ammonium hydroxide. The preferred degree of neutralization
20 is within the range of from 60 to 85 % from the viewpoint of water-absorbing power and safety. Monomer concentrations in the aqueous solution are in the range of 35 to 75% by weight, preferably 40 to 70% by weight.

An unsaturated monomer capable of copolymerizing it
25 with acrylic acid or its alkali salt may be used additionally



so long as a super water-absorbing polymer can be provided.

When the reversed-phase suspension polymerization of the aqueous solution of acrylic acid and its alkali salt is carried out, a water-soluble persulfate such as potassium
5 persulfate or ammonium persulfate, or hydrogen peroxide is preferably employed as an initiator because of the self-crosslinking nature of the polymer. The amount of initiator is within the range of from 0.1 to 2.0% by weight, preferably 0.2 to 1.0% by weight based on the monomers used.

10 Examples of the aliphatic hydrocarbon solvents suitable for use in the reversed-phase polymerization include aliphatic hydrocarbons such as n-pentane, n-hexane, n-heptane, and n-octane; alicyclic hydrocarbons such as cyclohexane and methyl cyclohexane, and decalin, with the
15 preferred ones being n-hexane, n-heptane and cyclohexane.

Another requisite for preparing the super water-absorbing polymer is that the resultant polymer is crosslinked by using a crosslinking agent in the presence or in the absence of an inorganic substance.

20 Any compound having two or more of the functional groups capable of reacting them with carboxyl group or carboxylate group may be used as the crosslinking agent. Examples of the agents include, e.g. polyglycidyl ethers such as ethylene glycol diglycidyl ether, polyethylene glycol
25 diglycidyl ether, glycerine triglycidyl ether; haloepoxy



compounds such as epichlorohydrin, α -methylchlorohydrin; polyaldehydes such as glutaraldehyde, glyoxal, with the preferred crosslinking agent being ethylene glycol glycidyl ether.

5 The amount of crosslinking agent is preferably within the range of from 0.05 to 2% by weight, depending on the particular crosslinking agent or dispersant employed. When the amount is less than 0.05% by weight, the fluidity and mechanical strength of the water-swollen granules become
10 poor, and inversely when it is more than 2% by weight, the crosslinking density becomes too high, with the result of a marked decrease in water-absorbing power.

 When the crosslinking is carried out in the presence of an inorganic substance, the fluidity of the
15 resulting granules increases. Examples of the inorganic substance include white carbon, talc, hydrotalcite, and pulverized silica such as aerosol. A surfactant such as the conventional nonionic one may be used together with the inorganic substance.

20 The crosslinking agent may be added in the drying step for the resulting granules by azeotropic distillation or heating in vacuo, with the preferred step being azeotropic distillation.

 Any process to coat the surface of granules of the
25 super water-absorbing polymer with a fluorine-containing



material or silicone oil may be used. The granules of a super water-absorbing polymer may be coated with a fluorine-containing material or silicone oil by a conventional blending or mixing process. When the super water-absorbing polymer is prepared by a reversed-phase suspension polymerization, the surface coating may also be carried out simultaneously by using an aliphatic hydrocarbon solution in which the fluorine-containing material or silicone oil is dispersed as a dispersant.

10 The amount of fluorine-containing material or silicone oil used as the dispersant is within the range of from 0.1 to 10% by weight, preferably 0.5 to 3% by weight on the basis of the total amount of acrylic acid and its monomeric alkali salt. When the amount is less than 0.1% by weight, an improvement effect on the gliding properties on skis cannot be exerted sufficiently, and the dispersibility of colloid during polymerization becomes poor, inversely when it is more than 10% by weight, any additional improvement effect on the gliding properties cannot be produced, and moreover often uneconomic because extremely fine granules form.

Examples of the fluorine-containing materials suitable for the invention include polymers and copolymers obtained by a suspension (co)polymerization or solution (co)polymerization of a fluorine base compound as a monomer.



Examples of the fluorine base monomer include one such as a fluoroalkyl (meth)acrylate the fluorine atom being positioned on the moiety which does not participate in the polymerization. Another monomer is a compound the fluorine atom is positioned on the moiety which participates in the polymerization.

Example of the fluorine base monomer containing fluorine atom on the moiety which participates in the polymerization include, e.g. vinyl fluoride, vinylidene fluoride, 1-chloro-1-fluoroethylene, trifluoroethylene, chlorotrifluoroethylene, tetrafluoroethylene, hexafluoropropylene, hexafluoroisobutylene, perfluoro(methylvinylether), perfluoro(n-propylvinylether).

Examples of the fluoroalkyl (meth)acrylate include heptafluorobutyl acrylate, heptadecafluorooctyl acrylate, hexafluorobutyl methacrylate, heptadecafluorooctylethyl methacrylate, trifluoroisopropyl α -cyanoacrylate, trifluoroethyl α -chloroacrylate, 2,2,2-trifluoroethyl acrylate, 2,2,3,3-tetrafluoropropyl acrylate, 1H,1H,5H-octafluoropentyl acrylate, 1H,1H,2H,2H-heptadecafluorodecyl acrylate, 2,2,2-trifluoroethyl methacrylate, 2,2,3,3-tetrafluoropropyl methacrylate, 1H,1H,5H-octafluoropentyl methacrylate, 1H,1H,2H,2H-heptadecafluorodecyl methacrylate, and the like.

The preferred fluorine-containing material is an acrylic (co)polymer obtained from a fluoroalkyl



(meth)acrylate, more preferably an acrylic (co)polymer which contains 10 to 90% by weight of a fluoroalkyl (meth)acrylate moiety having 3 fluorine atoms. When the fluoroalkyl (meth)acrylate is less than 10% by weight, an improvement
5 effect on the gliding properties on skis cannot be exerted sufficiently, and inversely when it is more than 90% by weight, blocking sometimes occurs in the preparation step of the super water-absorbing polymer.

Examples of the monomer capable of copolymerizing
10 it with the fluoroalkyl (meth)acrylate include a (meth)acrylate or a (meth)acrylamide and/or an alkyl (meth)acrylate having at least one alkyl group. These copolymerizable unsaturated monomers have a functional group such as carboxylic acid, hydroxyl, amino, or amide group.

15 The amount of (meth)acrylate or (meth)acrylamide moiety in the aforesaid acrylic (co)polymer is preferably within the range of from 5 to 40% by weight. When the amount is less than 10% by weight, blocking sometimes occurs in the preparation step of the super water-absorbing polymer. When
20 it is more than 40% by weight, the above acrylic (co)polymer to be used as a dispersant becomes hard to dissolve in the aforesaid aliphatic hydrocarbon solvent.

The amount of other copolymerizable unsaturated monomers is preferably within the range of from 0 to 85% by
25 weight.



Any silicon oil including low-, medium- and high-viscosity products may be used. Typical examples include methyl silicone oils, fluoromethyl silicone oils, phenylmethyl silicone oils, methylhydrogen silicone oils,
5 silicone oil-polyether copolymers, and amino-modified silicone oils.

The form of the super water-absorbing polymer of the present invention is preferably in the form of granules, the more preferred form being spheres. The preferred average
10 particle size of the super water-absorbing polymer is within the range of from about 20 to 500 μm before absorption of water, and within the range of from about 0.05 to 2 mm after absorption of water. When the particle size before absorption of water is about 20 μm or less, very hard snow is
15 obtained because the granules are too fine. When it is more than about 500 μm , artificial snow in the form of corn is obtained unpreferably.

Spherical granules of a super water-absorbing polymer is preferred for the following reasons: i) It is
20 easy to handle. ii) The resulting artificial snow granules are also in the spherical form, and can provide good gliding properties. iii) It can be readily blended with natural snow.

In order to make the granules to retain the
25 original spherical form with good fluidity even after



absorption of water, it is desirable to increase the crosslinking degree of the super water-absorbing polymer by using a polyvalent epoxy or amine compound as a crosslinking agent while regulating the amount so as to produce proper
5 water-absorbing power. When the crosslinking degree is too high, the water absorbing power decreases unpreferably.

One of the good reasons why the super water-absorbing polymer according to the present invention can retain the original spherical form with good fluidity even
10 after absorption of water may be that there is little clinging water among the water-swollen granules, and the opening in the granules increases due to the sliding of the granules with each other.

A water-absorbing polymer is also known in the
15 market which becomes pasty after absorption of water. Such paste forms a large block of ice when it freezes. The ice block is not suitable as artificial snow for ski slopes without a shattering step. Of course, it is hard to maintain the shattered snow under suitable conditions for skiing as
20 described above.

Depending upon the freezing method, the average particle size and the amount of water absorbed, the artificial snowseed of the invention can be provide a series of different forms ranging from the form of finely dispersed
25 powder to the form of rice-flour cakes wherein the individual



particles contact lightly each other.

As Photograph 1 shows, when the artificial snowseed of the invention freezes, water is oozed out of the artificial snowseed, and the surface of the granules are
5 covered with frozen ice shells formed from the oozed water. Therefore, when an artificial ski slope is produced by laying it with the artificial snow of the invention, the ski base and the granules become hard to contact each other. In addition, as the surface of the granules are coated with a
10 fluorine-containing material and/or a silicone oil, the artificial snow has a kinematic friction factor (μ_k) similar to that of natural powdery snow, e.g. of about 0.02 to 0.05 (μ_k), indicating a significant improvement in lubricating properties.

15 The deionized water-absorbing power of the super water-absorbing polymer is within the range of from about 30 to 500 times its own weight, preferably about 50 to 200 times. When the water-absorbing power is less than 30 times, it becomes hard to maintain the resulting snow in desired
20 conditions because of its inability to absorb the liquid water being formed on melting. When it is more than 500 times, the gel strength after absorption of water is impaired, and the water-swollen granules become fragile against pressure unpreferably.

25 The snowseed of the invention may be shipped before



absorption of water, or as water-swollen granules.

Any absorption method may be acceptable for making the water-swollen granules of the super absorbing polymer.

The granules may be placed in water while stirring, followed

5 by allowing them to stand for several minutes. Temperature has impact on the absorption rate. As temperature becomes higher, the rate becomes higher or vice versa; therefore it is desirable to heat the water properly when the temperature is below 10°C.

10 Any method may be employed for refrigerating the snowseed of the invention. Examples of the method include refrigeration of the snowseed with the aid of a coolant such as dried ice, liquid nitrogen, liquid air, or liquid carbon dioxide while mixing. A typical method comprises placing the

15 snowseed on a refrigerated floor laid with refrigeration metal pipes. Another method comprises using the aforesaid snow-falling or snow-making machine. The most preferred method may be selected on the desired snow quality. The refrigerating method by using liquid nitrogen, liquid air or

20 liquid carbon dioxide is preferably accepted because these liquid coolants are mixed readily with the water-swollen granules of a super water-absorbing polymer, and the snowseed may be refrigerated in a short period of time by the aid of vaporization latent heat of these coolants. Other coolants

25 similar to these may be also employed, with liquid carbon



dioxide being preferred. Liquid carbon dioxide exhibits a good refrigerating effect, and inexpensive and easy to handle and get.

A typical method of making snow of the invention comprising the steps of: swelling the water-swella-
ble granules of a super water-absorbing polymer in water until water-swollen granules having an average particle size of about 0.05 to 2 mm can be obtained, wherein the water-swella-
ble granules have an average particle size of about 20
10 to 500 μ m and a deionized water-absorbing power of about 30 to 500 times its own weight, and can retain the original spherical form after absorption of water without sticking to each other, mixing the water-swollen granules with natural snow, artificial snow made by a snow-falling machine, or icy
15 snow made by shattering ice blocks, and refrigerating the mixture by blending it with liquid carbon dioxide. In this case, the water-swollen granules alone may be refrigerated.

Liquid carbon dioxide is obtained from the market. Liquid carbon dioxide has a vaporization latent heat of 15.1
20 Kcal/Kg (at 30°C), 48.1 Kcal/Kg (at 10°C), and 56.1 Kcal/Kg (at 0°C). The latent heat is utilized favorably for cooling or refrigerating.

Liquid carbon dioxide is manufactured by liquefying gaseous carbon dioxide at a pressure of about 40 atm under
25 cooling. Resources of carbon dioxide are natural gas, off-



gas from ammonium manufacturing plants, off-gas from petroleum refining and ethylene manufacturing plants. Other off-gas or tail gas evolved in petrochemical plants or steel works may also be used as the source.

5 Any method, such as manual labor or a mechanical automatic means, may be employed for mixing the water-swollen granules of a super water-absorbing polymer with liquid carbon dioxide, for freezing the mixture, and for laying the resulting powdery artificial snow over a floor of an indoor
10 ski slope. Although the aforesaid snow-falling or snow-making machine may be employed, a quick-freezing method under the direct contact of liquid carbon dioxide with the water-swollen granules may be preferably employed for this purpose.

 Any amount of carbon dioxide or coolant may be
15 employed so far as the temperature of the resulting artificial snow is within the range of from about 0 to minus 30°C. The preferred temperature will depend on various conditions.

 Any known method for mixing the water-swollen
20 granules of a super water-absorbing polymer with natural snow and the like may be used. The granules/snow ratio is preferably within the range of 99/1 to 1/99 by weight, more preferably 99/2 to 20/80, depending on the purpose.

 Ski slopes may be laid with the artificial snow
25 alone made from the snowseed of the invention. Such



independent use makes the slope easy to produce and maintain. Natural snow, artificial snow or icy snow made by other methods may be properly blended.

In producing an artificial ski slope, the floor may
5 be laid with snow, e.g. in the form of rice-flour cakes,
followed by laying the surface with powdery snow, whereby a
ski slope troubleless and easy to plant poles can be
produced.

The snowseed of the invention may be recycled for
10 reuse after drying.

In addition, it is environmentally safe to dispose
the used snowseed because the snowseed of the invention is
photodecomposable and/or biodegradable; however a known
accelerator, catalyst, additive may blended, added,
15 impregnated or coated, if early degradation is desired, to
accelerate photodecomposition or biodegradation. The
snowseed of the invention are not harmful to the health;
therefore these additives should be properly selected after
due consideration of safety first.

20 The snowseed of the invention may be colored with
known pigments or dyes. The artificial snow made from the
colored artificial snowseed looks beautiful, and a commercial
value may be added to it. For example, discrimination of ski
slopes by coloring for beginners or experts may add a more
25 fun.



Further, other additives, e.g. perfume, fragrance, or aroma may be added.

An antioxidant, ultraviolet absorber, fluorescent agent, nucleating agent, extender, friction improver, and the like may also be added so far as the properties of the resulting snow are not impaired.

The invention is further illustrated by the following examples which are set forth by way of illustration only and not by way of limitation.

10

[EMBODIMENT]

Performance test procedures in the following examples are as follows:

15 (Deionized Water-Absorbing Power)

The dry granules of a polymer in an amount of 0.5 g are dispersed in 1000 ml of deionized water and allowed to stand for about 24 hours. The resulting water-swollen granules are filtered through a 60-mesh wire net. The water-swollen granules are weighed to measure the weight (W). The water-absorbing power is determined by dividing (W) by (W_0), wherein W_0 is the weight of dry granules.

20

(Fluidity after Absorption of Water)

25

The dry granules of a polymer in an amount of 1.0 g



are added to 50 ml of deionized water to saturate. Fluidity are evaluated visually under gentle vibration and reported as O (for good), x (for bad) or Δ (for normal).

5 (Bulk Density after Absorption of Water)

Into a 100-ml beaker are added the water-swollen granules of a super water-absorbing polymer in an amount of about 20g at a time until the beaker is packed with the granules up to the 100 cc marked line while holding the
10 surface down. The bulk density is determined by dividing the weight by the volume.

(Density of Artificial Snow after Freezing)

Frozen snow with known volume is weighed. The
15 density (g/cm^3) is determined by dividing the weight by the volume. When the sample snow is soft, a thin stainless steel box with known volume for sticking it into snow is conveniently used for the purpose; inversely when the sample snow is hard, the volume calculated by measuring the
20 dimensions of a snow cube made by sawing the frozen snow is used instead.

(Mechanical Strength of Artificial Snow after Freezing)

A disc in an adapter is released to fall straight
25 on to an artificial snow sample. Repeat the procedure by a



Kinoshita's Hardness Tester (Trade Name) while changing the adapter so that the disc can sink to a depth of about 7 to 30 mm beneath the surface. The strength is calculated by using a conversion table. In case of powdery snow, the feeling of
5 the snow sample is noted, e.g. by "powdery".

(Kinematic Friction Factor μ_k after Freezing)

The water-swollen granules of a water-absorbing polymer are spread in a layer to a depth of about 5 cm over
10 an inclined floor (10°) laid with flexible plastic cooling pipes having an inner diameter of 5 mm, followed by refrigerating the layer by circulating brine at minus 20°C for about 20 hours to make artificial snow. A ski slope (13 m in length) is produced by treading the snow. The time (t)
15 required for gliding over the slope on practical skis coated with only base wax alone is measured. The kinematic friction factor is calculated from the following formula:

$$\mu_k = (g \sin \theta - 2x/t^2) / g \cos \theta$$

wherein,

g : kinematic accelerated velocity (9.80 m/sec^2)
20 θ : inclined angle of slope (10°)
x : length of slope (13 m)
t : time required (sec)

[Preparative Examples 1-8]



(Preparative Example 1)

Spherical Granules of Super Water-Absorbing Polymer and the Properties of Artificial Snowseed and Snow

Into a 500 ml-separable flask equipped with a
5 stirrer, a reflux condenser, a dropping funnel, a
thermometer, and a nitrogen inlet tube was fed 150 g of
deionized water, followed by addition of 0.2 g of a partially
saponified polyvinyl alcohol (available from NIPPON GOSEI
KAGAKU K.K., under Trade Mark GH-23). After melting of the
10 contents, the flask was purged with a nitrogen stream.

Separately, into an Erlenmeyer flask were fed 25.0g
of heptadecafluorodecyl methacrylate (available from Osaka
Organic Chemical Industry Co. Ltd., under Trade Mark VISCOAT
V-#17FM), 5.0g of hydroxyethyl methacrylate (HEMA), 5.0g of
15 methacrylic acid (MMA), 15.0g of methyl methacrylate (MMA),
and 1.0g of azobisdimethylvaleronitrile to dissolve. The
resulting mixture was added dropwisely to the aforesaid
separable flask over a period of one hour while bubbling a
nitrogen stream. After holding for 5 hours at 65°C to
20 complete reaction, the solid matter was filtered after
cooling and washed with water, followed by drying it in vacuo
whereby a dispersant (a fluorine-containing acrylic
copolymer) in the form of beads was obtained.

The dispersant in an amount of 4.32g and n-hexane
25 in an amount of 360.7g were added to a 1000-ml separable



flask fitted with a stirrer, a reflux condenser, a dropping funnel, a thermometer and a nitrogen inlet tube. The contents were heated to 50°C to disperse and dissolve, followed by nitrogen purging.

5 Separately, acrylic acid in an amount of 72.0g was neutralized with 32.2g of sodium hydroxide dissolved in 103.6g of deionized water in an Erlenmeyer flask, followed by further addition of potassium persulfate (0.24g) while dissolving it at room temperature. The aqueous monomer
10 solution was added dropwisely to the aforesaid separable flask while stirring at 300 rpm under the bubbling of a nitrogen stream over a period of one hour. After reflux for two hours, 0.1g of 30%-hydrogen peroxide was added and the reflux was further continued for a period of one hour to
15 complete polymerization. Thereafter, 0.73g of ethylene glycol diglycidyl ether was added, and the contents were dehydrated by azeotropic distillation, filtered and dried in vacuo whereby a super water-absorbing polymer in the form of white beads, already coated with the above-described
20 fluorine-containing acrylic copolymer, was obtained.

(Preparative Examples 2 to 8)

Similarly, a dispersant (a fluorine-containing acrylic copolymer) of the composition as set forth in Table 1
25 was prepared. A super water-absorbing polymer in the form of



white beads already coated with the fluorine-containing acrylic polymer was obtained by using the dispersant.

Test results of the resulting polymers for the
5 water-absorbing power, average particle size, fluidity and bulk density after absorption of water, snow density and structure of snow crystals (whether ice crystals in the form of shells are present or not) are also set forth in Table 1.

In this case, the water-swollen particles (absorbed
10 water is 50 times its own weight) were spread in a layer to a depth of 50 mm over a copper plate (2 mm thick) equipped with brine pipes, followed by refrigeration by circulating brine at minus 25 °C for 20 hours to make the sample snow.

15 [Comparative Preparations 1 to 4]

Spherical Granules of Super Water-Absorbing Polymer and Properties of Artificial Snowseed and Snow

(Comparative Preparation 1)

20 A dispersant (an acrylic copolymer which does not contain a fluorine moiety) of the composition set forth in Table 1 was prepared in a similar manner. A super water-absorbing polymer in the form of white beads was obtained by using the dispersant. The test results of the resulting
25 polymer for the water-absorbing power, average particle size,



fluidity and bulk density after absorption of water, density and structure of the artificial snow (whether ice crystals in the form of shells are present or not) are also set forth in Table 1.

5

(Comparative Preparation 2)

A dispersant (an acrylic copolymer which contains a fluorine moiety) of the composition set forth in Table 1, the composition being not within the scope of the present
10 invention, was prepared in a similar manner. A water-absorbing polymer in the form of white beads already coated with the fluorine-containing acrylic copolymer was obtained. The test results of the polymer for the water-absorbing power, average particle size, fluidity and bulk density after
15 absorption of water, snow density and structure of snow crystals (whether ice crystals in the form of shells are present or not) are also set forth in Table 1.

(Comparative Preparation 3)

20 Attempts to prepare a super water-absorbing polymer by using a dispersant (a fluorine-containing acrylic copolymer) of the composition outside the range of that of the method of the present invention were unsuccessful.

25 (Comparative Preparation 4)

This Sheet Has Been Replaced



A super water-absorbing polymer in the form of crushed pieces was obtained by using a dispersant (available from NIPPON SHOKUBAI K.K., under Trade Name Aqualic CAW) in a similar manner.

5

The test results of the polymer for water-absorbing power, bulk density after absorption of water, snow density and structure of snow crystals(whether ice crystals in the form of shells are present or not) are set forth in Table 1.

This Sheet Has Been Replaced



[TABLE 1]

		Dispersant						Artificial Snowseed					Artificial Snow	
		Composition of dispersant (acrylic copolymer)						Water- absorbing power (times)	Average particle size (μm)		Fluidity after absorption of water	Bulk density after absorption of water	Snow density (g/cm^3)	Snow structure (whether ice shells are present or not present)
		V- #17FM (wt%)	LA (wt%)	HEMA (wt%)	MAA (wt%)	DMMA (wt%)	MMA (wt%)		before absorption of water	after absorption of water (50 times)				
Preparative Example	1	50	-	10	10	-	30	80	100	400	○	0.76	0.35	present
	2	50	-	10	10	-	30	300	100	400	△	0.82	0.42	present
	3	50	-	10	10	-	30	90	30	100	○	0.78	0.30	present
	4	50	-	10	10	-	30	90	400	1500	○	0.75	0.38	present
	5	15	35	10	10	-	30	90	100	400	○	0.74	0.29	present
	6	80	-	10	10	-	-	100	100	400	○	0.76	0.36	present
	7	50(V- #8FM)	-	10	10	5	30	100	100	400	○	0.76	0.40	present
	8	30(V- #4F)	20	10	10	-	30	90	100	400	○	0.74	0.33	present
Comparative Preparations	1	-	50	10	10	-	30	80	100	400	○	0.74	0.22	not present (needles)
	2	5	45	10	10	-	30	90	100	400	○	0.75	0.23	not present (needles)
	3	95	-	5	-	-	-	impossible to prepare a water- absorbing polymer						
	4	Aqualic CAW(Nippon Shokubai Co.)						260	150-300 crushed pieces			0.91	0.82	ice plates

V-#17FM : Heptadecafluorodecyl methacrylate
 V-#8FM : Octafluoropentyl methacrylate
 V-#4F : Tetrafluoropropyl acrylate
 LA : Lauryl acrylate

HEMA : Hydroxyethyl methacrylate
 DMMA : Dimethylaminoethyl methacrylate
 MMA : Methyl methacrylate
 MAA : Methacrylic acid

(Production of Artificial Skiing Slope)

Example 1

The water-swollen granules (absorbed water is 50 times its own weight) of the super water-absorbing polymer prepared in Preparative Example 1 were spread in a layer (about 5 cm in thickness) over an inclined floor (10°) laid with flexible plastic brine pipes having an inner diameter of about 5 mm.

When brine was circulated at minus 20°C for about 20 hours, the polymer layer froze thereby producing powdery artificial snow. A snow-covered slope suitable for gliding on skis was recreated by treading the snow. The test results of the artificial snow for the shape, density, hardness and kinematic friction factor on the slope are set forth in Table 2.

Example 2

The water-swollen granules (absorbed water is 120 times its own weight) of the super water-absorbing polymer prepared in Preparative Example 1 were spread in a layer (about 5 cm in thickness) over an inclined floor (10°) in a similar manner as Example 1.

When brine was circulated at minus 20°C for about 20 hours, artificial snow was produced in layers, i.e. powdery snow on top of an ice bed. A snow-covered ski slope



suitable for gliding over it on skis was recreated by treading the snow. The test results of the artificial snow for the shape, density, hardness and kinematic friction factor on the slope are set forth in Table 2.

5

Comparative Example 1

The water-swollen granules (absorbed water is 50 times its own weight) of the water-absorbing polymer prepared in Comparative Preparation 1 were spread in a layer (about 5
10 cm in thickness) over an inclined floor (10°) in a similar manner as Example 1.

When brine was circulated at minus 20°C for 20 hours, the layer froze. Powdery artificial snow was produced. A snow-covered ski slope was recreated by treading
15 the snow. The test results of the snow for the shape, density, hardness and kinematic friction factor on the slope are set forth in Table 2.

Comparative Example 2

20 The water-swollen granules (absorbed water is 120 times its own weight) of the super water-absorbing polymer prepared in Comparative Preparation 1 were spread in a layer (about 5 cm in thickness) over an inclined floor (10°) in a similar manner as Example 1.

25 When brine was circulated at minus 20°C for 20



hours, the layer froze. Powdery snow on top of an ice bed was produced. A snow-covered ski slope was produced by treading the snow. The test results of the snow for the shape, density, hardness and kinematic friction factor on the
5 slope are set forth in Table 2.

Comparative Example 3

Attempts to recreate a snow-covered slope by laying the water-swollen granules of the water-absorbing polymer
10 prepared in Comparative Preparation 4 were unsuccessful. Table 2 shows the results. Any snow-shape matter could not obtained.



[TABLE 2]

	Artificial snowseed	Absorbed water (times)	Form of snow	Snow density on slope (g/cm ³)	Hardness on slope (kg/cm ³)	Kinematic friction factor (μ_k)
Example 1	Preparative Example-1	50	Powdery snow	0.33	3~5	0.03~0.06
Example 2	Preparative Example-1	120	Powdery snow on top of an ice bed	0.33	3~5	0.02~0.04
Comparative Example 1	Comparative Preparation-1	50	Powdery snow	0.28	2~5	0.06~0.10
Comparative Example 2	Comparative Preparation-1	120	Powdery snow on top of an ice bed	0.35	3~4	0.05~0.08
Comparative Example 3	Comparative Preparation-1		Impossible to make snow			

This Sheet Has Been Replaced





WHAT IS CLAIMED IS:

1. An artificial snowseed comprising granules of a super water-absorbing polymer coated with a fluorine-containing material and/or a silicone oil, wherein said granules can
5 retain the original spherical form after absorption of water without sticking to each other.
2. An artificial snowseed according to claim 1 wherein said fluorine-containing material is the same dispersant as used
10 in the manufacture of granules of said super water-absorbing polymer by a reversed-phase suspension polymerization.
3. An artificial snowseed according to claim 2 wherein said fluorine-containing material is an acrylic copolymer.
15
4. An artificial snowseed according to claim 3 wherein said acrylic copolymer contains 10 to 90% by wight of an acrylic or methacrylic ester moiety having three or more of fluorine atoms.
20
5. A method for making artificial snow which comprises the steps of:
 - (a) swelling granules of a super water-absorbing polymer in water to provide spherical water-swollen granules
25 having an average diameter of about 0.05 to 2 mm, said water-





swellable granules being able to retain the original spherical form after absorption of water without sticking to each other and having a deionized water absorbing power of about 30 to 500 times its own weight, and said water-

5 swellable granules being further coated with a fluorine-containing material and/or a silicone oil and having an average diameter of 20 to 500 μm before absorption of water, and

(b) freezing the water-swollen granules by at least one
10 means selected from the group consisting of the steps:

(i) freezing the water-swollen granules on a refrigerated floor laid with refrigeration pipes,
(ii) freezing the water-swollen granules by
15 blending them with at least one coolant selected from the group consisting of dry ice, liquid carbon dioxide, and liquid nitrogen, and
(iii) freezing the water-swollen granules on a refrigerated floor laid with refrigeration pipes
after blending them with natural snow, artificial
20 snow made by means of a snow machine, or icy snow made by shattering ice blocks, freezing the water-swollen granules on the refrigerated floor after
blending them with at least one coolant selected
25 from the group consisting of dry ice, liquid carbon dioxide, and liquid nitrogen.

