HEAT TREATED FISCHER-TROPSCH CATALYST PARTICLES

This invention relates to catalysts. More particularly the invention relates to a method of making breakage resistant self-supported precipitated iron-based Fischer-Tropsch catalyst particles, to a method of making self-supported precipitated iron-based Fischer-Tropsch catalyst particles having superior synthesis performance or activity, to catalyst particles made according to the methods, and to the use of said catalyst particles in a slurry bed Fischer-Tropsch reactor.

BACKGROUND OF THE INVENTION

US Patent Nos. 5324335 and 5504118 disclose the production of roughly spherical iron-based Fischer-Tropsch catalyst particles having diameters in the range of between 1 and 50 microns which are annealed by heating in air at about 316°C (600°F) to drive off residual moisture and to stabilise the catalyst. The annealing step i.e. the heating and gradual controlled cooling, converts the Goethite to Hematite whereafter the catalyst may be activated and used. According to these patents, the annealing does not lead to a breakage resistant or a superior performance catalyst particle.

South African Patent No. 90/7530 discloses the production of an iron-based Fischer-Tropsch catalyst including from 1 to 80% by mass of activated carbon. This catalyst shows improved breakage resistance over conventional catalyst, particularly where the particle diameters are below about 45 micron. The catalyst particle of this patent does not have superior synthesis performance and is expected to hydrothermally sinter at about 300°C.

A need thus exists for breakage resistant iron-based Fischer-Tropsch catalyst particles, in particular for use in a low temperature Fischer-Tropsch process, such as that carried out in a slurry bed reactor, for the production of, amongst others, wax and other syncrudes, as well as chemicals. The breakage resistant self-supported precipitated iron-based Fischer-Tropsch catalyst particles will ideally inhibit the formation of catalyst fines in the reactor thereby maintaining the performance of the reactor and reduce the contamination of down stream processes and catalysts by the catalyst fines.

In this specification, unless the context clearly indicates to the contrary, the term "fines" when used in relation to catalysts and catalyst particles is to be understood to mean particles which due to their dimensions, when present at a concentration of about 30% of the total catalyst, tend to reduce the performance of the solid separation system of a Fischer-Tropsch slurry bed reactor. Typically fines have a diameter of less than about 45 microns, usually about 22 microns.

A further long felt need which exists is that for self-supported precipitated iron-based Fischer-Tropsch catalyst particles having superior synthesis performance or activity, in particular for use in a low temperature Fischer-Tropsch process, such as that carried out in a slurry bed reactor, for the production of wax and other syncrudes, as well as chemicals.

BRIEF SUMMARY OF THE INVENTION

It is well expected that heat treatment of self-supported precipitated catalyst particles has a negative effect on the activity thereof. In particular, the catalyst particle surface area and pore volume are likely to be reduced at temperatures above 250°C. Those skilled in the art therefore generally tend to avoid such heat treatment of such Fischer-Tropsch catalyst material.

Surprisingly it has now been found that the breakage resistance and the synthesis performance or activity of self-supported precipitated iron-based Fischer-Tropsch catalyst particles can be increased by the heat treatment thereof at temperatures of at least 250°C.

Accordingly, the invention provides a method of producing self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said particles being breakage resistant and thus inhibiting the formation of catalyst fines, the method including the heat treatment of the said particles at a temperature of at least 250°C.

The heat treatment may be calcination of the said particles at a temperature of at least 250°C.

The heat treatment of the said catalyst particles may be carried out at a temperature of between 250 °C and 500 °C, preferably between 320 °C and 500 °C, more preferably between 360 °C and 390 °C, most preferably at 380°C.

According to a second aspect of the invention, there is provided a method of producing self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed process, the catalyst particles having a superior synthesis performance or activity under low temperature Fischer-Tropsch slurry-bed operating conditions, the method including the heat treatment of the said catalyst particles at a temperature of at least 250 °C.

The heat treatment temperature of the method may be between 250 °C and 500°C, preferably between 320°C and 500°C, more preferably between 360°C and 390°C, most preferably 380°C.

Typically the said catalyst particles are maintained at the heat treatment temperature for at least 0.1 hours, preferably between 0.2 and 12 hours, more preferably between 0.5 and 4 hours.

According to a further aspect of the invention there are provided self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said catalyst particles being produced according to a method of heat treatment of the said catalyst particles as described above.

According to yet a further aspect of the invention, there is provided a method of maintaining the performance of a solid separation system of a Fischer-Tropsch process slurry bed reactor where a reduction in performance is caused by an increase in catalyst particle fines in the slurry bed reactor, the method including the use of the catalyst particles as described above.

According to yet a further aspect of the invention, there is provided a process for synthesis of syncrudes and/or chemicals, for example, waxes, the process comprising the step of contacting a suitable synthesis gas, at suitable temperatures and pressures in a Fischer-Tropsch slurry-bed reactor, with self-supported precipitated iron-based Fischer-Tropsch catalyst particles as described above.

The process may be carried out in a suitable vessel, with unreacted reactants and gaseous product being withdrawn above the slurry bed, and separated liquid product also being withdrawn from the vessel.

Typical suitable operating temperatures for the process are temperatures in the range 160°C to 280°C, or even higher for production of lower boiling point product.

Typical suitable operating pressures are pressures in the range 18 Bar to 50 Bar.

DETAILED DESCRIPTION OF THE INVENTION

The invention will now be illustrated by means of the following non-limiting examples:

EXAMPLE 1

This example illustrates that the heat treatment of self-supported precipitated iron-based Low Temperature Fischer Tropsch catalyst particles for slurry bed application results in an increase in the mechanical strength of the said catalyst.

For a laboratory microscale operation, 250 grams of pilot plant and commercially prepared catalyst was placed in a porcelain dish in a muffle furnace. The furnace was subsequently heated to the desired heat treatment temperature at a heating rate of 1°C/min. The heat treatment or calcination temperature (as indicated in Table 1 below) was maintained for 4 hours after which the furnace was allowed to cool down to below 100°C.

For larger scale operation the catalyst was fed from a hopper at room temperature to a portable pilot plant scale rotary kiln. This kiln had a refractory lining and was electrically heated. The dimensions of this equipment were as follows: length=2.1m, diameter=0.47m, inclination=2°, rotational speed=1rpm. The average temperature inside the kiln was controlled at 385°C. The feed rate was varied around 30 kg/h which resulted in a residence time of close to 1 hour. 1500 kg of catalyst was heat treated in this manner.

A sample of catalyst particles that were heat treated according to the manner described above was subjected to a Jet Impingement test. In this test a jet of air is used to impinge fresh catalyst particles against a plate. The smaller than 22 micron fraction of jet impinged sample is normally taken as a measure of the catalyst particle mechanical strength. Table 1 shows the results that were achieved from this test. Standard pilot plant prepared catalyst particles, and standard commercially prepared catalyst particles were used as reference materials.

Table 2 also reflects the results obtained from a repeated jet impingement test conducted on a sample that was heat treated at 300°C. Repeated jet impingement results indicated that the heat treated catalyst particles are stronger even after the initial break-up. It can be concluded that heat treatment induces strength to the whole particle, and not only to the outer shell of the particle.

EXAMPLE 2

This example illustrates that heat treatment of standard self-supported precipitated iron based Low Temperature Fischer Tropsch slurry bed catalyst particles does not alter the iron phase composition nor the crystallinity of the said catalyst particles; but rather promotes the enhancement of the catalyst particles' mechanical strength.

The phase composition and relative crystallite size of both the untreated standard catalyst particles and the heat treated samples were determined by Mössbauer spectroscopy at 4.2 K. The parameters are presented in Table 3.

Both samples can be described as highly dispersed Fe(III)oxide. The Fe-phase has been identified as α-Fe_2O_3. The particles display superparamagnetic behaviour and from the quadropole splitting parameter the size of the primary particles was estimated as between 2 and 4 nm.

At 77K the heat treated sample shows a slight increase in the Δ value, indicating a corresponding decrease in the primary particle size. Based on these results it would seem as if the heat treatment causes a restructuring or reordering of the ions making up the primary particle, thus leading to a state of lower energy i.e. a stronger particle.

EXAMPLE 3

This example illustrates that heat treatment of the catalyst particles results in a major improvement of the solid separation system performance of said catalyst particles as experienced in a semi-works pilot plant reactor.

The liquid product recovery rate as a function of cycle number for a synthesis run with untreated catalyst particles is depicted in Graph 1. The separation rate levels obtained from a synthesis run operating with these standard catalyst particles only reached a maximum of 350 relative units per hour.

Data for a similar synthesis run with heat treated catalyst is presented in Graph 2. The average liquid product recovery rate is clearly above 1000 relative units per hour.

EXAMPLE 4

This specific example illustrates that calcining or heat treating standard self-supported precipitated iron-based Low Temperature Fischer-Tropsch catalyst particles for slurry bed application results in a significant reduction of the amount of fines that the catalyst particles generate under normal Fischer-Tropsch synthesis conditions.

Particle size distributions of representative on line catalyst particle samples were obtained for periods when untreated and heat treated catalyst particles were run respectively as outlined in example 3 above. A comparison of the catalyst fines content is presented in Table 4. The heat treated catalyst clearly shows a dramatic decrease in the amount of fines present in the reactor.

Scanning electron micrographs of the above mentioned untreated and heat treated on-line catalyst particle samples are presented in Micrographs 1 and 2 respectively. The absence of fine catalyst particles in the heat treated sample is once again obvious for the heat treated version.

EXAMPLE 5

This example shows that there is a marked increase in activity of standard self-supported precipitated iron-based Fischer-Tropsch catalyst particles upon heat treatment. This is elegantly illustrated in Graph 3. The catalyst activity shows a continuous increase after the change to heat treated catalyst particles which is indicated by a vertical bar in Graph 3.

EXAMPLE 6

This example illustrates that removal of residual moisture from freshly prepared catalyst particles does not lead to mechanically stronger catalyst particles.

A sample of untreated standard catalyst particles was treated in a vacuum oven at 100°C until the moisture content was half the original value. Both the untreated and the vacuum dried samples were subsequently subjected to a Jet Impingement (JI) test in order to measure their mechanical strength. The results are compared with a heat treated example in Table 5.

* C L M S *

CLAIMS

1. A method of producing self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said particles being breakage resistant and thus, in-use, inhibiting the formation of catalyst fines, the method including the heat treatment of the said particles at a temperature of at least 300°C.

2. A method as claimed in claim 1 wherein the heat treatment of the said catalyst particles is carried out at a temperature of between 320 °C and 500 °C.

3. A method as claimed in claim 2, wherein the heat treatment of the said catalyst particles is carried out at a temperature of between 360 °C and 390 °C.

4. A method as claimed in claim 3, wherein the heat treatment of the said catalyst particles is carried out at a temperature of 380 °C.

5. A method of producing self-supported precipitated iron-based Fischer-Tropsch catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said catalyst particles having superior synthesis performance or activity under low temperature Fischer-Tropsch operating conditions, the method including the heat treatment of the said catalyst particles at a temperature of at least 300 °C.

This Sheet Has Been Replaced

THIS SHEET HAS BEEN REPLACED

6. A method as claimed in claim 5, wherein the heat treatment temperature is between 320 °C and 500 °C.

7. A method as claimed in claim 6, wherein the heat treatment temperature is between 360 °C and 390 °C.

8. A method as claimed in claim 6, wherein the heat treatment temperature is 380 °C.

9. A method as claimed in any one of the preceding claims, in which the said catalyst particles are maintained at the heat treatment temperature for at least 0.1 hours.

10. A method as claimed in claim 9, in which the said catalyst particles are maintained at the heat treatment temperature for between 0.5 and 4 hours.

11. A method of producing self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said catalyst particles having superior synthesis performance or activity under low temperature Fischer-Tropsch operating conditions and being breakage resistant and thus, in-use, inhibiting the formation of catalyst fines, the method including the heat treatment of the said particles at a temperature of at least 300°C.

This Sheet Has Been Replaced

THIS SHEET HAS BEEN REPLACED

12. A method as claimed in claim 11, wherein the heat treatment temperature is between 320 °C and 500 °C.



13. A method as claimed in claim 12, wherein the heat treatment temperature is between 360 °C and 390 °C.

14. A method as claimed in claim 13, wherein the heat treatment temperature is 380 °C.

15. Self-supported precipitated iron-based Fischer-Tropsch catalyst particles for use in a Fischer-Tropsch slurry-bed process, which particles are produced according to a method as claimed in any one of claims 1 to 14.

16. A method of maintaining the performance of a solid separation system of a Fischer-Tropsch process slurry-bed reactor where reduction in performance is caused by an increase in catalyst particle fines in the slurry-bed reactor, the method including the use of the said catalyst particles as claimed in claim 15.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN REPLACED

17. A process for synthesis of syncrudes and/or chemicals, the process comprising the step of contacting a suitable synthesis gas, at suitable temperatures and pressures in a Fischer-Tropsch slurry-bed reactor, with self-supported precipitated iron-based Fischer-Tropsch catalyst particles as claimed in claim 15.



18. A method of producing self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said particles being breakage resistant and thus, in-use, inhibiting the formation of catalyst fines, as claimed in claim 1, substantially as herein described and illustrated.

19. A method of producing self-supported precipitated iron-based Fischer-Tropsch catalyst particles for use in a Fischer-Tropsch slurry-bed process, the said catalyst particles having a superior synthesis performance or activity under low temperature Fischer-Tropsch operating conditions, as claimed in claim 5, substantially as herein described and illustrated.

20. Self-supported precipitated iron-based Fischer-Tropsch catalyst particles for use in a Fischer-Tropsch slurry-bed process as claimed in claim 15, substantially as herein described and illustrated.

This Sheet Has Been Replaced



THIS SHEET HAS BEEN REPLACED

21. A method for maintaining the performance of a solid separation system of a Fischer-Tropsch process slurry-bed reactor as claimed in claim 16, substantially as herein described and illustrated.



22. A process for synthesis of syncrudes and/or chemicals, substantially as herein described and illustrated.

23. A new method of producing self-supported precipitated iron-based catalyst particles for use in a Fischer-Tropsch slurry-bed, new self-supported iron-based catalyst particles, a new process for synthesis of syncrudes and/or chemicals, or a new method of maintaining the performance of a solid separation system of a Fischer-Tropsch process slurry bed reactor, substantially as herein described.

This Sheet Has Been Replaced

