

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷: F41H 1/02	A1	(11) International Publication Number: WO 00/08411 (43) International Publication Date: 17 February 2000 (17.02.00)
(21) International Application Number: PCT/EP99/05574 (22) International Filing Date: 30 July 1999 (30.07.99) (30) Priority Data: 98114608.7 4 August 1998 (04.08.98) EP (71) Applicants (for all designated States except US): ARAMID PRODUCTS GMBH [DE/DE]; Kasinostrasse 19-21, D-42097 Wuppertal (DE). FMS ENTERPRISES LTD. [IL/IL]; P.O. Box 18077, 61180 Tel Aviv (IL). (72) Inventors; and (75) Inventors/Applicants (for US only): FUCHS, Yuval [IL/IL]; Raines Street 35, 42475 Netanya (IL). BÖTTGER, Christian [DE/DE]; Geschwister Scholl-Strasse 25, D-42897 Remscheid (DE). FELS, Achim [DE/DE]; Adalbert-Stifter-Weg 8, D-42109 Wuppertal (DE). (74) Agent: SCHALKWIJK, Pieter, Cornelis; Akzo Nobel N.V., Intellectual Property Dept. (Dept AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: STAB RESISTANT MATERIAL (57) Abstract Stab-resistant material made from at least two woven fabrics joined together via a polymer film, whereby the fabrics comprise yarns with a tensile strength of at least 900 MPa and the polymer film joining the fabrics has a tensile strength of at least 10 MPa, characterized in that the polymer film joining the fabrics has a flexural modulus of 1500 to 4500 MPa.		