

GLASS FIBER FORMING COMPOSITIONS

CROSS REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. Provisional Application No. 60/330,178, filed October 18, 2001. This application is a continuation-in-part of pending U.S. Patent Application Serial No. 09/980,248, filed November 28, 2001, in the name of Frederick T. Wallenberger for "Glass Fiber Composition" which application claims the benefit of U.S. Provisional Application No. 60/136,538 filed May 28, 1999, and of pending U.S. Patent Application Serial No. US01/27451, filed September 5, 2001, in the name of Frederick T. Wallenberger for "Glass Fiber Forming Compositions" which application claims the benefit of U.S. Provisional Application No. 60/230,474 filed September 6, 2000, and PCT Application No. U.S. 00/14155.

U.S. Provisional Application No. 60/136,538 is the priority application of PCT Application No. U.S. 00/14155, and U.S. Provisional Application No. 60/230,474 is the priority application of PCT Application No. US01/27451. U.S. Provisional Application Nos. 60/136,538; 60/230,474 and 60/330,178; U.S. Patent Application No. 09/980,248, and PCT Application Nos. 00/14155 and 01/27451 are hereby incorporated herein by reference.

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION

This invention relates to glass compositions, and more particularly to (1) fiber glass compositions, and (2) mathematical relationships of the ingredients of the glass compositions to identify thermal properties of the glass compositions e.g., forming and liquidus temperatures with an acceptable temperature difference to prevent devitrification of the molten glass during forming of glass fibers.

2. Discussion of the Technology

In the art of forming glass fibers it is recognized that the difference between the forming temperature and liquidus temperature is maintained at a value to prevent devitrification of the molten glass during fiber forming. For example, the most common glass composition for making continuous glass fiber strands for textiles and glass fiber reinforcements is known in the trade as "E glass". The requirements as to what type of composition constitutes an E-glass composition are included in ASTM D578-00. An advantage of using E-glass having 6-10 percent by weight B_2O_3 is that its liquidus temperature is well below its forming temperature, i.e. typically greater than $56^{\circ}C$ ($100^{\circ}F$) and usually in the range of 83 to $111^{\circ}C$ (150 to $200^{\circ}F$). As used herein, the terms "forming temperature", " T_{FORM} ", "log 3 forming temperature" and "log3 FT" mean the temperature of the glass at which the viscosity of the glass is log 3, or 1000 poise, and the terms "liquidus temperature", "liquidus T" and " T_{LIQ} " mean the temperature at which the solid phase (crystals) and liquid phase (melt) of the glass are in equilibrium. The difference between T_{FORM} and T_{LIQ} , referred to herein as "delta T" or " ΔT ", is a common measure of the crystallization potential of a given melt composition. The lower the ΔT , in other words the smaller the difference between the forming temperature and the liquidus temperature, the greater the crystallization potential. In the glass fiber forming industry, ΔT is typically maintained at a temperature of at least $50^{\circ}C$ ($90^{\circ}F$) in order to prevent devitrification of the molten glass during a glass fiber forming operation, in particular, in the bushing area.

It is appreciated by those skilled in the art of forming glass fibers, that it is desirable to operate the glass fiber forming operation at low temperatures because operating the glass fiber forming operation at high temperatures results in high-energy usage, along with associated high-energy costs. In addition, the high temperatures accelerate degradation of the refractories used in the glass melting furnace, as well as the bushings used to form the fibers. The bushings include precious metals that cannot be recovered from the glass as the bushings wear.

It is recognized that boron and fluorine in addition to contributing to the electrical properties of the E-glass, e.g. dissipation factor and dielectric constant, also lower the forming and liquidus temperatures of the glass while providing a ΔT of at least $50^{\circ}C$ ($90^{\circ}F$). The boron in the form of an oxide and fluorine in the form of a fluoride are included in the glass batch materials and act as fluxes during the glass

melting operation. E-glass can include up to 10 wt% B₂O₃ and up to 1.0 wt% fluoride (see ASTM D 578-00 §4.2). Although the boron effectively lowers the forming and liquidus temperatures while providing an acceptable ΔT value and the fluoride or fluorine acts as a flux, there are drawbacks. More particularly, these materials
5 volatilize during melting and move with the exhaust gases into the exhaust system. If the boron and fluorine in the exhaust gases are not removed they are released to the atmosphere. Since boron and fluorine are considered pollutants, these emissions are closely controlled by environmental regulations, which in turn require careful control of the furnace operations and/or the use of costly additional pollution control
10 equipment. In response to these concerns, the boron and/or fluorine content in E-glasses were reduced. For example, U.S. Patent Nos. 4,542,106 and 5,789,329 and WO 99/12858 disclose boron free or low boron e.g. 1.8wt% glasses having a forming temperature in the range of about 1258 to 1263⁰C. As can be appreciated by those skilled in the art of glass making, reducing or removing the boron and/or fluorine
15 content in the batch materials raises the forming temperature. More particularly, the silica content increases as the boron content decreases, resulting in an increase in the forming temperature. As mentioned above, increasing the forming temperature results in high-energy usage, high-energy costs, and acceleration of the degradation of furnace refractories and bushings used to form the fibers.

20

For additional information concerning glass compositions and methods for fiberizing the glass composition, see K. Loewenstein, The Manufacturing Technology of Continuous Glass Fibres, (3d Ed. 1993) at pages 30-44, 47-60, 115-122 and 126-135, and F. T. Wallenberger (editor), Advanced Inorganic Fibers: Processes, Structures, Properties, Applications, (1999) at pages 81-102 and 129-168, which
25 documents are hereby incorporated by reference.

In general, glass compositions having particular properties, e.g. forming temperature and delta T are identified by weight percent and/or molar percent of the
30 components or ingredients in the glass. As can be appreciated by those skilled in the art of glass making and/or glass fiber forming, it would be advantageous to identify the performance of the glass compositions not only by the amount of a particular ingredient in the glass but also by a relationship, e.g. a mathematical relationship of the ingredients in the glass. WO 01/32576A1 discloses fiber glass compositions and
35 the mathematical relationship of several of the ingredients, e.g. the combined Wt% of CaO and MgO, and the ratio of Al₂O₃/CaO, in the glass. Using the combination of glass ingredients, e.g. the absolute weight percent of silica with the relationship of

other ingredients in the glass, e.g. the ratio of silica to RO (combined Wt% of CaO and MgO) would provide information regarding the melt properties of the glass.

Summary of the Invention

5 The present invention provides a low boron containing or a boron free glass fiber forming composition that has a forming temperature of no greater than 1240°C (2262°F), a ΔT of at least 50°C (90°F), and one or more or all of the following compositional features:

- a ratio of SiO₂ to RO (i.e. CaO + MgO) in the range of 1.9 to 2.55;
- 10 a ratio of SiO₂ to CaO in the range of 2.1 to 2.8;
- a ratio of SiO₂ to Al₂O₃ in the range of 3.7 to 5.0;
- a ratio of Al₂O₃ to CaO in the range of 0.5 to 0.6;
- a sum of SiO₂ and Al₂O₃ in the range of 66.0 to 73.7 wt%;
- a ratio of (SiO₂+Al₂O₃) to (R₂O+RO+B₂O₃) in the range of 2.0 to 3.0;
- 15 a ratio of Al₂O₃ to RO in the range of 0.4 to 0.6; and
- a difference between SiO₂ and RO; in the range of 26.5 to 36.6 wt%.

In one nonlimiting embodiment of the present invention, the glass composition further has a SiO₂ content of greater than 57 weight percent and B₂O₃ of no greater
20 than 2 weight percent. In another nonlimiting embodiment of the invention, the SiO₂ + Al₂O₃ content of the glass composition is less than 70 weight percent. In still another nonlimiting embodiment of the invention, the glass composition contains at least 1 weight percent TiO₂.

25 In the discussion under Description of the Preferred Embodiments are glass compositions and mathematical relationship of different types of glasses. One such glass composition has the following ingredients:

	SiO ₂	55.70 to 59 percent by weight;
	Al ₂ O ₃	12.35 to 13.94 percent by weight;
30	CaO	24.40 to 24.80 percent by weight;
	MgO	2.55 to 2.80 percent by weight;
	TiO ₂	0.05 to 0.55 percent by weight;
	Na ₂ O	0.40 to 0.50 percent by weight;
	K ₂ O	0.40 to 0.60 percent by weight;
35	Na ₂ O + K ₂ O	0.85 to 1.50 percent by weight;
	Fe ₂ O ₃	0.20 to 0.40 percent by weight, and

B_2O_3 1.25 to 1.55 percent by weight, and
the following relationship of ingredients

	RO	26.25 to 27.60 wt%
	SiO_2/CaO	2.20 to 2.40
5	SiO_2/RO	2.00 to 2.20
	SiO_2/Al_2O_3	3.95 to 4.70
	Al_2O_3/CaO	0.50 to 0.60
	$SiO_2 + Al_2O_3$	69.00 to 70.50 wt%
	$SiO_2 - RO$	28.00 to 31.00 wt%
10	Al_2O_3/RO	0.45 to 0.55
	$R_2O + RO + B_2O_3$	28.90 to 30.00 wt%
	$(SiO_2 + Al_2O_3)/(R_2O + RO + B_2O_3)$	2.25 to 2.45 and

a log3 forming temperature in the range of 1210 to 1225°C and ΔT is in the range of 52 to 65°C. R_2O is equal to the wt% of K_2O and Na_2O .

15

Reference should be made to the Description of the Preferred Embodiments thereto for a more detailed summary of the glass compositions of the invention and the relationship of the ingredients of the glass compositions.

20 The glass compositions meeting the mathematical relationships of the instant invention provide a glass having a forming temperature of less than 1240 °C, preferably 1205 to 1220°C, and more preferably between 1211 to 1218°C for boron free glass and more preferably between 1187 to 1205°C for boron containing glasses.

25

Description of the Preferred Embodiments

In the following discussion, all numbers expressing dimensions, physical characteristics, and so forth, used in the specification and claims are to be
30 understood as being modified in all instances by the term "about". Accordingly, unless indicated to the contrary, the numerical values set forth in the following specification and claims can vary depending upon the desired properties obtained by the practice of the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each
35 numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Moreover, all ranges

disclosed herein are to be understood to encompass any and all subranges subsumed therein. For example, a stated range of 1 wt% to 10 wt% should be considered to include any and all subranges between (and inclusive of) the minimum value of 1 and the maximum value of 10; that is, all subranges beginning with a
5 minimum value of 1 or more and ending with a maximum value of 10 or less, e.g., 5.5 to 10.

It should be appreciated that, unless otherwise indicated, all numerical values discussed herein, such as but not limited to weight percent of materials or
10 temperatures, are approximate and are subject to variations due to various factors well known to those skilled in the art such as, but not limited to, measurement standards, equipment and techniques. As a result, such values are to be understood as being modified in all instances by the term "about". Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification and
15 attached claims are approximations that may vary depending upon the desired properties sought to be obtained by the present invention. At the very least, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques.

20 Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any recognized deviations and/or errors are discussed. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their
25 respective testing measurements.

In the following discussion and in the claims the limits of defining the range are included in the range. For example and not limiting to the discussion, "in the range of 1230 to 1240°C" and "in the range of equal to and greater than 1230°C and
30 equal to and less than 1240°C" define the same range. Further in the preceding discussion, in the following discussion and in the claims, the terms "weight percent", "wt%" and "percent by weight" are used herein interchangeably.

In one embodiment of the present invention, the mathematical relationships of
35 the ingredients of a generic quaternary glass system are disclosed. The quaternary system includes SiO₂, CaO, Al₂O₃ and MgO. As can be appreciated by those skilled in the art of making glass, in particular making glass fibers, MgO if not added to the

batch materials is found in the batch materials as a tramp material, e.g. MgO is found in clay at 0.3 to 0.5 percent by weight. In the practice of the invention, MgO is added to the batch material to attain a level in the glass greater than the tramp level. The relationship of SiO_2 , CaO, Al_2O_3 and MgO of interest include $\text{RO} = \text{CaO} + \text{MgO}$, SiO_2/CaO , SiO_2/RO , $\text{SiO}_2/\text{Al}_2\text{O}_3$; $\text{Al}_2\text{O}_3/\text{CaO}$; $\text{SiO}_2 + \text{Al}_2\text{O}_3$; $\text{SiO}_2 - \text{RO}$ and $\text{Al}_2\text{O}_3/\text{RO}$ or $\text{RO}/\text{Al}_2\text{O}_3$. In the present invention when other ingredients or components are added to the glass batch materials to alter the forming and/or liquidus temperatures of the glass and/or are present in the glass, for example but not limiting to the invention Na_2O , Li_2O , K_2O and B_2O_3 the following mathematical relationships are of interest, $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ where RO is as previously defined and $\text{R}_2\text{O} = \text{Na}_2\text{O} + \text{Li}_2\text{O} + \text{K}_2\text{O}$. In Tables 1 through 22, the relationship $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ is shown as $(\text{Si} + \text{Al})/(\text{R}_2\text{O} + \text{RO} + \text{B})$ to fit the formula into a reasonable column width. Each of the compositional features of the glass identified above reflects the relative balance between the fluidity (i.e. viscosity) of the glass melt and its crystallization potential, as will be discussed below in more detail. The physical melt properties of interest in the present discussion are the forming temperature and the liquidus temperature because embodiments of the present invention are to provide low boron or boron free glass compositions having a low forming temperature and a desired ΔT . In this manner, the glass can be processed, e.g. to form glass fibers at a low temperature while reducing the possibility of devitrification of the molten glass, e.g. in the bushing area. Without limiting the present invention, one embodiment of the invention includes a glass composition having a forming temperature of no greater than 1240°C (2264°F) and a ΔT of at least 50°C (90°F).

25

In the following discussion, the mathematical relationship is to the ingredients in the glass; however, the invention is not limited thereto and contemplates identifying and using the relationship of the ingredients to be added to the batch, e.g. mixing the batch prior to melting the batch to form the glass. Further, in the following discussion the mathematical relationship of the ingredients will be in wt% of the ingredients in the glass composition; however, the invention is not limited thereto and maybe the mole% or any measurement that identifies the amount of the ingredient in the batch materials and/or the glass composition.

35

In regards to the ingredients or constituents of the quaternary system presented above, it is known that pure silica is the highest melting glass former. A

pure silica melt does not have a well defined melting point. At 2500°C (4532°F), it has a viscosity of greater than about log 4 (10,000) poise, and as it cools to room temperature, it gradually solidifies and forms a glass. Pure calcia, magnesia and alumina melts are known to have very low viscosities, e.g. in the range of 0.5-2.0 poise at their respective melting points. These materials do not solidify into a glass as the melt cools but rather crystallize instantly at their sharply defined melting point. In a typical quaternary SiO₂-Al₂O₃-CaO-MgO glass composition with 55-60% SiO₂ and 21-26% CaO, each oxide of the quaternary system contributes its unique characteristics toward its balance of melt properties.

10

Based on the material properties of the constituents of the quaternary system for a glass composition having these components, it can be inferred that as SiO₂, which is the largest oxide component of the glass composition in terms of weight percent, is reduced in a given composition of this type, the melt viscosity and the resulting log 3 forming temperature drops. If CaO, which is the second largest component of the glass composition in terms of weight percent, or MgO is increased in such a composition, the effect of RO (CaO + MgO) on the glass properties will be twofold. More specifically, it will not only increase the fluidity of the resulting melt (i.e. decrease its viscosity and the forming temperature) but it will also increase the crystallizability of the resulting melt (i.e. increase its liquidus temperature), and therefore reduce the ΔT.

15
20

As a result, although not required, in one nonlimiting embodiment of the present invention, the glass compositions have (1) the lowest SiO₂ content that will yield the lowest log 3 forming temperature, which in the present invention is below 1240°C, preferably below 1220°C in combination with (2) the ratio of SiO₂ to RO that yields the process-required ΔT, which in the present invention is at least 50°C. Based on the forgoing and although not required in the practice of the invention, in one nonlimiting embodiment of the present invention, the silica level is preferably no greater than 62 wt% SiO₂, in order to promote a lower log 3 forming temperature. In other nonlimiting embodiments of the present invention, the glass compositions have no greater than 60 wt% SiO₂ and no greater than 58 wt% SiO₂.

25
30

In general, MgO is included in a glass fiber forming composition because it has been found that the heating and melting profile of a glass fiber composition, and in particular the liquidus temperature, can be controlled and in particular optimized by

35

controlling the amount of MgO. More particularly, by regulating the amount of MgO, the liquidus temperature can be selected to provide a ΔT of at least 50°C . In addition, it has been determined that a eutectic exists in a generic quaternary SiO_2 - Al_2O_3 -CaO-MgO system at around 2.5 – 2.8 wt% MgO. For a discussion of the eutectic reference may be had to WO 00/73231 which document is hereby
5 incorporated by reference.

The value of the SiO_2/RO ratio can be manipulated by changing the amount of SiO_2 and/or RO to produce a glass composition having a ΔT as close as possible
10 to the minimum desired ΔT . A decrease in the value of SiO_2/RO , which is indicative of a reduction in the wt% of SiO_2 and/or an increase in the wt% of CaO and/or MgO, or any change or combination of changes in the wt% of the SiO_2 , CaO and/or MgO, will effect the melt viscosity and ΔT , and will increase the crystallization potential. Conversely, an increase in the value of SiO_2/RO will effect the melt viscosity and ΔT ,
15 and will decrease the crystallization potential. It should be appreciated that if the value of SiO_2/RO ratio drops too low, ΔT can drop to an unacceptable level. Although not required, in one nonlimiting embodiment of the present invention, SiO_2/RO is no greater than 2.40. In other nonlimiting embodiments, SiO_2/RO is no greater than 2.35, or no greater than 2.30, or no greater than 2.25, or no greater than
20 2.20. In still another nonlimiting embodiment of the invention, the value of SiO_2/RO ranges from 1.9 to 2.55, e.g. from 2.1 to 2.55 for boron-free glasses and from 1.9 to 2.4 for boron containing glasses.

In addition to the SiO_2 level and the SiO_2/RO ratio, the following parameters
25 also describe the compositional envelope level of a quaternary glass composition: the SiO_2/CaO ratio, the $\text{SiO}_2/\text{Al}_2\text{O}_3$ ratio, the $\text{Al}_2\text{O}_3/\text{CaO}$ ratio, the sum of $\text{SiO}_2 + \text{Al}_2\text{O}_3$, the difference between $\text{SiO}_2 - \text{RO}$, and the $\text{Al}_2\text{O}_3/\text{RO}$ ratio. The following parameters describe the compositional envelope level of a glass composition containing additional temperature modifying ingredients: the sum of $\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$, where $\text{R}_2\text{O} = \text{Na}_2\text{O} + \text{K}_2\text{O} + \text{Li}_2\text{O}$ and the $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$
30 ratio.

While the SiO_2/RO ratio at a given silica level describes the compositional effect of RO on the crystallization potential and melt fluidity, the SiO_2/CaO ratio
35 shows only the effect of CaO on the crystallization potential. If the MgO and the SiO_2 levels are kept constant in a comparison of various melts, a decrease in the

value of SiO_2/CaO will show an increase in crystallization potential due to the contribution of CaO and visa versa. The SiO_2 - RO difference serves as a similar indicator, i.e. a decrease in the difference or a smaller difference is typically indicative of a greater relative amount of RO and thus an increase in the crystallization potential. And conversely, an increase in the difference or a larger difference in SiO_2 - RO is indicative of a reduction in the crystallization potential. In one nonlimiting embodiment of the present invention, the SiO_2/CaO ratio of the glass composition ranges from 2.1 to 2.8, e.g. from 2.3 to 2.8 for boron-free glasses and from 2.2 to 2.7 for boron containing glasses. In another nonlimiting embodiment of the present invention, the SiO_2 - RO difference of the glass composition ranges from 26.5 to 36.6 wt%, e.g. from 30.5 to 36.6 wt% for boron-free glasses and from 26.5 to 34.0 wt% for boron containing glasses.

The sum of $\text{SiO}_2 + \text{Al}_2\text{O}_3$ is another parameter that describes the compositional envelope of a given melt. Up to about an Al_2O_3 level of 14 to 15 wt%, Al_2O_3 is believed to be able to participate in the network formation with SiO_2 , and counteract the crystallization potential of RO that is always present. At higher Al_2O_3 levels, e.g. greater than 15 wt%, Al_2O_3 will begin to act much like RO and contribute to a rise of the crystallization potential of a given melt. Thus a lower value of $\text{SiO}_2 + \text{Al}_2\text{O}_3$, which is indicative of a lower Al_2O_3 level for a glass composition of a given wt% of SiO_2 , will typically result in a lower crystallization potential, and a greater value of $\text{SiO}_2 + \text{Al}_2\text{O}_3$ will typically result in a higher crystallization potential for a given melt. In one nonlimiting embodiment of the present invention, the $\text{SiO}_2 + \text{Al}_2\text{O}_3$ sum of the glass composition ranges from 66.0 to 73.7 wt%, e.g. from 70.8 to 73.7 wt% for boron-free glasses and from 66.0 to 72.1 wt% for boron containing glasses.

Similarly with respect to $\text{SiO}_2/\text{Al}_2\text{O}_3$ and based on the characteristics of the melt provided by the amount of Al_2O_3 , an increasing ratio value would be indicative of a reduction in the amount of Al_2O_3 and/or an increase in the amount of SiO_2 and would be accompanied by a reduction in the crystallization potential of the melt. Conversely, a decreasing ratio value would be accompanied by an increase in the crystallization potential of the melt. In one nonlimiting embodiment of the present invention, the $\text{SiO}_2/\text{Al}_2\text{O}_3$ ratio of the glass composition ranges from 3.7 to 5.0, e.g. from 4.2 to 5.0 for boron-free glasses and from 3.7 to 4.9 for boron containing glasses.

As mentioned above, other mathematical relationships of ingredients of glass compositions, e.g. the $\text{Al}_2\text{O}_3/\text{CaO}$ ratio, the $\text{Al}_2\text{O}_3/\text{RO}$ ratio, and the $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ ratio may be developed to characterize a given melt. In one nonlimiting embodiment of the present invention, the value of the $\text{Al}_2\text{O}_3/\text{CaO}$ ratio of the glass composition ranges from 0.5 to 0.6. In another nonlimiting embodiment of the present invention, the value of the $\text{Al}_2\text{O}_3/\text{RO}$ ratio of the glass composition ranges from 0.4 to 0.6, e.g. from 0.46 to 0.53 for boron-free glasses and from 0.46 to 0.56 for boron containing glasses. In still another nonlimiting embodiment of the present invention, the value of the $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ ratio of the glass composition ranges from 2.0 to 3.0, e.g. from 2.3 to 3.0 for boron-free glasses and from 2.0 to 2.7 for boron containing glasses. Reference may be had to WO 01/32576 for additional discussion on the $\text{Al}_2\text{O}_3/\text{CaO}$ ratio, and the $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ ratio.

The discussion will now be directed to additives to the batch materials to alter the forming temperature, the liquidus temperature and the delta T. As previously discussed, boron is a material that is added to glass fiber compositions to reduce the forming temperature and the liquidus temperature. However, as discussed earlier, the inclusion of boron oxide results in the production of particulate emissions that, depending on the particulate level, may have to be removed from a melting furnace exhaust stream before being released into the environment. Although the amount of B_2O_3 can be as high as 10 wt% in an E-glass composition, in the present invention, the glass composition has no boron or a low boron content, i.e. has a B_2O_3 content in the range of 0 to 5.10 wt%. In other nonlimiting embodiments of the present invention, the glass fiber composition has no greater than 4 wt%, or no greater than 3 wt%, or no greater than 2 wt% B_2O_3 . In another nonlimiting embodiment of the present invention, the glass composition is boron-free or essentially boron-free. As the term "essentially free" is used herein, the glass composition does not include an ingredient purposely added to the glass but found in the glass in trace amounts. In the practice of the invention, a glass having up to 0.05 wt% B_2O_3 is considered a boron free glass.

Further, as previously discussed, fluorine is a material added to glass fiber compositions as a flux, however, because of the environmental concerns it is preferred not to include fluorine. Nevertheless because equipment is available to remove the fluorine from the exhaust gases, the invention may be practiced using fluorine. In one nonlimiting embodiment of the present invention, the glass

composition has low fluorine content, in other words, a fluorine content no greater than 0.30 wt%. In another nonlimiting embodiment, the glass composition is essentially fluorine free, i.e. it includes no more than a trace amount of fluorine, which is considered herein to be up to 0.05 wt%. In still another nonlimiting embodiment, the glass composition does not include any fluorine. Except where otherwise indicated, the glass fiber forming compositions disclosed and discussed herein are essentially fluorine free and/or do not include any fluorine.

Additional materials that can be added to the glass fiber composition to modify the melt properties, e.g. to reduce forming temperature and/or liquidus temperature of the glass include without limiting the glass compositions disclosed herein, are Li_2O , Na_2O , ZnO , TiO_2 , MnO and/or MnO_2 . Alkali oxides are network terminators and tend to effect the melt properties. K_2O an alkali oxide is found in levels up to 0.60 wt% in commercial clays and is not normally added as a separate ingredient to the batch materials; however, in the practice of the invention it may be added as a separate material. In the practice of the invention alkali oxides up to 2.00 wt%, preferably 1 wt% are present in the glass of one embodiment of the invention. In the instance where K_2O is present in the clay, the difference is usually made up by additions of Na_2O and Li_2O . Li_2O is more effective in reducing the melt properties than Na_2O . In one non-limiting embodiment of the present invention, the glass composition includes 0 to 1.0 wt% Li_2O and/or 0 to 1.00 wt% Na_2O and/or 0 to 1 wt% K_2O . Non-alkali oxide ingredients usually employed to reduce the melt properties are ZnO , TiO_2 , MnO and/or MnO_2 in amounts of about 0 to 1.5 wt% ZnO , 0 to 1.5 wt% TiO_2 , 0 to 3 wt% MnO and/or 0 to 3 wt% MnO_2 . It is believed that levels of these materials less than 0.05 wt% would be considered either tramp amounts or so low that they will not materially impact the glass melt properties. As a result, in another non-limiting embodiment, 0.05 to 1.5 wt% Li_2O and/or 0.05 to 1.0 wt% Na_2O and/or 0.05 to 1.0 wt% K_2O and/or 0.05 to 1.5 wt% ZnO and/or 0.05 to 1.5 wt% TiO_2 and/or 0.05 to 3 wt% MnO and/or 0.05 to 3 wt% MnO_2 are included in the glass composition. In still another nonlimiting embodiment of the invention, the glass composition includes 0.2 to 1 wt% Li_2O and/or 0.30 to 1.0 wt% Na_2O and/or 0.30 to 1.0 wt% K_2O and/or 0.2 to 1 wt% ZnO and/or 0.05 to 1.1 wt% TiO_2 and/or up to 1 wt% MnO and/or up to 1 wt% MnO_2 .

As mentioned above, the ratio $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ takes into account the wt% of the additions of B_2O_3 , Na_2O , K_2O and Li_2O that is (are) measured in the glass or batch materials regardless of the amount. Tramp amounts of these

materials in the glass and/or batch are to be used to determine the value of the ratio. If any or all of the additions of B_2O_3 , Na_2O , K_2O and Li_2O are not determined to be present in the glass and/or batch, the value of zero is used for that ingredient in determining the value of the ratio. For example but not limiting to the invention, if

5 Na_2O , K_2O and Li_2O are present and B_2O_3 is not, the ratio $(SiO_2 + Al_2O_3)/(R_2O + RO + B_2O_3)$ becomes $(SiO_2 + Al_2O_3)/(R_2O + RO)$. If none of the ingredients B_2O_3 , Na_2O , K_2O and Li_2O are determined to be present, the ratio becomes $(SiO_2 + Al_2O_3)/RO$. In the claims when the ratio $(SiO_2 + Al_2O_3)/(R_2O + RO + B_2O_3)$ is recited in a claim, if the ingredient is not recited in the claim, it is not used to determine the value of the

10 ratio even though it is determined to be present in a glass covered by the claim. The preceding discussion is applicable to the other mathematical relationships, e.g. but not limiting thereto $(R_2O + RO + B_2O_3)$.

It should be appreciated that glass fiber compositions can include other

15 oxides that are present as tramp materials such as BaO , ZrO_2 , SrO and Cr_2O_3 , which are usually present in amounts of up to 0.1wt%.

Further, it should be appreciated that the glass compositions disclosed herein can also include small amounts of other materials, for example melting and refining

20 aids, tramp materials or impurities. For example and without limiting the present invention, melting and fining aids, such as FeO , Fe_2O_3 and SO_3 , are useful during production of the glass, but their residual amounts in the glass can vary and typically have minimal, if any, material effect on the properties of the glass product. In addition, small amounts of the additives discussed above can enter the glass

25 composition as tramp materials or impurities included in the raw materials of the main constituents, e.g. 0 to 0.5 wt% for SO_3 , FeO and Fe_2O_3 .

Shown in Table 1 are several examples of glass compositions of an embodiment of the invention, which relates to the use of clay having high K_2O and

30 low TiO_2 levels in glass batch materials and to glass compositions having high levels K_2O and low levels of TiO_2 . K_2O and TiO_2 can be added to the batch materials but are not economically removed from the clays used as batch material. As can be appreciated by those skilled in the art of glass melting and as discussed above, high K_2O levels, e.g. up to 0.70wt% in the glass raises the forming temperature by as

35 much as about 7 to 10 °C in relation to a glass made from clay that introduces 0.10wt% K_2O . One embodiment of the present invention relates to an improved E-type glass having low weight percent B_2O_3 , a forming temperature no greater than

1230 °C, preferably no greater than 1222°C and a delta T of at least 50 °C and preferably up to 65°C. The following are the main constituents in wt% based on the total weight percent of the final glass composition. The K₂O and TiO₂ listed in the ranges below for commercial glasses may or may not be added to the batch as separate ingredient. If the K₂O and TiO₂ are not added, it is expected that they would be present in the clay in varying wt% depending on the geographical location of the clay. Although the K₂O and TiO₂ would be present in the clay, the invention contemplates separate additions of K₂O and/or TiO₂ to be within the ranges listed below.

10

In those instances when the clay has high wt% of K₂O, e.g. 0.60 wt%, it is necessary to counteract the effect of the K₂O. More particularly, the K₂O increases the forming temperature; therefore, the ingredients in the batch materials have to be modified so as to maintain a low forming temperature, e.g. below 1240°C. In one embodiment of the invention such a glass is as follows.

15

	<u>broad range</u>	<u>preferred range</u>	<u>most preferred range</u>
SiO ₂ (wt%)	52 to 60	54 to 59	55 to 58
Al ₂ O ₃ (wt%)	8 to 16	11 to 14	12 to 14
CaO (wt%)	21 to 26	22 to 25	23 to 25
MgO(wt%)	1 to 5	1 to 4	2 to 3
K ₂ O (wt%)	up to 1.00	0.30 to 1.00	0.30 to 0.80
Na ₂ O (wt%)	up to 1.00	0.30 to 1.00	0.30 to 0.90
K ₂ O+Na ₂ O(wt%)	0.70 to 2.00	0.80 to 1.5	0.90 to 1.20
B ₂ O ₃ (wt%)	1.00 to 3.50	1.10 to 2.00	1.20 to 1.50
Fe ₂ O ₃ (wt%)	0.10 to 0.50	0.15 to 0.45	0.20 to 0.40
TiO ₂	up to 2.0	Up to 1.5	Up to 1.3

The range provided for B₂O₃ is not limiting to the invention, and it is recommended the level of boron be adjusted to meet local environmental regulations. As such, the invention may be practiced having levels of B₂O₃ up to 3.5wt%.

20

The glasses of the invention are further defined by one or more of the following relationships:

25

	<u>broad range</u>	<u>preferred range</u>
wt% of CaO and MgO ("RO")	26 to 28 wt%	26 to 27.70 wt%


	SiO ₂ /CaO	2.10 to 2.80	2.20 to 2.70
	SiO ₂ /RO	1.90 to 2.55	1.90 to 2.40
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00	3.7 to 4.90
	Al ₂ O ₃ /CaO	0.45 to 0.65	0.50 to 0.60
5	SiO ₂ + Al ₂ O ₃	66 to 73.70 wt%	66 to 72.10 wt%
	SiO ₂ – RO	26.56 to 36.60 wt%	26.50 to 34 wt%
	Al ₂ O ₃ /RO	0.40 to 0.60	0.46 to 0.56
	R2O +RO+B ₂ O ₃	28.00 to 32.00 wt%	28.00 to 31.00 wt%
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.00 to 3.00	2.00 to 2.70
10	where R2O is equal to the sum of Na ₂ O +K ₂ O.		

Table 1 contains experimental samples A-E and illustrative samples F and G of glass compositions incorporating features of the invention. The ranges for the glass compositions listed on Table 1 are the minimum and maximum values for the glass compositions recited on Table 1, and for examples A-E, and F and G. More particularly, Table 1 provides the following glass compositions. A glass composition having the following ingredients:

	SiO ₂	55.00 to 58 percent by weight;
	Al ₂ O ₃	12.00 to 14.00 percent by weight;
20	CaO	23.80 to 24.80 percent by weight;
	MgO	2.50 to 3.00 percent by weight;
	TiO ₂	up to 0.60 percent by weight;
	Na ₂ O	0.40 to 0.50 percent by weight;
	K ₂ O	0.40 to 0.60 percent by weight;
25	Na ₂ O + K ₂ O	0.85 to 1.50 percent by weight;
	Fe ₂ O ₃	0.20 to 0.40 percent by weight;
	B ₂ O ₃	1.25 to 1.55 percent by weight;

the following relationship of ingredients

	RO	26.25 to 27.60 wt%
30	SiO ₂ /CaO	2.20 to 2.40
	SiO ₂ / RO	2.00 to 2.20
	SiO ₂ /Al ₂ O ₃	3.95 to 4.70
	Al ₂ O ₃ /CaO	0.50 to 0.60
	SiO ₂ + Al ₂ O ₃	69.00to 70.50 wt%
35	SiO ₂ – RO	28.00 to 31.00 wt%
	Al ₂ O ₃ /RO	0.45 to 0.55
	R2O +RO+B ₂ O ₃	28.90 to 30.00 wt%



where R_2O is equal to the sum of $\text{Na}_2\text{O} + \text{K}_2\text{O}$ has a log3 forming temperature in the range of 1210 to 1225°C and ΔT is in the range of 52 to 65°C.

5

Another glass composition defined by Examples A-E of Table 1 has the following ingredients

	SiO_2	55.60 to 57.60 percent by weight;
	Al_2O_3	12.35 to 13.94 percent by weight;
10	CaO	24.40 to 24.80 percent by weight;
	MgO	2.55 to 2.80 percent by weight;
	TiO_2	0.55 percent by weight;
	Na_2O	0.45 percent by weight;
	K_2O	0.45 to 0.58 percent by weight;
15	$\text{Na}_2\text{O} + \text{K}_2\text{O}$	0.90 to 1.03 percent by weight;
	Fe_2O_3	0.25 to 0.38 percent by weight;
	B_2O_3	1.30 to 1.50 percent by weight, and

the following relationships:

	RO	26.95 to 27.56 wt%
20	SiO_2/CaO	2.25 to 2.29
	SiO_2/RO	2.02 to 2.14
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.00 to 4.66
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.56
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.18 to 69.95 wt%
25	$\text{SiO}_2 - \text{RO}$	28.04 to 30.65 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.51
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	29.15 to 29.89 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3) / (\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.31 to 2.40

where R_2O is equal to the sum of $\text{Na}_2\text{O} + \text{K}_2\text{O}$. The glass composition has a log3 forming temperature in the range of 1156 to 1164°C and ΔT is in the range of 54 to 65°C.

Other glass compositions identified by Examples F and G of Table 1 have the following ingredients

35	SiO_2	56.70 to 57.85 percent by weight;
	Al_2O_3	12.55 to 13.67 percent by weight;

	CaO	23.87 to 24.45 percent by weight;
	MgO	2.55 to 2.62 percent by weight;
	TiO ₂	0.05 to 0.34 percent by weight;
	Na ₂ O	0.44 to 0.455 percent by weight;
5	K ₂ O	0.45 to 0.51 percent by weight;
	Na ₂ O + K ₂ O	0.90 to 1.03 percent by weight;
	Fe ₂ O ₃	0.30 to 0.40 percent by weight;
	B ₂ O ₃	1.30 to 1.50 percent by weight, and
	the following relationships:	
10	RO	26.49 to 27.00 wt%
	SiO ₂ /CaO	2.37 to 2.38
	SiO ₂ /RO	2.10 to 2.14
	SiO ₂ /Al ₂ O ₃	4.15 to 4.61
	Al ₂ O ₃ /CaO	0.51 to 0.57
15	SiO ₂ + Al ₂ O ₃	70.37 to 70.44 wt%
	SiO ₂ – RO	30.21 to 30.85 wt%
	Al ₂ O ₃ /RO	0.46 to 0.52
	R ₂ O + RO + B ₂ O ₃	28.94 to 29.20 wt%
	(SiO ₂ + Al ₂ O ₃) / (R ₂ O + RO + B ₂ O ₃)	2.41 to 2.43

20 where R₂O is equal to the sum of Na₂O + K₂O. The glasses have a log₃ forming temperature in the range of 1218 to 1219°C and ΔT is in the range of 52 to 58°C.

The experimental or laboratory examples or samples on Table 1 discussed
 25 above and on Tables 2 to 19 to be discussed below, unless indicated otherwise, were prepared from certified or reagent grade oxides (e.g., pure silica or calcia). Examples F and G on Table 1 and examples H and I on Table 2 are illustrative examples and were not prepared in the following manner. The batch size for each example was 1000 grams. The individual batch ingredients were weighed out,
 30 combined and placed in a tightly sealed glass jar or plastic container. The sealed jar or container was then placed in a paint shaker for 15 minutes or in a tubular mixer for 25 minutes to effectively mix the ingredients. A portion of the batch was then placed into a platinum crucible, filling no more than 3/4 of its volume. The crucible was then placed in a furnace and heated at 1427°C (2600°F) for 15 minutes. The remaining
 35 batch was then added to the hot crucible and heated at 1427°C (2600°F) for 15 to 30 minutes. The furnace temperature was then raised to 1482°C (2700°F) and held

there for 2 hours. The molten glass was then fritted in water and dried. The fritted samples were reheated to a temperature of 1482°C (2700°F) and held at that temperature for 2 hours. The molten glass was then fritted again in water and dried.

5 The forming temperature, i.e. the glass temperature at a viscosity of 1000 poise, was determined by ASTM method C965-81, and the liquidus temperature by ASTM method C829-81. The log 3 forming temperature of the compositions reported in Tables 1-20 were determined by a comparison of the glass against physical standards supplied by the National Institute of Standards and Testing (NIST). In the
10 Tables, the majority of the reported log 3 forming temperatures is based on comparison to NIST 710A. Several of the reported log 3 forming temperatures are originally based on NIST 717A which uses a borosilicate standard; in those instances the values were converted to correspond to NIST 710A. Therefore all the log3 forming temperatures are considered to be based on NIST 710A.

15

Selected samples had ingredients added that would be found in the clays used in the batch material. Such as K_2O , TiO_2 , calcium fluoride, SrO and/or Cr_2O_3 .

20 The weight percent of the constituents of the compositions shown in Tables 1-19 except for Examples F to I are based on the weight percent of each constituent in the batch. It is believed that the batch weight percent is generally about the same as the weight percent of the melted sample, except for glass batch materials that volatilize during melting, e.g. boron, fluorine and moisture absorbing materials. In the case of boron, it is believed that the weight percent of B_2O_3 in a laboratory sample
25 will be 10 to 16 weight percent less than the weight percent of B_2O_3 in the batch composition, the precise loss depending on the composition and melting conditions. In the case of fluorine, it is believed that the weight percent of fluorine in a laboratory test sample will be about 50 percent less than the weight percent of fluorine in the batch composition, the precise loss depending on the composition and melting
30 conditions. In the case of CaO , CaO has a certified ignition loss 3-5wt% (an average of 4wt%). The determination of the wt% of the batch materials for the samples listed on Tables 1-19 except for Examples F to I, through an oversight, did not take into account the ignition loss. Therefore in practicing the invention, this fact should be taken into account. Because the 4wt% error is minimal, the recitation of the
35 wt% of CaO recited in the claims covering the embodiments of the glass compositions listed on Tables 1 – 19 does not take into account the ignition loss.

Table 20 has production samples; the analysis of the ingredients of the examples on Table 20 were measured using XRF analysis.

As can be appreciated by those skilled in the art of converting data from laboratory melt sample to data used to prepare batch materials for commercial glass production, the melting and fining conditions of the commercial furnace to be used to melt and fine the glass has to be taken into consideration. It is believed that glass fiber compositions made from commercial grade materials and melted under conventional operating conditions will have similar batch and melt weight percents as discussed above, with the precise loss depending, in part, on the furnace operating temperature, through-put and quality of commercial batch materials. The amount of boron and fluorine reported in the tables takes into consideration the expected loss of these materials and represents the expected amount of the material in the glass composition. It should further be appreciated that the glass compositions disclosed herein can also include small amounts of other materials, for example melting and refining aids, tramp materials or impurities. For example and without limiting the present invention, melting and fining aids, such as SO_3 , are useful during production of the glass, but their residual amounts in the glass can vary and have no material effect on the properties of the glass product. In addition, small amounts of the additives discussed above can enter the glass composition as tramp materials or impurities included in the raw materials of the main constituents.

With reference to Tables 1-20, in each column of each Table, the upper portion of the column lists the wt% of the ingredients in the glass composition based on the batch materials as was discussed above. The middle portion of the column lists the mathematical relationship of the ingredients discussed above for the particular glass composition in the same column to obtain the thermal properties listed in the bottom portion of the column e.g. forming temperature, liquidus temperature and delta T (except for certain compositions of Table 20 which is discussed below.) Table 20 lists production glasses. The amount of each constituent of the commercial compositions shown in the Table 20 is the weight percent in the glass. The weight percent for the B_2O_3 was determined using Neutron Transmission analysis techniques and the weight percent for the remaining constituents was determined using X-ray fluorescence analysis (also referred to as "XRF analysis"), all of which are well known to those skilled in the art.

Tables 2 through 19 include, but are not limited to glass compositions disclosed in U.S. Patent Application Serial No. 09/980,248, filed November 28, 2001, in the name of Frederick T. Wallenberger for "Glass Fiber Compositions" (hereinafter "USPA No.09/980248"); in PCT International Application No. PCT/US01/27451, filed September 5, 2001, in the name of Frederick T. Wallenberger for "Glass Fiber Forming Compositions" (hereinafter "USPCT No. 01/27451"); and in International Application No. PCT/US00/14155. USPA No. 09/980248 and International Application No. PCT/US00/14155 are jointly referred to as "USPA No.09/980248 Combined".

10

USPA No.09/980248 Combined and USPCT No. 01/27451 discloses base composition for the low boron glass fibers that are suitable for textiles and glass fiber reinforcements, that may be used in the practice of the present invention. In general, the base compositions of USPA No.09/980248 Combined and USPCT No. 01/27451 include the following main constituents in weight percent ranges based on the total weight of the final glass composition with the exception that USPCT No. 01/27451 glass compositions are boron free.

15

	<u>broad range</u>	<u>preferred range</u>	<u>most preferred range</u>
SiO ₂ (wt%)	52 to 62	52 to 61	53 to 59
Na ₂ O (wt%)	0 to 2	up to 1.5	up to 1
CaO (wt%)	16 to 25	20 to 25	22 to 24
Al ₂ O ₃ (wt%)	8 to 16	11 to 14	12 to 14
Fe ₂ O ₃ (wt%)	0.05 to 0.80	up to 0.5	up to 0.4
K ₂ O (wt%)	0 to 2	Up to 1	up to 0.1
B ₂ O ₃ (wt%)	1 to 5	1 to 3.5	1 to 2.5

In one embodiment the glass composition of USPA No. 09/980248 Combined, the glass composition can include on or more of the following materials in the following amounts.

20

	<u>broad range</u>	<u>preferred range</u>
Li ₂ O (wt%)	0.05 to 1.5	0.2 to 1
ZnO (wt%)	0.05 to 1.5	0.2 to 1
MnO (wt%)	0.05 to 3	up to 1
MnO ₂ (wt%)	0.05 to 3	up to 1

For a complete discussion of the glass compositions disclosed in USPA No.09/980248 Combined, and disclosed in USPCT No. 01/27451, reference should be made thereto.

25

As discussed above the examples of Table 1 incorporate features of one embodiment of the invention, a low boron glass composition (see the upper portion of the columns on Table 1) having a forming temperature below 1240°C, more preferably below 1225°C and a delta T of greater than 50°C (see the lower portion of the columns on Table 1). The examples of Tables 1-20 include another feature of the invention, mathematical relationship of the ingredients in the glass composition (see middle portion of the columns on Tables 1-20) to provide a forming temperature below 1240°C and a delta T of greater than 50°C (see the lower portion of the columns on Tables 1-20). The mathematical relationship of the ingredients of the glass compositions on Table 1 were discussed above. Tables 2-19 include, but are not limited to examples of glass compositions disclosed in USPA No.09/980248 Combined and/or in USPCT No. 01/27451. Additional examples within the scope of the inventions of USPA No.09/980248 Combined and/or in USPCT No. 01/27451 are included herein. For example, but not a complete relationship, examples 188-236 are selected from USPA No.09/980248 Combined and examples 7-24, 43-50, 78-185, and 219-267 are selected from USPCT No. 01/27451. Examples A-E, 25, 30-32, 60-75 are examples, among others, presented by this application. The examples identified as selected from USPA No.09/980248 Combined and/or in USPCT No. 01/27451 and those added to the Tables by the instant disclosure are not complete. For a complete comparison reference may be had to USPA No.09/980248 Combined and/or in USPCT No. 01/27451.

For a better appreciation of the invention the samples on Tables 2-19 are categorized according to the following types of glass compositions.

- Type -1 Glasses boron-free (Table 2)
- Type -2 Glasses up to about 5.10 wt% B₂O₃ (Tables 3-11)
- Type -3 Glasses boron-free with lithium oxide (Tables 12 and 13)
- Type -4 Glasses boron-free with lithium and zinc oxide (Tables 14 and 15)
- Type -5 Glasses boron-free with zinc oxide (Table 16)
- Type -6 Glasses up to 5 wt% B₂O₃ with lithium oxide (Tables 17 and 18)
- Type 7 Glasses miscellaneous glass (Table 19)

Table 20, as previously discussed includes production glasses.

Table 2 (Type 1 Glasses) includes glass compositions of a quaternary system that includes SiO₂ in the range of 57-60 wt%, preferably in the range of 57.25-59.50 wt% and more preferable in the range of 57.40-59.10; Al₂O₃ in the range of 12-14 wt%, preferably in the range of 12-13.50 wt% and more preferably in the range of 12.15-13.45 wt%; CaO in the range of 23-25wt%, preferable in the range of 23.50-24.50 wt% and more preferable in the range of 23.70-24.20wt%, and MgO in the range of 2-3 wt%, preferably in the range of 2.25-2.75 wt% and more preferably in the range of 2.50-2.60 wt%. The glass compositions of Table 2 further include TiO₂ in the range of up to 1.25 wt%, preferably in the range of 0.25 - 1.20 wt% and more preferably in the range of 0.50-1.15 wt%; Na₂O in the range of 0.75-1.25, preferably in the range of 0.75-1.00 wt% and more preferably in the range of 0.85-0.9 5wt%; and Fe₂O₃ in the range of up to 0.50 wt%, preferably 0.10-0.50 wt% and more preferably in the range of 0.30-0.40 wt%. The compositions of Table 2 are boron free. Compositions 1-6 of Table 2 further include TiO₂ in the range of 1.00-1.25 wt%, preferably in the range of 1.00- 1.20 wt% and more preferably in the range of 1.05-1.15 wt%; Na₂O in the range of 0.75-1.25, preferably in the range of 0.75-1.00 wt% and more preferably in the range of 0.85-0.95wt%; and Fe₂O₃ in the range of up to .35 wt%, preferably 0.10-0.30 wt% and more preferably in the range of 0.20-0.30 wt%. Compositions H and I include TiO₂ in the range of 0-0.9 wt%, preferably in the range of 0.25 - 0.75 wt% and more preferably in the range of 0.50-0.6 wt%; Na₂O in the range of 0.75-1.25, preferably in the range of 0.75-1.00 wt% and more preferably in the range of 0.85-0.95wt%; and Fe₂O₃ in the range of up to 0.50 wt%, preferably 0.10-0.40 wt% and more preferably in the range of 0.30-0.40 wt%.

A glass composition having the ingredients of Table 2 within the above ranges and at least one of the following relationships provides a glass composition having a forming temperature below 1240°C and a delta T of greater than 50°C, e.g.:

	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
30	RO (CaO + MgO)	26 to 28 wt%	26.00 to 27.25 wt%
	SiO ₂ / CaO	2.10 to 2.80	2.30 to 2.80
	SiO ₂ / RO	1.90 to 2.55	1.90 to 2.40
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00;	4.20 to 5.00
	Al ₂ O ₃ /CaO	0.40 to 0.75	0.50 to 0.60
35	SiO ₂ + Al ₂ O ₃	66 to 73.7 wt%	70.80 to 73.7 wt%
	R ₂ O + RO	27 to 28.15 wt	27.15 to 20 wt%
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO)	2.0 to 3.0	2.30 to 3.00

SiO ₂ – RO	26.5 to 36.6 wt%	30.50 to 36.60 wt%
Al ₂ O ₃ /RO	0.4 to 0.6	0.46 to 0.56

The Type 1 glass compositions are not expected to have any Li₂O or K₂O,
 5 therefore R₂O is equal to the wt% of Na₂O.

As can be appreciated, Table 2 also provides ranges for the ingredients and the relationships. For example, but not limiting to the invention, the ranges for the ingredients of the glass compositions listed on Table 2 are as follows:

10	SiO ₂	57.45 to 59.05 percent by weight;
	Al ₂ O ₃	12.20 to 13.40 percent by weight;
	CaO	23.75 to 24.35 percent by weight;
	MgO	2.55 percent by weight;
	TiO ₂	1.10 percent by weight;
15	Na ₂ O ₃	0.90 percent by weight, and
	Fe ₂ O ₃	0.25 percent by weight.

The range of the mathematical relationships of the ingredients from Table 2 for the glass compositions listed on Table 2 is found in Table 21 in the column
 20 entitled "Type 1 Glasses". The glasses on Table 2 have a log₃ forming temperature in the range of 1232 to 1240°C and a ΔT in the range of 58 to 74°C.

Table 2 also provides ranges for the Examples 1-6. More particularly, from Table 2 Example 1-6 glass compositions have the following ingredients and ranges:

25	SiO ₂	57.45 to 59.05 percent by weight;
	Al ₂ O ₃	12.20 to 13.68 percent by weight;
	CaO	23.75 to 24.50 percent by weight;
	MgO	2.55 to 2.58 percent by weight;
	TiO ₂	0.55 to 1.10 percent by weight;
30	Na ₂ O ₃	0.90 to 0.91 percent by weight, and
	Fe ₂ O ₃	0.25 to 0.35 percent by weight.

The range of the mathematical relationship of the ingredients from Table 2 for the glass compositions of Examples 1- 6 can be found on Table 21 under Type 1
 35 Glasses. The glass compositions of Examples 1 – 6 have a log₃ forming temperature in the range of 1232 to 1240°C and a ΔT in the range of 58 to 74°C.

Further, Table 2 provides ranges for the Examples H and I. More particularly, from Table 2 Examples H and I glass compositions have the following ingredients and ranges:

5	SiO ₂	57.60 to 58.18 percent by weight;
	Al ₂ O ₃	13.55 to 13.68 percent by weight;
	CaO	23.75 to 24.50 percent by weight;
	MgO	2.55 to 2.58 percent by weight;
	TiO ₂	0.55 percent by weight;
10	Na ₂ O ₃	0.90 to 0.91 percent by weight, and
	Fe ₂ O ₃	0.35 percent by weight.

the ranges for the mathematical relationships of the ingredients from Table 2 are as follows:

	RO	26.33 to 27.05 wt%
15	SiO ₂ /CaO	2.35 to 2.45
	SiO ₂ /RO	2.13 to 2.20
	SiO ₂ /Al ₂ O ₃	4.25
	Al ₂ O ₃ /CaO	0.55 to 0.58
	SiO ₂ + Al ₂ O ₃	71.15 to 71.86 wt%
20	SiO ₂ – RO	30.55 to 31.85 wt%
	Al ₂ O ₃ /RO	0.50 to 0.52
	R ₂ O + RO	27.24 to 27.95 wt%
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO)	2.55 to 2.64

The glass compositions of Examples H and I have a log3 forming temperature in the range of 1238 to 1240°C and a ΔT of 55°C

Tables 3-11 (Type 2 Glasses) include glass compositions of a quaternary system that includes SiO₂ in the range of 50-60 wt%, preferably in the range of 52.25-59.00 wt% and more preferable in the range of 52.90-58.00 wt%; Al₂O₃ in the range of 10-14 wt%, preferably in the range of 11-14 wt% and more preferably in the range of 12 -14 wt%; CaO in the range of 21-26 wt%, preferable in the range of 21.50-25.50 wt% and more preferable in the range of 22-25 wt%, and MgO in the range of 1-4 wt%, preferably in the range of 1.25-3.50 wt% and more preferably in the range of 1.45-3.25 wt% . The compositions of Tables 3-11 include B₂O₃ in an amount within the range of greater than 0 to 5.10 wt%, e.g. 0.90 – 5.10 wt%. The compositions of Table 3-11 further contemplate TiO₂ in the range of 0.25-1.25 wt%, more likely in the range of 0.40- 1.20 wt% and most likely in the range of 0.45-1.15

wt%; Na₂O in the range of 0.25-1.25, preferably in the range of 0.35-1.00 wt% and more preferably in the range of 0.40-0.95 wt%; K₂O expected in amounts up to 0.60 wt%; and Fe₂O₃ in the range of up to .50 wt%, preferably up to -0.45 wt% and more preferably up to 0.40 wt%. Other ingredients included in the glass compositions of
 5 Tables 3-11 but not limited thereto are fluorine in amounts up to 0.50 wt%; SrO in amounts up to 0.15 wt% and Cr₂O₃ in amounts up to 0.15 wt%.

A glass composition having ingredients of Tables 3-11 within the above ranges and at least one of the following relationships provides a glass composition
 10 having a forming temperature below 1240°C and a delta T of greater than 50°C:

	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
	RO (CaO + MgO)	24 to 29 wt%	24.75 to 27.60 wt%
	SiO ₂ / CaO	2.10 to 2.80	2.15 to 2.75
15	SiO ₂ / RO	1.95 to 2.55	1.90 to 2.40
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00	3.70 to 4.90
	Al ₂ O ₃ /CaO	0.45 to 0.65	0.45 to 0.65
	SiO ₂ + Al ₂ O ₃	66 to 73.7 wt%	66 to 72.1 wt%
	R ₂ O + RO + B ₂ O ₃	27.5 to 34 wt%	28 to 33 wt%
20	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.00 to 3.00	2.00 to 2.70
	SiO ₂ – RO	26.5 to 36.6 wt%	26.5 to 34 wt%
	Al ₂ O ₃ /RO	0.40 to 0.60	0.46 to 0.56

Type 2 glasses of Tables 3-11 do not consider Li₂O as an ingredient;
 25 therefore for Tables 3-11, R₂O is equal to the sum of the wt% of K₂O and Na₂O. If one of the ingredients is not present in the glass it is given a 0 wt%. For the glasses listed on each of the Tables 3,4,6,7,10 and 11, only the addition of Na₂O is considered; therefore for the glasses on the individual Tables 3,4,6,7,10 and 11, R₂O is equal to the wt% of Na₂O. For the glasses listed on the individual Tables 5,8 and
 30 9, Na₂O and K₂O are considered; therefore for the glasses on the individual Tables 5,8 and 9, R₂O is equal to the sum of the wt% of Na₂O and K₂O

As can be appreciated, each of the Tables 3-11 provides ranges for the ingredients and the relationships. For example and not limiting to the invention,
 35 Tables 3-11 provide glass compositions having the following ingredients in the following ranges:

	SiO ₂	53.00 to 57.75 percent by weight;
	Al ₂ O ₃	12.20 to 14 percent by weight;
	CaO	22.25 to 24.95 percent by weight;
	MgO	1.50 to 3.00 percent by weight;
5	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O	0.45 to 0.90 percent by weight;
	K ₂ O	0 to 0.38 percent by weight;
	Fe ₂ O ₃	0 to 0.30 percent by weight;
	B ₂ O ₃	1.30 to 5.02 percent by weight;
10	F	0 to 0.50 percent by weight;
	SrO	0 to 0.13 percent by weight, and
	Cr ₂ O ₃	0 to 0.13 percent by weight.

The mathematical relationship of the ingredients is found on Table 21 in the
 15 column entitled "Type 2 Glasses".

Table 3 provides glass compositions having ingredients in the following
 ranges:

	SiO ₂	56.00 to 56.65 percent by weight;
20	Al ₂ O ₃	13.05 to 13.60 percent by weight;
	CaO	23.50 to 24.25 percent by weight;
	MgO	2.50 to 2.55 percent by weight;
	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
25	Fe ₂ O ₃	0.25 percent by weight, and
	B ₂ O ₃	2.00 percent by weight.

The ranges for the mathematical relationships of ingredients of the glass
 compositions on Table 3 from Table 3 are as follows:

30	RO	26.05 to 26.75 wt%
	SiO ₂ /CaO	2.31 to 2.41
	SiO ₂ /RO	2.09 to 2.17
	SiO ₂ /Al ₂ O ₃	4.12 to 4.28
	Al ₂ O ₃ /CaO	0.56 to 0.57
35	SiO ₂ + Al ₂ O ₃	69.60 to 69.95 wt%
	SiO ₂ – RO	29.25 to 30.60 wt%
	Al ₂ O ₃ /RO	0.50 to 0.52

R2O +RO+B ₂ O ₃	28.95 to 29.65 wt%
(SiO ₂ + Al ₂ O ₃)/(R2O +RO+B ₂ O ₃)	2.35 to 2.41

The glass compositions of Table 3 have a log3 forming temperature in the range of 1200 to 1220°C and a ΔT is in the range of 56 to 69°C.

5

Table 4 provides glass compositions having Ingredients in the following ranges:

	SiO ₂ is	56.25 to 57.75 percent by weight;
	Al ₂ O ₃ is	12.20 to 13.20 percent by weight;
10	CaO	23.75 to 24.25 percent by weight;
	MgO	2.55 percent by weight;
	TiO ₂	1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
	Fe ₂ O ₃	0.25 percent by weight, and
15	B ₂ O ₃	1.30 to 1.40 percent by weight.

The ranges for the mathematical relationships of the ingredients for the glass compositions of Table 4 from Table 4 are as follows:

	RO	26.30 to 26.80 wt%
20	SiO ₂ /CaO	2.32 to 2.43
	SiO ₂ /RO	2.10 to 2.20
	SiO ₂ /Al ₂ O ₃	4.26 to 4.73
	Al ₂ O ₃ /CaO	0.51 to 0.56
	SiO ₂ + Al ₂ O ₃	69.45 to 69.95 wt%
25	SiO ₂ – RO	29.45 to 31.45 wt%
	Al ₂ O ₃ /RO	0.46 to 0.50
	R2O +RO+B ₂ O ₃	28.50 to 29.00 wt%
	(SiO ₂ + Al ₂ O ₃)/(R2O +RO+B ₂ O ₃)	2.39 to 2.45.

The glass compositions of Table 4 have a log3 forming temperature in the range of 1200 to 1218°C and a ΔT in the range of 55°C to 70°C.

30

The glass compositions of Table 5 have the following ingredients in the following ranges:

	SiO ₂	55.19 to 56.00 percent by weight;
35	Al ₂ O ₃	13.10 to 13.80 percent by weight;
	CaO	24.50 to 24.67 percent by weight;
	MgO	2.55 to 2.95 percent by weight;

	TiO ₂	1.10 percent by weight;
	Na ₂ O	0.45 percent by weight;
	K ₂ O	0.45 to 0.58 percent by weight;
	Fe ₂ O ₃	0.25 to 0.38 percent by weight, and
5	B ₂ O ₃	1.30 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 5 from Table 5 are as follows:

	RO	27.08 to 27.45 wt%
10	SiO ₂ /CaO	2.25 to 2.28
	SiO ₂ /RO	2.01 to 2.07
	SiO ₂ /Al ₂ O ₃	4.01 to 4.19
	Al ₂ O ₃ /CaO	0.53 to 0.56
	SiO ₂ + Al ₂ O ₃	68.75 to 69.37 wt%
15	SiO ₂ – RO	27.78 to 28.92 wt%
	Al ₂ O ₃ /RO	0.48 to 0.51
	R ₂ O + RO + B ₂ O ₃	29.28 to 29.74 wt%
	(SiO ₂ + Al ₂ O ₃) / (R ₂ O + RO + B ₂ O ₃)	2.31 to 2.37

The glass compositions of Table 5 have a log3 forming temperature in the range of 1210 to 1222°C and a ΔT in the range of 53 to 79°C.

Table 6 provides glass compositions having ingredients in the following ranges:

	SiO ₂	56.15 to 57.60 percent by weight;
25	Al ₂ O ₃	13.25 to 13.95 percent by weight;
	CaO	24.40 to 24.95 percent by weight;
	MgO	2.55 percent by weight;
	TiO ₂	0.55 percent by weight;
	Na ₂ O	0.90 percent by weight;
30	Fe ₂ O ₃	0.25 to 0.35 percent by weight, and
	B ₂ O ₃	1.30 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 6 from Table 6 are as follows:

35	RO	26.95 to 27.50 wt%
	SiO ₂ /CaO	2.25 to 2.36
	SiO ₂ /RO	2.04 to 2.14

	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.01 to 4.66
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.54 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.50 to 69.99 wt%
	$\text{SiO}_2 - \text{RO}$	28.65 to 30.65 wt%
5	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.51
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	29.15 to 29.70 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3) / (\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.34 to 2.40.

The glass compositions of Table 6 have a log3 forming temperature in the range of 1211 to 1220°C and a ΔT is in the range of 52 to 66°C.

10

Table 7 provides glass compositions having ingredients in the following ranges:

	SiO_2	55.25 to 56.15 percent by weight;
	Al_2O_3	13.05 to 13.30 percent by weight;
15	CaO	23.00 to 24.20 percent by weight;
	MgO	2.55 percent by weight;
	TiO_2	0.25 to 1.25 percent by weight;
	Na_2O	0.90 percent by weight;
	Fe_2O_3	0.25 percent by weight; and
20	B_2O_3	3.00 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 7 from Table 7 are as follows:

	RO	25.55 to 26.75 wt%
25	SiO_2/CaO	2.28 to 2.44
	SiO_2/RO	2.07 to 2.20
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.15 to 4.30
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.55 to 0.56
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	68.20 to 69.20 wt%
30	$\text{SiO}_2 - \text{RO}$	28.45 to 30.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.50 to 0.51
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	29.45 to 30.65 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3) / (\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.24 to 2.35

The glass compositions of Table 7 have a log3 forming temperature in the range of 1193 to 1212°C and a ΔT is in the range of 64 to 90°C.

35

Table 8 provides glass compositions having ingredients in the following ranges:

	SiO ₂	54.12 to 55.25 percent by weight;
	Al ₂ O ₃	13.20 to 13.40 percent by weight;
5	CaO	24.20 to 24.55 percent by weight;
	MgO	2.55 percent by weight;
	TiO ₂	0.55 percent by weight;
	Na ₂ O	0.45 to 0.50 percent by weight;
	K ₂ O	0.45 to 0.55 percent by weight;
10	Fe ₂ O ₃	0.25 to 0.28 percent by weight;
	B ₂ O ₃	3.00 percent by weight;
	F	up to 0.20 percent by weight, and
	SrO	up to 0.12 percent by weight.

15 The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 8 from Table 8 are as follows:

	RO	26.75 to 27.55 wt%
	SiO ₂ /CaO	2.20 to 2.28
	SiO ₂ /RO	1.96 to 2.07
20	SiO ₂ /Al ₂ O ₃	4.06 to 4.15
	Al ₂ O ₃ /CaO	0.54 to 0.55
	SiO ₂ + Al ₂ O ₃	67.55 to 68.55 wt%
	SiO ₂ – RO	26.57 to 28.30 wt%
	Al ₂ O ₃ /RO	0.49 to 0.50
25	R2O +RO+B ₂ O ₃	30.65 to 31.40 wt%
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.14 to 2.22

The glass compositions of Table 8 have a log3 forming temperature in the range of 1190 to 1204°C and a ΔT is in the range of 55 to 83°C.

30 Table 9 provides glass compositions having Ingredients in the following ranges:

	SiO ₂	53.00 to 53.50 percent by weight;
	Al ₂ O ₃	13.10 to 14.00 percent by weight;
	CaO	24.00 percent by weight;
35	MgO	1.25t 2.50ercent by weight;
	TiO ₂	0.50 percent by weight;
	Na ₂ O	0.90 percent by weight;

	K ₂ O	0.37 percent by weight;
	Fe ₂ O ₃	0.10 percent by weight;
	B ₂ O ₃	4.93 to 5.02 percent by weight;
	F	0.50 percent by weight;
5	SrO	0.13 percent by weight, and
	Cr ₂ O ₃	0.13 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 9 from Table 9 are as follows:

10	RO	25.50 to 26.50 wt%
	SiO ₂ /CaO	2.21 to 2.23
	SiO ₂ /RO	2.00 to 2.10
	SiO ₂ /Al ₂ O ₃	3.82 to 4.05
	Al ₂ O ₃ /CaO	0.55 to 0.58
15	SiO ₂ + Al ₂ O ₃	66.10 to 67.50 wt%
	SiO ₂ – RO	26.50 to 28.00 wt%
	Al ₂ O ₃ /RO	0.49 to 0.55
	R ₂ O + RO + B ₂ O ₃	31.70 to 32.79 wt%
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.02 to 2.13

20 The glass compositions of Table 9 have a log₃ forming temperature in the range of 1167 to 1177 and a ΔT is in the range of 57 to 69°C.

Table 10 provides glass compositions having ingredients in the following ranges:

25	SiO ₂	55.40 to 57.75 percent by weight;
	Al ₂ O ₃	12.20 to 13.80 percent by weight;
	CaO	22.25 to 24.85 percent by weight;
	MgO	2.05 to 2.60 percent by weight;
	TiO ₂	0.50 to 1.10 percent by weight;
30	Na ₂ O	0.90 percent by weight;
	Fe ₂ O ₃	0.25 percent by weight, and
	B ₂ O ₃	1.00 to 3.00 percent by weight.

35 The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 10 from Table 10 are as follows:

	RO	26.80 to 27.35 wt%
	SiO ₂ /CaO	2.23 to 2.55

	SiO ₂ /RO	2.05 to 2.27
	SiO ₂ /Al ₂ O ₃	4.04 to 4.69
	Al ₂ O ₃ /CaO	0.51 to 0.59
	SiO ₂ + Al ₂ O ₃	69.00 to 70.95 wt%
5	SiO ₂ – RO	28.05 to 32.55 wt%
	Al ₂ O ₃ /RO	0.46 to 0.53
	R ₂ O + RO + B ₂ O ₃	28.15 to 30.25 wt%
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.28 to 2.67

The glass compositions of Table 10 have a log3 forming temperature in the
 10 range of 1202 to 1240°C and a ΔT is in the range of 53 to 100°C.

The glass compositions listed on Table 10 and the glasses within the scope of
 the embodiment of Table 10 have a forming temperature in the range of 1202 to
 1240°C. It should be noted that the measured delta T for Example 91 was 34°C; it is
 15 believed that this is a measuring error the liquidus temperature because the glass
 composition of Example 90 has similar ingredients, a lower liquidus temperature and
 a delta T of 100°C. Therefore the delta T of Example 91 is considered to be about
 90°C. The preferred glass compositions from Table 10 are those that provide the
 forming temperature range 1202 to 1219°C and a delta T greater than 5°C, more
 20 particularly Examples 78 - 91.

The glass compositions of Examples 78 – 91 of Table 10 from Table 10 have
 the following ingredients in the following ranges:

	SiO ₂	55.40 to 56.65 percent by weight;
25	Al ₂ O ₃	13.05 to 13.80 percent by weight;
	CaO	23.00 to 24.85 percent by weight;
	MgO	2.50 to 2.55 percent by weight;
	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
30	Fe ₂ O ₃	0.25 percent by weight, and
	B ₂ O ₃	2.00 to 3.00 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass
 compositions of Examples 78 – 91 of Table 10 from Table 10 are as follows:

35	RO	25.55 to 27.35 wt%
	SiO ₂ /CaO	2.23 to 2.44
	SiO ₂ /RO	2.03 to 2.20

	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.06 to 4.34
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.54 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	68.95 to 69.95 wt%
	$\text{SiO}_2 - \text{RO}$	28.05 to 30.60 wt%
5	$\text{Al}_2\text{O}_3/\text{RO}$	0.49 to 0.53
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	28.95 to 30.25 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.28 to 2.41

The glass composition of Examples 78 -91 have a log3 forming temperature in the range of 1202 to 1219°C and a ΔT is in the range of 53 to 100°C.

10

The glass compositions of Table 11 from Table 11 have the following ingredients in the following ranges:

	SiO_2	56.10 to 57.75 percent by weight;
	Al_2O_3	12.20 to 13.38 percent by weight;
15	CaO	23.75 to 24.42 percent by weight;
	MgO	2.55 percent by weight;
	TiO_2	0.55 to 1.10 percent by weight;
	Na_2O	0.90 percent by weight;
	Fe_2O_3	0.25 percent by weight; and
20	B_2O_3	1.30 to 1.40 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 11 from Table 11 are as follows:

	RO	26.30 to 26.97 wt%
25	SiO_2/CaO	2.30 to 2.43
	SiO_2/RO	2.08 to 2.20
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.19 to 4.73
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.54
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.48 to 69.95 wt%
30	$\text{SiO}_2 - \text{RO}$	29.13 to 31.45 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.50
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	28.60 to 29.17 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.38 to 2.44

35 The glass compositions of Table 11 have a log3 forming temperature in the range of 1215 to 1218°C and a ΔT in the range of 63°C to 65°C.

Tables 12 and 13 (Type 3 Glasses) include glass compositions of a quaternary system that includes SiO_2 in the range of 55-62 wt%, preferably in the range of 56-61 wt% and more preferably in the range of 57.5-61 wt%; Al_2O_3 in the range of 10-14 wt%, preferably in the range of 11-14 wt% and more preferably in the range of 11.75 –13.75 wt%; CaO in the range of 20-26 wt%, preferable in the range of 21.50-25.00wt% and more preferable in the range of 21.75-24.50 wt%, and MgO in the range of 1-4 wt%, preferably in the range of 1.35-3.50 wt% and more preferably in the range of 1.60-3.25 wt%. The compositions of Tables 12 and 13 are boron free. The compositions of Tables 12 and 13 contemplate a TiO_2 in the range of 0.25-1.75 wt%, more likely in the range of 0.40 - 1.60 wt% and most likely more preferably in the range of 0.45-1.55 wt%; Na_2O in amounts up to 0.75 wt%, preferably in amounts up to 0.70 wt% and more preferably in amounts up to 0.65 wt%; Li_2O in amounts in the range of 0.10 to 1.25 wt%, preferably in the range of 0.20 to 1.10 wt%, and more preferably in the range of 0.30 to 1.00 wt%, and Fe_2O_3 in the range of up to 0.50 wt%, preferably up to 0.45 wt% and more preferably up to 0.30 wt%.

A glass composition having ingredients of Tables 12 and 13 within the above ranges and at least one of the following relationships provides a glass composition having a forming temperature below 1240°C and a delta T of greater than 50°C :

	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
	RO ($\text{CaO} + \text{MgO}$)	23.50 to 27.50 wt%	23.75 to 27.00 wt%
25	SiO_2/CaO	2.10 to 2.80	2.30 to 2.80
	SiO_2/RO	1.90 to 2.55	2.10 to 2.55
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 5.00	4.20 to 5.00
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.65	0.45 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66 to 73.7 wt%	70.8 to 73.7 wt%
30	$\text{R}_2\text{O} + \text{RO}$	24.75 to 28 wt%	25 to 27.75 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.00 to 3.00	2.30 to 3.00
	$\text{SiO}_2 - \text{RO}$	26.5 to 36.6 wt%	30.50 to 36.6 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60	0.46 to 0.53

The Type 3 Glasses do not consider the addition of K_2O ; therefore for Type 3 Glasses R_2O is equal to the sum of the wt% of Na_2O and Li_2O .

As can be appreciated, each of the Tables 12 and 13 provides ranges for the ingredients and the relationships. More particularly, the glass compositions of Tables 12 and 13 from Tables 12 and 13 have the following ingredients in the following ranges:

5	SiO ₂	57.65 to 60.75 percent by weight;
	Al ₂ O ₃	12.00 to 13.64 percent by weight;
	CaO	22 to 24.155 percent by weight;
	MgO	1.70 to 3.40 percent by weight;
	TiO ₂	0.50 to 1.50 percent by weight;
10	Na ₂ O	0.30 to 0.60 percent by weight;
	Li ₂ O	0.30 to 1.00 percent by weight, and
	Fe ₂ O ₃	up to 0.25 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Tables 12 and 13 from Tables 12 and 13 are on Table 21 under the column entitled "Type 3 Glasses". The glass compositions of Tables 12 and 13 have a log₃ forming temperature in the range of 1205 to 1240°C, and a ΔT in the range of 50 to 100°C.

The glass compositions of Table 12 from Table 12 have the following ingredients in the following ranges:

	SiO ₂	58.25 to 59.97 percent by weight;
	Al ₂ O ₃	12.19 to 13.64 percent by weight;
	CaO	22.04 to 23.65 percent by weight;
25	MgO	2.50 to 3.12 percent by weight;
	TiO ₂	0.50 to 1.50 percent by weight;
	Na ₂ O	up to 0.30 percent by weight;
	Li ₂ O	0.90 to 0.91 percent by weight, and
	Fe ₂ O ₃	0.20 to 0.25 percent by weight.

30

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 12 are as follows:

	RO	24.94 to 26.20 wt%
	SiO ₂ /CaO	2.47 to 2.72
35	SiO ₂ /RO	2.23 to 2.40
	SiO ₂ /Al ₂ O ₃	4.31 to 4.92

	$\text{Al}_2\text{O}_3/\text{CaO}$	0.55 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.55 to 73.03 wt%
	$\text{SiO}_2 - \text{RO}$	32.15 to 34.91 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.48 to 0.52
5	$\text{R}_2\text{O} + \text{RO}$	25.84 to 27.10 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.64 to 2.79

The glass compositions of Table 12 have a log3 forming temperature in the range of 1211°C and to 1218°C, and a ΔT in the range of 56 to 68°C.

10 The glass compositions of Table 13 from Table 13 have the following ingredients in the following ranges:

	SiO_2	57.65 to 60.75 percent by weight;
	Al_2O_3	12.00 to 13.40 percent by weight;
	CaO	22.00 to 24.15 percent by weight;
15	MgO	1.70 to 3.12 percent by weight;
	TiO_2	0.50 to 1.50 percent by weight;
	Na_2O	0.45 to 0.90 percent by weight;
	Li_2O	0.45 to 1.00 percent by weight, and
	Fe_2O_3	up to 0.25 percent by weight.

20

The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 13 from Table 13 is as follows:

	RO	24.25 to 26.70 wt%
	SiO_2/CaO	2.39 to 2.72
25	SiO_2/RO	2.16 to 2.51
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.30 to 4.92
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.05 to 73.67 wt%
	$\text{SiO}_2 - \text{RO}$	31.35 to 36.56 wt%
30	$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.55
	$\text{R}_2\text{O} + \text{RO}$	24.91 to 27.90 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.30 to 2.96

The glass compositions have a log3 forming temperature in the range of 1205 to 1240°C and a ΔT are in the range of 50 to 101°C.

35

The glass compositions listed on Table 13 and the glasses within the scope of the embodiment of Table 13 have a forming temperature in the range of 1205 to 1240 °C and a delta T in the range of 50 –100°C; however the preferred glass compositions from Table 13 are those that provide the forming temperature range of 1205 to 1220°C and more preferably in the range of 1205 – 1218 °C. more particularly Examples 123,124,125,127-132,147,153, 155, 157, 160 and 161 with the appropriate delta T, e.g. 50°C or greater.

The glass compositions of Examples 123,124,125,127-132,147,153, 155, 157, 160 and 161 from Table 13 have the following ingredients in the following ranges:

	SiO ₂	57.65 to 60.33 percent by weight;
	Al ₂ O ₃	12.22 to 13.40 percent by weight;
	CaO	22.00 to 24.15 percent by weight;
15	MgO	2.30 to 3.40 percent by weight;
	TiO ₂	0.50 to 1.50 percent by weight;
	Na ₂ O	up to 0.45 percent by weight;
	Li ₂ O	0.45 to 1.00 percent by weight, and
	Fe ₂ O ₃	up to 0.25 percent by weight.

20

The ranges for the mathematical relationships of the ingredients of Examples 123,124,125,127-132,147,153, 155, 157, 160 and 161 from Table 13 are as follows:

	RO	24.84 to 26.70 wt%
	SiO ₂ /CaO	2.39 to 2.72
25	SiO ₂ /RO	2.16 to 2.42
	SiO ₂ /Al ₂ O ₃	4.30 to 4.92
	Al ₂ O ₃ /CaO	0.52 to 0.59
	SiO ₂ + Al ₂ O ₃	71.05 to 72.80 wt%
	SiO ₂ – RO	31.35 to 35.37 wt%
30	Al ₂ O ₃ /RO	0.47 to 0.52
	R2O +RO	25.74 to 27.60 wt%
	(SiO ₂ + Al ₂ O ₃)/(R2O +RO)	2.30 to 2.81

The glass compositions have a log3 forming temperature in the range of 1205 to 1220°C and in the range of 1205 to 1218°C, and a ΔT in the range of equal to and greater than 50°C and equal to and less than 60°C.

35

The selection of the above examples is made based on the low forming temperature. As can be appreciated, if a high delta T is of interest then Examples 135-141, for example, would be of interest because they have a delta T in the range of 77 -100 °C.

5

The glass compositions of Examples 135 - 141 from Table 13 have the following ingredients in the following ranges:

	SiO ₂	59.55 to 60.57 percent by weight;
	Al ₂ O ₃	12.25 to 13.10 percent by weight;
10	CaO	22.31 to 23.85 percent by weight;
	MgO	1.70 to 3.10 percent by weight;
	Na ₂ O	up to 0.30 percent by weight
	TiO ₂	1.10 percent by weight, and
	Li ₂ O	up to 0.60 percent by weight.

15

The ranges for the mathematical relationships of the ingredients of Examples 135 – 141 from Table 13 is as follows:

	RO	24.01 to 25.95 wt%
	SiO ₂ /CaO	2.50 to 2.71
20	SiO ₂ /RO	2.29 to 2.52
	SiO ₂ /Al ₂ O ₃	4.62 to 4.88
	Al ₂ O ₃ /CaO	0.52 to 0.59
	SiO ₂ + Al ₂ O ₃	71.80 to 73.67 wt%
	SiO ₂ – RO	33.60 to 36.56 wt%
25	Al ₂ O ₃ /RO	0.47 to 0.55
	R ₂ O + RO	24.91 to 26.85 wt%
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO)	2.67 to 2.96

The glass compositions have a log3 forming temperature in the range of 1234 to 1240°C, and a ΔT is in the range of 61 to 100°C.

30

Tables 14 and 15 (Type 4 Glasses) include glass compositions of a quaternary system that includes SiO₂ in the range of 55-62 wt%, preferably in the range of 56-61 wt% and more preferable in the range of 57-60 wt%; Al₂O₃ in the range of 10-14 wt%, preferably in the range of 11-14 wt% and more preferable in the range of 12 –13.75 wt%; CaO in the range of 21-26 wt%, preferable in the range of 21.50-25.00 wt% and more preferable in the range of 21.75-24.50 wt%, and MgO in the range of 1-3.25 wt%, preferably in the range of 1.50-3.00 wt% and more

35

preferably in the range of 1.75-2.75 wt% . The compositions of Tables 14 and 15 are boron free. The compositions of Tables 14 and 15 contemplate TiO_2 in the range of 0.25-1.75 wt%, more likely in the range of 0.40- 1.50 wt% and most likely in the range of 0.45-1.25 wt%; Li_2O in amounts in the range of 0.25 to 1.25 wt%, preferably
 5 in the range of 0.30 to 1.10 wt%, and more preferably in the range of 0.40 to 1.00 wt%, ZnO in amounts in the range of 0.25 to 1.25 wt%, preferably in the range of 0.30 to 1.15 wt%, and more preferably in the range of 0.40 to 1.10 wt%, and Fe_2O_3 in the range of up to 0.50 wt%, preferably up to 0.35 wt% and more preferably up to 0.30 wt%.

10

A glass composition having ingredients of Tables 14 and 15 within the above ranges and at least one of the following relationships provides a glass composition having a forming temperature below 1240°C and a delta T of greater than 50°C :

15	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
	RO ($\text{CaO} + \text{MgO}$)	24 to 28 wt%	25.25 to 27.00 wt%
	SiO_2/CaO	2.10 to 2.80	2.30 to 2.60
	SiO_2/RO	1.90 to 2.55	2.10 to 2.55
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 5.00	4.20 to 5.00
20	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.65	0.50 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	68 to 73.7 wt%	70.8 to 72 wt%
	$\text{R}_2\text{O} + \text{RO}$	25 to 30 wt%	26.0 to 28 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.00 to 3.00	2.30 to 3.00
	$\text{SiO}_2 - \text{RO}$	26.5 to 36.60 wt%	30.5 to 36.60 wt%
25	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60	0.46 to 0.53

The Type 4 Glasses are shown only to have Li_2O ; therefore for Type 4 Glasses R_2O is equal to the wt% of Li_2O

As can be appreciated, each of the Tables 14 and 15 provides ranges for the
 30 ingredients and the relationships. More particularly, the glass compositions of Tables 14 and 15 from Tables 14 and 15 have the following ingredients in the following ranges:

	SiO_2	57.35 to 59.618.30 percent by weight;
	Al_2O_3	12.16 to 13.63 percent by weight;
35	CaO	22.85 to 24.22 percent by weight;
	MgO	1.90 to 2.55 percent by weight;
	TiO_2	0.50 to 1.10 percent by weight;

Li ₂ O	0.45 to 0.90 percent by weight;
ZnO	0.45 to 1.00 percent by weight, and
Fe ₂ O ₃	up to 0.25 percent by weight.

in the range of 1195 to 1229°C, and a ΔT is in the range of 54 to 71°C. The ranges
 5 for the mathematical relationships of the ingredients of the glass compositions of
 Tables 14 and 15 are found on Table 21 under the column entitled "Type 4 Glasses".
 The glass compositions have a log3 forming temperature

10 The glass compositions of Table 14 from Table 14 have the following
 ingredients in the following ranges:

SiO ₂	58.00 to 58.30 percent by weight;
Al ₂ O ₃	13.03 to 13.33 percent by weight;
CaO	22.85 to 23.84 percent by weight;
MgO	2.50 to 2.55 percent by weight;
15 TiO ₂	0.50 to 1.10 percent by weight;
Li ₂ O	0.90 percent by weight;
ZnO	1.00 percent by weight, and
Fe ₂ O ₃	up to 0.25 percent by weight.

20 The ranges for the mathematical relationships of the ingredients of the glass
 compositions of Table 14 from Table 14 are as follows:

RO	25.40 to 26.34 wt%
SiO ₂ /CaO	2.43 to 2.54
SiO ₂ /RO	2.20 to 2.29
25 SiO ₂ /Al ₂ O ₃	4.36 to 4.47
Al ₂ O ₃ /CaO	0.55 to 0.58
SiO ₂ + Al ₂ O ₃	71.13 to 71.58 wt%
SiO ₂ – RO	31.66 to 32.75 wt%
Al ₂ O ₃ /RO	0.49 to 0.52
30 R ₂ O + RO	26.30 to 27.24 wt%
(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO)	2.61 to 2.71

The glass compositions have a log3 forming temperature in the range of 1204
 to 1213°C, and a ΔT in the range of 56 to 71°C.

35 The glass compositions of Table 15 from Table 15 have the following
 ingredients in the following ranges:

	SiO ₂	57.35 to 59.61 percent by weight;
	Al ₂ O ₃	12.16 to 13.63 percent by weight;
	CaO	23.14 to 24.22 percent by weight;
	MgO	1.90 to 2.55 percent by weight;
5	TiO ₂	0.50 to 1.10 percent by weight;
	Li ₂ O	0.45 to 0.90 percent by weight;
	ZnO	0.45 to 1.00 percent by weight, and
	Fe ₂ O ₃	up to 0.25 percent by weight.

10 The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 15 from Table 15 are as follows:

	RO	25.64 to 26.60 wt%
	SiO ₂ /CaO	2.41 to 2.54
	SiO ₂ /RO	2.18 to 2.29
15	SiO ₂ /Al ₂ O ₃	4.26 to 4.90
	Al ₂ O ₃ /CaO	0.50 to 0.59
	SiO ₂ + Al ₂ O ₃	70.55 to 71.77 wt%
	SiO ₂ – RO	31.15 to 33.61 wt%
	Al ₂ O ₃ /RO	0.47 to 0.53
20	R2O +RO	26.45 to 27.50 wt%
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO)	2.60 to 2.71

The glass compositions of Table 15 have a log3 forming temperature in the range of 1195 to 1229°C, and a ΔT in the range of 54 to 59°C.

25 **Table 16 (Type 5 Glasses)** include glass compositions of a quaternary system that includes SiO₂ in the range of 55-62 wt%, preferably in the range of 56-61 wt% and more preferable in the range of 58-60 wt%; Al₂O₃ in the range of 10-14 wt%, preferably in the range of 11.00-13.5 wt% and more preferably in the range of 11.75 –13.25 wt%; CaO in the range of 21-25 wt%, preferable in the range of 21.25-24.00
30 wt% and more preferable in the range of 21.25-23.00 wt%, and MgO in the range of 1-4.00 wt%, preferably in the range of 1.25-3.50 wt% and more preferably in the range of 1.50-3.50 wt%. The compositions of Table 16 are boron free. The compositions of Table 16 contemplate TiO₂ in the range of 0.50-2.00 wt%, more likely in the range of 0.50 – 1.50 wt% and more preferably in the range of 0.75-1.25 wt%;
35 Na₂O in amounts in no greater than 2.00 wt%; preferably no greater than 1.50 wt%, and more preferably no greater than 1.25 wt%; ZnO in amounts in the range of 0.50

to 3.00 wt%, preferably in the range of 0.50 to 2.75 wt%, and more preferably in the range of 0.75 to 2.50 wt%, and Fe_2O_3 in the range of up to 0.50 wt%, preferably in the range of up to 0.35wt% and more preferably in the range of up to 0.30 wt%.

- 5 A glass composition having ingredients of Table 16 within the above ranges and at least one of the following relationships provides a glass composition having a forming temperature below 1240°C and a ΔT of greater than 50°C :

	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
10	RO (CaO + MgO)	23 to 28 wt%	24.0 to 27.0 wt%
	SiO_2/CaO	2.10 to 2.80	2.30 to 2.80
	SiO_2/RO	1.90 to 2.55	2.10 to 2.55
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 5.00	4.20 to 5.00
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.65	0.45 to 0.60
15	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66 to 73.7 wt%	70.8 to 73.7 wt%
	R2O + RO	25 to 28 wt%	26.0 to 27.0 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R2O} + \text{RO})$	2.00 to 3.00	2.30 to 3.0
	$\text{SiO}_2 - \text{RO}$	30 to 39 wt%	31.50 to 37. wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60	0.46 to 0.53

- 20 Type 5 Glasses were considered having Na_2O ; therefore R2O is equal to the sum of Na_2O in wt%.

As can be appreciated, Table 16 provides ranges for the ingredients and the relationships. More particularly, the glass compositions of Table 16 from Table 16 have the following ingredients in the following ranges:

25	SiO_2	58.70 to 59.00 percent by weight;
	Al_2O_3	11.90 to 12.00 percent by weight;
	CaO	22.40 to 22.50 percent by weight;
	MgO	3.40 percent by weight;
	TiO_2	1.00 percent by weight;
30	Na_2O	0.90 percent by weight;
	ZnO	1.00 to 1.50 percent by weight, and
	Fe_2O_3	up to 0.20 percent by weight.

- 35 The ranges for the mathematical relationships of the ingredients of the glass compositions of Table 16 from Table 16 are on Table 21 under the column entitled "Type 5 Glasses". The glass compositions of Table 16 have a log3 forming temperature in the range of 1231 to 1234°C , and a ΔT in the range of 50 to 59°C .

Tables 17 and 18 (Type 6 Glasses) include glass compositions of a quaternary system that includes SiO_2 in the range of 50-62 wt%, preferably in the range of 52-61 wt% and more preferable in the range of 53.50-60.25 wt%; Al_2O_3 in the range of 10-14 wt%, preferably in the range of 11.00-14.00 wt% and more preferably in the range of 11.90 –13.75 wt%; CaO in the range of 21-26 wt%, preferable in the range of 22.00-25.00 wt% and more preferable in the range of 22.50-24.25 wt%, and MgO in the range of 1-4.00 wt%, preferably in the range of 1.50-3.00 wt% and more preferably in the range of 2.25-2.75 wt% . The compositions of Tables 17 and 18 have B_2O_3 in the range of 0.50-5.00 wt%, preferably in the range of 0.50-4.00 and more preferably in the range of 0.75-3.25 wt%. The compositions of Tables 17 and 18 contemplate further include TiO_2 in the range of 0.25-2.00 wt%, more likely in the range of 0.35- 1.50 wt% and most likely in the range of 0.40-1.25 wt%; Na_2O in amounts no greater than 1.00 wt%; preferably no greater than 0.90 wt%, and more preferably no greater than 0.75 wt%; K_2O in amounts no greater than 0.50 wt%; preferably no greater than 0.35 wt%, and more preferably no greater than 0.20 wt%; Li_2O in amounts in the range of 0.10 to 1.25 wt%, preferably in the range of 0.20 to 1.10 wt%, and more preferably in the range of 0.25 to 1.00 wt%, and Fe_2O_3 in the range of 0.10 -0.50 wt%, preferably in the range of 0.15-0.50 wt% and more preferably in the range of 0.20-0.40 wt%.

A glass composition having ingredients of Tables 17 and 18 within the above ranges and at least one of the following relationships provides a glass composition having a forming temperature below 1240°C and a delta T of greater than 50°C :

25

	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
	RO ($\text{CaO} + \text{MgO}$)	24 to 28 wt%	25.0 to 27.20 wt%
	SiO_2/CaO	2.10 to 2.80	2.20 to 2.70
	SiO_2/RO	1.90 to 2.55	1.90 to 2.40
30	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.50 to 5.00	4.00 to 5.00
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.60	0.50 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66 to 73.7 wt%	67 to 72.1 wt%
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	25 to 32 wt%	26.50 to 32 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.00 to 3.25	2.30 to 3.00
35	$\text{SiO}_2 - \text{RO}$	26.5 to 36.6 wt%	27 to 36.6 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60	0.46 to 0.56

Type 6 Glasses of Tables 17 and 18 included Li_2O , K_2O and Na_2O ; therefore R2O is equal to the sum in wt% of Li_2O , K_2O and Na_2O . Individual Table 17 includes Li_2O and Na_2O ; therefore R2O for Table 17 is equal to the sum in wt% of Li_2O and Na_2O . Individual Table 18 includes Li_2O , K_2O and Na_2O ; therefore R2O for Table 18 is equal to the sum in wt% of Li_2O , K_2O and Na_2O .

As can be appreciated, Tables 17 and 18 provide ranges for the ingredients and the relationships. More particularly, the glass compositions of Tables 17 and 18 have the following ingredients in the following ranges:

10	SiO_2	54.60 to 59.53 percent by weight;
	Al_2O_3	12.16 to 13.63 percent by weight;
	CaO	22.87 to 24.05 percent by weight;
	MgO	2.00 to 2.55 percent by weight;
	TiO_2	0.49 to 1.10 percent by weight;
15	Na_2O	0 to 0.60 percent by weight;
	K_2O	0 to 0.10 percent by weight;
	Li_2O	0.30 to 0.91 percent by weight;
	Fe_2O_3	0.23 to 0.30 percent by weight, and
	B_2O_3	0.90 to 3.00 percent by weight.

20 The ranges for the mathematical relationships of the ingredients of the glass compositions of Tables 17 and 18 are on Table 21 under the column entitled "Type 6 Glasses". The glass compositions of Table 17 and 18 have a log3 forming temperature in the range of 1187 to 1239°C, and a ΔT in the range of 50 to 142°C.

25 The glass compositions of Table 17 have the following ingredients in the following ranges:

	SiO_2	57.60 to 58.50 percent by weight;
	Al_2O_3	12.76 to 13.43 percent by weight;
	CaO	23.40 to 23.84 percent by weight;
30	MgO	2.50 percent by weight;
	TiO_2	0.50 percent by weight;
	Na_2O	up to 0.60 percent by weight;
	Li_2O	0.90 percent by weight;
	Fe_2O_3	0.23 percent by weight, and
35	B_2O_3	1.00 to 1.20 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Tables 17 are as follows:

	RO	25.90 to 26.34 wt%
5	SiO ₂ /CaO	2.42 to 2.48
	SiO ₂ /RO	2.19 to 2.24
	SiO ₂ /Al ₂ O ₃	4.30 to 4.47
	Al ₂ O ₃ /CaO	0.54 to 0.57
	SiO ₂ + Al ₂ O ₃	70.83 to 71.47 wt%
10	SiO ₂ – RO	31.26 to 32.39 wt%
	Al ₂ O ₃ /RO	0.49 to 0.52
	R2O +RO+B ₂ O ₃	27.80 to 28.44 wt%
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.49 to 2.57

Type 6 Glasses of Table 17 included Li₂O, K₂O and Na₂O; therefore R2O is equal to the sum in wt% of Li₂O, K₂O and Na₂O.

The glass compositions of Table 17 have a log3 forming temperature in the range of 1192 to 1198°C, and a ΔT in the range of 55 to 63°C.

The glass compositions of Table 18 have the following ingredients in the following ranges:

	SiO ₂	54.60 to 59.53 percent by weight;
	Al ₂ O ₃	12.16 to 13.63 percent by weight;
	CaO	22.93 to 24.05 percent by weight;
25	MgO	2.00 to 2.55 percent by weight;
	TiO ₂	0.49 to 1.10 percent by weight;
	Na ₂ O	up to 0.60 percent by weight;
	K ₂ O	up to 0.10 percent by weight;
	Li ₂ O	0.30 to 0.91 percent by weight;
30	Fe ₂ O ₃	0.23 to 0.35 percent by weight, and
	B ₂ O ₃	0.60 to 3.00 percent by weight.

The ranges for the mathematical relationships of the ingredients of the glass compositions of Tables 17 are as follows:

35	RO	25.80 to 26.60 wt%
	SiO ₂ /CaO	2.22 to 2.66

	SiO ₂ /RO	2.01 to 2.39
	SiO ₂ /Al ₂ O ₃	4.09 to 4.90
	Al ₂ O ₃ /CaO	0.51 to 0.59
	SiO ₂ + Al ₂ O ₃	67.95 to 72.05 wt%
5	SiO ₂ – RO	27.50 to 33.84 wt%
	Al ₂ O ₃ /RO	0.46 to 0.53
	R ₂ O + RO + B ₂ O ₃	26.70 to 31.10 wt%
	(SiO ₂ + Al ₂ O ₃) / (R ₂ O + RO + B ₂ O ₃)	2.18 to 2.68

10 The glass compositions of Table 18 have a log3 forming temperature in the range of 1187 to 1239°C, and a ΔT in the range of 50 to 42°C.

The glass compositions listed on Table 18 and the glasses within the scope of the embodiment of Table 18 have a forming temperature in the range of 1187 to 1239°C and a delta T in the range of 50 – 142°C; however the preferred glass compositions from Table 18 are those that provide the forming temperature range 1187 to 1220°C (Examples 188-213, 215-229, 213-235, 238-240, 242-260 and 262-267) and more preferably in the range of 1187 – 1205°C (Examples 188-191, 194, 195, 198, 200, 201 202-205, 208, 209, 211-213, 215-219, 221-223, 225-229, 233-235, 239, 242, 257 and 260).

20

A glass composition having the ingredients in the ranges mentioned above for Table 18 and having the following relationships will provide glass compositions having a log3 forming temperature in the range of 1187 to 1220°C, and a ΔT is in the range of 50 to 139°C:

25	RO	25.80 to 26.60 wt%
	SiO ₂ /CaO	2.22 to 2.66
	SiO ₂ /RO	2.01 to 2.39
	SiO ₂ /Al ₂ O ₃	4.09 to 4.87
	Al ₂ O ₃ /CaO	0.51 to 0.59
30	SiO ₂ + Al ₂ O ₃	67.95 to 72.05 wt%
	SiO ₂ – RO	27.50 to 33.84 wt%
	Al ₂ O ₃ /RO	0.46 to 0.53
	R ₂ O + RO + B ₂ O ₃	26.70 to 31.10 wt%
	(SiO ₂ + Al ₂ O ₃) / (R ₂ O + RO + B ₂ O ₃)	2.18 to 2.68

35

The glass compositions from Table 18 having a log3 forming temperature in the range of 1187 to 1205°C, and a ΔT in the range of 50 to 124°C have the following ingredients and the following ranges:

	SiO ₂	57.60 to 59.21 percent by weight;
5	Al ₂ O ₃	12.16 to 13.63 percent by weight;
	CaO	22.87 to 24.06 percent by weight;
	MgO	2.36 to 2.50 percent by weight;
	TiO ₂	0.49 to 1.10 percent by weight;
	Na ₂ O	up to 0.30 percent by weight;
10	K ₂ O	up to 0.09 percent by weight;
	Li ₂ O	0.70 to 0.90 percent by weight;
	Fe ₂ O ₃	0.23 to 0.29 percent by weight, and
	B ₂ O ₃	1.00 to 1.20 percent by weight;

And the following relationships:

15	RO	25.23 to 26.54 wt%
	SiO ₂ /CaO	2.40 to 2.57
	SiO ₂ /RO	2.17 to 2.32
	SiO ₂ /Al ₂ O ₃	4.26 to 4.87
	Al ₂ O ₃ /CaO	0.52 to 0.59
20	SiO ₂ + Al ₂ O ₃	70.63 to 71.73 wt%
	SiO ₂ – RO	31.06 to 33.61 wt%
	Al ₂ O ₃ /RO	0.47 to 0.53
	R ₂ O + RO + B ₂ O ₃	27.23 to 28.64 wt%
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.47 to 2.63

25

The selection of these examples is made based on the low forming temperature. Further examples 266 -268 are glass compositions that have a low forming temperature with 0.30 wt% Li₂O. Examples 265-268 define a range of ingredients and relationship of the ingredients to provide a low Li₂O containing glass with low forming temperature. As can be appreciated and as previously discussed, if a high delta T is of interest then Examples from Table 18 have a high delta T, e.g. above 75°C may be selected to define glass compositions.

Table 19 (Type 7 Misc. Glasses) includes glass compositions of a quaternary system that includes SiO₂ in the range of 56-60 wt%, preferably in the range of 57-59 wt% and more preferable in the range of 57.50-59 wt%; Al₂O₃ in the range of 10-14 wt%, preferably in the range of 11.00-14.00 wt% and more preferably

in the range of 11.50 –14.00 wt%; CaO in the range of 21-25 wt%, preferable in the range of 22.00-24.00 wt% and more preferable in the range of 22.50-24.00 wt%, and MgO in the range of 2.00-4.00 wt%, preferably in the range of 2.00-3.00 wt% and more preferably in the range of 2.25-2.75 wt% . The compositions of Table 19

5 include B₂O₃ in the range of 0 – 1.50 wt%, preferably in the range of 0-1.25 wt% and more preferably in the range of 0-1.10 wt%. The compositions of Table 19

contemplates further includes TiO₂ in the range of 0.25-1.50 wt%, more likely preferably in the range of 0.25-1.35 wt% and most likely in the range of 0.40-1.25 wt%; Na₂O in amounts no greater than 1.25 wt%; preferably no greater than 1.10

10 wt%, and more preferably no greater than 1.00 wt%; ZnO in amounts no greater than 0.50 wt%; preferably no greater than 0.40 wt%, and more preferably no greater than 0.35 wt%; MnO in amounts no greater than 4.00 wt%; preferably no greater than 3.50 wt%, and more preferably no greater than 3.25 wt%; MnO₂ in amounts no greater than 4.00 wt%; preferably no greater than 3.50 wt%, and more preferably no greater than 3.25 wt%, and Fe₂O₃ in the range of 0.10 -0.50 wt%, preferably in the range of

15 0.15-0.50 wt% and more preferably in the range of 0.20-0.40 wt%.

A glass composition having ingredients of Tables 19 within the above ranges and at least one of the following relationships provides a glass composition having a

20 forming temperature below 1240°C and a delta T of greater than 50°C:

	<u>Relationship</u>	<u>Broad Range</u>	<u>Preferred Range</u>
	RO (CaO + MgO)	24 to 27 wt%	25.00 to 26.50 wt%
	SiO ₂ / CaO	2.10 to 2.80	2.20 to 2.70
25	SiO ₂ / RO	1.90 to 2.55	1.90 to 2.40
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00	3.70 to 4.90
	Al ₂ O ₃ /CaO	0.45 to 0.65	0.55 to 0.60
	SiO ₂ + Al ₂ O ₃	66 to 73.7 wt%	66 to 72.1wt%
	R ₂ O + RO + B ₂ O ₃	25 to 28 wt%	25.75 to 27.50 wt%
30	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.00 to 3.00	2.00 to 2.75
	SiO ₂ – RO	26.50 to 36.6 wt%	26.5 to 34.00 wt%
	Al ₂ O ₃ /RO	0.40 to 0.60	0.46 to 0.56

The Misc. Glasses included Li₂O and Na₂O; therefore R₂O is equal to the sum in wt% of Li₂O and Na₂O.

35

Table 19 provides the following ranges for the following ingredients:

	SiO ₂	57.72 to 58.70 percent by weight;
	Al ₂ O ₃	11.88 to 13.35 percent by weight;
	CaO	22.80 to 23.50 percent by weight;
	MgO	2.43 to 2.50 percent by weight;
5	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O ₃	0.87 – 0.90 percent by weight;
	Li ₂ O	0 to 0.30 percent by weight;
	ZnO	0 to 0.30 percent by weight;
	Fe ₂ O ₃	0.22-0.25 percent by weight;
10	MnO	0.30 to 3.00 percent by weight;
	MnO ₂	0 to 3.00 percent by weight, and
	B ₂ O ₃	0 to 1.00 percent by weight.

The relationships for the ingredients of the glass compositions on Table 19
 15 are as follows:

	RO	25.23 to 26.00 wt%
	SiO ₂ /CaO	2.49 to 2.54
	SiO ₂ /RO	2.25 to 2.29
	SiO ₂ /Al ₂ O ₃	4.40 to 4.90
20	Al ₂ O ₃ /CaO	0.52 to 0.57
	SiO ₂ + Al ₂ O ₃	69.52 to 72.05 wt%
	SiO ₂ – RO	32.40 to 32.70 wt%
	Al ₂ O ₃ /RO	0.47 to 0.51
	R ₂ O + RO + B ₂ O ₃	26.10 to 27.30 wt%
25	(SiO ₂ + Al ₂ O ₃) / (R ₂ O + RO + B ₂ O ₃)	2.59 to 2.74

The glass compositions have a log₃ forming temperature of in the range of 1219 to 1241°C, and a ΔT in the range of 52 to 76°C.

Table 20 (Production Glasses) Table 20 is a representation of commercial
 30 glasses having embodiments of the invention similar to the embodiment of the glass compositions of Table 4. The glass compositions are of a quaternary system that includes SiO₂ in the range of 55.97-57.07 wt%; Al₂O₃ in the range of 12.68-12.86 wt%; CaO in the range of 23.91-24.69 wt% and MgO in the range of 2.42-2.60 wt%. The compositions of Table 20 include B₂O₃ in the range of 1.15 – 1.70 wt%; TiO₂ in
 35 the range of 0.94 – 1.09 wt%; Na₂O in the range of 0.87 – 0.93 wt%; K₂O in the range of greater than 0.050 – 0.070 wt%; SrO in the range of 0.040 – 0.050 wt%;

Cr_2O_3 in the range of 0.002 – 0.008 wt%; SO_3 in the range of 0.018 – 0.032 wt%, and Fe_2O_3 in the range of 0.255 -0.278 wt%.

A glass composition having ingredients of Tables 20 within the above ranges and at least one of the following relationships provides a glass composition having a forming temperature in the range of 1203 - 1217°C and a ΔT in the range of 55 - 83°C. Several of the glass compositions do not have the forming and liquidus temperatures, and the ΔT . The glass compositions without the temperatures and ΔT were glass compositions made between glass compositions whose forming temperature, liquidus temperature and ΔT were measured. As indicated by the position on the Table which is in general in chronological order, it is expected that the glass compositions not measured would have temperature performances similar to those that were measured. The mathematical relationships of the ingredients of the glass compositions on Table 20 are listed on Table 22 in the column entitled "Production Glasses (contain boron)". The R2O from the listed Production Glasses is equal to the sum in wt% of Li_2O and Na_2O .

As can now be appreciated, a range for each of the ingredients of the glass compositions of Types 1 and 2 glasses (Tables 2-11) can be determined from Tables. More particularly, Tables 1 and 2 provide a quaternary system including SiO_2 , Al_2O_3 , CaO and MgO and the ingredients of the glass having the relationship as shown in Table 22 under the column entitled "Types 1 & 2 Glasses". Types 1 & 2 Glasses included K_2O and Na_2O ; therefore R2O is equal to the sum in wt% of K_2O and Na_2O .

The glass compositions having the following ingredients in the following ranges has a log3 forming temperature in the range of 1167 to 1240°C and a ΔT in the range of 50 to 100°C:

	SiO_2	53.00. to 59.05 percent by weight;
	Al_2O_3	12.20 to 14.00 percent by weight;
30	CaO	22.25 to 24.95 percent by weight, and
	MgO	1.50 to 3.00 percent by weight, and

the composition may further include:

	TiO_2	0.50 to 1.10 percent by weight;
	Na_2O	0.45 to 0.90 percent by weight;
35	K_2O	0 to 0.58 percent by weight;
	Fe_2O_3	0 to 0.50 percent by weight, and

B_2O_3 0 to 5.02 percent by weight.

Further as can be appreciated, a range for each of the ingredients for Type 3-6 glasses on Tables 12 -19 can be determined by selecting the lowest and highest values to define the range for an ingredient and/or relationship on Tables 12-19. More particularly
 5 Tables 12-19 provide glass compositions having a quaternary system including SiO_2 , Al_2O_3 , CaO and MgO with the ingredients of the glass having the relationship shown on Table 22 under the column entitled "Types 3-6 Glasses". Types 3-6 Glasses included Li_2O , K_2O and Na_2O ; therefore R_2O is equal to the sum in wt% of Li_2O , K_2O and Na_2O .

10

The glass composition having the following ingredients in the following ranges has a log3 forming temperature in the range of 1187 to 1240°C and a delta T in the range of 50 to 142°C:

	SiO_2	54.60 to 60.75 percent by weight;
15	Al_2O_3	11.90 to 13.64 percent by weight;
	CaO	22.00 to 24.22 percent by weight, and
	MgO	1.90 to 3.40 percent by weight, and

the composition may further include:

	TiO_2	0.49 to 1.50 percent by weight;
20	Na_2O	0 to 0.90 percent by weight;
	K_2O	0 to 0.10 percent by weight;
	ZnO	0.45 to 1.50 percent by weight;
	Li_2O	0.30 to 1.00 percent by weight;
	Fe_2O_3	0 to 0.35 percent by weight, and
25	B_2O_3	0 to 3.00 percent by weight.

Still further as can be appreciated, a range for each of the ingredients for boron free glasses: Type 1 Glasses (Table 2), Type 3 Glasses (Tables 12 and 13); Type 4 Glasses (Tables 14 and 15); Type 5 Glasses (Table 16) and their relationship
 30 can be determined from Tables 2 and 12-16. More particularly, Tables 2 and 12-16 glass compositions having a quaternary system including SiO_2 , Al_2O_3 , CaO and MgO with the ingredients of the glass having the relationship shown on Table 22 under the column entitled "Types 1 & 3-5 Glasses". Types 1 & 3-5 Glasses included Li_2O and Na_2O ; therefore R_2O is equal to the sum in wt% of Li_2O and Na_2O . Further Types 1
 35 3&5 Glasses are boron free, therefore the formula " $R_2O + RO + B_2O_3$ " becomes " $R_2O + RO$ ".

The glass compositions having the following ingredients in the following ranges has a log3 forming temperature in the range of 1195 to 1240°C and a delta T in the range of 50 to 100°C:

5	SiO ₂	57.45 to 60.75 percent by weight;
	Al ₂ O ₃	12.00 to 13.68 percent by weight;
	CaO	22.00 to 24.50 percent by weight;
	MgO	1.70 to 3.10 percent by weight, and

the composition may further include:

10	TiO ₂	0.50 to 1.50 percent by weight;
	Na ₂ O	0 to 0.91 percent by weight;
	ZnO	0 to 1.00 percent by weight;
	Li ₂ O	0 to 1.00 percent by weight, and
	Fe ₂ O ₃	0 to 0.35 percent by weight.

15

Still further as can be appreciated, a range for each of the ingredients for boron containing: Type 2 Glasses (Tables 3-11) and Type 6 Glasses (Tables 17 and 18) and their relationship can be determined from Tables 3-11, 17 and 18. More particularly, Tables 3-11, 17 and 18 glass compositions having a boron containing (for example up to 5.05 wt%) quaternary system including SiO₂, Al₂O₃, CaO and MgO with the ingredients of the glass having the relationship shown on Table 22 under the column entitled "Types 2 & 6 Glasses". Types 2 & 6 Glasses included Li₂O, K₂O and Na₂O; therefore R₂O is equal to the sum in wt% of Li₂O, K₂O and Na₂O.

25 The glass compositions having the following ingredients in the following ranges has a log3 forming temperature in the range of 1167 to 1240°C and a delta T in the range of 50 to 142°C:

	SiO ₂	53.00 to 59.53 percent by weight;
	Al ₂ O ₃	12.00 to 14.00 percent by weight;
30	CaO	22.25 to 24.95 percent by weight, and
	MgO	1.50 to 3.00 percent by weight, and

the composition may further include:

	TiO ₂	0.40 to 1.10 percent by weight;
	Na ₂ O	0 to 0.90 percent by weight;
35	K ₂ O	0 to 0.30 percent by weight;
	F	0 to 0.50 percent by weight;

SrO	0 to 0.13 percent by weight;
Cr ₂ O ₃	0 to 0.13 percent by weight;
Li ₂ O	0 to 0.91 percent by weight, and
Fe ₂ O ₃	0 to 0.30 percent by weight.

5

It will be appreciated by those skilled in the art that changes could be made to the embodiments described above without departing from the broad inventive concept thereof. For example, but not limiting thereto, one, two, three or more or all of the formulas discussed above setting forth the mathematical relationship of the ingredients may be used to identify properties of a glass composition. Based on the description of the embodiments of the invention, it can be appreciated that this invention is not limited to the particular embodiments disclosed, but it is intended to cover modifications that are within the spirit and scope of the invention, as defined by the appended claims.

15

Table 1

Components (wt%)	Examples						
	A	B	C	D	E	F	G
SiO ₂	55.60	56.45	55.70	57.60	56.35	56.70	57.85
Al ₂ O ₃	13.58	13.25	13.94	12.35	13.45	13.67	12.55
CaO	24.76	24.75	24.80	24.40	24.65	23.87	24.45
MgO	2.80	2.55	2.55	2.55	2.55	2.62	2.55
TiO ₂	0.55	0.55	0.55	0.55	0.55	0.34	0.05
Na ₂ O	0.45	0.45	0.45	0.45	0.45	0.44	0.45
K ₂ O	0.58	0.45	0.45	0.45	0.45	0.51	0.45
Fe ₂ O ₃	0.38	0.25	0.25	0.25	0.25	0.35	0.35
B ₂ O ₃	1.30	1.30	1.30	1.30	1.30	1.50	1.30
RO (CaO + MgO)	27.56	27.30	27.35	26.95	27.20	26.49	27.00
SiO ₂ /CaO	2.25	2.28	2.25	2.36	2.29	2.38	2.37
SiO ₂ /RO	2.02	2.07	2.04	2.14	2.07	2.14	2.14
SiO ₂ /Al ₂ O ₃	4.09	4.26	4.00	4.66	4.19	4.15	4.61
Al ₂ O ₃ /CaO	0.55	0.54	0.56	0.51	0.55	0.57	0.51
SiO ₂ + Al ₂ O ₃	69.18	69.70	69.64	69.95	69.80	70.37	70.44
R2O+RO+B ₂ O ₃	29.89	29.50	29.55	29.15	29.40	28.94	29.20
(Si+Al)/(R2O+RO+B)	2.31	2.36	2.36	2.40	2.37	2.43	2.41
SiO ₂ - RO	28.04	29.15	28.35	30.65	29.15	30.21	30.85
Al ₂ O ₃ /RO	0.49	0.49	0.51	0.46	0.49	0.52	0.46
Log3 FT, °C	1213	1220	1220	1221	1221	1218	1219
Liquidus T, °C	1159	1160	1165	1164	1156	1160	1167
Delta T, °C	54	60	55	57	65	58	52

Table 2 – Type 1 Glasses

Components (wt%)	Examples									
	H	I	1	2	3	4	5	6		
SiO ₂	57.60	58.18	57.75	57.45	57.65	58.05	57.95	59.05		
Al ₂ O ₃	13.55	13.68	13.20	13.40	13.40	13.40	13.20	12.20		
CaO	24.50	23.75	24.25	24.35	24.15	23.75	24.05	23.95		
MgO	2.55	2.58	2.55	2.55	2.55	2.55	2.55	2.55		
TiO ₂	0.55	0.55	1.10	1.10	1.10	1.10	1.10	1.10		
Na ₂ O	0.90	0.91	0.90	0.90	0.90	0.90	0.90	0.90		
Fe ₂ O ₃	0.35	0.35	0.25	0.25	0.25	0.25	0.25	0.25		
B ₂ O ₃	-	-	-	-	-	-	-	-		
RO (CaO + MgO)	27.05	26.33	26.80	26.90	26.70	26.30	26.60	26.50		
SiO ₂ /CaO	2.35	2.45	2.38	2.36	2.39	2.44	2.41	2.47		
SiO ₂ /RO	2.13	2.20	2.15	2.14	2.16	2.21	2.18	2.23		
SiO ₂ /Al ₂ O ₃	4.25	4.25	4.38	4.29	4.30	4.33	4.39	4.84		
Al ₂ O ₃ /CaO	0.55	0.58	0.54	0.55	0.56	0.56	0.55	0.51		
SiO ₂ + Al ₂ O ₃	71.15	71.86	70.95	70.85	71.05	71.45	71.15	71.25		
R2O+RO+B ₂ O ₃	27.95	27.24	27.70	27.80	27.60	27.20	27.50	27.40		
(Si+Al)/(R2O+RO+B)	2.55	2.64	2.56	2.55	2.57	2.63	2.59	2.60		
SiO ₂ - RO	30.55	31.85	30.95	30.55	30.95	31.75	31.35	32.55		
Al ₂ O ₃ /RO	0.50	0.52	0.49	0.50	0.50	0.51	0.50	0.46		
Log3 FT, °C	1240	1238	1232	1238	1240	1240	1235	1239		
Liquidus T, °C	1185	1183	1166	1165	1166	1167	1164	1181		
Delta T, °C	55	55	66	73	74	73	71	58		

Table 3 – Type 2 Glasses

Components (wt%)	Examples										
	7	8	9	10	11	12					
SiO ₂	56.00	56.40	56.35	56.65	56.20	56.50					
Al ₂ O ₃	13.60	13.40	13.60	13.05	13.60	13.20					
CaO	24.25	24.05	23.85	23.50	24.05	23.50					
MgO	2.50	2.50	2.55	2.55	2.50	2.55					
TiO ₂	0.50	0.50	0.50	1.10	0.50	1.10					
Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90					
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	0.25					
B ₂ O ₃	2.00	2.00	2.00	2.00	2.00	2.00					
RO (CaO + MgO)	26.75	26.55	26.40	26.05	26.55	26.05					
SiO ₂ /CaO	2.31	2.35	2.36	2.41	2.34	2.40					
SiO ₂ /RO	2.09	2.12	2.13	2.17	2.12	2.17					
SiO ₂ /Al ₂ O ₃	4.12	4.21	4.14	4.34	4.13	4.28					
Al ₂ O ₃ /CaO	0.56	0.56	0.57	0.56	0.57	0.56					
SiO ₂ + Al ₂ O ₃	69.60	69.80	69.95	69.70	69.80	69.70					
R2O+RO+B ₂ O ₃	29.65	29.45	29.30	28.95	29.45	28.95					
(Si+Al)/(R2O+RO+B)	2.35	2.37	2.39	2.41	2.37	2.41					
SiO ₂ - RO	29.25	29.85	29.95	30.60	29.65	30.45					
Al ₂ O ₃ /RO	0.51	0.50	0.52	0.50	0.51	0.51					
Log3 FT, °C	1213	1216	1218	1218	1219	1220					
Liquidus T, °C	1136	1143	1138	1131	1136	1133					
Delta T, °C	59	56	62	69	65	69					

Table 4 – Type 2 Glasses

Components (wt%)	Examples											
	13	14	15	16	17	18	19	20	21	22		
SiO ₂	56.25	56.45	56.75	56.50	56.75	57.5	56.75	57.75	57.75	57.75		
Al ₂ O ₃	13.2	13.20	13.20	13.20	13.20	12.2	13.2	12.2	12.2	12.2		
CaO	24.25	24.25	23.95	24.00	23.75	24	23.95	23.75	23.75	23.95		
MgO	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55		
TiO ₂	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10		
Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90		
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25		
B ₂ O ₃	1.30	1.30	1.30	1.30	1.40	1.30	1.20	1.40	1.30	1.40		
RO (CaO + MgO)	26.80	26.80	26.50	26.55	26.30	26.55	26.50	26.30	26.30	26.50		
SiO ₂ /CaO	2.32	2.33	2.37	2.35	2.39	2.40	2.37	2.43	2.43	2.41		
SiO ₂ /RO	2.10	2.11	2.14	2.13	2.16	2.17	2.14	2.20	2.20	2.18		
SiO ₂ /Al ₂ O ₃	4.26	4.28	4.30	4.28	4.30	4.71	4.30	4.73	4.73	4.73		
Al ₂ O ₃ /CaO	0.54	0.54	0.55	0.55	0.56	0.51	0.55	0.51	0.51	0.51		
SiO ₂ + Al ₂ O ₃	69.45	69.65	69.95	69.70	69.95	69.70	69.95	69.95	69.95	69.95		
R2O+RO+B ₂ O ₃	29.00	29.00	28.70	28.75	28.60	28.75	28.60	28.60	28.50	28.80		
(Si+Al)/(R2O+RO+B)	2.39	2.40	2.44	2.42	2.45	2.42	2.45	2.45	2.45	2.43		
SiO ₂ - RO	29.45	29.65	30.25	29.95	30.45	30.95	30.25	31.45	31.45	31.25		
Al ₂ O ₃ /RO	0.49	0.49	0.50	0.50	0.50	0.46	0.50	0.46	0.46	0.46		
Log3 FT, °C	1210	1214	1215	1215	1215	1216	1216	1217	1217	1218		
Liquidus T, °C	1154	1159	1154	1154	1160	1152	1147	1151	1147	1155		
Delta T, °C	56	55	61	61	55	64	69	66	70	63		

Table 5 – Type 2 Glasses

Components (wt%)	Examples											
	23	24	25	26	27	28	29	30	31	32		
SiO ₂	55.40	55.40	55.19	55.40	56.05	55.85	56.00	55.90	55.40	55.19		
Al ₂ O ₃	13.60	13.60	13.59	13.60	13.10	13.38	13.37	13.37	13.80	13.59		
CaO	24.50	24.50	24.55	24.50	24.55	24.67	24.53	24.63	24.50	24.55		
MgO	2.95	2.95	2.86	2.95	2.75	2.55	2.55	2.55	2.75	2.86		
TiO ₂	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10		
Na ₂ O	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45		
K ₂ O	0.45	0.45	0.58	0.45	0.45	0.45	0.45	0.45	0.45	0.58		
Fe ₂ O ₃	0.25	0.25	0.38	0.25	0.25	0.25	0.25	0.25	0.25	0.38		
B ₂ O ₃	1.30	1.30	1.30	1.30	1.30	1.30	1.30	1.30	1.30	1.30		
RO (CaO + MgO)	27.45	27.45	27.41	27.45	27.30	27.22	27.08	27.18	27.25	27.41		
SiO ₂ /CaO	2.26	2.26	2.25	2.26	2.28	2.26	2.28	2.27	2.26	2.25		
SiO ₂ /RO	2.02	2.02	2.01	2.02	2.05	2.05	2.07	2.06	2.03	2.01		
SiO ₂ /Al ₂ O ₃	4.07	4.07	4.06	4.07	4.28	4.17	4.19	4.18	4.01	4.06		
Al ₂ O ₃ /CaO	0.56	0.56	0.55	0.56	0.53	0.54	0.55	0.54	0.56	0.55		
SiO ₂ + Al ₂ O ₃	69.00	69.00	68.78	69.00	69.15	69.23	69.37	69.27	69.20	68.78		
R ₂ O+RO+B ₂ O ₃	29.65	29.65	29.74	29.65	29.50	29.42	29.28	29.38	29.45	29.74		
(Si+Al)/(R ₂ O+RO+B)	2.33	2.33	2.31	2.33	2.34	2.35	2.37	2.36	2.35	2.31		
SiO ₂ - RO	27.95	27.95	27.78	27.95	28.75	28.63	28.92	28.72	28.15	27.78		
Al ₂ O ₃ /RO	0.50	0.50	0.50	0.50	0.48	0.49	0.49	0.49	0.51	0.50		
Log3 FT, °C	1210	1211	1216	1217	1218	1220	1221	1221	1221	1222		
Liquidus T, °C	1157	1151	1154	1167	1156	1148	1157	1142	1167	1154		
Delta T, °C	53	60	62	56	62	72	64	79	54	63		

Table 6 – Type 2 Glasses

Components (wt%)	Examples											
	33	34	35	36	37	38	39	40	41	42		
SiO ₂	56.60	56.50	56.50	55.95	57.60	56.50	56.45	56.50	56.55	56.15		
Al ₂ O ₃	13.25	13.45	13.45	13.95	12.35	13.49	13.48	13.45	13.35	13.35		
CaO	24.60	24.50	24.50	24.55	24.40	24.46	24.52	24.50	24.55	24.95		
MgO	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55		
TiO ₂	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55		
Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90		
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.35	0.25	0.25	0.25	0.25	0.25		
B ₂ O ₃	1.30	1.30	1.30	1.30	1.30	1.30	1.30	1.30	1.30	1.30		
RO (CaO + MgO)	27.15	27.05	27.05	27.10	26.95	27.01	27.07	27.05	27.10	27.50		
SiO ₂ /CaO	2.30	2.31	2.31	2.28	2.36	2.31	2.30	2.31	2.30	2.25		
SiO ₂ /RO	2.08	2.09	2.09	2.06	2.14	2.09	2.09	2.09	2.09	2.04		
SiO ₂ /Al ₂ O ₃	4.27	4.20	4.20	4.01	4.66	4.19	4.19	4.20	4.24	4.21		
Al ₂ O ₃ /CaO	0.54	0.55	0.55	0.57	0.51	0.55	0.55	0.55	0.54	0.54		
SiO ₂ + Al ₂ O ₃	69.85	69.95	69.95	69.90	69.95	69.99	69.93	69.95	69.90	69.50		
R2O+RO+B ₂ O ₃	29.35	29.25	29.25	29.30	29.15	29.21	29.27	29.25	29.30	29.70		
(Si+Al)/(R2O+RO+B)	2.38	2.39	2.39	2.39	2.40	2.40	2.39	2.39	2.39	2.34		
SiO ₂ - RO	29.45	29.45	29.45	28.85	30.65	29.49	29.38	29.45	29.45	28.65		
Al ₂ O ₃ /RO	0.49	0.50	0.50	0.51	0.46	0.50	0.50	0.50	0.49	0.49		
Log3 FT, °C	1211	1212	1215	1216	1216	1218	1219	1220	1220	1220		
Liquidus T, °C	1153	1158	1157	1162	1164	1161	1158	1160	1155	1154		
Delta T, °C	58	54	58	54	52	57	61	60	65	66		

Table 7 – Type 2 Glasses

Components (wt%)	Examples											
	43	44	45	46	47	48	49	50	51	52		
SiO ₂	55.50	55.25	55.25	55.5	55.00	55.75	55.75	55.75	56.00	56.15		
Al ₂ O ₃	13.20	13.20	13.30	13.30	13.20	13.30	13.20	13.20	13.30	13.05		
CaO	23.50	23.75	24.20	23.95	24.00	23.70	23.25	23.25	23.45	23.00		
MgO	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55		
TiO ₂	1.10	1.10	0.55	0.55	1.10	0.55	1.10	1.10	0.55	1.10		
Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90		
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25		
B ₂ O ₃	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00		
RO (CaO + MgO)	26.05	26.30	26.75	26.50	26.55	26.25	25.80	25.80	26.00	25.55		
SiO ₂ /CaO	2.36	2.33	2.28	2.32	2.29	2.35	2.40	2.40	2.39	2.44		
SiO ₂ /RO	2.13	2.10	2.07	2.09	2.07	2.12	2.16	2.16	2.15	2.20		
SiO ₂ /Al ₂ O ₃	4.20	4.19	4.15	4.17	4.17	4.19	4.22	4.22	4.21	4.30		
Al ₂ O ₃ /CaO	0.56	0.56	0.55	0.56	0.55	0.56	0.57	0.57	0.57	0.57		
SiO ₂ + Al ₂ O ₃	68.70	68.45	68.55	68.80	68.20	69.05	68.95	68.95	69.30	69.20		
R ₂ O+RO+B ₂ O ₃	29.95	30.20	30.65	30.40	30.45	30.15	29.70	29.70	29.90	29.45		
(Si+Al)/(R ₂ O+RO+B)	2.29	2.27	2.24	2.26	2.24	2.29	2.32	2.32	2.32	2.35		
SiO ₂ - RO	29.45	28.95	28.50	29.00	28.45	29.50	29.95	29.95	30.00	30.60		
Al ₂ O ₃ /RO	0.51	0.50	0.50	0.50	0.50	0.51	0.51	0.51	0.51	0.51		
Log3 FT, °C	1193	1198	1198	1200	1201	1201	1204	1204	1207	1212		
Liquidus T, °C	1129	1122	1128	1129	1127	1127	1127	1123	1127	1122		
Delta T, °C	64	76	70	71	74	74	77	81	80	90		

Table 8 – Type 2 Glasses

Components (wt%)	Examples												
	53	54	55	56	57	58	59	60	61	62	63		
SiO ₂	54.20	54.50	54.12	55.00	54.5	54.5	54.7	54.50	54.20	54.50	54.80		
Al ₂ O ₃	13.35	13.25	13.30	13.25	13.25	13.25	13.2	13.25	13.35	13.25	13.25		
CaO	24.55	24.55	24.55	24.25	24.55	24.55	24.5	24.55	24.55	24.55	24.25		
MgO	2.55	2.55	3.00	2.55	2.67	2.67	2.55	2.65	2.85	2.65	2.55		
TiO ₂	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55		
Na ₂ O	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45		
K ₂ O	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55		
Fe ₂ O ₃	0.28	0.28	0.28	0.28	0.28	0.28	0.28	0.28	0.28	0.28	0.28		
B ₂ O ₃	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00		
F	0.20	0.20	0.10	0.10	0.10	0.10	0.10	0.10	0.10	0.10	0.20		
SiO	0.12	0.12	0.10	0.12	0.10	0.10	0.12	0.12	0.12	0.12	0.12		
RO (CaO + MgO)	27.10	27.10	27.55	26.80	27.22	27.22	27.05	27.20	27.40	27.20	26.80		
SiO ₂ /CaO	2.21	2.22	2.20	2.27	2.22	2.22	2.23	2.22	2.21	2.22	2.26		
SiO ₂ /RO	2.00	2.01	1.96	2.05	2.00	2.00	2.02	2.00	1.98	2.00	2.04		
SiO ₂ /Al ₂ O ₃	4.06	4.11	4.07	4.15	4.11	4.11	4.14	4.11	4.06	4.11	4.14		
Al ₂ O ₃ /CaO	0.54	0.54	0.54	0.55	0.54	0.54	0.54	0.54	0.54	0.54	0.55		
SiO ₂ + Al ₂ O ₃	67.55	67.75	67.42	68.25	67.75	67.75	67.90	67.75	67.55	67.75	68.05		
R2O+RO+B ₂ O ₃	31.10	31.10	31.55	30.80	31.22	31.22	31.05	31.20	31.40	31.20	30.80		
(Si+Al)/(R2O+RO+B)	2.17	2.18	2.14	2.22	2.17	2.17	2.19	2.17	2.15	2.17	2.21		
SiO ₂ - RO	27.10	27.40	26.57	28.20	27.28	27.28	27.65	27.30	26.80	27.30	28.00		
Al ₂ O ₃ /RO	0.49	0.49	0.48	0.49	0.49	0.49	0.49	0.49	0.49	0.49	0.49		
Log3 FT, °C	1190	1194	1196	1197	1201	1199	1201	1196	1196	1197	1197		
Liquidus T, °C	1120	1124	1132	1124	1131	1137	1119	1130	1130	1127	1121		
Delta T, °C	70	70	64	73	70	62	82	66	66	70	76		

Table 8 – Type 2 Glasses (cont'd)

	Examples											
Components (wt%)	64	65	66	67	68	69	70	71	721	73	74	
SiO ₂	55.05	54.95	54.20	55.25	54.8	55.25	54.95	54.75	54.55	54.80	54.70	
Al ₂ O ₃	13.25	13.25	13.35	13.30	13.25	13.30	13.25	13.20	13.40	13.20	13.30	
CaO	24.20	24.3	24.55	24.20	24.25	24.20	24.30	24.45	24.45	24.40	24.40	
MgO	2.55	2.55	2.85	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	
TiO ₂	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	0.55	
Na ₂ O	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	0.45	
K ₂ O	0.55	0.55	0.55	0.45	0.55	0.45	0.55	0.55	0.55	0.55	0.55	
Fe ₂ O ₃	0.28	0.28	0.28	0.25	0.28	0.25	0.28	0.28	0.28	0.28	0.28	
B ₂ O ₃	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	3.00	
F	0.10	0.10	0.10	-	0.20	-	-	0.10	0.10	0.10	0.10	
SrO	0.12	0.12	0.12	-	0.12	-	0.12	0.12	0.12	0.12	0.12	
RO (CaO + MgO)	26.75	26.85	27.40	26.75	26.80	26.75	26.85	27.00	27.00	26.95	26.95	
SiO ₂ /CaO	2.27	2.26	2.21	2.28	2.26	2.28	2.26	2.24	2.23	2.25	2.24	
SiO ₂ /RO	2.06	2.05	1.98	2.07	2.04	2.07	2.05	2.03	2.02	2.03	2.03	
SiO ₂ /Al ₂ O ₃	4.15	4.15	4.06	4.15	4.14	4.15	4.15	4.15	4.07	4.15	4.11	
Al ₂ O ₃ /CaO	0.55	0.55	0.54	0.55	0.55	0.55	0.55	0.54	0.55	0.54	0.55	
SiO ₂ + Al ₂ O ₃	68.30	68.20	67.55	68.55	68.05	68.55	68.20	67.95	67.95	68.00	68.00	
R2O+RO+B ₂ O ₃	30.75	30.85	31.40	30.65	30.80	30.65	30.85	31.00	31.00	30.95	30.95	
(Si+Al)/(R2O+RO+B)	2.22	2.21	2.15	2.24	2.21	2.24	2.21	2.19	2.19	2.20	2.20	
SiO ₂ - RO	28.30	28.10	26.80	28.50	28.00	28.50	28.10	27.75	27.55	27.85	27.75	
Al ₂ O ₃ /RO	0.50	0.49	0.49	0.50	0.49	0.50	0.49	0.49	0.50	0.49	0.49	
Log3 FT, °C	1198	1198	1199	1202	1202	1203	1203	1203	1203	1204	1204	
Liquidus T, °C	1127	1123	1137	1126	1147	1124	1125	1125	1124	1121	1122	
Delta T, °C	71	75	62	76	55	79	78	78	79	83	82	

Table 9 – Type 2 Glasses

Components (wt%)	Examples		
	75	76	77
SiO ₂	53.00	53.00	53.50
Al ₂ O ₃	13.10	13.50	14.00
CaO	24.00	24.00	24.00
MgO	2.50	2.50	1.50
TiO ₂	0.50	0.50	0.50
Na ₂ O	0.90	0.90	0.90
K ₂ O	0.37	0.37	0.37
Fe ₂ O ₃	0.10	0.10	0.10
B ₂ O ₃	5.02	4.93	4.94
F	0.50	0.50	0.50
SrO	0.13	0.13	0.13
Cl ₂ O ₃	0.13	0.13	0.13
RO (CaO + MgO)	26.50	26.50	25.50
SiO ₂ /CaO	2.21	2.21	2.23
SiO ₂ /RO	2.00	2.00	2.10
SiO ₂ /Al ₂ O ₃	4.05	3.93	3.82
Al ₂ O ₃ /CaO	0.55	0.56	0.58
SiO ₂ + Al ₂ O ₃	66.10	66.50	67.50
R2O+RO+B ₂ O ₃	32.79	32.70	31.71
(Si+Al)/(R2O+RO+B)	2.02	2.03	2.13
SiO ₂ – RO	26.50	26.50	28.00
Al ₂ O ₃ /RO	0.49	0.51	0.55
Log3 FT, °C	1167	1172	1177
Liquidus T, °C	1110	1103	1122
Delta T, °C	57	69	57

Table 10 – Type 2 Glasses

		Examples											
Components (wt%)		78	79	80	81	82	83	84	85	86	87	88	89
	SiO ₂	55.40	55.80	56.20	55.75	56.35	55.60	55.80	56.40	56.0	56.00	56.00	56.65
	Al ₂ O ₃	13.60	13.40	13.60	13.20	13.60	13.60	13.60	13.40	13.60	13.80	13.60	13.05
	CaO	24.85	24.65	24.05	23.25	23.85	24.65	24.45	24.05	24.25	24.05	24.25	23.50
	MgO	2.50	2.50	2.50	2.55	2.55	2.50	2.50	2.50	2.50	2.50	2.50	2.55
	TiO ₂	0.50	0.50	0.50	1.10	0.50	0.50	0.50	0.50	0.50	0.50	0.50	1.10
	Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90
	Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25
	B ₂ O ₃	2.00	2.00	2.00	3.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00
	RO	27.35	27.15	26.55	25.80	26.40	27.15	26.95	26.55	26.75	26.55	26.75	26.05
	SiO ₂ /CaO	2.23	2.25	2.34	2.40	2.36	2.26	2.28	2.35	2.31	2.33	2.31	2.41
	SiO ₂ /RO	2.03	2.06	2.12	2.16	2.13	2.05	2.07	2.12	2.09	2.11	2.09	2.17
	SiO ₂ /Al ₂ O ₃	4.07	4.16	4.13	4.22	4.14	4.09	4.10	4.21	4.12	4.06	4.11	4.34
	Al ₂ O ₃ /CaO	0.54	0.54	0.57	0.57	0.57	0.55	0.56	0.55	0.56	0.57	0.56	0.56
	SiO ₂ + Al ₂ O ₃	69.00	69.20	69.80	68.95	69.95	69.20	69.40	69.80	69.60	69.80	69.60	69.70
	R ₂ O+RO+B ₂ O ₃	30.25	30.05	29.45	29.70	29.30	30.05	29.85	29.45	29.65	29.45	29.65	28.95
	(Si+Al)/(R ₂ O+RO+B)	2.28	2.30	2.37	2.32	2.39	2.30	2.32	2.37	2.35	2.37	2.35	2.41
	SiO ₂ – RO	28.05	28.65	29.65	29.95	29.95	28.45	28.85	29.85	29.25	29.45	29.25	30.60
	Al ₂ O ₃ /RO	0.50	0.49	0.51	0.51	0.51	0.50	0.50	0.50	0.51	0.52	0.51	0.50
	Log3 FT, °C	1217	1211	1219	1204	1218	1211	1209	1216	1213	1219	1202	1218
	Liquidus T, °C	1153	1156	1136	1127	1138	1154	1156	1143	1136	1151	1137	1131
	Delta T, °C	64	55	83	77	80	57	53	73	77	68	65	87

Table 10 – Type 2 Glasses (cont'd)

Components (wt%)	Examples									
	90	91	92	93	94	95	96	97	98	99
SiO ₂	56.25	56.15	57.75	57.75	56.75	57.15	57.25	58.55	57.25	56.25
Al ₂ O ₃	13.20	13.05	13.20	12.20	13.20	13.05	13.20	12.20	12.20	13.20
CaO	23.25	23.00	24.25	24.25	24.25	24.00	24.25	23.45	23.75	23.75
MgO	2.55	2.55	2.50	2.50	2.50	2.55	2.50	2.55	2.50	2.50
TiO ₂	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10
Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25
B ₂ O ₃	3.00	3.00	1.00	1.00	1.00	1.00	1.00	1.00	2.00	2.00
RO	25.80	25.55	26.75	26.75	26.75	26.55	26.75	26.00	26.25	26.25
SiO ₂ /CaO	2.41	2.44	2.38	2.38	2.34	2.38	2.36	2.50	2.41	2.37
SiO ₂ /RO	2.18	2.20	2.16	2.16	2.12	2.15	2.14	2.25	2.18	2.14
SiO ₂ /Al ₂ O ₃	4.26	4.30	4.38	4.73	4.30	4.38	4.33	4.80	4.69	4.26
Al ₂ O ₃ /CaO	0.56	0.56	0.54	0.50	0.54	0.54	0.54	0.52	0.51	0.56
SiO ₂ + Al ₂ O ₃	69.45	69.20	70.95	69.95	69.95	70.20	70.45	70.75	69.45	69.45
R2O+RO+B ₂ O ₃	29.70	29.45	28.65	28.65	28.65	28.45	28.65	27.90	29.15	29.15
(Si+Al)/(R2O+RO+B)	2.34	2.34	2.67	2.44	2.44	2.47	2.47	2.54	2.38	2.38
SiO ₂ – RO	30.45	30.60	31.00	31.00	30.00	30.60	30.50	32.55	31.00	30.00
Al ₂ O ₃ /RO	0.51	0.51	0.49	0.46	0.49	0.49	0.49	0.47	0.46	0.50
Log3 FT, °C	1214	1212	1240	1227	1228	1235	1239	1236	1227	1224
Liquidus T, °C	1114	1178	1178	1164	1161	1154	1159	1159	1148	1149
Delta T, °C	100	34	62	63	67	81	80	77	79	75

Table 10 – Type 2 Glasses (cont'd)

Components (wt%)	Examples													
	100	101	102	103	104	105	106	107	108	109				
SiO ₂	56.65	56.75	58.05	55.80	57.25	56.75	56.25	56.50	55.80	56.75				
Al ₂ O ₃	13.05	13.20	12.20	13.60	13.20	13.20	13.20	13.20	13.80	13.20				
CaO	23.50	23.25	22.95	24.45	22.75	23.75	23.75	23.50	24.25	22.25				
MgO	2.55	2.55	2.55	2.50	2.50	2.05	2.55	2.55	2.50	2.55				
TiO ₂	1.10	1.10	1.10	0.50	1.10	1.10	1.10	1.10	0.50	1.10				
Na ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90				
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25				
B ₂ O ₃	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00	2.00				
RO	26.05	25.80	25.50	26.95	25.25	25.80	26.30	26.05	26.75	24.80				
SiO ₂ /CaO	2.41	2.44	2.53	2.28	2.52	2.39	2.37	2.40	2.30	2.55				
SiO ₂ /RO	2.17	2.20	2.28	2.07	2.27	2.20	2.14	2.16	2.09	2.29				
SiO ₂ /Al ₂ O ₃	4.34	4.30	4.76	4.10	4.34	4.30	4.26	4.28	4.04	4.30				
Al ₂ O ₃ /CaO	0.56	0.57	0.53	0.56	0.58	0.56	0.55	0.56	0.57	0.59				
SiO ₂ + Al ₂ O ₃	69.70	69.95	70.25	69.40	70.45	69.95	69.45	69.70	69.60	69.95				
R2O+RO+B ₂ O ₃	28.95	28.70	28.40	29.85	28.15	28.70	29.20	28.95	29.65	28.70				
(Si+Al)/(R2O+RO+B)	2.41	2.44	2.47	2.32	2.50	2.44	2.38	2.41	2.35	2.44				
SiO ₂ – RO	30.60	30.95	32.55	28.85	32.00	30.95	29.95	30.45	29.05	31.95				
Al ₂ O ₃ /RO	0.50	0.51	0.48	0.50	0.52	0.51	0.50	0.51	0.52	0.53				
Log3 FT, °C	1225	1225	1225	1222	1237	1230	1220	1220	1222	1221				
Liquidus T, °C	1145	1147	1142	1153	1149	1141	1131	1133	1137	1121				
Delta T, °C	80	78	83	69	86	89	89	87	85	100				

Table 11 - Type 2 Glasses

Components (wt%)	Examples		
	110	111	112
SiO ₂	57.75	57.75	56.10
Al ₂ O ₃	12.2	12.2	13.38
CaO	23.75	23.95	24.42
MgO	2.55	2.55	2.55
TiO ₂	1.10	1.10	0.55
Na ₂ O	0.90	0.90	0.90
K ₂ O	-	-	-
Fe ₂ O ₃	0.25	0.25	0.25
B ₂ O ₃	1.40	1.40	1.30
RO (CaO + MgO)	26.30	26.50	26.97
SiO ₂ /CaO	2.43	2.41	2.30
SiO ₂ /RO	2.20	2.18	2.08
SiO ₂ /Al ₂ O ₃	4.73	4.73	4.19
Al ₂ O ₃ /CaO	0.51	0.51	0.54
SiO ₂ + Al ₂ O ₃	69.95	69.95	69.48
R2O+RO+B ₂ O ₃	28.60	28.80	29.17
(Si+Al)/(R2O+RO+B)	2.44	2.43	2.38
SiO ₂ - RO	31.45	31.25	29.13
Al ₂ O ₃ /RO	0.46	0.46	0.50
Log3 FT, °C	1217	1218	1215
Liquidus T, °C	1151	1155	1150
Delta T, °C	66	63	65

Table 12 -- Type 3 Glasses

Components (wt%)	Examples										
	113	114	115	116	117	118	119	120	121		
SiO ₂	58.70	57.95	58.35	60.05	58.25	58.86	59.97	59.16	58.76		
Al ₂ O ₃	13.35	13.20	13.20	12.98	13.40	13.44	12.19	13.24	13.64		
CaO	23.50	24.05	23.65	22.14	23.55	23.55	22.25	23.45	23.45		
MgO	2.50	2.55	2.55	3.12	2.55	2.50	2.90	2.50	2.50		
TiO ₂	0.50	1.10	1.10	0.55	1.10	0.50	1.50	0.50	0.50		
Na ₂ O	0.30	-	-	-	-	-	-	-	-		
K ₂ O	-	-	-	-	-	-	-	-	-		
Li ₂ O	0.90	0.90	0.90	0.91	0.90	0.90	0.90	0.90	0.90		
Fe ₂ O ₃	0.20	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25		
B ₂ O ₃	-	-	-	-	-	-	-	-	-		
RO (CaO + MgO)	26.00	26.60	26.20	25.26	26.10	26.05	25.15	25.95	25.95		
SiO ₂ /CaO	2.50	2.41	2.47	2.71	2.47	2.50	2.70	2.52	2.51		
SiO ₂ /RO	2.26	2.18	2.23	2.38	2.23	2.26	2.38	2.28	2.26		
SiO ₂ /Al ₂ O ₃	4.40	4.39	4.42	4.63	4.35	4.38	4.92	4.47	4.31		
Al ₂ O ₃ /CaO	0.57	0.55	0.56	0.59	0.57	0.57	0.55	0.56	0.58		
SiO ₂ + Al ₂ O ₃	72.05	71.15	71.55	73.03	71.65	72.30	72.16	72.40	72.40		
R2O+RO+B ₂ O ₃	27.20	27.50	27.10	26.17	27.00	26.95	26.05	26.85	26.85		
(Si+Al)/(R2O+RO+B)	2.65	2.59	2.64	2.79	2.65	2.68	2.77	2.70	2.70		
SiO ₂ - RO	32.70	31.35	32.15	34.79	32.15	32.81	34.82	33.21	32.81		
Al ₂ O ₃ /RO	0.51	0.50	0.50	0.51	0.51	0.52	0.48	0.51	0.53		
Log3 FT, °C	1211	1205	1211	1214	1215	1216	1217	1218	1218		
Liquidus T, °C	1153	1151	1146	1159	1153	1153	1161	1156	1150		
Delta T, °C	58	54	65	55	62	63	56	62	68		

Table 13 – Type 3 Glasses

Components (wt%)	Examples												
	122	123	124	125	126	127	128	129	130	131			
SiO ₂	58.70	59.30	57.65	58.96	58.15	60.09	60.21	60.33	59.73	59.85			
Al ₂ O ₃	13.35	12.10	13.40	13.24	13.20	12.22	12.24	12.27	12.92	12.95			
CaO	23.50	22.60	24.15	23.65	23.85	23.31	23.35	23.40	22.00	22.04			
MgO	2.50	3.40	2.55	2.50	2.55	2.70	2.50	2.30	3.10	2.90			
TiO ₂	0.50	1.50	1.10	0.50	1.10	0.50	0.50	0.50	1.10	1.10			
Na ₂ O	0.60	0.45	-	-	-	-	-	-	-	-			
Li ₂ O	0.60	0.45	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90			
Fe ₂ O ₃	0.25	0.20	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25			
B ₂ O ₃	-	-	-	-	-	-	-	-	-	-			
RO (CaO + MgO)	26.00	26.00	26.70	26.15	26.40	26.01	25.85	25.70	25.10	24.94			
SiO ₂ /CaO	2.50	2.62	2.39	2.49	2.44	2.58	2.58	2.58	2.70	2.72			
SiO ₂ /RO	2.26	2.28	2.16	2.25	2.20	2.31	2.33	2.35	2.38	2.40			
SiO ₂ /Al ₂ O ₃	4.40	4.90	4.30	4.45	4.41	4.92	4.92	4.92	4.62	4.62			
Al ₂ O ₃ /CaO	0.57	0.54	0.55	0.56	0.55	0.52	0.52	0.52	0.59	0.59			
SiO ₂ + Al ₂ O ₃	72.05	71.40	71.05	72.20	71.35	72.31	72.45	72.60	72.65	72.80			
R ₂ O+RO+B ₂ O ₃	27.20	27.45	27.60	27.05	27.30	26.91	26.75	26.60	26.00	25.84			
(Si+Al)/(R ₂ O+RO+B)	2.65	2.70	2.57	2.67	2.61	2.69	2.71	2.73	2.30	2.32			
SiO ₂ - RO	32.7	33.30	30.95	32.81	31.75	34.08	34.36	34.63	34.63	34.91			
Al ₂ O ₃ /RO	0.51	0.47	0.50	0.51	0.50	0.47	0.47	0.48	0.51	0.52			
Log3 FT, °C	1226	1205	1206	1212	1237	1217	1213	1216	1214	1214			
Liquidus T, °C	1157	1151	1154	1158	1172	1163	1162	1166	1164	1161			
Delta T, °C	69	54	52	54	65	54	51	50	50	53			

Table 13 – Type 3 Glasses (cont'd)

Components (wt%)	Examples												
	132	133	134	135	136	137	138	139	140	141			
SiO ₂	59.97	60.09	60.21	60.00	60.57	59.80	59.75	59.65	59.60	59.55			
Al ₂ O ₃	12.97	13.00	13.02	12.50	13.10	12.25	12.25	12.25	12.25	12.25			
CaO	22.09	22.13	22.18	23.70	22.31	22.60	22.85	23.35	23.60	23.85			
MgO	2.70	2.50	2.30	1.90	1.70	3.10	2.90	2.50	2.30	2.10			
TiO ₂	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10			
Na ₂ O	-	-	-	-	-	0.30	0.30	0.30	0.30	0.30			
Li ₂ O	0.90	0.90	0.90	0.90	0.90	0.60	0.60	0.60	0.60	0.60			
Fe ₂ O ₃	0.25	0.25	0.25	0.25	0.25	-	-	-	-	-			
B ₂ O ₃	-	-	-	-	-	-	-	-	-	-			
RO (CaO + MgO)	24.79	24.63	24.48	25.60	24.01	25.70	25.75	25.85	25.90	25.95			
SiO ₂ /CaO	2.71	2.71	2.71	2.53	2.71	2.64	2.61	2.57	2.52	2.50			
SiO ₂ /RO	2.42	2.44	2.46	2.34	2.52	2.33	2.32	2.31	2.30	2.29			
SiO ₂ /Al ₂ O ₃	4.62	4.62	4.82	4.80	4.62	4.88	4.88	4.87	4.87	4.86			
Al ₂ O ₃ /CaO	0.59	0.59	0.59	0.53	0.59	0.54	0.54	0.52	0.52	0.51			
SiO ₂ + Al ₂ O ₃	72.87	73.09	73.23	72.50	73.67	72.05	72.00	71.90	71.85	71.80			
R2O+RO+B ₂ O ₃	25.69	25.53	25.38	26.50	24.91	26.60	26.65	26.75	26.80	26.85			
(Si+Al)/(R2O+RO+B)	2.33	2.86	2.89	2.74	2.96	2.71	2.70	2.69	2.68	2.67			
SiO ₂ - RO	35.18	35.46	35.73	34.40	36.56	34.10	34.00	33.80	33.7	33.60			
Al ₂ O ₃ /RO	0.47	0.53	0.53	0.49	0.55	0.47	0.48	0.47	0.47	0.47			
Log3 FT, °C	1219	1223	1233	1239	1239	1240	1236	1236	1238	1234			
Liquidus T, °C	1160	1155	1142	1139	1141	1156	1156	1159	1167	1173			
Delta T, °C	59	68	91	100	98	94	80	77	71	61			

Table 13 – Type 3 Glasses (cont'd)

Components (wt%)	Examples													
	142	143	144	145	146	147	148	149	150	151				
SiO ₂	59.50	60.00	59.95	59.90	59.85	60.21	60.33	60.75	60.21	59.71				
Al ₂ O ₃	12.25	12.40	12.40	12.40	12.0	12.24	12.27	12.35	13.02	13.24				
CaO	24.10	22.05	23.30	23.55	23.80	22.34	22.39	22.55	22.52	22.90				
MgO	1.90	2.30	2.10	1.90	1.70	2.50	2.30	1.70	2.50	2.50				
TiO ₂	1.10	1.10	1.10	1.10	1.10	1.50	1.50	1.50	0.50	0.50				
Na ₂ O	0.30	-	-	-	-	-	-	-	-	-				
Li ₂ O	0.60	0.90	0.90	0.90	0.90	0.90	0.90	0.90	1.00	0.90				
Fe ₂ O ₃	-	0.25	0.25	0.26	0.25	0.25	0.25	0.25	0.25	0.25				
B ₂ O ₃	-	-	-	-	-	-	-	-	-	-				
RO (CaO + MgO)	26.00	24.35	25.40	25.45	25.50	24.84	24.69	24.25	25.02	25.40				
SiO ₂ /CaO	2.47	2.72	2.57	2.54	2.51	2.70	2.69	2.69	2.67	2.61				
SiO ₂ /RO	2.29	2.46	2.36	2.35	2.35	2.42	2.44	2.51	2.41	2.35				
SiO ₂ /Al ₂ O ₃	4.86	4.84	4.83	4.83	4.99	4.92	4.92	4.92	4.62	4.51				
Al ₂ O ₃ /CaO	0.51	0.56	0.53	0.53	0.50	0.55	0.55	0.55	0.58	0.58				
SiO ₂ + Al ₂ O ₃	71.75	72.40	72.35	72.30	71.85	72.45	72.60	73.10	73.23	72.95				
R ₂ O+RO+B ₂ O ₃	26.90	25.23	26.30	26.35	26.40	25.74	25.59	25.15	26.02	26.30				
(Si+Al)/(R ₂ O+RO+B)	2.67	2.87	2.75	2.74	2.72	2.81	2.83	2.91	2.81	2.77				
SiO ₂ - RO	33.50	35.65	36.55	34.45	34.35	35.37	35.64	36.50	35.19	34.31				
Al ₂ O ₃ /RO	0.47	0.51	0.53	0.49	0.47	0.49	0.50	0.50	0.52	0.52				
Log3 FT, °C	1234	1230	1231	1224	1224	1215	1231	1240	1231	1227				
Liquidus T, °C	1181	1146	1152	1156	1156	1162	1160	1166	1143	1142				
Delta T, °C	53	84	79	68	68	53	71	74	88	85				

Table 13 – Type 3 Glasses (cont'd)

Components (wt%)	Examples												
	152	153	154	155	156	157	158	159	160	161	162	163	164
SiO ₂	59.46	60.02	60.26	60.14	60.10	60.23	60.10	60.23	60.14	60.05	60.05	60.05	60.05
Al ₂ O ₃	13.24	12.35	12.40	12.37	13.00	12.25	13.00	12.25	12.37	12.98	12.98	12.98	12.98
CaO	23.15	23.35	23.45	23.40	22.15	23.36	22.15	23.36	23.40	22.14	22.14	22.14	22.14
MgO	2.50	2.54	2.55	2.54	2.50	2.50	2.50	2.50	2.54	3.12	3.12	3.12	3.12
TiO ₂	0.50	0.50	0.51	0.51	1.10	0.51	1.10	0.51	0.51	0.55	0.55	0.55	0.55
Na ₂ O	-	-	-	-	-	-	-	-	-	-	-	-	-
Li ₂ O	0.90	1.00	0.60	0.80	0.90	0.90	0.90	0.90	0.80	0.91	0.91	0.91	0.91
Fe ₂ O ₃	0.25	0.23	0.23	0.23	0.25	0.25	0.25	0.25	0.23	0.25	0.25	0.25	0.25
B ₂ O ₃	-	-	-	-	-	-	-	-	-	-	-	-	-
RO (CaO + MgO)	26.65	25.89	26.00	25.94	24.65	25.86	24.65	25.86	25.94	25.26	25.26	25.26	25.26
SiO ₂ /CaO	2.57	2.57	2.57	2.57	2.71	2.58	2.71	2.58	2.57	2.71	2.71	2.71	2.71
SiO ₂ /RO	2.32	2.32	2.32	2.32	2.44	2.33	2.44	2.33	2.32	2.38	2.38	2.38	2.38
SiO ₂ /Al ₂ O ₃	4.49	4.86	4.89	4.86	4.62	4.92	4.62	4.92	4.86	4.63	4.63	4.63	4.63
Al ₂ O ₃ /CaO	0.57	0.53	0.53	0.53	0.59	0.52	0.59	0.52	0.53	0.59	0.59	0.59	0.59
SiO ₂ + Al ₂ O ₃	72.70	72.37	72.66	72.51	73.10	72.48	73.10	72.48	72.51	73.03	73.03	73.03	73.03
R ₂ O+RO+B ₂ O ₃	26.50	26.85	26.60	26.74	25.55	26.76	25.55	26.76	26.74	26.17	26.17	26.17	26.17
(Si+Al)/(R ₂ O+RO+B)	2.74	2.70	2.73	2.71	2.86	2.71	2.86	2.71	2.71	2.79	2.79	2.79	2.79
SiO ₂ - RO	33.81	34.13	34.26	34.20	34.45	34.37	35.45	34.44	34.20	34.79	34.79	34.79	34.79
Al ₂ O ₃ /RO	0.52	0.48	0.48	0.48	0.53	0.47	0.53	0.47	0.48	0.51	0.51	0.51	0.51
Log3 FT, °C	1226	1209	1230	1219	1235	1220	1237	1224	1219	1219	1223	1223	1223
Liquidus T, °C	1147	1159	1158	1159	1133	1160	1136	1158	1159	1164	1163	1163	1163
Delta T, °C	79	50	72	60	102	60	101	66	60	55	60	60	60

Table 14 – Type 4 Glasses

Components (wt%)	Examples									
	163	164	165	166	167	168	169			
SiO ₂	58.30	58.20	58.10	58.15	58.15	58.00	58.25			
Al ₂ O ₃	13.03	13.03	13.03	13.20	13.33	13.03	13.33			
CaO	23.54	23.64	23.74	22.85	23.39	23.84	23.29			
MgO	2.50	2.50	2.50	2.55	2.50	2.50	2.50			
TiO ₂	0.50	0.50	0.50	1.10	0.50	0.50	0.50			
Li ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90			
ZnO	1.00	1.00	1.00	1.00	1.00	1.00	1.00			
Fe ₂ O ₃	0.23	0.23	0.23	0.25	0.23	0.23	0.23			
B ₂ O ₃	-	-	-	-	-	-	-			
RO (CaO + MgO)	26.04	26.14	26.24	25.40	25.89	26.34	25.79			
SiO ₂ /CaO	2.48	2.46	2.45	2.54	2.49	2.43	2.50			
SiO ₂ /RO	2.24	2.23	2.21	2.29	2.25	2.20	2.26			
SiO ₂ /Al ₂ O ₃	4.47	4.47	4.46	4.41	4.36	4.45	4.37			
Al ₂ O ₃ /CaO	0.55	0.55	0.55	0.58	0.57	0.55	0.57			
SiO ₂ + Al ₂ O ₃	71.33	71.23	71.13	71.35	71.48	71.03	71.58			
R2O+RO+B ₂ O ₃	26.94	27.04	27.14	26.30	26.79	27.24	26.69			
(Si+Al)/(R2O+RO+B)	2.65	2.63	2.62	2.71	2.67	2.61	2.68			
SiO ₂ - RO	32.26	32.06	31.86	32.75	32.26	31.66	32.46			
Al ₂ O ₃ /RO	0.50	0.50	0.50	0.52	0.51	0.49	0.52			
Log3 FT, °C	1204	1205	1206	1207	1208	1208	1213			
Liquidus T, °C	1147	1148	1144	1136	1152	1152	1146			
Delta T, °C	57	57	62	71	56	56	67			

Table 15 – Type 4 Glasses

Components (wt%)	Examples							
	170	171	172	173	174	175		
SiO ₂	58.00	58.10	57.35	57.95	59.61	59.47		
Al ₂ O ₃	13.03	13.63	13.20	13.20	12.16	12.16		
CaO	23.84	23.14	23.65	24.05	23.50	24.22		
MgO	2.50	2.50	2.55	2.55	2.50	1.90		
TiO ₂	0.50	0.50	1.10	1.10	1.10	1.10		
Li ₂ O	0.90	0.90	0.90	0.90	0.45	0.45		
ZnO	1.00	1.00	1.00	1.00	0.45	0.45		
Fe ₂ O ₃	0.23	0.23	0.25	0.25	-	-		
B ₂ O ₃	-	-	-	-	-	-		
RO (CaO + MgO)	26.34	25.64	26.20	26.60	26.00	26.12		
SiO ₂ /CaO	2.43	2.51	2.42	2.41	2.54	2.46		
SiO ₂ /RO	2.20	2.26	2.19	2.18	2.29	2.28		
SiO ₂ /Al ₂ O ₃	4.45	4.26	4.34	4.39	4.90	4.89		
Al ₂ O ₃ /CaO	0.55	0.59	0.56	0.55	0.52	0.50		
SiO ₂ + Al ₂ O ₃	71.03	71.73	70.55	71.15	71.77	71.63		
R2O+RO+B ₂ O ₃	27.24	26.54	27.10	27.50	26.45	26.57		
(Si+Al)/(R2O+RO+B)	2.61	2.70	2.60	2.60	2.71	2.70		
SiO ₂ - RO	31.66	32.46	31.15	31.30	33.61	33.35		
Al ₂ O ₃ /RO	0.49	0.53	0.50	0.50	0.47	0.47		
Log3 FT, °C	1208	1212	1195	1195	1229	1218		
Liquidus T, °C	1149	1157	1141	1140	1154	1159		
Delta T, °C	59	55	54	55	75	59		

Table 16 – Type 5 Glasses

Components (wt%)	Example	
	176	177
SiO ₂	59.00	58.70
Al ₂ O ₃	12.00	11.90
CaO	22.50	22.4
MgO	3.40	3.40
TiO ₂	1.00	1.00
Na ₂ O	0.90	0.90
ZnO	1.00	1.50
K ₂ O	-	-
Fe ₂ O ₃	0.20	0.20
B ₂ O ₃	-	-
RO	25.90	25.80
SiO ₂ /CaO	2.62	2.62
SiO ₂ /RO	2.28	2.28
SiO ₂ /Al ₂ O ₃	4.92	4.93
Al ₂ O ₃ /CaO	0.53	0.53
SiO ₂ +Al ₂ O ₃	71.00	70.60
R2O+RO+B ₂ O ₃	26.80	26.70
(Si+Al)/(R2O+RO+B)	2.65	2.64
SiO ₂ -RO	33.10	32.90
Al ₂ O ₃ /RO	0.46	0.46
Log3 FT °C	1234	1231
Liquidus T °C	1175	1181
Delta(T3-TL) °C	59	50

Table 17 – Type 6 Glasses

Components (wt%)	Examples													
	178	179	180	181	182	183	184	185	186	187				
SiO ₂	58.00	58.10	58.30	57.90	58.11	57.60	58.50	57.80	58.00	57.80				
Al ₂ O ₃	13.03	13.03	13.03	13.23	13.36	13.23	12.76	13.43	13.03	13.03				
CaO	23.84	23.74	23.54	23.74	23.40	23.84	23.61	23.64	23.84	23.84				
MgO	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50				
TiO ₂	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50				
Na ₂ O	-	-	-	-	-	0.10	-	-	-	-				
K ₂ O	-	-	-	-	-	-	-	-	-	-				
Li ₂ O	0.90	0.90	0.90	0.90	0.90	0.80	0.90	0.90	0.90	0.90				
Fe ₂ O ₃	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23				
B ₂ O ₃	1.00	1.00	1.00	1.00	1.00	1.20	1.00	1.00	1.00	1.20				
RO (CaO + MgO)	26.34	26.24	26.04	26.24	25.90	26.34	26.11	26.14	26.34	26.34				
SiO ₂ /CaO	2.43	2.45	2.48	2.44	2.48	2.42	2.48	2.45	2.43	2.42				
SiO ₂ /RO	2.20	2.21	2.24	2.21	2.24	2.19	2.24	2.21	2.20	2.19				
SiO ₂ /Al ₂ O ₃	4.45	4.46	4.47	4.38	4.35	4.35	4.58	4.30	4.45	4.44				
Al ₂ O ₃ /CaO	0.55	0.55	0.55	0.56	0.57	0.55	0.54	0.57	0.55	0.55				
SiO ₂ + Al ₂ O ₃	71.03	71.13	71.33	71.13	71.47	70.83	71.26	71.23	71.03	70.83				
R2O+RO+B ₂ O ₃	28.24	28.14	27.94	28.14	27.80	28.44	28.01	28.04	28.24	28.44				
(Si+Al)/(R2O+RO+B)	2.52	2.53	2.55	2.53	2.57	2.49	2.54	2.54	2.52	2.49				
SiO ₂ - RO	31.66	31.86	32.26	31.66	32.21	31.26	32.39	31.66	31.66	31.46				
Al ₂ O ₃ /RO	0.49	0.50	0.50	0.50	0.52	0.50	0.49	0.51	0.49	0.49				
Log3 FT, °C	1192	1194	1195	1195	1196	1196	1197	1197	1198	1198				
Liquidus T, °C	1137	1135	1140	1137	1133	1133	1139	1139	1138	1135				
Delta T, °C	55	59	55	58	63	63	58	58	60	63				

Table 18 – Type 6 Glasses

Components (wt%)	Examples										
	188	189	190	191	192	193	194	195	196*	197*	
SiO ₂	58.00	57.90	58.15	58.25	58.00	58.10	58.30	58.20	58.74	58.64	
Al ₂ O ₃	13.43	13.43	13.33	13.33	13.63	13.63	13.03	13.03	13.05	13.15	
CaO	23.44	23.54	23.39	23.29	23.24	23.14	23.54	23.64	22.97	22.97	
MgO	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.36	2.36	
TiO ₂	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.49	0.49	
Na ₂ O	-	-	-	-	-	-	-	-	-	-	
K ₂ O	-	-	-	-	-	-	-	-	0.09	0.09	
Li ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.91	0.91	
Fe ₂ O ₃	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.29	0.29	
B ₂ O ₃	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	
RO (CaO + MgO)	25.94	26.04	25.89	25.79	25.74	25.64	26.04	26.14	25.33	25.33	
SiO ₂ /CaO	2.47	2.45	2.49	2.51	2.50	2.51	2.48	2.46	2.56	2.55	
SiO ₂ /RO	2.24	2.22	2.25	2.26	2.25	2.27	2.24	2.23	2.32	2.32	
SiO ₂ /Al ₂ O ₃	4.32	4.31	4.36	4.37	4.26	4.26	4.47	4.47	4.50	4.46	
Al ₂ O ₃ /CaO	0.57	0.57	0.57	0.57	0.59	0.59	0.55	0.55	0.57	0.57	
SiO ₂ + Al ₂ O ₃	71.43	71.33	71.48	71.58	71.63	71.73	71.33	71.23	71.79	71.79	
R2O+RO+B ₂ O ₃	27.84	27.94	27.79	27.69	27.14	27.54	27.94	28.04	27.33	27.33	
(Si+Al)/(R2O+RO+B)	2.57	2.55	2.57	2.59	2.64	2.60	2.55	2.54	2.63	2.63	
SiO ₂ - RO	32.06	31.86	32.26	32.46	32.26	32.46	32.26	32.06	33.41	33.31	
Al ₂ O ₃ /RO	0.51	0.52	0.51	0.52	0.53	0.53	0.50	0.50	0.52	0.52	
Log3 FT, °C	1202	1203	1203	1202	1207	1212	1200	1201	1210	1209	
Liquidus T, °C	1139	1137	1136	1145	1144	1146	1132	1137	1145	1151	
Delta T, °C	63	66	67	57	63	66	68	64	65	58	

* compositions include 0.05 wt% SrO and 0.08 wt% SO₃

Table 18 – Type 6 Glasses (cont'd)

Components (wt%)	Examples												
	198*	199	200	201	202	203	204	205	206	207			
SiO ₂	58.64	58.75	57.80	57.60	57.60	57.60	58.50	58.40	58.30	58.40			
Al ₂ O ₃	12.95	12.93	13.23	13.23	13.23	13.03	12.76	12.76	13.03	13.03			
CaO	22.87	22.93	23.84	23.84	23.84	24.04	23.61	23.71	23.54	23.44			
MgO	2.36	2.36	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50			
TiO ₂	0.49	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50			
Na ₂ O	-	0.04	-	-	0.20	0.20	-	-	-	-			
K ₂ O	0.09	0.10	-	-	-	-	-	-	-	-			
Li ₂ O	0.91	0.90	0.90	0.90	0.70	0.70	0.90	0.90	0.90	0.90			
Fe ₂ O ₃	0.29	0.29	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23			
B ₂ O ₃	1.00	1.20	1.00	1.20	1.20	1.20	1.00	1.00	1.00	1.00			
RO (CaO + MgO)	25.23	25.29	26.34	26.34	26.34	26.54	26.11	26.21	26.04	25.94			
SiO ₂ /CaO	2.56	2.56	2.42	2.42	2.42	2.40	2.48	2.46	2.48	2.49			
SiO ₂ /RO	2.32	2.32	2.19	2.19	2.19	2.17	2.24	2.23	2.24	2.25			
SiO ₂ /Al ₂ O ₃	4.53	4.54	4.37	4.35	4.35	4.37	4.58	4.58	4.47	4.48			
Al ₂ O ₃ /CaO	0.57	0.56	0.55	0.55	0.55	0.54	0.54	0.54	0.55	0.56			
SiO ₂ + Al ₂ O ₃	71.59	71.68	71.03	70.83	70.83	70.63	71.26	71.16	71.33	71.43			
R2O+RO+B ₂ O ₃	27.23	27.53	28.24	28.44	28.44	28.64	28.01	28.11	27.94	27.84			
(Si+Al)/(R2O+RO+B)	2.63	2.60	2.51	2.49	2.49	2.47	2.54	2.53	2.55	2.57			
SiO ₂ - RO	33.41	33.46	31.46	31.26	31.26	31.06	32.39	32.19	32.26	32.36			
Al ₂ O ₃ /RO	0.51	0.51	0.50	0.50	0.50	0.49	0.49	0.49	0.50	0.51			
Log3 FT, °C	1204	1210	1201	1200	1208	1201	1202	1203	1201	1208			
Liquidus T, °C	1142	1127	1126	1125	1135	1145	1141	1145	1138	1137			
Delta T, °C	62	83	75	75	73	56	61	58	63	71			

* compositions include 0.05 wt% SrO and 0.08 wt% SO₃

Table 18 – Type 6 Glasses (cont'd)

Components (wt%)	Examples													
	208	209	210	211	212	213	214	215	216	217				
SiO ₂	58.15	58.25	58.70	58.00	57.60	58.61	58.61	58.00	58.40	58.40				
Al ₂ O ₃	13.33	13.33	12.75	13.03	13.03	12.16	12.16	13.23	13.36	13.03				
CaO	23.39	23.29	23.50	23.84	24.04	23.50	23.50	23.64	23.11	23.44				
MgO	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50				
TiO ₂	0.50	0.50	0.50	0.50	0.50	1.10	1.10	0.50	0.50	0.50				
Na ₂ O	-	-	0.60	-	-	-	0.45	-	-	-				
K ₂ O	-	-	-	-	-	-	-	-	-	-				
Li ₂ O	0.90	0.90	0.60	0.90	0.90	0.90	0.45	0.90	0.90	0.90				
Fe ₂ O ₃	0.25	0.25	0.25	0.23	0.23	0.23	0.23	0.23	0.23	0.23				
B ₂ O ₃	1.00	1.00	0.60	1.00	1.20	1.00	1.00	1.00	1.00	1.00				
RO (CaO + MgO)	25.89	25.79	26.00	26.34	26.54	26.00	26.00	26.14	25.61	25.94				
SiO ₂ /CaO	2.49	2.50	2.50	2.43	2.40	2.49	2.49	2.45	2.52	2.49				
SiO ₂ /RO	2.25	2.26	2.26	2.20	2.17	2.25	2.25	2.22	2.28	2.25				
SiO ₂ /Al ₂ O ₃	4.36	4.37	4.60	4.45	4.42	4.82	4.82	4.38	4.37	4.48				
Al ₂ O ₃ /CaO	0.57	0.57	0.54	0.55	0.54	0.52	0.52	0.56	0.58	0.56				
SiO ₂ + Al ₂ O ₃	71.48	71.58	71.45	71.03	70.63	70.77	70.77	71.23	71.76	71.43				
R2O+RO+B ₂ O ₃	27.79	27.69	27.80	28.24	28.64	27.90	27.90	28.04	27.51	27.84				
(Si+Al)/(R2O+RO+B)	2.57	2.59	2.57	2.52	2.47	2.54	2.54	2.54	2.61	2.57				
SiO ₂ - RO	32.26	32.46	32.70	31.66	31.06	32.61	32.61	31.86	32.79	32.46				
Al ₂ O ₃ /RO	0.51	0.52	0.49	0.49	0.49	0.47	0.47	0.51	0.52	0.50				
Log3 FT, °C	1197	1200	1216	1202	1194	1201	1227	1201	1204	1201				
Liquidus T, °C	1130	1134	1160	1137	1142	1142	1159	1135	1133	1136				
Delta T, °C	67	66	56	65	52	59	68	66	71	65				

Table 18 -- Type 6 Glasses (cont'd)

Components (wt%)	Examples													
	218	219	220	221	222	223	224	225	226	227				
SiO ₂	58.50	58.60	58.00	58.10	58.10	58.70	58.70	58.70	58.61	58.40				
Al ₂ O ₃	13.03	13.03	13.63	13.23	13.43	12.75	12.35	12.35	12.16	12.76				
CaO	23.34	23.24	23.24	23.54	23.34	23.50	23.50	23.50	23.50	23.71				
MgO	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50				
TiO ₂	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	1.10	0.50				
Na ₂ O	-	-	-	-	-	0.30	0.60	0.30	-	-				
K ₂ O	-	-	-	-	-	-	-	-	-	-				
Li ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.60	0.90	0.90	0.90				
Fe ₂ O ₃	0.23	0.23	0.23	0.23	0.23	0.25	0.25	0.25	0.23	0.23				
B ₂ O ₃	1.00	1.00	1.00	1.00	1.00	0.60	1.00	1.00	1.00	1.00				
RO (CaO + MgO)	25.84	25.74	25.74	26.04	25.84	26.00	26.00	26.00	26.00	26.21				
SiO ₂ /CaO	2.51	2.51	2.50	2.47	2.49	2.50	2.50	2.50	2.49	2.46				
SiO ₂ /RO	2.26	2.28	2.25	2.23	2.25	2.26	2.26	2.26	2.25	2.23				
SiO ₂ /Al ₂ O ₃	4.49	4.50	4.26	4.39	4.33	4.60	4.75	4.75	4.82	4.58				
Al ₂ O ₃ /CaO	0.56	0.56	0.59	0.56	0.58	0.54	0.53	0.53	0.52	0.54				
SiO ₂ + Al ₂ O ₃	71.53	71.63	71.63	71.33	71.53	71.45	71.05	71.05	70.77	71.16				
R2O+RO+B ₂ O ₃	27.74	27.64	27.64	27.94	27.74	27.80	28.20	28.20	27.90	28.11				
(Si+Al)/(R2O+RO+B)	2.58	2.59	2.59	2.55	2.58	2.57	2.52	2.52	2.54	2.53				
SiO ₂ - RO	32.66	32.86	32.26	32.06	32.26	32.70	32.70	32.70	32.61	32.19				
Al ₂ O ₃ /RO	0.50	0.51	0.53	0.51	0.52	0.49	0.48	0.48	0.47	0.49				
Log3 FT, °C	1204	1204	1206	1199	1204	1204	1207	1202	1194	1194				
Liquidus T, °C	1133	1135	1136	1133	1134	1153	1157	1149	1141	1144				
Delta T, °C	71	69	70	63	70	51	50	53	53	50				

Table 18 – Type 6 Glasses (cont'd)

Components (wt%)	Examples												
	228	229	230	231	232	233	234	235	236	237			
SiO ₂	58.80	57.60	58.11	58.91	58.11	58.30	58.20	58.10	58.70	58.70			
Al ₂ O ₃	12.46	13.03	13.36	12.16	13.36	13.03	13.03	13.03	13.35	13.35			
CaO	23.61	24.04	23.40	23.80	23.40	23.54	23.64	23.74	23.50	23.50			
MgO	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50			
TiO ₂	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50	0.50			
Na ₂ O	-	0.10	-	-	-	-	-	-	-	-			
K ₂ O	-	-	-	-	-	-	-	-	-	-			
Li ₂ O	0.90	0.80	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.60			
Fe ₂ O ₃	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.25	0.25			
B ₂ O ₃	1.00	1.20	1.00	1.00	1.00	1.00	1.00	1.00	0.30	0.60			
RO (CaO + MgO)	26.11	26.54	25.90	26.30	25.90	26.04	26.14	26.24	26.00	26.00			
SiO ₂ /CaO	2.49	2.40	2.48	2.48	2.48	2.48	2.46	2.45	2.50	2.50			
SiO ₂ /RO	2.25	2.17	2.24	2.24	2.24	2.24	2.23	2.21	2.26	2.26			
SiO ₂ /Al ₂ O ₃	4.70	4.42	4.35	4.84	4.35	4.47	4.47	4.46	4.40	4.40			
Al ₂ O ₃ /CaO	0.53	0.54	0.57	0.51	0.57	0.55	0.55	0.55	0.57	0.57			
SiO ₂ + Al ₂ O ₃	71.26	70.63	71.47	71.07	71.47	71.23	71.23	71.13	72.05	72.05			
R2O+RO+B ₂ O ₃	28.01	28.64	27.80	28.20	27.80	27.94	28.04	28.14	27.20	27.20			
(Si+Al)/(R2O+RO+B)	2.54	2.47	2.57	2.52	2.57	2.55	2.54	2.53	2.65	2.65			
SiO ₂ - RO	32.69	31.06	32.21	32.61	32.21	32.26	32.06	31.86	32.70	32.70			
Al ₂ O ₃ /RO	0.48	0.49	0.52	0.46	0.52	0.50	0.50	0.50	0.51	0.51			
Log3 FT, °C	1195	1196	1229	1216	1213	1202	1202	1205	1207	1224			
Liquidus T, °C	1145	1145	1155	1148	1142	1136	1136	1137	1144	1145			
Delta T, °C	50	51	133	123	126	120	119	122	114	142			

Table 18 – Type 6 Glasses (cont'd)

Components (wt%)	Examples												
	238	239	240	241	242	243	244	245	246	247			
SiO ₂	58.11	58.20	59.53	59.61	59.11	59.11	59.16	59.21	59.11	59.36			
Al ₂ O ₃	13.36	13.23	12.25	12.16	12.16	12.16	12.16	12.16	12.16	12.41			
CaO	23.40	23.44	23.17	23.50	23.00	23.00	23.20	23.40	23.50	23.60			
MgO	2.50	2.50	2.52	2.50	2.50	2.50	2.25	2.00	2.00	2.00			
TiO ₂	0.50	0.50	0.50	1.10	1.10	1.10	1.10	1.10	1.10	0.50			
Na ₂ O	-	-	-	-	-	-	-	-	-	-			
K ₂ O	-	-	-	-	-	-	-	-	-	-			
Li ₂ O	0.90	0.90	0.80	0.45	0.90	0.90	0.90	0.90	0.90	0.90			
Fe ₂ O ₃	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23			
B ₂ O ₃	1.00	1.00	1.00	0.45	1.00	1.00	1.00	1.00	1.00	1.00			
RO (CaO + MgO)	25.90	25.94	25.69	26.00	25.50	25.50	25.45	25.40	25.50	25.60			
SiO ₂ /CaO	2.48	2.48	2.57	2.54	2.57	2.57	2.55	2.53	2.51	2.51			
SiO ₂ /RO	2.24	2.24	2.32	2.29	2.32	2.32	2.32	2.33	2.32	2.32			
SiO ₂ /Al ₂ O ₃	4.35	4.40	4.86	4.90	4.86	4.86	4.87	4.87	4.87	4.78			
Al ₂ O ₃ /CaO	0.57	0.56	0.53	0.52	0.53	0.53	0.52	0.52	0.52	0.53			
SiO ₂ + Al ₂ O ₃	71.47	71.43	71.78	71.77	71.27	71.27	71.32	71.37	71.27	71.77			
R ₂ O+RO+B ₂ O ₃	27.80	27.84	27.49	26.90	27.40	27.40	27.35	27.30	27.40	27.50			
(Si+Al)/(R ₂ O+RO+B)	2.57	2.57	2.61	2.67	2.60	2.60	2.61	2.61	2.60	2.61			
SiO ₂ - RO	32.21	32.26	33.84	33.61	33.61	33.61	33.71	33.81	33.61	33.76			
Al ₂ O ₃ /RO	0.52	0.51	0.48	0.47	0.48	0.48	0.48	0.48	0.48	0.53			
Log3 FT, °C	1212	1204	1214	1230	1205	1216	1218	1213	1209	1216			
Liquidus T, °C	1135	1135	1143	1155	1142	1143	1147	1153	1153	1153			
Delta T, °C	139	124	71	75	63	73	71	60	56	63			

Table 18 – Type 6 Glasses (cont'd)

Component (wt%)	Examples												
	248	249	250	251	252	253	254	255	256	257			
SiO ₂	59.31	59.36	59.41	59.11	59.16	59.21	59.16	59.11	59.01	59.21			
Al ₂ O ₃	12.56	12.51	12.46	12.16	12.16	12.16	12.26	12.26	12.36	12.16			
CaO	23.50	23.50	23.50	23.00	23.20	23.40	23.45	23.50	23.50	23.50			
MgO	2.00	2.00	2.00	2.50	2.25	2.00	2.50	2.50	2.50	2.50			
TiO ₂	0.50	0.50	0.50	1.10	1.10	1.10	0.50	0.50	0.50	0.50			
Na ₂ O	-	-	-	-	-	-	-	-	-	-			
K ₂ O	-	-	-	-	-	-	-	-	-	-			
Li ₂ O	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90	0.90			
Fe ₂ O ₃	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23	0.23			
B ₂ O ₃	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00			
RO (CaO + MgO)	25.50	25.50	25.50	25.50	25.45	25.40	25.95	26.00	26.00	26.00			
SiO ₂ /CaO	2.52	2.53	2.53	2.57	2.55	2.53	2.52	2.52	2.51	2.52			
SiO ₂ /RO	2.33	2.33	2.33	2.32	2.32	2.33	2.28	2.27	2.27	2.28			
SiO ₂ /Al ₂ O ₃	4.72	4.75	4.77	4.86	4.87	4.87	4.83	4.82	4.77	4.87			
Al ₂ O ₃ /CaO	0.53	0.53	0.53	0.53	0.52	0.52	0.52	0.52	0.53	0.52			
SiO ₂ + Al ₂ O ₃	71.87	71.87	71.87	71.27	71.32	71.37	71.42	71.37	71.37	71.37			
R ₂ O+RO+B ₂ O ₃	27.40	27.40	27.40	27.40	27.35	27.30	27.85	27.90	27.90	27.90			
(Si+Al)/(R ₂ O+RO+B)	2.62	2.62	2.62	2.60	2.61	2.61	2.56	2.56	2.56	2.56			
SiO ₂ - RO	33.81	33.86	33.91	33.61	33.71	33.81	33.21	33.11	33.01	33.21			
Al ₂ O ₃ /RO	0.49	0.49	0.49	0.48	0.48	0.48	0.47	0.47	0.48	0.47			
Log3 FT, °C	1220	1220	1220	1216	1214	1220	1209	1210	1210	1201			
Liquidus T, °C	1153	1158	1155	1144	1147	1158	1150	1152	1152	1143			
Delta T, °C	67	62	65	72	67	62	59	58	58	58			

Table 18 – Type 6 Glasses (cont'd)

Components (wt%)	Examples														
	258	259	260	261	262	263	264	265	266	267					
SiO ₂	58.75	58.75	58.10	58.70	59.11	59.31	59.21	54.60	56.75	57.85					
Al ₂ O ₃	12.93	12.93	13.63	13.35	12.16	12.26	12.26	13.35	13.20	12.45					
CaO	22.93	22.93	23.14	23.50	23.50	22.30	23.40	24.55	23.95	24.05					
MgO	2.36	2.36	2.50	2.50	2.00	2.50	2.50	2.55	2.55	2.55					
TiO ₂	0.50	0.50	0.50	0.50	1.10	0.50	0.50	0.35	1.10	0.55					
Na ₂ O	0.14	0.24	-	-	-	-	-	0.15	0.60	0.60					
K ₂ O	0.10	0.10	-	-	-	-	-	0.55	-	-					
Li ₂ O	0.80	0.70	0.90	0.30	0.90	0.90	0.90	0.30	0.30	0.30					
Fe ₂ O ₃	0.29	0.29	0.23	0.25	0.23	0.23	0.23	0.28	0.25	0.35					
B ₂ O ₃	1.20	1.20	1.00	0.90	1.00	1.00	1.00	3.00	1.40	1.30					
F	-	-	-	-	-	-	-	0.20	-	-					
SrO	-	-	-	-	-	-	-	0.12	-	-					
RO (CaO + MgO)	25.29	25.29	25.64	26.00	25.50	24.80	25.90	27.10	26.50	26.60					
SiO ₂ /CaO	2.56	2.56	2.51	2.50	2.52	2.66	2.53	2.22	2.37	2.39					
SiO ₂ /RO	2.32	2.32	2.27	2.26	2.32	2.39	2.29	2.01	2.14	2.35					
SiO ₂ /Al ₂ O ₃	4.54	4.54	4.26	4.40	4.86	4.84	4.83	4.09	4.30	4.65					
Al ₂ O ₃ /CaO	0.56	0.56	0.59	0.57	0.52	0.55	0.52	0.54	0.55	0.52					
SiO ₂ + Al ₂ O ₃	71.68	71.68	71.73	72.05	71.27	71.57	71.47	67.95	69.95	71.30					
R2O+RO+B ₂ O ₃	27.53	27.53	27.54	27.20	27.40	26.70	27.80	31.10	28.80	28.80					
(Si+Al)/(R2O+RO+B)	2.60	2.60	2.60	2.65	2.60	2.68	2.57	2.18	2.43	2.48					
SiO ₂ - RO	33.46	33.46	32.46	32.70	33.61	34.51	33.31	27.50	30.25	31.25					
Al ₂ O ₃ /RO	0.51	0.51	0.53	0.51	0.48	0.49	0.47	0.49	0.50	0.47					
Log3 FT, °C	1211	1218	1204	1239	1215	1209	1210	1187	1206	1208					
Liquidus T, °C	1127	1129	1115	1143	1155	1148	1156	1133	1152	1154					
Delta T, °C	84	89	89	96	60	61	54	54	54	54					

Table 19— Misc. Glasses

Components (wt%)	Examples						
	268	269	270	271	272		
SiO ₂	57.82	58.70	58.70	57.72	58.61		
Al ₂ O ₃	11.80	13.35	13.35	11.80	12.16		
CaO	22.80	23.50	23.50	22.80	23.50		
MgO	2.43	2.50	2.50	2.52	2.50		
TiO ₂	1.07	0.50	0.50	1.07	1.10		
Na ₂ O	0.87	-	0.90	0.87	-		
Li ₂ O	-	0.30	0.30	-	0.30		
ZnO	-	-	-	-	0.30		
MnO	3.00	-	-	-	0.30		
MnO ₂	-	-	-	3.00	-		
Fe ₂ O ₃	0.22	0.25	0.25	0.22	0.23		
B ₂ O ₃	-	0.90	-	-	1.00		
RO	25.23	26.00	26.00	25.32	26.00		
SiO ₂ /CaO	2.54	2.50	2.50	2.53	2.49		
SiO ₂ /RO	2.29	2.26	2.26	2.28	2.25		
SiO ₂ /Al ₂ O ₃	4.90	4.40	4.40	4.89	4.82		
Al ₂ O ₃ /CaO	0.52	0.57	0.57	0.52	0.52		
SiO ₂ +Al ₂ O ₃	69.62	72.05	72.05	69.52	70.77		
RO2+RO+B ₂ O ₃	26.10	27.20	26.30	26.19	27.30		
(Si+Al)/(R2O+RO+B)	2.67	2.65	2.74	2.65	2.59		
SiO ₂ -RO	32.59	32.70	32.70	32.40	32.61		
Al ₂ O ₃ /RO	0.47	0.51	0.51	0.47	0.47		
Log3 FT, °C	1219	1239	1241	1222	1223		
Liquidus T, °C	1163	1143	1165	1161	1139		
Delta T, °C	52	96	76	61	94		

Table 20— Production Glasses

Components (wt%)	Examples									
	273	274	275	276	277	278	279			
SiO ₂	57.07	57.21	56.94	56.68	56.71	56.53	55.97			
Al ₂ O ₃	12.69	12.77	12.72	12.68	12.95	12.84	12.68			
CaO	23.91	24.15	24.00	24.11	24.56	24.42	24.00			
MgO	2.53	2.57	2.56	2.58	2.44	2.42	2.45			
TiO ₂	1.09	1.12	1.12	1.09	1.07	1.07	1.05			
Na ₂ O	0.89	0.90	0.87	0.90	0.92	0.92	0.88			
K ₂ O	0.060	0.050	0.050	0.060	0.070	0.060	0.060			
Fe ₂ O ₃	0.255	0.271	0.255	0.263	0.278	0.267	0.265			
B ₂ O ₃	1.37	1.36	1.42	1.40	1.54	1.70	1.36			
SO ₃	0.029	0.032	0.032	0.031	0.028	0.024	0.025			
SrO	0.040	0.040	0.050	0.050	0.050	0.050	0.050			
Cr ₂ O ₃	0.002	0.002	0.002	0.002	0.009	0.008	0.007			
RO	26.44	26.72	26.56	26.69	27.00	26.84	26.45			
SiO ₂ /CaO	2.39	2.37	2.37	2.35	2.31	2.31	2.33			
SiO ₂ /RO	2.16	2.14	2.14	2.12	2.10	2.11	2.12			
SiO ₂ /Al ₂ O ₃	4.50	4.48	4.48	4.47	4.38	4.40	4.41			
Al ₂ O ₃ /CaO	0.53	0.53	0.53	0.53	0.53	0.53	0.53			
SiO ₂ +Al ₂ O ₃	69.76	69.98	69.66	69.36	69.66	69.37	68.65			
RO2+RO+B ₂ O ₃	28.96	29.25	29.11	29.25	29.74	29.73	28.96			
(Si+Al)/(R2O+RO+B)	2.41	2.39	2.39	2.37	2.34	2.33	2.37			
SiO ₂ -RO	30.63	30.49	30.38	29.99	29.71	29.69	29.52			
Al ₂ O ₃ /RO	0.48	0.48	0.48	0.48	0.48	0.48	0.48			
Log3 FT, °C	1214		1217		1203	1212	1212			
Liquidus T, °C	1147		1134		1145	1147	1134			
Delta T, °C	67		83		58	65	76			

Table 20 – Production Glasses (cont'd)

Components (wt%)	Examples							
	280	281	282	283	284	285		
SiO ₂	56.70	56.66	56.63	56.54	56.43	56.61		
Al ₂ O ₃	12.91	12.86	12.85	12.79	12.75	12.83		
CaO	24.61	24.53	24.69	24.53	24.44	25.24		
MgO	2.54	2.56	2.60	2.54	2.54	2.55		
TiO ₂	1.10	1.09	0.94	0.94	1.09	1.20		
Na ₂ O	0.91	0.90	0.93	0.90	0.90	0.92		
K ₂ O	0.060	0.060	0.070	0.070	0.050	0.050		
Fe ₂ O ₃	0.260	0.265	0.267	0.268	0.270	0.279		
B ₂ O ₃	1.32	1.15	1.34	1.27	1.24	1.29		
SO ₃	0.018	0.020	0.018	0.016	0.014	0.016		
SrO	0.040	0.040	0.040	0.040	0.040	0.040		
Cr ₂ O ₃	0.004	0.004	0.003	0.002	0.008	0.004		
RO	27.15	27.09	27.29	27.07	26.98	27.79		
SiO ₂ /CaO	2.30	2.31	2.29	2.30	2.31	2.24		
SiO ₂ /RO	2.09	2.09	2.08	2.09	2.09	2.04		
SiO ₂ /Al ₂ O ₃	4.39	4.41	4.41	4.42	4.43	4.41		
Al ₂ O ₃ /CaO	0.52	0.52	0.52	0.52	0.52	0.51		
SiO ₂ +Al ₂ O ₃	69.61	69.52	69.48	69.33	69.18	69.44		
RO ₂ +RO+B ₂ O ₃	29.64	29.41	29.83	29.51	29.39	30.28		
(Si+Al)/(R ₂ O+RO+B)	2.35	2.36	2.33	2.35	2.35	2.29		
SiO ₂ -RO	29.55	29.57	29.34	29.47	29.45	28.82		
Al ₂ O ₃ /RO	0.48	0.47	0.47	0.47	0.47	0.46		
Log3 FT, °C		1213	1214					
Liquidus T, °C		1149	1158					
Delta T, °C		64	55					

Table 21 – Summary Sheet

	Type 1 Glasses		Type 2 Glasses		Type 3 Glasses		Type 4 Glasses		Type 5 Glasses		Type 6 Glasses	
	Low	High	Low	High	Low	High	Low	High	Low	High	Low	High
RO (CaO + MgO)	26.30	27.05	24.80	27.56	24.01	26.70	25.40	26.60	25.80	25.90	25.29	26.60
SiO ₂ /CaO	2.35	2.47	2.20	2.55	2.39	2.71	2.41	2.54	2.62	2.62	2.22	2.66
SiO ₂ /RO	2.13	2.23	1.96	2.29	2.16	2.52	2.18	2.29	2.28	2.28	2.01	2.39
SiO ₂ /Al ₂ O ₃	4.25	4.84	3.79	4.76	4.30	4.99	4.26	4.90	4.92	4.93	4.09	4.90
Al ₂ O ₃ /CaO	0.51	0.58	0.51	0.59	0.50	0.59	0.50	0.59	0.53	0.53	0.51	0.59
SiO ₂ + Al ₂ O ₃	70.85	71.86	66.10	70.95	71.05	73.67	71.03	71.73	70.60	71.00	67.95	72.05
R2O+RO+B ₂ O ₃	27.20	27.95	28.15	32.79	25.15	27.60	26.30	27.50	26.70	26.80	26.70	31.10
(Si+Al)/(R2O+RO+B)	2.55	2.64	2.02	2.67	2.30	2.96	2.60	2.71	2.64	2.65	2.18	2.68
SiO ₂ - RO	30.55	32.55	26.50	32.55	30.95	36.56	31.15	33.61	32.90	33.10	27.50	33.91
Al ₂ O ₃ /RO	0.46	0.52	0.46	0.56	0.47	0.53	0.47	0.53	0.46	0.46	0.46	0.53

Table 22 – Summary Sheet

	Types 1 & 2 Glasses		Types 3-6 Glasses		Types 1&3-5 Glasses (boron-free)		Types 2 & 6 Glasses (contains boron)		Production Glasses (contains boron)	
	Low	High	Low	High	Low	High	Low	High	Low	High
RO (CaO + MgO)	24.80	27.56	24.01	26.70	24.01	26.90	24.80	27.56	26.44	27.79
SiO ₂ /CaO	2.20	2.55	2.39	2.71	2.36	2.73	2.20	2.66	2.24	2.37
SiO ₂ /RO	1.96	2.29	2.16	2.52	2.14	2.52	1.96	2.39	2.08	2.16
SiO ₂ /Al ₂ O ₃	3.79	4.84	4.26	4.99	4.26	4.99	3.79	4.90	4.38	4.50
Al ₂ O ₃ /CaO	0.51	0.59	0.50	0.59	0.50	0.59	0.51	0.59	0.51	0.53
SiO ₂ + Al ₂ O ₃	66.10	71.45	70.60	73.67	70.85	73.67	66.10	72.05	68.65	69.98
R2O+RO+B ₂ O ₃	27.20	32.79	25.15	28.64	25.15	27.80	26.90	32.79	28.96	30.28
(Si+Al)/(R2O+RO+B)	2.02	2.67	2.30	2.96	2.30	2.96	2.02	2.68	2.29	2.41
SiO ₂ – RO	26.50	32.55	30.95	36.56	30.55	36.56	26.50	33.91	28.82	30.63
Al ₂ O ₃ /RO	0.46	0.56	0.46	0.53	0.46	0.53	0.46	0.56	0.46	0.48

WHAT IS CLAIMED IS:

- 5 1. A glass composition comprising ingredients in the ranges of:
- | | | |
|----|--------------------------------------|---------------------------------|
| | SiO ₂ | 52 to 60 percent by weight; |
| | Al ₂ O ₃ | 8 to 16 percent by weight; |
| | CaO | 21 to 26 percent by weight; |
| | MgO | 1 to 5 percent by weight; |
| 10 | TiO ₂ | up to 2.00 percent by weight; |
| | Na ₂ O | up to 1.00 percent by weight; |
| | K ₂ O | up to 1.00 percent by weight; |
| | Na ₂ O + K ₂ O | 0.70 to 2.00 percent by weight; |
| | Fe ₂ O ₃ | 0.10 to 0.50 percent by weight; |
| 15 | B ₂ O ₃ | 1.00 to 3.50 percent by weight |

wherein:

the glass composition has a log3 forming temperature in the range of equal to and greater than 1200°C and equal to and less than 1230°C based on an NIST 710A reference standard, and

- 20 the difference between the log3 forming temperature and the liquidus temperature define as ΔT is at least 50°C and at least two of the following relationships are present.

	SiO ₂ /CaO	2.10 to 2.80
	SiO ₂ /RO	1.90 to 2.55
25	SiO ₂ /Al ₂ O ₃	3.70 to 5.00
	Al ₂ O ₃ /CaO	0.45 to 0.65
	SiO ₂ + Al ₂ O ₃	66.00 to 73.70 wt%
	SiO ₂ – RO	26.50 to 36.60 wt%
	Al ₂ O ₃ /RO	0.40 to 0.60
30	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.00 to 3.00

where RO is equal to MgO + CaO , and

R2O is equal to the wt% of Na₂O + K₂O.

- 35 2. The glass composition according to claim 1 wherein the ingredients are in the following ranges:

	SiO ₂	54 to 59 percent by weight;
	Al ₂ O ₃	11 to 14 percent by weight;

	CaO	22 to 25 percent by weight;
	MgO	1 to 4 percent by weight;
	TiO ₂	up to 1.50 percent by weight;
	Na ₂ O	0.30 to 1.00 percent by weight;
5	K ₂ O	0.30 to 1.00 percent by weight;
	Na ₂ O + K ₂ O	0.80 to 1.50 percent by weight, and
	B ₂ O ₃	1.2 to 1.40 percent by weight

10 3. The glass composition according to claim 2 wherein the relationships are in the following ranges

	SiO ₂ /CaO	2.20 to 2.70
	SiO ₂ /RO	1.90 to 2.40
	SiO ₂ /Al ₂ O ₃	3.70 to 4.90
	Al ₂ O ₃ /CaO	0.50 to 0.60
15	SiO ₂ + Al ₂ O ₃	66.00 to 72.10 wt%
	SiO ₂ – RO	26.50 to 34.00 wt%
	Al ₂ O ₃ /RO	0.46 to 0.56
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO + B ₂ O ₃)	2.00 to 2.70

20 4. The glass composition according to claim 3 wherein the ingredients are in the following ranges:

	SiO ₂	55 to 58 percent by weight;
	Al ₂ O ₃	12 to 14 percent by weight;
	CaO	23 to 25 percent by weight;
25	MgO	2 to 3 percent by weight;
	TiO ₂	up to 1.30 percent by weight;
	Na ₂ O	0.30 to 0.90 percent by weight;
	K ₂ O	0.30 to 0.80 percent by weight;
	Na ₂ O + K ₂ O	0.90 to 1.20 percent by weight;
30	Fe ₂ O ₃	0.20 to 0.40 percent by weight;
	B ₂ O ₃	1.20 to 1.50 percent by weight

5. A glass composition comprising ingredients in the ranges of:

	SiO ₂	55.00 to 58.00 percent by weight;
35	Al ₂ O ₃	12.00 to 14.00 percent by weight;
	CaO	23.80 to 24.80 percent by weight;
	MgO	2.50 to 3.00 percent by weight;

	TiO ₂	up to 0.60 percent by weight;
	Na ₂ O	0.40 to 0.50 percent by weight;
	K ₂ O	0.40 to 0.60 percent by weight;
	Na ₂ O + K ₂ O	0.85 to 1.50 percent by weight;
5	Fe ₂ O ₃	0.20 to 0.40 percent by weight;
	B ₂ O ₃	1.25 to 1.55 percent by weight,

wherein:

the glass composition has a log3 forming temperature in the range of 1210 to 1225°C based on an NIST 710A reference standard, and the difference between the log3 forming temperature and the liquidus temperature define as ΔT is in the range of 52 to 65°C and wherein two or more of the following relationships is present:

	SiO ₂ /CaO	2.20 to 2.40
	SiO ₂ /RO	2.00 to 2.20
15	SiO ₂ /Al ₂ O ₃	3.95 to 4.70
	Al ₂ O ₃ /CaO	0.50 to 0.60
	SiO ₂ + Al ₂ O ₃	69.00to 70.50 wt%
	SiO ₂ – RO	28.00 to 31.00 wt%
	Al ₂ O ₃ /RO	0.45 to 0.55
20	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.25 to 2.45

where RO is equal to MgO +CaO and R2O is equal to wt% of Na₂O + K₂O

6. The glass composition according to claim 5 wherein the ingredients are in the following ranges:

	SiO ₂	55.60 to 57.60 percent by weight;
	Al ₂ O ₃	12.35 to 13.94 percent by weight;
	CaO	24.40 to 24.80 percent by weight;
	MgO	2.55 to 2.80 percent by weight;
30	TiO ₂	0.55 percent by weight;
	Na ₂ O	0.45 percent by weight;
	K ₂ O	0.45 to 0.58 percent by weight;
	Na ₂ O + K ₂ O	0.90 to 1.03 percent by weight;
	Fe ₂ O ₃	0.25 to 0.38 percent by weight;
35	B ₂ O ₃	1.30 to 1.50 percent by weight, and

7. The glass composition according to claim 6, wherein the relationships are in the following ranges:

	SiO_2/CaO	2.25 to 2.29
	SiO_2/RO	2.02 to 2.14
5	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.00 to 4.66
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.56
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.18 to 69.95 wt%
	$\text{SiO}_2 - \text{RO}$	28.04 to 30.65 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.51
10	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.31 to 2.40

8. The glass composition according to claim 5 wherein the ingredients are in the following ranges:

	SiO_2	56.70 to 57.85 percent by weight;
15	Al_2O_3	12.55 to 13.67 percent by weight;
	CaO	23.87 to 24.45 percent by weight;
	MgO	2.55 to 2.62 percent by weight;
	TiO_2	0.05 to 0.34 percent by weight;
	Na_2O	0.44 to 0.455 percent by weight;
20	K_2O	0.45 to 0.51 percent by weight;
	$\text{Na}_2\text{O} + \text{K}_2\text{O}$	0.90 to 1.03 percent by weight;
	Fe_2O_3	0.30 to 0.40 percent by weight;
	B_2O_3	1.30 to 1.50 percent by weight, and

9. The glass composition according to claim 8, wherein the relationships are in the following ranges:

	SiO_2/CaO	2.37 to 2.38
	SiO_2/RO	2.10 to 2.14
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.15 to 4.61
30	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.37 to 70.44 wt%
	$\text{SiO}_2 - \text{RO}$	30.21 to 30.85 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.52
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.41 to 2.43

10. A glass composition comprising ingredients selected from ingredients of one of the following Groups I, II or III:

Group I

	SiO ₂	57 to 60 percent by weight;
5	Al ₂ O ₃	12 to 14 percent by weight;
	CaO	23 to 25 percent by weight;
	MgO	2 to 3 percent by weight;
	TiO ₂	up to 1.25 percent by weight;
	Na ₂ O ₃	0.75 to 1.25 percent by weight, and
10	Fe ₂ O ₃	up to 0.50 percent by weight; or

Group II:

	SiO ₂	57.25 to 59.00 percent by weight;
	Al ₂ O ₃	12.00 to 13.50 percent by weight;
	CaO	23.50 to 24.50 percent by weight;
15	MgO	2.25 to 2.75 percent by weight;
	TiO ₂	0.25 to 1.20 percent by weight;
	Na ₂ O	0.75 to 1.00 percent by weight, and
	Fe ₂ O ₃	0.10 to 0.50 percent by weight, or

Group III:

20	SiO ₂	57.40 to 59.10 percent by weight;
	Al ₂ O ₃	12.15 to 13.45 percent by weight;
	CaO	23.70 to 24.20 percent by weight;
	MgO	2.50 to 2.60 percent by weight;
	TiO ₂	0.50 to 1.15 percent by weight;
25	Na ₂ O	0.85 to 0.95 percent by weight;
	Fe ₂ O ₃	0.30 to 0.40 percent by weight, and

at least two of the following relationships from one of the following Groups A or B is present:

Group A

30	SiO ₂ /CaO	2.10 to 2.80
	SiO ₂ /RO	1.90 to 2.55
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00
	Al ₂ O ₃ /CaO	0.40 to 0.75
	SiO ₂ + Al ₂ O ₃	66.00 to 73.70 wt%
35	SiO ₂ – RO	26.50 to 36.60 wt%
	Al ₂ O ₃ /RO	0.40 to 0.60
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO)	2.00 to 3.00

where RO is equal to CaO + MgO and R2O is equal to wt% of Na₂O or

Group B

5	SiO ₂ /CaO	2.30 to 2.80
	SiO ₂ /RO	1.90 to 2.40
	SiO ₂ /Al ₂ O ₃	4.20 to 5.00
10	Al ₂ O ₃ /CaO	0.50 to 0.60
	SiO ₂ + Al ₂ O ₃	70.80 to 73.70 wt%
	SiO ₂ – RO	30.50 to 36.60 wt%
15	Al ₂ O ₃ /RO	0.46 to 0.56,
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO)	2.30 to 3.00

where RO is equal to CaO + MgO and R2O is equal to the wt% of Na₂O wherein:

the glass composition has a log3 forming temperature no greater than 1240°C based on an NIST 710A reference standard, and

the difference between the log3 forming temperature and the liquidus temperature define as ΔT is equal to and greater than 50°C.

11. The glass composition according to claim 10 wherein the ingredients are present in the following ranges:

25	SiO ₂	57.45 to 59.05 percent by weight;
	Al ₂ O ₃	12.20 to 13.40 percent by weight;
	CaO	23.75 to 24.35 percent by weight;
30	MgO	2.55 percent by weight;
	TiO ₂	1.10 percent by weight;
	Na ₂ O ₃	0.90 percent by weight, and
	Fe ₂ O ₃	0.25 percent by weight and

the relationships are in the following ranges:

35	SiO ₂ /CaO	2.35 to 2.47
	SiO ₂ /RO	2.13 to 2.23
	SiO ₂ /Al ₂ O ₃	4.25 to 4.84
	Al ₂ O ₃ /CaO	0.51 to 0.58
	SiO ₂ + Al ₂ O ₃	70.85 to 71.86 wt%

$\text{SiO}_2 - \text{RO}$	30.55 to 32.55 wt%
$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.52 and
$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.55 to 2.64

wherein the glass composition has a log3 forming temperature in the range of
 5 1232 to 1240°C based on an NIST 710A reference standard, and the ΔT is in the
 range of 58 to 74°C.

12. The glass composition according to claim 10 wherein the
 ingredients are present in the following ranges:

10	SiO_2	57.45 to 59.05 percent by weight;
	Al_2O_3	12.20 to 13.68 percent by weight;
	CaO	23.75 to 24.50 percent by weight;
	MgO	2.55 to 2.58 percent by weight;
	TiO_2	0.55 to 1.10 percent by weight;
15	Na_2O_3	0.90 to 0.91 percent by weight, and
	Fe_2O_3	0.25 to 0.35 percent by weight, and

the relationships have the following ranges:

	SiO_2/CaO	2.36 to 2.47
	SiO_2/RO	2.14 to 2.23
20	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.29 to 4.84
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.56
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.85 to 71.45 wt%
	$\text{SiO}_2 - \text{RO}$	30.55 to 32.55 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.51
25	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.55 to 2.63

wherein the glass composition has a log3 forming temperature in the
 range of 1232 to 1240°C based on an NIST 710A reference standard, and
 the ΔT is in the range of 58 to 74°C.

30 13. The glass composition according to claim 10 wherein the
 ingredients are present in the following ranges:

	SiO_2	57.60 to 58.18 percent by weight;
	Al_2O_3	13.55 to 13.68 percent by weight;
	CaO	23.75 to 24.50 percent by weight;
35	MgO	2.55 to 2.58 percent by weight;
	TiO_2	0.55 percent by weight;

Na_2O_3	0.90 to 0.91 percent by weight, and
Fe_2O_3	0.35 percent by weight, and

the relationships are in the following ranges:

5	SiO_2/CaO	2.35 to 2.45
	SiO_2/RO	2.13 to 2.20
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.25
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.55 to 0.58
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.15 to 71.86 wt%
10	$\text{SiO}_2 - \text{RO}$	30.55 to 31.85 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.50 to 0.52
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.55 to 2.64

wherein the glass composition has a log3 forming temperature in the range of 1238 to 1240°C based on an NIST 710A reference standard, and the ΔT is 55°C.

14. A glass composition comprising ingredients in the following ranges selected from one of the following Groups I, II or III:

Group I:

20	SiO_2	50 to 60 percent by weight;
	Al_2O_3	10.00 to 14 percent by weight;
	CaO	21 to 26 percent by weight;
	MgO	1 to 4.00 percent by weight;
	TiO_2	0.25 to 1.25 percent by weight;
25	Na_2O	0.25 to 1.15 percent by weight;
	K_2O	up to 0.60 percent by weight;
	Fe_2O_3	up to 0.50 percent by weight, and
	B_2O_3	0.90 to 5.10 percent by weight;

Group II:

30	SiO_2	52.25 to 59.00 percent by weight;
	Al_2O_3	11.00 to 14 percent by weight;
	CaO	21.50 to 25.50 percent by weight;
	MgO	1.25 to 3.50 percent by weight;
	TiO_2	0.40 to 1.20 percent by weight;
35	Na_2O	0.35 to 1.00 percent by weight;
	K_2O	up to 0.60 percent by weight;

Fe_2O_3	up to 0.45 percent by weight, and
B_2O_3	0.90 to 5.10 percent by weight; or

Group III:

5	SiO_2	52.90 to 58.00 percent by weight;
	Al_2O_3	12.00 to 14.00 percent by weight;
	CaO	22 to 25 percent by weight;
	MgO	1.45 to 3.25 percent by weight;
	TiO_2	0.45 to 1.15 percent by weight;
10	Na_2O	0.40 to 0.95 percent by weight;
	K_2O	up to 0.60 percent by weight;
	Fe_2O_3	up to 0.40 percent by weight, and
	B_2O_3	0.90 to 5.10 percent by weight;

wherein:

15 the glass composition has a log3 forming temperature of no greater than 1240°C based on an NIST 710A reference standard;

the difference between the log3 forming temperature and the liquidus temperature define as ΔT is at least 50°C. and

20 at least two of the following relationships in the following ranges from one of the following Groups A or B is present:

Group A:

	SiO_2/CaO	2.10 to 2.80
	SiO_2/RO	1.95 to 2.50
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 5.00
25	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.65
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.00 to 73.70 wt%
	$\text{SiO}_2 - \text{RO}$	26.50 to 36.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.00 to 3.00

30 where RO is equal to $\text{CaO} + \text{MgO}$ and R_2O is equal to wt% of $\text{Na}_2\text{O} + \text{K}_2\text{O}$; or

Group B:

	SiO_2/CaO	2.15 to 2.75
	SiO_2/RO	1.90 to 2.40
35	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 4.90
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.65

	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.00 to 72.10 wt%
	$\text{SiO}_2 - \text{RO}$	28.00 to 33.00 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.45 to 0.60
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	1.75 to 2.75
5	where RO equals $\text{CaO} + \text{MgO}$ and R_2O is equal to the wt% of $\text{Na}_2\text{O} + \text{K}_2\text{O}$	

15. The glass composition according to claim 14 wherein the relationships are in the following ranges:

10	RO	24.80 to 27.56 wt%
	SiO_2/CaO	2.20 to 2.55
	SiO_2/RO	1.96 to 2.29
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.79 to 4.76
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.59
15	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.10 to 70.95 wt%
	$\text{SiO}_2 - \text{RO}$	26.50 to 32.55 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.56
	$\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3$	28.15 to 32.79 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.02 to 2.67

20

16. The glass composition according to claim 15 wherein the ingredients are in the following ranges:

	SiO_2	53.00 to 57.75 percent by weight;
	Al_2O_3	12.20 to 14 percent by weight;
25	CaO	22.25 to 24.95 percent by weight;
	MgO	1.50 to 3.00 percent by weight;
	TiO_2	0.50 to 1.10 percent by weight;
	Na_2O	0.45 to 0.90 percent by weight;
	K_2O	0.10 to 0.38 percent by weight;
30	Fe_2O_3	up to 0.30 percent by weight;
	B_2O_3	1.30 to 5.02 percent by weight; and

further including:

	F	up to 0.50 percent by weight;
	SrO	up to 0.13 percent by weight, and
35	Cr_2O_3	up to 0.13 percent by weight

17. The glass composition having ingredients in the following ranges:

	SiO ₂	56.00 to 56.65 percent by weight;
	Al ₂ O ₃	13.05 to 13.60 percent by weight;
5	CaO	23.50 to 24.25 percent by weight;
	MgO	2.50 to 2.55 percent by weight;
	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
	Fe ₂ O ₃	0.25 percent by weight,
10	B ₂ O ₃	2.00 percent by weight; and

at least two of the following relationships:

	SiO ₂ /CaO	2.31 to 2.41
	SiO ₂ /RO	2.09 to 2.17
	SiO ₂ /Al ₂ O ₃	4.12 to 4.28
15	Al ₂ O ₃ /CaO	0.56 to 0.57
	SiO ₂ + Al ₂ O ₃	69.60 to 69.95 wt%
	SiO ₂ – RO	29.25 to 30.60 wt%
	Al ₂ O ₃ /RO	0.50 to 0.52
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.35 to 2.41

20 where RO equals CaO + MgO and R₂O is equal to the wt% of Na₂O and wherein:

the glass composition has a log₃ forming temperature in the range of 1200 to 1220°C and the ΔT is in the range of 56 to 69°C.

25 18. The glass composition according to claim 14 wherein the relationships are in the following ranges:

	SiO ₂ /CaO	2.32 to 2.43
	SiO ₂ /RO	2.10 to 2.20
	SiO ₂ /Al ₂ O ₃	4.26 to 4.73
30	Al ₂ O ₃ /CaO	0.51 to 0.56
	SiO ₂ + Al ₂ O ₃	69.45 to 69.95 wt%
	SiO ₂ – RO	29.45 to 31.45 wt%
	Al ₂ O ₃ /RO	0.46 to 0.50
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.39 to 2.45

35 wherein the glass composition has a log₃ forming temperature in the range of 1200 to 1218°C and a ΔT in the range of 55°C to 70°C.

19. The glass composition according to claim 18 wherein the ingredients are in the following ranges:

	SiO ₂	56.25 to 57.75 percent by weight;
5	Al ₂ O ₃	12.20 to 13.20 percent by weight;
	CaO	23.75 to 24.25 percent by weight;
	MgO	2.55 percent by weight;
	TiO ₂	1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
10	Fe ₂ O ₃	0.25 percent by weight,
	B ₂ O ₃	1.30 to 1.40 percent by weight, and
	Wherein R2O is equal to the wt% of Na ₂ O.	

20. The glass composition according to claim 14 wherein the relationships are in the following ranges:

	SiO ₂ /CaO	2.25 to 2.28
	SiO ₂ /RO	2.01 to 2.07
	SiO ₂ /Al ₂ O ₃	4.01 to 4.19
	Al ₂ O ₃ /CaO	0.53 to 0.56
20	SiO ₂ + Al ₂ O ₃	68.75 to 69.37 wt%
	SiO ₂ – RO	27.78 to 28.92 wt%
	Al ₂ O ₃ /RO	0.48 to 0.51
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.31 to 2.37

wherein the glass composition has a log3 forming temperature in the range of 1210 to 1222°C and the ΔT is in the range of 53 to 79°C.

21. The glass composition according to claim 20 wherein the ingredients are in the following ranges:

	SiO ₂	55.19 to 56.00 percent by weight;
30	Al ₂ O ₃	13.10 to 13.80 percent by weight;
	CaO	24.50 to 24.67 percent by weight;
	MgO	2.55 to 2.95 percent by weight;
	TiO ₂	1.10 percent by weight;
	Na ₂ O	0.45 percent by weight;
35	K ₂ O	0.45 to 0.58 percent by weight;
	Fe ₂ O ₃	0.25 to 0.38 percent by weight, and
	B ₂ O ₃	1.30 percent by weight.

22. The glass composition according to claim 14 wherein the relationships are in the following ranges:

5	SiO_2/CaO	2.25 to 2.36
	SiO_2/RO	2.04 to 2.14
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.01 to 4.66
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.54 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.50 to 69.99 wt%
10	$\text{SiO}_2 - \text{RO}$	28.65 to 30.65 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.51
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3) / (\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.34 to 2.40

wherein the glass composition has a log3 forming temperature in the range of 1211 to 1220°C and the ΔT is in the range of 52 to 66°C.

23. A glass composition comprising ingredients in the following ranges:

20	SiO_2	56.15 to 57.60 percent by weight;
	Al_2O_3	13.25 to 13.95 percent by weight;
	CaO	24.40 to 24.95 percent by weight;
	MgO	2.55 percent by weight;
	TiO_2	0.55 percent by weight;
	Na_2O	0.90 percent by weight;
	Fe_2O_3	0.25 to 0.35 percent by weight, and
25	B_2O_3	1.30 percent by weight, and

wherein at least two of the following relationships are present:

30	SiO_2/CaO	2.25 to 2.36
	SiO_2/RO	2.04 to 2.14
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.01 to 4.66
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.54 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.50 to 69.99 wt%
	$\text{SiO}_2 - \text{RO}$	28.65 to 30.65 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.51
35	$(\text{SiO}_2 + \text{Al}_2\text{O}_3) / (\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.34 to 2.40

where RO equals $\text{CaO} + \text{MgO}$ and R_2O is equal to wt% of Na_2O wherein the glass composition has a log3 forming temperature in the range of 1211 to 1220°C and the ΔT is in the range of 52 to 66°C.

24. The glass composition according to claim 14 wherein at least two of the following relationships are present

	SiO_2/CaO	2.28 to 2.44
5	SiO_2/RO	2.07 to 2.20
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.15 to 4.30
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.55 to 0.56
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	68.20 to 69.20 wt%
	$\text{SiO}_2 - \text{RO}$	28.45 to 30.60 wt%
10	$\text{Al}_2\text{O}_3/\text{RO}$	0.50 to 0.51
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.24 to 2.35

wherein the glass composition has a log3 forming temperature in the range of 1193 to 1212°C and the ΔT is in the range of 64 to 90°C.

25. A glass composition comprising the following ingredients in the following ranges:

	SiO_2	55.25 to 56.15 percent by weight;
	Al_2O_3	13.05 to 13.30 percent by weight;
	CaO	23.00 to 24.20 percent by weight;
20	MgO	2.55 percent by weight;
	TiO_2	0.25 to 1.25 percent by weight;
	Na_2O	0.90 percent by weight;
	Fe_2O_3	0.25 percent by weight.
	B_2O_3	3.00 percent by weight; and

at least two of the following relationships

	SiO_2/CaO	2.28 to 2.44
	SiO_2/RO	2.07 to 2.20
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.15 to 4.30
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.55 to 0.56
30	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	68.20 to 69.20 wt%
	$\text{SiO}_2 - \text{RO}$	28.45 to 30.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.50 to 0.51
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.24 to 2.35

where RO equals $\text{CaO} + \text{MgO}$ and R_2O is equal to wt% of Na_2O

wherein the glass composition has a log3 forming temperature in the range of 1193 to 1212°C and the ΔT is in the range of 64 to 90°C.

26. The glass composition according to claim 14 wherein the relationships are in the following ranges:

5	SiO_2/CaO	2.20 to 2.28
	SiO_2/RO	1.96 to 2.07
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.06 to 4.15
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.54 to 0.55
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	67.55 to 68.55 wt%
	$\text{SiO}_2 - \text{RO}$	26.57 to 28.30 wt%
10	$\text{Al}_2\text{O}_3/\text{RO}$	0.49 to 0.50
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.14 to 2.22

wherein the glass composition has a log3 forming temperature in the range of 1190 to 1204°C and the ΔT is in the range of 55 to 83°C.

27. The glass composition according to claim 26 wherein the ingredients are in the following ranges:

	SiO_2	54.12 to 55.25 percent by weight;
	Al_2O_3	13.20 to 13.40 percent by weight;
	CaO	24.20 to 24.55 percent by weight;
20	MgO	2.55 percent by weight;
	TiO_2	0.55 percent by weight;
	Na_2O	0.45 to 0.50 percent by weight;
	K_2O	0.45 to 0.55 percent by weight;
	Fe_2O_3	0.25 to 0.28 percent by weight.
25	B_2O_3	3.00 percent by weight;
	and further including:	
	F	up to 0.20 percent by weight
	SrO	up to 0.12 percent by weight.

28. The glass composition according to claim 14 wherein the relationships are in the following ranges:

	SiO_2/CaO	2.21 to 2.23
	SiO_2/RO	2.00 to 2.10
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.82 to 4.05
35	$\text{Al}_2\text{O}_3/\text{CaO}$	0.55 to 0.58
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.10 to 67.50 wt%
	$\text{SiO}_2 - \text{RO}$	26.50 to 28.00 wt%

$\text{Al}_2\text{O}_3/\text{RO}$ 0.49 to 0.55

$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$ 2.02 to 2.13

wherein the glass composition has a log3 forming temperature in the range of 1167 to 1177 and the ΔT is in the range of 57 to 69°C.

5

29. The glass composition according to claim 28 wherein the ingredients are in the following ranges:

	SiO_2	53.00 to 53.50 percent by weight;
10	Al_2O_3	13.10 to 14.00 percent by weight;
	CaO	24.00 percent by weight;
	MgO	1.25 to 2.50 percent by weight;
	TiO_2	0.50 percent by weight;
	Na_2O	0.90 percent by weight;
15	K_2O	0.37 percent by weight;
	Fe_2O_3	0.10 percent by weight;
	B_2O_3	4.93 to 5.02 percent by weight; and
	Further including	
	F	0.50 percent by weight;
20	SrO	0.13 percent by weight, and
	Cr_2O_3	0.13 percent by weight.

30. The glass composition of claim 14 wherein the relationships are in the following ranges:

	SiO_2/CaO	2.23 to 2.55
25	SiO_2/RO	2.05 to 2.27
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.04 to 4.69
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.00 to 70.95 wt%
	$\text{SiO}_2 - \text{RO}$	28.05 to 32.55 wt%
30	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.28 to 2.67

where R_2O is equal to the wt% of Na_2O , and

the glass composition has a log3 forming temperature in the range of 1202 to 1240°C and the ΔT is in the range of 53 to 100°C.

35

31. The glass composition of claim 30 wherein:

	SiO ₂	55.40 to 57.75 percent by weight;
	Al ₂ O ₃	12.20 to 13.80 percent by weight;
	CaO	22.25 to 24.85 percent by weight;
	MgO	2.05 to 2.60 percent by weight;
5	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
	Fe ₂ O ₃	0.25 percent by weight, and
	B ₂ O ₃	1.00 to 3.00 percent by weight.

10 32. The glass composition of claim 30 wherein the glass composition has a log3 forming temperature in the range of equal to and greater than 1202°C and equal to and less than 1219°C based on an NIST 710A reference standard, and

the relationships are in the following ranges:

15	SiO ₂ /CaO	2.23 to 2.44
	SiO ₂ /RO	2.03 to 2.20
	SiO ₂ /Al ₂ O ₃	4.06 to 4.34
	Al ₂ O ₃ /CaO	0.54 to 0.57
	SiO ₂ + Al ₂ O ₃	68.95 to 69.95 wt%
20	SiO ₂ – RO	28.05 to 30.60 wt%
	Al ₂ O ₃ /RO	0.49 to 0.53
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O +RO+B ₂ O ₃)	2.28 to 2.41

25 33. The glass composition of claim 32 wherein the ingredients are in the following ranges:

	SiO ₂	55.40 to 56.65 percent by weight;
	Al ₂ O ₃	13.05 to 13.80 percent by weight;
	CaO	23.00 to 24.85 percent by weight;
	MgO	2.50 to 2.55 percent by weight;
30	TiO ₂	0.50 to 1.10 percent by weight;
	Na ₂ O	0.90 percent by weight;
	Fe ₂ O ₃	0.25 percent by weight, and
	B ₂ O ₃	2.00 to 3.00 percent by weight.

35 34. The glass composition according to claim 14 wherein the glass composition has a log3 forming temperature in the range of equal to

and greater than 1215°C and equal to and less than 1218°C based on an NIST 710A reference standard, and

the ΔT is in the range of equal to and greater than 63°C and equal to and less than 65°C at least 50°C, and

5 the relationships are in the following ranges:

	SiO_2/CaO	2.30 to 2.43
	SiO_2/RO	2.08 to 2.20
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.19 to 4.73
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.54
10	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.48 to 69.95 wt%
	$\text{SiO}_2 - \text{RO}$	29.13 to 31.45 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.50
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.38 to 2.44
	where R_2O is equal to the wt% of Na_2O .	

15

35. The glass composition according to claim 34 wherein the ingredients are in the following ranges:

	SiO_2	56.10 to 57.75 percent by weight;
	Al_2O_3	12.20 to 13.38 percent by weight;
20	CaO	23.75 to 24.42 percent by weight;
	MgO	2.55 percent by weight;
	TiO_2	0.55 to 1.10 percent by weight;
	Na_2O	0.90 percent by weight;
	Fe_2O_3	0.25 percent by weight.
25	B_2O_3	1.30 to 1.40 percent by weight;

36. A glass composition comprising ingredients in the following ranges selected from one of the following Groups I, II or III:

Group I:

30	SiO_2	55.00 to 62.00 percent by weight;
	Al_2O_3	10.00 to 14.00 percent by weight;
	CaO	20.00 to 26.00 percent by weight;
	MgO	1.00 to 4.00 percent by weight;
	TiO_2	0.25 to 1.75 percent by weight;
35	Na_2O	up to 0.75 percent by weight;
	Li_2O	0.10 to 1.25 percent by weight;

	Fe ₂ O ₃	up to 0.50 percent by weight, or
	Group II:	
	SiO ₂	56.00 to 61.00 percent by weight;
	Al ₂ O ₃	11.00 to 14.00 percent by weight;
5	CaO	21.50 to 25.00 percent by weight;
	MgO	1.35 to 3.50 percent by weight;
	TiO ₂	0.40 to 1.60 percent by weight;
	Na ₂ O	up to 0.70 percent by weight;
	Li ₂ O	0.20 to 1.10 percent by weight;
10	Fe ₂ O ₃	up to 0.45 percent by weight, or

	Group III:	
	SiO ₂	57.5 to 61.00 percent by weight;
	Al ₂ O ₃	11.75 to 13.75 percent by weight;
15	CaO	21.75 to 24.50 percent by weight;
	MgO	1.60 to 3.25 percent by weight;
	TiO ₂	0.45 to 1.55 percent by weight;
	Na ₂ O	up to 0.65 percent by weight;
	Li ₂ O	0.30 to 1.00 percent by weight;
20	Fe ₂ O ₃	up to 0.30 percent by weight, and

wherein:

the glass composition has a log3 forming temperature of no greater than 1240°C based on an NIST 710A reference standard;

the difference between the log3 forming temperature and the liquidus temperature define as ΔT is at least 50°C. and

at least two of the following relationships from one of the following Groups A or B is present:

Group A:

	SiO ₂ /CaO	2.00 to 2.80
30	SiO ₂ /RO	1.90 to 2.55
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00
	Al ₂ O ₃ /CaO	0.45 to 0.65
	SiO ₂ + Al ₂ O ₃	66.00 to 73.7 wt%
	SiO ₂ – RO	26.50 to 36.60 wt%
35	Al ₂ O ₃ /RO	0.40 to 0.60
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO)	2.00 to 3.00

where RO equals CaO + MgO and R2O is equal to wt% of Na₂O + Li₂O; or

Group B:

5	SiO ₂ /CaO	2.30 to 2.80
	SiO ₂ /RO	2.10 to 2.55
	SiO ₂ /Al ₂ O ₃	4.20 to 5.00
	Al ₂ O ₃ /CaO	0.45 to 0.60
	SiO ₂ + Al ₂ O ₃	70.80 to 73.70 wt%
	SiO ₂ – RO	30.50 to 36.60 wt%
10	Al ₂ O ₃ /RO	0.45 to 0.58
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO)	2.30 to 3.00

where RO is equal to the wt% of CaO + MgO, and R2O is equal to the wt% of Na₂O + Li₂O.

37. The glass composition according to claim 36 wherein the glass composition has a log3 forming temperature in the range of equal to and greater than 1205°C and equal to and less than 1240°C based on an NIST 710A reference standard, and

the ΔT is in the range of equal to and greater than 50°C and equal to and less than 100°C, and

	the relationships are in the following ranges;	
	SiO ₂ /CaO	2.39 to 2.72
	SiO ₂ /RO	2.16 to 2.52
	SiO ₂ /Al ₂ O ₃	4.30 to 4.92
25	Al ₂ O ₃ /CaO	0.51 to 0.59
	SiO ₂ + Al ₂ O ₃	71.05 to 73.67 wt%
	SiO ₂ – RO	31.35 to 36.56 wt%
	Al ₂ O ₃ /RO	0.47 to 0.55
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO)	2.30to 2.96

30

38. The Glass composition according to claim 37 wherein the ingredients are in the following ranges:

	SiO ₂	57.65 to 60.75 percent by weight;
	Al ₂ O ₃	12.00 to 13.64 percent by weight;
35	CaO	22 to 24.155 percent by weight;
	MgO	1.70 to 3.40 percent by weight;

TiO ₂	0.50 to 1.50 percent by weight;
Na ₂ O	0.30 to 0.60 percent by weight;
Li ₂ O	0.30 to 1.00 percent by weight, and
Fe ₂ O ₃	up to 0.25 percent by weight.

5

39. The glass composition according to claim 37 wherein the glass composition has a log₃ forming temperature in the range of equal to and greater than 1211°C and equal to and less than 1218°C based on an NIST 710A reference standard, and

10

the ΔT is in the range of equal to and greater than 56°C and equal to and less than 68°C, and

the relationships are in the following ranges;

15

SiO ₂ /CaO	2.47 to 2.72
SiO ₂ /RO	2.23 to 2.40
SiO ₂ /Al ₂ O ₃	4.31 to 4.92
Al ₂ O ₃ /CaO	0.55 to 0.59
SiO ₂ + Al ₂ O ₃	71.55 to 73.03 wt%
SiO ₂ – RO	32.15 to 34.91 wt%
Al ₂ O ₃ /RO	0.48 to 0.52
(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO)	2.64 to 2.79

20

40. The glass composition according to claim 39 wherein the ingredients are in the following ranges:

25

SiO ₂	58.25 to 59.97 percent by weight;
Al ₂ O ₃	12.19 to 13.64 percent by weight;
CaO	22.04 to 23.65 percent by weight;
MgO	2.50 to 3.12 percent by weight;
TiO ₂	0.50 to 1.50 percent by weight;
Na ₂ O	up to 0.30 percent by weight;
Li ₂ O	0.90 to 0.91 percent by weight;
Fe ₂ O ₃	0.20 to 0.25 percent by weight.

30

41. The glass composition according to claim 36 wherein:

the glass composition has a log₃ forming temperature in the range of equal to and greater than 1205°C and equal to and less than 1240°C based on an NIST 710A reference standard;

35

the ΔT is in the range of equal to and greater than 50°C and equal to and less than 101°C , and

the relationships are in the following ranges:

	SiO_2/CaO	2.39 to 2.72
5	SiO_2/RO	2.16 to 2.51
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.30 to 4.92
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.05 to 73.67 wt%
	$\text{SiO}_2 - \text{RO}$	31.35 to 36.56 wt%
10	$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.55
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.30 to 2.96

42. The glass composition according to claim 41 wherein the ingredients are in the following ranges:

15	SiO_2	57.65 to 60.75 percent by weight;
	Al_2O_3	12.00 to 13.40 percent by weight;
	CaO	22.00 to 24.15 percent by weight;
	MgO	1.70 to 3.12 percent by weight;
	TiO_2	0.50 to 1.50 percent by weight;
20	Na_2O	0.45 to 0.90 percent by weight;
	Li_2O	0.45 to 1.00 percent by weight;
	Fe_2O_3	up to 0.25 percent by weight.

43. The glass composition according to claim 41 wherein,
the glass composition has a log₃ forming temperature in the range of equal to and greater than 1205°C and equal to and less than 1220°C based on an NIST 710A reference standard;

the ΔT is in the range of equal to and greater than 50°C and equal to and less than 59°C , and

30	the relationships are in the following ranges:	
	SiO_2/CaO	2.39 to 2.72
	SiO_2/RO	2.16 to 2.42
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.30 to 4.92
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.52 to 0.59
35	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.05 to 73.03 wt%
	$\text{SiO}_2 - \text{RO}$	31.35 to 35.37 wt%

$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.52
$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.30 to 2.81

5 44. The glass composition according to claim 43 wherein the ingredients are in the following ranges:

SiO_2	57.65 to 60.33 percent by weight;
Al_2O_3	12.22 to 13.40 percent by weight;
CaO	22.00 to 24.15 percent by weight;
MgO	2.30 to 3.12 percent by weight;
10 TiO_2	0.50 to 1.50 percent by weight;
Na_2O	up to 0.45 percent by weight
Li_2O	0.45 to 1.00 percent by weight, and
Fe_2O_3	up to 0.25 percent by weight.

15

45. The glass composition according to claim 41 wherein:

the glass composition has a log3 forming temperature in the range of equal to and greater than 1205°C and equal to and less than 1218°C based on an NIST 710A reference standard;

20 the ΔT is in the range of equal to and greater than 50°C and equal to and less than 60°C, and

the relationships are in the following ranges:

SiO_2/CaO	2.39 to 2.72
SiO_2/RO	2.16 to 2.42
25 $\text{SiO}_2/\text{Al}_2\text{O}_3$	4.30 to 4.92
$\text{Al}_2\text{O}_3/\text{CaO}$	0.52 to 0.59
$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.05 to 72.80 wt%
$\text{SiO}_2 - \text{RO}$	31.35 to 35.37 wt%
$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.52
30 $(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.30 to 2.81

46. The glass composition according to claim 45 wherein the ingredients are in the following ranges:

SiO_2	57.65 to 60.33 percent by weight;
35 Al_2O_3	12.22 to 13.40 percent by weight;
CaO	22.00 to 24.15 percent by weight;
MgO	2.30 to 3.40 percent by weight;

TiO ₂	0.50 to 1.50 percent by weight;
Na ₂ O	up to 0.45 weight percent;
Li ₂ O	0.45 to 1.00 percent by weight, and
Fe ₂ O ₃	up to 0.25 percent by weight.

5

47. The glass composition according to claim 45 wherein:

the glass composition has a log3 forming temperature in the range of equal to and greater than 1234°C and equal to and less than 1240°C based on an NIST 710A reference standard;

10

the ΔT is in the range of equal to and greater than 61°C and equal to and less than 100°C, and

the relationships are in the following ranges:

SiO ₂ /CaO	2.50 to 2.71
SiO ₂ /RO	2.29 to 2.52
SiO ₂ /Al ₂ O ₃	4.62 to 4.88
Al ₂ O ₃ /CaO	0.52 to 0.59
SiO ₂ + Al ₂ O ₃	71.80 to 73.67 wt%
SiO ₂ – RO	33.60 to 36.56 wt%
Al ₂ O ₃ /RO	0.47 to 0.55
(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO)	2.67 to 2.96

20

48. The glass composition according to claim 47 wherein the ingredients are in the following ranges:

SiO ₂	59.55 to 60.57 percent by weight;
Al ₂ O ₃	12.25 to 13.10 percent by weight;
CaO	22.31 to 23.85 percent by weight;
MgO	1.70 to 3.10 percent by weight;
Na ₂ O	up to 0.30 percent by weight
TiO ₂	1.10 percent by weight, and
Li ₂ O	up to 0.60 percent by weight.

25

30

49. A glass composition comprising ingredients in the following ranges selected from one of the following Groups I, II or III:

Group I:

SiO ₂	55 to 62 percent by weight;
Al ₂ O ₃	10.00 to 14.00 percent by weight;
CaO	21 to 26 percent by weight;

35

	MgO	1 to 3.25 percent by weight;
	TiO ₂	0.25 to 1.75 percent by weight;
	Li ₂ O	0.25 to 1.25 percent by weight;
	ZnO	0.25 to 1.25 percent by weight
5	Fe ₂ O ₃	up to 0.50 percent by weight, or
	Group II:	
	SiO ₂	56 to 61.00 percent by weight;
	Al ₂ O ₃	11.00 to 14.00 percent by weight;
	CaO	21.50 to 25.00 percent by weight;
10	MgO	1.50 to 3.00 percent by weight;
	TiO ₂	0.40 to 1.50 percent by weight;
	Li ₂ O	0.30 to 1.10 percent by weight;
	ZnO	0.30 to 1.15 percent by weight;
	Fe ₂ O ₃	up to 0.35 percent by weight, or
15	Group III:	
	SiO ₂	57 to 60.00 percent by weight;
	Al ₂ O ₃	12 to 13.75 percent by weight;
	CaO	21.75 to 24.50 percent by weight;
	MgO	1.75 to 2.75 percent by weight;
20	TiO ₂	0.45 to 1.25 percent by weight;
	Li ₂ O	0.40 to 1.00 percent by weight;
	ZnO	0.40 to 1.10 percent by weight;
	Fe ₂ O ₃	up to 0.30 percent by weight, and
	wherein:	
25	the glass composition has a log3 forming temperature of no greater than 1240°C based on an NIST 710A reference standard;	
	the difference between the log3 forming temperature and the liquidus temperature define as ΔT is at least 50°C. and	
	at least two of the following relationships in the following ranges from	
30	one of the following Groups A or B is present:	
	Group A:	
	SiO ₂ /CaO	2.10 to 2.80
	SiO ₂ /RO	1.90 to 2.55
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00
35	Al ₂ O ₃ /CaO	0.45 to 0.65
	SiO ₂ + Al ₂ O ₃	68.00 to 73.70 wt%

	$\text{SiO}_2 - \text{RO}$	26.50 to 36.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.00 to 3.00
	where RO is equal to the wt% of CaO + MgO and R ₂ O is equal to the	
5	wt% of Li ₂ O; or	
	Group B:	
	SiO_2/CaO	2.30 to 2.60
	SiO_2/RO	2.10 to 2.55
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.20 to 5.00
10	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.80 to 72.00 wt%
	$\text{SiO}_2 - \text{RO}$	30.50 to 36.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.30 to 3.00
15	where RO is equal to the wt% of CaO + MgO, and R ₂ O is equal to the	
	wt% of Li ₂ O	

50. The glass composition according to claim 49 wherein the glass composition has a log₃ forming temperature in the range of equal to and greater than 1195°C and equal to and less than 1229°C, and

the ΔT is in the range of equal to and greater than 54°C and equal to and less than 71°C, and

the relationships are present in the following ranges:

	SiO_2/CaO	2.41 to 2.54
25	SiO_2/RO	2.18 to 2.29
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.26 to 4.90
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	71.03 to 71.73 wt%
	$\text{SiO}_2 - \text{RO}$	31.15 to 33.61 wt%
30	$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.60 to 2.71

51. The glass composition according to claim 50 wherein the ingredients are in the following ranges:

35	SiO_2	57.35 to 59.618.30 percent by weight;
	Al_2O_3	12.16 to 13.63 percent by weight;

	CaO	22.85 to 24.22 percent by weight;
	MgO	1.90 to 2.55 percent by weight;
	TiO ₂	0.50 to 1.10 percent by weight;
	Li ₂ O	0.45 to 0.90 percent by weight;
5	ZnO	0.45 to 1.00 percent by weight;
	Fe ₂ O ₃	up to 0.25 percent by weight.

52. The glass composition according to claim 49 wherein the glass composition has a log3 forming temperature in the range of equal to and greater than 1204°C and equal to and less than 1213°C, and
 10 the ΔT is in the range of equal to and greater than 56°C and equal to and less than 71°C, and

the relationships are present in the following ranges:

	SiO ₂ /CaO	2.43 to 2.54
15	SiO ₂ /RO	2.20 to 2.29
	SiO ₂ /Al ₂ O ₃	4.36 to 4.47
	Al ₂ O ₃ /CaO	0.55 to 0.58
	SiO ₂ + Al ₂ O ₃	71.13 to 71.58 wt%
	SiO ₂ – RO	31.66 to 32.75 wt%
20	Al ₂ O ₃ /RO	0.49 to 0.52
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO)	2.61 to 2.71

53. The glass composition according to claim 48 wherein the ingredients are present in the following ranges:

25	SiO ₂	58.00 to 58.30 percent by weight;
	Al ₂ O ₃	13.03 to 13.33 percent by weight;
	CaO	22.85 to 23.84 percent by weight;
	MgO	2.50 to 2.55 percent by weight;
	TiO ₂	0.50 to 1.10 percent by weight;
30	Li ₂ O	0.90 percent by weight;
	ZnO	1.00 percent by weight;
	Fe ₂ O ₃	up to 0.25 percent by weight.

54. (Table 15) The glass composition according to claim 49
 35 wherein the glass composition has a log3 forming temperature in the range of equal to and greater than 1195°C and equal to and less than 1229°C based on an NIST 710A reference standard, and

the ΔT is in the range of equal to and greater than 54°C and equal to and less than 59°C, and

the relationships are present in the following ranges:

	SiO_2/CaO	2.41 to 2.54
5	SiO_2/RO	2.18 to 2.29
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.26 to 4.90
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.55 to 71.77 wt%
	$\text{SiO}_2 - \text{RO}$	31.15 to 33.61 wt%
10	$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.53,
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.60 to 2.71

55. The glass composition according to claim 54 wherein the ingredients are present in the following ranges:

15	SiO_2	57.35 to 59.61 percent by weight;
	Al_2O_3	12.16 to 13.63 percent by weight;
	CaO	23.14 to 24.22 percent by weight;
	MgO	1.90 to 2.55 percent by weight;
	TiO_2	0.50 to 1.10 percent by weight;
20	Li_2O	0.45 to 0.90 percent by weight;
	ZnO	0.45 to 1.00 percent by weight;
	Fe_2O_3	up to 0.25 percent by weight.

56. A glass composition comprising ingredients in the following ranges selected from one of the following Groups I, II or III:

Group I:

	SiO_2	55.00 to 62.00 percent by weight;
	Al_2O_3	10.00 to 14.00 percent by weight;
	CaO	21.00 to 25.00 percent by weight;
30	MgO	1.00 to 4.00 percent by weight;
	TiO_2	0.50 to 2.00 percent by weight;
	Na_2O	up to 2.00 percent by weight;
	ZnO	0.50 to 3.00 percent by weight
	Fe_2O_3	up to 0.50 percent by weight, or

35 Group II:

	SiO_2	56.00 to 61.00 percent by weight;
--	----------------	-----------------------------------

	Al ₂ O ₃	11.00 to 13.50 percent by weight;
	CaO	21.25 to 24.00 percent by weight;
	MgO	1.25 to 3.50 percent by weight;
	TiO ₂	0.50 to 1.50 percent by weight;
5	Na ₂ O	up to 1.50 percent by weight
	ZnO	0.50 to 2.75 percent by weight;
	Fe ₂ O ₃	up to 0.35 percent by weight, or
	Group III:	
	SiO ₂	58.00 to 60.00 percent by weight;
10	Al ₂ O ₃	11.75 to 13.25 percent by weight;
	CaO	21.25 to 23.00 percent by weight;
	MgO	1.50 to 3.50 percent by weight;
	TiO ₂	0.75 to 1.25 percent by weight;
	Na ₂ O	up to 1.25 percent by weight
15	ZnO	0.75 to 2.50 percent by weight;
	Fe ₂ O ₃	up to 0.30 percent by weight, and

wherein:

the glass composition has a log3 forming temperature of no greater than 1240°C based on an NIST 710A reference standard;

20 the difference between the log3 forming temperature and the liquidus temperature define as ΔT is at least 50°C. and

at least two of the following relationships in the following ranges from one of the following Groups A or B is present:

Group A:

25	SiO ₂ /CaO	2.10 to 2.80
	SiO ₂ /RO	1.90 to 2.55
	SiO ₂ /Al ₂ O ₃	3.70 to 5.00
	Al ₂ O ₃ /CaO	0.45 to 0.65
	SiO ₂ + Al ₂ O ₃	66.00 to 73.70 wt%
30	SiO ₂ – RO	26.50 to 36.60 wt%
	Al ₂ O ₃ /RO	0.40 to 0.60
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO)	2.00 to 3.00

where RO is equal to the wt% of CaO + MgO and R2O is equal to the wt% of Na₂O; or

35 Group B:

SiO ₂ /CaO	2.30 to 2.80
-----------------------	--------------

	SiO_2/RO	2.10 to 2.55
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.25 to 5.00
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.80 to 73.70 wt%
5	$\text{SiO}_2 - \text{RO}$	30.50 to 36.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.30 to 3.00

where RO is equal to the wt% of CaO + MgO, and R₂O is equal to the wt% of Na₂O.

10

57. The glass composition according to claim 56 wherein the glass composition has a log₃ forming temperature in the range of equal to and greater than 1231°C and equal to and less than 1234°C based on an NIST 710A reference standard, and

15

the ΔT is in the range of equal to and greater than 50°C and equal to and less than 59°C, and

the relationships are present in the following ranges:

	SiO_2/CaO	2.62
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.92 to 4.93
20	$\text{Al}_2\text{O}_3/\text{CaO}$	0.53
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.16 to 71.00 wt%
	$\text{SiO}_2 - \text{RO}$	32.90 to 33.10 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO})$	2.64 to 2.65

25

58. The glass composition according to claim 57 wherein the ingredients are in the following ranges:

	SiO_2	58.70 to 59.00 percent by weight;
	Al_2O_3	11.90 to 12.00 percent by weight;
30	CaO	22.40 to 22.50 percent by weight;
	MgO	3.40 percent by weight;
	TiO ₂	1.00 percent by weight;
	Na ₂ O	0.90 percent by weight;
	ZnO	1.00 to 1.50 percent by weight, and
35	Fe ₂ O ₃	up to 0.20 percent by weight.

59. A glass composition comprising ingredients in the following ranges selected from one of the following Groups I, II or III:

Group I:

5	SiO ₂	50.00 to 62.00 percent by weight;
	Al ₂ O ₃	10.00 to 14.00 percent by weight;
	CaO	21.00 to 26.50 percent by weight;
	MgO	1.00 to 4.00 percent by weight;
	TiO ₂	0.25 to 2.00 percent by weight;
10	Na ₂ O	up to 1.00 percent by weight;
	K ₂ O	up to 0.50 percent by weight;
	Li ₂ O	0.10 to 1.25 percent by weight;
	Fe ₂ O ₃	0.10 to 0.50 percent by weight, and
	B ₂ O ₃	0.50 to 5.00 percent by weight; or

Group II:

15	SiO ₂	52.00 to 61.00 percent by weight;
	Al ₂ O ₃	11.00 to 14.00 percent by weight;
	CaO	22.00 to 25.00 percent by weight;
	MgO	1.50 to 3.00 percent by weight;
	TiO ₂	0.35 to 1.50 percent by weight;
20	Na ₂ O	up to 0.90 percent by weight;
	K ₂ O	up to 0.35 percent by weight;
	Li ₂ O	0.20 to 1.10 percent by weight;
	Fe ₂ O ₃	0.15 to 0.50 percent by weight, and
	B ₂ O ₃	0.50 to 4.00 percent by weight; or

25 Group III

30	SiO ₂	53.50 to 60.25 percent by weight;
	Al ₂ O ₃	11.90 to 13.75 percent by weight;
	CaO	22.50 to 24.25 percent by weight;
	MgO	2.25 to 2.75 percent by weight;
	TiO ₂	0.40 to 1.25 percent by weight;
35	Na ₂ O	up to 0.75 percent by weight;
	K ₂ O	up to 0.20 percent by weight;
	Li ₂ O	0.25 to 1.00 percent by weight
	ZnO	0.75 to 2.50 percent by weight;
	Fe ₂ O ₃	0.20 to 0.40 percent by weight;
	B ₂ O ₃	0.75 to 3.25 percent by weight; and

wherein:

the glass composition has a log3 forming temperature of no greater than 1240°C based on an NIST 710A reference standard;

the difference between the log3 forming temperature and the liquidus temperature define as ΔT is at least 50°C. and

5 at least two of the following relationships in the following ranges from one of the following Groups A or B is present:

Group A

	SiO_2/CaO	2.10 to 2.80;
	SiO_2/RO	1.90 to 2.55;
10	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.50 to 5.00;
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.60;
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.00 to 73.70 wt%;
	$\text{SiO}_2 - \text{RO}$	26.50 to 36.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60
15	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.00 to 3.00

where RO is equal to the wt% of CaO + MgO, and R2O is equal to the wt% of Na₂O + K₂O + Li₂O; or

Group B

	SiO_2/CaO	2.20 to 2.70
20	SiO_2/RO	1.90 to 2.40
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.00 to 5.00
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	67 to 72.1wt%
	$\text{SiO}_2 - \text{RO}$	27.00 to 36.60 wt%,
25	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.56,
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.30 to 3.00

where RO is equal to the wt% of CaO + MgO, and R2O is equal to the wt% of Na₂O + K₂O + Li₂O.

30 60. The glass composition according to claim 59 wherein the glass composition has a log3 forming temperature in the range of equal to and greater than 1187°C and equal to and less than 1239°C, the ΔT is in the range of equal to and greater than 50°C and equal to and less than 142°C, and the are present in the following ranges:

35	SiO_2/CaO	2.22 to 2.66
	SiO_2/RO	2.01 to 2.39

	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.09 to 4.90
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	67.95 to 72.05 wt%
	$\text{SiO}_2 - \text{RO}$	27.50 to 33.91 wt%
5	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.18 to 2.68

61. The glass composition according to claim 60 wherein the ingredients are in the following ranges:

10

	SiO_2	54.60 to 59.53 percent by weight;
	Al_2O_3	12.16 to 13.63 percent by weight;
	CaO	22.87 to 24.05 percent by weight;
	MgO	2.00 to 2.55 percent by weight;
15	TiO_2	0.49 to 1.10 percent by weight;
	Na_2O	up to 0.60 percent by weight;
	K_2O	up to 0.10 percent by weight;
	Li_2O	0.30 to 0.91 percent by weight;
	Fe_2O_3	0.23 to 0.30 percent by weight, and
20	B_2O_3	0.90 to 3.00 percent by weight.

62. The glass composition according to claim 59 wherein the glass composition has a log3 forming temperature in the range of equal to and greater than 1192°C and equal to and less than 1198°C,
the ΔT is in the range of equal to and greater than 55°C and equal to and less than 63°C, and the relationships are present in the following ranges:

25

	SiO_2/CaO	2.42 to 2.48
	SiO_2/RO	2.19 to 2.24
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.30 to 4.47
30	$\text{Al}_2\text{O}_3/\text{CaO}$	0.54 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.83 to 71.47 wt%
	$\text{SiO}_2 - \text{RO}$	31.26 to 32.39 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.49 to 0.52
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.49 to 2.57

35

63. The glass composition according to claim 62 wherein the ingredients are present in the following ranges:

	SiO ₂	57.60 to 58.50 percent by weight;
	Al ₂ O ₃	12.76 to 13.43 percent by weight;
	CaO	23.40 to 23.84 percent by weight;
	MgO	2.50 percent by weight;
5	TiO ₂	0.50 percent by weight;
	Na ₂ O	up to 0.60 percent by weight;
	Li ₂ O	0.90 percent by weight;
	Fe ₂ O ₃	0.23 percent by weight,
	B ₂ O ₃	1.00 to 1.20 percent by weight. and
10	wherein R ₂ O is equal to the wt% of Na ₂ O + Li ₂ O	

64. The glass composition according to claim 59 wherein the glass composition has a log₃ forming temperature in the range of equal to and greater than 1187°C and equal to and less than 1239°C,
 15 the ΔT is in the range of equal to and greater than 50°C and equal to and less than 142°C, and the relationships are present in the following ranges:

	SiO ₂ /CaO	2.22 to 2.66
	SiO ₂ /RO	2.01 to 2.39
20	SiO ₂ /Al ₂ O ₃	4.09 to 4.90
	Al ₂ O ₃ /CaO	0.51 to 0.59
	SiO ₂ + Al ₂ O ₃	67.95 to 72.05 wt%
	SiO ₂ – RO	27.50 to 33.84 wt%
	Al ₂ O ₃ /RO	0.46 to 0.53
25	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O +RO+B ₂ O ₃)	2.18 to 2.68

65. The glass composition according to claim 64 wherein the ingredients are present in the following ranges:

	SiO ₂	54.60 to 59.53 percent by weight;
30	Al ₂ O ₃	12.16 to 13.63 percent by weight;
	CaO	22.93 to 24.05 percent by weight;
	MgO	2.00 to 2.55 percent by weight;
	TiO ₂	0.49 to 1.10 percent by weight;
	Na ₂ O	up to 0.60 percent by weight;
35	K ₂ O	up to 0.10 percent by weight;
	Li ₂ O	0.30 to 0.91 percent by weight;

Fe_2O_3	0.23 to 0.35 percent by weight;
B_2O_3	0.60 to 3.00 percent by weight;

66. The glass composition according to claim 65 wherein
 5 the glass composition has a log3 forming temperature in the range of equal to and greater than 1187°C and equal to and less than 1220°C, the ΔT is in the range of equal to and greater than 50°C and equal to and less than 139°C, and the relationships are present in the following ranges:

10	SiO_2/CaO	2.22 to 2.66
	SiO_2/RO	2.01 to 2.39
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.09 to 4.87
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.51 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	67.95 to 72.05 wt%
15	$\text{SiO}_2 - \text{RO}$	27.50 to 33.84 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.18 to 2.68

67. The glass composition according to claim 65 wherein
 20 the glass composition has a log3 forming temperature in the range of equal to and greater than 1187°C and equal to and less than 1205°C, the ΔT is in the range of equal to and greater than 50°C and equal to and less than 139°C, and the relationships are present in the following ranges:

25	SiO_2/CaO	2.40 to 2.57
	SiO_2/RO	2.17 to 2.32
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.26 to 4.87
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.52 to 0.59
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	70.63 to 71.73 wt%
30	$\text{SiO}_2 - \text{RO}$	31.06 to 33.61 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.53
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.47 to 2.63

68. The glass composition according to claim 67 wherein:
 35 SiO_2 57.60 to 59.21 percent by weight;
 Al_2O_3 12.16 to 13.63 percent by weight;

	CaO	22.87 to 24.06 percent by weight;
	MgO	2.36 to 2.50 percent by weight;
	TiO ₂	0.49 to 1.10 percent by weight;
	Na ₂ O	up to 0.30 percent by weight;
5	K ₂ O	up to 0.09 percent by weight;
	Li ₂ O	0.70 to 0.90 percent by weight;
	Fe ₂ O ₃	0.23 to 0.29 percent by weight;
	B ₂ O ₃	1.00 to 1.20 percent by weight;

10 69. The glass composition according to claim 65 wherein the ingredients are in the following ranges:

	SiO ₂	54.60 to 58.70 percent by weight;
	Al ₂ O ₃	12.45 to 13.35 percent by weight;
	CaO	23.50 to 24.55 percent by weight;
15	MgO	2.50 to 2.55 percent by weight;
	TiO ₂	0 to 0.90 percent by weight;
	Na ₂ O	0 to 0.60 percent by weight;
	K ₂ O	0 to 0.55 percent by weight;
	Li ₂ O	0.30 percent by weight;
20	Fe ₂ O ₃	up to 0.35 percent by weight;
	B ₂ O ₃	0.90 to 3.00 percent by weight;

wherein:

25 the glass composition has log3 forming temperature in the 1187 to 1239°C, and the ΔT is in the range of 54 to 96°C. and

at least two of the following relationships are present;

	SiO ₂ /CaO	2.22 to 2.50
	SiO ₂ /RO	2.01 to 2.26
	SiO ₂ /Al ₂ O ₃	4.09 to 4.65
30	Al ₂ O ₃ /CaO	0.52 to 0.57
	SiO ₂ + Al ₂ O ₃	67.95 to 72.05 wt%
	SiO ₂ – RO	27.50 to 32.70 wt%
	Al ₂ O ₃ /RO	0.47 to 0.51
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO + B ₂ O ₃)	2.18 to 2.65

35

70. A glass composition comprising ingredients in the following ranges selected from one of the following Groups I, II or III:

Group I:

	SiO ₂	56.00 to 60.00 percent by weight;
	Al ₂ O ₃	10.00 to 14.00 percent by weight;
	CaO	21.00 to 25.00 percent by weight;
5	MgO	2.00 to 4.00 percent by weight;
	TiO ₂	0.25 to 1.50 percent by weight;
	Na ₂ O	up to 1.25 percent by weight;
	Li ₂ O	0.10 to 1.25 percent by weight;
	ZnO	up to 0.50 percent by weight;
10	MnO	up to 4.00 percent by weight;
	MnO ₂	up to 4.00 percent by weight;
	Fe ₂ O ₃	0.10 to 0.50 percent by weight, and
	B ₂ O ₃	0 to 1.50 percent by weight; or

Group II:

15	SiO ₂	57.00 to 59.00 percent by weight;
	Al ₂ O ₃	11.00 to 14.00 percent by weight;
	CaO	22.00 to 24.00 percent by weight;
	MgO	2.00 to 3.00 percent by weight;
	TiO ₂	0.25 to 1.35 percent by weight;
20	Na ₂ O	up to 1.10 percent by weight;
	Li ₂ O	0.20 to 1.10 percent by weight;
	ZnO	up to 0.40 percent by weight;
	MnO	up to 3.50 percent by weight;
	MnO ₂	up to 3.25 percent by weight;
25	Fe ₂ O ₃	0.15 to 0.50 percent by weight, and
	B ₂ O ₃	0 to 1.25 percent by weight; or

Group III

	SiO ₂	57.50 to 59.00 percent by weight;
	Al ₂ O ₃	11.50 to 14.00 percent by weight;
30	CaO	22.50 to 24.00 percent by weight;
	MgO	2.25 to 2.75 percent by weight;
	TiO ₂	0.40 to 1.25 percent by weight;
	Na ₂ O	up to 1.00 percent by weight;
	Li ₂ O	0.25 to 1.00 percent by weight
35	ZnO	up to 0.35 percent by weight;
	MnO	up to 3.25 percent by weight;
	MnO ₂	up to 3.25 percent by weight;

Fe_2O_3 0.20 to 0.40 percent by weight;
 B_2O_3 0 to 1.10 percent by weight; and

wherein:

the glass composition has a log3 forming temperature of in the no
 5 greater than 1241°C based on an NIST 710A reference standard;

the difference between the log3 forming temperature and the liquidus
 temperature define as ΔT is at least 50°C.

and at least two of the following relationships in the following ranges
 from one of the following Groups A or B is present:

10 Group A

	SiO_2/CaO	2.10 to 2.8
	SiO_2/RO	1.90 to 2.55
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 5.00
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.45 to 0.65
15	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.00 to 73.70 wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.00 to 3.00
	$\text{SiO}_2 - \text{RO}$	26.50 to 36.60 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.40 to 0.60

where RO is equal to the wt% of $\text{CaO} + \text{MgO}$, and R_2O is equal to the wt%
 20 of $\text{Na}_2\text{O} + \text{Li}_2\text{O}$; or

Group B

	SiO_2/CaO	2.20 to 2.70
	SiO_2/RO	1.90 to 2.40
	$\text{SiO}_2/\text{Al}_2\text{O}_3$	3.70 to 4.90
25	$\text{Al}_2\text{O}_3/\text{CaO}$	0.50 to 0.60
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	66.66 to 72.1wt%
	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.00 to 2.75
	$\text{SiO}_2 - \text{RO}$	26.50 to 33.34 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.46 to 0.56

30 where RO is equal to the wt% of $\text{CaO} + \text{MgO}$, and R_2O is equal to the wt%
 of $\text{Na}_2\text{O} + \text{Li}_2\text{O}$.

71. The glass composition according to claim 70 wherein:
 the glass composition has a log3 forming temperature of equal to and
 35 greater than 1219°C and equal to and less than 1241°C, and

a ΔT equal to and greater than 52°C and equal to and less than 76°C and the relationships are present in the following ranges:

	SiO_2/CaO	2.49 to 2.54
	SiO_2/RO	2.25 to 2.29
5	$\text{SiO}_2/\text{Al}_2\text{O}_3$	4.40 to 4.90
	$\text{Al}_2\text{O}_3/\text{CaO}$	0.52 to 0.57
	$\text{SiO}_2 + \text{Al}_2\text{O}_3$	69.52 to 72.05 wt%
	$\text{SiO}_2 - \text{RO}$	32.40 to 32.70 wt%
	$\text{Al}_2\text{O}_3/\text{RO}$	0.47 to 0.51
10	$(\text{SiO}_2 + \text{Al}_2\text{O}_3)/(\text{R}_2\text{O} + \text{RO} + \text{B}_2\text{O}_3)$	2.59 to 2.74

72. The glass composition according to claim 71 wherein the ingredients are in the following ranges:

	SiO_2	57.72 to 58.70 percent by weight;
15	Al_2O_3	11.88 to 13.35 percent by weight;
	CaO	22.80 to 23.50 percent by weight;
	MgO	2.43 to 2.50 percent by weight;
	TiO_2	0.50 to 1.10 percent by weight;
	Na_2O_3	0.87 – 0.90 percent by weight;
20	Li_2O	0 to 0.30 percent by weight;
	ZnO	0 to 0.30 percent by weight
	Fe_2O_3	0.22-0.25 percent by weight;
	MnO	0.30 to 3.00 percent by weight,
	MnO_2	0 to 3.00 percent by weight, and
25	B_2O_3	0 to 1.00 percent by weight.

73. A glass composition comprising the following ingredients :

	SiO_2	55.97 to 57.07 percent by weight;
30	Al_2O_3	12.68 to 12.86 percent by weight;
	CaO	23.91 to 24.69 percent by weight;
	MgO	2.42 to 2.60 percent by weight;
	TiO_2	0.94 – 1.09 percent by weight;
	Na_2O	0.87 – 0.93 percent by weight;
35	K_2O	0.05 – 0.07 percent by weight;
	Fe_2O_3	0.255 – 0.2.78 percent by weight;
	B_2O_3	1.15 – 1.70 percent by weight;

SO ₃	0.018 – 0.032 percent by weight;
SrO	0.04 – 0.05 percent by weight, and
Cr ₂ O ₃	0.002 – 0.008 percent by weight;

wherein:

5 the above glass composition have a log₃ forming temperature in the range of 1203 to 1217°C based on an NIST 710A reference standard, and the difference between the log₃ forming temperature and the liquidus temperature define as ΔT is in the range of 55 to 83°C. and

10 at least two of the following relationships in the following ranges are present

SiO ₂ /CaO	2.29 to 2.39
SiO ₂ /RO	2.04 to 2.14
SiO ₂ /Al ₂ O ₃	4.38 to 4.50
Al ₂ O ₃ /CaO	0.52 to 0.53
15 SiO ₂ + Al ₂ O ₃	68.65 to 69.98 wt%
SiO ₂ – RO	28.82 to 30.63 wt%
Al ₂ O ₃ /RO	0.47 to 0.48
(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO + B ₂ O ₃)	2.29 to 2.41

20 where Ro is equal to the wt% of MgO + CaO and R₂O is equal to the wt% of Na₂O + K₂O

74. A glass composition comprising:

a quaternary system including SiO₂, Al₂O₃, CaO and MgO and the ingredients of the glass having the following relationship:

25 SO ₂ /CaO	2.20 to 2.55
SiO ₂ /RO	1.96 to 2.29
SiO ₂ /Al ₂ O ₃	3.79 to 4.84
Al ₂ O ₃ /CaO	0.51 to 0.59
SiO ₂ + Al ₂ O ₃	66.10 to 71.45 wt%
30 SiO ₂ – RO	26.5 to 32.55 wt%
Al ₂ O ₃ /RO	0.46 to 0.56
(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO + B ₂ O ₃)	2.02 to 2.67

35 where the sum of MgO and CaO in percent by weight is defined as "RO", and the sum of Na₂O + K₂O + Li₂O in percent by weight is defined as "R₂O" and the above ingredients are in percent by weight to provide a glass composition having log₃ forming temperature of equal to and no greater than

1240°C based on an NIST 710A reference standard, and the difference between the $\log_3$ forming temperature and the liquidus temperature define as ΔT is at least 50°C.

5 75. The glass composition according to claim 74 wherein the ingredients are in the following ranges;

	SiO ₂	53.00. to 59.05 percent by weight;
	Al ₂ O ₃	12.20 to 14.00 percent by weight;
	CaO	22.25 to 24.95 percent by weight, and
10	MgO	1.50 to 3.00 percent by weight.

	76.	The glass composition according to claim 75 further including:	
	TiO ₂	0.50 to 1.10 percent by weight;	
	Na ₂ O	0.45 to 0.90 percent by weight;	
15	K ₂ O	0 to 0.58 percent by weight;	
	Fe ₂ O ₃	0 to 0.50 percent by weight;	
	B ₂ O ₃	0 to 5.02 percent by weight; and further.	

20 77. A quaternary system including SiO₂, Al₂O₃, CaO and MgO with the ingredients of the glass having the following relationship:

	SiO ₂ /CaO	2.39 to 2.71
	SiO ₂ /RO	2.16 to 2.52
	SiO ₂ /Al ₂ O ₃	4.26 to 4.99
	Al ₂ O ₃ /CaO	0.50 to 0.59
25	SiO ₂ + Al ₂ O ₃	70.60 to 73.67 wt%
	SiO ₂ – RO	30.95 to 36.56 wt%
	Al ₂ O ₃ /RO	0.46 to 0.53
	(SiO ₂ + Al ₂ O ₃)/ (R2O +RO+B ₂ O ₃)	2.30 to 2.96

30 where the sum of MgO and CaO in percent by weight is defined as "RO", and the sum of Na₂O + K₂O + Li₂O in percent by weight is defined as "R2O".

the glass composition having $\log_3$ forming temperature in the range of 1187 to 1240°C based on an NIST 710A reference standard, and

35 the difference between the $\log_3$ forming temperature and the liquidus temperature define as ΔT is in the range of 50 to 142°C.

78. The glass composition according to claim 77 wherein the ingredients are in the following ranges:

5	SiO ₂	54.60 to 60.75 percent by weight;
	Al ₂ O ₃	11.90 to 13.64 percent by weight;
	CaO	22.00 to 24.22 percent by weight, and
	MgO	1.90 to 3.40 percent by weight.

79. The glass composition according to claim 78 further including the following ingredients in the following ranges:

10	TiO ₂	0.49 to 1.50 percent by weight;
	Na ₂ O	0 to 0.90 percent by weight;
	K ₂ O	0 to 0.10 percent by weight;
	ZnO	0.45 to 1.50 percent by weight;
15	Li ₂ O	0.30 to 1.00 percent by weight
	Fe ₂ O ₃	0 to 0.35 percent by weight;
	B ₂ O ₃	0 to 3.00 percent by weight;

80. A glass composition comprising:
20 a quaternary system including SiO₂, Al₂O₃, CaO and MgO having the following relationship:

	SiO ₂ /CaO	2.36 to 2.73
	SiO ₂ /RO	2.14 to 2.52
	SiO ₂ /Al ₂ O ₃	4.26 to 4.99
25	Al ₂ O ₃ /CaO	0.50 to 0.59
	SiO ₂ + Al ₂ O ₃	70.85 to 73.67 wt%
	SiO ₂ – RO	30.55 to 36.56 wt%
	Al ₂ O ₃ /RO	0.46 to 0.53
	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO + B ₂ O ₃)	2.30 to 2.96

30 where the sum of MgO and CaO in percent by weight is defined as "RO", and the sum of Na₂O + K₂O + Li₂O in percent by weight is defined as "R₂O".

35 the above ingredients are in percent by weight to provide a glass composition having log₃ forming temperature in the range of equal to and greater than 1195°C and equal to and less than 1240°C based on an NIST 710A reference standard, and

the difference between the log₃ forming temperature and the liquidus temperature define as ΔT is in the range of equal to and greater than 50°C and equal to and less than 100°C.

5 81. The glass composition according to claim 80 wherein
 SiO₂ 57.45 to 60.75 percent by weight;
 Al₂O₃ 12.00 to 13.68 percent by weight;
 CaO 22.00 to 24.50 percent by weight, and
 MgO 1.70 to 3.10 percent by weight.

10 82. The glass composition according to claim 81 further including:
 TiO₂ 0.50 to 1.50 percent by weight;
 Na₂O 0 to 0.91 percent by weight;
 ZnO 0 to 1.00 percent by weight;
 15 Li₂O 0 to 1.00 percent by weight, and
 Fe₂O₃ 0 to 0.35 percent by weight.

 83. A glass composition comprising:
 20 a quaternary system including SiO₂, Al₂O₃, CaO and MgO and
 up to 5.10 wt% B₂O₃ wt% and ingredients of the glass having the following
 relationship:

	SiO ₂ /CaO	2.20 to 2.66
	SiO ₂ /RO	1.96 to 2.39
25	SiO ₂ /Al ₂ O ₃	3.79 to 4.90
	Al ₂ O ₃ /CaO	0.51 to 0.59
	SiO ₂ + Al ₂ O ₃	66.10 to 72.05 wt%
	SiO ₂ – RO	26.50 to 33.91 wt%
	Al ₂ O ₃ /RO	0.46 to 0.56
30	(SiO ₂ + Al ₂ O ₃)/ (R ₂ O + RO + B ₂ O ₃)	2.02 to 2.68

where the sum of MgO and CaO in percent by weight is defined as "RO", and the sum of Na₂O + K₂O + Li₂O in percent by weight is defined as "R₂O".

the above ingredients are in percent by weight to provide a glass
 35 composition having log₃ forming temperature in the range of equal to and

greater than 1167°C and equal to and less than 1240°C based on an NIST 710A reference standard, and

the difference between the log3 forming temperature and the liquidus temperature define as ΔT is in the range of equal to and greater than 50 and equal to and less than 142°C.

84. The glass composition according to claim 83 wherein the ranges for SiO₂, Al₂O₃, CaO and MgO are:

	SiO ₂	53.00 to 59.53 percent by weight;
10	Al ₂ O ₃	12.00 to 14.00 percent by weight;
	CaO	22.25 to 24.95 percent by weight, and
	MgO	1.50 to 3.00 percent by weight.

85. The glass composition according to claim 84 further including:

15	TiO ₂	0.40 to 1.10 percent by weight;
	Na ₂ O	0 to 0.90 percent by weight;
	K ₂ O	0 to 0.30 weight percent;
	F	0 to 0.50 percent by weight;
	SrO	0 to 0.13 percent by weight;
20	Cr ₂ O ₃	0 to 0.13 percent by weight;
	Li ₂ O	0 to 0.91 percent by weight, and
	Fe ₂ O ₃	0 to 0.30 percent by weight.

86. The glass composition according to claim 85 wherein B₂O₃ is in the range of 0.90 to 3.00 wt%.

87. The glass composition according to claim 86 wherein B₂O₃ is in the range of 1.30 to 5.02 wt%.

88. A glass fiber composition comprising:

	SiO ₂	52 to 62 percent by weight;
	Na ₂ O	0 to 2 percent by weight;
	CaO	16 to 25 percent by weight;
	Al ₂ O ₃	8 to 16 percent by weight;
	Fe ₂ O ₃	0.05 to 0.80 percent by weight;
	K ₂ O	0 to 2 percent by weight;
	MgO	1 to 5 percent by weight;

B ₂ O ₃	0 to 5 percent by weight;
TiO ₂	0 to 2 percent by weight; and
F	0 to 1 percent by weight;

wherein the glass composition has a log₃ forming temperature of no greater than 1240°C based on an NIST 710A reference standard,

a ΔT of at least 50°C, and a SiO₂/RO ratio of no greater than 2.35, and further wherein the glass composition has at least one of the following features;

	SiO ₂ /RO	1.9 to 2.55;
	SiO ₂ /CaO	2.1 to 2.8;
	SiO ₂ /Al ₂ O ₃	3.7 to 5.0;
10	Al ₂ O ₃ /CaO	0.5 to 0.6;
	SiO ₂ + Al ₂ O ₃	66.0 to 73.7 wt%;
	(SiO ₂ + Al ₂ O ₃)/(R ₂ O + RO + B ₂ O ₃)	2.0 to 3.0;
	SiO ₂ – RO	26.5 to 36.6 wt%; and
	Al ₂ O ₃ /RO	0.4 to 0.6.

15

89. The glass fiber composition according to claim 88, wherein the SiO₂ + Al₂O₃ content of the glass composition is greater than 70 wt%.

90. The glass fiber composition according to claim 89, wherein the SiO₂ content of the glass composition is greater than 57 wt% and the B₂O₃ content of the glass composition is no greater than 2 wt%.

91. The glass fiber composition according to claim 90, wherein the glass composition comprises at least 1 wt% TiO₂.

25

92. The glass fiber composition according to claim 91, wherein the glass composition is boron-free.

93. The glass fiber composition according to claim 52, wherein the glass composition further includes at least one material selected from:

30

Li ₂ O	0.05 to 1.5 percent by weight;
ZnO	0.05 to 1.5 percent by weight;
MnO	0.05 to 3 percent by weight; and
MnO ₂	0.05 to 3 percent by weight.

94. The glass composition according to claim 1 further including the relationships:

RO	26 to 28 wt%
R2O +RO+B ₂ O ₃	28.00 to 32.00 wt%

5

95. The glass composition according to claim 5 further including the relationships:

RO	26.25 to 27.60 wt%
R2O +RO+B ₂ O ₃	28.90 to 30.00 wt%

10

96. The glass composition according to claim 75 further including the relationships:

RO	24.80 to 27.56 wt%
R2O +RO+B ₂ O ₃	27.20 to 32.79 wt%

15

97. The glass composition according to claim 78 further including the relationships

RO	24.01 to 26.70 wt%
R2O +RO+B ₂ O ₃	25.15 to 28.64 wt%

20

98. The glass composition according to claim 81 further including the relationships

RO	24.01 to 26.90 wt%
R2O +RO+B ₂ O ₃	25.15 to 27.80 wt%

25

99. The glass composition according to claim 81 further including the relationships

RO	24.80 to 27.56 wt%
R2O +RO+B ₂ O ₃	26.90 to 32.79 wt%

30