

CATALYST FOR PREPARING CUMENE AND USE THEREOF

5

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims priorities of the following applications: Chinese patent application 201710473492.X, entitled “Catalyst for preparing cumene and preparation method thereof” and filed on June 21, 2017; Chinese patent application 201710473479.4, entitled “Cumene catalyst and preparation method thereof” and filed on June 21, 2017; Chinese patent application 201710473465.2, entitled “Catalyst for preparing cumene by hydrogenation” and filed on June 21, 2017. The entirety of the above applications is incorporated herein by reference.

15

FIELD OF THE INVENTION

The present disclosure relates to the technical field of a catalyst for preparing cumene. The present disclosure further relates to use of the catalyst and, in particular, to use of the catalyst in preparation of cumene by α -Methyl styrene hydrogenation.

20

BACKGROUND OF THE INVENTION

At present, cumene output in the world reaches nearly ten million tons, and more than 90% of the cumene are used to produce phenol and acetone. In this process, α -methyl styrene (AMS), a byproduct, is generated generally, and it is difficult to separate and remove AMS in subsequent refining procedures. However, AMS can be converted into raw material cumene by hydrogenation, and the raw material cumene can be used again in an oxidation procedure. By doing this, unit consumption of cumene can be reduced; a yield coefficient of phenol can be improved; and cost of raw materials can be saved. In this way, not only consumption of propylene and benzene raw materials can be reduced, but also technical and economic indexes of a device can be improved.

30

500 tons of AMS may be generated as a byproduct by a device for producing phenol/acetone with an annual output of 10000 tons, and devices for producing phenol/acetone used abroad all comprise an AMS hydrogenation unit. A traditional method of producing cumene by AMS hydrogenation is a slurry process, in which a Reney nickel catalyst is used, but the slurry process has defects such as complicated procedures, low selectivity of catalysts and a short usage cycle. The slurry process is gradually replaced by a fixed bed process. Performance of hydrogenation catalysts are very critical for the fixed bed process. There are many reports on catalysts for producing cumene by AMS hydrogenation. Saito studied experiments of catalytic hydrogenation to AMS using platinum as a catalyst. Phenolchemie Co. used $\text{Cu}_2\text{Cr}_2\text{Ni}$ to perform AMS hydrogenation. Chongheng He studied high-temperature thermal sintering of a palladium/alumina catalyst. Franco C et al. used a Pd/C catalyst in α -Methyl styrene hydrogenation. Little et al. respectively studied AMS selective hydrogenation properties of Ni, Pt, Pd, Co, Cr_2O_3 and several metal alloy catalysts. Activity and selectivity of non-palladium catalysts are not high, and catalysts which comprise palladium as a main or unique ingredient receive great attention in recent years. AMS is chemically active and has poor stability. Therefore, it is hoped that a hydrogenation catalyst has higher low-temperature activity and selectivity, as well as proper impurity-resistance property so as to increase a regeneration cycle of the catalyst, thereby prolonging the service life of the catalyst.

US patent US3646235 discloses a use of nickel, platinum, palladium, cobalt, chromium oxides and mixed metal catalysts in AMS hydrogenation. Under conditions of a temperature of 24-50 °C and a pressure of 0.17-0.45 MPa, a Pd catalyst with metal content of 1-5% (by weight) is better.

Chinese patent CN1793089A discloses a method for selective hydrogenation of AMS to cumene by using a combined catalyst system having a nickel catalyst and a noble-metal catalyst. In the method, a combination of commercially available catalysts is packed, 70-95% of AMS conversion in a first reaction zone was achieved and at least 95% of AMS conversion in a second reaction zone was achieved.

There is a need for a novel catalyst used for production of cumene which has an improved AMS conversion rate and cumene selectivity.

SUMMARY OF THE INVENTION

The purpose of the present disclosure is to solve the technical problem of low
5 AMS conversion rate and low cumene selectivity in preparation of cumene by AMS
hydrogenation.

In a first aspect, the present disclosure provides a catalyst for preparing cumene,
which comprises a carrier and an active ingredient. The active ingredient comprises:
10 ingredient (1), which is palladium element; and
ingredient (2), which is one or more selected from a group consisting of alkali
metal elements, alkaline earth metal elements and molybdenum element.

According to the present disclosure, the palladium element can exist in the
15 catalyst in a form of elementary substance, oxide, and/or salt.

According to the present disclosure, the alkali metal element can exist in the
catalyst in a form of oxide and/or salt.

20 According to the present disclosure, the alkaline earth metal element can exist in
the catalyst in a form of oxide and/or salt.

According to the present disclosure, the molybdenum element can exist in the
catalyst in a form of oxide and/or salt.

25 It is founded unexpectedly by the inventors that ingredient (1) and ingredient (2)
have a synergistic effect on improving the AMS conversion rate and the cumene
selectivity.

30 According to the present disclosure, g/L can be used as a unit of measurement to
describe content of ingredient (1) and ingredient (2), and it represents ingredient mass
loaded in one liter of the carrier. A conversion relation between g/L and a commonly
used mass percentage is as follows:

$$g_{\text{ingredient}}/L_{\text{carrier}} = (g_{\text{ingredient}}/g_{\text{carrier}}) \times \rho_{\text{carrier}}, \quad \text{wherein } \rho_{\text{carrier}} \text{ represents packing}$$

density of the carrier.

According to some preferred embodiments of the catalyst of the present disclosure, calculated by element, content of ingredient (1) is in a range of 0.01-10 g/L, preferably 0.05-5 g/L, and more preferably 0.1-4 g/L.

According to some preferred embodiments of the present disclosure, calculated by element, content of ingredient (2) is in a range larger than 0 g/L and equal to or less than 60 g/L, preferably 0.5-5 g/L, and more preferably 1.0-3.5 g/L.

10

According to the present disclosure, as a non-limitative example, content of ingredient (1) can be 0.1 g/L, 0.2 g/L, 0.5 g/L, 1 g/L, 1.5 g/L, 2 g/L, 2.7 g/L, 3 g/L, 3.5 g/L, 4 g/L, 4.5 g/L, 5 g/L, 5.5 g/L, 6 g/L, 6.5 g/L, 7 g/L, 8 g/L, 9 g/L and so on.

15 According to the present disclosure, as a non-limitative example, content of ingredient (2) can be 0.01 g/L, 0.06 g/L, 0.12 g/L, 0.15 g/L, 0.18 g/L, 0.24 g/L, 0.30 g/L, 0.5 g/L, 1.0 g/L, 2.0 g/L, 3.0 g/L, 4.0 g/L, 5.0 g/L, 10 g/L, 15 g/L, 20 g/L, 25 g/L, 30 g/L, 35 g/L, 40 g/L, 45 g/L, 50 g/L, 55 g/L and so on.

20 According to some preferred embodiments of the present disclosure, a mass ratio of ingredient (1) to ingredient (2) is in a range of (20-1):1, preferably (15-5):1, and more preferably (12-8):1.

25 According to some embodiments of the catalyst of the present disclosure, ingredient (2) is molybdenum element, an alkali metal element, or an alkaline earth metal element.

30 According to some preferred embodiments of the catalyst of the present disclosure, ingredient (2) comprises an alkali metal element and molybdenum element. Preferably, calculated by element mass, a mass ratio of the alkali metal element to the molybdenum element is in a range of (0.1-10):1, preferably (0.2-5):1, more preferably (0.25-4), and most preferably (1-4):1, such as 1:1, 1.5:1, 2:1, 3:1, or 4:1. In the presence of ingredient (1), the alkali metal element and molybdenum element have a synergistic effect on improving the AMS conversion rate and the cumene selectivity.

According to some preferred embodiments of the catalyst of the present disclosure, ingredient (2) comprises an alkaline earth metal element and molybdenum element. Preferably, calculated by element mass, a mass ratio of the alkali metal element to the molybdenum element is in a range of (0.1-10):1, preferably (0.2-5):1, more preferably (0.25-4), and further preferably (1-4):1, such as 1:1, 1.5:1, 2:1, 3:1, or 4:1. In the presence of ingredient (1), the alkaline earth metal element and molybdenum element have a synergistic effect on improving the AMS conversion rate and the cumene selectivity.

According to some preferred embodiments of the catalyst of the present disclosure, ingredient (2) comprises an alkali metal element, an alkaline earth metal element and molybdenum element. Preferably, calculated by element mass, a mass ratio of a sum of the alkali metal element and the alkaline earth metal element to the molybdenum element is in a range of (0.1-10):1, preferably (0.2-5):1, more preferably (0.25-4), and further preferably (1-4):1, such as 1:1, 1.5:1, 2:1, 3:1, or 4:1. In the presence of ingredient (1), the alkali metal element, the alkaline earth metal element and molybdenum element have a synergistic effect on improving the AMS conversion rate and the cumene selectivity.

According to some examples of the present disclosure, ingredient (2) is one or more selected from a group consisting of the alkali metal elements and the alkaline earth metal elements, and the catalyst does not comprise a metal element selected from IVA group elements.

According to some embodiments of the present disclosure, the active ingredient consists of ingredient (1) and ingredient (2). That is, the catalyst does not contain any active ingredient other than ingredient (1) and ingredient (2).

According to some preferred embodiments of the catalyst of the present disclosure, the alkaline earth metal element is at least one selected from a group consisting of Ca, Mg, Sr and Ba.

According to some preferred embodiments of the catalyst of the present

disclosure, the alkali metal element is at least one selected from a group consisting of Li, Na and K.

According to some preferred embodiments of the catalyst of the present disclosure, the carrier comprises at least one selected from a group consisting of alumina, zirconia, silica, titania and activated carbon. Preferably, the carrier comprises more than 80wt%, preferably more than 90wt%, and more preferably more than 95wt% of alumina.

According to some preferred embodiments of the catalyst of the present disclosure, a BET specific surface area of the carrier is in a range of 60-200 m²/g, preferably 80-150 m²/g.

According to some preferred embodiments of the catalyst of the present disclosure, a pore volume of the carrier is in a range of 0.2-0.7 mL/g, preferably 0.3-0.5 mL/g.

According to some preferred embodiments of the catalyst of the present disclosure, the carrier has a most probable pore size in a range of 10-30 nm. It is found unexpectedly by the inventors of the present disclosure that the most probable pore size of the carrier affects diffusion performance of the catalyst. A proper most probable pore size can match with the molecular diameter of raw materials and the material viscosity, and thus improve diffusion performance of molecules of the raw materials, and is more favorable for the contact of the raw material molecules and an active center of the catalyst. Preferably, the most probable pore size of the carrier is in a range of 12-20 nm.

According to some preferred embodiments of the catalyst of the present disclosure, the alumina comprises δ -alumina, θ -alumina, or a mixture of the δ -alumina and the θ -alumina. Preferably, the alumina comprises more than 30wt%, preferably more than 50wt%, and more preferably more than 75wt% of δ -alumina, θ -alumina, or a mixture of the δ -alumina and the θ -alumina. It is found unexpectedly by the inventors of the present disclosure that when the catalyst of the present disclosure using the mixture of the δ -alumina and the θ -alumina as the carrier is used in the

preparation of cumene by α -methyl styrene hydrogenation, there is a synergistic effect on improving the AMS conversion rate and the cumene selectivity.

According to some preferred embodiments of the catalyst of the present disclosure, in the mixture of the δ -alumina and the θ -alumina, a mass ratio of the δ -alumina to θ -alumina is in a range of (0.2-5.0):1, preferably (0.45-3):1, and more preferably (0.5-2):1.

According to some preferred embodiments of the catalyst of the present disclosure, the palladium element is loaded in the carrier in a form of elementary substance. It is found by the inventors that when a size of palladium particles is too big, properties of bulk phase palladium are exhibited, which causes a lower activity in a hydrogenation reaction; and when the size of the palladium particles is too small, activity of the catalyst is overly high, which causes the catalyst to be less selective, and the activity of the catalyst decreases rapidly. It is found unexpectedly by the inventors that the catalyst has an optimum performance when the size of the palladium particles is in a range of 1.5-3 nm.

The catalyst provided by the present disclosure can be prepared by using a method known in the art, such as mixing, kneading, extruding, drying, calcinating of powders of the carrier, impregnating active ingredients, and drying, calcinating and activating the catalyst, and so on.

As an example, the catalyst of the present disclosure can be prepared using method, comprising:

step A, mixing a carrier with a solution of a compound containing an active ingredient;

step B, calcinating the carrier treated in step A, optionally drying the carrier treated in step A before calcinating, to obtain a catalyst precursor;

step C, mixing the catalyst precursor obtained in step B with a solution of a compound containing palladium element; and

step D, calcinating the catalyst precursor treated in step C, optionally drying the catalyst precursor treated in step C before calcinating, to obtain the catalyst.

According to the present disclosure, the solution of a compound containing active ingredient is a solution of a compound containing ingredient (2), which is selected from a solution of a compound containing an alkali metal, a solution of a compound containing an alkaline earth metal, and a solution of a compound containing molybdenum element.

According to the present disclosure, there is no special limitation to the compound containing an alkali metal, the compound containing an alkaline earth metal, and the compound containing molybdenum element. As long as the compound containing an alkali metal, the compound containing an alkaline earth metal, and the compound containing molybdenum element are soluble in water, they can be used in the present disclosure. Examples are nitrate, hydrochloride, and C1-C4 carboxylate (oxalate is excluded because it is poorly soluble in water).

According to the present disclosure, there is no limitation to the compound containing palladium element. As long as the compound containing palladium element is soluble in water, it can be used in the present disclosure. Examples are palladium chloride, palladium acetate, palladium nitrate, chloropalladate, ammonium chloropalladate, and soluble complex compounds of palladium.

According to the present disclosure, as long as a solvent can dissolve the compound, it can be used for the preparation of the catalyst. However, in order to be economical and environment-friendly, a preferably used solvent is water.

According to some embodiments of the present disclosure, in step C, a pH value of the solution of a compound containing palladium is in a range of 2.0-4.0.

In order to obtain a catalyst with better strength, it is better to perform drying before calcinating in step B and/or step D. According to some embodiments of the present disclosure, in step B, a time duration for drying is in a range of 2-6 hours, and a temperature for drying is in a range of 80-120 °C. According to some embodiments of the present disclosure, in step D, a time duration for drying is in a range of 2-6 hours, and a temperature for drying is in a range of 80-120 °C.

According to the present disclosure, there is no special limitation to the calcinating atmosphere, as long as a comparable technical effect can all be achieved. In order to be economical, air atmosphere is used. For the convenience of comparison, air atmosphere is used in the embodiment of the present disclosure. According to
5 embodiment s of the present disclosure, in step B, a time duration for calcinating is in a range of 3-8 hours, and a temperature for calcinating is in a range of 400-600 °C. According to examples of the present disclosure, in step D, a time duration for calcinating is in a range of 3-8 hours, and a temperature for calcinating is in a range of 400-600 °C.

10 In the above catalyst, Pd can be reduced to elementary substance, which can be directly used in a reaction for the preparation of cumene by α -methyl styrene hydrogenation. In the above catalyst, Pd can also exist in a form of Pd oxide, which is convenient for storage and stable for transportation, but the Pd oxide needs to be
15 activated with a reducing agent before use. The reducing agent for activation can be hydrogen or a material containing hydrogen. For the convenience of comparison, Pd in the catalyst in examples of the present disclosure all exist as Pd oxide, and the Pd oxide should be activated at a temperature of 50 °C in a hydrogen atmosphere under a pressure of 0.4MPa for 4 hours before use.

20 In a second aspect, the present disclosure further provides use of the above catalyst in the preparation of cumene by hydrogenating α -methyl styrene.

25 In a third aspect, the present disclosure further provides a method for preparing cumene, comprising contacting a raw material containing α -methyl styrene and hydrogen with the above catalyst provided by the present disclosure for reaction to generate cumene.

30 According to some preferred embodiments of the method of the present disclosure, the method is performed in a single reactor or a reactor having two stages in series, and the reactor is preferably a fixed bed reactor.

According to some preferred embodiments of the method of the present disclosure, the reaction is performed under a pressure in a range of 0.2-3.0 MPa,

preferably 0.25-1.5 MPa.

According to some preferred embodiments of the method of the present disclosure, the reaction is performed under a temperature in a range of 30-100 °C, preferably 40-60 °C.

According to some preferred embodiments of the method of the present disclosure, the reaction is performed with a ratio of liquid circulation in a range of 1.0-10.0, preferably 2.0-7.0. If the ratio of liquid circulation is overly low, the concentration of α -methyl styrene at an inlet of the reactor is too high. As a result, polymerization of α -methyl styrene is easily caused. Polymer generated may cover the catalyst surface, which causes performance of the catalyst to decrease. If the ratio of liquid circulation is overly high, an amount of raw material needed to be processed by the catalyst increases. As a result, a space velocity increases, and the retention time is shortened, which causes a conversion rate to be reduced.

According to some preferred embodiments of the method of the present disclosure, a volume space velocity of the raw material containing α -methyl styrene is in a range of 0.3-3.0 h⁻¹, preferably 0.8-1.5 h⁻¹, such as 0.8 h⁻¹, 0.9 h⁻¹, 1.0 h⁻¹, 1.1 h⁻¹, 1.2 h⁻¹, 1.3 h⁻¹, 1.4 h⁻¹, 1.5 h⁻¹ and so on.

According to some preferred embodiments of the method of the present disclosure, a molar ratio of hydrogen to α -methyl styrene is in a range of (0.5-8):1, preferably (1-5):1, and more preferably (1.1-3.5):1.

According to some preferred embodiments of the method of the present disclosure, calculated by weight, the raw material contains 1-25% of α -methyl styrene and 75-99% of a solvent. It is found by the inventors that an overly high concentration of α -methyl styrene in the raw materials may result in that α -methyl styrene polymerizes to generate α -methyl styrene oligomer or a polymer having a higher molecular weight. Preferably, the raw material contains 2-10% of α -methyl styrene and 90-98% of a solvent. The solvent is, preferably, an inert solvent, which can be selected from methylbenzene, ethylbenzene, xylene, cumene and so on.

According to some preferred embodiments of the method of the present disclosure, the raw material containing α -methyl styrene is from a device for producing phenol and acetone using cumene.

5 The catalyst provided in the present disclosure has higher activity and selectivity when it is used in the preparation of cumene by α -methyl styrene hydrogenation. When the catalyst used in the present disclosure is used in the preparation of cumene, an AMS conversion rate can reach 99.97%, and cumene selectivity can reach 99.60%, the effect of which is good.

10 DETAILED DESCRIPTION OF THE EMBODIMENTS

The present disclosure will be explained in detail with reference to the examples, but the present disclosure is not limited by the following examples.

15 Each carrier used in the following examples and comparative examples has a bar length of 2 mm to 8 mm, a diameter of 1.8 mm to 2.2 mm, and a packing density of 0.5 g/mL to 0.8 g/mL.

20 Most probable pore sizes of the carriers used in examples and comparative examples were determined by the nitrogen adsorption BET method.

Example 1A

25 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500
30 ml of an aqueous solution of calcium nitrate containing 0.30 g of Ca; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of

Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which has Pd content of 2.7 g/L and Ca content of 0.30 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

40 ml of the above prepared catalyst was packed into a fixed bed reactor, and then the catalyst was activated for 4 hours at a temperature of 50 °C under a hydrogen atmosphere of 0.4 MPa. After that, a reaction was performed. Conditions for the reaction are as follows: a temperature for the reaction was 45 °C; a pressure for the reaction was 0.3 MPa; a molar ratio of hydrogen to AMS was 1.2; a liquid space velocity of the raw material (which includes 21% of AMS and 79% of cumene) of the reaction was 1.0 h⁻¹; and a time duration for the reaction was 72 hours.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Example 2A

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of ammonium molybdate containing 0.30 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L and Mo content of 0.30 g/L) was obtained. In the obtained catalyst, the Pd particle

size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

5 2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

10 For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Example 3A

15 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 0.24 g of Ca and ammonium molybdate containing 0.06 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, Ca content of 0.24 g/L and Mo content of 0.06 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

5 For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Example 4A

10 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 0.18 g of Ca and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, Ca content of 0.18 g/L and Mo content of 0.12 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

30 2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation

results thereof are listed in Table 1.

Example 5A

5 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 0.15 g of Ca and ammonium molybdate containing 0.15 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, Ca content of 0.15 g/L and Mo content of 0.15 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

25

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

30

Example 6A

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 0.12 g of Ca and ammonium molybdate containing 0.18 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, Ca content of 0.12 g/L and Mo content of 0.18 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Example 7A

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500

ml of an aqueous solution of calcium nitrate containing 0.06 g of Ca and ammonium molybdate containing 0.24 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, Ca content of 0.06 g/L and Mo content of 0.24 g/L,) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Example 8A

1. Preparation of a catalyst

1 L of cylindrical titania carrier (which had a most probable pore size of 16.8 nm and a specific surface area of 85 m²/g) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 0.18 g of Ca and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, Ca content of 0.18 g/L and Mo content of 0.12 g/L) was

obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

5

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation
10 results thereof are listed in Table 1.

Example 9A

1. Preparation of a catalyst

15

1 L of cylindrical silica carrier (which had a most probable pore size of 21.8 nm and a specific surface area of 185 m²/g) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 0.18 g of Ca and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product
20 obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired
25 catalyst (which had Pd content of 2.7 g/L, Ca content of 0.18 g/L and Mo content of 0.12 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

30

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Comparative Example 1A

5

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of palladium chloride containing 3.0 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 3.00 g/L) was obtained. In the obtained catalyst, the Pd particle size was 3.5 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

20

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

25

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Comparative Example 2A

30

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina

and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of calcium nitrate containing 3.00 g of Ca; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Ca content of 3.00 g/L) was obtained.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Comparative Example 3A

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of ammonium molybdate containing 3.00 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Mo content of 3.00 g/L) was obtained.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1A.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 1.

Table 1 Compositions of the catalyst and evaluation results thereof

	Contents of active ingredient, g/L			Carrier	AMS conversion rate, %	Cumene Selectivity, %
	Pd	Ca	Mo			
Example 1A	2.70	0.30	--	alumina	94.33	93.51
Example 2A	2.70	--	0.30	alumina	94.50	96.62
Example 3A	2.70	0.24	0.06	alumina	98.54	98.31
Example 4A	2.70	0.18	0.12	alumina	99.56	99.21
Example 5A	2.70	0.15	0.15	alumina	98.16	98.21
Example 6A	2.70	0.12	0.18	alumina	96.76	97.87
Example 7A	2.70	0.06	0.24	alumina	96.03	97.12
Example 8A	2.70	0.18	0.12	titania	90.34	91.67
Example 9A	2.70	0.18	0.12	silica	91.57	92.09
Comparative Example 1A	3.00	--	--	alumina	90.13	91.37
Comparative Example 2A	--	3.00	--	alumina	0	0
Comparative Example 3A	--	--	3.00	alumina	0	0

Example 1B

5

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.30 g of K; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a

temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L and K content of 0.30 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

40 ml of the catalyst was packed into a fixed bed reactor, and then the catalyst was activated for 4 hours at a temperature of 50 °C under a hydrogen atmosphere of 0.4 MPa. After that, a reaction was performed. Conditions for the reaction were as follows: a temperature for the reaction was 45 °C; a pressure for the reaction was 0.3 MPa; a molar ratio of hydrogen to AMS was 1.2; a liquid space velocity of the raw material (which includes 21% of AMS and 79% of cumene) of the reaction was 1.0 h⁻¹; and a time duration for the reaction was 72 hours.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Example 2B

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of ammonium molybdate containing 0.30 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of

Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L and Mo content of 0.30 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Example 3B

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.24 g of K and ammonium molybdate containing 0.06 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.24 g/L and Mo content of 0.06 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

5 The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

10 Example 4B

1. Preparation of a catalyst

15 1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at
20 a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours,
25 and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

30 2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Example 5B

5

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.15 g of K and ammonium molybdate containing 0.15 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.15 g/L and Mo content of 0.15 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

25

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

30

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Example 6B

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.12 g of K and ammonium molybdate containing 0.18 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.12 g/L and Mo content of 0.18 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Example 7B

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500

ml of an aqueous solution of potassium carbonate containing 0.06 g of K and ammonium molybdate containing 0.24 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, and K content of 0.06 g/L and Mo content of 0.24 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Example 8B

1. Preparation of a catalyst

1 L of cylindrical titania carrier (which had a most probable pore size of 16.8 nm, a specific surface area of 85 m²/g) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was

obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

5

The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

10

Example 9B

1. Preparation of a catalyst

15

1 L of cylindrical silica carrier (which had a most probable pore size of 21.8 nm, a specific surface area of 185 m²/g) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained. In the obtained catalyst, the Pd particle size was 2.2 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

20

25

2. Evaluation of the catalyst

30

The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation

results thereof are listed in Table 2.

Comparative Example 1B

5 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of palladium chloride containing 3.0 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which has Pd content of 3.00 g/L) was obtained.
15 In the obtained catalyst, the Pd particle size was 3.5 nm, which was obtained by using a TEM (transmission electron microscopy) average mensuration method.

2. Evaluation of the catalyst

20 The evaluation of the catalyst prepared above was the same as that in Example 1B.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

25

Comparative Example 2B

1. Preparation of a catalyst

30 1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ -alumina and θ -alumina, wherein the mass ratio of δ -alumina and θ -alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 3.00 g of K; then a

mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had K content of 3.00 g/L) was obtained.

5 2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

10 For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Comparative Example 3B

15 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which had a most probable pore size of 15.8 nm, a specific surface area of 125 m²/g, and a pore volume of 0.46 mL/g, and contained 75wt% of δ-alumina and θ-alumina, wherein the mass ratio of δ-alumina and θ-alumina was 1:1, and the rest was other phases of alumina) was mixed with 500 ml of an aqueous solution of ammonium molybdate containing 3.00 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Mo content of 3.00 g/L) was obtained.

25

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1B.

30

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 2.

Table 2 Compositions of the catalyst and evaluation results thereof

	Contents of active ingredient, g/L			Carrier	AMS conversion rate, %	Cumene Selectivity, %
	Pd	K	Mo			
Example 1B	2.70	0.30	--	alumina	95.63	94.21
Example 2B	2.70	--	0.30	alumina	94.50	96.62
Example 3B	2.70	0.24	0.06	alumina	98.67	98.48
Example 4B	2.70	0.18	0.12	alumina	99.97	99.60
Example 5B	2.70	0.15	0.15	alumina	98.32	98.39
Example 6B	2.70	0.12	0.18	alumina	97.21	98.15
Example 7B	2.70	0.06	0.24	alumina	96.12	97.51
Example 8B	2.70	0.18	0.12	titania	91.24	92.32
Example 9B	2.70	0.18	0.12	silica	92.36	92.87
Comparative Example 1B	3.00	--	--	alumina	90.13	91.37
Comparative Example 2B	--	3.00	--	alumina	0	0
Comparative Example 3B	--	--	3.00	alumina	0	0

Example 1C

5 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 52wt% of δ -alumina and 48wt% θ -alumina and had a most probable pore size of 15.3 nm) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH

value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained.

5

2. Evaluation of the catalyst

40 ml of the catalyst was packed into a fixed bed reactor, and then the catalyst was activated for 4 hours at a temperature of 50 °C under a hydrogen atmosphere of 0.4 MPa. After that, a reaction was performed. Conditions for the reaction were as follows: a temperature for the reaction was 45 °C; a pressure for the reaction was 0.3 MPa; a molar ratio of hydrogen to AMS was 1.2; a liquid space velocity of the raw material of the reaction (which included 21% of AMS and 79% of cumene) was 1.0 h⁻¹; and a time duration for the reaction was 72 hours.

15

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

Example 2C

20

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 100wt% of δ -alumina and has a most probable pore size of 17.9 nm) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained.

30

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1C.

5

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

Example 3C

10

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 100wt% θ -alumina and had a most probable pore size of 18.4 nm) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained.

25

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1C.

30

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

Example 4C

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 65wt% of δ -alumina and 35wt% θ -alumina and had a most probable pore size of 16.2 nm) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1C.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

Example 5C

1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 35wt% of δ -alumina and 65wt% θ -alumina and had a most probable pore size of 15.8 nm) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at a

temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained.

5 2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1C.

10 For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

Example 6C

15 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 50wt% of δ -alumina and 50wt% θ -alumina and had a most probable pore size of 14.7 nm) was mixed with 500 ml of an aqueous solution of potassium carbonate containing 0.18 g of K and ammonium molybdate containing 0.12 g of Mo; then a mixture obtained was dried at a
20 temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours; after that, a product obtained from calcination was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and at last, a mixture obtained was dried at
25 temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 2.7 g/L, K content of 0.18 g/L and Mo content of 0.12 g/L) was obtained.

 2. Evaluation of the catalyst

30

The evaluation of the catalyst prepared above was the same as that in Example 1C.

For the convenience of comparison, compositions of the catalyst and evaluation

results thereof are listed in Table 3.

Comparative Example 1C

5 1. Preparation of a catalyst

1 L of cylindrical alumina carrier (which included 100wt% of γ -alumina and had a most probable pore size of 10.2 nm) was mixed with 500 ml of an aqueous solution of palladium chloride containing 2.7 g of Pd which was adjusted to a pH value of 3.2
10 using hydrochloric acid; and then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 3.00 g/L) was obtained.

2. Evaluation of the catalyst

15

The evaluation of the catalyst prepared above was the same as that in Example 1C.

For the convenience of comparison, compositions of the catalyst and evaluation
20 results thereof are listed in Table 3.

Comparative Example 2C

1. Preparation of a catalyst

25

1 L of cylindrical alumina carrier (which included 70wt% of δ -alumina 30wt% of γ -alumina and had a most probable pore size of 18.6 nm) were mixed with 500 ml of an aqueous solution of palladium chloride containing 3.00 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and then a mixture obtained was dried at
30 a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 3.00 g/L) was obtained.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1C.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

Comparative Example 3C

1. Preparation of a catalyst

10

1 L of cylindrical alumina carrier (which included 100wt% of α -alumina and had a most probable pore size of 131.7 nm) was mixed with 500 ml of an aqueous solution of palladium chloride containing 3.00 g of Pd which was adjusted to a pH value of 3.2 using hydrochloric acid; and then a mixture obtained was dried at a temperature of 80 °C for 4 hours and calcinated at a temperature of 450 °C for 4 hours, and a desired catalyst (which had Pd content of 3.00 g/L) was obtained.

2. Evaluation of the catalyst

The evaluation of the catalyst prepared above was the same as that in Example 1C.

For the convenience of comparison, compositions of the catalyst and evaluation results thereof are listed in Table 3.

25

Table 2 Phases and most probable pore sizes of the carriers for the catalyst and evaluation results thereof

	Phase of the carrier	Most probable pore size of the carrier, nm	AMS conversion rate, %	Cumene Selectivity, %
Example 1C	δ -alumina + θ -alumina	15.3	99.97	99.60
Example 2C	δ -alumina	17.9	98.32	98.39

Example 3C	θ -alumina	18.4	97.21	98.15
Example 4C	δ -alumina + θ -alumina	16.2	99.86	99.74
Example 5C	δ -alumina + θ -alumina	15.8	99.36	99.15
Example 6C	δ -alumina + θ -alumina	14.7	99.14	99.24
Comparative Example 1C	γ - alumina	10.2	92.41	93.57
Comparative Example 2C	δ -alumina + γ - alumina	18.6	93.89	94.63
Comparative Example 3C	α - alumina	131.7	73.6	83.5

Although the present disclosure is described hereinabove by referring to some examples, various improvements can be made to the present disclosure, and components therein can be replaced by equivalents without departing from the scope of the present disclosure. In particular, as long as there is no conflict, all the technical features mentioned in all the examples disclosed in the present disclosure may be combined together in any manner, and the present disclosure does not provide exhaustive descriptions of these combinations just for saving space and resources. Therefore, the present disclosure is not limited by particular examples disclosed hereinabove, but includes all technical solutions that fall within the scope of the claims.

CLAIMS

1. A catalyst for preparing cumene, comprising a carrier and an active ingredient, wherein the active ingredient comprises:

ingredient (1) that is palladium in elemental, salt or oxide form, and

ingredient (2) comprising molybdenum and, optionally, an alkali metal, an alkaline earth metal, or both,

wherein ingredient (2) is in salt or oxide form,

wherein, based on the weight of element metal, a content of palladium is 0.01-10 g/L and a mass ratio of ingredient (1) to ingredient (2) is in a range of (20-1):1,

and wherein g/L is a unit representing a total mass of the active ingredient loaded on one liter of the carrier.

2. The catalyst according to claim 1, wherein a content of ingredient (2) is in a range larger than 0 g/L and equal to or less than 60 g/L.

3. The catalyst according to claim 2, wherein the content of ingredient (2) is 0.5-5 g/L.

4. The catalyst according to claim 3, wherein the content of ingredient (2) is 1.0-3.5 g/L.

5. The catalyst according to claim 1, wherein a mass ratio of ingredient (1) to ingredient (2) is (15-5):1.

6. The catalyst according to claim 5, wherein the mass ratio of ingredient (1) to ingredient (2) is (12-8):1.

7. The catalyst according to claim 1, wherein ingredient (2) comprises an alkali metal and molybdenum, wherein, based on the weight of elemental metal, a mass ratio of the alkali metal to molybdenum is in a range of (0.1-10):1;

ingredient (2) comprises an alkaline earth metal and molybdenum; or

ingredient (2) comprises an alkali metal element, an alkaline earth metal element

and molybdenum.

8. A method for preparing cumene, which comprises contacting a raw material containing α -methyl styrene and hydrogen with the catalyst according to claim 7 for reaction to generate cumene.

9. The catalyst according to claim 1, wherein the alkaline earth metal element is at least one selected from the group consisting of Ca, Mg, Sr and Ba, and the alkali metal element is at least one selected from the group consisting of Li, Na and K.

10. The catalyst according to claim 1, wherein the carrier comprises at least one selected from the group consisting of alumina, zirconia, silica, titania and activated carbon.

11. The catalyst according to claim 1, wherein the carrier has a BET specific surface area in a range of 60-200 m²/g, a pore volume in a range of 0.2-0.7 mL/g, and a most probable pore size in a range of 10-30 nm.

12. The catalyst according to claim 10, wherein the alumina comprises δ -alumina, θ -alumina, or a mixture of the δ -alumina and the θ -alumina.

13. The catalyst according to claim 12, wherein in the mixture of the δ -alumina and the θ -alumina, a mass ratio of the δ -alumina to the θ -alumina is in a range of (0.2-5.0):1.

14. A method for preparing cumene, comprising contacting a raw material containing α -methyl styrene and hydrogen with the catalyst according to claim 1 to generate cumene.

15. The method according to claim 14, wherein the reaction is carried out under a pressure in a range of 0.2-3.0 MPa, at a temperature in a range of 30-100 °C, at a ratio of liquid circulation of 1.0-10.0.

16. The method according to claim 14, wherein a volume space velocity of the raw material containing α -methyl styrene is in a range of 0.3-3.0 h⁻¹, and a molar ratio of hydrogen to α -methyl styrene is in a range of (0.5-8):1.

17. The method according to claim 14, wherein the raw material contains 1-25wt% of α -methyl styrene and 75-99wt% of a solvent.

18. The method according to claim 14, wherein the raw material containing α -methyl styrene is from a device for producing phenol and acetone using cumene.

19. The catalyst according to claim 1, wherein the content of ingredient (1) is 0.05-5 g/L.

20. The catalyst according to claim 1, wherein the content of ingredient (1) is 0.1-4 g/L.