



159159

0050/51364

Preparation of caprolactam



G00002

The present invention relates to a process for the preparation of caprolactam, wherein

5

a) a mixture (I) containing 6-aminocapronitrile ("ACN") and water is reacted in the liquid phase, in the presence of a catalyst, to give a mixture (II) containing caprolactam, ammonia, water, high-boiling components and low-boiling components,

10

b) ammonia is then removed from the mixture (II) to give a mixture (III) containing caprolactam, water, high-boiling components and low-boiling components,

15

c) water is then removed from the mixture (III) to give a mixture (IV) containing caprolactam, high-boiling components and low-boiling components, and

20

d) a solid (V) containing caprolactam is then obtained from the mixture (IV) by crystallization, the proportion by weight of caprolactam in the solid (V) being greater than in the mixture (IV).

25

Processes for the preparation of caprolactam are generally known.

It is also generally known, for example from Ullmann's Encyclopedia of Industrial Chemistry, 5th Ed., Vol. A5, VCH Verlagsgesellschaft mbH, Weinheim (Germany), 1986, pages 46-48, or Kirk-Othmer, Encyclopedia of Chemical Technology, 4th Ed., Vol. 4, John Wiley & Sons, New York, 1992, page 836, that caprolactam used for the preparation of polymers must have a purity of 99.9 to 99.94%, the main impurity conventionally being water in an amount of 0.04 to 0.1%. Other impurities must only be present in an amount of at most a few ppm.

30

35

Thus caprolactam can be prepared by a Beckmann rearrangement of cyclohexanone oxime with sulfuric acid or oleum. After neutralization of the resulting mixture with ammonia, the caprolactam can be obtained
5 from the ammonium sulfate formed as a by-product by extraction with an organic solvent.

Depending on the processes for the preparation of the educts used to prepare the cyclohexanone oxime, such as
10 cyclohexanone and hydroxylammonium sulfate, and on the oximation and rearrangement conditions, the crude caprolactam obtained by a Beckmann rearrangement contains different types and amounts of impurities. Typical impurities in crude caprolactam prepared by a
15 Beckmann rearrangement are C-methylcaprolactams, 6-methylvalerolactam and n-pentylacetamide.

Various processes are described for the purification of crude caprolactam obtained by a Beckmann rearrangement.
20

According to DE-A-1253716, the crude caprolactam can be purified by hydrogenation in suspension, in the presence of a catalyst and with the addition of an acid.
25

According to DE-A-1253716, the crude caprolactam can be purified by hydrogenation in suspension, in the presence of a catalyst and with the addition of a base.

30 DD-A-75083 describes a process for the purification of crude caprolactam in which the crude caprolactam is first distilled and then dissolved in an organic solvent, hydrogenated in the presence of a catalyst and then treated with an ion exchanger.

35 According to EP-A-411455, the important characteristic quality features of caprolactam can be preserved by hydrogenating the crude caprolactam continuously in a

liquid phase process.

Crude caprolactam, obtained by the hydroformylation of 3-pentenoic acid and/or its esters to give 5-formylvaleric acid (esters) as main products and 4- and 3-formylvaleric acid (esters) as by-products, separation of this (these) branched formylvaleric acid (esters) by extraction (WO 97/02228) or distillation (WO 97/06126), aminating hydrogenation of 5-formylvaleric acid (esters) to 6-aminocaproic acid (esters) and/or 6-aminocaproic acid amide, and cyclization of 6-aminocaproic acid (esters) or 6-aminocaproic acid amide, contains other typical impurities.

Thus it is known e.g. from WO 99/48867, Example 1, to crystallize crude caprolactam obtained from 5-formylvaleric acid esters, according to WO 98/37063, Example 9, from mixtures of 6-aminocaproic acid, 6-aminocaproic acid amide and corresponding oligomers, by the addition of 10% by weight of water. This crude caprolactam, from which high-boiling and low-boiling components were not separated before crystallization, contained 6345 ppm of N-methylcaprolactam, 100 ppm of 5-methylvalerolactam, 78 ppm of valeramide and other impurities. The crude caprolactam/water melt was homogenized at 50°C and then cooled to 30°C. The crystals which precipitated out were filtered off and washed 2 to 3 times with aqueous caprolactam. The 5-methylvalerolactam and valeramide contents were reduced to 1 ppm and the N-methylcaprolactam content to 51 ppm. 33.7 g of pure lactam were obtained from 73.6 g of crude lactam (caprolactam yield: 45.8%). The characteristic of the volatile bases (VB) was only achieved by a second crystallization. If high-boiling and low-boiling components were separated from the crude caprolactam before crystallization, according to WO 99/48867, Example 3, the caprolactam yield after

crystallization was 52%.

It is further known from WO 99/65873 selectively to adsorb caprolactam from mixtures with 4-ethyl-2-pyrrolidone, 5-methyl-2-piperidone, 3-ethyl-2-pyrrolidone and 3-methyl-2-piperidone or octahydro-phenazine on adsorbents like activated carbon, molecular sieves or zeolites to give pure caprolactam after desorption. This separation of caprolactam can be followed by crystallization from the melt or crystallization from a solvent.

It is further known to purify, by crystallization, crude caprolactam which, starting from 6-amino-capronitrile, is first hydrolyzed with water to 6-aminocaproic acid, according to WO 98/37063, claim 8. Water and ammonia formed by hydrolysis are then separated off, the 6-aminocaproic acid formed is cyclized and the crude caprolactam obtained is crystallized according to WO 99/48867.

Caprolactam can also be obtained by reacting ACN with water in the liquid phase, in the presence or absence of a catalyst, with the release of ammonia.

In addition to caprolactam, water, ammonia and optionally another liquid diluent, the mixture obtained in this reaction contains impurities boiling above caprolactam ("high-boiling components") and impurities boiling below caprolactam ("low-boiling components").

It is known from the Example in US-A-496,941 that, after the separation of water, solvent, ammonia, low-boiling component and high-boiling component from a mixture obtained by reacting ACN with water and solvent, a crude caprolactam is obtained with a purity of 99.5%.

Other methods of purification are described for a crude caprolactam obtained from ACN in the liquid phase since the impurities in this type of crude caprolactam are markedly different from those in a crude caprolactam
5 obtained by other processes, as described in US-A-5,496,941.

In a first step, according to US-A-5,496,941, ACN is converted to caprolactam in the liquid phase, low-
10 boiling components, water, ammonia and optionally other solvents are simultaneously separated off, high-boiling components are separated off to give a crude caprolactam with a purity of 99.5%, this crude caprolactam is hydrogenated in the presence of a catalyst, the
15 product obtained is treated with an acidic ion exchanger or sulfuric acid and the resulting product is distilled in the presence of a base.

WO 96/20923 discloses a method of purifying crude
20 caprolactam originating from the liquid phase cyclization of 6-aminocapronitrile with water in the presence of a solvent and heterogeneous catalysts. In this case, crude caprolactam is first hydrogenated, then treated with acidic agents and finally distilled
25 in the presence of alkali. The disadvantage of this method of purification is that three separate reaction steps are required to prepare pure caprolactam.

Said methods of purifying crude caprolactam prepared
30 from ACN have the disadvantage of being technically expensive and energy-intensive, especially on account of the numerous separation steps.

It is an object of the present invention to provide a
35 process which makes it possible to prepare, in high purity and in a technically simple and energy-saving manner, caprolactam which has been obtained from ACN in the liquid phase.

We have found that this object is achieved by the process defined at the outset.

In step a), a mixture (I) containing 6-aminocapro-
5 nitrile, water and optionally liquid diluent is converted in the liquid phase, in the presence of a solid which promotes the reaction catalytically, to a mixture (II) containing caprolactam, ammonia, water, optionally liquid diluent, high-boiling components and
10 low-boiling components.

The ACN required for step a) can be obtained from adipodinitrile, as is generally known from Ullmann's Encyclopedia of Industrial Chemistry, 5th Ed., Vol. A5,
15 VCH Verlagsgesellschaft mbH, Weinheim (Germany), 1986, page 46, Fig. 8.

Particularly appropriate here is the partial catalytic hydrogenation of adipodinitrile in the presence of
20 ammonia as solvent and e.g. in the presence of rhodium on magnesium oxide (US-A-4,601,859), Raney nickel (US-A-2,762,835, WO 92/21650) or nickel on aluminum oxide (US-A-2,208,598) as a suspension catalyst or Cu-Co-Zn spinel (DE-B-954416, US-A-2,257,814) or iron
25 (DE-A-42 35 466) as a fixed bed catalyst, or a process according to US-A-2,245,129, US-A-2,301,964, EP-A-150295 or FR-A-2 029 540, or a process described in US-A-5,496,941.

30 The adipodinitrile required for this reaction is prepared industrially, e.g. by the double hydrocyanation of butadiene in the presence of nickel-containing catalysts, and is commercially available, e.g. from Aldrich-Chemie Gesellschaft mbH & Co. KG,
35 Steinheim, Germany.

The conversion of the mixture (I) to the mixture (II) can be carried out according to FR-A-2029540 in the

presence of catalysts, the catalysts used being metallic Zn or Cu powder or the oxides, hydroxides, halides or cyanides of rubidium, lead, mercury or the elements of atomic numbers 21 to 30 or 39 to 48. The catalysts described are used as suspension catalysts in stirred autoclaves operated batchwise.

A process described in US-A-5,646,277, US-A-5,739,324 or WO 59/14665 is particularly preferred as step a).

10

In these processes, the reaction is carried out in the liquid phase at temperatures generally of 140 to 320°C, preferably of 160 to 280°C; the pressure ranges generally from 1 to 250 bar, preferably from 5 to 150 bar, it being necessary to ensure that the reaction mixture is predominantly liquid under the conditions used. The residence times range generally from 1 to 120 min, preferably from 1 to 90 min and particularly preferably from 1 to 60 min. Residence times of 1 to 10 min have proved totally satisfactory in some cases.

The reaction can be carried out batchwise or, preferably, continuously. Suitable reactors are a stirred tank, an autoclave or, preferably, a multitube fixed-bed reactor. Combinations of such reactors are also possible.

The amount of water used is generally at least 0.1 mol, preferably 0.5 to 100 mol and particularly preferably 1 to 20 mol per mol of ACN.

Advantageously, the ACN is used in the form of a 1 to 50% by weight, especially 5 to 50% by weight and particularly preferably 5 to 30% by weight solution in water (in which case the solvent is simultaneously a reactant) or in mixtures containing water and a liquid diluent. Examples of liquid diluents which may be mentioned are alkanols such as methanol, ethanol, n-

and i-propanol and n-, i- and t-butanol, polyols such as diethylene glycol and tetraethylene glycol, hydrocarbons such as petroleum ether, benzene, toluene and xylene, lactams such as pyrrolidone or caprolactam, 5 alkyl-substituted lactams such as N-methylpyrrolidone, N-methylcaprolactam or N-ethylcaprolactam, and carboxylic esters, preferably those of carboxylic acids having from 1 to 8 C atoms. Ammonia can also be present in the reaction. Of course, it is also 10 possible to use mixtures of organic liquid diluents. Mixtures of water and alkanols in a water/alkanol weight ratio of 1-75/25-99, preferably 1-50/50-99, have been shown to be particularly advantageous in some cases.

15

In principle, it is equally possible to use the ACN as reactant and solvent at the same time.

Examples of heterogeneous catalysts which can be used 20 are acidic, basic or amphoteric oxides of the elements of main group II, III or IV of the Periodic Table, such as calcium oxide, magnesium oxide, boron oxide, aluminum oxide, tin oxide or silicon dioxide in the form of pyrogenic silicon dioxide, silica gel, kiesel- 25 guhr, quartz or mixtures thereof, and also oxides of metals of subgroups II to VI of the Periodic Table, such as amorphous titanium oxide in the form of anatase or rutile, zirconium oxide, zinc oxide, manganese oxide or mixtures thereof. It is also possible to use 30 lanthanide and actinide oxides such as cerium oxide, thorium oxide, praseodymium oxide, samarium oxide, a rare earth mixed oxide or mixtures thereof with the abovementioned oxides. Examples of other possible catalysts are:

35

vanadium [sic] oxide, niobium oxide, iron oxide, chromium oxide, molybdenum oxide, tungsten oxide or mixtures thereof. Mixtures of said oxides with one

another are also possible. Some sulfides, selenides and tellurides, such as zinc telluride, tin selenide, molybdenum sulfide, tungsten sulfide and the sulfides of nickel, zinc and chromium, can also be used.

5

The abovementioned compounds can be doped with, or contain, compounds of main groups I and VII of the Periodic Table.

- 10 Other suitable catalysts which may be mentioned are zeolites, phosphates and heteropolyacids, as well as acidic and alkaline ion exchangers like Nafion.

These catalysts can optionally contain up to 50% by
15 weight in each case of copper, tin, zinc, manganese, iron, cobalt, nickel, ruthenium, palladium, platinum, silver or rhodium.

Particularly preferred catalysts which have very high
20 conversions, yields, selectivities and working lives under the above-described reaction conditions are heterogeneous catalysts based on titanium oxide, zirconium oxide, cerium oxide and aluminum oxide, especially titanium dioxide. They can be used in the
25 form of powders, chips, grit, strands or tablets (produced by compression). The form of the oxides normally depends on the requirements of the particular reaction procedure, powder or chips being used in suspension. In the fixed bed procedure, it is
30 conventional to use tablets or strands with diameters of between 1 mm and 10 mm.

Aluminum oxide is suitable in any modifications which can be obtained by heating the aluminum hydroxide
35 precursor compounds (gibbsite, boehmite, pseudo-boehmite, bayerite and diaspora) at varying temperatures. These include especially gamma- and alpha-aluminum oxide and mixtures thereof.

The oxides can be used in the pure form (content of the individual oxide > 80% by weight), as a mixture of the abovementioned oxides, in which case the sum of the abovementioned oxides should be >80% by weight, or as a supported catalyst, in which case the abovementioned oxides can be applied to a mechanically and chemically stable support, usually with a high surface area.

The pure oxides may have been prepared by precipitation from aqueous solutions, e.g. titanium dioxide by the sulfate process, or by other processes such as the pyrogenic preparation of fine aluminum oxide, titanium dioxide or zirconium dioxide powders, which are commercially available.

A choice of several methods is available for the preparation of mixtures of the different oxides. The oxides, or their precursor compounds which can be converted to the oxides by calcination, can be prepared e.g. by joint precipitation from solution. A very good distribution of the two oxides used is generally obtained by this method. The oxide or precursor mixtures can also be obtained by precipitation of one oxide or precursor in the presence of the second oxide or precursor present as a suspension of fine particles. Another method consists in mechanically mixing the oxide or precursor powders, it being possible for this mixture to be used as a starting material for the production of strands or tablets.

In principle, supported catalysts can be prepared by any of the methods described in the literature. Thus the oxides can be applied to the support in the form of their sols simply by impregnation. The volatile constituents of the sol are conventionally removed from the catalyst by drying and calcination. Such sols are commercially available for titanium dioxide, aluminum oxide and zirconium dioxide.

Another possible way of applying layers of the active oxides consists in hydrolyzing or pyrolyzing organic or inorganic compounds. Thus a ceramic support can be coated with a thin layer of titanium dioxide by
5 hydrolyzing titanium isopropylate or other Ti alkoxides. Other suitable compounds are TiCl_4 , zirconyl chloride, aluminum nitrate and cerium nitrate, inter alia. Suitable supports are powders, strands or tablets of said oxides themselves or of other stable
10 oxides like silicon dioxide. The supports used can be in a macroporous form in order to improve the material transport.

In step b), ammonia is removed from the mixture (II) to
15 give a mixture (III) containing caprolactam, water, optionally liquid diluent, high-boiling components and low-boiling components.

In principle, the separation of the ammonia from the
20 mixture (II) can be effected by methods known per se for the separation of materials, such as extraction or, preferably, distillation, or a combination of such methods.

25 The distillation can advantageously be carried out at bottom temperatures of 60 to 220°C, especially of 100 to 220°C. The pressure, measured at the top of the distillation performance [sic], is conventionally set at 2 to 30 bar absolute.

30 Suitable apparatuses are those conventionally used for distillation, for example the ones described in Kirk-Othmer, Encyclopedia of Chemical Technology, 3rd Ed., Vol. 7, John Wiley & Sons, New York, 1979,
35 pages 870-881, such as sieve-plate columns, bubble-cap columns or packed columns.

The distillation can be carried out in several columns, such as 2 or 3, but advantageously in a single column.

5 In step c), water and optionally liquid diluents are removed from the mixture (III) to give a mixture (IV) containing caprolactam, high-boiling components and low-boiling components.

10 If a liquid diluent has been used in step a), water and liquid diluent can be separated off simultaneously in step c) or the water can be separated off before or after the liquid diluent.

15 In principle, the water can be separated from the mixture (III) by methods known per se for the separation of materials, such as extraction, crystallization or, preferably, distillation, or a combination of such methods.

20 The distillation can advantageously be carried out at bottom temperatures of 50 to 250°C, especially of 100 to 230°C.

25 Suitable apparatuses are those conventionally used for distillation, for example the ones described in Kirk-Othmer, Encyclopedia of Chemical Technology, 3rd Ed., Vol. 7, John Wiley & Sons, New York, 1979, pages 870-881, such as sieve-plate columns, bubble-cap columns or packed columns.

30

The distillation can be carried out in several columns, such as 2 or 3, but advantageously in a single column.

35 A heat-coupled multistage separation of the water and optionally the liquid diluent is particularly preferred.

Before the mixture (IV) is introduced into step d), it is appropriate to separate off the low-boiling component [sic] and high-boiling component [sic], advantageously only the high-boiling components, especially neither the low-boiling component [sic] nor the high-boiling component [sic] and particularly advantageously only the low-boiling components from the mixture (IV).

10 If the low-boiling components and high-boiling components are separated from the mixture, the low-boiling components can be separated off before, after or together with the high-boiling components.

15 In the case where the low-boiling component [sic] and high-boiling component [sic], or only the high-boiling component [sic], or only the low-boiling component [sic], are separated off, the separation can be effected in principle by methods known per se for the separation of materials, such as extraction, 20 crystallization or, preferably, distillation, or a combination of such methods.

The distillation can advantageously be carried out at 25 bottom temperatures of 50 to 250°C, especially of 100 to 230°C. The pressure, measured at the top of the distillation performance [sic], is conventionally set at 1 to 500 mbar absolute, preferably 5 to 100 mbar absolute.

30

Suitable apparatuses are those conventionally used for distillation, for example the ones described in Kirk-Othmer, Encyclopedia of Chemical Technology, 3rd Ed., Vol. 7, John Wiley & Sons, New York, 1979, 35 pages 870-881, such as sieve-plate columns, bubble-cap columns or packed columns.

The distillation for separating off the low-boiling components can be carried out in several columns, such as 2 or 3, but advantageously in a single column.

- 5 The distillation for separating off the high-boiling components can be carried out in several columns, such as 2 or 3, but advantageously in a single column.

10 In step d), a solid (V) containing caprolactam is obtained from the mixture (IV) by partial crystallization, the proportion by weight of caprolactam in the solid (V) being greater than in the mixture (IV).

- 15 The sum of the contents of high-boiling and low-boiling components, not including water and organic diluents, in the mixture (IV) used in step d) is advantageously at least 100 ppm by weight, preferably 200 ppm by weight, particularly preferably at least 500 ppm by weight and especially at least 1000 ppm by weight, based on the mixture (IV).

The crystallization can be effected batchwise or continuously.

25

The crystallization can be effected with the addition of an aid such as an organic or inorganic liquid diluent, for example water, but preferably without the addition of an aid.

30

The crystallization can be effected in one or more stages, such as two, three or four stages, preferably one stage. In another preferred embodiment of the invention, the crystallization can be effected as fractional crystallization.

35

In the case of fractional crystallization, all the stages producing a crystalline product (caprolactam)

which is purer than the initial crude product (crude caprolactam) are conventionally called purification stages, and all the other stages are conventionally called refining stages. It is advisable here to
5 operate multistage processes according to the counter-current principle, whereby, after the crystallization in each stage, the crystalline product is separated from the remaining liquid phase ("mother liquor") and transferred to the appropriate stage with the next
10 highest degree of purity, the crystallization residue being transferred to the appropriate stage with the next lowest degree of purity.

Advantageously, the temperature of the solution or melt
15 during crystallization is not higher than the melting point of caprolactam (70°C) and is preferably between -10 [sic] and the melting point of caprolactam and especially between 20 [sic] and the melting point of caprolactam. The solids content in the crystallizer is
20 conventionally between 0 and 70 g, preferably between 30 and 60 g, per 100 g of charge.

In another advantageous embodiment of the invention, the crystallization is effected in apparatuses in which
25 the crystals grow on cooled surfaces in the crystallization apparatus, i.e. are fixed in the apparatus (e.g. layer crystallization process from Sulzer Chemtech (Switzerland) or static crystallization process from BEFS PROKEM (France)).

30 The crystallization can also be effected by cooling apparatus walls or by evaporating a solution of the crude caprolactam under reduced pressure. Five to 30% by weight solutions of crude caprolactam in a liquid
35 diluent, especially water, are particularly suitable for this purpose.

In the case of crystallization by cooling, the heat can

be removed via scraped wall chillers connected to a stirred tank or an unstirred vessel. The crystal suspension can be circulated by means of a pump. A further possibility is to remove the heat via the wall of a tank with a wall-fitted stirrer. Another preferred embodiment of crystallization by cooling is the use of cooling disk crystallizers, e.g. those manufactured by Gouda (Holland). In another suitable variant of crystallization by cooling, the heat can be removed via conventional heat exchangers (preferably shell-and-tube or parallel-plate heat exchangers). In contrast to scraped wall chillers, tanks with wall-fitted stirrers or cooling disk crystallizers, these apparatuses do not possess a device for preventing layers of crystals from forming on the heat-transfer surfaces. If, during operation, a situation is reached where the resistance to heat transition due to the formation of layers of crystals becomes excessive, the conventional procedure is to switch over to a second apparatus. During the operating period of the second apparatus, the first apparatus can be regenerated (preferably by melting the layer of crystals or flushing the apparatus with unsaturated solution). If the resistance to heat transition in the second apparatus becomes excessive, the procedure is to switch back to the first apparatus, and so on. This variant can also be operated with more than two apparatuses in alternation. The crystallization can also be effected by conventional evaporation of the solution under reduced pressure.

The solid-liquid separation methods known per se are suitable for separating the mother liquor from the caprolactam which has crystallized out.

In one preferred embodiment of the invention, the crystals can be separated from the mother liquor by filtration and/or centrifugation. Advantageously, the

filtration or centrifugation can be preceded by preliminary concentration of the suspension, for example by means of one or more hydrocyclones. Centrifuges known per se, which operate batchwise or
5 continuously, are suitable for the centrifugation. It is most advantageous to use pusher centrifuges, which can be operated in one or more stages. Screen-conveyor centrifuges or helical-conveyor centrifuges (decanter) are also suitable. The filtration can advantageously
10 be effected by means of suction filters, which can be operated batchwise or continuously and with or without a stirrer, or by means of belt filters. The filtration can generally be carried out under superatmospheric pressure or under reduced pressure.

15

During and/or after the solid-liquid separation, provision can be made for further process steps to increase the purity of the crystals or crystal cake. In one particularly advantageous embodiment of the
20 invention, the separation of the crystals from the mother liquor is followed by washing and/or sweating of the crystals or crystal cake in one or more stages.

In the case of washing, the amount of washing liquor
25 should preferably be between 0 and 500 g per 100 g of crystalline product, preferably between 30 and 200 g per 100 g of crystalline product.

Suitable washing liquors are organic or inorganic
30 liquids or mixtures of such liquids, examples of preferred washing liquors being

a) in the case where a liquid diluent has been used in the crystallization in step d), said liquid
35 diluent,

b) a melt of a crystalline product obtained in a crystallization stage of step d),

c) a mother liquor obtained in a crystallization stage of step d), or

5 d) a melt of an educt used in a crystallization stage of step d).

The washing can be effected in apparatuses conventionally used for this purpose. It is advantageous to use wash columns, in which the
10 separation of the mother liquor and the washing take place in one apparatus, centrifuges, which can be operated in one or more stages, or suction filters or belt filters. The washing can be effected on centrifuges or belt filters in one or more stages, it
15 being possible for the washing liquor to be conveyed in countercurrent to the crystal cake.

Particularly in the case of crystallization without the addition of an aid, the washing liquor can be recycled
20 into the crystallization, optionally after impurities have been separated off.

Sweating is conventionally understood as meaning a local melting of contaminated regions. The amount of
25 sweating should advantageously be 0.1 to 90 g of melted crystalline product per 100 g of crystalline product prior to sweating, preferably 5 to 35 g of melted crystalline product per 100 g of crystalline product. It is particularly preferred to carry out the sweating
30 on centrifuges or belt filters. It may also be appropriate to combine washing and sweating in one apparatus.

Particularly in the case of crystallization without the
35 addition of an aid, the mother liquor can be recycled into the crystallization, optionally after impurities have been separated off.

Caprolactam can be obtained in a purity of at least

99.90% by weight, preferably 99.90 to 99.99% by weight, by the present process.

5 The caprolactam obtainable by the process according to the invention can be used for the preparation of polyamides like polycaprolactam.

Examples

10 Example 1a

Preparation of crude caprolactam

15 The purification sequence was carried out with crude caprolactam obtained according to WO 95/14664 by the cyclization of a 10% ethanolic solution of 6-aminocapronitrile (ACN) in the presence of 2.5 mol of water per mol of ACN:

20 A solution of 6-aminocapronitrile (ACN) in water and ethanol (10% by weight of ACN, 4.0% by weight of water, remainder: ethanol) was passed at 100 bar into a heated tubular reactor of capacity 25 ml (diameter 6 mm; length 800 mm) packed with titanium dioxide (anatase)
25 in the form of 1.5 mm strands, the reaction temperature being 245°C and the residence time being 30 min. The product stream leaving the reactor was analyzed by gas chromatography: conversion: 100%, yield: 87%.

30 The reaction discharge was freed of high-boiling and low-boiling components by fractional distillation. According to gas chromatographic analysis, the resulting crude caprolactam had a purity of 99.90%.

35 Example 1b

Purification of crude caprolactam by crystallization
492 g of liquid crude caprolactam from Example 1a were

crystallized on the flat cooled bottom plate of a stirred vessel.

The bottom plate of the vessel was cooled from an
5 initial temperature of 75°C at a rate of -50 K/h. After
the temperature had fallen below the melting point of
the crude caprolactam melt, a constantly growing layer
of pure caprolactam crystals formed on the cooling
surface. To ensure a good material transition between
10 the liquid and solid phases during the growth process,
the crude caprolactam melt was stirred with a vane
stirrer at 500 rpm. When the weight of crystal mass
had reached 378 g (yield 77% by weight), the cooling
was stopped, the stirrer was switched off and the
15 stirred vessel was rotated through 180° so that the
bottom was now pointing upward, thereby separating the
residual melt enriched in impurities (mother liquor,
23% by weight) from the layer of caprolactam crystals
adhering to the bottom plate. The mass of caprolactam
20 crystals could be removed by dismantling the bottom
plate of the vessel.

Table 1 shows the properties of the crude caprolactam
of Example 1a and the crystals and mother liquor of
25 Example 1b.

Table 2 shows the conventional required specification
of commercially available caprolactam, together with
the corresponding values of the crude lactam of Example
30 1a and the caprolactam purified according to Example 1b
("crystals").

	Amount [% by weight]	Capro	ACN	HMD	EAC	EECL	ZECL
Crude lactam	100	99.90	52 ppm	31 ppm	101 ppm	35 ppm	22 ppm
Crystals	77	99.991	4 ppm	<1 ppm	5 ppm	12 ppm	7 ppm
Mother liquor	23	99.832	205 ppm	122 ppm	431 ppm	105 ppm	81 ppm

Table 1

	Free bases [meq/kg]	Volatile bases [meq/kg]	Absorbance	Color number	PAN
Specification	0.1	0.5	0.05	5	4
Crude lactam	1.3	0.73	0.18	7.2	7.8
Crystals	0.09	0.34	0	0	1.6

5

Table 2

Abbreviations:

- 10 ACN: 6-aminocapronitrile
HMD: hexamethylenediamine
EAC: ethyl 6-aminocaproate
EECL: E-alpha-ethylidenecaprolactam
ZECL: Z-alpha-ethylidenecaprolactam

15

Methods of analysis

Free bases

- 20 To determine the free bases, 150 ml of CO₂-free distilled water through which nitrogen had been passed were adjusted to exactly pH 7.0 with 0.01 N sodium hydroxide solution, and 50 ± 0.1 g of caprolactam were

added. The mixture was then titrated to pH 7.0 with 0.01 N hydrochloric acid at 25°C. The proportion of free base could then be calculated according to the formula below, A (ml) denoting the volume of 0.01 N hydrochloric acid consumed. Free bases = $0.01 \times A \times 1000/50 = 0.2 \times A$ meq/kg.

Volatile bases (VB)

The volatile bases were determined according to ISO standard 8661 ("Caprolactam for industrial use - Determination of volatile bases content").

The volatile bases were liberated from the sample by distillation in an alkaline medium (Kjeldahl apparatus), trapped in 0.01 N hydrochloric acid and determined by titration with 0.01 N sodium hydroxide solution. The initial weight of caprolactam sample was 20 ± 0.1 g.

$$VB = \frac{(B - A) \times 0.01}{20} \times 1000 \text{ meq/kg}$$

A = volume of 0.01 N sodium hydroxide solution consumed
B = volume of 0.01 N sodium hydroxide solution consumed for a blank determination

Absorbance

The absorbance was carried out according to ISO standard 7059 ("Caprolactam for Industrial Use - Determination of Absorbance at a Wavelength of 290 nm").

Color number

The color number was determined according to

ISO standard 8112.

50 $\pm$ 0.1 g of caprolactam were dissolved in 50 ml of distilled water in a 250 ml Erlenmeyer flask and left to stand until the air bubbles had disappeared. In two reference cuvettes (l = 5 cm), the difference in absorbance A_{290} between water and CL/water was determined at $\lambda = 390$ [sic] nm.

10 Color number = $150 \times A_{290}$ (rounded to nearest integer)

Permanganate absorption number (PAN)

The PAN was determined according to ISO standard 8660.

15

This was done by adding identical amounts of 0.01 N potassium permanganate solution to a 3% (m/m) aqueous solution of caprolactam and to a blank sample (distilled water). After 10 minutes the absorbances A of both the caprolactam sample and the blank sample were compared at 420 nm. The permanganate absorption number is calculated according to the following formula:

25 PAN (PI) = $(A - A_0)_{420} \times 100/3$

We claim:-

1. A process for the preparation of caprolactam,
wherein
 - a) a mixture (I) containing 6-aminocapronitrile and water is reacted in the liquid phase, in the presence of a catalyst, to give a mixture (II) containing caprolactam, ammonia, water, high-boiling components and low-boiling components,
 - b) ammonia is then removed from the mixture (II) to give a mixture (III) containing caprolactam, water, high-boiling components and low-boiling components,
 - c) water is then removed from the mixture (III) to give a mixture (IV) containing caprolactam, high-boiling components and low-boiling components, and
 - d) a solid (V) containing caprolactam is then obtained from the mixture (IV) by crystallization, the proportion by weight of caprolactam in the solid (V) being greater than in the mixture (IV).
2. A process as claimed in claim 1 wherein the mixture (I) additionally contains an organic liquid diluent.
3. A process as claimed in claim 2 wherein the liquid diluent is removed in step c) before, during or after the separation of the water from the mixture (III).

4. A process as claimed in any of claims 1 to 3 wherein the low-boiling components are separated off between steps c) and d).
- 5 5. A process as claimed in any of claims 1 to 3 wherein the high-boiling components are separated off between steps c) and d).
- 10 6. A process as claimed in any of claims 1 to 3 wherein the low-boiling and high-boiling components are separated off between steps c) and d).
- 15 7. A process as claimed in any of claims 1 to 6 wherein the sum of the contents of high-boiling and low-boiling components, not including water and any liquid diluent present, in the mixture (IV) used in step d) is at least 100 ppm by weight.
- 20 8. A process as claimed in any of claims 1 to 7 wherein the crystallization in step d) is effected in the absence of aids.
- 25 9. A process as claimed in any of claims 1 to 8 wherein the crystallization in step d) is effected on a cooled surface on which the solid (V) grows.
- 30 10. A process as claimed in any of claims 1 to 9 wherein the mother liquor obtained after the crystallization of step d) is mixed with the mixture (IV) and recycled into step d).
- 35 11. A process as claimed in any of claims 1 to 10 wherein the crystallization in step d) is effected batchwise.