acryloxyacetophenone, ortho-acrylamidoacetophenone, acrylated anthraquinones, and any combinations thereof.

8. A precursor according to any of the preceding claims, wherein the co-polymerized hydrogen-donating monomer is selected from the group consisting of (meth)acrylamide, (meth)acrylate monomers containing at least one nitrogen functional group, urethane (meth)acrylate monomers containing at least one nitrogen functional group, vinylic monomers containing at least one nitrogen functional group, and combinations thereof.

9. A precursor according to any of the preceding claims, wherein the co-polymerized hydrogen-donating monomer is selected from the group consisting of N,N-dimethyl (meth)acrylamide; N,N-diethyl (meth)acrylamide; N-vinyl caprolactam; N-Vinylpyrrolidone; N-isopropyl (meth)acrylamide; N,N-dimethylaminoethyl (meth)acrylate; 2-[[(Butylamino)carbonyl]oxy]ethyl (meth) acrylate N,N-dimethylaminopropyl (meth)acrylamide; N,N-diethylaminopropyl (meth)acrylamide; ; N,N-diethylaminoethyl (meth)acrylate; N,N-dimethylaminopropyl (meth)acrylate; N,N-diethylaminopropyl (meth)acrylate;N,N-dimethylaminoethyl (meth)acrylamide; N,N-diethylaminoethyl (meth)acrylamide; (meth)acryloyl morpholine, vinylacetamide and any combinations or mixtures thereof. Preferably still, the co-polymerized hydrogen-donating monomer for use herein is selected from the group consisting of N,N-dimethyl acrylamide;N,N-dimethylaminoethyl (meth)acrylate; N,N-diethylaminoethyl (meth)acrylate, vinylacetamide and any combinations or mixtures thereof.

10. An adhesive comprising a crosslinked form of a precursor of any of the preceding claims.

11. An article comprising a precursor of any of claims 1-9 or an adhesive of claim 10.

12. The article of claim 11, further comprising one or more adherends.

13. The article of any of claims 11-12, wherein the article is a tape.

14. The article of any of claims 11-12 wherein the article is a label.

15. The article of any of claims 11-14, wherein the article further comprises a release liner.