

BUILT-IN BYPASS DIODE

BACKGROUND

[0001] Photovoltaic cells, commonly known as solar cells, are well known devices for direct conversion of solar radiation into electrical energy. Generally, solar cells are fabricated on a semiconductor wafer or substrate using semiconductor processing techniques to form a p-n junction near a surface of the substrate. Solar radiation impinging on the surface of, and entering into, the substrate creates electron and hole pairs in the bulk of the substrate. The electron and hole pairs migrate to p-doped and n-doped regions in the substrate, thereby generating a voltage differential between the doped regions. The doped regions are connected to conductive regions on the solar cell to direct an electrical current from the cell to an external circuit coupled thereto.

SUMMARY

[0001a] According to the first aspect, a method of fabricating a bypass diode for a solar cell is provided, the method comprising:

- forming a first conductive region of a first conductivity type on a first dielectric layer on a substrate of the solar cell;
- forming a second dielectric layer on the first conductive region;
- removing a portion of the second dielectric layer;
- forming a second conductive region of a second conductivity type above a portion of the first conductive region exposed by the removed portion of the second dielectric layer;
- coupling metal of the second conductivity type to the first conductive region and metal of the first conductivity type to the first portion of the second conductive region

[0001b] According to the second aspect, a method of fabricating a bypass diode for a solar cell is provided, the method comprising:

- forming an opening in a dielectric layer on a first conductive region;
- forming a second conductive region above the first conductive region through the opening in the dielectric layer;
- isolating a first portion of the second conductive region from a second portion of the second conductive region; and
- forming a conductive connection between the first conductive region of a first conductivity type and a metal of a second conductivity type, and between the second portion of the second conductivity region of the second conductivity type and a metal of the first conductivity type.

[0001c] According to a third aspect, a bypass diode for a solar cell is provided, the bypass diode comprising:

- a first conductive region of a first conductivity type disposed on a first dielectric layer on a substrate of the solar cell;
- a second dielectric layer disposed above the first conductive region, a portion of the second dielectric layer being removed;
- a second conductive region of a second conductivity type disposed above a portion of the first conductive region exposed by the removed portion of the second dielectric layer; a portion of the second conductive region being removed to separate the second conductive region into first and second portions of the second conductive region;
- a metal of the second conductivity type is coupled to the first conductive region and a metal of the first conductivity type is coupled to the first portion of the second conductive region; and
- a thin dielectric region disposed directly between the first and second conductive regions.

BRIEF DESCRIPTION OF THE DRAWINGS

[0002] Figure 1 illustrates a top-down plan view of a bypass diode for a solar cell, according to some embodiments.

[0003] Figure 2 illustrates a top-down plan view of a bypass diode including P-type and N-type regions, according to some embodiments.

[0004] Figure 3 illustrates a cross-section view of a bypass diode, according to some embodiments.

[0005] Figure 4 is a flowchart illustrating an example method of forming a bypass diode, according to some embodiments.

[0006] Figures 5-14 illustrate cross-sectional views of example sequences of forming a bypass diode, according to some embodiments.

DETAILED DESCRIPTION

[0007] The following detailed description is merely illustrative in nature and is not intended to limit the embodiments of the subject matter of the application or uses of such embodiments. As used herein, the word “exemplary” means “serving as an example, instance, or illustration.” Any implementation described herein as exemplary is not necessarily to be construed as preferred or

advantageous over other implementations. Furthermore, there is no intention to be bound by any expressed or implied theory presented in the preceding technical field, background, brief summary or the following detailed description.

[0008] This specification includes references to “one embodiment” or “an embodiment.” The appearances of the phrases “in one embodiment” or “in an embodiment” do not necessarily refer to the same embodiment. Particular features, structures, or characteristics may be combined in any suitable manner consistent with this disclosure.

[0009] Terminology. The following paragraphs provide definitions and/or context for terms found in this disclosure (including the appended claims):

[0010] “Comprising.” This term is open-ended. As used in the appended claims, this term does not foreclose additional structure or steps.

[0011] “Configured To.” Various units or components may be described or claimed as “configured to” perform a task or tasks. In such contexts, “configured to” is used to connote structure by indicating that the units/components include structure that performs those task or tasks during operation. As such, the unit/component can be said to be configured to perform the task even when the specified unit/component is not currently operational (e.g., is not on/active). Reciting that a unit/circuit/component is “configured to” perform one or more tasks is expressly intended not to invoke 35 U.S.C. § 112, sixth paragraph, for that unit/component.

[0012] “First,” “Second,” etc. As used herein, these terms are used as labels for nouns that they precede, and do not imply any type of ordering (e.g., spatial, temporal, logical, etc.). For example, reference to a “first” conductive region of a solar cell does not necessarily imply that this conductive region is the first conductive region in a sequence; instead the term “first” is used to differentiate this conductive region from another conductive region (e.g., a “second” conductive region).

[0013] “Based On.” As used herein, this term is used to describe one or more factors that affect a determination. This term does not foreclose additional factors that may affect a determination. That is, a determination may be solely based on those factors or based, at least in part, on those factors. Consider the phrase “determine A based on B.” While B may be a factor that affects the determination of A, such a phrase does not foreclose the determination of A from also being based on C. In other instances, A may be determined based solely on B.

[0014] “Coupled” – The following description refers to elements or nodes or features being “coupled” together. As used herein, unless expressly stated otherwise, “coupled” means that one element/node/feature is directly or indirectly joined to (or directly or indirectly communicates with) another element/node/feature, and not necessarily mechanically.

[0015] In addition, certain terminology may also be used in the following description for the purpose of reference only, and thus are not intended to be limiting. For example, terms such as “upper”, “lower”, “above”, and “below” refer to directions in the drawings to which reference is made. Terms such as “front”, “back”, “rear”, “side”, “outboard”, and “inboard” describe the

orientation and/or location of portions of the component within a consistent but arbitrary frame of reference which is made clear by reference to the text and the associated drawings describing the component under discussion. Such terminology may include the words specifically mentioned above, derivatives thereof, and words of similar import.

[0016] Although many of the examples described herein are back contact solar cells, the techniques and structures apply equally to other (e.g., front contact) solar cells as well. Moreover, although much of the disclosure is described in terms of solar cells for ease of understanding, the disclosed techniques and structures apply equally to other semiconductor structures.

[0017] Bypass diodes for solar cells and methods of forming solar cell bypass diodes are described herein. In the following description, numerous specific details are set forth, such as specific process flow operations, in order to provide a thorough understanding of embodiments of the present disclosure. It will be apparent to one skilled in the art that embodiments of the present disclosure may be practiced without these specific details. In other instances, well-known fabrication techniques, such as lithography and patterning techniques, are not described in detail in order to not unnecessarily obscure embodiments of the present disclosure. Furthermore, it is to be understood that the various embodiments shown in the figures are illustrative representations and are not necessarily drawn to scale.

[0018] Solar cells are typically heated when reversely biased by shading and/or soiling. Bypass diodes can be used to protect solar cells from breakdown during such events. However, power can be lost because bypass diodes are typically attached on a per-string basis (e.g., 12-18 cells) and the protection is not perfect if hot spots are present. Thus, the disclosed bypass diodes can provide bypass diode protection at the individual solar cell level. The protection can be for reverse bias events as well as for temperature suppression of hot spots.

[0019] Turning now to Figure 1, a top-down plan view of an example bypass diode for a solar cell is shown. Portion 100 of a solar cell can include polysilicon bypass diode 102 with N+ region 104 and P+ region 106. As shown, metal grid 108 can make contact to region 104. As depicted by diode schematic 110, bypass diode 102 is shunted to its corresponding solar cell.

[0020] In one embodiment and as described herein, P+ polysilicon is at the bottom of bypass diode 102 and is isolated from other P fingers. In various embodiments, the area consumed by bypass diode 102 cannot be used for power generation and is thus fabricated to be small relative to the total area of the solar cell. Note that a single solar cell can include multiple bypass diodes and is not limited to a single built-in bypass diode. In one embodiment, bypass diode 102 can provide higher current in reverse bias to reduce power consumption.

[0021] Turning to Figure 2, a top-down plan view of one embodiment of a bypass diode including P-type and N-type conductive regions is illustrated. As shown, N-type polysilicon 206 can be contacted with P-type pad 210. Contact is also made to the P-type portion of polysilicon diode 208 to provide interconnection of built-in bypass diode 208 shunted to solar cells. The spatial area of such a bypass diode can be adjusted depending on the amount of current protected, and/or depending on a selected sacrifice in forward bias.

[0022] Turning now to Figure 3, a cross-section view of one embodiment of a bypass diode is shown. As illustrated, bypass diode 302 can include first conductive region 312 of a first conductivity type disposed above substrate 310 of a solar cell. In one embodiment, the first conductivity type is P-type such that first conductive region 312 is P-type doped polysilicon. In other embodiments, the first conductivity type can be N-type doped polysilicon. In an embodiment in which the first conductivity type is P-type, the substrate can be doped with N-type dopant impurity atoms whereas in an embodiment in which the first conductivity type is N-type, the substrate can be doped with P-type dopant impurity atoms. In one embodiment, first conductive region 312 can be disposed on a thin dielectric layer, such as thin dielectric layer 316 disposed on the substrate.

[0023] In various embodiments, bypass diode 302 can include a second conductive region of a second conductivity type (opposite the first conductivity type) disposed above the first conductive region. As shown in Figure 3, the second conduction region can be second conductive region 345. In embodiments in which the first conductivity type is P-type, the second conductivity is N-type. Similarly, in embodiments in which the first conductivity type is N-type, the second conductivity type is P-type.

[0024] In one embodiment, bypass diode 302 can include a metal of the first conductivity type 360 disposed on the second conductive region and a metal of the second conductivity type 362 disposed on the first conductive region. Note that a metal of the first conductivity type may be the same type of metal (e.g., aluminum, copper, silver, etc.) of the second conductivity type. The term metal of a particular (first, second, etc.) conductivity type is used herein to describe that the metal corresponds to fingers of a particular conductivity type. For example, metal that is used for the P fingers of a solar cell is referred to as P metal or P-type metal. Thus, in the bypass diode of Figure 3, P-type metal is disposed on the N-type conductive region and N-type metal is disposed on the P-type conductive region. Note that in other portions of the solar cell that do not include a bypass diode, N-type metal contacts N-type conductive regions and P-type metal contacts P-type conductive regions to form the fingers of the solar cell.

[0025] As shown in Figure 3, in some embodiments, the metal of the second conductivity type 362 can be disposed through an opening in a dielectric layer, as shown in the opening

between dielectric regions 352 and 354. In one embodiment, dielectric regions 352, 354, and 314 can be an oxide layer, such as silicon dioxide. Also shown in Figure 3, in some embodiments, second conductive region 345 can be disposed through an opening in a dielectric layer, such as the opening between dielectric regions 314 and 352.

[0026] In various embodiments, bypass diode includes a thin dielectric region disposed directly between the first and second conductive regions. The thin dielectric region disposed directly between the first and second conductive regions can have a thickness approximately in the range of 10-20 Angstroms. In one embodiment, the thin dielectric region is a tunnel oxide.

[0027] In one embodiment, the thin dielectric region, such as thin dielectric region 332 can be disposed laterally directly between the first conductive region 312 and second conductive region 347 without an isolation trench disposed in the substrate between the first and second conductive regions. Avoiding using an isolation trench disposed in the substrate between the first and second conductive regions can avoid having to metallize over the trench and therefore avoid shunting in manufacturing.

[0028] In one embodiment, the thin dielectric region, such as thin dielectric region 330, can be disposed directly above first conductive region 312 with the second conductive region 345 being disposed directly above thin dielectric region 330. In one embodiment, bypass diode 302 can include both thin dielectric regions 330 and 332.

[0029] Turning now to Figure 4, a flow chart illustrating a method for forming a bypass diode is shown, according to some embodiments. In various embodiments, the method of Figure 4 can include additional (or fewer) blocks than illustrated. The method of Figure 4 is described in conjunction with cross-sectional sequential illustrations of various stages of the method shown at Figures 5-14. Note that some of the stages shown at Figures 5-14 are not necessarily part of the method for forming the bypass diode but are included for context.

[0030] At 402, a first conductive region of a first conductivity type can be formed on a first dielectric layer on a substrate of a solar cell, such as substrate 310 of Figure 5. Forming a first conductive region can include forming a p-type conductive region. Forming the p-type conductive region can include forming a p-type polysilicon region (e.g., by doping polysilicon with p-type impurities) or can include forming an amorphous silicon region, which can then be formed into the p-type conductive region by performing a thermal process.

[0031] As illustrated at 404, a second dielectric layer can be formed on the first conductive region. In one embodiment, the second dielectric layer can be a silicon dioxide layer.

[0032] Figure 6 illustrates an example result of blocks 402 and 404 with second dielectric layer 313 formed on first conductive region 312, which is formed on first dielectric layer 316 on substrate 310. Note that another dielectric layer 318 is illustrated in Figure 6, which can be

formed at the same time as first dielectric layer 316 or at a different time. In one embodiment, the other dielectric layer 318 is not formed at this stage of the method and instead, first dielectric layer 316 is formed without also forming other dielectric layer 318.

[0033] Figure 7 illustrates a portion of the second dielectric layer 313 and first conductive region 312 being removed. Various techniques can be used to perform the removal, such as laser ablation or masking, then removing by etching the unmasked portion.

[0034] Turning back to Figure 4, as shown at 406, a portion of the second dielectric layer can be removed and an opening in the second dielectric layer can be formed, as illustrated in Figure 8 by the opening between remaining portions 314 and 322 of the second dielectric layer. In one embodiment, the portion of the second dielectric layer can be removed by laser ablation and in some embodiments, can be performed without also removing a portion (or removing a very shallow portion) of the first conductive region below the ablated portion. For example, the laser may be configured (e.g., power, shape, pulse duration, and/or wavelength, etc.) such that it is transparent to or has little or no effect on the first conductive region but ablates the second dielectric layer portion. In various embodiments in which the removal of materials shown in Figures 7 and 8 are both performed by laser ablation, the removals can be performed in the same tool but with different laser configurations or can be done with different lasers such that varying depths of ablation can be achieved as illustrated.

[0035] In one embodiment, regions of the solar cell can be texturized as shown at Figure 9. Figure 9 illustrates etching to texturize regions 326, 328, and 324. Note that texturized region 324 is textured less than regions 326 and 328 due to etch-resistant properties of p-poly.

[0036] At 408, a second conductive region of a second conductivity type, as illustrated by second conduction region 340 of Figure 11, can be formed above a portion of the exposed first conductive region (e.g., through the opening in the dielectric layer). In an embodiment in which the first conductivity type is p-type, forming the second conductive region can include forming an n-type conductive region. For example, forming the n-type conductive region can include forming an n-type polysilicon region (e.g., by doping polysilicon with n-type impurities) or can include forming an amorphous silicon region, which can then be formed into the n-type conductive region. In one embodiment, the formed second conductive region has an approximate thickness of 500 Angstroms.

[0037] In one embodiment, before forming the second conductive region at block 408, a third dielectric layer can be formed, which can provide separation between the first and second conductive regions. As described herein, the third dielectric layer can be a thin dielectric layer (e.g., 15 Angstroms, 10-20 Angstroms, etc.) and can isolate the first and second conductive regions without using a trench.

[0038] In one embodiment, the third dielectric layer can be formed such that it is disposed laterally between the first and second conductive regions (e.g., as shown by dielectric layer 332 in Figure 10) and/or it can be formed such that it is disposed directly above the first conductive region (e.g., as shown by dielectric layer 330 in Figure 10) with the second conductive region being disposed directly above the third dielectric layer (e.g., providing vertical separation). Note that a thin dielectric layer 334 can also be formed on the texturized portion of substrate 310, also as shown in Figure 10. In various embodiments, depositing a tunnel oxide as the third dielectric layer can be conformal to the geometry of the back surface.

[0039] In various embodiments, the first dielectric layer can also be a thin dielectric layer, but may be a different thickness than the thin dielectric layer of the third dielectric layer. For example, the first dielectric layer can have a thickness approximately in the range of 5-50 Angstroms instead of the 10-20 Angstrom thickness of the third dielectric layer. The second dielectric layer can have a thickness approximately greater than 50 Angstroms.

[0040] In some embodiments, a tunnel oxide layer and doped polysilicon (e.g., n-poly doped polysilicon) can be formed on the front surface as shown in Figure 12. In various embodiments, the n-poly on both sides of the substrate can be annealed and nitride layer 342 can be deposited on the front surface as shown in Figure 13.

[0041] Referring again to Figure 4, as illustrated at 410, a portion of the second conductive region can be removed to form, or isolate, first and second portions of the second conductive region. In one embodiment, the portion of the second conductive region (e.g., the region between portions 345 and 347 as shown in Figure 14) can be removed by laser ablating that portion. Such laser ablation may be refer to as scribing and can include ablating the portion of the second conductive region without also ablating dielectric layer 322 under the second conductive region. In one embodiment, the scribing of the portion of the second conductive region can be performed by the same laser tool as other laser operations described herein but with the laser in a lower power setting (or different wavelength, shape, pulse duration, etc.). Or, the scribing can be performed with separate, lower power laser than is used for ablating multiple different layers at once.

[0042] At 412, metal of the second conductivity type can be coupled to the first conductive region and metal of the first conductivity type can be coupled to one of the portions (e.g., the first portion) of the second conductive region to form corresponding conductive connections. For example, in one embodiment, coupling metal of second conductivity type to the first conductive region can include coupling n-type metal to the p-type conductive region. And coupling metal of the first conductivity type can include coupling p-type metal to the one of the portions (e.g., first portion 345) of n-type conductive regions.

[0043] An example of the coupling of block 412 is illustrated in Figure 3. Note that in some embodiments, the method can include removing a portion of dielectric layer 322. The result of such removal is illustrated in Figure 3 by the region between dielectric layers 352 and 354. The region between dielectric layers 352 and 354 can permit second conductivity type metal 362 (e.g., n-type metal) to be coupled to the first conductive region (e.g., p-type conductive region). Also as shown in Figure 3, first conductivity type metal 360 (e.g., p-type metal) can be coupled to first portion 345 of the second conductive region (e.g., n-type conductive region).

[0044] In one embodiment, third dielectric layer 330 can be made more conductive, for example by electrical stress (e.g., conductive a high current or applying a high bias, such as 10V, for a short period of time) or thermal stress (e.g., by anneal, by laser, etc.). By making the third dielectric layer more conductive, the area of the solar cell used by a bypass diode or diodes can be reduced thereby allowing the resulting solar cell to produce more power.

[0045] The disclosed structures and techniques can provide protection for reverse bias events and for temperature suppression of hot spots at the cell level, which in turn, can enable hot spot testing to be removed from the module processing flow. In addition, the disclosed structures and techniques can avoid shunting in manufacturing without requiring metallization over an isolation trench.

[0046] Although specific embodiments have been described above, these embodiments are not intended to limit the scope of the present disclosure, even where only a single embodiment is described with respect to a particular feature. Examples of features provided in the disclosure are intended to be illustrative rather than restrictive unless stated otherwise. The above description is intended to cover such alternatives, modifications, and equivalents as would be apparent to a person skilled in the art having the benefit of this disclosure.

[0047] The scope of the present disclosure includes any feature or combination of features disclosed herein (either explicitly or implicitly), or any generalization thereof, whether or not it mitigates any or all of the problems addressed herein. Accordingly, new claims may be formulated during prosecution of this application (or an application claiming priority thereto) to any such combination of features. In particular, with reference to the appended claims, features from dependent claims may be combined with those of the independent claims and features from respective independent claims may be combined in any appropriate manner and not merely in the specific combinations enumerated in the appended claims.

[0048] In an embodiment, a method of fabricating a bypass diode for a solar cell involves forming a first conductive region of a first conductivity type on a first dielectric layer on a substrate of the solar cell, forming a second dielectric layer on the first conductive region,

removing a portion of the second dielectric layer, forming a second conductive region of a second conductivity type above a portion of the first conductive region exposed by the removed portion of the second dielectric layer, removing a portion of the second conductive region to separate the second conductive region into first and second portions of the second conductive region, and coupling metal of the second conductivity type to the first conductive region and metal of the first conductivity type to the first portion of the second conductive region.

[0049] In one embodiment, said forming the first conductive region includes forming a p-type conductive region, and said forming the second conductive region includes forming an n-type conductive region, wherein said coupling includes coupling n-metal to the p-type conductive region and p-metal to the first portion of the n-type conductive region.

[0050] In one embodiment, said removing a portion of the second conductive region includes laser ablating the portion of the second conductive region.

[0051] In one embodiment, the method further involves, prior to said forming the second conductive region, forming a third dielectric layer, wherein the third dielectric layer provides separation between the first and second conductive regions.

[0052] In one embodiment, said removing the portion of the second dielectric layer includes laser ablating the portion of the second dielectric layer without removing a portion of the first conductive region below the ablated portion.

[0053] In an embodiment, a method of fabricating a bypass diode for a solar cell involves forming an opening in a dielectric layer on a first conductive region, forming a second conductive region above the first conductive region through the opening in the dielectric layer, isolating a first portion of the second conductive region from a second portion of the second conductive region, and forming a conductive connection between the first conductive region and its corresponding opposite metal type and between the second portion of the second conductive region and its corresponding opposite metal type.

[0054] In one embodiment, said forming the opening in the dielectric layer is performed by laser ablation.

[0055] In one embodiment, said isolating the first from the second portion of the second conductive region includes laser ablating the second conductive region.

[0056] In one embodiment, said forming the conductive connection includes forming a conductive connection between an n-type conductive region and p-type metal and between a p-type conductive region and n-type metal.

[0057] In one embodiment, said forming the opening in the dielectric layer includes forming the opening in a silicon dioxide layer on the first conductive region, wherein the first conductive region is a p-type conductive region.

[0058] In one embodiment, the method further involves forming another dielectric layer before said forming the second conductive region wherein the other dielectric layer provides separation between the first and second conductive regions.

[0059] In one embodiment, forming the other dielectric layer provides a lateral separation between the first and second conductive regions.

[0060] In one embodiment, forming the other dielectric layer provides lateral and vertical separation between the first and second conductive regions.

[0061] In one embodiment, forming the second conductive region includes forming amorphous silicon above the first conductive region through the opening in the dielectric layer.

[0062] In one embodiment, said forming the second conductive region includes forming n-type polysilicon on the first conductive region. In an embodiment, a bypass diode for a solar cell includes a first conductive region of a first conductivity type disposed above a substrate of the solar cell, a second conductive region of a second conductivity type disposed above the first conductive region, and a thin dielectric region disposed directly between the first and second conductive regions.

[0063] In one embodiment, the thin dielectric region is disposed laterally directly between the first and second conductive regions without an isolation trench disposed in the substrate between the first and second conductive regions.

[0064] In one embodiment, the thin dielectric region is disposed directly above the first conductive region and wherein the second conductive region is disposed directly above the thin dielectric region.

[0065] In one embodiment, the thin dielectric region is a tunnel oxide.

[0066] In one embodiment, the bypass diode further includes a thin dielectric layer disposed on the substrate, and the first conductive region is disposed on the thin dielectric layer.

CLAIMS

What is claimed is:

1. A method of fabricating a bypass diode for a solar cell, the method comprising:
forming a first conductive region of a first conductivity type on a first dielectric layer on a substrate of the solar cell;
forming a second dielectric layer on the first conductive region;
removing a portion of the second dielectric layer;
forming a second conductive region of a second conductivity type above a portion of the first conductive region exposed by the removed portion of the second dielectric layer;
removing a portion of the second conductive region to separate the second conductive region into first and second portions of the second conductive region; and
coupling metal of the second conductivity type to the first conductive region and metal of the first conductivity type to the first portion of the second conductive region.
2. The method of claim 1, wherein said forming the first conductive region includes forming a p-type conductive region, and wherein said forming the second conductive region includes forming an n-type conductive region, wherein said coupling includes coupling n-metal to the p-type conductive region and p-metal to the first portion of the n-type conductive region.
3. The method of claim 1, wherein said removing the portion of the second conductive region includes laser ablating the portion of the second conductive region.
4. The method of claim 1; further comprising prior to said forming the second conductive region, forming a third dielectric layer, wherein the third dielectric layer provides separation between the first and second conductive regions.
5. The method of claim 1, wherein said removing the portion of the second dielectric layer includes laser ablating the portion of the second dielectric layer without removing a portion of the first conductive region below the ablated portion.

6. A method of fabricating a bypass diode for a solar cell, the method comprising:
forming an opening in a dielectric layer on a first conductive region;
forming a second conductive region above the first conductive region through the
opening in the dielectric layer;
isolating a first portion of the second conductive region from a second portion of the
second conductive region; and
forming a conductive connection between the first conductive region of a first
conductivity type and a metal of a second conductivity type, and between the
second portion of the second conductive region of the second conductivity type
and a metal of the first conductivity type .
7. The method of claim 6, wherein said forming the opening in the dielectric layer is
performed by laser ablation.
8. The method of claim 6, wherein said isolating the first from the second portion of the
second conductive region includes laser ablating the second conductive region.
9. The method of claim 6, wherein said forming the conductive connection includes forming
a conductive connection between an n-type conductive region and p-type metal and between a p-
type conductive region and n-type metal.
10. The method of claim 6, wherein said forming the opening in the dielectric layer includes
forming the opening in a silicon dioxide layer on the first conductive region, wherein the first
conductive region is a p-type conductive region.
11. The method of claim 6, further comprising forming another dielectric layer before said
forming the second conductive region wherein the other dielectric layer provides separation
between the first and second conductive regions.
12. The method of claim 11, wherein forming the other dielectric layer provides a lateral
separation between the first and second conductive regions.

13. The method of claim 11, wherein forming the other dielectric layer provides lateral and vertical separation between the first and second conductive regions.

14. The method of claim 6, wherein said forming the second conductive region includes forming amorphous silicon above the first conductive region through the opening in the dielectric layer.

15. The method of claim 6, wherein said forming the second conductive region includes forming n-type polysilicon on the first conductive region.

16. A bypass diode for a solar cell, the bypass diode comprising:
a first conductive region of a first conductivity type disposed on a first dielectric layer on a substrate of the solar cell;
a second dielectric layer disposed above the first conductive region, a portion of the second dielectric layer being removed;
a second conductive region of a second conductivity type disposed above a portion of the first conductive region exposed by the removed portion of the second dielectric layer; a portion of the second conductive region being removed to separate the second conductive region into first and second portions of the second conductive region;
a metal of the second conductivity type is coupled to the first conductive region and a metal of the first conductivity type is coupled to the first portion of the second conductive region; and
a thin dielectric region disposed directly between the first and second conductive regions.

17. The bypass diode of claim 16, wherein the thin dielectric region is disposed laterally directly between the first and second conductive regions without an isolation trench disposed in the substrate between the first and second conductive regions.

18. The bypass diode of claim 16, wherein the thin dielectric region is disposed directly above the first conductive region and wherein the second conductive region is disposed directly above the thin dielectric region.

19. The bypass diode of claim 16, wherein the thin dielectric region is a tunnel oxide.

20. The bypass diode of claim 16, further comprising:
a thin dielectric layer disposed on the substrate, wherein the first conductive region is
disposed on the thin dielectric layer.