

MEMBRANE COMPRISING SELF-ASSEMBLED BLOCK COPOLYMER AND PROCESS FOR PRODUCING THE SAME BY SPRAY COATING (Ic)


BACKGROUND OF THE INVENTION

[0001] Membranes, particularly nanoporous membranes, are known to have applications in a number of areas including filtration of biological fluids, removal of micropollutants, water softening, wastewater treatment, retention of dyes, preparation of ultrapure water in the electronics industry, and concentration of food, juice, or milk. Methods involving block copolymers, which self-assemble into nanostructures, have been proposed for preparing nanoporous membranes. While self-assembled structures are advantageous in that they produce membranes with uniform pore size and pore size distribution, challenges or difficulties remain with the proposed block copolymers and methods. For example, in some of these methods, a film is produced first from a block copolymer, which is then followed by the removal of one of the blocks of the block copolymer by employing a harsh chemical such as a strong acid or strong base.

[0002] The foregoing indicates that there is an unmet need for membranes made from block copolymers that are capable of self-assembling into nanostructures and for a method for producing nanoporous membranes from these block copolymers, which does not require a removal of one of the blocks after a nanostructure is formed.

BRIEF SUMMARY OF THE INVENTION

[0003] The invention provides a porous membrane comprising a diblock copolymer of the formula (I):



wherein:

R^1 is a C_1 - C_{22} alkyl group optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro, or a C_3 - C_{11} cycloalkyl group,

optionally substituted with a substituent selected from alkyl, halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro;

R^2 is a C_6 - C_{20} aryl group or a heteroaryl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro;

one of R^3 and R^4 is a C_6 - C_{14} aryl group, optionally substituted with a substituent selected from hydroxy, halo, amino, and nitro, and the other of R^3 and R^4 is a C_1 - C_{22} alkoxy group, optionally substituted with a substituent selected from carboxy, amino, mercapto, alkynyl, alkenyl, halo, azido, and heterocyclyl;

n and m are independently about 10 to about 2000.

[0004] The invention also provides a method for preparing the above membrane comprising:

- (i) dissolving the diblock copolymer in a solvent system to obtain a polymer solution;
- (ii) spray coating the polymer solution onto a substrate;
- (iii) annealing the coating obtained in (ii) in a vapor comprising a solvent or a mixture of solvents to obtain a self-assembled structure; and optionally
- (iv) annealing or soaking the self-assembled structure obtained in (iii) in a solvent or mixture of solvents to obtain a porous membrane.

[0005] The invention also provides composite membranes, for example, a composite membrane comprising at least two layers, the first layer being the porous membrane as described above and the second layer being a porous support.

[0006] The present invention takes advantage of the ability of the block copolymers having thermodynamically incompatible blocks to undergo phase separation and self-assemble into structures, thereby creating porous membranes having uniform porosity.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0007] Fig. 1 depicts the overlaid traces of the Multi-angle Laser Light Scattering (MALS) gel permeation chromatograms (GPC) of a homopolymer 1 (a precursor to the diblock copolymer) and a diblock copolymer 2 in accordance with an embodiment of the invention.


[0008] Fig. 2A depicts the AFM topographic image of the height of the surface of the thin film after spray coating but without annealing and Fig. 2B depicts the AFM topographic image of the phase of the surface of the thin film.

[0009] Fig. 3A depicts AFM topographic image of the height of the surface of the thin film after annealing, Fig. 3B depicts the AFM topographic image of the phase of the surface of the membrane, and Fig. 3C depicts the line profile of extracted from Fig. 3A.

[0010] Fig. 4A depicts the AFM image of the cross-section of a thin film spray coated on a glass surface. Fig. 4B depicts a higher magnification AFM image of the thin film depicted in Fig. 4A.

DETAILED DESCRIPTION OF THE INVENTION

[0011] In an embodiment, the invention provides a porous membrane comprising a diblock copolymer of the formula (I):



wherein:


R^1 is a C_1 - C_{22} alkyl group optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro, or a C_3 - C_{11} cycloalkyl group, optionally substituted with a substituent selected from alkyl, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro;

R^2 is a C_6 - C_{20} aryl group or a heteroaryl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro;

one of R^3 and R^4 is a C_6 - C_{14} aryl group, optionally substituted with a substituent selected from hydroxy, halo, amino, and nitro, and the other of R^3 and R^4 is a C_1 - C_{22} alkoxy group, optionally substituted with a substituent selected from carboxy, amino, mercapto, alkynyl, alkenyl, halo, azido, and heterocyclyl;

n and m are independently about 10 to about 2000.

[0012] In an embodiment, the invention provides a method for preparing a porous membrane comprising a diblock copolymer of the formula (I):



wherein:

R^1 is a C_1 - C_{22} alkyl group optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro, or a C_3 - C_{11} cycloalkyl group, optionally substituted with a substituent selected from alkyl, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro;

R^2 is a C_6 - C_{20} aryl group or a heteroaryl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro;


one of R^3 and R^4 is a C_6 - C_{14} aryl group, optionally substituted with a substituent selected from hydroxy, halo, amino, and nitro, and the other of R^3 and R^4 is a C_1 - C_{22} alkoxy group, optionally substituted with a substituent selected from carboxy, amino, mercapto, alkynyl, alkenyl, halo, azido, and heterocyclyl;

n and m are independently about 10 to about 2000;

the method comprising:

- (i) dissolving the diblock copolymer in a solvent system to obtain a polymer solution;
- (ii) spray coating the polymer solution onto a substrate;
- (iii) annealing the coating obtained in (ii) in a vapor comprising a solvent or a mixture of solvents to obtain a self-assembled structure; and optionally
- (iv) annealing or soaking the self-assembled structure obtained in (iii) in a solvent or mixture of solvents to obtain a porous membrane.

[0013] In accordance with an embodiment, the above diblock copolymer is of the formula (II), wherein the monomers are *exo* isomers:



[0014] In any of the embodiments above, R^1 is a C_6 - C_{20} alkyl group optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro, or a C_3 - C_{11} cycloalkyl group, optionally substituted with a substituent selected from alkyl, halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro.

[0015] In an embodiment, R^1 is a C_{10} - C_{18} alkyl group, optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro.

[0016] In a particular embodiment, R^1 is a C_{16} alkyl group.

[0017] In any of the embodiments above, R^2 is a C_6 - C_{10} aryl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro.

[0018] In an embodiment, R^2 is a phenyl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxy carbonyl, amido, and nitro;

[0019] In any of the embodiments above, R^3 is a C_6 - C_{14} aryl group, optionally substituted with a substituent selected from hydroxy, halo, amino, and nitro and R^4 is a C_1 - C_{22} alkoxy group, optionally substituted with a substituent selected from carboxy, amino, mercapto, alkynyl, alkenyl, halo, azido, and heterocyclyl.

[0020] In an embodiment, R^3 is phenyl, optionally substituted with a substituent selected from hydroxy, halo, amino, and nitro and R^4 is a C_1 - C_6 alkoxy group, optionally substituted with a substituent selected from carboxy, amino, mercapto, alkynyl, alkenyl, halo, azido, and heterocyclyl.

[0021] In an embodiment, R^3 is provided by the ROMP catalyst employed for the polymerization of the monomers.

[0022] In an embodiment, R^4 is a group provided by the vinyl ether compound employed for terminating the polymerization.

[0023] In accordance with the invention, the term “aryl” refers to a mono, bi, or tricyclic carbocyclic ring system having one, two, or three aromatic rings, for example, phenyl, naphthyl, anthracenyl, or biphenyl. The term “aryl” refers to an unsubstituted or substituted

aromatic carbocyclic moiety, as commonly understood in the art, and includes monocyclic and polycyclic aromatics such as, for example, phenyl, biphenyl, naphthyl, anthracenyl, pyrenyl, and the like. An aryl moiety generally contains from, for example, 6 to 30 carbon atoms, preferably from 6 to 18 carbon atoms, more preferably from 6 to 14 carbon atoms and most preferably from 6 to 10 carbon atoms. It is understood that the term aryl includes carbocyclic moieties that are planar and comprise $4n+2$ π electrons, according to Hückel's Rule, wherein $n = 1, 2, \text{ or } 3$.

[0024] In accordance with the invention, the term “heteroaryl” refers to a cyclic aromatic radical having from five to ten ring atoms of which at least one atom is O, S, or N, and the remaining atoms are carbon. Examples of heteroaryl radicals include pyridyl, pyrazinyl, pyrimidinyl, pyrrolyl, pyrazolyl, imidazolyl, thiazolyl, oxazolyl, isooxazolyl, thiadiazolyl, oxadiazolyl, thiophenyl, furanyl, quinolinyl, and isoquinolinyl. The term “heteroaryl” as used herein, means a monocyclic heteroaryl or a bicyclic heteroaryl. The monocyclic heteroaryl is a five- or six-membered ring. The five-membered ring consists of two double bonds and one sulfur, nitrogen or oxygen atom. Alternatively, the five-membered ring has two double bonds and one, two, three or four nitrogen atoms and optionally one additional heteroatom selected from oxygen or sulfur, and the others carbon atoms. The six-membered ring consists of three double bonds, one, two, three or four nitrogen atoms, and the others carbon atoms. The bicyclic heteroaryl consists of a monocyclic heteroaryl fused to a phenyl, or a monocyclic heteroaryl fused to a monocyclic cycloalkyl, or a monocyclic heteroaryl fused to a monocyclic cycloalkenyl, or a monocyclic heteroaryl fused to a monocyclic heteroaryl. The monocyclic and the bicyclic heteroaryl are connected to the parent molecular moiety through any substitutable atom contained within the monocyclic or the bicyclic heteroaryl. The monocyclic and bicyclic heteroaryl groups of the present invention can be substituted or unsubstituted. In addition, the nitrogen heteroatom may or may not be quaternized, and may or may not be oxidized to the N-oxide. Also, the nitrogen containing rings may or may not be N-protected. Representative examples of monocyclic heteroaryl include, but are not limited to, furanyl, imidazolyl, isoxazolyl, isothiazolyl, oxadiazolyl, oxazolyl, pyridinyl, pyridine-N-oxide, pyridazinyl, pyrimidinyl, pyrazinyl, pyrazolyl, pyrrolyl, tetrazolyl, thiadiazolyl, thiazolyl, thienyl, triazolyl, and triazinyl. Representative examples of bicyclic heteroaryl groups include, but not limited to, benzothienyl, benzoxazolyl, benzimidazolyl, benzoxadiazolyl, 6,7-dihydro-1,3-benzothiazolyl, imidazo[1,2-a]pyridinyl, indazolyl, 1H-indazol-3-yl, indolyl, isoindolyl, isoquinolinyl,

naphthyridinyl, pyridoimidazolyl, quinolinyl, quinolin-8-yl, and 5,6,7,8-tetrahydroquinolin-5-yl.

[0025] The “alkyl” group could be linear or branched. In accordance with an embodiment, the alkyl group is preferably a C₁-C₂₂ alkyl. Examples of alkyl group include methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, n-pentyl, isopentyl, n-hexyl, hexadecyl, and the like. This definition also applies wherever “alkyl” occurs such as in hydroxyalkyl, monohalo alkyl, dihalo alkyl, and trihalo alkyl. The C₁-C₂₂ alkyl group can also be further substituted with a cycloalkyl group, e.g., a C₃-C₁₁ cycloalkyl group.

[0026] The “cycloalkyl” group can be monocyclic or bicyclic. Examples of monocyclic cycloalkyl groups include cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl, and cyclooctyl. Examples of bicyclic cycloalkyl groups include those with one common ring carbon atom such as spirooctane, spirononane, spirodecane, and spiroundecane, and those with two common ring carbon atoms such as bicyclooctane, bicyclononane, bicyclodecane, and bicycloundecane. Any of the cycloalkyl groups could be optionally substituted with one or more alkyl groups, e.g., C₁-C₆ alkyl groups.

[0027] In accordance with an embodiment, the “alkoxy” group is preferably a C₁-C₂₂ alkoxy. Examples of alkoxy group include methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec-butoxy, isobutoxy, tert-butoxy, n-pentoxy, isopentoxy, n-hexoxy, hexadecyloxy, and the like.

[0028] The term “halo” refers to a halogen selected from the group consisting of fluorine, chlorine, bromine, and iodine, preferably chlorine or bromine.

[0029] The term “heterocycle” or “heterocyclic” as used herein, means a monocyclic heterocycle or a bicyclic heterocycle. The monocyclic heterocycle is a three-, four-, five-, six- or seven-membered ring containing at least one heteroatom independently selected from the group consisting of O, N, N(H) and S. The three- or four-membered ring contains zero or one double bond and a heteroatom selected from the group consisting of O, N, N(H) and S. The five-membered ring contains zero or one double bond, and one, two or three heteroatoms selected from the group consisting of O, N, N(H) and S. The six-membered ring contains zero, one or two double bonds and one, two or three heteroatoms selected from the group consisting of O, N, N(H) and S. The seven-membered ring contains zero, one, two, or three double bonds and one, two or three heteroatoms selected from the group consisting of O, N, N(H) and S. The monocyclic heterocycle can be unsubstituted or substituted and is connected to the parent molecular moiety through any substitutable carbon atom or any

substitutable nitrogen atom contained within the monocyclic heterocycle. Representative examples of monocyclic heterocycle include, but are not limited to, azetidiny, azepanyl, aziridiny, diazepanyl, [1,4]diazepan-1-yl, 1,3-dioxanyl, 1,3-dioxolanyl, 1,3-dithiolanyl, 1,3-dithianyl, homomorpholinyl, homopiperazinyl, imidazoliny, imidazolidiny, isothiazoliny, isothiazolidiny, isoxazoliny, isoxazolidiny, morpholinyl, oxadiazoliny, oxadiazolidiny, oxazohnyl, oxazolidiny, piperazinyl, piperidiny, pyranyl, pyrazoliny, pyrazolidiny, pyrroliny, pyrrolidiny, tetrahydrofuranyl, tetrahydropyranyl, tetrahydrothienyl, thiadiazoliny, thiadiazolidiny, thiazoliny, thiazolidiny, thiomorpholinyl, 1,1-dioxidothiomorpholinyl (thiomorpholine sulfone), thiopyranyl, and trithianyl. The bicyclic heterocycle is a monocyclic heterocycle fused to a phenyl group, or a monocyclic heterocycle fused to a monocyclic cycloalkyl, or a monocyclic heterocycle fused to a monocyclic cycloalkenyl, a monocyclic heterocycle fused to a monocyclic heterocycle, or a monocyclic heterocycle fused to a monocyclic heteroaryl. The bicyclic heterocycle is connected to the parent molecular moiety through any substitutable carbon atom or any substitutable nitrogen atom contained within the bicyclic heterocycle and can be unsubstituted or substituted. Representative examples of bicyclic heterocycle include, but are not limited to, benzodioxiny, benzopyranyl, thiochromanyl, 2,3-dihydroindolyl, indoliziny, pyranopyridiny, 1,2,3,4-tetrahydroisoquinoliny, 1,2,3,4-tetrahydroquinoliny, thiopyranopyridiny, 2-oxo-1,3-benzoxazolyl, 3-oxo-benzoxazinyl, 3-azabicyclo[3.2.0]heptyl, 3,6-diazabicyclo[3.2.0]heptyl, octahydrocyclopenta[c]pyrrolyl, hexahydro-1H-furo[3,4-c]pyrrolyl, octahydropyrrolo[3,4-c]pyrrolyl, 2,3-dihydrobenzofuran-7-yl, 2,3-dihydrobenzofuran-3-yl, and 3,4-dihydro-2H-chromen-4-yl. The monocyclic or bicyclic heterocycles as defined herein may have two of the non-adjacent carbon atoms connected by a heteroatom selected from N, N(H), O or S, or an alkylene bridge of between one and three additional carbon atoms. Representative examples of monocyclic or bicyclic heterocycles that contain such connection between two non-adjacent carbon atoms include, but not limited to, 2-azabicyclo[2.2.2]octyl, 2-oxa-5-azabicyclo[2.2.2]octyl, 2,5-diazabicyclo[2.2.2]octyl, 2-azabicyclo[2.2.1]heptyl, 2-oxa-5-azabicyclo[2.2.1]heptyl, 2,5-diazabicyclo[2.2.1]heptyl, 2-azabicyclo[2.1.1]hexyl, 5-azabicyclo[2.1.1]hexyl, 3-azabicyclo[3.1.1]heptyl, 6-oxa-3-azabicyclo[3.1.1]heptyl, 8-azabicyclo[3.2.1]octyl, 3-oxa-8-azabicyclo[3.2.1]octyl, 1,4-diazabicyclo[3.2.2]nonyl, 1,4-diazatricyclo[4.3.1.1 3,8]undecyl, 3,10-diazabicyclo[4.3.1]decyl, or 8-oxa-3-azabicyclo[3.2.1]octyl, octahydro-1H-4,7-methanoisoindolyl, and octahydro-1H-4,7-epoxyisoindolyl. The nitrogen heteroatom may or

may not be quaternized, and may or may not be oxidized to the N-oxide. In addition, the nitrogen containing heterocyclic rings may or may not be N-protected.

[0030] Examples of heterocyclyl groups include pyridyl, piperidinyl, piperazinyl, pyrazinyl, pyrrolyl, pyranyl, tetrahydropyranyl, tetrahydrothiopyranyl, pyrrolidinyl, furanyl, tetrahydrofuranlyl, thiophenyl, tetrahydrothiophenyl, purinyl, pyrimidinyl, thiazolyl, thiazolidinyl, thiazolinyl, oxazolyl, triazolyl, tetrazolyl, tetrazinyl, benzoxazolyl, morpholinyl, thiophosphorolyl, quinolinyl, and isoquinolinyl.

[0031] Five-membered unsaturated heterocyclics with and without benzo: furanyl, thiophenyl, pyrrolyl, pyrazolyl, pyrazolinyl, imidazolyl, imidazolinyl, dithiazolyl, furazanyl, 1,2,3-triazolyl, tetrazolyl, 1,2,4-triazolyl, oxadiazolyl, thiadiazolyl, isoxazolyl, isoxazolinyl, oxazolyl, oxazolinyl, phospholyl, isothiazolyl, thiazolyl, thiazolinyl, isothiazolyl, isothiazolidinyl, benzofuranlyl, benzothiophenyl, indolyl, benzimidazolyl, benzoxazolinyl, and benzothiazolinyl.

[0032] Whenever a range of the number of atoms in a structure is indicated (e.g., a C₁₋₂₂, a C₁₋₁₂, C₁₋₈, C₁₋₆, or C₁₋₄ alkyl, alkoxy, etc.), it is specifically contemplated that any sub-range or individual number of carbon atoms falling within the indicated range also can be used. Thus, for instance, the recitation of a range of 1-22 carbon atoms (e.g., C_{1-C22}), 1-20 carbon atoms (e.g., C_{1-C20}), 1-18 carbon atoms (e.g., C_{1-C20}), 1-16 carbon atoms (e.g., C_{1-C16}), 1-14 carbon atoms (e.g., C_{1-C14}), 1-12 carbon atoms (e.g., C_{1-C12}), 1-10 carbon atoms (e.g., C_{1-C10}), 1-8 carbon atoms (e.g., C_{1-C8}), 1-6 carbon atoms (e.g., C_{1-C6}), 1-4 carbon atoms (e.g., C_{1-C4}), 1-3 carbon atoms (e.g., C_{1-C3}), or 2-8 carbon atoms (e.g., C_{2-C8}) as used with respect to any chemical group (e.g., alkyl, alkoxy, alkylamino, etc.) referenced herein encompasses and specifically describes 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, or 22 carbon atoms, as appropriate, as well as any sub-range thereof, e.g., 1-2 carbon atoms, 1-3 carbon atoms, 1-4 carbon atoms, 1-5 carbon atoms, 1-6 carbon atoms, 1-7 carbon atoms, 1-8 carbon atoms, 1-9 carbon atoms, 1-10 carbon atoms, 1-11 carbon atoms, 1-12 carbon atoms, 1-13 carbon atoms, 1-14 carbon atoms, 1-15 carbon atoms, 1-16 carbon atoms, 1-17 carbon atoms, 1-18 carbon atoms, 1-19 carbon atoms, 1-20 carbon atoms, 1-21 carbon atoms, and 1-22 carbon atoms, and anything in between such as 2-3 carbon atoms, 2-4 carbon atoms, 2-5 carbon atoms, 2-6 carbon atoms, 2-7 carbon atoms, 2-8 carbon atoms, 2-9 carbon atoms, 2-10 carbon atoms, 2-11 carbon atoms, 2-12 carbon atoms, 2-12 carbon atoms, 2-13 carbon atoms, 2-14 carbon atoms, 2-15 carbon atoms, 2-16 carbon atoms, 2-17 carbon atoms, 2-18 carbon atoms, 2-19 carbon atoms, 2-20 carbon atoms, 2-21 carbon atoms, and 2-22 carbon

atoms, 3-4 carbon atoms, 3-5 carbon atoms, 3-6 carbon atoms, 3-7 carbon atoms, 3-8 carbon atoms, 3-9 carbon atoms, 3-10 carbon atoms, 3-11 carbon atoms, 3-12 carbon atoms, 3-13 carbon atoms, 3-14 carbon atoms, 3-15 carbon atoms, 3-16 carbon atoms, 3-17 carbon atoms, 3-18 carbon atoms, 3-19 carbon atoms, 3-20 carbon atoms, 3-21 carbon atoms, and 3-22 carbon atoms, and 4-5 carbon atoms, 4-6 carbon atoms, 4-7 carbon atoms, 4-8 carbon atoms, 4-9 carbon atoms, 4-10 carbon atoms, 4-11 carbon atoms, 4-12 carbon atoms, 4-13 carbon atoms, 4-14 carbon atoms, 4-15 carbon atoms, 4-16 carbon atoms, 4-17 carbon atoms, 4-18 carbon atoms, 4-19 carbon atoms, 4-20 carbon atoms, 4-21 carbon atoms, 4-22 carbon atoms, etc., as appropriate.

[0033] In the above embodiments, “n” and “m” represent the average degree of polymerization of the respective monomers.

[0034] In accordance with embodiments of the invention, n is about 10 to about 1000, about 10 to about 500, about 10 to about 250, about 20 to about 1000, about 20 to about 500, about 20 to about 250, about 30 to about 1000, about 30 to about 500, about 30 to about 250, about 40 to about 1000, about 40 to about 500, about 40 to about 250, about 50 to about 1000, about 50 to about 500, about 50 to about 250, about 60 to about 1000, about 60 to about 500, or about 60 to about 250.

[0035] In any of the above embodiments, m is about 50 to about 2000, about 50 to about 1500, about 50 to about 1000, about 100 to about 2000, about 100 to about 1500, about 100 to about 1000, about 150 to about 2000, about 150 to about 1500, about 150 to about 1000, about 200 to about 2000, about 200 to about 1500, or about 200 to about 1000.

[0036] In any of the above embodiments, n is typically about 10 to about 200, preferably about 20 to about 190, more preferably about 30 to about 140, and even more preferably 105.

[0037] In any of the above embodiments of the diblock copolymer, m is typically about 50 to about 2000, preferably about 675 to about 1525, more preferably about 675 to about 1120, and even more preferably 870.

[0038] In an embodiment, n is about 10 to about 200 and m is about 80 to about 160.

[0039] The diblock copolymer can have any suitable total molecular weight, for example, a number average molecular weight (M_n) of from about 50 kDa to about 1000 kDa; in certain embodiments, the diblock copolymer has an M_n of from about 100 kDa to about 600 kDa; in certain other embodiments, the diblock copolymer has an M_n of from about 180 kDa to about 500 kDa; and in further embodiments, the diblock copolymer has an M_n of from about 195

kDa to about 441 kDa. In certain embodiments, the diblock copolymer has an M_n of from about 250 kDa to 500 kDa.

[0040] The double bonds in the diblock copolymer can have any suitable orientation, *cis*, *trans*, and the *cis* and the *trans* forms can be distributed in a random manner.

[0041] The diblock copolymer may self-assemble into any suitable morphology, for example, but not limited to, cylindrical morphology, lamellar morphology, or double gyroid morphology. The type of structure into which the copolymers self-assemble would depend, among others, on the volume fraction of the two blocks in the block copolymer as well as the nature of the solvent system.

[0042] For example, at a polymer volume fraction ratio range ($f_A:f_B$) of the two monomers of 37-50:63-50, formation of a lamellar morphology involving a stack of layers of equivalent domain size is favored, at a volume fraction ratio range of 15-70:85-30, formation of a cylindrical morphology where the minor polymer component forms cylinders in a matrix of major polymer block component is favored, and at a volume fraction ratio range of 7-15:83-85, formation of body centered cubic phase where the minor polymer component forms spheres in a matrix of the major polymer block component is favored. At a volume fraction ratio range of 33-37:67-33, formation of a double gyroid morphology is favored.

[0043] Cylindrical morphology includes a phase domain morphology having discrete tubular or cylindrical shapes. The tubular or cylindrical shapes may be hexagonally packed on a hexagonal lattice. In embodiments, the cylindrical domain size is from about 5 nm to about 100 nm.

[0044] Lamellar morphology includes a phase domain morphology having layers of alternating compositions that are generally oriented parallel with respect to one another. In embodiments, the lamellar domain size is from about 5 nm to about 100 nm.


[0045] The double gyroid morphology comprises two interpenetrating continuous network. In embodiments, the double gyroid domain size is from about 5 nm to about 100 nm.

[0046] In an embodiment, the polymerized second monomer (bearing R^2) and the polymerized first monomer (bearing R^1) are present in the diblock copolymer in any suitable volume fraction. For example, the % volume fraction of the first monomer to that of the second monomer can be in the range of about 15: about 85 to about 30: about 70, preferably in the range of about 19: about 81 to about 25: about 75, and more preferably about 20: about


80. In an embodiment, the volume fraction of the second monomer is about 80%, and the mass fraction is about 83%, of the total polymer.

[0047] In an embodiment, the polymer volume fraction of the second monomer to that of the first monomer is about 2.3 to about 5.6:1, which favors the formation of a cylindrical morphology. In a preferred embodiment, the polymer volume fraction of the second monomer to that of the first monomer is about 4:1.

[0048] In a specific embodiment, the membrane comprises a diblock copolymer of formula (I) has the following structure, in particular, wherein n is 105 and m is 870:




[0049] In an embodiment, the membrane comprises the diblock copolymer of formula (I) has the following structure where the monomers are exo isomers, in particular, wherein n is 105 and m is 870:



[0050] The diblock copolymers described above can be prepared by a method comprising:

(i) polymerizing one of the two monomers of the formulas:




with a ring opening metathesis polymerization (ROMP) catalyst to obtain a ring-opened polymer having a living chain end;


(ii) polymerizing the other of the two monomers on the living end of the ring-opened polymer obtained in (i) to obtain a diblock copolymer having a living end; and

(iii) terminating the living end of the diblock copolymer obtained in (ii) with an optionally substituted alkyl vinyl ether.

[0051] In the above method, the monomer that is first polymerized is of the formula:




[0052] After the polymerization of the above monomer, the second monomer that is polymerized thereon is a monomer of the formula:




[0053] The first monomer and the second monomer can be in an exo or endo stereochemical configuration. In an embodiment, the first and second monomers are of the exo configuration, e.g., a monomer having the exo isomer at 98% or higher.

[0054] In the first and second monomers, R^1 and R^2 are the same as described above for the diblock copolymer of formula (I). The first and second monomers are (oxa)norbornene (di)carboxylic imide derived monomers. The monomers can be prepared by any suitable method, for example, starting from maleimide and furan via a Diels-Alder reaction, illustrated below:




[0055] The first monomer can be synthesized via Mitsunobu Coupling reaction, as illustrated below:




[0056] Alternatively, the first monomer can be synthesized by the reaction of exo-7-oxanorbornene-5,6-dicarboxyanhydride with hexadecylamine or N-hexadecyl-maleimide reaction with furan via a Diels-Alder reaction.


[0057] The second monomer can be synthesized via a Diels-Alder reaction between N-phenyl maleimide and furan in acetonitrile, as illustrated below.




[0058] The polymerization of the monomers is carried out by ring-opening olefin metathesis polymerization (ROMP), in which a cyclic olefin monomer is polymerized or copolymerized by ring-opening of the cyclic olefin monomer. Typically, a transition metal catalyst containing a carbene ligand mediates the metathesis reaction.


[0059] Any suitable ROMP catalyst can be used, for example, Grubbs' first, second, and third generation catalysts, Umicore, Hoveyda-Grubbs, Schrock, and Schrock-Hoveyda catalysts can be employed. Examples of such catalysts include the following:








[0060] In an embodiment, Grubbs' third generation catalysts are particularly suitable due to their advantages such as stability in air, tolerance to multiple functional groups, and/or fast polymerization initiation and propagation rates. In addition, with the Grubbs' third generation catalysts, the end groups can be engineered to accommodate any compatible groups, and the catalyst can be recycled readily. A preferred example of such a catalyst is:



[0061] The above third generation Grubbs catalyst (G3) may be obtained commercially or prepared from a Grubbs second generation catalyst (G2) as follows:



[0062] The first monomer and the second monomer are polymerized sequentially to obtain the diblock copolymer. Any of the two monomers can be polymerized first. For example, the first monomer can be polymerized first, followed by the second monomer. Alternatively, the second monomer can be polymerized first, followed by the first monomer.

[0063] Typically, the monomers have a chemical purity of at least 95%, preferably 99% or greater, and more preferably 99.9% or greater. It is preferred that the monomers are free of impurities that will interfere with the polymerization, e.g., impurities that will affect the ROMP catalyst. Examples of such impurities include amines, thiols (mercaptans), acids, phosphines, and N-substituted maleimides.

[0064] The polymerization of the monomers is conducted in a suitable solvent, for example, solvents generally used for conducting ROMP polymerizations. Examples of suitable solvents include aromatic hydrocarbons such as benzene, toluene, and xylene, aliphatic hydrocarbons such as n-pentane, hexane, and heptane, alicyclic hydrocarbons such as cyclohexane, and halogenated hydrocarbons such as dichloromethane, dichloroethane, dichloroethylene, tetrachloroethane, chlorobenzene, dichlorobenzene, and trichlorobenzene, as well as mixtures thereof.

[0065] The monomer concentration can be in the range of 1 to 50 wt%, preferably 2 to 45 wt%, and more preferably 3 to 40 wt %.

[0066] The polymerization can be carried out at any suitable temperature, for example, from -20 to +100 °C, preferably 10 to 80 °C.

[0067] The polymerization can be carried out for any period of time suitable to obtain the appropriate chain length of each of the blocks, which can be from about 1 minute to 100 hours.

[0068] The amount of catalyst can be chosen in any suitable amount. For example, the molar ratio of the catalyst to the monomer can be about 1:10 to about 1:1000, preferably

about 1:50 to 1:500, and more preferably about 1:100 to about 1:200. For example, the molar ratio of the catalyst to the monomer could be 1:n and 1:m, where n and m are the average degrees of polymerization.

[0069] After the polymerization of the two monomers, the chain end of the diblock copolymer is terminated by adding an optionally substituted alkyl vinyl ether to the polymerization mixture.

[0070] The diblock copolymer can be isolated by suitable techniques such as precipitation with a nonsolvent.

[0071] The homopolymer formed during the preparation of the diblock copolymer and the diblock copolymer of the invention can be characterized for its molecular weight and molecular weight distribution by any known techniques. For example, a MALS-GPC technique can be employed. The technique uses a mobile phase to elute, via a high pressure pump, a polymer solution through a bank of columns packed with a stationary phase. The stationary phase separates the polymer sample according to the chain size followed by detecting the polymer by three different detectors. A series of detectors can be employed, e.g., an Ultraviolet detector (UV-detector), followed by a multi-angle laser light scattering detector (MALS-detector), which in turn, is followed by a refractive index detector (RI-detector) in a row. The UV-detector measures the polymer light absorption at 254 nm wavelength; the MALS-detector measures the scattered light from polymer chains relative to mobile phase.

[0072] The diblock copolymers of the invention are preferably highly monodisperse. For example, the copolymers have an M_w/M_n of 1.01 to 1.2, preferably 1.05 to 1.10.

[0073] The present invention provides a porous membrane comprising a diblock copolymer described above.

[0074] In an embodiment, the porous membrane is prepared by a spray coating process.

[0075] To prepare the membrane, the diblock copolymer is first dissolved in a suitable solvent or solvent system to obtain a polymer solution. The polymer solution can be prepared by any suitable method known to those skilled in the art. The diblock copolymer is added to the solvent system and stirred until a homogeneous solution is obtained. If desired, the solution can be stirred for an extended time to allow the diblock copolymer to assume its thermodynamically favorable structure in the solution. The diblock copolymer is dissolved in a good solvent or a mixture containing good solvents.

[0076] Embodiments of a suitable solvent system include a solvent or a mixture of solvents selected from halogenated hydrocarbons, ethers, amides, and sulfoxides. In an embodiment, the solvent system includes a volatile solvent, for example, a solvent having a boiling point less than 100 °C.

[0077] In the above embodiments, where a mixture of solvents is used as the solvent system, the mixture can include any suitable ratio of the solvents, for example, in a binary solvent mixture, either of the solvents can be present in a volume or mass ratio of 80/20, 75/25, 70/30, 65/35, 60/40, 55/45, or 50/50, or any ratio therebetween. In a ternary solvent system, any of the three solvents can be present in any suitable ratio, for example, a volume or mass ratio of 80/10/10, 75/15/10, 70/20/10, 65/25/10, 60/30/10, 55/25/30, 40/40/20, or 30/30/40 or any ratio therebetween.

[0078] The polymer solution can contain any suitable amount of the diblock copolymer. In accordance with an embodiment, the polymer solution contains about 2 to about 10% or more, preferably about 3 to about 8%, and more preferably about 4 to about 6% by weight of the diblock copolymer. In an example, the polymer solution contains about 5% by weight of the diblock copolymer. The polymer concentration can control the thickness of the film, and hence the thickness of the membrane obtained. The polymer concentration can also control the porosity of the membrane, with high concentrations producing less porous membrane.

[0079] In accordance with embodiments, the polymer solution contains DMF and THF at a mass ratio of about 60:40.

[0080] The polymer solution is sprayed on a substrate such as glass plates, plastic films, woven or nonwoven fabrics, silicon wafer, or metal plates. Examples of fabrics include polyethylene, polypropylene, polyester, and nylon fabrics. The substrates can be porous or nonporous. A porous substrate can be soaked in a nonsolvent or imbibed with a water soluble polymer such as polyvinyl alcohol or polyethylene glycol. The solution containing the diblock copolymer can be sprayed on to the thus prepared porous substrate.

[0081] The substrate surface has an influence on the resulting morphology orientation, and the orientation or morphology outcome is determined based on the thermodynamic interaction between the substrate and each block within the diblock. If the substrate surface has favorable interaction with one of the two blocks, the diblock copolymer will self-assemble in such a way that it maximizes the interaction by spreading and exposing the block that it has favorable interaction with. For example, in the case of cylinder morphology the cylinder will interface with the substrate surface in which the cylinder will be parallel to the

surface if the substrate has higher affinity to one block than the other. If the substrate surface has neutral or little affinity toward either block, the cylinders will be aligned normal to the substrate.

[0082] In accordance with an embodiment of the invention, the polymer solution is atomized during the spraying process. Any suitable spraying process can be used. The atomization can be airless or pressure activated, which involves forcing the coating liquid through a small diameter nozzle under high pressure. The fluid pressure can be between about 5 and about 35 MPa (about 700 to about 5000 psi), and fluid flow rates can be between about 150 to about 1500 cm³/min. A suitable pump is designed to develop such pressures, which can be driven mechanically, electrically, pneumatically, or hydraulically. The nozzle apertures can have diameters in the range of about 0.2 to about 2.0 mm. As the fluid is forced through the nozzle, it accelerates to a high velocity and leaves the nozzle in a thin sheet or jet of liquid in the relatively motionless ambient air, producing a shear force between the fluid and the air. The fluid is atomized by turbulent or aerodynamic disintegration. The most common nozzles produce a long, narrow fan-shaped pattern of various sizes; some produce a solid hollow cone. The airless atomization can be assisted with a small amount of compressed air at about 35 to about 170 kPa (about 5 to about 25 psi). The air assists in obtaining improved atomization at lower fluid pressures. In an embodiment, the coating solution can be mixed with a supercritical fluid, which tends to reduce the volatile organic compound emission.

[0083] Alternatively, the polymer solution can be electrostatically atomized or atomized in a bell (cup) or disk that rotates at a speed of about 10,000 to about 40,000 rpm.

[0084] The film can be of any suitable thickness, for example, a thickness of about 10 to about 1000 nm, typically about 100 to about 500 nm.

[0085] The polymer solution is spray coated at any suitable temperature, for example, at about 10 °C to about 40 °C, preferably about 15 °C to about 30 °C, and more preferably about 20 °C to about 25 °C.

[0086] The substrate can be stationary or moving. In an embodiment, the substrate is a moving belt, plastic film, or fabric.

[0087] The thin film of the polymer solution obtained by spray coating is then annealed in a solvent vapor, preferably in two steps, wherein the first annealing urges the block copolymer into forming a self-assembled structure, for example, into a structure having minor and major domains. In an embodiment, the minor domains are cylindrical domains. The

second annealing urges the formation of a porous membrane, for example, by the confined swelling of the minor domains. The first annealing or the second annealing is carried out in a vapor of a solvent or a vapor of a mixture of solvents to develop a self-assembled nanostructure. The solvent is a good solvent for the minor block. Any of the solvents identified above for the solvent system can be employed as a solvent vapor to carry out the annealing steps. For example, dichloromethane can be employed as a vapor.

[0088] Alternatively, instead of carrying out a second annealing, the self-assembled structure can be soaked in a solvent or mixture of solvents to obtain a porous membrane. The solvent or mixture of solvents can be at any suitable temperature, for example, from ambient temperature, for example, 20 °C to 25 °C, to elevated temperatures, such as up to 40 °C, 50 °C, 60 °C, 70 °C, 80 °C, or 90 °C. Any of the solvents used for annealing can be used for the soaking step.

[0089] Each of the annealing or the soaking step can be carried out for any suitable length of time, for example, 0.1 hour to 1 month or more, 5 hours to 15 days or more, or 10 hours to 10 days or more.

[0090] Without wishing to be bound by any theory or mechanism, the formation of a nanostructure is believed to take place as follows. The diblock copolymer in solution experiences certain thermodynamic forces. Since the diblock copolymer comprises two chemically different blocks of polymer chains connected by a covalent bond, there exists an incompatibility between the two blocks. In addition, there exists a connectivity constraint imparted by the connecting covalent bond. As a result of these thermodynamic forces, the diblock copolymer when dissolved in an appropriate solvent system self-assemble into micro-phase separated domains that exhibit ordered morphologies at equilibrium. When a film is cast from a dilute solution, the diblock copolymer forms micelles composed of a core and a corona, each made of a different block. In dilute solution, the micelles tend to be isolated from each other. However, in concentrated solution, as for example, when the solvent is removed from a thin film of the solution by evaporation, the micelles tend to aggregate with the result that the coronas merge to form a continuous matrix and the cores merge to form porous channels.

[0091] The block copolymer's ability to form ordered structures depends on a number of factors, including the polymer's relaxation rate, its viscosity, its concentration, and the nature of the solvent, in particular its chi parameter or the Hansen solubility parameter. A neutral solvent to both the blocks tends to orient the cylindrical pores normal to the membrane

surface. The solvent system mediates the interaction between the two blocks. As the system is annealed in the solvent vapor, the polymer chain mobility increases leading to polymer relaxation and formation of self-assembled ordered structures motivated by chain incompatibility and as a result of free energy minimization between the two blocks. Two competing thermodynamically deriving forces govern the process; the first is that the chains are chemically incompatible and have a tendency to segregate from each other, which increases system entropy, and the second is the restorative force leading to a loss of entropy as the system retracts due to the chemical bonds between monomer units and the diblock chains. The energy minimization occurs between these two competing factors. Accordingly, the choice of the solvent or solvent system is an important factor in obtaining ordered nanostructures.

[0092] The film is then optionally washed in a water bath for a suitable length of time, e.g., from about 1 min to about 2 hr, to remove any residual solvents, and optionally dried, to obtain a nanoporous membrane in accordance with an embodiment of the invention.

[0093] In accordance with an embodiment, the porous membrane is a symmetric membrane wherein the diblock copolymer is self-assembled into an ordered structure and the pores extend through the thickness of the membrane. In accordance with another embodiment, the porous membrane is an asymmetric membrane comprising a first layer and a second layer, the first layer comprising the diblock copolymer having ordered pores, for example, in a cylindrical morphology, and the second layer comprising a polymeric support having larger pores, for example, pores of diameter 0.5 μm or more, e.g., 1 to 10 μm .

[0094] In the self-assembled structure, the diblock copolymer and the pores are ordered in a cylindrical morphology and perpendicular to the plane of the membrane and the cylindrical pores whose diameters are in the range of about 40 to about 60 nm and the pores extend all the way down to the film thickness and at a depth of about 50 nm.

[0095] The polymeric support which serves as the second layer of the asymmetric composite membrane can be made of any suitable polymer, for example, polyaromatics; sulfones (e.g., polysulfones, including aromatic polysulfones such as, for example, polyethersulfone (PES), polyether ether sulfone, bisphenol A polysulfone, polyarylsulfone, and polyphenylsulfone), polyamides, polyimides, polyvinylidene halides (including polyvinylidene fluoride (PVDF)), polyolefins, such as polypropylene and polymethylpentene, polyesters, polystyrenes, polycarbonates, polyacrylonitriles ((PANs) including

polyalkylacrylonitriles), cellulosic polymers (such as cellulose acetates and cellulose nitrates), fluoropolymers, and polyetherether ketone (PEEK).

[0096] In accordance with an embodiment of the invention, the porous membrane is a nanoporous membrane, for example, a membrane having pores of diameter between 1 nm and 100 nm.

[0097] Porous membranes according to embodiments of the invention can be used in a variety of applications, including, for example, diagnostic applications (including, for example, sample preparation and/or diagnostic lateral flow devices), ink jet applications, filtering fluids for the pharmaceutical industry, filtering fluids for medical applications (including for home and/or for patient use, e.g., intravenous applications, also including, for example, filtering biological fluids such as blood (e.g., to remove leukocytes)), filtering fluids for the electronics industry (e.g., filtering photoresist fluids in the microelectronics industry), filtering fluids for the food and beverage industry, clarification, filtering antibody- and/or protein-containing fluids, filtering nucleic acid-containing fluids, cell detection (including *in situ*), cell harvesting, and/or filtering cell culture fluids. Alternatively, or additionally, membranes according to embodiments of the invention can be used to filter air and/or gas and/or can be used for venting applications (e.g., allowing air and/or gas, but not liquid, to pass therethrough). Membranes according to embodiments of the inventions can be used in a variety of devices, including surgical devices and products, such as, for example, ophthalmic surgical products.

[0098] In accordance with embodiments of the invention, the membrane can have a variety of configurations, including planar, flat sheet, pleated, tubular, spiral, and hollow fiber.

[0099] Porous membranes according to embodiments of the invention are typically disposed in a housing comprising at least one inlet and at least one outlet and defining at least one fluid flow path between the inlet and the outlet, wherein at least one inventive membrane or a filter including at least one inventive membrane is across the fluid flow path, to provide a filter device or filter module. In an embodiment, a filter device is provided comprising a housing comprising an inlet and a first outlet, and defining a first fluid flow path between the inlet and the first outlet; and at least one inventive membrane or a filter comprising at least one inventive membrane, the inventive membrane or filter comprising at least one inventive membrane being disposed in the housing across the first fluid flow path.

[0100] Preferably, for crossflow applications, at least one inventive membrane or filter comprising at least one inventive membrane is disposed in a housing comprising at least one inlet and at least two outlets and defining at least a first fluid flow path between the inlet and the first outlet, and a second fluid flow path between the inlet and the second outlet, wherein the inventive membrane or filter comprising at least one inventive membrane is across the first fluid flow path, to provide a filter device or filter module. In an illustrative embodiment, the filter device comprises a crossflow filter module, the housing comprising an inlet, a first outlet comprising a concentrate outlet, and a second outlet comprising a permeate outlet, and defining a first fluid flow path between the inlet and the first outlet, and a second fluid flow path between the inlet and the second outlet, wherein at least one inventive membrane or filter comprising at least one inventive membrane is disposed across the first fluid flow path.

[0101] The filter device or module may be sterilizable. Any housing of suitable shape and providing an inlet and one or more outlets may be employed.

[0102] The housing can be fabricated from any suitable rigid impervious material, including any impervious thermoplastic material, which is compatible with the fluid being processed. For example, the housing can be fabricated from a metal, such as stainless steel, or from a polymer, e.g., transparent or translucent polymer, such as an acrylic, polypropylene, polystyrene, or a polycarbonate resin.

[0103] The following examples further illustrate the invention but, of course, should not be construed as in any way limiting its scope.

EXAMPLE 1

[0104] This example describes some of the materials used in the preparation of the monomers and polymers.

[0105] Maleimide, furan, diisopropylazodicarboxylate (DIAD), triphenylphosphine (Ph_3P), 1-hexadecanol, tetrahydrofuran (THF), ethyl acetate, N-phenylmaleimide, acetonitrile, methanol, Grubbs second generation catalyst, 3-bromopyridine, and pentane were obtained from Sigma-Aldrich Co. and used without further treatment. Dichloropentane, also obtained from Sigma-Aldrich Co., was treated with basic alumina before use.

EXAMPLE 2

[0106] This example illustrates the preparation of *exo*-7-oxanorbornene-5,6-dicarboxyimide (C1), an intermediate in the preparation of the first and second monomers in accordance with an embodiment of the invention.

[0107] In a clean 500 mL round bottom flask (RBF) equipped with magnetic stirring bar, furan (21.0 g, 309 mmol) was added to a solution of maleimide (25 g, 258 mmol) in 250 mL of ethyl acetate. The mixture was heated at 90 °C for 30 h. C1 was obtained as white precipitate from solution upon washing with ether (100 mL, 3X) and filtration. The white solid was dried under vacuum at room temperature for 24 h. C1 was obtained as a pure *exo*-isomer in yield of 29 g, 68%. ¹H-NMR (300MHz, CDCl₃): δ (ppm) 8.09 (s, 1H), 6.53 (s, 2H), 5.32 (s, 2H), 2.89 (s, 2H).

EXAMPLE 3

[0108] This example illustrates the preparation of dichloro[1,3-bis(2,4,6-trimethylphenyl)-2-imidazolidinylidene](benzylidene)bis(3-bromopyridine)ruthenium(II) (G3) catalyst.

[0109] The second generation Grubbs catalyst (G2) illustrated above (1.0 g, 1.18 mmol) was mixed with 3-bromopyridine (1.14 mL, 11.8 mmol) in 50 mL flask. Upon stirring at room temperature for 5 min, the red mixture turned into bright green. Pentane (40 mL) was added with stirring for 15 minutes and green solid was obtained. The mixture was cooled in the freezer for 24 h and filtered under vacuum. The resulting G3 catalyst, a green solid, was washed with cold pentane and dried under vacuum at room temperature to give a yield of 0.9 g, 88% yield.

EXAMPLE 4

[0110] This example illustrates the preparation of a first monomer *exo*-7-oxanorbornene-N-hexadecyl-5,6-dicarboxyimide.

[0111] In a clean 500 mL RBF equipped with magnetic stirring bar, a mixture of *exo*-7-oxanorbornene-5,6-dicarboxyimide (C1) (10 g, 61 mmol), Ph₃P (23.84 g, 91 mmol), and 1-hexadecanol (17.6 g, 72.7 mmol) were dissolved in anhydrous THF (130 mL) under a stream of dry nitrogen gas. The solution was cooled in ice bath. DIAD (22.1 g, 109.3 mmol) was added from a dropping funnel drop-wise to the cooled solution. The reaction mixture was allowed to warm up to room temperature and stirred for 24 h. THF was removed by

rotary evaporator till dryness to obtain white solid. The first monomer was obtained from the crude as white solid upon crystallization from methanol (2X) and drying at room temperature under vacuum for 24 h (yield of 18.6 g, 80%). ¹H-NMR (300MHz, CDCl₃): δ (ppm) 6.5 (s, 2H), 5.26 (s, 2H), 5.32 (s, 2H), 3.45 (t, 2H), 2.82 (s, 2H), 1.56-1.38 (m, 2H), 1.28-1.1 (m, 26H), 0.88 (t, 3H).

EXAMPLE 5

[0112] This example illustrates the preparation of a second monomer *exo*-7-oxanorbornene-N-phenyl-5,6-dicarboxyimide.

[0113] In a clean 500mL round bottom flask (RBF) equipped with magnetic stirring bar, Furan (29.51 g, 433.5 mmol) was added to a solution of N-phenyl maleimide (25 g, 144.5 mmol) in 135 mL of acetonitrile. The solution was refluxed at 90 °C for 5 h. White crystalline solid was obtained upon cooling the reaction mixture. The second monomer was obtained by filtering the solid and purified by recrystallization from acetonitrile (2X). Yield of 19 g, 76%. ¹H-NMR (300 MHz, CDCl₃): δ (ppm) 7.55-7.35 (m, 3H, phenyl), 7.35-7.2 (m, 2H, phenyl), 6.57 (s, 2H), 5.37 (s, 2H), 3.05 (s, 2H).

EXAMPLE 6

[0114] This example illustrates the preparation of a diblock copolymer suitable for preparing a membrane in accordance with an embodiment of the invention.

[0115] The Grubbs 3rd generation (G3) catalyst from Example 3 (34.4 mg, 0.039 mmol) was weighed in 40 mL vial with equipped with fluoropolymer resin-silicone septa open-top cap. The catalyst was dissolved in argon-degassed dichloromethane (DCM) (60 mL) and transferred via cannula to a clean 1L RBF equipped with stirring bar. A solution of the first monomer (1.5 g, 3.85 mmol) in DCM (86 mL) was degassed with argon and transferred into the catalyst solution and stirred for 30 minutes. An aliquot of 1-2 mL of the homopolymer formed from the first monomer was taken after 30 minutes for molecular weight characterization. A solution of the second monomer (7.9 g, 32.8 mmol) in DCM (208 mL) was degassed with argon and transferred into the growing homopolymer solution in the RBF, and the contents of the flask were stirred for another 60 minutes. Ethyl vinyl ether (2mL) was then added to the yellow solution of the diblock copolymer to terminate the polymerization. The resulting polymer was precipitated in methanol (2 L, 2X) to recover the pure polymer as a white solid. The polymer was filtered and dried under vacuum at room

temperature; yield (9.2 g, 98%). $^1\text{H-NMR}$ (300MHz, CDCl_3): δ (ppm) 7.7-7.25 (m, 3H, phenyl), 7.25-6.8 (m, 2H, phenyl), 6.3-5.9 (broad, 1H), 5.9-5.3 (broad m, 1H), 5.3-4.9 (broad m, 1H), 4.9-4.2 (broad m, 1H), 3.6-3.0 (broad s, 2H), 1.6-1.4 (broad, 2H), 1.4-1.0 (s, 26H), 0.88 (t s, 3H).

EXAMPLE 7

[0116] This example illustrates a method to characterize the diblock copolymer involving the Multi-angle Laser Light Scattering and gel permeation chromatography (GPC).

[0117] The homopolymer and diblock copolymer obtained in Example 6 were characterized for their molecular weight and molecular weight distribution properties by the MALS-GPC technique under the following conditions:

[0118] Mobile phase: Dichloromethane (DCM).

[0119] Mobile phase temperature: 30 °C.

[0120] UV wavelength: 245 nm.

[0121] Columns used: three PSS SVD Lux analytical columns (Styrene-divinylbenzene copolymer network), columns having as stationary phase beads of diameter 5 μm and pore sizes of 1000 Å, 100,000 Å, and 1,000,000 Å, and guard columns.

[0122] Flow rate: 1 mL/min.

[0123] GPC system: waters HPLC alliance e2695 system with UV and RI detectors

[0124] MALS system: The DAWN HELEOS 8 system with 8 detectors operating a laser at 664.5 nm.

[0125] The chromatograms are depicted in Fig. 1. The diblock copolymer 2 eluted earlier than homopolymer 1 since it had a higher molecular weight.

EXAMPLE 8

[0126] This example illustrates a method for preparing a membrane in accordance with an embodiment of the invention.

[0127] A polymer solution containing the diblock copolymer from Example 6 was prepared by mixing the diblock copolymer with DMF and THF until a clear solution was obtained. The solution contained the diblock copolymer at 5 mass%. The mass ratio of DMF to THF was 60:40.

[0128] Spray coating conditions are as follows: Air spray coating was used to generate the membrane of a substrate with following general conditions. The substrate was glass. The

air pressure was 20 psi. The distance from the nozzle to substrate was 20 cm. Two layers were deposited by spray coating.

[0129] The thin films are studied as cast or after annealing. The thin film was annealed in a solvent chamber containing DCM vapor for a period of 16 hr at low humidity. The film was washed and dried, and then imaged with atomic force microscopy (AFM) to reveal the nanostructure.

[0130] Fig. 2A depicts the AFM topographic image of the height of the surface of the thin film after spray coating but without annealing and Fig. 2B depicts the AFM topographic image of the phase of the surface of the thin film. Fig. 3C depicts the line profile extracted from Fig. 3A.

[0131] Fig. 3A depicts AFM topographic image of the height of the surface of the thin film after spray coating and annealing and Fig. 3B depicts the AFM topographic image of the phase of the surface of the thin film.

[0132] Fig. 4A depicts the AFM image of the cross-section of a thin film spray coated on a glass surface. Fig. 4B depicts a higher magnification AFM image.

[0133] The domain size of the block copolymer in the as cast film was about 20 to about 30 nm. The domain size of the block copolymer in the annealed film was about 40 to about 60 nm.

[0134] All references, including publications, patent applications, and patents, cited herein are hereby incorporated by reference to the same extent as if each reference were individually and specifically indicated to be incorporated by reference and were set forth in its entirety herein.


[0135] The use of the terms “a” and “an” and “the” and “at least one” and similar referents in the context of describing the invention (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. The use of the term “at least one” followed by a list of one or more items (for example, “at least one of A and B”) is to be construed to mean one item selected from the listed items (A or B) or any combination of two or more of the listed items (A and B), unless otherwise indicated herein or clearly contradicted by context. The terms “comprising,” “having,” “including,” and “containing” are to be construed as open-ended terms (i.e., meaning “including, but not limited to,”) unless otherwise noted. Recitation of ranges of values herein are merely intended to serve as a shorthand method of referring individually to each separate value falling within the range,

unless otherwise indicated herein, and each separate value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., “such as”) provided herein, is intended merely to better illuminate the invention and does not pose a limitation on the scope of the invention unless otherwise claimed. No language in the specification should be construed as indicating any non-claimed element as essential to the practice of the invention.

[0136] Preferred embodiments of this invention are described herein, including the best mode known to the inventors for carrying out the invention. Variations of those preferred embodiments may become apparent to those of ordinary skill in the art upon reading the foregoing description. The inventors expect skilled artisans to employ such variations as appropriate, and the inventors intend for the invention to be practiced otherwise than as specifically described herein. Accordingly, this invention includes all modifications and equivalents of the subject matter recited in the claims appended hereto as permitted by applicable law. Moreover, any combination of the above-described elements in all possible variations thereof is encompassed by the invention unless otherwise indicated herein or otherwise clearly contradicted by context.

CLAIMS:

1. A method of preparing a porous membrane comprising a diblock copolymer of the formula (I):



wherein:

R^1 is a C_1 - C_{22} alkyl group optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro, or a C_3 - C_{11} cycloalkyl group, optionally substituted with a substituent selected from alkyl, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro;

R^2 is a C_6 - C_{20} aryl group or a heteroaryl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro;

one of R^3 and R^4 is a C_6 - C_{14} aryl group, optionally substituted with a substituent selected from hydroxy, halo, amino, and nitro, and the other of R^3 and R^4 is a C_1 - C_{22} alkoxy group, optionally substituted with a substituent selected from carboxy, amino, mercapto, alkynyl, alkenyl, halo, azido, and heterocyclyl; and

n and m are independently about 10 to about 2000;

the method comprising:

- (i) dissolving the diblock copolymer in a solvent system to obtain a polymer solution;
- (ii) spray coating the polymer solution onto a substrate; and
- (iii) annealing the coating obtained in (ii) in a vapor comprising a solvent or a mixture of solvents to obtain a self-assembled structure.

2. The method of claim 1, wherein R^1 is a C_{10} - C_{18} alkyl group, optionally substituted with a substituent selected from halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro.
3. The method of claim 1 or 2, wherein R^2 is a phenyl group, optionally substituted with a substituent selected from hydroxy, amino, halo, alkoxy, alkylcarbonyl, alkoxycarbonyl, amido, and nitro.
4. The method of any one of claims 1-3, wherein R^3 is phenyl.
5. The method of any one of claims 1-4, wherein R^4 is a C_1 - C_6 alkoxy group.
6. The method of any one of claims 1-5, wherein n is about 10 to about 200 and m is about 50 to about 2000.
7. The method of any one of claims 1-6, wherein n is about 83 to about 190 and m is about 675 to about 1525.
8. The method of any one of claims 1-7, wherein n is about 105 and m is about 870.
9. The method of any one of claims 1-8, wherein the diblock copolymer of formula (I) has the following structure:

10. The method of any one of claims 1-9, wherein the solvent system includes a solvent or a mixture of solvents selected from halogenated hydrocarbons, ethers, amides, and sulfoxides.
11. The method of any one of claims 1-10, wherein the solvent system includes a solvent or a mixture of solvents selected from dichloromethane, 1-chloropentane, chloroform, 1,1-dichloroethane, N,N-dimethylformamide, N,N-dimethylacetamide, N-methylpyrrolidone, dimethylsulfoxide, tetrahydrofuran, 1,3-dioxane, and 1,4-dioxane.
12. The method of any one of claims 1-11, wherein the polymer solution contains about 3 to about 8% by weight of the diblock copolymer.
13. The method of any one of claims 1-12, wherein the substrate is selected from glass, silicon wafer, metal plate, plastic film, woven or nonwoven fabric, and a plastic film coated on a glass substrate or on or a silicon wafer.

14. The method of any one of claims 1-13, wherein the substrate is porous.
15. The method of any one of claims 1-14, wherein the annealing is carried out in the presence of a solvent vapor comprising dichloromethane.
16. The method of any one of claims 1-14, wherein the annealing is carried out twice.
17. A porous membrane prepared by the method of any one of claims 1-16.
18. The porous membrane of claim 17, which is a single layer membrane.
19. The porous membrane of claim 18, which is a composite membrane comprising a first layer and a second layer, the first layer comprising the diblock copolymer and ordered pores in a cylindrical morphology and the second layer comprising a microporous support layer.