

9905697-0

IPOS's
copy.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 1/08, B29D 23/00, B65B 53/02	A1	(11) International Publication Number: WO 98/52742 (43) International Publication Date: 26 November 1998 (26.11.98)
(21) International Application Number: PCT/US98/09675 ✓ (22) International Filing Date: 7 May 1998 (07.05.98) ✓ (30) Priority Data: 08/858,850 ✓ 19 May 1997 (19.05.97) ✓ US ✓ (71) Applicant: ① MOBIL OIL CORPORATION [US/US]; 3225 Gallows Road, Fairfax, VA 22037 (US). ✓ (72) Inventors: AMON, Moris; 61 Kitty Hawk Drive, Pittsford, NY 14534 (US) ✓ SPEET, Robert; 44 Sunset Boulevard, Pittsford, NY 14534 (US) ✓ PELLINGRA, Salvatore, James, Jr.; 7 Orchard Street, Wolcott, NY 14590 (US). ✓ (74) Agents: CUOMO, Lori, F. et al.; Mobil Oil Corporation, 3225 Gallows Road, Fairfax, VA 22037 (US). ✓		(81) Designated States: AU, BR, CA, CN, ID, JP, KR, ② VN, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report. ✓ 1 appln. 3 Invs
(54) Title: IMPROVED COMPOSITION FOR UNIAXIALLY HEAT-SHRINKABLE BIAXIALLY ORIENTED POLYPROPYLENE FILM ✓		
(57) Abstract A uniaxially heat-shrinkable, biaxially oriented, multilayer film having a polypropylene-containing core layer comprising at least 70 wt.% of said multilayer film and optionally, at least one polyolefin-containing skin layer adjacent said core layer, is prepared by biaxially orienting a coextrudate and thereafter orienting said coextrudate by stretching 10 to 40 % in the machine direction. The core layer contains isotactic polypropylene and a sufficient amount of syndiotactic polypropylene to inhibit uniaxial heat shrinkage at temperatures below 50 °C. The skin layer can be selected from the group consisting of polypropylene, ethylene-propylene copolymer, polyethylene, and ethylene-propylene-butylene terpolymer.		