

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 8/04	A1	(11) International Publication Number: WO 00/56782 (43) International Publication Date: 28 September 2000 (28.09.00)
(21) International Application Number: PCT/US00/04359 (22) International Filing Date: 22 February 2000 (22.02.00) (30) Priority Data: 60/125,256 19 March 1999 (19.03.99) US 09/330,663 11 June 1999 (11.06.99) US (71) Applicant: THE DOW CHEMICAL COMPANY [US/US], 2030 Dow Center, Midland, MI 48674 (US). (72) Inventors: HAHN, Stephen, F.; 4302 James Drive, Midland, MI 48642 (US). HAHNFELD, Jerry, L.; 920 Scenic Drive, Midland, MI 48642 (US). HUCUL, Dennis, A.; 5001 Foxcroft Drive, Midland, MI 48642 (US). (74) Agent: ZETTLER, Lynn, M.; Intellectual Property, P.O. Box 1967, Midland, MI 48641-1967 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>  *G00001*
(54) Title: HYDROGENATED BLOCK COPOLYMERS (57) Abstract The present invention is a hydrogenated block copolymer comprising at least two distinct blocks of hydrogenated vinyl aromatic polymer, and at least one block of hydrogenated conjugated diene polymer, characterized by: a) a total number average molecular weight (M_n) of from 30,000 to 120,000, wherein each hydrogenated vinyl aromatic polymer block (A) has a M_{nA} of from 5,000 to 50,000 and the hydrogenated conjugated diene polymer block (B) has a M_{nB} of from 4,000 to 110,000; and b) a hydrogenation level such that each hydrogenated vinyl aromatic polymer block has a hydrogenation level of greater than 90 percent and the hydrogenated conjugated diene polymer block has a hydrogenation level of greater than 95 percent.  *162162*		