What is claimed is:

1. An article comprising:

a continuous web comprising a substrate having a first major side and a second major side opposite to the first major side, and at least two web edges; and

one or more discrete quantities of adhesive disposed on one or both of the first and second major sides and adjacent to one or both of the web edges,

wherein the substrate is rolled upon itself in multiple revolutions, and

wherein each revolution is held substantially separate from the next by the one or more stripes of adhesive dots.

2. The article of claim 1, wherein the discrete quantities of adhesive include adhesive dots each having a dome shape.

3. The article of claim 1, wherein the adhesive has a cured ink composition with a glass transition temperature (Tg) no greater than about 25 ^{o}C.

4. The article of claim 3, wherein the cured ink composition includes one or more pressure sensitive adhesives (PSA).

5. The article of claim 3, wherein the cured ink composition is obtained by curing a curable ink composition.

6. The article of claim 5, wherein the curable ink composition comprises:

between about 50 to 99.89 parts by weight of hydroxyalkyl acrylate having 2 to 6 carbon alkyl;

between about 0 to 49.89 parts by weight of ethylenically unsaturated monomer including one or more of vinyl, acrylate, and (meth)acrylate monomer;

between about 0.01 to 5.0 parts by weight of a multi-functional acrylate or oligomer having (meth)acryl functional groups; and

between about 0.1 to 10 parts by weight of a photo-initiator.

7. The article of claim 5, wherein the ink composition is curable by ultraviolet (UV) light.

8. The article of claim 5, wherein the curable ink composition has a viscosity of about 1 to about 50 mPa-s.