

Device and Method for Stripping a Product Substrate Off a Carrier Substrate

Specification

The invention relates to a device and a method for stripping a product substrate off a carrier.

The back-grinding of product substrates is often necessary in the semiconductor industry and can take place mechanically and/or chemically. For purposes of back-grinding in general the product substrates are temporarily fixed on a carrier, there being various methods for the fixing. The carrier material can be for example films, glass substrates or silicon wafers.

Depending on the carrier materials used and the bonding layer used between the carrier and the product substrate, different methods for dissolving or destroying the bonding layer are known, such as for example the use of UV light, laser beams, the action of temperature, or solvents.

Stripping increasingly constitutes one of the most critical process steps since thin substrates with substrate thicknesses of a few microns easily break during stripping/peeling or are damaged by the forces which are necessary for the stripping process.

Moreover thin substrates have hardly any stability of shape or none at all and typically curl without support material. During handling of back-ground wafers therefore fixing and support of the wafers are essentially indispensable.

Embodiments of this invention disclose a device and a method to detach a product substrate from a carrier as nondestructively and easily as possible.

According to a first aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer; mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive; receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir; delivering the solvent into the solvent reservoir; and at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir, wherein said bonding layer connecting the product substrate to the carrier substrate is comprised of a plurality of different adhesive layers.

According to a second aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer, said method comprising: receiving the product substrate on a flexible film having an adhesive layer, said adhesive layer holding the product substrate on a contacting surface section of the flexible film; connecting an attachment section of the flexible film to the film frame, said attachment section surrounding the contacting surface section; and detaching the product substrate from the carrier substrate, wherein the detaching step includes: applying a force F_s that acts on the flexible film, and applying a force F_f that acts on the film frame, said force F_f directed against the force F_s , wherein said bonding layer connecting the product substrate to the carrier substrate is comprised of a plurality of different adhesive layers.

According to a third aspect, there is provided a method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer; fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film; applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ; and tilting the film frame, wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section.

According to a fourth aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer; mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive; receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the

solvent reservoir; delivering the solvent into the solvent reservoir; at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir; and detaching the product substrate from the carrier substrate after delivering of the solvent into the solvent reservoir and at least partially dissolving the bonding layer, wherein detaching the product substrate from the carrier substrate takes place concentrically from a periphery of said product substrate to a center of said product substrate.

According to a fifth aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer; mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive; receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir; delivering the solvent into the solvent reservoir; and at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir, wherein said bonding layer is comprised of a plurality of bonding layers, said method including selectively dissolving a specific bonding layer of the plurality of bonding layers.

According to a sixth aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween,

wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer; mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive; receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir; delivering the solvent into the solvent reservoir; and at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir, wherein a plurality of bonding layers connect the carrier substrate to the product substrate, said method including selectively dissolving more than one bonding layer.

According to a seventh aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer, said method comprising: receiving the product substrate on a flexible film having an adhesive layer, said adhesive layer holding the product substrate on a contacting surface section of the flexible film; connecting an attachment section of the flexible film to the film frame, said attachment section surrounding the contacting surface section; and detaching the product substrate from the carrier substrate, wherein the detaching step includes: applying a force F_s that acts on the flexible film, and applying a force F_f that acts on the film frame, said force F_f directed against the force F_s , wherein said product substrate is detached from the carrier substrate concentrically from a periphery of the product substrate to a center of the product substrate.

According to an eighth aspect, there is provided a method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer, said

method comprising: receiving the product substrate on a flexible film having an adhesive layer, said adhesive layer holding the product substrate on a contacting surface section of the flexible film; connecting an attachment section of the flexible film to the film frame, said attachment section surrounding the contacting surface section; and detaching the product substrate from the carrier substrate, wherein the detaching step includes: applying a force F_s that acts on the flexible film, applying a force F_f that acts on the film frame, said force F_f directed against the force F_s , exposing at least a portion of the bonding layer to a solvent, and at least partially dissolving the bonding layer, wherein said bonding layer is comprised of a plurality of different bonding layers, each of said plurality of different bonding layers selectively dissolved by a solvent having a different fluid agent.

According to a ninth aspect, there is provided a method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer; fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film; and applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s , wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed

between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and wherein the at least one force F_f includes a first force F_{f1} applied to the film frame and a second force F_{f2} applied to the film frame, wherein the first force F_{f1} is applied at a first location of the film frame and the second force F_{f2} is applied at a second location of the film frame, the first force F_{f1} being greater than the second force F_{f2} to strip the product substrate from the carrier substrate starting at a peripheral edge of the product substrate.

According to a tenth aspect, there is provided a method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer; fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film; and applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s , wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and wherein the at least one force F_f includes a plurality of different forces F_{f1} , F_{f2} to F_{fn} applied to the film frame, each of said plurality of different forces

F_{f1} , F_{f2} to F_{fn} applied at different locations of the film frame to strip the product substrate from the carrier substrate concentrically from the periphery of the product substrate to a center of the product substrate.

According to an eleventh aspect, there is provided a method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combinations said method comprising: mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer; fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film; and applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s , wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, increases a volume of the solvent reservoir to increase capacity of the solvent reservoir to receive the solvent.

According to a twelfth aspect, there is provided a method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-

product substrate combination, said method comprising: mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer; fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film; and applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s , wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and wherein the force F_s and the at least one force F_f are applied to deform at least the stripping section of the flexible film, in first and second operating modes, wherein in the first operating mode the contacting surface section of the flexible film is moved in a first direction, and in the second operating mode the contacting surface section of the flexible film is moved in a second direction that is opposite of the first direction.

According to a thirteenth aspect, there is provided a method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising: mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer; fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the

outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film; and applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s , wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, moves the flexible film between (i) an initial position, wherein the contacting surface section and the attachment surface section are substantially in the same plane, (ii) a detachment position, wherein the contacting surface section is located in a plane below the attachment surface section, and (iii) a stripping position, wherein the contacting surface section is located in a plane above the attachment surface section.

The framework of the invention also

encompasses all combinations of at least two of the features given in the specification, the claims, and/or the figures. In the specified value ranges, values which lie within the indicated limits will also be disclosed as boundary values and they are to be claimed in any combination.

Embodiments of the invention are based on the idea of developing a generic device and a generic method by solvent being delivered to a solvent reservoir which is formed by the film frame and the film attached to it. Due to the elasticity or flexibility of the film which is mounted on the film frame it is at the same time possible to make the solvent tank of variable volume and the elasticity or flexibility of a film is moreover used to carefully strip the product substrate starting from the edge of the product substrate. In this way the product substrate is immediately available for other process steps directly after separation and is protected by the film and the film frame. Many process steps can be carried out directly on the product substrate mounted on the film frame.

A product substrate is defined as a product substrate, for example a semiconductor wafer, which is conventionally thinned to a thickness between 0.5 μm and 250 μm , the trend being toward thinner and thinner product substrates. Embodiments of the invention work especially effectively with product substrates which themselves have a flexibility similar to the film mounted on the film frame. The product substrate in the device as per embodiments of the invention and the method as per embodiments of the invention is peeled off the carrier substrate, especially proceeding concentrically from the periphery of the product substrate.

The carrier is for example a carrier substrate with a thickness between 50 μm and 5000 μm , especially between 500 μm and 1000 μm .

The bonding layer can be an adhesive, for example a soluble adhesive, especially a thermoplastic, which is applied for example selectively in the edge region of the carrier-product

substrate combination, especially in an edge zone from 0.1 to 20 mm. Alternatively the adhesive can be applied over the entire surface, and the adhesive force can be reduced in the center by an adhesion-reducing layer, for example a fluoropolymer, preferably teflon.

A chuck is especially well suited as the holding means, especially a spinner chuck for holding the carrier substrate, especially by means of negative pressure, for example on suction paths, holes or suction cups. Alternatively, mechanical holding, for example by lateral clamps, is conceivable. Holding takes place electrostatically in another alternative configuration.

The stripping means encompass the film mounted on the film frame and a film frame holder which applies a force and which holds the film frame.

In one advantageous embodiment of the invention it is provided that the solvent is made to work essentially without heating. The solvent is preferably used at ambient temperature. In this way it is possible to omit any heating means.

By the solvent being intended for at least partially detaching the connection between the carrier substrate and the product substrate caused by the bonding layer, stripping by the stripping means is advantageously clearly facilitated.

Because the solvent comprises especially a fluid agent which selectively dissolves the bonding layer for at least partial detachment of the bonding layer, for bonding layers encompassing different adhesives it becomes possible to dissolve a certain bonding layer in a controlled manner or in defined regions. Chemical dissolution of the bonding layer is especially protective of the product substrate and with the corresponding material choice, dissolution can also take place very quickly, especially when only edge regions of the product substrate are provided with an bonding layer, so that the solvent can act very quickly from the side. In this way perforations in the carrier substrate

and/or product substrate can be omitted.

To the extent the solvent reservoir is made such that the solvent acts at least at the start of detachment of the bonding layer, especially solely in the region of the periphery of the product substrate, action on the product substrate and/or carrier substrate from the top and/or bottom, especially the inner region of the product substrate which lies within the side edge, can be omitted.

In another embodiment of the invention it is provided that the stripping means are made to cause a force F_s which acts on the carrier substrate and a force F_f which acts on the film frame and which is directed against the force F_s . In this way stripping is effected in a manner which is simple and especially protective by the film. The force F_f acts on the periphery of the film frame, especially at at least two locations on the film frame which are distributed over the periphery, and the forces F_{f1} and F_{f2} can be controlled differently in one advantageous embodiment in order to strip the product substrate from the side with the greater force F_f .

Here it is especially advantageous if the film can be clamped, especially by the force F_s and force F_f in a stripping section which lies between the contacting surface section and the attachment section. In this way stripping is carefully effected on the periphery of the product substrate. Detachment by the solvent and stripping by the forces F_s and F_f mutually support one another.

According to one advantageous embodiment of the invention it is provided that there is a vibration generator which acts on the solvent and/or the bonding layer, which adjoins especially the film, and/or which can be placed in the solvent in the solvent reservoir. "Can be placed" comprises both surface contact and also at least partial immersion. This supports detachment by the solvent and accelerates the detachment process at least by a factor of 2, with an optimized configuration by a factor of 5, even more preferably by a factor of 10 to 50. Preferably the vibration generator acts by

ultrasonic waves, especially in the region of the contacting surface section.

In another advantageous embodiment the solvent reservoir is made trough-shaped, by which stripping of the product substrate can be achieved with a minimum solvent consumption.

Other advantages, features and details of the invention will become apparent from the following description of preferred exemplary embodiments and using the drawings.

Figure 1a shows a schematic top view of a substrate combination consisting of the product substrate, the carrier substrate and the bonding layer on a film frame,

Figure 1b shows a schematic side view to Figure 1a with a detailed view,

Figure 2 shows a schematic according to Figure 2 when the solvent is being delivered,

Figure 3 shows a schematic of the method step of detaching the bonding layer,

Figure 4 shows a schematic of the method step of stripping of the product substrate off the carrier substrate as claimed in the invention,

Figure 5 shows a schematic of one alternative method step of stripping the product substrate off the carrier substrate as claimed in the invention.

In the figures the same components and components with the same function are identified with the same reference number.

Figure 1a shows a film frame 1 which is round in this embodiment at least on the inner periphery 1i, on whose bottom according to the sectional view shown in Figure 1b a film 3 is cemented with its adhesive layer 3s concentrically to the film frame 1. With a radial distance A to the inner periphery 1i of the film frame 1, within the film frame 1 the product substrate-carrier substrate combination is cemented on a adhesive layer 3s of the film 3 concentrically to the film frame 1. The product substrate-carrier substrate combination consists of a product substrate 4 which

adheres to the film 3, a carrier substrate 2 and a bonding layer 6 which connects the product substrate 4 and the carrier substrate 2. The diameters of the product substrate 4 and of the carrier substrate 2 are essentially identical, while the thickness of the product substrate 4 is less than the thickness of the carrier substrate 2.

The film 3 consists of an attachment section 3b which has the shape of a circular ring in this case and in which the film 3 is fixed to the film frame 1. Furthermore, the film 3 consists of a contacting surface section 3k in which the product substrate 4 can be fixed on the adhesive layer 3s of the film 3. Between the attachment section 3b and the contacting surface section 3k there is a stripping section 3a which is located especially concentrically to the attachment section 3b and the contacting surface section 3k, and which need not have a cementing function, to which however a function which is critical as claimed in the invention is attached. The stripping section 3a thus extends from the periphery 4u of the product substrate 4 to the inner periphery 1i of the film frame 1, here labeled the radial distance A. The ratio between the thickness D of the film frame 1 and the distance A is advantageously at least 1:2 to 1:50, especially 1:5 to 1:25.

In the initial position shown in Figure 1b, the side of the product substrate 4 which makes contact with the film 3 and the side of the film frame 1 which makes contact with the film 3 are arranged flush and in one plane E. The parts shown in Figures 1a and 1b are assembled on a known film frame mounter.

The film 3 and the inner periphery 1i of the film frame 1 form a trough-shaped solvent reservoir 20 in which the product substrate-carrier substrate can be arranged as described above.

According to the method step shown in Figure 2 the solvent 22 can be delivered into the solvent reservoir 20 by delivery means 23. The delivery means 23 here consists of a line 24 and a

solvent storage 25 which can be triggered from a central unit in order to deliver the solvent 22 into the solvent reservoir 20.

As Figure 2 shows, the solvent reservoir 20 is of variable volume due to the film 3 which is elastic at least in the stripping section 3a by a force F_s acting on the carrier substrate 2 downwardly and a force F_f acting on the film frame 1 upwardly. Application of the force is likewise controlled by a central unit.

Increasing the volume of the storage means reservoir prevents the solvent 22 running over the edge of the film frame 1 and at the same time prompt distribution or delivery of the solvent 22 is enabled.

The force F_s as shown in Figure 3 is transferred by way of the carrier substrate holder 7 for holding the carrier substrate 2, fixing of the carrier substrate 2 on the carrier substrate holder 7 taking place by vacuum paths 8 which have been machined into the surface of the carrier substrate holder 7 and via a vacuum means which is connected to them and which is not shown.

On the opposite side of the film 3 to the product substrate 4 there can be an acoustic wave generator 10, especially for producing ultrasonic waves, by which ultrasonic waves can be transmitted onto the product substrate 4, but especially onto the bonding layer 6 and the solvent 22, since in this way the process of detachment is greatly accelerated, especially by a factor of 2, preferably by a factor of 5, even more preferably by a factor of 10 to 50.

According to one alternative embodiment shown in Figure 5, the acoustic wave generator 10' is in contact at least with the surface of the fluid solvent 22, but preferably is at least partially immersed in it. In this way the acoustic waves can be transmitted directly onto the solvent 22 and from the solvent 22 onto the bonding layer 6.

The force F_f acting on the film frame 1, as shown in Figure 3, can act uniformly distributed as a superficial force on the film frame 1 so that a change in the volume of the solvent reservoir 20 can be caused by way of deformation of the film 3 in the stripping section 3a.

As shown in Figure 4, stripping of the product substrate 2 from the carrier substrate 4 takes place in reverse, by the forces F_s and F_f or F_{s1} and F_{s2} being pointed in the opposite direction, the force F_{f1} in the embodiment shown here being set to be greater than the force F_{f2} in order to have the stripping of the product substrate 4 start carefully first from the edge side according to the enlargement shown in Figure 4.

The force F_{f1} or several forces F_{f1} , F_{f2} to F_{fn} can be delivered in spots distributed on the periphery of the film frame 1 or can be delivered distributed by a film frame holder.

To the extent the forces F_{f1} , F_{f2} and/or F_{fn} are made differently, the holding means for applying the force to the film frame 1 must be made to allow tilting of the film frame 1.

Between the process step of detachment by the solvent 22 shown in Figure 3 and the method step of stripping by opposing forces F_s , F_{f1} , F_{f2} , F_{fn} shown in Figure 4 there can be one method step by which the solvent 22 is removed from the solvent reservoir 20, especially by suction.

Reference Number List

- 1 film frame
- 2 carrier substrate
- 3 film
- 3a stripping section
- 3b attachment section
- 3k contacting surface section
- 3s adhesive layer
- 4 product substrate
- 4u periphery
- 6 bonding layer
- 7 carrier substrate holder
- 8 vacuum paths
- 10, 10' acoustic wave generator
- 20 solvent reservoir
- 22 solvent
- 23 delivery means
- 24 line
- 25 solvent storage
- $F_s, F_{f1}, F_{f2} \dots F_{fn}$ force
- F_s force

Claims:

1. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer;

mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive;

receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir;

delivering the solvent into the solvent reservoir; and

at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir,

wherein said bonding layer connecting the product substrate to the carrier substrate is comprised of a plurality of different adhesive layers.

2. Method as claimed in claim 1, wherein, at least at the start of dissolving the bonding layer, the solvent acts solely in a region of a periphery of the product substrate.

3. Method as claimed in claim 1, wherein the step of receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir includes:

(i) applying a force F_s acting on the carrier substrate that is transferred to the flexible film, and

(ii) applying a force F_f acting on the film frame, said force F_f directed against the force F_s .

4. Method as claimed in claim 1, wherein the step of at least partially dissolving the bonding layer includes dissolving the bonding layer in the solvent reservoir starting from a periphery of the product substrate.
5. Method as claimed in claim 1, wherein said method further comprises:
detaching the product substrate from the carrier substrate after delivering of the solvent into the solvent reservoir and at least partially dissolving the bonding layer.
6. Method as claimed in claim 5, wherein detaching the product substrate from the carrier substrate is caused by a force F_s acting on said carrier substrate and a force F_f acting on said film frame and which is directed against the force F_s .
7. Method as claimed in claim 5, wherein detaching the product substrate from the carrier substrate takes place concentrically from a periphery of said product substrate to a center of said product substrate.
8. Method as claimed in claim 1, wherein the solvent comprises a fluid that selectively dissolves the bonding layer, for at least partial detachment of the bonding layer.
9. Method as claimed in claim 1, wherein the bonding layer is dissolved in defined regions.
10. Method as claimed in claim 1, wherein said bonding layer is comprised of a plurality of bonding layers, said method including selectively dissolving a specific bonding layer of the plurality of bonding layers.
11. Method as claimed in claim 1, wherein a plurality of bonding layers connect the carrier substrate to the product substrate, wherein said method further comprises selectively dissolving more than one bonding layer.
12. Method as claimed in claim 1, wherein the solvent acts solely in the region of the periphery of the product substrate.

13. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer, said method comprising:

receiving the product substrate on a flexible film having an adhesive layer, said adhesive layer holding the product substrate on a contacting surface section of the flexible film;

connecting an attachment section of the flexible film to the film frame, said attachment section surrounding the contacting surface section; and

detaching the product substrate from the carrier substrate, wherein the detaching step includes:

applying a force F_s that acts on the flexible film, and

applying a force F_f that acts on the film frame, said force F_f directed against the force F_s ,

wherein said bonding layer connecting the product substrate to the carrier substrate is comprised of a plurality of different adhesive layers.

14. Method as claimed in claim 13, wherein said product substrate is detached from the carrier substrate concentrically from a periphery of the product substrate to a center of the product substrate.

15. Method as claimed in claim 13, wherein the detaching step includes:

exposing at least a portion of the bonding layer to a solvent; and

at least partially dissolving the bonding layer

16. Method as claimed in claim 15, wherein said bonding layer is comprised of a plurality of different bonding layers, each of said plurality of different bonding layers selectively dissolved by a solvent having a different fluid agent.

17. Method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer;

fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section; receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer; applying a force F_s to the carrier substrate that is transferred to the flexible film;

applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ; and

tilting the film frame,

wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section.

18. Method as claimed in claim 17, wherein the method further comprises engaging a carrier substrate holder with the carrier substrate to apply the force F_s to the carrier substrate.

19. Method as claimed in claim 17, wherein the method further comprises engaging a film frame holder with the film frame to apply the at least one force F_f to the film frame.

20. Method as claimed in claim 17, wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, varies the volume of the solvent reservoir.

21. Method as claimed in claim 17, wherein the method further comprises:

producing acoustic waves that are transmitted to at least one of: (i) the solvent received in the solvent reservoir, and (ii) the bonding layer.

22. Method as claimed in claim 21, wherein the method further comprises:

producing said acoustic waves using a vibration generator.

23. Method as claimed in claim 17, wherein said solvent reservoir is trough-shaped.
24. Method as claimed in claim 17, wherein the method further comprises:
dissolving the bonding layer from a periphery of the product substrate using the solvent received in the solvent reservoir.
25. Method as claimed in claim 17, wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, moves the contacting surface section of the flexible film to a different plane than the attachment surface section of the flexible film.
26. Method as claimed in claim 17, wherein the at least one force F_f is uniformly distributed on the film frame.
27. Method as claimed in claim 17, wherein the at least one force F_f includes a first force F_{f1} applied to the film frame and a second force F_{f2} applied to the film frame, wherein the first force F_{f1} is applied at a first location of the film frame and the second force F_{f2} is applied at a second location of the film frame, the first force F_{f1} being greater than the second force F_{f2} to strip the product substrate from the carrier substrate starting at a peripheral edge of the product substrate.
28. Method as claimed in claim 17, wherein the at least one force F_f includes a plurality of different forces F_{f1} , F_{f2} to F_{fn} applied to the film frame, wherein each of said plurality of different forces F_{f1} , F_{f2} to F_{fn} is applied at different locations of the film frame to strip the product substrate from the carrier substrate concentrically from the periphery of the product substrate to a center of the product substrate.
29. Method as claimed in claim 17, wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, increases a volume of the solvent reservoir to increase capacity of the solvent reservoir to receive the solvent.

30. Method as claimed in claim 17, wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, strips the product substrate from the carrier substrate.

31. Method as claimed in claim 17, wherein said method further comprises:

applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, in first and second operating modes, wherein in the first operating mode the contacting surface section of the flexible film is moved in a first direction, and in the second operating mode the contacting surface section of the flexible film is moved in a second direction that is opposite of the first direction.

32. Method as claimed in claim 17, wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, moves the flexible film between (i) an initial position, wherein the contacting surface section and the attachment surface section are substantially in the same plane, (ii) a detachment position, wherein the contacting surface section is located in a plane below the attachment surface section, and (iii) a stripping position, wherein the contacting surface section is located in a plane above the attachment surface section.

33. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer;

mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive;

receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir;

delivering the solvent into the solvent reservoir;

at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir; and

detaching the product substrate from the carrier substrate after delivering of the solvent into the solvent reservoir and at least partially dissolving the bonding layer, wherein detaching the product substrate from the carrier substrate takes place concentrically from a periphery of said product substrate to a center of said product substrate.

34. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer;

mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive;

receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir;

delivering the solvent into the solvent reservoir; and

at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir,

wherein said bonding layer is comprised of a plurality of bonding layers, said method including selectively dissolving a specific bonding layer of the plurality of bonding layers.

35. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

connecting a flexible film to a film frame to form a solvent reservoir that receives a solvent for dissolving the bonding layer;

mounting the carrier-product substrate combination to the flexible film by fixing the product substrate to a contacting surface section of the flexible film using an adhesive;

receiving at least the product substrate and the bonding layer of the carrier-product substrate combination into the solvent reservoir;

delivering the solvent into the solvent reservoir; and

at least partially dissolving the bonding layer between the carrier substrate and the product substrate by exposing the bonding layer of the carrier-product substrate combination to the solvent received by the solvent reservoir.

wherein a plurality of bonding layers connect the carrier substrate to the product substrate, said method including selectively dissolving more than one bonding layer.

36. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer, said method comprising:

receiving the product substrate on a flexible film having an adhesive layer, said adhesive layer holding the product substrate on a contacting surface section of the flexible film;

connecting an attachment section of the flexible film to the film frame, said attachment section surrounding the contacting surface section; and

detaching the product substrate from the carrier substrate, wherein the detaching step includes:

applying a force F_s that acts on the flexible film, and

applying a force F_f that acts on the film frame, said force F_f directed against the force F_s , wherein said product substrate is detached from the carrier substrate concentrically from a periphery of the product substrate to a center of the product substrate.

37. Method for stripping a product substrate off a carrier substrate connected to the product substrate by a bonding layer, said method comprising:

receiving the product substrate on a flexible film having an adhesive layer, said adhesive layer holding the product substrate on a contacting surface section of the flexible film;

connecting an attachment section of the flexible film to the film frame, said attachment section surrounding the contacting surface section; and

detaching the product substrate from the carrier substrate, wherein the detaching step includes:

- applying a force F_s that acts on the flexible film,
- applying a force F_f that acts on the film frame, said force F_f directed against the force F_s ,
- exposing at least a portion of the bonding layer to a solvent, and at least partially dissolving the bonding layer,
- wherein said bonding layer is comprised of a plurality of different bonding layers, each of said plurality of different bonding layers selectively dissolved by a solvent having a different fluid agent.

38. Method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

- mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer;

- fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section;

- receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer;

- applying a force F_s to the carrier substrate that is transferred to the flexible film; and

- applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ,

- wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and

- wherein the at least one force F_f includes a first force F_{f1} applied to the film frame and a second force F_{f2} applied to the film frame, wherein the first force F_{f1} is applied at a first location

of the film frame and the second force F_2 is applied at a second location of the film frame, the first force F_1 being greater than the second force F_2 to strip the product substrate from the carrier substrate starting at a peripheral edge of the product substrate.

39. Method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer;

fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section;

receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer;

applying a force F_s to the carrier substrate that is transferred to the flexible film; and

applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ,

wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and

wherein the at least one force F_f includes a plurality of different forces F_{f1} , F_{f2} to F_{fn} applied to the film frame, each of said plurality of different forces F_{f1} , F_{f2} to F_{fn} applied at different locations of the film frame to strip the product substrate from the carrier substrate concentrically from the periphery of the product substrate to a center of the product substrate.

40. Method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combinations said method comprising:

mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer;

fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section;

receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer;

applying a force F_s to the carrier substrate that is transferred to the flexible film; and applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ,

wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and

wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, increases a volume of the solvent reservoir to increase capacity of the solvent reservoir to receive the solvent.

41. Method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer;

fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section;

receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer;

applying a force F_s to the carrier substrate that is transferred to the flexible film; and

applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ,

wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and

wherein the force F_s and the at least one force F_f are applied to deform at least the stripping section of the flexible film, in first and second operating modes, wherein in the first operating mode the contacting surface section of the flexible film is moved in a first direction, and in the second operating mode the contacting surface section of the flexible film is moved in a second direction that is opposite of the first direction.

42. Method for stripping a product substrate off a carrier substrate fixed to the product substrate by a bonding layer therebetween, wherein said carrier substrate connected to the product substrate by a bonding layer forms a carrier-product substrate combination, said method comprising:

mounting the product substrate of the carrier-product substrate combination to a contacting surface section of a flexible film, said contacting surface section including an adhesive layer;

fixing a film frame to an attachment surface section of the flexible film, wherein the attachment surface section is disposed at the outer periphery of the contacting surface section;

receiving the bonding layer in a solvent reservoir defined by the film frame and the flexible film, said solvent reservoir receiving a solvent for dissolving at least a portion of the bonding layer;

applying a force F_s to the carrier substrate that is transferred to the flexible film; and

applying at least one force F_f to the film frame, said at least one force F_f directed against the force F_s ,

wherein applying the force F_s and the at least one force F_f deforms at least a stripping section of the flexible film that is disposed between the contacting surface section and the attachment surface section, the flexible film being elastic at least in the stripping section, and

wherein applying the force F_s and the at least one force F_f to deform at least the stripping section of the flexible film, moves the flexible film between (i) an initial position, wherein the

contacting surface section and the attachment surface section are substantially in the same plane, (ii) a detachment position, wherein the contacting surface section is located in a plane below the attachment surface section, and (iii) a stripping position, wherein the contacting surface section is located in a plane above the attachment surface section.

Device and Method for Stripping a Product Substrate Off a Carrier Substrate

Abstract

Device for stripping a product substrate off a carrier substrate connected to the product substrate by an bonding layer by means of a film frame, a flexible film which is connected to the film frame and which has an adhesive layer for holding the product substrate in a contacting surface section of the film, the film being connected to the film frame in an attachment section of the film which surrounds the contacting surface section, as well as a solvent reservoir formed by the film frame and the film, especially of variable volume, for holding the solvent for detaching the bonding layer, and the product substrate and the bonding layer can be accommodated in the solvent reservoir, and by delivery means for delivering the solvent into the solvent reservoir and by stripping means for stripping the product substrate off the carrier substrate.

Furthermore the invention relates to a method for stripping a product substrate off a carrier substrate by forming a solvent reservoir for holding solvent for detaching the bonding layer, which is formed by a film frame and a flexible film connected to the film frame, as well as by holding the product substrate and the bonding layer in the solvent reservoir, and by delivering solvent into the solvent reservoir and by detaching the product substrate from the carrier substrate.

Figure 4